



(86) Date de dépôt PCT/PCT Filing Date: 2011/03/31
(87) Date publication PCT/PCT Publication Date: 2011/10/06
(45) Date de délivrance/Issue Date: 2018/10/09
(85) Entrée phase nationale/National Entry: 2013/09/12
(86) N° demande PCT/PCT Application No.: US 2011/030648
(87) N° publication PCT/PCT Publication No.: 2011/123591
(30) Priorité/Priority: 2010/03/31 (US61/319,289)

(51) Cl.Int./Int.Cl. *A61K 47/59* (2017.01),
A61K 47/34 (2017.01), *A61K 49/00* (2006.01),
A61K 9/10 (2006.01), *A61K 9/14* (2006.01),
C08J 3/075 (2006.01)


(72) Inventeurs/Inventors:
RANGARAMANUJAM, KANNAN, US;
KANNAN, SUJATHA, US;
ROMERO, ROBERTO, US;
NAVATH, RAGHAVENDRA, US;
MENJOGE, ANUPA, US

(73) Propriétaires/Owners:
WAYNE STATE UNIVERSITY, US;
NATIONAL INSTITUTES OF HEALTH, US

(74) Agent: BORDEN LADNER GERVAIS LLP

(54) Titre : NANOPARTICULES D'HYDROGEL DE DENDRIMERE INJECTABLES

(54) Title: INJECTABLE DENDRIMER HYDROGEL NANOPARTICLES



(57) **Abrégé/Abstract:**

The invention discloses injectable hydrogels which are in the form of crosslinked nano beads or particle in the size range 5 nm to 10µm, comprising PAMAM dendrimer with asymmetrical peripheral end groups such that one of the terminal groups is involved in formation of hydrogel and the other is involved in the conjugation of drugs or imaging agents and their methods of preparation. The said gel is formed by reaction of the PAMAM dendrimer with asymmetrical end groups with other polymer wherein the other polymer is selected from the group of linear, branched, hyperbranched or star shaped polymers with functionalized terminal groups. The PAMAM dendrimer with asymmetrical terminal groups consists of a Generation 2 and above PAMAM dendrimer with symmetrical end groups modified using the amino acids or their modified forms. The gel disclosed in the present invention is formed as small crosslinked particles in the size range 25 nm to 10µm and is suitable for injectable delivery of hydrogel to any of the body orifices, tissues by intramuscular or subcutaneous route and ocular delivery for the purpose of therapeutic treatment and imaging.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
6 October 2011 (06.10.2011)(10) International Publication Number
WO 2011/123591 A1

(51) International Patent Classification:

A61K 31/74 (2006.01) **C08G 69/00** (2006.01)

(21) International Application Number:

PCT/US2011/030648

(22) International Filing Date:

31 March 2011 (31.03.2011)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/319,289 31 March 2010 (31.03.2010) US

(71) Applicants (for all designated States except US):

WAYNE STATE UNIVERSITY [US/US]; 5057 Woodward Ave., Suite 6306, Detroit, MI 48202 (US). **NATIONAL INSTITUTES OF HEALTH** [US/US]; Office Of Technology Transfer, 6011 Executive Boulevard Suite 325, Rockville, MD 20852-3804 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **KANNAN, Rangaramanujam M.** [US/US]; 1121 Engineering Building, 5050 Anthony wayne Drive, Detroit, MI 48202 (US). **KANNAN, Sujatha** [IN/US]; 3901 Beaubein, Detroit, MI 48201 (US). **ROMERO, Roberto** [US/US]; 3901 John R, 4 Brush, Detroit, MI 48201 (US). **NAVATH, Raghavendra** [IN/US]; 1140 Easton Ave. Apt. D., Som-erser, NJ 08873 (US). **MENJOGE, Anupa** [IN/US]; 1256 Stanhope Ln.#259, Hayward, CA 94545 (US).(74) Agent: **RINALDO, Amy, E.**; Oakland Law Group PLLC, 38955 Hills Tech Drive, Farmington Hills, MI 48331 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: INJECTABLE DENDRIMER HYDROGEL NANOPARTICLES




FIG - 1

(57) **Abstract:** The invention discloses injectable hydrogels which are in the form of crosslinked nano beads or particle in the size range 5 nm to 10μm, comprising PAMAM dendrimer with asymmetrical peripheral end groups such that one of the terminal groups is involved in formation of hydrogel and the other is involved in the conjugation of drugs or imaging agents and their methods of preparation. The said gel is formed by reaction of the PAMAM dendrimer with asymmetrical end groups with other polymer wherein the other polymer is selected from the group of linear, branched, hyperbranched or star shaped polymers with functionalized terminal groups. The PAMAM dendrimer with asymmetrical terminal groups consists of a Generation 2 and above PAMAM dendrimer with symmetrical end groups modified using the amino acids or their modified forms. The gel disclosed in the present invention is formed as small crosslinked particles in the size range 25 nm to 10μm and is suitable for injectable delivery of hydrogel to any of the body orifices, tissues by intramuscular or subcutaneous route and ocular delivery for the purpose of therapeutic treatment and imaging.

WO 2011/123591 A1



Published:

— *with international search report (Art. 21(3))*

INJECTABLE DENDRIMER HYDROGEL NANOPARTICLES

BACKGROUND OF THE INVENTION

1. Field of the Invention

Generally, the present invention relates to the field of therapeutic agents. More specifically, the present invention relates to a hydrogels containing therapeutic agents.

2. Description of the Related Art

Dendrimers are a class of well-defined nanostructured macromolecules with narrow polydispersity, and a multivalent surface amenable for further modifications. Dendrimers are extensively and continually investigated for biomedical applications such as gene therapy, drug delivery and bioimaging purposes. As nanocarriers, dendrimers have the versatility to allow conjugation, complexation, and/or encapsulation of multifunctional moieties. The functional groups on the periphery of dendrimer act as highly accessible handles for drug or other functional group attachments. Since the functionalities of the drugs and ligands are diverse, there is a need to explore multiple functional group presentations at the dendrimer surface. Adding diverse functional moieties (drugs or imaging agents) onto a single dendrimer is difficult because all the peripheral groups of the symmetric dendrimer have the same reactivity. A suitable linker or spacer is required to react with the surface functionality of dendrimer, which offers the flexibility to link multiple moieties such as drugs, imaging or targeting agents.

Functionalization of dendrimers has enabled several end objectives like reduction in cytotoxicity, targeted drug delivery, formation of hydrogels, increase plasma residence time, imaging, in-vivo biodegradation, or potentially any combination of these. For example, modification of G4 dendrimers with 19, 29, 46 molecules of phenylalanine resulted in improved gene transfection ability, while modification with 64 molecules of phenylalanine resulted in poorly soluble compounds with loss in DNA complexing ability. Widespread use of cationic dendrimers in drug and gene delivery is hindered by their cytotoxicity. PEGylation and acetylation are highly successful approaches in overcoming the cytotoxicity of amine terminated dendrimers but the higher degree of amine neutralization compromises its gene slicing efficiency. The dendrimer surface modification should therefore be such that several end objectives are met without compromising on any attributes and yet having chemically reactive groups suitable for

modifications to attach drug or targeting moieties. There is a need to develop new methodologies for synthesis of functionalized dendrimers that involve fewer reaction steps, achieve high yields, are compatible with a variety of functional groups, and occur under mild reaction conditions offering clean and efficient synthesis.

5 To make dendrimers as efficient delivery vectors, apart from multivalency there is a need to have unique orthogonal end groups for chemoselective surface modifications and multi-functionalization. There are studies described in the literature for development of hetero-bifunctional dendrimers. However, the research into development of such dendrimers for biomedical applications is not extensive. The dendrimer synthesis
10 requires elaborate steps, and is expensive, thereby limiting the commercial availability to PAMAM, DAB, Phosphorous PMMH and 2,2-bis(methylol)propionic acid (bis-MPA) dendrimers. There have been few reports on the synthesis of dendrimers bearing different asymmetric groups at the periphery. It is reported that to obtain a total of 32 (16+16) and 48 (24 + 24) reactive groups on the generation 4 dendrimer several
15 sequential steps were required. Previously, melamine dendrimers with orthogonal reactive groups on surface comprising 4 hydroxyl groups, 4 hydroxyl groups masked as tert-butyldiphenylsilyl ether and 16 *tert*-Butoxycarbonyl protected amines was synthesized in eight total steps with a 55% overall yield. An efficient method to synthesize dendrimers with orthogonal peripheral groups is to grow a symmetric
20 dendrimer in bulk and then tune its periphery for the desired application. However, this process requires that the subsequent differentiation and coupling steps be minimal in number and efficient in reactivity.

Functionalization of the peripheral groups of dendrimers is an extremely fruitful and convenient strategy for developing novel functional materials for biomedical
25 applications and ways to simplify the synthesis towards achieving would be beneficial. For the application of dendrimers in drug delivery and biomedical area there is a need to develop these scaffolds with biocompatible (or generally recognized as safe materials by US FDA) materials such that their metabolites are non-toxic. Since dendrimers offer multivalency, one of the advantages is to use the functional handles to append diverse
30 functional groups such as different drug molecules and imaging agents. However, these functional groups bear different reactive groups and to append these on dendrimers

there is a need to undergo several synthetic steps for attachment of specific linkers or spacer molecule. Hence there is a need to have a dendrimer with biocompatible orthogonal groups that facilitate chemoselective attachment of these functional groups in minimal synthetic steps.

5

SUMMARY OF THE INVENTION

According to the present invention there is provided a biocompatible nanosized hydrogel particles suitable for injectable delivery of therapeutic agents for treatment of diseases or disease states and also for bioimaging purposes. These nanoparticles, including crosslinked hydrogels of the modified asymmetric PAMAM dendrimers and
10 other polymers, are biodegradable and release the therapeutic agent over an extended period of time. The release of the therapeutic agent occurs by dual mechanism, the first mechanism of release involves the degradation of the linking bond to release free therapeutic agent while the second mechanism involves the diffusion of free therapeutic agent from the gel network thus providing a sustained release pattern. The
15 biodistribution of the nanosized hydrogel can be optimized based on the modulation of the size of the particle. The nanosized hydrogels disclosed in the present invention are useful for selectively treating the neuroinflammation, inflammation, and targeted delivery of drugs intra-ocularly by injecting the particles into the eye and confining their residence into the organ of interest such as vitreous chamber.

20

These and other objects, advantages, and features of the invention will be more fully understood and appreciated by reference to the description of the current embodiment and the drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

Other advantages of the present invention will be readily appreciated as the
25 same becomes better understood by reference to the following detailed description when considered in connection with the accompanying drawings wherein:

Figure 1 is a schematic representation of bifunctional dendrimer and its post-functionalization in immediate succession.

Figure 2 shows ^1H NMR, MALDI TOF /MS spectrum and HPLC chromatogram
30 for G4-PAMAM-NH-CO-Ser(OH)-NHBoc (3)

Figure 3 shows ^1H NMR, MALDI TOF /MS spectrum and HPLC chromatogram for G4-PAMAM-NH-CO-Ser(OH)-NH₂ (4).

Figure 4 shows the MALDI TOF /MS spectra for G4-PAMAM-O-Asp(COOH)-NHBoc (16) showing mass of 25.7 kDa. On deprotection of Boc groups G4-PAMAM-O-Asp(COOH)-NH₂ (17) dendrimer showed a mass of 18.9 kDa. The conjugation of dexamethasone to (16) decreases after Boc deprotection the mass to 21.9 kDa. Further the attachment of indomethacin on (20) increases the mass to 30.1 kDa on formation of G4-PAMAM-O-Asp(CO-Dex)-NH-Ind (22).

Figure 5 shows the ^1H NMR spectra for G4-PAMAM-O-Asp(COOH)-NHBoc (16), after deprotection of *tert*-Butoxycarbonyl groups G4-PAMAM-O-Asp(COOH)-NH₂ (17), the conjugation of dexamethasone to give G4-PAMAM-O-Asp(CO-Dex)-NH₂ (20) and further the attachment of indomethacin G4-PAMAM-O-Asp(CO-Dex)-NH-Ind (22).

Figure 6 shows the HPLC chromatograms absorbance at 210 nm (arbitrary AU units) for G4-PAMAM-Asp-(COOH)-NHBoc and its postfunctionalization products; (A) G4-PAMAM-Asp-(COOH)-NHBoc showing retention time 16.5 minutes, (B) G4-PAMAM-Asp-(COOH)-NHBoc spiked with dexamethasone, the dexamethasone appears at 22.8 minutes (C) G4-PAMAM-Asp-(CO-Dex)-NH₂ showing retention time 20.5 minutes, (D) G4-PAMAM-Asp-(CO-Dex)-NH-Ind spiked with indomethacin, the unconjugated indomethacin appears at 25.8 minutes (E) G4-PAMAM-Asp-(CO-Dex)-NH-Ind appears at 22.7 minutes.

Figure 7 shows the *in-situ* gel formation by crosslinking of G4-PAMAM-Asp-(CO-Dex)-NH₂ (20) with N-hydroxy-succinimide terminated PEG (PEG-NHS) (25). The gel (3) formed by reaction of 'NH₂' groups of G4-PAMAM-Asp-(COO-Dex)-NH₂ (20) with PEG-NHS (25) (colorless), while the 'COOH' groups are used for conjugating dexamethasone by ester linkage. The hydrogel (2) physically entrapping blue dextran is seen in blue color, while the hydrogel (3) formed by linking FITC to few NH₂ groups of G4-PAMAM-Asp (CO-Dex)-NH₂ (20) while the remaining NH₂ groups crosslink by formation of amide bond on reaction with PEG-NHS (yellow). The SEM image shows the gel network (in 200 μm) for the Dexamethasone conjugated (C) and FITC conjugated (D) dendrimer G4-PAMAM-Asp-(CO-Dex)-NH₂ crosslinked with PEG-NHS.

Figure 8 shows the in-vitro hemolytic activity of new hetero-bifunctional dendrimers.

Figure 9 shows the in vitro cytotoxicity of new bifunctional dendrimer in A549 cell.

Figure 10 is a DSC thermogram of G4-NH-PDP that shows the T_g at 21.4 °C and an endotherm at 109.6 °C. The increase in T_g to 21.4 °C from -28 °C is indicative of the addition of PDP groups on to the dendrimer.

Figures 11A and B show the *in-situ* forming hydrogel by crosslinking of G4-NH-PDP with 8-arm-PEG-SH. The gel formed by reaction of 'PDP' groups of G4-NH-PDP (5) with 8-arm-PEG-SH. The hydrogel (1) physically entrapping blue dextran is seen in (2).

Figures 12A-C show the SEM images of dendrimer G4-NH-PDP crosslinked with 8-PEG-SH gel. These gels were dehydrated by lyophilization.

Figures 13A-C show hydrogel labeled with FITC to demonstrate the pore structure of the gel. By introducing the different concentration of polymer in the hydrogels, crosslinking density gradually increased by increasing the concentration of polymer. 3% hydrogel (Figure 13A), 6% hydrogel (Figure 13B) 10% hydrogel (Figure 13C) shows the cross linking net work changes on increasing polymer concentration, scale bar represents 50 μ .

Figures 14A and B show the DSC thermograms for the 3, 6 and 10 % dendrimer-PEG hydrogels. Figure 14A shows hydrogels without formulation additives (absence of glycerin, PVP and PEG600), The 8-arm PEG-SH (e) shows an endotherm at 51.7 °C, which is lowered on crosslinking with G4-NH-PDP as seen in curves (b), (c) and (d) for 3, 6 and 10% hydrogels respectively. Figure 14B shows hydrogels with formulation additives (glycerin, PVP and PEG 600). In addition to the endotherms corresponding to 8armPEG-SH (37.9 to 38.9 °C) in hydrogels, an endotherm for PEG 600 is seen between 15.6 to 14.3 °C.

Figures 15A and B shows the dendrimer-PEG hydrogels exposed to the GSH solutions at pH 4.0 are stable upto 72 hours. Figure 15A shows the intact gel after 72 hours of treatment with GSH solution at pH 4. Figure 15B shows the gel in simulated vaginal fluid with GSH

Figure 16A shows the cumulative amount of amoxicillin released with respect to time (h) across per cm^2 area for 3, 6 and 10% hydrogels and Figure 16B shows cumulative amount of amoxicillin released with respect to time. The release mechanism was found to be non-fickian for 3 and 6% hydrogels while for 10% hydrogels it approached fickian diffusion.

Figures 17A-D show intravaginal and intracervical application of *in-situ* forming Dendrimer-PEG hydrogels in the pregnant guinea pigs. The green arrows mark the presence of hydrogel on the tissue (Figure 17A) day 1: hydrogel after 5h of application, (Figure 17B) day 1: hydrogel after 12 h of application (Figure 17C) day 2: after hydrogel application (Figure 17D) day 3: after hydrogel application, where 'C' = cervix, V= vaginal cavity, U = uterus with pups. The hydrogel is retained in the cervix and vaginal cavity for 2 days and on day 3 it's seen largely in the vaginal cavity of pregnant guinea pigs.

Figures 18A-C show the Dendrimer-PEG hydrogels after intravaginal and intracervical application in pregnant guinea pigs do not cross the fetal membrane and enter into the gestational (sac) cavity. (Figure 18A) day 3: hydrogel seen on the fetal membrane of the pup positioned close to the cervix, the green arrows mark the presence of fetal membrane on the pup, the black arrows show the presence of gel outside of the fetal membrane (Figure 18B) the pup covered in fetal membrane with hydrogel on top of the fetal membrane (Figure 18C) the pup after removal of the fetal membrane showing no signs of hydrogel on the fur or inside the fetal membrane.

Figures 19A-I show the hemotoxylin and eosin stained histological sections of uterus (U), upper cervix (Ucx) and cervix (Cx) of guinea pig treated with the hydrogels for 24 hours and 72 hours (n=3 per group). The epithelial cell lining in all the tissues is intact and does not show any signs of inflammation and edema. The submucosa of hydrogel treated cervix after 24 and 72 hours is comparable to the control. None of the tissues showed any signs of epithelial sloughing, necrosis in the submucosa or massive infiltration of inflammatory cells. EP = epithelial cells, SE = subepithelium, SM = submucosa, M = muscular layer EGC = endometrial gland cells, Figure 19A shows UC= uterus control, Figure 19B shows U24 and Figure 19C shows 72 hours = hydrogel treated uterus 24 and 74 hours, Figure 19D shows UCxC = control upper cervix, Figure 19E shows UCx24 and Figure 19F shows 72 hours = hydrogel treated upper cervix 24

and 74 hours, Figure 19G shows Cx-C = cervix control, Figure 19H shows Cx24 and Figure 19I shows 72 hours = hydrogel treated cervix 24 and 74 hours (40x magnification)

Figures 20A-F show the confocal images of the cervical region of pregnant guinea pigs treated with hydrogels for 24 and 72 hours. The *in-situ* forming hydrogel comprising FITC-G4-NH-PDP crosslinked with 8-arm PEG-SH was applied to the cervicovaginal region. The hydrogel (green color) is seen on the surface of the mucosal layer (red color). The confocal images after 24 and 72 hours confirm the presence of the gel on the tissue surface. The nuclei for all cells are stained blue with DAPI. There is no sign of the degraded gel into the subepithelial or submucosal layers. EP=epithelial layer, SE= subepithelial layer, ML= mucified epithelial layer.

Figures 21A and B show the confocal images of the fetal membrane and uterus of guinea pigs treated with hydrogels for 72 hours. The *in-situ* forming hydrogel comprising FITC-G4-NH-PDP crosslinked with 8-arm PEG-SH was applied to the cervicovaginal region. The cross section of the uterus (Figure 21B) and the fetal membrane (Figure 21A) do not show presence of hydrogel or degraded hydrogel across the tissue.

Figure 22 shows an example of an NMR figure.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Generally, the present invention provides biocompatible, injectable, nanosized hydrogels. The size of the nanohydrogels can be controlled and optimized for the targeted delivery to the organs of interest.

Generation 4-PAMAM dendrimers bear approximately 64 symmetrical end groups, often requiring different spacers to conjugate various functional groups, increasing the synthetic steps. In the present invention, a simple one step synthesis is used to convert the symmetrical end groups of generation 4 polyamidoamine (G4-PAMAM) dendrimers into two reactive, distinct orthogonal and chemoselective groups. A near complete end capping of the dendrimers (87-91%) with amino acids results in hetero-bifunctional G4-PAMAM dendrimers bearing very high (≥ 110) diverse peripheral end groups (OH+NHBoc, OH+COOMe, SH+NHBoc and COOH+NHBoc). The hetero-bifunctional groups at the dendrimer periphery can be chemoselectively conjugated to

multiple functional groups such as drugs (indomethacin and dexamethasone) and/or imaging agents (dexamethasone and fluorescein isothiocyanate). These conjugations can be achieved in immediate succession without requiring any protection and/or deprotection steps or functional group conversions, eliminating the additional elaborate synthetic steps traditionally required to append specific linkers. Further, one of the two functional handles at the periphery can be used to develop *in-situ* forming hydrogels, while the other handle could be used for conjugating the drugs (eg dexamethasone).

More specifically, the present invention discloses a sustained drug releasing hydrogel wherein the drug is covalently attached to the gel only at one functional terminal of the PAMAM dendrimer while the other terminal of the PAMAM dendrimer is used for gel formation. This is achieved in immediate successions and these gels are formed as nanosized particles resulting from crosslinking of the PAMAM dendrimer and another polymer. These compounds have shown a significant improvement in the reduction of the synthetic steps and conjugation of multiple functionalities. Further, the compositions have shown increased efficacy and treatment of neuroinflammation and inflammation.

The hydrogel of the present invention can act as a nanodevice and can offer several advantages. Unlike the conventional hydrogels where the drug is passively entrapped in the hydrogel, the nanosized hydrogel of the present invention has the drug covalently attached to one functional terminal end group of PAMAM dendrimer while the other terminal end of the dendrimer forms the hydrogel. The drug release pattern from these hydrogels is governed by hydrolysis or breakdown of the chemical bond linking the drug to the hydrogel mediated by the enzymes; change in pH or by action of other body fluids. The nature of linking bond can be tailored to provide a sustained release in the region of interest. These hydrogels therefore provide better handle in providing sustained delivery of the therapeutic agents over the conventional hydrogels where the drug is released by diffusion. A high payload of the drug can be achieved on one of the terminal groups of the asymmetric PAMAM dendrimer while the other terminal end group forms hydrogels. The possibility of burst release with excessive drug release is overcome and a sustained drug release is achieved. Since the drug payload is high, the

amount of the carrier or the polymer scaffold is lower. The injectable nanosized hydrogels disclosed in the present invention are biocompatible.

The hydrogels of the present invention can be formed of crosslinked nano beads or particles. The size of the hydrogels can be controlled and optimized for targeted
5 delivery to the tissue of interest. For example, the hydrogels can be in the size range 5 nm to 10 μ m. The presence of orthogonal chemoselective groups on the PAMAM dendrimer with asymmetrical terminations enables the attachment of drugs or imaging agents or both in immediate succession eliminating the elaborate synthetic and purification steps. The conventional hydrogels are formed by crosslinking of the
10 polymers bearing symmetrical terminal groups. The hydrogels are based on PAMAM dendrimers wherein the dendrimer by itself has two terminal functionalities enabling formation of hydrogel exclusively involving only one functional group which conserving the other for attachment of drugs and imaging agents is not known. The gel is formed by reaction of the PAMAM dendrimer with asymmetrical end groups with other
15 polymers. Examples of such polymers include, but are not limited to, linear, branched, hyperbranched or star shaped polymers with functionalized terminal groups. The PAMAM dendrimer with asymmetrical terminal groups consists of a Generation 2 and the PAMAM dendrimer with symmetrical end groups modified using the amino acids or their modified forms. The gel disclosed in the present invention is formed as small
20 crosslinked particles in the size range 25 nm to 10 μ m and is suitable for injectable delivery of hydrogel to any of the body orifices, tissues by intramuscular or subcutaneous route and ocular delivery for the purpose of therapeutic treatment and imaging.

In another embodiment of the present invention, the hydrogel can be formed by
25 chemical modification of symmetric PAMAM dendrimer with amino acids. For example, the said gel can be in the form of particles in the size range 5 nm to 10 μ m (wherein nanoparticles can be in the size range of 5nm to 900nm, preferably from 50nm to 500 nm.), and the other polymer involved in crosslinking is a linear, branched or star shape polymer or a dendrimer.

30 Specifically, the nanoparticles of the present invention is obtained by crosslinking with other polymer is characterized by presence of disulfide crosslinks, thioester and

amide linkages. The PAMAM dendrimer can also be a poly(amidoamine) dendrimer of generation 2 and above wherein the surface has an asymmetrical end or peripheral groups obtained by modification of the symmetrical end groups by reaction with amino acids. Alternatively, the PAMAM dendrimer can include a generation 4
 5 poly(amidoamine) dendrimer surfacized or modified with amino acids to yield all symmetrical terminal end groups into asymmetrical end or peripheral groups.

The PAMAM dendrimer of the present invention can also include amine, carboxylic acid, or hydroxyl terminations prior to modification with amino acids. Wherein, the amino acids can include, but are not limited to, serine, aspartic acid,
 10 cysteine, glutamic acid, threonine, tyrosine or their protected forms such as tert-butylcarbonyl-serine-hydroxysuccinimide (Boc-Ser-NHS), tert-butylcarbonyl-aspartic acid (Boc-Asp-OH), tert-butylcarbonyl-glutamic acid (Boc-Glu-OH), fluorenylmethoxycarbonyl-serine (Fmoc-Ser), fluorenylmethoxycarbonyl-aspartic acid (Fmoc-Asp-OH), fluorenylmethoxycarbonyl-glutamic acid (Fmoc-Glu-OH), tert-
 15 butylcarbonyl-cysteine-hydroxysuccinimide (Boc-Cys-NHS), serine-methylester (H-ser-OMe), cysteine-methylester (H-Cys-OMe), aspartic acid-methylester (H-Asp-OMe), glutamic acid-methyl ester (H-Glu-OMe), tert-butylcarbonyl-threonine-hydroxysuccinimide (Boc-Thr-NHS), threonine-methylester (H-Thr-OMe), fluorenylmethoxycarbonyl-threonine (Fmoc-Thr), tert-butylcarbonyl-tyrosine-
 20 hydroxysuccinimide (Boc-Tyr-NHS), tert-butylcarbonyl-tyrosine (Boc-Tyr-OH), Tyrosine-methylester (H-Tyr-OMe), cysteine-dithiopyridine (Cys-S-STP), tert-butylcarbonyl-cysteine-dithiopyridine (Boc-Cys-S-STP).

The PAMAM dendrimer of the present invention can be formed wherein one of the end groups is involved in formation of hydrogel while the other end group is
 25 available for conjugation of drug or an imaging agent. Examples of such drugs and imaging agents can include, but are not limited to, G4-PAMAM-NH-CO-Ser(OH)-NHBoc, G4-PAMAM-NH-CO-Ser(OH)-NH₂, G4-PAMAM-NH-CO-Cys(SH)-NHBoc, G4-PAMAM-NH-CO-Cys(SH)-NH₂, G3.5-PAMAM-CO-NH-Ser(OH)-COOMe, G3.5-PAMAM-CO-NH-Ser(OH)-COOH, G4-PAMAM-O-CO-Cys(SH)-NHBoc, G4-PAMAM-O-CO-
 30 Cys(SH)-NH₂, G4-PAMAM-O-CO-Asp(COOH)-NHBoc, G4-PAMAM-O-CO-Asp(COOH)-NH₂, G4-PAMAM-O-CO-Cys(S-STP)-NHBoc and G4-PAMAM-O-CO-Cys(S-STP)-NH₂.

The PAMAM dendrimers of the present invention can also be reacted with the amino acid such that it yields two distinct orthogonal chemoselective asymmetrical end groups on the surface suitable for post-functionalization in immediate succession such as conjugation for drugs and / or imaging agents and hydrogel formation.

5 The hydrogel of the present invention is formed by the direct crosslinking of the asymmetric PAMAM dendrimer with other polymer involving a chemical reaction, or by physical crosslinking and photopolymerization reactions. The formed hydrogel is degradable in nature wherein the crosslinks are hydrolyzed over a period of time in response to the change in pH of environment, presence of enzymes and body fluids.
10 Additionally, the rate of degradation can be modulated by the nature of the crosslinks.

The drug contained within the hydrogel can be released over an extended period of time in a dual manner, wherein the first mechanism of release involves the degradation of the linking bond to release free drug while the second mechanism involves the diffusion of free drug from the gel network. Examples of such drugs include,
15 but are not limited to, macrolide antibiotics, such as, erythromycin, azithromycin, rapamycin and clarithromycin; tetracyclines, such as, minocycline, doxycycline, fluroquinolones, such as, ciprofloxacin, enrofloxacin, ofloxacin, gatifloxacin, levofloxacin and norfloxacin; cephalosporins, such as, cefuroxime, cefaclor, cephalexin, cephadroxil and cefpodoxime proxetil; nonsteroidal, anti-inflammatory and analgesic drugs , such
20 as, ibuprofen, aspirin, acetaminophen and diclofenac sodium and corticosteroids such as fluocinolone acetonide and methylprednisolone, antibodies such as ranibizumab, vitamins, peptides, growth factors, siRNAs, microRNAs, resolvins, neurostimulants and neuroprotectants or a pharmaceutically acceptable salts thereof.

The imaging agent for use with the present invention can include, but is not
25 limited to, fluorescent dyes, for example, fluorescein isothiocyanate, Carboxyfluorescein, fluorescein hydroxysuccinimide, tetramethyl rhodamine isothiocyanate, alexa fluor dyes bearing hydroxylamine, hydrazide, cadaverine, aldehyde, ketone, carboxylic, amine and thiol reactive groups, cyanine dye, Texas red radiolabelled dyes selected from the group of ^{14}C , ^3H , ^{64}Cu , magnetic resonance imaging agents ^{125}I , ^{99}Tc , ^{111}In , gadolinium, and
30 gadolinium tetra-azacyclododecanetetraacetic acid (Gd-DOTA).

The crosslinking polymer for use in the present invention is a functionalized polyethylene glycol (PEG) polymer in the size range of 5 kDa to 80kDa, preferably 20-40kDa. The functionalized PEG polymer can be either a linear or a branched PEG having a molecular weight of 20-40kDa and bearing symmetrical terminations such as,
 5 amine, thiol, maleimide, carbonates, carbamates, N-hydroxy-succinimide, dithiopyridine, methacrylate, methoxy, hydrazine, azide, acid, alcohol, aldehyde, allyl, vinyl, epoxy, isothiocyanate and isocyanate.

The hydrogel occurs due to the interaction between the asymmetric PAMAM dendrimer and the other polymer directly and alternately by use of suitable spacer which
 10 crosslinks the dendrimer and other polymer wherein the spacer is selected from the group consisting of bifunctional molecules in the size range 1-10 kDa wherein the bifunctional molecules are maleimide-poly(ethyleneglycol)-maleimide, Succinimidyl-carboxyl-methyl ester- poly(ethyleneglycol)-succinimidyl-carboxyl-methyl ester, acrylate-poly(ethyleneglycol)-acrylate, ortho-pyridyldisulfide-poly(ethyleneglycol)-ortho-
 15 pyridyldisulfide, thiol- poly(ethyleneglycol)-thiol, nitrophenyl carbonate-poly(ethyleneglycol)-nitrophenyl carbonate, isocyanate-poly(ethyleneglycol)-isocyanate, 1,6-hexane-bis-vinylsulfone and any other polymer which bears these functional terminations.

Examples of the nanoparticles include, but are not limited to, G4-PAMAM-NH-
 20 CO-Cys(S-TP) cross linked with 8-arm-poly(ethyleneglycol) with thiol terminations, G4-PAMAM-NH- pyridyldithio-propionate cross linked 8-arm-poly(ethyleneglycol) with thiol terminations, FITC-G4-PAMAM-NH-pyridyldithio-propionate crosslinked with 8-arm-poly(ethyleneglycol) with thiol terminations, G4-PAMAM-O-Cys(SH)-NH-FITC and 8-arm-poly(ethyleneglycol) with thiol terminations, FITC-G4-NH-Maleimide cross linked
 25 with 8-arm-poly(ethyleneglycol) with thiol terminations, G4-PAMAM-O-CO-Cys(S-Tp)-NH₂ cross linked with methoxy-poly(ethyleneglycol) with thiol termination (Meo-PEG-SH), G4-PAMAM-O-CO-Cys(SH)-NH₂ cross linked with pyridyldithio-propionate-poly(ethyleneglycol)-pyridyldithio-propionate. A high payload of the drug can be achieved on one of the terminal groups of the asymmetric PAMAM dendrimer while the
 30 other terminal end group forms hydrogels. This type of hydrogel where the drug is covalently bond to the hydrogel offers a sustained release of the drug over the extended

period of times as compared the conventional hydrogels preparations where the drug is physically entrapped and diffuses out of the hydrogel.

The drug release pattern from these hydrogels is governed by hydrolysis or breakdown of the chemical bond linking the drug to the hydrogel mediated by the enzymes, change in pH or by action of other body fluids. The nature of linking bond can be tailored to provide a sustained release in the region of interest. These hydrogels therefore provide better sustained delivery of the therapeutic agents over the conventional hydrogels where the drug is released by diffusion.

A library of dendrimers having hetero-bifunctional groups at periphery, amenable for further modifications is disclosed (Table 1). The present invention provides a robust, simple synthetic approach to attain near complete surface modification with amino acids to yield hetero-bifunctional end terminations on a biocompatible dendrimer scaffold (Figure 1). Past reports on synthesis of bifunctional dendrimers involve multiple steps. A simple one pot synthesis to achieve orthogonal and chemoselective end groups by complete end capping of the G4 PAMAM dendrimers with amino acids is shown in Schemes 1-5, 7. The present invention shows that ≥ 110 hetero-bifunctional end groups can be achieved on a generation four (G4) dendrimer (Figure 1) without going to next generation (G5) dendrimers. This is a significant since it is well known that dendrimers exhibit generation dependant cytotoxicity. PEGylation of G5 and G6 PAMAM-NH₂ dendrimers significantly reduced its hemolytic activity but paradoxically compromised its transfection ability. The choice of the materials to design these hetero-bifunctional dendrimers was based on developing biocompatible dendrimer scaffolds for drug delivery applications, and also retaining the reactivity of terminal groups for drug conjugation.

One of the advantages of the present system, having multiple diverse functional handles on periphery groups is the ease of conjugating different drugs, along with imaging agents and/or targeting ligands without the need of additional synthetic steps to attach specific spacer or linker molecules. The feasibility of the concept, and the chemoselective and orthogonal nature of these new hetero-bifunctional dendrimers was demonstrated by conjugation of 1) two drugs viz. dexamethasone and indomethacin and 2) indomethacin and imaging agent (FITC) on the aspartic acid surface-modified

PAMAM dendrimer. Thus two different moieties were added in immediate succession without any deprotection steps or functional group conversions owing to the orthogonal peripheral groups. Additionally, of the two diverse functional handles on the hetero-bifunctional dendrimers, one of the functional handles was selectively used for *in-situ* hydrogel formation, while the second functional handle was used for conjugating drug and or imaging agent.

Dendrimers have emerged as multifunctional carriers for targeted drug delivery and diagnostic agents. Additionally, dendrimers have become integral in improving the functional versatility at the surface for carrying multiple conjugation reactions is becoming vital. The compositions disclosed in present invention performs several functions like targeting, localization at diseased site, releasing the drug, imaging purpose and therefore the composition in itself acts as a nanodevice.

Hydrogels can be used for many different applications such as molecularly engineered scaffolds for controlled drug release, cellular delivery, tissue engineering and as wound dressings due to the highly hydrated and three dimensional properties which are similar to the native extracellular matrix (ECM). They have attracted a great deal of attention as a matrix for the controlled delivery of biologically active substances. The suitability of hydrogels for the pharmaceutical applications is mainly determined by their mechanical properties, drug loading and controlled drug release capability. *In-situ* forming gels have been investigated for a varied applications such as oral, nasal, ocular, injectable, vaginal and rectal. Thermosensitive gels are commonly investigated for the vaginal delivery of therapeutic agents as they gel in response to the body temperature. Thermosensitive vaginal gels for delivery of cotrimazole were formulated using Pluronic F127. Polycarbophil hydrogels were investigated for intravaginal delivery of granulocyte-macrophage colony-stimulating factor (GM-CSF) for treatment of human papillomavirus (HPV)-associated genital (pre)neoplastic lesions.

The intravaginal route of drug administration can be used as an effective means for local delivery of antibacterials, antifungals, antiprotozoals and antivirals agents. The use of topical microbicides is common in pregnant women to treat yeast and bacterial infections. Bacterial vaginosis (BV) is found in 15-20% of pregnant women and it is an ascending genital tract infection of chorioamnion and amniotic fluid. Intrauterine

infection during pregnancy is often responsible for disease causing spontaneous preterm birth and the infection which is associated with the microorganisms ascending from vagina and cervix is known to affect the fetal membranes and the cervical mucosa and endometrium. Local drug delivery to cervical tissues is preferred. To treat BV in pregnant women antibiotics are administered intra-vaginally and the intravaginal route is preferred to attain high local drug concentration in the vagina, which cannot be achieved by oral administrations. One major problem associated with intravaginal and intrauterine drug delivery is limited contact time of administered dosage form with the mucosa due to the physiological conditions imposed by the protective mechanisms of the cervix and vagina. This reduces the therapeutic efficacy and necessitates frequent dosing. Hydrogels are better tolerated than other conventional dosage forms and thus provide a better treatment option.

Hydrogels are preferred drug delivery vehicles in pharmaceutical industry especially for the ocular delivery of drugs. Dendrimer based imaging agents are in the process of gaining approvals for human use. Dendrimer based intravaginal gels can also be used as topical microbicides. Polylysine dendrimer SPL7013 exhibited antimicrobial activity against herpes simplex virus and its formulation development into a prototype acidified carbopol gel for intravaginal delivery was evaluated in animal models. Human clinical trials (Phase I and II) were conducted to determine the retention, duration of activity, safety and tolerability of a gel containing SPL7013 applied intravaginally to young non-pregnant women and the gel was found to be safe and well tolerated. Apart from SPL7013, the amine terminated PAMAM dendrimers are found to exhibit antibacterial activity towards gram-ve bacteria. PAMAM dendrimer with hydroxyl terminations was found to effectively inhibit intrauterine *Escherichia coli* (*E. Coli*) infections in guinea pigs. These dendrimers have also been used as carriers for the antimicrobial agents (e.g. triazine antibiotics). Quinolone drugs encapsulated in PAMAM dendrimers are highly active when used as topical microbicidal agents. The PAMAM dendrimer based silver complexes and nanocomposites have been shown to have increased antibacterial activity towards the *S. aureus*, *P. aeruginosa* and *E. coli*. Further, dendrimers are also extensively evaluated in several gel formulations. Many

polymers can be used as topical microbicides or as a component of the topical microbicide formulations to be applied on the vagina or rectal mucosa.

The hydrogels of the present invention can be used to treat several macular degeneration related diseased conditions. The hydrogels can also be used in treating neuro-inflammation and inflammation in the eye by intraocular delivery. The hydrogels also have site-specific localization of the dendrimers based on their size and can therefore effectively deliver drugs to the diseased site. Further, these nanodevices can be used for the diagnostic and imaging purposes.

The above discussion provides a factual basis for the methods and uses described herein. The methods used with and the utility of the present invention can be shown by the following non-limiting examples.

EXAMPLES

Example 1.

Synthesis of asymmetrical hetero-bifunctional G4 PAMAM dendrimers

15 Synthesis of G4-PAMAM-NH-CO-Ser(OH)-NHBoc (3)

To a stirred solution of G4-PAMAM-NH₂ (1) (500 mg, 0.035 mol) and Boc-Ser-NHS (2) (1360 mg, 4.50 mol) in DMSO/DMF (4:1, 25 mL) followed by addition of DIEA (775 µl, 4.50 mol). The reaction was allowed to continue for 24 hours at room temperature (r.t.). The crude product was purified by dialysis against DMSO (3 times for 20 36 hours), and after dialysis the solvent was removed under lyophilization to get pure compound in 75% yield (646 mg, 0.026 mol). The chemical structure of G4-PAMAM-NH-CO-Ser(OH)-NH₂ (3) was confirmed by ¹H-NMR and MALDI-MS spectra. ¹H-NMR (DMSO-d₆, 400 MHz), 1.38 (s, 9H, Boc), 2.10-2.22 (br.s, OH), 3.22-3.38 (m, 1H, CH₂), 4.50-4.58(m, 1H, CH₂) 4.80-4.90 (m, 1H, CH) 6.50-6.60 (m, 1H, NH amide), 7.78-25 7.97(br.d, NH amide interior dendrimer amide), MALDI-MS : 24501 Da

Synthesis of G4-PAMAM-NH-CO-Ser(OH)-NH₂ (4)

Boc (*tert*-Butoxycarbonyl) deprotection was carried out by adding G4-PAMAM-NH-CO-Ser (OH)-NHBoc (3) (500 mg, 0.020 mol) in TFA/DCM (50:50 % v/v, 10 mL) for 15 minutes. Post de-protection, the solution was neutralized pH = 7.0 using 1N NaOH solution. The compound was dialyzed overnight using water as solvent and lyophilized to yield G4-PAMAM-NH-COSer(OH)-NH₂ with NH₂ and OH terminations. The compound 30

(4) was obtained by lyophilization in 89% yield (339 mg, 0.018 mol). ¹H-NMR and MALDI-MS spectra. ¹H-NMR (DMSO-d₆, 400 MHz), δ, 1.0-1.19 (m, 2H, NH₂), 1.80-1.98 (br. s, 2H, OH), 4.21-4.26(s, 1H), 8.0-8.15 (br. d from amide NH), 8.30-8.6 (br.d, amide NH), MALDI-MS : 18747 Da.

5 Synthesis of G4-PAMAM-NH-CO-Cys (SH)-NHBoc (6)

To a stirred solution of G4-PAMAM-NH₂ (1) (500 mg, 0.035 mol) and Boc-Cys-NHS (5) (1432 mg, 4.50 mol) in DMSO/ DMF (4:1, 25 mL), DIEA (775 μl, 4.50 mol). The reaction was continued for 24 hours at r.t. The reaction mixture was purified on dialysis with DMSO (36 hours) to remove by-products and the excess of reactants, and after
10 dialysis the solvent was removed under lyophilization to get pure compound (6) in 77% yield (671 mg, 0.027 mol). ¹H-NMR (DMSO-d₆, 400 MHz), δ 1.35 (s, 9H, Boc) 2.10-2.20(br.s, SH), 3.25-3.40 (m, 2H, CH₂), 3.95-4.20(m, 1H, CH), 7.80-8.20 (br.d, 1H, dendrimer interior amide), 8.22-8.45(br.s, 1H, amide) MALDI-MS : 25807 Da

Synthesis of G4-PAMAM-NH-CO-Cys (SH)-NH₂ (7)

15 Boc (*tert*-Butoxycarbonyl) deprotection was carried out by adding G4-PAMAM-NH-CO-Cys (SH)-NHBoc (6) (500 mg, 0.019 mol) in TFA/DCM (50:50 % v/v, 10 mL) for 15 minutes. Post de-protection, the solution was neutralized pH = 7.0 using 1N NaOH solution. The compound was dialyzed overnight using water as solvent and lyophilized to yield G4-PAMAM-NH-CO-Cys (SH)-NH₂ with NH₂ and SH terminations. The
20 compound (7) was obtained by lyophilization in 88% yield (326 mg, 0.017 mol). ¹H-NMR (DMSO-d₆, 400 MHz), δ 1.0-1.23 (m, NH₂), 1.78-2.00 (br.s, 2H, OH) 3.60-3.75 (m, 1H – CH- for Cysteine) 7.97-8.10 (br. s, amide NH from Cysteine), 9.80-10.10 (br. m, amide NH from dendrimer interior amide). MALDI-MS: 19365 Da

Synthesis of G3.5-PAMAM-CO-NH-Ser-OMe (10)

25 To a stirred solution of G3.5-PAMAM-COOH (6) (100 mg, 0.0086 mol) and H-Ser-OMe (9) (132 mg, 1.11 mol) in water (4 ml) was added DMSO/ DMF (4:1, 12 mL), DMAP (136 mg, 1.11 mol) and the reaction was stirred for 5 minutes followed by addition of EDC (213 mg, 1.11 mol) at once. The reaction was continued for 24 hours at r.t. The reaction mixture was purified by dialysis with DMSO (36 hours) to remove by-
30 products and the excess of reactants, and after dialysis the solvent was removed under lyophilization to get pure compound (10) in 78 % yield (116 mg, 0.0067 mol). ¹H-NMR

(DMSO- d_6 , 400 MHz) , δ 3.60 (s, 3H, COOMe), 6.62-3.75 (m, 2H, CH₂), 4.30-4.58 (m, 1H, CH), 7.77-7.95 (br.d, NH), 8.37-8.41(s, 1H, amide), MALDI-MS: 17209 Da

Synthesis of G3.5-PAMAM-CO-NH-Ser-OH (11)

Hydrolysis of methyl ester was carried out by adding G3.5-PAMAM-CO-Ser (OH)-OMe (10) (100 mg, 0.005 mol) with LiOH (5 mg, 2.26 mol) in THF/H₂O (9:1 10 mL) for 5 hours after completion of reaction, the compound was dialyzed overnight using water as solvent and lyophilized to yield G3.5-PAMAM-CO-NH-Ser-OH (11) with COOH and OH terminations. The compound (11) was obtained by lyophilization in 88% yield (81 mg, 0.0005 mol) ¹H-NMR (DMSO- d_6 , 400 MHz, δ in ppm) 1.40-1.50 (m, 2H, NH₂), 1.92-2.05 (br. s, 1H, OH), 3.33-3.42 (br.s, 1H, -CH-, Serine), 8.15-8.40 (br. d, amide NH), 8.75-8.90 (br. s, amide NH), ¹³C-NMR (DMSO- d_6 , 400 MHz), 14.97, 26.45, 33.94, 36.80, 37.56, 45.12, 50.29, 52.87, 56.02, 155.60, 170.10, 172.91. FTIR spectrum shows absorptions at 1720, 2950, 3550 cm⁻¹ assigned for C=O, C-H, O-H stretch of serine, MALDI-MS: 15959 Da.

Synthesis of G4-PAMAM-O-CO-Cys(SH)-NHBoc (13)

To a stirred solution of Boc-Cys-OH (5) (1487 mg, 6.72 mol) and G4-PAMAM-OH (12) (500 mg, 0.035 mol) in DMSO/DMF (3:1) was added DMAP (366 mg, 3.0 mol), EDC (899 mg, 4.51 mol) and the reaction was allowed to proceed overnight for 18 hours. The product so obtained was purified by dialysis using spectrapor dialysis membranes in DMSO as a solvent, to remove the by-products and the excess of reactants. After dialysis the solvent was removed under lyophilization to get pure compound (13) in 80% yield (732 mg, 0.144 mol). ¹H-NMR (DMSO- d_6 , 400 MHz), δ , 1.25 (br. s, 1H from Cysteine SH), 1.35 (br. s, 9H, *tert*-Butoxycarbonyl from Cysteine), 2.10-2.25 (br.s, 1H, -SH from Cysteine), 4.55-4.75 (br.d -CH- from Cysteine), 7.80-8.10 (br. d, NH from dendrimer interior amide), 8.20-8.30 (br. s, NH from Cysteine amide), ¹³C-NMR (DMSO- d_6 , 100 MHz), 28.59, 28.78, 33.86, 37.51, 38.02, 42.12, 50.23, 52.80, 54.19, 56.94, 60.55, 66.50, 79.76, 108.10, 143.20, 155.90, 156.69, 169.61, 172.01, 172.32, 172.56, MALDI-TOF/MS: 25068 Da.

Synthesis of G4-PAMAM-O-CO-Cys(SH)-NH₂ (14)

Boc (*tert*-Butoxycarbonyl) deprotection was carried out by adding G4-PAMAM-O-CO-Cys (SH)-NHBoc (13) (500 mg, 0.019 mol) in TFA/DCM (50:50 % v/v, 10 mL) for 5

minutes. Post de-protection, the solution was neutralized pH = 7.0 using 1N NaOH solution. The compound was dialyzed overnight using water as solvent and lyophilized to yield G4-O-Cys(SH)-NH₂ with NH₂ and SH terminations. The compound (14) was obtained by lyophilization in 87% yield (334 mg, 0.017 mol). ¹H-NMR (DMSO-d₆, 400 MHz), δ, 2.12-2.24 (m, 2H, -CH₂-, Cysteine), 4.70-4.78 (m, 1H, -CH-, Cysteine), 7.76-7.89 (br. d, NH from dendrimer interior amide), 7.91 (br. s, NH from Cysteine amide). MALDI-MS: 19262 Da.

Synthesis of G4-PAMAM-O-CO-Asp(COOH)-NHBoc (16)

To a stirred solution of BOC-Asp-OH (15) (2500 mg, 10.7 mol) was added G4-PAMAM-OH (12) (1000 mg, 0.070 mol) in DMSO/DMF (3:1) and DMAP (729.9mg, 5.975 mol), EDC (1783mg, 8.95 mol) and PyBOP (1993 mg, 3.83 mol) and the reaction was allowed to proceed overnight for 18 hours. The product was purified by dialysis using spectrapor dialysis membranes in DMSO as solvent to remove by-products and the excess of reactants, and after dialysis the solvent was removed under lyophilization to get pure compound (16) in 80 % yield (1503 mg, 0.058 mol). ¹H-NMR (DMSO-d₆, 400 MHz), δ, 1.30 (s, 9H), 4.28-4.38 (br. s, 1H), 7.75-7.90 (br.s, amide NH), 7.92-8.10 (br.d, amide NH). ¹³C-NMR (DMSO-d₆, 100MHz), 28.77, 33.46, 37.39, 38.13, 50.04, 50.76, 52.79, 63.76, 79.08, 79.12, 95.10, 155.91, 170.66, 171.82, 172.23. MALDI-MS: 25740 Da.

Synthesis of G4-PAMAM-O-CO-Asp-(COOH)-NH₂ (17)

Boc (*tert*-Butoxycarbonyl) deprotection was carried out by adding G4-PAMAM-O-CO-Asp-Boc (16) (1000 mg) in TFA/DCM (50:50 % v/v) for 5 minutes. Post de-protection, the solution was neutralized using 1N NaOH solution. The compound was dialyzed overnight using water as solvent and lyophilized to yield G4-O-Asp-OH with COOH and NH₂ terminations. The compound (17) was obtained by lyophilization in 90% yield (627 mg, 0.033 mol). ¹H-NMR (DMSO-d₆, 400 MHz, δ in ppm) 4.22-4.35 (br.s, 1H), 7.96-8.10 (br. s, amide NH) 8.10-30 (br.d, amide, NH). MALDI-MS: 18990 Da.

Synthesis of G4-PAMAM-O-CO-Asp-(CO-Dex)-NH₂ (20)

To a stirred solution of G4-PAMAM-O-CO-Asp-(COOH)-NHBoc (16) (200 mg, 0.0105 mol) in a DMSO/DMF(3:1, 20 mL) was added EDC (506 mg, 2.64 mol), DMAP (160 mg, 1.31 mol) and dexamethasone (15) (520 mg, 1.32 mol) and the reaction was

allowed to proceed at room temperature for 12 hours. After completion of the reaction, crude product was purified by dialysis using spectrapor dialysis membranes in DMSO (3 times for 36 hours) to remove by-products and the excess of reactants, and after dialysis the solvent was removed under lyophilization to get (20) pure compound in 82% yield (190 mg, 0.0086 mmol). Boc (*tert*-Butoxycarbonyl) deprotection was carried out by adding G4-PAMAM-O-CO-Asp(CO-Dex)-NHBoc (16) (1000 mg) in TFA/DCM (50:50 % v/v) for 5 minutes. Post de-protection, the solution was neutralized using 1N NaOH solution. The compound was dialyzed overnight using water as solvent and lyophilized to yield G4-PAMAM-O-CO-Asp(CO-Dex)-NH₂. The compound (20) was obtained by lyophilization in 90% yield. ¹H-NMR (DMSO-d₆, 400MHz, δ in ppm), 0.75 (s, 3H), 0.82(s, 3H), 1.0-1.10(m, 2H), 1.280-1.36(d, 2H), 1.38-1.41(d, 2H), 1.45(s, 3H) 4.45-4.50(d, 1H), 4.92(s,1H), 5.24(s, 1H), 6.01(s, 1H), 6.23(d, 1H), 7.30(d, 1H). ¹³C-NMR (DMSO-d₆, 100MHz) 15.98, 17.33, 23.55,23.61, 27.94, 30.95, 32.68, 33.75, 34.21, 34.41, 35.55, 36.60, 42.10, 43.95, 48.12, 48.75, 50.15, 52.70, 60.56, 66.94, 71.18, 71.55, 90.84, 94.71, 101.06, 102.80, 124.80, 129.67, 153.53, 167.80, 186.0. MALDI-TOF/MS: 21981 Da.

Synthesis of G4-PAMAM-O-Asp (CO-Dex)-Ind (22)

To a stirred solution of indomethacin (21) (249 mg, 0.69 mol) in a DMSO/DMF (3:1, 20 mL) was added EDC (133 mg, 0.69 mol), DMAP (85 mg, 0.69 mol). The reaction mass was stirred for 15 minutes and G4-PAMAM-O-CO-Asp-(CO-Dex)-NH₂ (20) (80 mg, 0.0036 mol) was added to it. Reaction was continued at room temperature for 15 hours. After completion of the reaction, crude product was purified by dialysis using spectrapor dialysis membranes in DMSO (36 hours) to remove by-products and the excess of reactants. After dialysis the solvent was removed under lyophilization to get G4-PAMAM-O-Asp(CO-Dex)-Ind (22) pure compound in 78% yield. Apart from dexamethasone protons listed for (20), the ¹H-NMR of compound (22) shows appearance of protons corresponding to indomethacin. ¹H-NMR (DMSO-d₆, 400MHz), δ , 2.10-2.30 (m, 3H, CH₃), 3.62-3.80 (m, 5H, -OCH₃, -CO-CH₂-), 6.60-7.9 (m, 2H, Ar), 6.83-7.04 (m, 2H, Ar), 7.60-7.70(m, 3H, Ar).

Synthesis of G4-PAMAM-O-CO-Asp(CO-Dex)-NH-FITC (24)

To a stirred solution of G4-PAMAM-O-CO-Asp-(CO-Dex)-NH₂ (20) (100 mg, 0.0038 mol) in a DMSO (10 mL) was added FITC (23) (17.6 mg, 0.045 mol). The reaction mixture was stirred at room temperature for 12 hours in dark. After completion of the reaction, crude product was purified by dialysis in dark using spectrapor dialysis membranes in DMSO (36 hours) to remove by-products and the excess of reactants, and after dialysis the solvent was removed under lyophilization to get (24) pure compound in 85% yield. Apart from dexamethasone protons listed for (23), the ¹H-NMR of compound (24) shows appearance of protons corresponding to FITC. ¹H-NMR (DMSO-d₆, 400MHz), δ, 6.57-6.62 (d, 6H, Ar), 6.63-6.70 (s, 3H Ar)..

10 Synthesis of Boc-Cys (S-TP)-OH (27)

Boc-Cys(S-TP)-OH (27) was prepared from the reaction of 2, 2'-dithiodipyridine (7.96 g, 36 mol) and Boc-Cys-OH (4 g, 18 mol) in a mixture of methanol and water (1:1, 50 mL) and stirred for 24 hours at room temperature. Upon completion of the reaction (monitored by TLC), methanol was removed in vacuo and the residue was recrystallized with acetone and petroleum ether to give the pure product as a white solid in 70% yield (4.19 g, 0.012 mol). ¹H-NMR (DMSO-d₆, 400 MHz), δ in ppm), 1.40 (s, 9H, *tert*-Butoxycarbonyl), 2.49 (solvent DMSO-d₆) 3.0-3.20 (m, 2H, -CH₂-), 3.33 (H₂O peak in DMSO-d₆), 4.10-4.20 (m, 1H, -CH-), 7.25-7.30 (m, 1H, Ar), 7.35-7.40 (m, 1H, Ar), 7.78-7.88 (m, 2H, NH amide, and Ar), 8.42-8.52 (m, 1H, Ar), 12.88 (s, 1H, COOH). ¹³C-NMR (DMSO-d₆, 100 MHz), δ, 28.83, 53.42, 79.03, 94.69, 119.96, 121.95, 138.48, 150.29, 172.86.

20 Synthesis of G4-PAMAM-O-CO-Cys(S-TP)-NHBoc (28)

To a stirred solution of Boc-Cys (S-TP)-OH (27) (1484 mg, 4.48 mol) and G4-PAMAM-OH (12) (500 mg, 0.036 mol) in DMSO/DMF (3:1) was added DMAP (273 mg, 2.23 mol), EDC (856 mg, 4.48 mol)) and the reaction was allowed to proceed overnight for 18 hours. The product was purified by dialysis using spectrapor dialysis membranes in DMSO as solvent to remove by-products and the excess of reactants, and after dialysis the solvent was removed under lyophilization to get pure compound (28) in 78 % yield (764 mg, 0.028 mol). ¹H-NMR (DMSO-d₆, 400 MHz, δ in ppm) 1.38 (s, 9H, from Cysteine *tert*-Butoxycarbonyl), 4.0-4.10 (m, 2H, -CH₂-, from Cysteine), 4.60-4.70 (m, 1H,

-CH-, from Cysteine), 6.70-7.77 (m, 1H, Ar), 7.0-7.18 (br.d, 1H, NH amide), 7.25-7.35 (m, 1H, Ar), 7.38-7.45 (m, 1H, Ar), 7.60-7.68 (m, 1H, Ar), 8.15-8.24 (m, 1H, amide NH).

Synthesis of G4-PAMAM-O-CO-Cys(S-TP)-NH₂ (29)

Tert-Butoxycarbonyl deprotection was carried out by adding G4-PAMAM-O-CO-Cys(S-TP)-NHBoc (28) (500 mg, 0.018 mol) in TFA/DCM (50:50 % v/v, 10 mL) for 5 minutes. Post de-protection, the solution was neutralized using 1N NaOH solution and pH of solution was monitored to obtain pH 7. The compound was dialyzed overnight using water as solvent. After dialysis the solvent was lyophilized to get compound (29) in 50% yield (238 mg, 0.0093 mol). ¹H-NMR (DMSO-d₆, 400 MHz, δ in ppm) 1.82-1.97 (m, 2H, -CH₂-, from Cysteine), 4.62-4.70 (m, 1H -CH-, from Cysteine), 7.60-7.64 (d, 1H, Ar), 7.66-7.75 (m, 1H, Ar), 7.77-7.84 (m, 1H, Ar), 7.89-7.96 (m, 1H, NH amide), 8.19-8.25 (m, 1H, Ar), 8.40-8.52 (m, 1H, NH amide).

To achieve hetero-bifunctional G4-PAMAM dendrimer with high density of amine and hydroxyl functional groups at the periphery of (3), the symmetrical terminal 'amine' groups of G4 PAMAM dendrimer (1) were reacted with acid terminal of Boc-Ser-NHS (2). This was a straightforward coupling reaction which converted the symmetrical peripheral amines (~64 theoretically) of G4-PAMAM-NH₂ (1) dendrimer into a total of ~116 hetero-bifunctional groups on the periphery bearing 58 of 'Boc-amine' and 58 of 'hydroxyl' functionalities respectively (Scheme-1), in a one step reaction. Schemes 1-2 are schematic representations for synthesis of G4-PAMAM-NH-CO-Ser(OH)-NHBoc (3), and G4-PAMAM-NH-CO-Cys(SH)-NHBoc (6) Compounds (3 and 6) show the conversion of symmetric peripheral amines of G4-PAMAM-NH₂ (1) into hetero bifunctional terminal groups 'OH + NHBoc' and 'SH + NHBoc' respectively. The compounds (3, 6) on deprotection of Boc group gave OH + NH₂' and 'SH + NH₂' respectively.

The coupling reaction between G4-PAMAM-NH₂ dendrimer (1) and Boc-Ser-NHS (2) was carried out in N, N-Diisopropylethylamine (DIEA) in a two component solution of DMSO/DMF. Because of the higher reactivity of the NHS group of Boc-serine-NHS (2) with amine terminations of G4-PAMAM-NH₂ (1), it is expected that the product will consist of Boc-Ser residues conjugated at the G4-PAMAM-NH₂ (1) by amide bond, the reaction was monitored by MALDI-TOF analysis to ensure complete substitution. The

product so obtained was purified by dialysis using DMSO to remove the excess of unreacted Boc-Ser-NHS and other by products. The appearance of characteristic signals of Boc-Serine in the ^1H NMR spectrum at 1.38 (s, 9H, Boc), 2.10-2.22 (br.s, OH), 3.22-3.38 (m, 1H, CH_2), 4.50-4.58 (m, 1H, CH_2), 4.80-4.90 (m, 1H, CH), 6.50-6.60 (m, 1H, NH amide), 7.78-7.97 (br.d, NH amide interior dendrimer amide), ppm of G4-PAMAM-NH-CO-Ser(OH)-NHBoc (3) (Figure 2) confirm the desired product. It is evident from the integral ratio of the amide protons of PAMAM-NH-CO-Ser(OH)-NHBoc at 7.78-7.97 ppm to the two methylene protons of serine at 3.22-3.38 (m, 1H, CH_2), 4.50-4.58 (m, 1H, CH_2) ppm, that each G4-PAMAM- NH_2 dendrimer contains approximately 58 Boc-serine molecules attached. The MALDI-TOF/MS analysis of G4-PAMAM-NH-CO-Ser(OH)-NHBoc (3) shows the appearance of molecular mass peak at 24.5 kDa (Figure 2). For G4-PAMAM dendrimer the measured molecular weights (13.7 kDa) were lower than the theoretical value (14.21 kDa). The corresponding increase in mass from 13.7 kDa (G4-PAMAM-NH) to 24.5 kDa for G4-PAMAM-NH-CO-Ser(OH)-NHBoc (3), confirms attachment of 58 Boc-serine molecules since the molecular weight of serine is 205 Da. This further supports the NMR data which showed attachment of 58 molecules. The conversion of symmetrical terminal amines of G4-PAMAM to hetero-bifunctional 'OH' and 'NHBoc' terminal groups was 84 %. The results show that a high degree of surface functionalization has occurred. The PAMAM dendrimers have predominant structural defects in the starting compounds themselves and these were previously known to preclude the complete conversion. The HPLC chromatogram (210nm) shows a single peak corresponding to G4-PAMAM-NH-CO-Ser(OH)-NHBoc (3), confirming the purity of the product (Figure 2).

Achieving 'near complete' attachment of the Boc-serine moieties on the dendritic core was challenging. One of the probabilities was steric hindrance avoids the conjugation of the bulky molecules. When the attachment of cysteine with one protecting group (6, 13) and two protecting groups (28) was compared, to G4-PAMAM-OH (12), a drastic reduction in number of cysteines (28) attached to dendrimer was observed. This shows that presence of thiopyridyl and *tert*-Butoxycarbonyl protecting groups makes the cysteine (28) molecule bulky and hence causes steric hindrance leading to lower number of cysteines (28) attached to the dendrimer *vis a vis* cysteine

(5) with one protecting group. A single broad peak was observed in MALDI-TOF/Ms spectrum (Figure 2) and the peak corresponding to dendrimer (starting compound) at ~14.2 kDa was not observed in this spectrum indicating that the peak at 24.5 kDa belongs to the obtained G4-PAMAM-Ser-(OH)-NHBoc (3) compound. Further, the spectrum did not show multiple peaks confirming the absence of other by products. The ¹H NMR spectra and MALDI-TOF/Ms for G4-PAMAM-Ser-(OH)-NHBoc dendrimer (3) collectively suggest attachment of 58 molecules of Boc-Serine to G4-PAMAM-NH₂. The evaluations suggested that the 2-fold excess of serine was sufficient to achieve the complete end capping of the G4-PAMAM-NH₂ dendrimer (1) to provide G4-PAMAM-Ser-(OH)-NHBoc dendrimer (3). The above compound so obtained was further used to get amine terminations at the periphery attained by global deprotection of the *tert*-Butoxycarbonyl (Boc) groups using trifluoroacetic acid (scheme-1) and the resulting hetero-bifunctional dendrimer (4) can be then utilized in a variety of subsequent conjugation reactions. The characteristic signals of *tert*butyl groups appearing at 1.30 (s, 9H) in ¹H NMR spectrum of (4) disappear on deprotection but the other peaks corresponding to serine are seen at ¹H NMR spectrum at δ , 1.0-1.19 (m, 2H, NH₂), 1.80-1.98 (br. s, 1H, OH), 4.21-4.26 (s, 1H), 8.0-8.15 (br. d from amide NH), 8.30-8.60 (br. d, amide NH) ppm of G4-PAMAM-NH-CO-Ser(OH)-NH₂ (4) (Figure 3) confirm the desired product. It is evident from the integral ratio of the amide protons of PAMAM-NH-CO-Ser(OH)-NHBoc at 8.30-8.60 ppm to the two methylene protons of serine at 3.50-3.68 (m, 2H, CH₂) ppm, that each PAMAM-NH₂ dendrimer contains approximately 58 serine molecules attached. After deprotection, the molecular weight decreased from 24.5 kDa for (3) to 18.7 kDa for (4) (Figure 3). The mass of G4-PAMAM-NH₂ dendrimer is 13.7 kDa and this increase to 18.7 kDa corresponds to 58 molecules of serine attached since the molecular weight of serine is 105 Da. The HPLC chromatogram (210 nm) shows a single peak corresponding to G4-PAMAM-NH-CO-Ser(OH)-NH₂ (4), confirming the purity of the product (Figure 3). The diverse end groups so obtained are amenable for post-functionalization modifications or reactions. The high density of diverse end groups is achieved through a choice of the end termination of parent scaffold and the reacting amino acid. Different permutations of the end group functionality of the dendrimers were explored and several amino acids to develop a library of hetero-bifunctional dendrimers

(Table 1 (Library of Amino Acid Surface Modified Dendrimers) and Table 2 (Molecular weight estimation of amino acid functionalized dendrimers)).

Other hetero-bifunctional dendrimers (6, 10, 13, 16, 28) bearing 'SH + NHBoc' and 'COOMe + OH' terminal groups were synthesized by reacting G4-PAMAM-NH₂ dendrimer (1), G3.5-PAMAM-COOH dendrimer (8) and G4-PAMAM-OH (12) with Boc-Ser-NHS (2), Boc-Cys-NHS (4) and Boc-Ser-OMe respectively (Scheme 2-5, 7).

Schemes 3-4 are schematic representations for synthesis of G3.5-PAMAM-CO-NH-Ser(OH)-COOMe (10) and G4-PAMAM-O-CO-Cys(SH)-NHBoc (13) Compounds (10 and 13) show the conversion of symmetric peripheral acid of G3.5-PAMAM-NH₂ (8) into hetero bifunctional terminal groups 'COOMe+OH' and 'SH + NHBoc' respectively. The compounds 10, 13 was further hydrolysis of methyl ester and Boc gave compounds 'COOH+OH' and 'SH+NH₂' respectively.

Scheme 5 is a schematic representation for the post-functionalization reactions of hetero-bifunctional dendrimers showing conjugation of multiple drugs and or imaging agents in immediate succession. G4-PAMAM-O-Asp(COOH)-NH₂(17) dendrimer bearing COOH and NH₂ termini was synthesized. Dexamethasone was conjugated to G4-PAMAM-O-Asp(COOH)-NH₂(16) and indomethacin was added to achieve G4-PAMAM-O-Asp(CO-Dex)-NH-Ind (22). Similarly, FITC was conjugated in immediate succession to G4-PAMAM-O-Asp(CO-Dex)-NH₂ (20) to yield G4-PAMAM-O-Asp(CO-Dex)-NH-FITC (24).

Scheme 6 is a schematic representation for the post-functionalization reactions of hetero-bifunctional dendrimers showing conjugation of drug (e.g. dexamethasone) to one functional handle while the other functional handle is used for hydrogel formation (26) with N-hydroxysuccinimide terminated 8-arm-polyethylene glycol (25).

Scheme 7 is a schematic representation for the formation of hydrogel involving one of the functional handles of the G4-PAMAM-O-CO-Cys(S-TP)-NH₂ dendrimer while the 'NH₂' handle is available for further modifications. The thiol terminated 8arm PEG (20 kDa) formed gel at pH 7.4 by reacting with the dithiopyridine terminations of the G4-PAMAM-O-CO-Cys(S-TP)-NH₂ resulting in disulfide linkages.

Scheme-8. G4-NH-CO-Cys(S-TP) cross linked with 8-arm-PEG-SH to form dendrimer-PEG nanogel (or nanoparticles)

Scheme-9. G4-NH-PDP cross linked with 8-arm-PEG-SH to form G4-FITC encapsulated dendrimer-PEG nanogel (or nanoparticles)

Scheme-10: FITC-G4-NH-PDP cross linked with 8-arm-PEG-SH to form dendrimer-PEG nanogel (or nanoparticles)

5 Scheme-11: HBVS cross linked with G4-O-Cys(SH)-NH-FITC and 8-arm-PEG-SH to form dendrimer-PEG nanogel (or nanoparticles)

Scheme-12: FITC-G4-NH-Mal cross linked with 8-arm-PEG-SH to form dendrimer-PEG nanogel (or nanoparticles)

10 Scheme-13: G4-O-CO-Cys(S-Tp)-NH₂ cross linked with Meo-PEG-SH to form dendrimer-PEG nanogel (or nanoparticles)

Scheme-14: G4-O-CO-Cys(SH)-NH₂ cross linked with PDP-PEG-PDP to form dendrimer-PEG nanogel (or nanoparticles)

15 The compounds 3, 6, 13, 16, 28 on global deprotection of Boc groups with trifluoroacetic acid and dichloromethane gave 7, 14, 17, 29 and compound 10 on hydrolysis of methyl ester with lithium hydroxide in tetrahydrofuran / water (THF/H₂O) gave compound 11. The Table 1 gives the PAMAM dendrimer scaffold and the respective amino acids used to functionalize the periphery. The % conversion, and number of amino acids attached to the dendrimer is given in Table 2. In the past, it has been reported that attachment of 64 groups of phenylalanine on G4 dendrimer resulted
20 in a significant reduction in the water solubility of the compound. Herein, all the compounds with significantly high end group modifications of G4-PAMAM dendrimers with amino acids resulted in highly water soluble compounds (4, 7, 11, 14, and 17).

Conjugation of Drugs and Imaging agent on one terminal group and formation of hydrogel using the other.

25 The orthogonal and chemoselective nature of the peripheral end groups in the hetero-bifunctional dendrimers was demonstrated by conjugation of (i) two drugs *viz* dexamethasone and indomethacin and (ii) indomethacin, and an imaging agent (FITC) on the aspartic acid surface modified PAMAM dendrimer (16) (Scheme-5). In addition, the *in-situ* hydrogel formation using only one functional handle of the hetero-bifunctional
30 dendrimer is demonstrated, while the second functional handle is used for drug conjugation as shown in Scheme -6.

A hetero-bifunctional G4-PAMAM dendrimer bearing 'carboxylic' and 'Boc-amine' peripheral terminations, to facilitate the diverse post-functionalization reaction was obtained by reacting the 'hydroxyls' of G4-PAMAM-OH (12) with Boc-aspartic acid (15). The coupling reaction of G4-PAMAM-OH dendrimer (12) with Boc-aspartic acid (15) was carried out using EDC/DMAP (scheme-5) to obtain G4-PAMAM-O-Asp(COOH)-NH₂Boc (16). MALDI-TOF/MS of the functionalized dendrimer (16) reveals the mass peak at 25.7 kDa as seen from the mass spectrum (Figure 4). The molecular weight of Boc-Aspartic acid is 233 Da and so the increase from ~14 kDa for G4 PAMAM-OH (12) to 25.7 kDa corresponds to 56 molecules of Boc-aspartic acid (15) attached to G4-PAMAM-O-Asp(COOH)-NH₂Boc (16). The appearance of characteristic signals of Boc-Asp-OH in the ¹H NMR spectrum at 1.30 (s, 9H), 2.10-2.20 (m, 2H), 4.50-4.60 (br. s, 1H), 7.19-7.24 (br.s, amide NH), of G4-PAMAM-O-CO-Asp(COOH)-NH₂Boc (16) (Figure 5) confirm the desired product. It is evident from the integral ratio of the amide protons of PAMAM-O-CO-Asp(COOH)-NH₂Boc at 7.70-8.05 (br.d, amide NH) to the two methylene protons of Boc-Asp-OH 2.10-2.20 (m, 2H) that each PAMAM-OH dendrimer contains approximately 56. It is estimated that the extent of surface functionalization is 80% by taking the average of the MALDI/MS and NMR data and purity of the compound confirmed by RP-HPLC (Figure 6 (A)). On repeating the synthetic procedure several times 56 molecules could be conjugated, rather than the theoretical ~64 that are available, resulting in a total of 112 end functionalities (56 + 56 each). The structural defects in the starting compounds themselves (PAMAM dendrimers) could attribute for the observed effect. Both the MALDI and NMR, analysis do not account for the small structural imperfections. The results show a high degree of conversion (80%) of 'OH' terminal groups into 'COOH and Boc-NH' groups. In addition to carboxylic groups the amine terminations at the periphery are attained by global deprotection of the *tert*-Butoxycarbonyl (Boc) groups using trifluoroacetic acid (scheme-5) and the resulting hetero-bifunctional dendrimer (17) can then be utilized in a variety of subsequent conjugation reactions. The characteristic signals of *tert*-butyl groups appearing at 1.30 (s, 9H) in ¹H NMR spectrum of (17) disappear on deprotection but the other peaks corresponding to aspartic acid are seen at 2.20-2.38 (m, 2H), 4.22-4.31 (br.s, 1H), 7.96-8.10 (br. s, amide NH). 8.10-30 (br.d, amide, NH). After deprotection, the molecular

weight decreased from 25.7 kDa for (16) to 18.9 kDa for (17) (Figure 3), since the molecular weight of aspartic acid is 133 Da the mass of 15 corresponds to 46 molecules of the aspartic acid appended on the dendrimer thereby yielding a total of 92 end functionalities (46 + 46 each). Yet there is a merit in this scaffold as it has a high density of diverse end groups as compared to G4-PAMAM-OH dendrimer.

To test if the terminal groups are amenable to further modification, the G4-PAMAM-O-Asp(COOH)-NHBoc (16) was reacted with dexamethasone (18) as a model steroidal anti-inflammatory drug involving the carboxylic end groups on dendrimer to link the drug by ester bond using EDC/DMAP as coupling reagents (Scheme-5). Compound (19) was used without further characterization to get amine terminations at the periphery by global deprotection of the *tert*-Butoxycarbonyl (Boc) groups using trifluoroacetic acid (scheme-5) and the resulting (20) can be then utilized in a variety of subsequent conjugation reactions. The formation of G4-PAMAM-O-Asp(CO-Dex)-NH₂ (20) conjugate was validated by ¹H NMR analysis. The appearance of dexamethasone methyl protons at 0.75 (s, 3H), 0.82(s,3H) and 1.45(s, 3H), double bond protons at 6.01(s, 1H) 6.23(d, 1H) and 7.30(d, 1H), confirm the conjugation between G4-PAMAM-O-Asp(COOH)-NHBoc (16) and Dexamethasone (18) (Figure 5). The attachment of multiple copies of dexamethasone to G4-PAMAM-O-Asp(COOH)-NHBoc (16) dendrimers was determined by MALDI-TOF/Ms and purity of the compound confirmed by RP-HPLC (Figure 6C). The attachment of dexamethasone followed by Boc deprotection shifted the mass of G4-PAMAM-O-Asp(CO-Dex)-NH₂ dendrimer from 25.7 kDa to 21.9 kDa (Figure 4). Dexamethasone (18) has a molecular weight of 392 Da, therefore, the incremental mass corresponds to average of 8 molecules of dexamethasone molecules per dendrimer (number attained from 3 independent experiments).

To examine this further, the possibility of the conjugation of second drug to the hetero-bifunctional dendrimer (20) in immediate succession, the G4-PAMAM-O-Asp(CO-Dex)-NH₂ (20) was reacted with indomethacin (21) without the need to attach additional spacer or linker molecules. Indomethacin was chosen as another model drug which belongs to a class of anti-inflammatory drugs. The conjugation was carried out in presence of EDC/DMAP as coupling reagents (Scheme-5). The ¹H NMR analysis shows

that the aromatic protons corresponding to indomethacin appear at 2.10-2.30(m, 3H, CH₃) 3.62-3.80 (m, 5H, -OCH₃, -CO-CH₂-) 6.60-6.79 (m, 2H, Ar), 6.63-7.04 (m, 2H, Ar), 7.60-7.70 (m, 3H, Ar) confirming the conjugation of indomethacin to G4-PAMAM-O-Asp(CO-Dex)-NH₂ (20) to yield G4-PAMAM-O-Asp(CO-Dex)-NH-Ind (22) (Figure 5).

- 5 The purified dendrimer conjugate was subjected to MALDI-TOF analysis and the obtained mass exhibited an increase from 21.9 kDa (for 20) to 30.1 kDa (for 22) as expected (Figure 4) and purity of the compound confirmed by RP-HPLC (Figure 6 (E)). The increase in molecular weight corresponds to an average of 24 indomethacin molecules per dendrimer molecule, since indomethacin has a molecular mass of 357
- 10 Da, suggesting an overall 36 % loading of dexamethasone and indomethacin (number attained from 3 independent experiments). The ¹H NMR analysis showed that any undesired side products were not observed suggesting the clean attachment of two drugs (both dexamethasone and indomethacin).

- Polymeric scaffolds used in drug delivery are often tagged with imaging agents
- 15 and radio nucleotides to investigate their distribution pattern *in-vitro* and *in-vivo*. This attachment could be direct on to the scaffold or mediated through an appropriate linking chemistry, which may at times require a suitable spacer molecule. As shown herein, the carboxylic terminations G4-PAMAM-O-Asp-(CO-Dex)-NHBoc (20) were consumed for esterification with Dexamethasone (18), but the presence of Boc-amine groups
- 20 bestowed flexibility to explore after Boc deprotection for direct attachment of fluorescent imaging dye (FITC) (23) by thiourea bond. This demonstrated the ability of the hetero-bifunctional dendrimers to attach to drug and an imaging agent in immediate succession without any further modification thereby excluding the additional synthetic steps to append a suitable spacer to the dendrimer scaffold. G4-PAMAM-O-Asp-(CO-Dex)-NH₂
- 25 (20) conjugate was tagged with FITC (23) (scheme-5) in one step by adding FITC (23) to a solution of G4-PAMAM-O-Asp-(CO-Dex)-NH₂ (20) in DMSO and the reaction was stirred at room temperature in dark. The FITC-labeled G4-PAMAM-O-Asp(CO-Dex)-(NH-FITC) (23) was purified by dialysis using spectrapor membrane (cutoff 1000 Da) against DMSO in dark. The dialyzed product was dried under vacuum to obtain the
- 30 conjugate (24). Purity of G4-PAMAM-O-Asp(CO-Dex)-(NH-FITC) (24) conjugate was confirmed by HPLC using florescent detector (λ_{ex} =495nm / λ_{em} =521nm) (data not

shown). Further, the appearance of aromatic protons at 6.57-6.62 (d, 6H, Ar), 6.63-6.70 (s, 3H, Ar) in ^1H -NMR spectrum confirm the attachment of FITC and the integral ratio of amide protons of G4-PAMAM-O-Asp(CO-Dex)-NH₂ (20) appearing at 8.10-8.30 ppm to the aromatic protons at 6.57-6.62, 6.63-6.70 confirms the attachment of 6 molecules of FITC in G4-PAMAM-O-Asp(CO-Dex)-(NH-FITC) conjugate (24). The MALDI-TOF/MS of G4-PAMAM-O-Asp-(CO-Dex)-NH₂ (20) showed a mass of 21.9 kDa and a further increase in mass to 23.2 kDa affirmed the attachment of 6 molecules of FITC (data not shown).

The presence of two functional handles led the inventors to develop *in-situ* forming hydrogels using only one of the functional handles for chemical reaction forming the gel, while the other handle can be used for conjugating the drugs (Scheme 6). The ability of the NH₂ groups of G₄-PAMAM-O-Asp-(CO-Dex)-NH₂ (20) for hydrogel formation was tested by its reaction with N-hydroxy-succinimide terminated 8-arm-PEG polymer (25) and blue dextran (Mw 5000) was physically entrapped in this gel. Hydrogel formation was determined by the "inverted tube method" and hydrogels were considered to have formed once the solution ceased to flow from the inverted tube (Figure 7). The gelation times for these hydrogels ranged 30-50 seconds and these open new vistas for the drug delivery application of these hereto-bifunctional dendrimers. Of the amine and the COOH terminal groups of G₄-PAMAM-O-Asp-(CO-Dex)-NH₂ (20) the COOH groups were involved in conjugation of drug dexamethasone (18) by ester linkage, while the NH₂ groups were involved in gel formation by amide linkages on reaction with N-hydroxy-succinimide terminated 8-arm-PEG (25) polymer (Scheme 6). This provides a new approach to design of hydrogels where the rate of drug release can be further slowed since the drug release involves two steps (i) release from covalent linkage of dendrimer after the degradation or hydrolysis of the bond (ii) diffusion of the drug from the hydrogel. Different concentrations of the polymer solution were tested in the stoichiometric ratio 1:1 and the gel formation was observed at 3, 5 and 8% w/w. Further, FITC (23) was attached to few NH₂ groups (3 end groups) of the G₄-PAMAM-O-Asp-(CO-Dex)-NH₂ (20) and this dendrimer also formed hydrogel by amide linkages on reaction with N-hydroxy-succinimide terminated 8-arm-PEG polymer (25), this gel is shown in Figure 7. The SEM image shows the gel network formed by

reaction of PEG-NHS (25) with G₄-PAMAM-O-Asp-(CO-Dex)-NH₂ (20) and G₄-PAMAM-O-Asp-(CO-Dex)-NH-FITC (24).

The above conjugation reactions show the ability of robust post-functionalization modifications in these hetero-bifunctional dendrimers, a hallmark of synthetic efficiency which further confirms that these peripheral end groups exhibit chemoselectivity based on their asymmetric or orthogonal nature. With these results there was demonstrated the ability to achieve a large number of asymmetric end groups (112) on G₄ PAMAM dendrimer as compared to 64 symmetric end groups available traditionally, in just one step one pot reaction. Dexamethasone and indomethacin were conjugated to G₄-PAMAM-O-Asp(COOH)-NHBoc (16) using an ester and after Boc deprotection amide linkage respectively. Further, FITC and dexamethasone were attached on G₄-PAMAM-O-Asp(COOH)-NHBoc by thiourea and ester linkage respectively. The *in-situ* gelling hydrogels with the ability to physically entrap and covalently attach the drugs was demonstrated. The diverse nature of these hetero-bifunctional groups on dendrimers additionally confer the flexibility to append several functional groups in immediate succession, without the need for protection deprotection steps or need to append specific linker, all contributing the drastic reduction in the synthetic and purification steps.

In-situ hydrogel formation by crosslinking of hetero-bifunctional dendrimers bearing 'S-TP' and 'NH₂' terminations

Hydrogels have been used as vehicles for sustained drug delivery. The rich end functionalities prepared using the current approach could enable a new class of multifunctional hydrogels. There is disclosed herein an approach where a dendrimer based degradable hydrogel comprising redox sensitive bond is disclosed. The hydroxyl-terminated G₄-PAMAM-OH dendrimer (12) was end capped with Boc-Cys(S-thiopyridyl)-OH (27) to yield 70 % hetero-bifunctional end groups comprising 42 thiol protected and 42 amine terminations in protected form (Scheme-7). The thiol groups in Boc-cysteine were protected using 2-aldrithiol before modifying the dendrimer to yield G₄-PAMAM-O-CO-Cys(S-thiopyridyl)-NHBoc (28). The thiol protection reaction was carried out in mild reaction conditions using methanol/water as solvent at room temperature for 24 hours. The product was obtained by recrystallization in acetone and

hexane. The *tert*-Butoxycarbonyl (Boc) protecting groups were removed by using trifluoroacetic acid in dichloromethane to yield amine functionality. G4-PAMAM-O-CO-Cys(S-thiopyridyl)-NH₂ (29) so obtained was mixed with the solution of 8arm-polyethylene glycol with thiol terminations (ratio 1:4 w/v respectively), resulting in *in-situ* forming hydrogel. This reaction is simple and occurs in physiological pH 7.4 phosphate buffer saline by the formation of disulfide crosslinks (Scheme-7). Apparently the disulfide crosslink reactions occur rapidly and hence the gelation time for these gels was less than 45 seconds. Over a period of time (20 days) physiological (pH 7.4, 37°C) condition these gels undergo a gel to sol transformation suggesting the degradation or breakdown of the gels. It has been reported that disulfide exchange reactions occur slowly in milieu under physiological conditions which contribute for the degradation of the hydrogel. With these studies there is demonstrated the potential of these hetero-bifunctional dendrimers for *in-situ* forming hydrogels. These hydrogels can be further explored for physical encapsulation of drug or covalent linkage of drug to the other functional group for providing sustained release of drugs in a similar way as disclosed for the gels formed between G4-PAMAM-Asp-(CO-Dex)-NH₂ (20) with PEG-NHS (25). An interesting feature of this reaction is that both the *tert*-Butoxycarbonyl and thiopyridyl groups are orthogonal in nature and under the acidic conditions trifluoroacetic acid in dichloromethane used for deprotection of *tert*-Butoxycarbonyl groups the thiopyridyl groups are extremely stable. With the introduction of two protecting groups in cysteine it was observed that the total number of copies of cysteine attached drastically reduced to 38 (59% conversion) as compared to other amino acids used without protecting groups or with single protecting group showing 87 % to 91% conversion. The ¹H-NMR, MALDI-TOF characterization of G4-PAMAM-O-CO-Cys(S-thiopyridyl)-NHBoc (28) and its *tert*-Butoxycarbonyl deprotection are provided in supporting information.

Example 2

Preparation of dendrimer-PEG-nanogel

Nanogel composed of the dendrimer-PDP (or dendrimer drug conjugate) and the PEG-SH (8 arm or liner) were synthesized. In brief, To a solution of 8-arm-PEG-SH (polymer) (100mg) in PBS(1ml) (pH =7.4) in 1st 50 ml round bottom flask. Dendrimer-PDP (100mg) in PBS (1ml) (pH =7.4) in 2nd 50 ml of round bottom flak. In 3rd round

bottom flask containing water phase(50ml) consisted of a 2.5% (w/v) aqueous solution of the surfactant polyvinyl alcohol (PVA, MW 13,000-23,000, 87-89% hydrolyzed). The above 1st polymer and 2nd dendrimer-PDP was slowly added to the water phase with high-speed blending (24,000 rpm) for two minutes and the mixture formed a cloudy white emulsion. The emulsion was then allowed to stir in an uncovered beaker for several hours (24 hours) in a vacuum hood. The emulsion was centrifuged at 10,000 rpm for 30 minutes. The supernatant was lyophilized and stored for analysis of dendrimer-drug conjugate concentration to be determined by spectrophotometry. The white, nanoparticles were twice resuspended in deionized water following ten minute centrifugation at 10,000 rpm. They were finally resuspended in a minimal amount of deionized water and freeze-dried overnight. A fine white powder of dendrimer-PEG nanoparticles were then obtained and analyzed using scanning electron microscopy (SEM).

Example 3

15 Particle size and zeta potential

The impact of surface modification of the dendrimers on particle size, zeta potential, blood retention and *in vivo* organ distribution has been previously reported. The complete surface modification of the dendrimers with amino acids on an average increased the particle size by 1-2nm as seen from Table 3 (Particle size and zeta potential hetero-bifunctional dendrimers). The end capping of the cationic G4-PAMAM - NH₂ dendrimer with serine and cysteine resulted in drastic reduction in the zeta potential from +11.5 to -1.83 and 4.80 mV respectively. The interesting part is that both these constructs retain equal number of surface NH₂ termini as compared to unmodified G4-PAMAM-NH₂, yet exhibit reduced charge and are therefore expected to reduce the cytotoxicity. The hydroxyl terminated G4-PAMAM dendrimers are nontoxic due to the neutral surface charge and end capping it with aspartic acid and cysteine did not increase the charge significantly (Table 3). Again, both these constructs have NH₂ termini in addition to other groups yet exhibit low charge. By end capping of the hydroxyl terminated dendrimer, hydrogels can be attained and attachment of several functional groups, without eliciting the cytotoxicity. The unusual and unexpectedly high zeta potential was exhibited by the carboxylic acid terminated dendrimer end capped with

serine (+8.83mV). The increase in zeta potential was consistent with the increased cytotoxicity of this construct.

Example 4

Biocompatible nature of the components

5 Hemolytic and in-vitro cytotoxicity

Red blood cell (RBC) lysis is a simple quantitative measure of hemoglobin (Hb) release widely used to study polymer-membrane interaction. Both cationic and anionic PAMAM dendrimers at 1 mg/ml concentration and exposure of 1 hour induce marked morphological changes evidenced by clumping of RBCs. The study showed a zero
10 hemolysis and 100% hemolysis on incubating the RBCs with PBS (negative control) and 1% Triton X-100 (hemolytic agent-positive control) respectively. All the hetero-bifunctional dendrimers synthesized were non hemolytic in the concentration range 1 – 100 µg/ml on exposure for 3 hours (Figure 8). At concentration of 1 mg/ml and exposure for 3 hours about 1.5 %-3.0 % was observed for all the compounds except the G3.5-
15 PAMAM-CO-Ser(OH)-COOH which showed a hemolysis of 5% in 3 hours. Consistent with the hemolysis study, the *in-vitro* cytotoxicity study showed that the new compounds were nontoxic (Figure 8) in the concentration range 10-100 µg/ml and few were nontoxic even at 1 mg/ml concentrations.

Dendrimer cytotoxicity is strongly influenced by the nature of surface group and
20 dendrimers bearing NH₂ termini display concentration and generation dependant cytotoxicity. The amine-terminated dendrimers are known to exhibit cytotoxicity due to high cationic charge while the hydroxyl dendrimers are non-cytotoxic due to the neutral surface charge. The G4-PAMAM-NH₂ dendrimers exhibited cytotoxicity at 5 µg/ml concentration after 5 hours exposure to B16F10. The cell viability fell to < 10% for the
25 V79 chinese hamster lung fibroblasts cells after 24 hours exposure to PAMAM dendrimers generations G3 (1nM), G5 (10 mM) and G7 (100 nM). A previous study showed that G4-PAMAM-OH and G3.5-PAMAM-COOH were nontoxic to A549 cells at concentrations 10-1000 µg/ml while G4-PAMAM-NH₂ dendrimer was nontoxic at 10-100 µg/ml and exhibited toxicity at 1000 µg/ml after 72 hours treatment. These results were
30 consistent with those reported by Duncan et al.

The cytotoxicity of all the hetero-bifunctional dendrimers synthesized using human lung carcinoma cells (A549) and mouse microglial cells (BV-2) were evaluated, both cells with clinical implications for dendrimer use in cancer and neuroinflammation. MTT assay showed that the compounds G4-OH-Cys-(SH)-NH₂ and G4-OH-Asp-(COOH)-NH₂ were not toxic to A549 cells in the concentration range of 1 µg/mL -1 mg/mL after 24h exposure (Figure 9). It is interesting to note that both these compounds have NH₂ termini and yet they were non-toxic at higher concentrations (in contrast to G4-PAMAM-NH₂ dendrimers with the same end groups) and retained the behavior similar to the neutral, non-toxic G4-PAMAM-OH dendrimers. This was consistent with the zeta potential measurements for both these compounds which showed that the zeta potential did not increase significantly from that of G4-PAMAM-OH (Table 3). While, modifying the surface of G4-PAMAM-NH₂ with serine and cysteine, the compounds; G4-PAMAM-NH-Ser(OH)-NH₂ and G4-PAMAM-NH-Cys(SH)-NH₂ were nontoxic at concentrations 1-100 µg/ml after 24 hours. Both the compounds had NH₂ termini after surface modification yet they were non-toxic at the concentrations evaluated. Further, more than 40 % of cells were viable after exposure to high concentration of 1 mg/ml for 24 hours for these two compounds indicative of marked reduction in cytotoxicity when compared to G4-PAMAM-NH₂ alone. It has been reported that COOH terminated dendrimers G1.5 to 9.5 are nontoxic up to 5 mg/ml concentrations to B16F10, CCRF and HepG2. It was observed that on modifying G3.5-PAMAM-COOH with serine, the compound was nontoxic at 1-10 µg/ml concentration but exhibited marked toxicity at 100 µg/ml, and this can be expected since this compound exhibited a very high zeta potential +8.83 mV. From these results some promising candidates for drug delivery appear to be G4-OH-Cys-(SH)-NH₂ and G4-OH-Asp-(COOH)-NH₂ which showed post-functionalization ability, applicability in hydrogel formation and as carriers for multiple functional groups such as drug and imaging agents.

There was demonstrated that by appropriate choice of G4-PAMAM dendrimer end groups (NH₂, OH, COOH) and amino acids for surface modifications, a library of multivalent, multifunctional dendrimers bearing OH and NH₂, COOH and NH₂, NH₂ and SH, COOH and OH at the peripheries can be achieved. High yields were achieved in

the coupling reactions since an excess of amino acid could be used, and the unreacted material could later be removed by a simple dialysis process. Conversions 70-90% of hetero-bifunctional dendrimers were obtained by carrying out the reactions in mild simplistic conditions such as water/dimethylsulfoxide/dimethyl formamide or in some cases dimethylsulfoxide/dimethyl formamide. The orthogonal peripheral handles of the resulting dendrimers are available for the eventual attachment of drugs, imaging agents or radiolabels and for the biological evaluation of these carriers.

One of the key features is the use of biocompatible amino acids used to achieve these diverse end functionalities. The objective was to use compounds that would not elicit undesirable interactions of dendrimers with cell surfaces, enzymes, and proteins in the blood serum. Further, the degree of drug loading could be easily adjusted. The amino acids are known to provide catalytic pockets for the enzymatic cleavage, hence the byproducts obtained by the cleavage of drug products are expected to be nontoxic. By decorating the dendrimer periphery with amino acid motifs, an enhanced solubility, reduced cytotoxicity, reduced hemolytic toxicity, while retaining the chemoselective reactivity and conferring flexibility to conjugate varied functional groups such as drugs and or imaging agents could be achieved.

Example 5:

Local intravaginal drug therapy is preferred for treatment of ascending genital infections during pregnancy. There is disclosed herein an *in-situ* forming biodegradable hydrogel for sustained release of amoxicillin in the cervicovaginal region is described. Amino terminated, ethylenediamine-core generation-4 poly(amidoamine) dendrimer with peripheralthiopyridyl groups (G4-NH₂-NHPPD) was crosslinked with 8-arm polyethylene glycol (PEG) bearing thiol terminations. The hydrogels were formulated and tested *in-vivo* in pregnant guinea pig model for volume, retention times, biodegradation, tolerability and transport across fetal membrane. The physicochemical characterization of the hydrogels was carried out using differential calorimetry, SEM, and confocal imaging. The hydrogels offer dual antibacterial activity arising from sustained release of amoxicillin followed by the release of amine terminated PAMAM dendrimer from the degrading gels. The *in-vivo* studies in guinea pig showed that 100-200 μ L of gel sufficiently covered the cervicovaginal region with a residence time of at

least 72 hours and gel was primarily retained in the maternal tissues without crossing the fetal membranes into the fetus. The dendrimer gels were stable up to 72 hours and the *in-vivo* biodegradation of gel occurred after 72 hours and this correlated well with the *in-vitro* degradation pattern. The pH of the vagina was not altered on application of the gel and none of the animals aborted upto 72 hours after application of gel. The histological evaluation of the cervical tissues showed absence of edema in epithelial cell layer, no sloughing of the epithelial or superficial mucous layer, absence of necrosis and infiltration of inflammatory cells in the submucosal layers confirmed that tissues were tolerant to the gel.

The immunohistofluorescence images showed the localization of the gel components on the superficial mucified epithelial layer. The crosslinking density and swelling of hydrogels was impacted by the polymer content and the 10 % hydrogels exhibited highest crosslink density. The *in-vitro* drug release studies carried out using Franz diffusion cells showed that amoxicillin release from 6 and 10 % gels was sustained for 240 hours as compared to 3 % gels. As the polymer concentration increased to 10% the release pattern from gels approached diffusion controlled mechanism with diffusional exponent $n = 0.49$. In conclusion, studied biodegradable *in-situ* forming hydrogels offer a therapeutic option to provide sustained localized delivery of amoxicillin intracervically to the pregnant woman for the treatment of ascending genital infections.

Herein, there was investigated the *in-situ* forming biodegradable hydrogels obtained by crosslinking of thiopyridyl functionalized G4-NH₂-PDP PAMAM dendrimer with 8-arm polyethylene glycol (20 kDa) for sustained intravaginal delivery of amoxicillin to treat ascending genital infections during pregnancy. Multiple thiopyridyl surface functionalities of the dendrimer and the star-PEG are utilized to create a biodegradable gel with disulfide linkages. This offers the potential for the dendrimer and drug to be released, as the hydrogel degrades. Further dendrimers offer the potential to target selectively inflammatory cells. The hydrogels were investigated for biodegradation, retention, tolerability and volume of distribution by intravaginal application in the pregnant guinea pig model. In the past hydrogels containing dendritic materials obtained by photocrosslinking, radiation, thermal gelation, ion interactions and freeze

thaw cycles of polymers have been described. The hydrogels discussed herein are formed *in-situ* by chemical crosslinking resulting from simple mixing of the G4-NH₂-NHPDP dendrimer and the PEG polymer solutions in buffer through the formation of disulfide bonds and these hydrogels possess the properties of both the PEG hydrogels and the dendrimer.

The cervical infections in pregnant women caused by pathogens such as *Streptococcus group B*, *E. coli* and *Gardnerella vaginalis* are responsible for the premature rupture of the fetal membranes, chorioamnionitis and prematurity. Amine terminated PAMAM dendrimers exhibit antibacterial activity against *E. coli*, *P. aeruginosa* and *S. aureus* by inducing formation of nanoscale holes in lipid bilayers of bacterial cell membrane causing cell lysis and death. The partially pegylated amine terminated PAMAM dendrimers demonstrate antibacterial activity against *E. Coli* bacteria, *P. aeruginosa*. The pegylation of dendrimers reduces their cytotoxicity and yet retains the antibacterial activity. The poly(amidoamine) generation 4 amine terminated PAMAM dendrimer has been partially modified with thiopyridine moieties and chemically bound to 8arm PEG via disulfide bridges to form the hydrogel while number of the primary amine groups remained unmodified. The covalent linking of PEG to dendrimer while gel formation was expected to overcome the cytotoxicity. Further, the investigated amoxicillin loaded hydrogels were expected to exhibit dual antibacterial mechanism, arising from sustained release of the antibiotic and activity exhibited by the amine terminated dendrimer released from the degrading gel.

Materials and methods

Materials

Amine terminated, ethylenediamine-core poly(amidoamine) dendrimer (G4-NH₂) (diagnostic grade generation-4 with -NH₂ groups) was purchased from Dendritech and 8-arm-PEG-SH (20 kDa) (5) was purchased from NOF America Corporation, USA. Other reagents were obtained from assorted vendors in the highest quality available. Of these, amoxicillin, N-Succinimidyl 3-(2-pyridylthio)-propionate (SPDP), polyvinylpyrrolidone (PVP 30 kDa), PEG 600, glycerol, glutathione (GSH), dimethyl sulfoxide (DMSO), fluorescein isothiocyanate (FITC), dimethylformamide (DMF),

Ethanol, phosphate buffer saline (PBS, pH, 7.4), and HPLC-grade solvents were obtained from Sigma-Aldrich.

Synthesis of G4-NH₂-NHPDP (4)

G4-NH₂ (2) dendrimer was dissolved in PBS buffer pH 7.4 (20 mL) and the solution of SPDP (3) in ethanol (10 mL) was added to it under stirring to provide sufficient modification whilst preventing loss of product due to the insolubility of highly modified dendrimer. Reaction was stirred at room temperature for 2 hours. After completion of the reaction, solvent was removed under reduced pressure to get a solid compound. The crude product obtained from the reaction mixture was dialyzed against water using spectrapor dialysis membranes (MW cut-off 1000 Da) (pH = 5 obtained by addition of 1% HCl) to remove by-products and the excess of reactants. After dialysis, the solvent was removed using lyophilization. Solid was reconstituted in desired amount of PBS (pH 7.4) and used for hydrogel formulation.

Preparation of -G4-NH₂-FITC-NHPDP

FITC (0.082g M=389.38 2.10×10^{-4} mol) was added to the solution of G4-NH₂ dendrimer in DMSO (20 mL) under stirring and the reaction was continued in dark for 18 hours. To remove unreacted FITC, the reaction mixture was dialyzed (molecular weight cut off of membrane 1000Da) in DMSO for 24 hours (solvent was changed every 8 hours). After dialysis the DMSO was lyophilized to get pure G4-NH₂-FITC conjugate as dark orange color solid. The G4-NH₂-FITC conjugate was dissolved in methanol and precipitated in acetone. Absence of free FITC in the conjugate was verified by TLC using chloroform and methanol (ratio 1:1) as mobile phase. After purification of the G4-NH₂-FITC conjugate, the above described procedure was used to synthesize -G4-NH₂-NHPDP-FITC for hydrogel formulation for *in vivo* applications

Hydrogel formation

Hydrogels were prepared by crosslinking of the branched thiol terminated PEG polymer (8-arm-PEG-SH, 20 kDa) with G4-NH₂-NHPDP (or G4NH₂FITC-NHPDP). Hydrogels containing 10, 6 and 3 % w/v of polymers were prepared by mixing equal volumes (1:1 v/v, 100 μ L each) of the 10, 6 and 3 %w/v polymer solutions of G4-NH₂-NH-PDP and 8-arm-PEG-SH in PBS (pH=7.4) as shown in Table 4. The ratio of PDP to thiol functionalities in these hydrogels was 2:1. The hydrogels resulted in 10-30 seconds

of mixing the two polymer solutions. The gelation time was determined by the vial tilting method. When the sample showed no flow, it was regarded as a gel. These hydrogels were further investigated to determine the degree of swelling, drug loading efficiency, *in vitro* release studies, and *in vivo* applications.

5 Morphology of the hydrogel

Scanning Electron Microscopy (SEM) analyses were performed to investigate the morphology of hydrogel. The 10, 6 and 3 % w/v hydrogels were prepared for electron microscopy at room temperature, followed by dehydration using lyophilization. It was observed that the hydrogel volume was reduced by ~75% during the dehydration process. The samples were critical point dried, sputter-coated with 9 nm of gold/palladium, and imaged using SEM (HITACHI S-2400 Scanning Electron Microscope) at 20 kV. The cross sections of the hydrogels were observed using confocal microscopy, to determine the crosslink density. The gels were formed by crosslinking of -G4-NH₂- FITC NHPDP with 8-arm-PEG-SH in PBS (pH=7.4). The 10, 6 and 3% w/v gels were embedded in OCT media (Tissue-Tek[®]) and frozen at -80 °C until they were sectioned. Gels sections (20 μ thick) were cut using a cryostat (Leica Microsystems; Nuchloss, Germany). Images of the sectioned gels were captured on a Leica TCS SP5 laser scanning confocal microscope (Leica Microsystems GmbH, Wetzlar, Germany).

20 Equilibrium swelling of hydrogels

The 10, 6 and 3 % w/v hydrogel discs were obtained by crosslinking of G4-NH₂-NH-PDP and PEG (1:1v/v, 100 μL each) in a cylindrical glass vial (12x35mm). These hydrogel discs were weighed and subsequently immersed in 5 mL of pH 7.4 phosphate buffered saline (PBS) solution at 37°C in 30 mL scintillation vials. The swollen hydrogels were removed from PBS and weighted at various time intervals until a swelling equilibrium had been reached. All experiments were carried out in triplicate and the results are expressed as means ± standard deviations.

The degree of swelling was calculated from the formula previously reported where W_s is the weight of the swollen hydrogel at time t and W_0 (wet) is the initial weight.

$$\%Swelling = \frac{(W_s - W_o)}{W_o} \times 100$$

Formulation of hydrogel

The prototype vaginal gels were made using excipients; glycerin (5%, v/v), PVP (4%, w/w) and PEG 600 (5%, v/v), which were included in hydrogel formulation to improve the emollient, adhesion, retention and spreadability properties of hydrogels. These excipients were dissolved in the PBS buffer at the concentrations as shown in Table 4 and this solution was used as a vehicle to dissolve separately the G4-NH₂-NHPDP (or G4-NH₂-FITC-NHPDP) and 8-arm PEG-SH. The hydrogel formulation was obtained by mixing the solution of G4-NH₂-NHPDP and 8-arm PEG-SH in the solvent vehicle at the ratio 1:1 v/v. The gelling time was recorded for the different compositions of vehicle and polymers. The optimal concentration of additives was determined by measuring the crosslinking time and retention time of hydrogel formulation on targeted area.

Reverse Phase HPLC characterization

In vitro drug release and characterization of conjugates was carried out with waters HPLC instrument equipped with one pump, an auto sampler and dual UV, RI, and fluorescence detector interfaced to millennium software instruments models should included. The mobile phase used was acetonitrile (both 0.14% TFA by w.) and water phase had a pH of 2.25. Mobile phases were freshly prepared, filtered and degassed prior to the use. Supelco Discovery BIO Wide Pore C5 HPLC Column (5 µm particle size, 25 cm × 4.6 mm length × I.D.) equipped with C5 Supelguard Cartridge (5 µm particle size, 2 cm × 4.0 mm length × I.D.) was used for characterization of the conjugates as well as *in vitro* drug release studies. Gradient method was used for analysis and the method used was water: acetonitrile (100:0) to water-acetonitrile (60:40) in 25 minutes followed by returning to initial conditions for 5 minutes. The flow rate was 1 mL/min. Calibration curves were prepared for amoxicillin, based on UV absorbance peak area at 229 nm. These calibrations were used to measure of *in vitro* drug release from cellulose membrane in Franz diffusion cell.

Differential scanning calorimetry (DSC) analysis of hydrogels

The neat and modified polymers and hydrogels were subjected to thermal analysis using TA Instruments DSC Q2000 V24.4 Build 116 Module DSC Standard Cell RC. The experiments were conducted in crimped sealed aluminium pans and the weight of each sample was in the range 1–2 mg. All the samples were analyzed using the heat cool heat cycles. The samples were equilibrated at - 50 °C for 2 minutes and were heated to 150 °C at a heating rate of 5°C/min under nitrogen flow. The samples were quench cooled to -50 °C and equilibrated for 2 minutes and again heated to 150 °C at a heating rate of 5 °C/min.

Degradation of hydrogels

In vitro degradation of hydrogel was performed in glutathione (GSH) solutions at pH 4 and simulated vaginal fluid up to 72 hours. The simulated vaginal fluid (SVF) was prepared as described previously by addition of GSH. Briefly, the SVF was prepared by 350mg of NaCl, 140mg of KOH, 22 mg of Ca(OH)₂, 18 mg of bovine serum albumin, 200mg of lactic acid, 100mg of acetic acid, 16 mg of glycerol, 40mg of urea, 500mg of glucose, 20mg of GSH and the pH was adjusted to 4 ± 0.02 using 0.1 M HCl. Hydrogel discs obtained by crosslinking of G4-NH₂-NHPDP and 8-arm PEG-SH (1:1v/v, 100 µL each) were immersed into the 5 mL GSH solution at pH 4 and simulated vaginal fluid at pH 4 in 30 mL scintillation vials in triplicate and observed for degradation.

Drug loading into the hydrogels

Antibiotic (amoxicillin) was physically entrapped into the hydrogels. The drug was (0.5 mg) added to the PEG solution (100 µL) in vehicle and the solution of G4-NH₂-NHPDP (100 µL) in vehicle was added to this PEG solution to form the dendrimer-PEG hydrogel (200 µL).

Drug loading efficiency

The amount of amoxicillin entrapped in the dendrimer-PEG hydrogels (10%, 6% and 3%) was determined by breaking the gel into small pieces and transferring into 1 mL eppendorf tube filled with PBS (pH 7.4) and sonicated for 10 minutes and washed the hydrogel pieces three times to extract drug. The washings were collected and filtered with 0.2µm millipore filter and quantified by a reverse phase (RP) HPLC

analysis, using UV detection at a wavelength of 229 nm. Water: acetonitrile were used as mobile phase at a flow rate of 1 mL/min. The difference between the amount of drug taken initially and the drug content in the washings is the amount of drug entrapped.

In vitro drug release using Franz diffusion cell

5 For the *in-vitro* drug release study, jacketed Franz diffusion cells with flat ground joint were used. The membrane was clamped between the donor and receiver chambers of the Franz diffusion cell apparatus with a diameter of 5 mm and a diffusional area of 0.64 cm² and the receptor chamber volume of 5 mL. Nitrocellulose acetate membranes (Millipore, America) with an average pore size of 0.45 µm were
10 used. The receptor chambers filled with PBS (pH = 7.4) were maintained at 37°C in order to ensure the body temperature. Drug (Amoxicillin) is well soluble in the chosen receptor medium. Each cell contained a magnetic bar and was stirred (600 rpm) during the experiment. The cells were equilibrated for 1 hour before the samples were mounted. 200 µL samples were taken at predetermined time points and replaced with
15 equal amount of fresh receptor medium to maintain sink condition. The samples were kept frozen at 4 °C prior to analysis, to quantify the drug release by reverse phase high performance liquid chromatography (RP-HPLC). All samples were run in triplicates for statistical analysis.

Evaluation of hydrogel in pregnant guinea pig model

20 Pregnant Dunkin-Hartley strain guinea pigs (n =15) (Charles River) at 55 days of gestation (third trimester) were anesthetized by inhalation of 5.0% Isoflurane in 100 % oxygen at a flow rate of 2 L/min in an approved rodent anesthesia chamber. Surgical-level of anesthesia was maintained with 1.5 and 2.0% Isoflurane in 100% oxygen at a flow rate of 1-2 L/min via a nose cone. An endoscope was used to visualize the cervix.
25 FITC labeled dendrimer-PEG hydrogel (100-500 µL) was injected into the cervix using i.v. catheter (BD Angiocath, Infusion, Therapy systems Inc. Sandy Utah, 16GA 5.25IN, 1.7x 133mm). The pH of the vagina was intermittently tested by wiping the vaginal fluid using cotton swabs. After single vaginal application, the vaginal cavity was observed for any signs of possible irritation of the vaginal mucosa (edema or redness of tissue). The
30 observations were scored and recorded as follows: no erythema, slight erythema (light pink) and moderate to severe erythema (dark pink or light red). After 5, 12, 24 and 72

hours intervention, guinea pigs were euthanized with pentobarbital sodium (120 mg/kg) and midline laparotomy was performed to expose cervicovaginal region for further evaluation. The retention times, biodegradation and tolerability were studied *in-vivo* using the guinea pigs. The vaginal and cervical tissues were used for histopathological evaluation.

Immunofluorescence histochemistry

An immunofluorescence studies were performed to investigate biodistribution of the FITC-dendrimer-PEG hydrogel in the cervicovaginal tissues of guinea pig after 24 and 72 hours of treatment. Double immunofluorescent staining was performed on 20 μ m thick, paraffin sections of tissues placed on silanized slides. The mucified epithelial cells were identified based on the positive staining for cytokeratin. The immunofluorescent staining was performed using Ventana Discovery autostainer for controlled and optimised reaction environment using the automation-optimized reagents from Ventana Medical Systems Inc. Briefly, paraffin wax sections were loaded onto the Ventana Discovery platform and following steps were completed automatically, these included dewaxing by EZ prep buffer (Ventana Medical Inc.), pre-treatment in Tris/EDTA pH 8.0 antigen retrieval solution (Ventana mCC1) or protease solution for 1 hour (Ventana protease 2). Endogenous peroxidase was inactivated using an enhanced inhibitor provided in the staining kit and nonspecific antibody binding was blocked by treatment with blocking solution for 10 minutes. The blocking solution was removed and the sections were washed three times with PBS/Tween solution incubated with primary antibodies for 1 hour using the liquid cover slip (Ventana Medical Inc). The primary antibody used was monoclonal mouse anti-human cytokeratin (1:200, M7018, Dako Carpinteria, CA, USA). The sections were again washed three times with PBS/Tween solution incubated with secondary antibodies, Alexa Fluor[®]594 goat anti-mouse IgG (1:500, A11005, Invitrogen) for 1 hour using the antibody diluent from Ventana. The sections were washed with PBS/Tween, counterstained and mounted with DAPI prolong Gold antifade and cover slipped. Images were captured from Leica TCS SP5 Laser Scanning Confocal Microscope (Leica Microsystems GmbH, Wetzlar, Germany). All study specimens were analyzed by a pathologist blinded to the clinical information.

Results and discussion

Synthesis of G4-NH₂-NHPDP

To incorporate the thiol reactive terminal groups on the dendrimer to form hydrogel with 8-arm PEG-SH, the SPDP linkers were covalently attached to the dendrimer surface to yield thiopyridine functionalities. It was achieved by reacting amine terminated generation 4 PAMAM dendrimer (for short G4-NH₂) with the heterobifunctional cross-linker SPDP (Scheme 15). The *N*-succinimidyl activated ester groups of SPDP were coupled to the terminal primary amines to form amide-linked 2-pyridyldithiopropionyl (PDP) groups (G4-NH₂-NHPDP) (Scheme 15). The ¹H NMR spectra of G4-NH₂-NHPDP showed presence of protons corresponding to the aromatic ring of thiopyridyl groups and protons related the dendrimer. The aromatic protons of thiopyridine emerged at 7.20-2.26 (m, 1H, Ar), 7.74-7.82 (br.d, 1H, Ar), and 8.15-8.22 (m, 2H, Ar) ppm while the other protons appeared at 2.42-2.50 (m, 4H, -CH₂-CH₂-).

Scheme 15 is a schematic representation of the hydrogel formation. The thiol terminated 8-arm PEG (20 kDa) formed gel at pH 7.4 by reacting with the dithiopyridine terminal groups of the G4-NH₂-NHPDP resulting in disulfide linkages from PDP, 2.67-2.72 (m, 2H, -CH₂- from interior dendrimer) 2.86-2.92 (m, 1H, -CH₂- from interior dendrimer), 3.03-3.12 (m, 1H, -CH₂- from interior dendrimers) 8.38-8.45 (br.d, 1H, NH, from interior amide protons), and 8.52-8.59 (br.d, 1H, NH, from interior amide protons) ppm as seen in the ¹H NMR spectra of G4-NH₂-NHPDP. Data indicates the presence of thiopyridine (PDP) groups in the G4-NH₂-NHPDP dendrimer. These results are consistent with ¹³C NMR data, further affirmed by DSC analysis of the G4-NH-PDP. The G4-NH₂ dendrimer showed a T_g at -28 °C, which is in good agreement with previously reported values. G4-NH₂-NH-PDP exhibited T_g at 21.4°C and an endotherm at 109.6°C (Figure 10). The difference in the T_g values between G4-NH₂ and G4-NH₂-NH-PDP can be attributed to the PDP groups covalently bound to the dendrimer. The endotherm observed in case of G4-NH₂-NH-PDP conjugate further confirms successful modification of dendrimer with PDP functionalities, which is consistent with previous reported results. The G4-NH₂-NHPDP conjugate equipped with PDPcrosslinkers was used to fabricate dendrimer-PEG hydrogel with 8-arm-PEG-SH (G4-NH₂-NHPDP-SSPEG). The partial modification of primary amines of G4-NH₂ dendrimer resulting in formation of G4-NH₂-

NH-PDP was carried out to enable the linking of PEG chains to the dendrimer by formation of disulfide bonds.

Figure 10 shows the DSC thermogram of G4-NH₂-NH-PDP shows the T_g at 21.4 °C and an endotherm at 109.6 °C. The increase in T_g to 21.4 °C from -28 °C indicattesmodification of dendrimer with PDP groups.

Hydrogel formation

In-situ forming hydrogels with disulfide crosslinks were investigated for intravaginal amoxicillin delivery. These hydrogels were designed for local delivery of antibacterial agents to treat the ascending genital infections. Hydrogels composed of 3, 6 and 10 % w/v of the polymers were formed by mixing the solutions of G4-NH₂-NH-PDP and 8-arm PEG-SH, resulting in covalent disulfide crosslinks arising from the interaction of thiol groups of the PEG-SH with the thiopyridine functionalities present on the dendrimer surface (G4-NH₂-NH-PDP) (Table 4). The hydrogel results from intermolecular crosslinking as shown in Scheme 15. For the formation of hydrogels, the crosslinking agent (G4-NH₂-NH-PDP) was used in an excess of molar ratio (in terms of the functional groups) relative to PEG-SH (Table 4). The hydrogels were formed in 10-30 seconds of mixing the dendrimer conjugate and PEG-SH solutions as seen from the inverted tube method, and obtained gels were not pourable (Figure 11). Higher polymers concentration resulted in increase of the rate of gel formation

Figure 11 shows the *in-situ* forming hydrogel by crosslinking of G4-NH₂-NH-PDP with 8-arm-PEG-SH. The gel was formed by reaction of 'PDP' groups of G4-NH₂-NH-PDP with 8-arm-PEG-SH (1) and (2) hydrogel (1) physically entrapping blue dextran. (Table 4). The rapid formation of hydrogels with the increased concentration of polymers might be due to rapid creation of intense crosslinking networks, reducing the time for gelation. For example 10% hydrogel formed in 10 seconds, while formatation of 3% hydrogel takes 30 seconds. Hydrogels appeared to be transparent, with uniform surface. The hydrogels were designed to facilitate linking of PEG-SH chains to the partially modified G4-NH₂-NH-PDP dendrimer. The linking of PEG chains by disulfide bonds was expected to eliminate cytotoxicity of the primary amine terminated dendrimer. Pegylated dendrimers have been shown to be biocompatible

Table 4 shows hydrogel compositions and stoichiometric ratio between thiopyridine and thiol groups

% of Hydrogel	Hydrogel volume	Weight of polymer and ratio (1:1)	Stoichiometric ratio of thiopyridine groups to thiol groups	Gelation Time (s)	Total Polymer content
3%	200 μ L	G4-NH ₂ -NHPDP(3mg) +PEG-SH(3 mg)(1:1)	(2:1)	30	3%
6%	200 μ L	G4-NH ₂ -NH-PDP(3mg) +PEG-SH(3 mg)(1:1)	(2:1)	20	6%
10%	200 μ L	G4-NH ₂ -NH-PDP(3mg) +PEG-SH(3 mg)(1:1)	(2:1)	10	10%

and the *in-vivo* studies, discussed herein, show that the gels were well tolerable without any toxic effects.

Morphology of the hydrogel

Scanning electron microscopy (SEM) experiments were performed to study the surface morphology of dendrimer-PEG hydrogel (Figure 12). SEM micrographs of critical point dried gels show a uniform dense structure with striations. The SEM experiments were performed on a dehydrated sample that exhibited significant reduction in volume compared to the hydrated state. It is likely that the water hydrated dendrimer-PEG hydrogel adopts a dense structure with regular cross linking network throughout the gel. The cross section of the hydrogels was investigated by crosslinking the G4-NH₂-FITC-NHPDP and 8-arm PEG-SH. The cross section observed under the

confocal microscopy shows an isotropic hydrogel that exhibits a classic uniform morphology with pores seen in Figure 13. A characteristic change in morphology based on changes in polymer content in the hydrogel was observed (Figure 13). The 3% hydrogel does not form a dense crosslinked network as seen for the 6 and 10 % gels. By introducing the different concentration PEG and dendrimer in the hydrogels, the porosity of the network changed, pore size is gradually decreased by increasing the concentration of polymer. These results suggest that dehydration of gels for SEM leads to artifact in the highly water-saturated gels, their morphology can be better viewed by cryo-sectioning the gels with the presence of fluorescein isothiocyanate (FITC).

Figure 12 shows the SEM images of dendrimer G4-NH₂-NHPDP crosslinked with 8-PEG-SH gel (Figure 12A) 200 μ (Figure 12B) 50 μ (Figure 12C) 20 μ . These gels were dehydrated by lyophilization.

Figure 13 shows hydrogel labeled with FITC to demonstrate the pore structure of the gel. By introducing the different concentration of polymer in the hydrogels, crosslinking density gradually increased by increasing the concentration of polymer. 3% hydrogel (Figure 13A), 6% hydrogel (Figure 13B) 10% hydrogel (Figure 13C) shows the cross linking net work changes with increasing polymer concentration, scale bar represents 50 μ .

Effect of formulation additives

The G4-NH₂-NHPDP and 8-arm-PEG-SH crosslinked hydrogels were formulated with glycerin (5 %, v/v), PVP (4 %, w/w) and PEG 600 (5 %, v/v). The vaginal musoca is moist and at any given time the volume of the vaginal fluid is less than 1 mL and there is a possibility of fluid being reabsorbed. The studied hydrogels were placed in a vaginal environment with relatively low water content. The formulation additives were incorporated in the hydrogel to prevent it from becoming brittle and dehydrated. Glycerin and PEG 600 was incorporated in the hydrogels since they act as humectant and help maintain gels in plasticized supple form. The humectant properties of glycerin and PEG 600 are well known. PVP was incorporated in the gel to provide mucoadhesive property and to increase viscosity of the gel forming solutions to prevent their leak outside the cavity during instillation and formation of crosslinked hydrogels. Use of PVP in vaginal gels for enhancing the mucoadhesive properties is well known. The optimal

concentration of the additives to prevent brittleness and increase retention time on vaginal mucosa for prolonged periods of time was found to be glycerin (5 %, v/v), PVP (4 %, w/w) and PEG 600 (5 %, v/v).

Thermal analysis

5 The thermal behavior of the dendrimer-PEG hydrogel components and the hydrogel was investigated by DSC analysis. The DSC thermograms of dendrimer-PEG hydrogels, G4-NH₂-NHPDP, 8-arm-PEG-SH, are shown in Figure 14A. 8-arm-PEG-SH exhibits an endotherm at 51.7 °C (Figure 14A (e)). The T_g of G4-NH₂ dendrimer was -28 °C and G4-NH₂-NHPDP showed the presence of an endothermic peak at 109.3 °C with
10 a T_g at 21.4 °C (Figure 14A (a)). The DSC profiles show that after dendrimer was converted to its PDP derivative, the T_g shifted, indicating an altered polymer microstructure. When comparing the profiles of G4-NH₂-NHPDP and 8-arm-PEG-SH, the crosslinking of the two polymers clearly produced a new material having a microstructure different from either of its two components. In case of hydrogels the T_g
15 was found to be higher than that observed for the G4-NH₂-NHPDP, e.g. the 3 % hydrogel exhibited at T_g of 34.7 °C and the 10% and 6% hydrogels displayed a T_g at 35.3 °C. The 3, 6 and 10 % hydrogels exhibited the endotherms at 39.2, 45.9 and 46.8 °C respectively which was lower than that observed for the 8-arm PEG-SH (51.7 °C). The intermolecular crosslinking of the polymer chains results in reduced mobility
20 (resulting in increased T_g), and these polymer chains cannot reorient to form a highly ordered crystalline structure (lowered melting point). The addition of glycerin, PVP and PEG 600 lowered the endotherms of 3 %, 6 % and 10 % hydrogels when compared to hydrogels without additives (Figure 14B). The hydrogels with PEG 600 showed a characteristic endotherm between 15.6 to 14.3 °C in addition to the endotherm (37.9 to
25 38.9 °C) corresponding to 8-arm PEG-SH (Figure 14B). The structural characteristics of both PEG hydrogel and dendrimer are seen in the dendrimer-PEG hydrogels.

Figure 14 showed the DSC thermograms for the 3, 6 and 10 % dendrimer-PEG hydrogels. (Figure 14A) Hydrogels without formulation additives (absence of glycerin, PVP and PEG600), The 8-arm PEG-SH (e) shows an endotherm at 51.7 °C, which is
30 lowered upon crosslinking with G4-NH₂-NH-PDP as seen in curves (b), (c) and (d) for 3, 6 and 10% hydrogels respectively (Figure 14B) Hydrogels with formulation additives

(glycerin, PVP and PEG 600). In addition to the endotherms corresponding to 8armPEG-SH (37.9 to 38.9 °C) in hydrogels, an endotherm for PEG 600 is seen between 15.6 to 14.3 °C.

Degradation of hydrogels

5 The hydrogels investigated in the current study are biodegradable in nature. Their degradation was evaluated in simulated vaginal fluid and buffer since they were designed for intravaginal and intracervical application. The disulfide crosslinks in the hydrogels were used to lead to its slow degradation and easy self washout from the body orifice. The female reproductive tract secretions are rich in glutathione and
10 glutathione transferase. GSH levels range between 28-284 mg in human cervical secretions. The disulfide linkages or crosslinks present in the gel are cleavable in presence of GSH. Thiol-disulfide exchange is a chemical reaction in which a thiolate group S^- attacks one of the sulfur atom of a disulfide bond $-S-S-$. Under basic or mild acidic conditions GSH is known to act as thiolate moiety and it gets oxidized while
15 cleaving disulfide bonds. These reactions are facilitated at higher basic pH. Since vaginal pH is low (3.8-4.5) it was expected that disulfide bonds present in the hydrogels would undergo a slow degradation in vaginal environment. The *in-vitro* experiments showed that hydrogels were stable up to 3 days upon exposure to GSH solution at a pH 4.0, and in simulated vaginal fluid, and did not show any signs of degradation as seen in
20 Figure 15. After 72 hours the gels started to degrade and erode in both the solutions. This is consistent with the *in-vivo* degradation pattern, which is discussed in the subsequent sections. The chromatograms (what kind of SEC or HPLC) of the GSH solutions containing hydrogels did not show generation of any peaks until 50 hours (data not shown). After 65 hours the presence of few small peaks could be seen, which
25 is attributed to breakdown of the gel into the smaller polymer components. The slow degradation of hydrogel is expected over time and would release the polymer components. The G4-NH₂ dendrimers exhibit antibacterial activity by altering bacterial cell walls. The G4-NH₂-NHPDP dendrimer is present in hydrogels has unmodified amine groups and was therefore expected to act as antibacterial agents. The antibacterial
30 activity of partially pegylated amine terminated dendrimers is well known. Hence the hydrogels of the present study exhibit dual antibacterial mechanism attributed to the

slow release of the amoxicillin followed by release of partially amine terminated G4 dendrimer.

Figure 15 shows the dendrimer-PEG hydrogels exposed to the GSH solutions at pH 4.0 are stable up to 72 hours. Figure 15A shows the intact gel after 72 hours of treatment with GSH solution at pH 4, Figure 15B the gel in simulated vaginal fluid with GSH.

Degree of swelling

The degree of hydrogels swelling was measured gravimetrically, calculating the equilibrium swelling obtained by comparing the ratios of the weights of the dry and water-swollen hydrogels over the time course. The degree of hydrogels swelling influences the pore size which affects the mechanical strength of the hydrogels and the drug release properties. The 3% hydrogel showed higher swelling when compared to 6% and 10% gels. The equilibrium swelling state was reached for the 3, 6 and 10% hydrogels at 10, 7 and 6 hours respectively. The observed pattern is attributed to the increased cross-linking density in hydrogels containing higher polymer concentration. In the confocal microscopy studies it was observed that the crosslinking density in 3% hydrogel was low as compared to the 6 and 10% and the swelling results in good agreement with this observation

Drug loading efficiency

Amoxicillin was physically entrapped in the *in-situ* forming gels. Amoxicillin was dissolved in the 8-arm PEG solution and mixed with the G4-NH₂-NHPDP solution to form the gel. The theoretical amounts of drug used for entrapment were 0.50 mg in 200 μ L of hydrogel formulation (3, 6 and 10%). The drug extracts from the hydrogel were quantified by reverse phase (RP) HPLC analysis with UV detection at a wavelength of 229 nm using water: acetonitrile as mobile phase. The amount of drug entrapped in the 3, 6 and 10 % w/v hydrogels was 52, 45 and 41% respectively. The 3% gels showed relatively higher drug loading efficiency compared to the 6 and 10% gels. This difference could be attributed to higher crosslinking density in gels with higher polymer concentration and reduced pores size.

In vitro drug release

The in vitro drug release profiles from three different hydrogel formulations were studied using Franz diffusion cells. The plot of cumulative amount of drug released (mg/cm^2) as a function of time (hours) from the three different types of hydrogels is presented in Figure 16A. The drug release plot shows that amoxicillin release was sustained for 260 hours with a release of 72 %, 63 %, 51 % from 3 %, 6 % and 10 % hydrogels respectively. A relatively slower drug release was observed from 10 % hydrogel when compared to 3 % hydrogel. This result is consistent with the lower swelling of the 10 % hydrogel, which is attributed to the high crosslinking density in polymer network obtained for higher polymer concentrations, leading to smaller pores size. The plot of percentage drug released verses time was used to determine the release mechanism (Figure 16B). The data (first 60 % of the amount release) was fitted to explain the release mechanism and pattern using the Peppas equation as follows:

$$\frac{M_t}{M_\infty} = kt^n \quad (\text{eq. I})$$

Where M_t/M_∞ is the fraction of drug released, ' k ' is a kinetic (proportionality) constant dependent on the system, ' t ' is the time period for release, and ' n ' is the diffusion exponent indicative of the release mechanism for matrices of various shapes and swelling patterns. In the case of Fickian release, the exponent ' n ' has a limiting value of 0.50, 0.45, and 0.43 from slabs, cylinders, and spheres, respectively. The values of ' n ' and ' k ' are inversely related, and a higher value of ' k ' suggests a burst release of drug from matrix. The values of diffusional exponent are shown in Table 5. At higher polymer concentration (10 %) the drug release mechanism seems to approach the Fickian diffusion with $n = 0.49$, while the lower polymer concentrations exhibit non Fickian release mechanism.

Table 5. Determination of flux, diffusional exponent (n) and permeability coefficient for hydrogels

% w/v Hydrogels	Flux (J) ($\text{mg cm}^{-2} \text{s}^{-1}$) x 10^{-7}	Diffusion exponent (n)	Permeability Coefficient (P)
--------------------	--	----------------------------------	------------------------------------

			(cm. h ⁻¹) x 10 ⁻⁶
3%	4.72	0.20	1.81
6 %	4.16	0.25	1.85
10 %	3.88	0.49	1.89

Permeation parameters were obtained from the cumulative amounts of drug permeated (mg cm⁻²) as a function of time (hours). The steady state flux (J) representing the absorption rate per unit area was determined from the slope of the linear portion of the plots. In all experiments same number of data points was taken to calculate the steady state flux. The permeability constant (P) was calculated according to Fick's first law of diffusion, based on the steady state flux and the applied drug concentration (C_i) on the donor side. The permeability coefficients were deduced, dividing the flux by the initial drug load (C_i) as shown in equation:

10

$$J = \frac{dQ}{dt.A} \quad (\text{eq. II})$$

$$P = \frac{J}{C_i} \quad (\text{eq. III})$$

Figure 16 (A) shows a cumulative amount of amoxicillin released with respect to time (hours) across per cm² area for 3, 6 and 10% hydrogels and Figure 16(B) shows a cumulative amount of amoxicillin released with respect to time. The release mechanism was found to be non-fickian for 3 and 6% hydrogels while for 10% hydrogels it approached fickian diffusion.

The flux, diffusional exponent and permeability coefficient are collected in Table 5. The flux and permeability was found to decrease with the increase in the polymer concentration. This is due to the increased crosslinking density and lower swelling of the hydrogels at higher polymer content. Observed result is consistent with the lower drug release rate at higher polymer concentrations. At higher PEG concentrations (20-45%w/v) the PEG hydrogels exhibit 10 folds higher flux as compared to the dendrimer-

20

PEG hydrogels. This indicates that the PEG-dendrimer hydrogel forms a tighter network in comparison to the PEG crosslinked hydrogels. Investigated dendrimer-PEG hydrogels are therefore expected to sustain the drug release efficiently.

In-vivo testing of hydrogel formulations in guinea pig model

5 Vaginal distribution, retention, biodegradation and tolerability of gels are important parameters to achieve sustained residence in the body cavity. Discussed intravaginal gels were developed to treat the ascending genital infections during pregnancy. Since the gel is *in-situ* forming, permeation and transport of the gel (PEG and G4-NH₂-NH-PDP polymers) across the fetal membranes into the fetus was
10 investigated. The 10% w/v gels were used for *in-vivo* testing as these were found to sustain the drug release for longer times as compared to 3 and 6 % gels. The volume of the gel for intravaginal application was determined by injecting the samples 100 µL to 500 µL. The ideal volume for application was found to be 200 µL and any volume above that resulted in leaking of the gel material outside the vagina. Similar volumes for
15 intravaginal gels in guinea pigs were reported. The hydrogels without formulation additives exhibited short residence times and were leaked out as brittle particles after 24 hours. The gels with formulation additives (glycerin, PVP and PEG 600) were retained in the cervicovaginal region at least up to 72 hours, the end point used in this protocol. The incorporation of PVP in the gels provides the mucoadhesive effect. Figure
20 17 shows the presence of gel after 5, 12, 24 and 72 hours of application. The visual examination revealed that 200 µL gel volume was sufficient to cover the cervicovaginal region. The gel could be seen in the cervicovaginal region in the early hours after application (5 and 12 hours) and the gel was retained in this region even at later time points (24 to 72 hours). The gel was found to slowly degrade with change in morphology
25 and the eroded material was seen on the fetal membranes of the pups positioned very close to the cervix (Figure 18A). The gel was not seen on any other pup (fetus) positioned away from the cervix. It is interesting to note that the gels with disulfide bonds exhibited a slow degradation *in-vivo* in vaginal environment. This observation is similar to the *in-vitro* degradation study in simulated vaginal fluid with GSH at pH 4. The
30 gel components remained on the surface of the fetal membranes without transport across the membranes (Figures 18A and 18B). The G4-NH₂-NHPDP dendrimer

conjugate released due to degradation of the gel is not seen across the fetal membrane. The pups did not show traces of gel on fur after removal of the fetal membranes (Figure 18C) indicating that the gel does not cross across the fetal membranes and can be used for the selective local treatment of the pregnant mother without transfer to the fetus. The

5 previous *ex-vivo* studies in human fetal membranes showed that the transport of FITC labeled G4-NH₂ dendrimer is restricted across the membrane. Presented *in-vivo* results combined with the previous *ex-vivo* studies indicate that the hydrogels formed using the G4-NH₂-NH-PDP and 8-arm-PEG- SH do not cross the fetal membranes and could be used for the selective local treatment of pregnant woman without transfer to the fetus.

10 The pH of vagina was tested after 5 hours, 12 hours and 24 hours of hydrogels application, using the swabs. No change in pH was observed after application of the gel. The investigated hydrogels were formed rapidly *in-situ* and they absorb buffer in which they were formed without affecting pH of vagina. None of the animals showed any discomfort after application of gel, none of the animals aborted in 72 hours. The visual

15 examination of the vaginal tissues showed no signs of edema and irritation and the gels were well tolerated by the animals.

Figure 17 shows the intravaginal and intracervical application of *in-situ* forming dendrimer-PEG hydrogels in the pregnant guinea pigs. The green arrows mark the presence of hydrogel on the tissue (Figure 17A) day 1: hydrogel after 5 hours of

20 application, (Figure 17B) day 1: hydrogel after 12 hours of application (Figure 17C) day 2: 24 hours after hydrogel application (Figure 17D) day 3: 72 hours after hydrogel application, where 'C' = cervix, V= vaginal cavity, U = uterus with pups. The hydrogel is retained in the cervix and vaginal cavity for 2 days and on day 3 it's seen largely in the vaginal cavity of pregnant guinea pigs.

25 Figure 18 shows the dendrimer-PEG hydrogels after intravaginal and intracervical application in pregnant guinea pigs do not cross the fetal membrane and enter into the gestational (sac) cavity. (Figure 18A) day 3: hydrogel seen on the fetal membrane of the pup positioned close to the cervix, the green arrows mark the presence of fetal membrane on the pup, the black arrows show the presence of gel

30 outside of the fetal membrane (Figure 18B) the pup covered in fetal membrane with

hydrogel on top of the fetal membrane (Figure 18C) the pup after removal of the fetal membrane showing no signs of hydrogel on the fur or inside the fetal membrane.

The histological evaluation of the uterus and cervicovaginal epithelial layer shows that the cell layer was not disrupted and no morphological changes were observed in the cells after 24 and 72 hours treatment with hydrogels (Figure 19). The epithelial layer of the control tissue and the 24 and 72 hours tissue with hydrogel treatment appear comparable. There are no signs of sloughing of the epithelial cells into the lumen, inflammation or edema of the epithelium. The submucosal tissues after hydrogel treatment (24 and 72 hours) did not show any signs of necrosis or massive infiltration of the inflammatory cells. The cervical tissues show presence of the superficial mucous cell layer and after treatment with hydrogels the tissues do not show any signs of sloughing of the superficial mucous layer.

Figure 19 shows the hemotoxylin and eosin stained histological sections of uterus (U), upper cervix (Ucx) and cervix (Cx) of guinea pig treated with the hydrogels for 24 hours and 72 hours (n=3 per group). The epithelial cell lining in all the tissues is intact and does not show any signs of inflammation and edema. The submucosa of hydrogel treated cervix after 24 and 72 hours is comparable to the control. None of the tissues showed any signs of epithelial sloughing, necrosis in the submucosa or massive infiltration of inflammatory cells. EP = epithelial cells, SE = subepithelium, SM = submucosa, M = muscular layer EGC = endometrial gland cells, UC= uterus control, U24 and 72 hours = hydrogel treated uterus 24 and 74 hours, UCxC = control upper cervix, UCx24 and 72 hours = hydrogel treated upper cervix 24 and 74 hours, Cx-C = cervix control, Cx24 and 72 hours = hydrogel treated cervix 24 and 74 hours (40x magnification).

Figure 20 shows the confocal images of the cervical region of pregnant guinea pigs treated with hydrogels for 24 and 72 hours. The *in-situ* forming hydrogel comprising FITC-G4-NH-PDP crosslinked with 8-arm PEG-SH was applied to the cervicovaginal region. The hydrogel (green color) is seen on the surface of the mucosal layer (red color). The confocal images after 24 and 72 hours confirm the presence of the gel on the tissue surface. The nuclei for all cells are stained blue with DAPI. There is no sign of

the degraded gel into the subepithelial or submucosal layers. EP=epithelial layer, SE= subepithelial layer, ML= mucified epithelial layer.

No signs of atrophy of the epithelial cell layer or the superficial mucous layer were observed after the hydrogel treatment for 72 hours. The animals treated with hydrogels
5 did not show any signs of thickening of the mucous cell layer when compared to the control animal (Figure 19). These results suggested that the animals were tolerant to the gels and no untoward reaction was exhibited. The residence of the gel on the mucified epithelial cells of the cervicovaginal region was further confirmed from the histological evaluation of immunohistofluorescence images (Figure 20). The fluorescent
10 gel comprising G4-NH₂-FITC-NHPDP crosslinked with 8-arm PEG-SH was used for this investigation and the cross sections of the vagina and cervix show the presence of fluorescent gel (green color) on the mucified epithelial layer (red) marked positive with anticytokeratin. The presence of gel is apparent at time points 24 and 72 hours respectively. The immunohistofluorescence images of the *fetal* membrane and the
15 uterus at 72 hours do not show the presence of the gel across these tissues (Figure 21), as seen by the absence of the fluorescent green. These results confirm that the gel components are primarily located on the epithelial surface of cervical region and do not cross into deeper tissue. The ascending bacterial infection causes chorioamnionitis which is associated with development of cerebral palsy, a motor disorder in children due
20 to stimulation of proinflammatory cytokines causing white matter damage and fetal brain injury. The local delivery of antibiotics in the cervicovaginal region is preferred therapy for the treatment of these infections.

Figure 21 shows the confocal images of the fetal membrane and uterus of guinea pigs treated with hydrogels for 72 hours. The *in-situ* forming hydrogel comprising G4-
25 NH₂-FITC-NHPDP crosslinked with 8-arm PEG-SH was applied to the cervicovaginal region. The cross section of the uterus and the fetal membrane do not show presence of hydrogel or degraded hydrogel across the tissue.

The hydrogels exhibited long residence times of at least 72 hours and were very well tolerated by the tissues. The hydrogels exhibit dual antibacterial activity by the
30 release of amoxicillin followed by the release of partially modified amine terminated dendrimer due to degradation of the hydrogels. Dendrimers with amine terminations

exhibit antibacterial activity. The covalent linking of the dendrimer to the PEG overcomes the cytotoxicity associated with the dendrimer which is well documented. These findings are significant as the dendrimers in the size range 5 to 6 nm do not cross the human fetal membranes which separate the extra-amniotic cavity and the fetus, and could be used for the local intravaginal delivery of pregnant woman. The overall findings of the present study suggest that the proposed hydrogels offer an excellent degradable drug delivery system which exhibits sustained local delivery of the antibacterial agents intravaginally to the pregnant mother without transfer to the fetus.

Conclusions

Drug therapy during pregnancy is challenging, and effective ways to selectively treat the pregnant woman without affecting the fetus are always desired. Topical delivery of therapeutic agents is favored to treat ascending genital infections in pregnant women. Biodegradable *in-situ* forming hydrogels obtained by crosslinking of G4-NH₂-FITC-NHPDP dendrimer and 8-arm PEG via formation of disulfide bridges is described. Amoxicillin release from these hydrogels (3, 6 and 10% w/v) is sustained for more than 240 hours and the release approaches Fickian diffusion pattern from the 10 % w/v hydrogels. The *in-vivo* evaluation of the hydrogels using pregnant guinea pig model shows that gels are very well tolerated by the animals and no signs of change in vaginal pH and erythema are observed up to 72 hours. The gel volume of 100-200 μ l was found to sufficiently cover the entire cervicovaginal region as seen by visual examination. The gels exhibited a slow degradation *in-vivo* at the vaginal pH and the degraded gel was retained in the maternal tissues without transfer across the fetal membranes. These results were confirmed by visual and immunohistofluorescence images of tissues which showed that the gel is largely retained in the superficial mucified epithelial cells. The histopathological evaluation of the vaginal and the cervical tissues showed absence of epithelial cell edema, necrosis and infiltration of inflammatory cells in the subepithelial and submucosal tissues. There were no signs of sloughing of the superficial epithelial cell layer after application of the hydrogels. The morphology of the tissues treated with the hydrogels for 24 and 72 hours was comparable to that of the control tissues. The overall results confirm that the gels were very well tolerated by the animals and none of the animals aborted in 72 hours after application of gels. The *in-situ* forming hydrogels

of the present invention offer therapeutic approaches to provide localized selective treatment of the pregnant woman with ascending genital infections without adverse effects to the fetus.

Throughout this application, author and year and patents by number reference
5 various publications, including United States patents. Full citations for the publications are listed below.

The invention has been described in an illustrative manner, and it is to be
10 understood that the terminology, which has been used herein, is intended to be in the nature of words of description rather than of limitation.

Obviously, many modifications and variations of the present invention are possible in light of the above teachings. It is, therefore, to be understood that within the scope of the described invention, the invention can be practiced otherwise than as
15 specifically described.

References:

1. Svenson, S.; Tomalia, D. A., Dendrimers in biomedical applications--reflections on the field. *Adv Drug Deliv Rev* 2005, 57, (15), 2106-29.
2. Goodwin, A. P.; Lam, S. S.; Frechet, J. M. J., Rapid, Efficient Synthesis of Heterobifunctional Biodegradable Dendrimers. *Journal of the American Chemical Society* 2007, 129, (22), 6994-6995.
3. Menjoge, A. R.; Kannan, R. M.; Tomalia, D. A., Dendrimer-based drug and imaging conjugates: design considerations for nanomedical applications. *Drug Discov Today*. 2010, 15, 171-185
- 10 4. Okuda, T.; Kawakami, S.; Maeie, T.; Niidome, T.; Yamashita, F.; Hashida, M., Biodistribution characteristics of amino acid dendrimers and their PEGylated derivatives after intravenous administration. *J Control Release* 2006, 114, (1), 69-77.
5. Tomalia, D. A., Reyna, L.A., Svenson, S., Dendrimers as multi-purpose nanodevices for oncology drug delivery and diagnostic imaging. *Biochemical Society Transactions* 2007, 35, 61- 67.
- 15 6. Lee, C. C.; MacKay, J. A.; Frechet, J. M.; Szoka, F. C., Designing dendrimers for biological applications. *Nat Biotechnol* 2005, 23, (12), 1517-26.
7. Sato, N.; Kobayashi, H.; Saga, T.; Nakamoto, Y.; Ishimori, T.; Togashi, K.; Fujibayashi, Y.; Konishi, J.; Brechbiel, M. W., Tumor targeting and imaging of intraperitoneal tumors by use of antisense oligo-DNA complexed with dendrimers and/or avidin in mice. *Clin Cancer Res* 2001, 7, (11), 3606-12.
- 20 8. Han, H. J.; Kannan, R. M.; Sunxi, W.; Guangzhao, M.; Juan Pedro, K.; Roberto, R., Multifunctional Dendrimer-Templated Antibody Presentation on Biosensor Surfaces for Improved Biomarker Detection. *Adv. Funct. Mater.* 2010, 20, 409-421.
- 25 9. Navath, R. S.; Kurtoglu, Y. E.; Wang, B.; Kannan, S.; Romero, R.; Kannan, R. M., Dendrimer-drug conjugates for tailored intracellular drug release based on glutathione levels. *Bioconjug Chem* 2008, 19, (12), 2446-55.
10. Antoni, P.; Hed, Y.; Nordberg, A.; Nystrom, D.; von Holst, H.; Hult, A.; Malkoch, M., Bifunctional dendrimers: from robust synthesis and accelerated one-pot postfunctionalization strategy to potential applications. *Angew Chem Int Ed Engl* 2009, 30 48, (12), 2126-30.

11. Kolhe, P.; Misra, E.; Kannan, R. M.; Kannan, S.; Lieh-Lai, M., Drug complexation, in vitro release and cellular entry of dendrimers and hyperbranched polymers. *Int J Pharm* 2003, 259, (1-2), 143-60.
12. Kurtoglu, Y. E.; Navath, R. S.; Wang, B.; Kannan, S.; Romero, R.; Kannan, R. M., Poly(amidoamine) dendrimer-drug conjugates with disulfide linkages for intracellular drug delivery. *Biomaterials* 2009, 30, (11), 2112-21.
13. Khandare, J.; Kolhe, P.; Pillai, O.; Kannan, S.; Lieh-Lai, M.; Kannan, R. M., Synthesis, cellular transport, and activity of polyamidoamine dendrimer-methylprednisolone conjugates. *Bioconjug Chem* 2005, 16, (2), 330-7.
- 10 14. Gillies, E. R.; Frechet, J. M. J., Designing Macromolecules for Therapeutic Applications: Polyester DendrimerPoly(ethylene oxide) "Bow-Tie" Hybrids with Tunable Molecular Weight and Architecture. *Journal of the American Chemical Society* 2002, 124, (47), 14137-14146.
- 15 15. Sivanandan, K.; Vutukuri, D.; Thayumanavan, S., Functional group diversity in dendrimers. *Org Lett* 2002, 4, (21), 3751-3.
16. Fischer-Durand, N.; Salmain, M.; Rudolf, B.; Juge, L.; Guerineau, V.; Laprevote, O.; Vessieres, A.; Jaouen, G., Design of a New Multifunctionalized PAMAM Dendrimer with Hydrazide-Terminated Spacer Arm Suitable for Metal-Carbonyl Multilabeling of Aldehyde-Containing Molecules. *Macromolecules* 2007, 40, (24), 8568-8575.
- 20 17. Kobayashi, H.; Kawamoto, S.; Jo, S. K.; Sato, N.; Saga, T.; Hiraga, A.; Konishi, J.; Hu, S.; Togashi, K.; Brechbiel, M. W.; Star, R. A., Renal tubular damage detected by dynamic micro-MRI with a dendrimer-based magnetic resonance contrast agent. *Kidney Int* 2002, 61, (6), 1980-1985.
18. Kobayashi, H.; Saga, T.; Kawamoto, S.; Sato, N.; Hiraga, A.; Ishimori, T.; Konishi, J.; Togashi, K.; Brechbiel, M. W., Dynamic micro-magnetic resonance imaging of liver micrometastasis in mice with a novel liver macromolecular magnetic resonance contrast agent DAB-Am64-(1B4M-Gd)(64). *Cancer Res* 2001, 61, (13), 4966-4970.
- 25 19. Saad, M.; Garbuzenko, O. B.; Ber, E.; Chandna, P.; Khandare, J. J.; Pozharov, V. P.; Minko, T., Receptor targeted polymers, dendrimers, liposomes: which nanocarrier is the most efficient for tumor-specific treatment and imaging? *J Control Release* 2008, 130, (2), 107-14.
- 30

20. Fuchs, S.; Kapp, T.; Otto, H.; Schoneberg, T.; Franke, P.; Gust, R.; Schluter, A. D., A surface-modified dendrimer set for potential application as drug delivery vehicles: synthesis, in vitro toxicity, and intracellular localization. *Chemistry* 2004, 10, (5), 1167-92.
- 5 21. Kitchens, K. M.; El-Sayed, M. E.; Ghandehari, H., Transepithelial and endothelial transport of poly (amidoamine) dendrimers. *Adv Drug Deliv Rev* 2005, 57, (15), 2163-76.
22. Patil, M. L.; Zhang, M.; Taratula, O.; Garbuzenko, O. B.; He, H.; Minko, T., Internally cationic polyamidoamine PAMAM-OH dendrimers for siRNA delivery: effect of
10 the degree of quaternization and cancer targeting. *Biomacromolecules* 2009, 10, (2), 258-66.
23. Chow, H.-F.; Leung, C.-F.; Xi, L.; Lau, L. W. M., Synthesis and Characterization of Outer Sphere~Outer Sphere Connected Organoplatinum Dendritic Networks from Surface-Difunctionalized and Surface-Trifunctionalized Dendritic Monomers.
15 *Macromolecules* 2004, 37, (10), 3595-3605.
24. Kaminskas, L. M.; Boyd, B. J.; Karellas, P.; Krippner, G. Y.; Lessene, R.; Kelly, B.; Porter, C. J., The impact of molecular weight and PEG chain length on the systemic pharmacokinetics of PEGylated poly L-lysine dendrimers. *Mol Pharm* 2008, 5, (3), 449-63.
- 20 25. Kono, K.; Akiyama, H.; Takahashi, T.; Takagishi, T.; Harada, A., Transfection activity of polyamidoamine dendrimers having hydrophobic amino acid residues in the periphery. *Bioconjug Chem* 2005, 16, (1), 208-14.
26. Majoros, I. J.; Keszler, B.; Woehler, S.; Bull, T.; Baker, J. R., Acetylation of Poly(amidoamine) Dendrimers. *Macromolecules* 2003, 36, (15), 5526-5529.
- 25 27. Majoros, I. J.; Thomas, T. P.; Mehta, C. B.; Baker, J. R., Jr., Poly(amidoamine) dendrimer-based multifunctional engineered nanodevice for cancer therapy. *J Med Chem* 2005, 48, (19), 5892-9.
28. Waite, C. L.; Sparks, S. M.; Uhrich, K. E.; Roth, C. M., Acetylation of PAMAM dendrimers for cellular delivery of siRNA. *BMC Biotechnol* 2009, 9, 38.

29. Qi, R.; Gao, Y.; Tang, Y.; He, R. R.; Liu, T. L.; He, Y.; Sun, S.; Li, B. Y.; Li, Y. B.; Liu, G., PEG-conjugated PAMAM Dendrimers Mediate Efficient Intramuscular Gene Expression. *Aaps J* 2009.
30. Kolhatkar, R. B.; Kitchens, K. M.; Swaan, P. W.; Ghandehari, H., Surface
5 acetylation of polyamidoamine (PAMAM) dendrimers decreases cytotoxicity while maintaining membrane permeability. *Bioconjug Chem* 2007, 18, (6), 2054-60.
31. Antoni, P.; Nystrom, D.; Hawker, C. J.; Hult, A.; Malkoch, M., A chemoselective approach for the accelerated synthesis of well-defined dendritic architectures. *Chem Commun (Camb)* 2007, (22), 2249-51.
- 10 32. Mulders, S. J. E.; Brouwer, A. J.; van der Meer, P. G. J.; Liskamp, R. M. J., Synthesis of a novel amino acid based dendrimer. *Tetrahedron Letters* 1997, 38, (4), 631-634.
33. Goyal, P.; Yoon, K.; Weck, M., Multifunctionalization of dendrimers through orthogonal transformations. *Chemistry* 2007, 13, (31), 8801-10.
- 15 34. Steffensen, M. B., Simanek, E.E., Synthesis and manipulation of orthogonally protected dendrimers: building blocks for library synthesis. *Angew. Chem.* 2004, 116, 5290 –5292.
35. Brauge, L.; Magro, G.; Caminade, A. M.; Majoral, J. P., First divergent strategy using two AB(2) unprotected monomers for the rapid synthesis of dendrimers. *J Am*
20 *Chem Soc* 2001, 123, (27), 6698-9.
36. Oh, S.-K.; Kim, Y.-G.; Ye, H.; Crooks, R. M., Synthesis, Characterization, and Surface Immobilization of Metal Nanoparticles Encapsulated within Bifunctionalized Dendrimers. *Langmuir* 2003, 19, (24), 10420-10425.
37. Wu, P.; Malkoch, M.; Hunt, J. N.; Vestberg, R.; Kaltgrad, E.; Finn, M. G.; Fokin,
25 V. V.; Sharpless, K. B.; Hawker, C. J., Multivalent, bifunctional dendrimers prepared by click chemistry. *Chem Commun (Camb)* 2005, (46), 5775-7.
38. Lim, J., Simanek, E.E., Synthesis of water-soluble dendrimers based on melamine bearing 16 paclitaxel groups. *Organic Letters* 2008, 10, 201-204.
39. Paleos, C. M.; Tsiourvas, D.; Sideratou, Z.; Tziveleka, L., Acid- and salt-triggered
30 multifunctional poly(propylene imine) dendrimer as a prospective drug delivery system. *Biomacromolecules* 2004, 5, (2), 524-9.

40. Toli, L. P., Anderson, G.A., Smith, R.D., Brothers II, H.M., Spindler, R., Tomalia, D.A., Electrospray ionization Fourier transform ion cyclotron resonance mass spectrometric characterization of high molecular mass Starburst™ dendrimers. *International Journal of Mass Spectrometry and Ion Processes* 1997, 165-166, 405-418.
- 5 41. Woller, E. K.; Cloninger, M. J., The lectin-binding properties of six generations of mannose-functionalized dendrimers. *Org Lett* 2002, 4, (1), 7-10.
42. Duncan, R.; Izzo, L., Dendrimer biocompatibility and toxicity. *Adv Drug Deliv Rev* 2005, 57, (15), 2215-37.
43. Malik, N.; Wiwattanapatapee, R.; Klopsch, R.; Lorenz, K.; Frey, H.; Weener, J.
10 W.; Meijer, E. W.; Paulus, W.; Duncan, R., Dendrimers: relationship between structure and biocompatibility in vitro, and preliminary studies on the biodistribution of 125I-labelled polyamidoamine dendrimers in vivo. *J Control Release* 2000, 65, (1-2), 133-48.
44. Kannan, S., Kolhe, P., Kannan, R.M., Lieh-lai, M., Glibatec, M, Effect of dendrimer end functionality on the cytotoxicity and the cellular drug delivery in lung
15 epithelial cells. *Journal of Biomaterials Science: Polymers Edition* 2004, 15, 311 -330.
45. Darbre, T.; Reymond, J.-L., Peptide Dendrimers as Artificial Enzymes, Receptors, and Drug-Delivery Agents. *Accounts of Chemical Research* 2006, 39, (12), 925-934.

Table 1. Library of PAMAM dendrimers with asymmetrical peripheral end groups obtained by Amino Acid Surface Modifications











S.N o	Dendrimer generation and end group	Amino Acid	Deprotection h/ Hydrolysis	Peripheral Functionality	Structure
1	G4-PAMAM- NH ₂	Boc-Ser- OH	--	OH, NHBoc	
2	G4-PAMAM- NH ₂	Boc-Ser- OH	Boc	OH, NH ₂	
3	G4-PAMAM- NH ₂	Boc-Cys- OH	--	SH, NHBoc	
4	G4-PAMAM- NH ₂	Boc-Cys- OH	Boc	SH, NH ₂	
5	G3.5-PAMAM- COOH	H-Ser- OMe	--	OH, COOMe	
6	G3.5-PAMAM- COOH	H-Ser- OMe	Me	OH, COOH	
7	G4-PAMAM-OH	Boc-Cys- OH	--	SH, NHBoc	
8	G4-PAMAM-OH	Boc-Cys- OH	Boc	SH, NH ₂	
9	G4-PAMAM-OH	Boc-Asp- OH	--	NHBoc, COOH	
10	G4-PAMAM-OH	Boc- Cys(S-TP)- OH	--	NHBoc, S- TP	
11	G4-PAMAM-OH	Boc- Cys(S-TP)- OH	Boc	NH ₂ , S-TP	

Table 2. Molecular weight estimation of amino acid modified PAMAM dendrimers


Name of the compound	Mol. wt	No of amino acids attached	Total hetero-bi-functional peripheral groups	% Conversion	Purity of compound in %	Solubility Aqueous /DMSO
G4-PAMAM-NH-CO-Ser(OH)-NHBoc	24.5 kDa	58	116 (58+58)	91	98	DMSO soluble
G4- PAMAM-NH-CO-Ser(OH)-NH ₂	18.7 kDa*	58	116 (58+58)	91	96	H ₂ O soluble
G4- PAMAM-NH-CO-Cys(SH)-NHBoc	24.8 kDa	55	110 (55+55)	86	96	DMSO soluble
G4- PAMAM-NH-CO-Cys(SH)-NH ₂	19.3 kDa*	55	110 (55+55)	86	95	H ₂ O soluble
G3.5- PAMAM-CO-NH-Ser(OH)-COOMe	17.2 kDa	57	114 (57+57)	89	97	DMSO soluble
G3.5- PAMAM-CO-NH-Ser(OH)-COOH	15.9 kDa*	57	114 (57+57)	89	96	H ₂ O soluble
G4- PAMAM-O-CO-Cys(SH)-NH-Boc	25.0 kDa*	56	112 (64+64)	87.5	96	DMSO soluble
G4- PAMAM-O-CO-Cys(SH)-NH ₂	19.2 kDa	46	92 (46+46)	72	98%	H ₂ O soluble

G4- PAMAM-O-CO-Asp(COOH)-NH-Boc	25.7 kDa*	56	112 (56+56)	87.5	95%	DMSO soluble
G4- PAMAM-O-CO-Asp(COOH)-NH ₂	18.99 kDa	46	92 (46+46)	72	96%	H ₂ O soluble
G4- PAMAM-O-CO-Cys(S-TP)-NH-Boc	26.8 kDa	42	84 (46+46)	65.6	97%	DMSO soluble
G4- PAMAM-O-CO-Cys(S-TP)-NH ₂	25.5 kDa	38	76 (38+38)	59	95%	DMSO soluble

*Molecular weight determined by MALDI-TOF


Table 3: Particle size and zeta potential hetero-bifunctional dendrimers

Name of the sample	Sample Particle diameter (nm)	Zeta Potential (mV)
G4-PAMAM-NH ₂	4.70	+11.5
G3.5-PAMAM-COOH	4.20	-9.30
G4-PAMAM-OH	4.78	-2.10
G4-PAMAM-NH-Ser(OH)-NH ₂	5.65	-1.83
G4-PAMAM-NH-Cys(SH)-NH ₂	6.21	+4.80
G3.5-PAMAM-CO-Ser(OH)-COOH	6.56	+8.83
	6.01	3.60
G4-PAMAM-OH-Cys(SH)-NH ₂	5.59	+1.51
G4-PAMAM-Asp(COOH)-NH ₂		




Schemes 1-2. Schematic representation for synthesis of G4-PAMAM-NH-CO-Ser(OH)-NHBoc (3), and G4-PAMAM-NH-CO-Cys(SH)-NHBoc (6) Compounds (3 and 6) show the conversion of symmetric peripheral amines of G4-PAMAM-NH₂ (1) into hetero
 5 bifunctional terminal groups 'OH + NHBoc' and 'SH + NHBoc' respectively. The

compounds (3, 6) on deprotection of Boc group gave OH + NH₂' and 'SH + NH₂' respectively.




Schemes 3-4. Schematic representation for synthesis of G3.5-PAMAM-CO-NH-Ser(OH)-COOMe (10) and G4-PAMAM-O-CO-Cys(SH)-NHBoc (13) Compounds (10 and 13) show the conversion of symmetric peripheral acid of G3.5-PAMAM-NH₂ (8) into hetero bifunctional terminal groups 'COOMe+OH' and 'SH + NHBoc' respectively. The
5 compounds 10, 13 was further hydrolysis of methyl ester and Boc gave compounds 'COOH+OH' and 'SH+NH₂' respectively.




Scheme 5. Schematic representation for the post-functionalization reactions of hetero-bifunctional dendrimers showing conjugation of multiple drugs and or imaging agents in immediate succession. G4-PAMAM-O-Asp(COOH)-NH₂(17) dendrimer bearing COOH and NH₂ termini was synthesized. Dexamethasone was conjugated to G4-PAMAM-O-Asp(COOH)-NH₂(16) and indomethacin was added to achieve G4-PAMAM-O-Asp(CO-

Dex)-NH-Ind (22). Similarly, FITC was conjugated in immediate succession to G4-PAMAM-O-Asp(CO-Dex)-NH₂ (20) to yield G4-PAMAM-O-Asp(CO-Dex)-NH-FITC (24).




Scheme 6. Schematic representation for the post-functionalization reactions of hetero-bifunctional dendrimers showing conjugation of drug (e.g. dexamethasone) to one functional handle while the other functional handle is used for hydrogel formation (26) with N-hydroxysuccinimide terminated 8-arm-polyethylene glycol (25).

5




Scheme 7. Schematic representation for the formation of hydrogel involving one of the functional handles of the G4-PAMAM-O-CO-Cys(S-TP)-NH₂ dendrimer while the 'NH₂' handle is available for further modifications. The thiol terminated 8arm PEG (20 kDa)

formed gel at pH 7.4 by reacting with the thiopyridine terminations of the G4-PAMAM-O-CO-Cys(S-TP)-NH₂ resulting in disulfide linkages.




Scheme-8. G4-NH-CO-Cys(S-TP) cross linked with 8-arm-PEG-SH to form dendrimer-PEG nanogel (or nanoparticles)



Scheme-9

Dendrimer-FITC encapsulated or dendrimer-drug conjugate Dendrimer-PEG nanogel or Nanoparticles




Dendrimer-FITC Covalently linked or any drug Dendrimer-PEG Nanogel or Nanoparticles


Scheme-10

Scheme-9. G4-NH-PDP cross linked with 8-arm-PEG-SH to form G4-FITC encapsulated dendrimer-PEG nanogel (or nanoparticles).

Scheme-10: FITC-G4-NH-PDP cross linked with 8-arm-PEG-SH to form dendrimer-PEG nanogel (or nanoparticles)




Scheme-11: HBVS cross linked with G4-O-Cys(SH)-NH-FITC and 8-arm-PEG-SH to form dendrimer-PEG nanogel (or nanoparticles)



Scheme-12


Dendrimer-FITC Covalently linked
Dendrimer-PEG nanogel or Particles

Scheme-12: FITC-G4-NH-Mal cross linked with 8-arm-PEG-SH to form dendrimer-PEG
5 nanogel (or nanoparticles)




Scheme-13

Scheme-13: G4-O-CO-Cys(S-Tp)-NH₂ cross linked with Meo-PEG-SH to form dendrimer-PEG nanogel (or nanoparticles)



Scheme-14: G4-O-CO-Cys(SH)-NH₂ cross linked with PDP-PEG-PDP to form dendrimer-PEG nanogel (or nanoparticles)



Scheme 15 Schematic representation for the formation of hydrogel. The thiol terminated 8-arm PEG (20 kDa) formed gel at pH 7.4 by reacting with the dithiopyridine terminations of the G4-NH-PDP resulting in disulfide linkages.

CLAIMS:

1. An injectable hydrogel nanoparticle comprising:
a plurality of poly(amidoamine) (PAMAM) dendrimers with an end group covalently bound to an amino acid linker comprising serine, aspartic acid, cysteine, glutamic acid, threonine, or tyrosine,
wherein the amino acid linker is covalently bound by a first functional group to a crosslinkable polymer and is covalently bound by a second, different functional group to a drug or imaging agent; and
wherein the hydrogel nanoparticle is formed by crosslinking of the crosslinkable polymer.
2. The injectable hydrogel nanoparticle of claim 1 wherein the amino acid linker is conjugated to the first or second functional group of the dendrimer by a linkage selected from the group consisting of an amide bond and an ester bond.
3. The injectable hydrogel nanoparticle of claim 1 or 2, wherein the crosslinkable polymer is selected from the group consisting of a linear polymer, a branched polymer, and a star shaped polymer.
4. The injectable hydrogel nanoparticle of any one of claims 1 to 3, wherein the diameter of the nanoparticle is between 5 nm and 10 μ m.
5. The injectable hydrogel nanoparticle of any one of claims 1 to 4, formulated for intravenous, topical, intravitreal, intramuscular, or subcutaneous administration.
6. The injectable hydrogel nanoparticle of any one of claims 1 to 5, wherein the PAMAM dendrimer is a G4 PAMAM dendrimer.
7. The injectable hydrogel nanoparticle of any one of claims 1 to 6, wherein the drug is selected from the group consisting of macrolide antibiotics, tetracyclines, fluoroquinolones, non-steroidal anti-inflammatory drugs, non-steroidal analgesic drugs, and corticosteroids.

8. The injectable hydrogel nanoparticle of claim 3, wherein the crosslinkable polymer is a functionalized polyethylene glycol (PEG) polymer.
9. The injectable hydrogel nanoparticle of claim 8, wherein the functionalized PEG polymer is between 5 kDa and 80 kDa in size.
10. The injectable hydrogel nanoparticle of claim 8, wherein the functionalized PEG polymer is between 20 kDa and 40 kDa in size.
11. The injectable hydrogel nanoparticle of claim 7, wherein the drug is selected from the group consisting of erythromycin, azithromycin, rapamycin, clarithromycin, minocycline, doxycycline, ciprofloxacin, enrofloxacin, ofloxacin, gatifloxacin, levofloxacin, norfloxacin, cefuroxime, cefaclor, cephalexin, cephadroxil, cefpodoxime proxetil, N-acetyl cysteine, ibuprofen, aspirin, acetaminophen, diclofenac sodium, fluocinolone acetonide, and methylprednisolone.
12. A composition comprising a poly(amidoamine) (PAMAM) dendrimer covalently conjugated via a terminal functional group to an amino acid linker,
wherein the amino acid linker after conjugation to the dendrimer comprises at least two different chemical reactive groups.
13. The composition of claim 12, wherein each of the chemical reactive groups is conjugated to a functional moiety, optionally via one or more spacers, and
wherein the functional moiety is selected from the group consisting of a polymer, a drug, an imaging agent, and a targeting moiety.
14. The composition of claim 12, wherein the terminal functional group of the dendrimer is selected from the group consisting of amine, carboxylic acid, and hydroxyl.
15. The composition of claim 12, wherein the amino acid linker comprises an amino acid selected from the group consisting of serine, aspartic acid, cysteine, glutamic acid, threonine, tyrosine, and derivatives thereof.

16. The composition of claim 15, wherein the amino acid linker is conjugated to the terminal functional group of the dendrimer by a linkage selected from the group consisting of an amide bond and an ester bond.
17. The composition of claim 13, wherein the polymer is selected from the group consisting of a linear polymer, a branched polymer, and a star shaped polymer.
18. The composition of claim 17, wherein the polymer is a functionalized polyethylene glycol (PEG) polymer.
19. The composition of claim 18, wherein the functionalized polyethylene glycol (PEG) polymer is between 5 kDa and 80 kDa in size, inclusive.
20. The composition of claim 19, wherein the functionalized polyethylene glycol (PEG) polymer is between 20 kDa and 40 kDa in size, inclusive.
21. The composition of claim 18, wherein the functionalized polyethylene glycol (PEG) polymer is selected from the group consisting of 8-arm-polyethylene glycol with thiol terminations, methoxy-polyethylene glycol with thiol termination, and pyridyldithio-propionate polyethylene glycol-pyridyldithio-propionate.
22. The composition of claim 12, wherein the PAMAM dendrimer is a Generation 2 or greater PAMAM dendrimer.
23. The composition of claim 12, wherein the PAMAM dendrimer is G4 PAMAM dendrimer.
24. The composition of claim 13, wherein the one or more spacers are selected from the group consisting of maleimide-poly(ethyleneglycol)-maleimide, succinimidyl-carboxyl-methyl ester- poly(ethyleneglycol)-succinimidyl-carboxyl-methyl ester, acrylate-poly(ethyleneglycol)-acrylate, ortho-pyridyldisulfide-poly(ethyleneglycol)-ortho-pyridyldisulfide, thiol-poly(ethyleneglycol)-thiol, nitrophenyl carbonate-poly(ethyleneglycol)-nitrophenyl carbonate, isocyanate-poly(ethyleneglycol)-isocyanate, and 1,6-hexane-bis-vinylsulfone.

25. The composition of claim 13, wherein the drug comprises a macrolide antibiotic, a tetracycline, a fluoroquinolone, a cephalosporin, a non-steroidal anti-inflammatory, an analgesic drug, a corticosteroid, an antibody, a vitamin, a growth factor, a neurostimulant, a neuroprotectant, or a pharmaceutically acceptable salt thereof.
26. The composition of claim 25, wherein the drug is selected from the group consisting of erythromycin, azithromycin, rapamycin, clarithromycin, minocycline, doxycycline, ciprofloxacin, enrofloxacin, ofloxacin, gatifloxacin, levofloxacin, norfloxacin, cefuroxime, cefaclor, cephalexin, cephadroxil, cefodoxime proxetil, N-acetyl cysteine, ibuprofen, aspirin, resolvins, acetaminophen, diclofenac sodium, fluocinolone acetonide, methylprednisolone, and ranibizumab.
27. The composition of claim 13, wherein the imaging agent comprises a fluorescent dye, a radiolabeled dye, or a magnetic resonance imaging agent.
28. The composition of claim 12, further comprising a pharmaceutically acceptable excipient suitable for intravenous, topical, intravitreal, intramuscular, or subcutaneous administration.
29. A hydrogel nanoparticle comprising the composition of claim 12.


Application number / Numéro de demande: 2830052


Figures:


Pages: 10, 11, 13, 15, 16, 17, 18, 19
23-30

Unscannable items received with this application
(Request original documents in File Prep. Section on the 10th floor)

Documents reçu avec cette demande ne pouvant être balayés
(Commander les documents originaux dans la section de la préparation
des dossiers au 10^{ième} étage)

FIG - 1

FIG - 2

FIG - 3










FIG - 4CFIG - 4D

FIG - 5AFIG - 5B

FIG - 5C

WO 2011/123591

PCT/US2011/030648




FIG - 6A




FIG - 6B










FIG - 6C



FIG - 6DFIG - 6E


FIG - 8

FIG - 10


FIG - 14A

FIG - 14B



FIG - 16AFIG - 16B



G4-PAMAM
 ● = OH, COOH, NH₂



Bifunctional G4-PAMAM dendrimer
 ● = NH₂
 ○ = SH, or OH, or COOH } **Total of ≥ 110 functionality**



★ = Drug
 ★ = Imaging agent, or Drug