

ORGANISATION AFRICAINE DE LA PROPRIETE INTELLECTUELLE
(O.A.P.I.)

(19)



(11) N° 010397

(51) Inter. Cl.⁶

A01N 25/04, 25/34, 57/20, 43/90,
43/40

/(A01N 57/20, 25:34, 25:04)

(A01N 43/90, 25:04)

(A01N 43/40, 25:04)

(12) BREVET D'INVENTION

(21) Numéro de dépôt: 60955

(22) Date de dépôt: 28.01.1997

(30) Priorité(s): Grande-Bretagne
28.07.1994 N° 9415290.7

(24) Délivré le: 29.12.1997

(45) Publié le: 3 NOV 2001

(73) Titulaire(s):

ZENECA LIMITED

15 Stanhope Gate
LONDRES W1Y 6LN
(GB)

(72) Inventeur(s):

1- TADROS Tharwat Fouad
89 Nash Grove Lane
WOKINGHAM, Berkshire RG11 4HE
(GB)

2- TAYLOR Philip (GB)

(74) Mandataire: CABINET CAZENAVE
B.P. 500
YAOUNDE - Cameroun

(54) Titre: Gel formulation.

(57) Abrégé:

A water dispersible gel comprising : a) an effective amount of an ionic, water soluble agrochemical ; b) an effective amount of a cross-linked polyacrylic acid ; c) water ; and d) an amount of a base sufficient to cause a mixture of (a), (b) and (c) to gel.

GEL FORMULATION

The present invention relates to a water dispersible agrochemical gel formulation.

Gels comprising a surfactant, an agrochemical, an acrylic acid polymer or copolymer and water are disclosed in W092/01377.

5 The present invention provides a water dispersible gel comprising (a) an effective amount of an ionic, water soluble agrochemical, (b) an effective amount of a crosslinked polyacrylic acid, (c) water, and (d) an amount of a base sufficient to cause a mixture of (a), (b) and (c) to gel.

10 The water dispersible gels of the present invention are suitable for packaging in standard containers or for containment in a water-soluble or water dispersible bag. The gels of the present invention are able to be dispersed in water, and the rate of dispersion depends on the degree agitation the gel water mixture is subjected to and also the amount of water present.

15 The ionic, water soluble agrochemical, is, for example, a herbicide (such as a paraquat salt (for example paraquat dichloride or paraquat bis(methylsulphate), a diquat salt (for example diquat dibromide or diquat alginate) or glyphosate or a salt or ester thereof (such as glyphosate isopropylammonium, glyphosate sesquisodium or glyphosate trimesium (also known as sulfosate)), an insecticide or a fungicide. It is preferred that 20 the ionic, water soluble agrochemical is paraquat dichloride, diquat dibromide, glyphosate isopropylammonium or glyphosate trimesium (also known as sulfosate).

25 Crosslinked polyacrylic acids preferably have a molecular weight in the range 5×10^5 to 5×10^6 , especially in the range 1×10^6 to 4×10^6 . They are available commercially, for example as CARBOPOLs marketed by B F Goodrich (such as CARBOPOLs 5984, 2984, 940, 5984, 910, 941, 934, 934P or ETD 2050).

30 Suitable bases include ammonium or alkali metal (such as sodium or potassium) hydroxides, carbonates or bicarbonates (for example sodium hydroxide, sodium carbonate or sodium bicarbonate); or amines of formula $R^1R^2R^3N$ (wherein R^1 , R^2 and R^3 are, independently, hydrogen or C_{1-6} alkyl [optionally substituted by C_{1-6} alkoxy, hydroxy, halogen, C_{1-6} haloalkoxy (such as OCF_3), C_{1-6} hydroxyalkoxy (such as $HOCH_2CH_2O$) or C_{1-4} alkoxy(C_{1-6})alkoxy (such as $CH_3O(CH_2)_2O$ or $CH_3O(CH_2)_5O$] such as $HOCH_2CH_2$).

It is preferred that R^1 , R^2 and R^3 are, independently, C_{1-6} alkyl or C_{1-6} alkyl monosubstituted with hydroxy. An amine of formula $R^1R^2R^3N$ is, for example, triethylamine or triethanolamine.

Alkyl and the alkyl part of alkoxy groups is straight or branched
5 chain and preferably contains from 1 to 4 carbon atoms. It is, for example, methyl, ethyl, n-propyl, iso-propyl, n-butyl or tert-butyl.

In one aspect the present invention provides a water dispersible gel comprising (a) 1-60% (especially 5-60%) by weight of an ionic, water
soluble agrochemical, (b) 1-4% by weight of a crosslinked polyacrylic acid,
10 (c) 30-80% by weight of water, and (d) 2-20% by weight of a base.

In another aspect the present invention provides a water dispersible gel comprising (a) 20-60% by weight of an ionic, water soluble agrochemical, (b) 1-4% by weight of a crosslinked polyacrylic acid, (c) 30-80% by weight of water, and (d) 2-20% by weight of a base.

15 In a further aspect the present invention provides a water dispersible gel comprising (a) 20-60% by weight of an ionic, water soluble agrochemical, (b) 1-4% by weight of a crosslinked polyacrylic acid, (c) 30-80% by weight of water, (d) 2-20% by weight of a base, and (e) 1-40% of an electrolyte.

20 When a gel of the present invention is going to be held in a water-soluble or water dispersible sachet and when the ionic strength of said gel is low it is preferred that said gel comprises a suitable electrolyte in addition to the ionic agrochemical present. The electrolyte helps to improve the insolubility of the material from which the sachet is
25 made in the gel. (See Polyvinyl Alcohol - Properties and Applications pages 38-43, edited by C. A. Finch, published by J Wiley & Sons in 1973 and EP-A1-0518689.) Suitable electrolytes may, for example, comprise a cation or mixtures of cations selected from the list comprising: ammonium, copper, iron, potassium and sodium; and an anion or mixture of anions selected from
30 the list comprising: sulphate, nitrate, fluoride, chloride, bromide, iodide, acetate, tartrate, ammonium tartrate, benzenesulphonate, benzoate, bicarbonate, carbonate, bisulphate, bisulphite, sulphate, sulphite, borate, borotartrate, bromate, butyrate, chlorate, camphorate, chlorite, cinnamate, citrate, disilicate, dithionate, ethylsulphate, ferricyanide, ferrocyanide,
35 fluorosilicate, formate, glycerophosphate, hydrogenphosphate, hydroxostannate, hypochlorite, hyponitrite, hypophosphite, iodate,

isobutyrate, lactate, laurate, metaborate, metasilicate, methionate, methylsulphate, nitrite, oleate, orthophosphate, orthophosphite, orthosilicate, oxalate, perborate, perchlorate, phosphate, polyfluoride, polychloride, polyiodide, polybromide, polysulphide, polysulphate, polysulphite, salicylate, silicate, sorbate, stannate, stearate, succinate or valerate. Preferred electrolytes are ammonium sulphate, sodium sulphate, potassium sulphate, copper sulphate, ammonium nitrate, sodium nitrate, potassium nitrate, sodium chloride or potassium chloride.

It is preferred that sufficient base is added cause the pH of the water dispersible gel to be in the range 6 to 10, especially 6 to 8. If too much base is added the pH of the mixture will be too high and the gel formed will break down. Thus, in another aspect the present invention provides a water dispersible gel comprising (a) an effective amount of an ionic, water soluble agrochemical, (b) an effective amount of a crosslinked polyacrylic acid, (c) water, and (d) an amount of a base sufficient to cause the pH of the resulting gel to lie in the range 6 to 10 (especially 6 to 8, particularly 6 to 7).

In a further aspect the present invention provides a water dispersible gel which comprises 2-5% by weight of an alkali metal hydroxide, carbonate or bicarbonate.

A Bohlin VOR rheometer may be used to measure the elasticity and viscosity of the gel formulation of the present invention under low shear conditions. Here a sinusoidally varying strain (at a frequency of 1Hz) is applied to a sample of a formulation maintained at 25°C. The resultant stress, which also varies sinusoidally with time, is observed. The ratio of the maximum stress to the maximum strain is known as the complex modulus (G^*). By using the phase shift, δ , between the stress and strain wave forms the complex modulus may be split into two components - the storage (elastic) modulus (G') and the loss (viscous) modulus (G''). The storage and loss moduli are a measure of the energy stored and the energy lost respectively, in an oscillatory cycle. The relative magnitude of the loss and storage moduli ($G''/G' = \tan \delta$) provides information on the elasticity of the gel. The lower the value of $\tan \delta$ the greater the degree of gelation. Similarly, gels are characterised by their non-Newtonian flow behaviour, exhibiting, for example, yield values and shear thinning. Yield values can be measured using a Haake Rotovisco RV20 under high shear

gel of the present invention may also comprise an adhesive, an antifoaming agent, a buffer, a deodorant, a dye, an emetic, a preservative, an odourant, a perfume, a safener, a further solvent, a stabiliser, a synergist, a thickener or a wetting agent.

5 A gel of the invention can be made simply by initially mixing all the components other than the base, and then adding the base to form the gel. Thus it can be appreciated that a gel of the present invention is made by a pH switching process.

10 In a further aspect the present invention provides a containerisation system comprising a water soluble or water dispersible bag containing a water dispersible gel of the present invention, provided the gel has sufficient ionic strength.

15 The water soluble or water dispersible bag can be made from a variety of materials and preferred materials are polyethylene oxide, methyl cellulose or, especially, polyvinylalcohol (PVA). The PVA is generally partially or fully alcoholysed or hydrolysed, for example 40-100%, especially 80-100%, alcoholysed or hydrolysed polyvinyl-acetate film. It is preferred that the PVA film is a laminate of two or more thicknesses of film, a surface modified film or a co-extruded film (such as is described
20 in WO 94/29188).

In another aspect the containerisation system comprises a bag-in-bag arrangement comprising a water-soluble or water dispersible bag holding a gel of the present invention and a second water-soluble or water dispersible bag also holding a gel of the present invention. This
25 bag-in-bag arrangement can be used, for example, to contain a gel of the present invention comprising an ionic, water soluble agrochemical in the inner bag and a gel of the present invention comprising adjuvant, synergist or penetrating agent in the outer bag.

30 In a further aspect the containerisation system provides two water-soluble or water dispersible bags joined at a common seal, one containing a gel of the present invention comprising one ionic, water soluble agrochemical, the other bag containing a gel of the present invention comprising a different ionic, water soluble agrochemical.

35 In a still further aspect the containerisation system comprises a bag-in-bag arrangement comprising a first water-soluble or water dispersible bag holding a gel of the present invention and a second

water-soluble or water dispersible bag surrounding the first water-soluble or water dispersible bag. The advantage of this system is that the second bag presents a barrier to any matter leaking from the first bag.

In another aspect the containerisation system comprises a bag-in-bag arrangement comprising a first water-soluble or water dispersible bag holding a gel of the present invention and a second water-soluble or water dispersible bag holding an agrochemical composition (such as a liquid, granule, powder or gel composition comprising a fungicide, herbicide, insecticide, adjuvant, synergist or penetrating agent).

10 In a further aspect the containerisation system comprises a bag-in-bag arrangement comprising a first water-soluble or water dispersible bag holding an agrochemical composition (such as a liquid, granule, powder or gel composition comprising a fungicide, herbicide, insecticide, adjuvant, synergist or penetrating agent) and a second water-soluble or water
15 dispersible bag holding a gel of the present invention.

In another aspect the containerisation system provides two water-soluble or water dispersible bags joined at a common seal, one containing a gel of the present invention comprising a fungicide, herbicide, insecticide, adjuvant, synergist or penetrating agent the other
20 bag containing an agrochemical composition (such as a liquid, granule, powder or gel composition comprising a fungicide, herbicide, insecticide, adjuvant, synergist or penetrating agent).

The water soluble or water dispersible sachet can be formed and filled using standard techniques (such as thermoforming or vertical
25 form-fill-sealing).

In use the containerisation system can be mixed with water to give a sprayable solution or dispersion of the ionic chemical. The containerisation system is especially useful in agriculture.

The following Examples illustrate the invention. CARBOPOL is a Trade
30 Mark of B F Goodrich.

EXAMPLE 1

A solution of sulfosate in water (61.4% w/w, 34.19g) was added to a 5% (w/w) aqueous solution of CARBOPOL 2984 (35.04g), and water (0.88g) and ethylene glycol (0.35g) were then added. The mixture was then shaken and
35 left on rollers to ensure thorough mixing. Sodium hydroxide (2.48g) was

then added to neutralize the acid and bring the pH of the system up to 6.45. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 2

5 A solution of sulfosate in water (61.4% w/w, 34.16g) was added to a 5% (w/w) aqueous solution of CARBOPOL 2984 (21.00g), and water (14.89g) and ethylene glycol (0.36g) were then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.27g) was then added to neutralize the acid and bring the pH of the system up to 6.65. This resulted in the CARBOPOL 2984 swelling.

10

EXAMPLE 3

15 A solution of sulfosate in water (61.4% w/w, 34.17g) was added to a 6% (w/w) aqueous solution of CARBOPOL 2984 (35.00g), and water (0.90g) and ethylene glycol (0.35g) were then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.48g) was then added to neutralize the acid and bring the pH of the system up to 6.23. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 4

20 A solution of sulfosate in water (61.4% w/w, 34.18g) was added to a 5% (w/w) aqueous solution of CARBOPOL 2984 (24.50g), and water (11.36g) and ethylene glycol (0.35g) were then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.28g) was then added to neutralize the acid and bring the pH of the system up to 6.59. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 5

25 A solution of sulfosate in water (61.4% w/w, 34.14g) was added to a 5% (w/w) aqueous solution of CARBOPOL 2984 (31.49g), and water (4.37g) and ethylene glycol (0.38g) were then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.39g) was then added to neutralize the acid and bring the pH of the system up to 6.35. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 6

35 A solution of sulfosate in water (61.4% w/w, 39.81g) was added to a 5% (w/w) aqueous solution of CARBOPOL 2984 (17.51g), and water (12.77g) and ethylene glycol (0.35g) were then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.70g) was then added to neutralize the acid and bring the pH of the system up to

6.52. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 7

A solution of sulfosate in water (61.4% w/w, 39.81g) was added to a 5% (w/w) aqueous solution of CARBOPOL 2984 (20.42g), and water (9.93g) and ethylene glycol (0.35g) were then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.80g) was then added to neutralize the acid and bring the pH of the system up to 6.48. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 8

A solution of sulfosate in water (61.4% w/w, 39.80g) was added to a 5% (w/w) aqueous solution of CARBOPOL 2984 (23.34g), and water (6.95g) and ethylene glycol (0.35g) were then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.88g) was then added to neutralize the acid and bring the pH of the system up to 6.48. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 9

A solution of sulfosate in water (61.4% w/w, 39.89g) was added to a 5% (w/w) aqueous solution of CARBOPOL 2984 (26.23g), and water (4.09g) and ethylene glycol (0.36g) were then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.81g) was then added to neutralize the acid and bring the pH of the system up to 6.38. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 10

A solution of sulfosate in water (61.4% w/w, 39.78g) was added to a 5% (w/w) aqueous solution of CARBOPOL 2984 (29.17g), and water (1.10g) and ethylene glycol (0.36g) were then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.85g) was then added to neutralize the acid and bring the pH of the system up to 6.36. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 11

A solution of sulfosate in water (61.4% w/w, 39.81g) was added to a 5% (w/w) aqueous solution of CARBOPOL 2984 (24.63g), and water (5.82g) and ethylene glycol (0.35g) were then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.82g) was then added to neutralize the acid and bring the pH of the system up to 6.23. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 12

A solution of sulfosate in water (61.4% w/w, 39.79g) was added to a 5% (w/w) aqueous solution of CARBOPOL 2984 (22.56g), and water (7.79g) and ethylene glycol (0.35g) were then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.32g) was then added to neutralize the acid and bring the pH of the system up to 6.23. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 13

CARBOPOL 2984 (2.12g) was mixed with a solution of sulfosate in water (61.4% w/w, 45.50g) after which water (12.34g) and ethylene glycol (0.34g) were added. The mixture was shaken and left on rollers to ensure thorough mixing. Triethanolamine (10.01g) was then added to neutralize the acid and bring the pH of the system up to 6.66. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 14

CARBOPOL 2984 (1.94g) was mixed with a solution of sulfosate in water (61.4% w/w, 45.51g) after which water (12.57g) and ethylene glycol (0.35g) were added. The mixture was shaken and left on rollers to ensure thorough mixing. Triethanolamine (10.01g) was added to neutralize the acid and bring the pH of the system up to 6.71. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 15

CARBOPOL 2984 (1.75g) was mixed with a solution of sulfosate in water (61.4% w/w, 45.58g) after which water (12.89g) and ethylene glycol (0.35g) were added. The mixture was shaken and left on rollers to ensure thorough mixing. Triethanolamine (10.05g) were added to neutralize the acid and bring the pH of the system up to 6.81. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 16

CARBOPOL 2984 (1.41g) was mixed with a solution of sulfosate in water (61.4% w/w, 45.53g) after which water (13.12g) and ethylene glycol (0.35g) were added. The mixture was shaken and left on rollers to ensure thorough mixing. Triethanolamine (10.05g) was added to neutralize the acid and bring the pH of the system up to 6.81. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 17

CARBOPOL 2984 (1.58g) was mixed with a solution of sulfosate in water (61.4% w/w, 45.55g) after which water (13.07g) and ethylene glycol (0.34g) were added. The mixture was shaken and left on rollers to ensure thorough mixing. Triethanolamine (10.05g) was added to neutralize the acid and bring the pH of the system up to 6.78. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 18

CARBOPOL 2984 (1.23g) was mixed with a solution of sulfosate in water (61.4% w/w, 45.67g) after which water (13.22g) and ethylene glycol (0.36g) were added. The mixture was shaken and left on rollers to ensure thorough mixing. Triethanolamine (10.08g) was added to neutralize the acid and bring the pH of the system up to 6.87. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 19

CARBOPOL 2984 (1.05g) was mixed with a solution of sulfosate in water (61.4% w/w, 45.62g) after which water (13.43g) and ethylene glycol (0.37g) were added. The mixture was shaken and left on rollers to ensure thorough mixing. Triethanolamine (10.13g) was added to neutralize the acid and bring the pH of the system up to 6.93. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 20

A solution of sulfosate in water (61.4% w/w, 40.02g) was added to a 6% (w/w) aqueous solution of CARBOPOL 2984 (26.23g), and water (20.00g) was then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.77g) was then added to neutralize the acid and bring the pH of the system up to 6.49. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 21

A solution of sulfosate in water (61.4% w/w, 40.02g) was added to a 6% (w/w) aqueous solution of CARBOPOL 2984 (26.67g), and water (13.33g) was then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.99g) was then added to neutralize the acid and bring the pH of the system up to 6.47. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 22

A solution of sulfosate in water (61.4% w/w, 40.07g) was added to a 6% (w/w) aqueous solution of CARBOPOL 2984 (30.00g), and water (10.00g) was then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.97g) was then added to neutralize the acid and bring the pH of the system up to 6.40. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 23

A solution of sulfosate in water (61.4% w/w, 40.02g) was added to a 6% (w/w) aqueous solution of CARBOPOL 2984 (33.34g), and water (6.68g) was then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (3.59g) was then added to neutralize the acid and bring the pH of the system up to 6.86. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 24

A solution of sulfosate in water (61.4% w/w, 250.14g) was added to a mixture of 4.7% (w/w) aqueous solution of CARBOPOL 2984 (33.34g) and ethylene glycol (1.27g). The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (15.51g) was then added to neutralize the acid and bring the pH of the system up to 6.28. This resulted in the CARBOPOL 2984 swelling.

A sample of the gel formed (25g) was placed into a sachet made of polyvinylalcohol (Chris Craft M7030) and the sachet's opening was heat sealed. After storage at 25°C for 3 months the sachet remained supple and, when put in contact with water, the sachet and its contents readily dispersed.

EXAMPLE 25

A solution of sulfosate in water (61.4%, 20.02g) was added to a 6.25% (w/w) aqueous solution of CARBOPOL 941 (15.02g) and water (5.00g). The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (1.68g) was then added to neutralize the acid and bring the pH up to 6.57. This resulted in the CARBOPOL 941 swelling.

EXAMPLE 26

A solution of sulfosate in water (61.4%, 20.06g) was added to a 6.22% (w/w) aqueous solution of CARBOPOL 910 (15.02g) and water (5.14g). The mixture was then shaken and left on rollers to ensure thorough mixing.

Sodium hydroxide (1.53g) was then added to neutralize the acid and bring the pH up to 6.44. This resulted in the CARBOPOL 910 swelling.

EXAMPLE 27

5 A solution of sulfosate in water (61.4%, 26.04g) was added to a 6.18% (w/w) aqueous solution of CARBOPOL 2984 (30.02g) and water (24.06g). The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (3.11g) was then added to neutralize the acid and bring the pH up to 6.72. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 28

10 A solution of sulfosate in water (61.4%, 32.50g) was added to a 6.17% (w/w) aqueous solution of CARBOPOL 2984 (30.00g) and water (17.52g). The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (3.01g) was then added to neutralize the acid and bring the pH up to 6.57. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 29

15 A solution of sulfosate in water (61.4%, 45.55g) was added to a 6.17% (w/w) aqueous solution of CARBOPOL 2984 (30.00g) and water (4.50g). The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (3.16g) was then added to neutralize the acid and bring
20 the pH up to 6.51. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 30

A solution of sulfosate in water (61.4%, 40.09g) was added to a 5.99% (w/w) aqueous solution of CARBOPOL 2984 (30.00g) and water (10.00g). The mixture was then shaken and left on rollers to ensure thorough mixing.
25 Sodium bicarbonate (6.45g) was then added to neutralize the acid and bring the pH up to 6.66. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 31

A solution of sulfosate in water (61.4%, 39.99g) was added to a 6.18% (w/w) aqueous solution of CARBOPOL 2984 (30.00g) and water (10.02g). The
30 mixture was then shaken and left on rollers to ensure thorough mixing. Sodium carbonate (4.80g) was then added to neutralize the acid and bring the pH up to 6.59. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 32

A solution of sulfosate in water (61.4%, 40.00g) was added to a 6.15%
35 (w/w) aqueous solution of CARBOPOL 5984 (30.00g) and water (10.50g). The mixture was then shaken and left on rollers to ensure thorough mixing.

Sodium hydroxide (3.03g) was then added to neutralize the acid and bring the pH up to 6.55. This resulted in the CARBOPOL 5984 swelling.

EXAMPLE 33

5 A solution of sulfosate in water (61.4%, 20.00g) was added to a 5.19% (w/w) aqueous solution of CARBOPOL ETD 2050 (16.68g) and water (3.44g). The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (1.71g) was then added to neutralize the acid and bring the pH up to 6.71. This resulted in the CARBOPOL ETD 2050 swelling.

EXAMPLE 34

10 A solution of glyphosate isopropylammonium in water (61.5%, 20.21g) was added to a (w/w) aqueous solution of 6.17% CARBOPOL 2984 (15.00g) and water (5.01g). The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.86g) was then added to neutralize the acid and bring the pH up to 6.49. This resulted in the CARBOPOL 2984 swelling.
15

EXAMPLE 35

A solution of diquat dibromide in water (26.3% w/v, 32.50g) was added to a 6.09% (w/w) aqueous solution of CARBOPOL 2984 (11.67g) and water (8.35g). The mixture was then shaken and left on rollers to ensure
20 thorough mixing. Sodium hydroxide (0.30g) and a 40% aqueous solution of sodium hydroxide in water (0.14g) were then added to neutralize the acid and bring the pH up to 6.42. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 36

25 A solution of paraquat dichloride in water (32.3% w/w, 20.01g) was added to a 6.10% (w/w) aqueous solution of CARBOPOL 2984 (11.68g) and water (8.45g). The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (0.24g) and a 40% aqueous solution of sodium hydroxide (0.16g) were then added to neutralize the acid and bring the pH up to 6.57. This resulted in the CARBOPOL 2984 swelling.

30 EXAMPLE 37

A solution of paraquat dichloride in water (32.3% w/w, 25.01g) was added to a 6.10% (w/w) aqueous solution of CARBOPOL 2984 (15.00g). The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (0.37g) and a 40% aqueous solution of sodium hydroxide
35 (0.10g) were then added to neutralize the acid. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 38

A solution of paraquat dichloride in water (32.3% w/w, 20.02g) was added to a 6.13% (w/w) aqueous solution of CARBOPOL 2984 (17.50g), sodium chloride (1.00g) and water (2.38g). The mixture was then shaken and left
5 on rollers to ensure thorough mixing. Sodium hydroxide (0.45g) was then added to neutralize the acid. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 39

A solution of sulfosate in water (61.4%, 20.05g) was added to a 5.10% (w/w) aqueous solution of CARBOPOL 2984 (15.03g) and water (1.02g). The
10 mixture was then shaken and left on rollers to ensure thorough mixing. Triethylamine (4.04g) was then added to neutralize the acid and raise the pH up to 7.29. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 40

A solution of sulfosate in water (57.6% w/w, 30.41g) was added to a
15 6.55% (w/w) aqueous solution of CARBOPOL 2984 (22.03g), and water (6.57g) and ethylenediaminetetraacetic acid (1.51g) were then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium hydroxide (2.29g) was then added to bring the pH of the system up to 6.16. This resulted in the CARBOPOL 2984 swelling.

20

EXAMPLE 41

A solution of sulfosate in water (57.6% w/w, 30.35g) was added to a
6.55% (w/w) aqueous solution of CARBOPOL 2984 (21.97g), and water (5.03g) and ethylenediaminetetraacetic acid (3.05g) were then added. The mixture was then shaken and left on rollers to ensure thorough mixing. Sodium
25 hydroxide (3.05g) was then added to bring the pH of the system up to 6.29. This resulted in the CARBOPOL 2984 swelling.

EXAMPLE 42

The rheological properties of the products of the foregoing Examples were measured on a Bohlin rheometer using a cup and bob or cone and plate
30 geometry. The measurements were primarily carried out at a temperature of 25°C. Oscillation measurements were carried out within the linear viscoelastic region as determined by strain sweep measurements made at a frequency of 1Hz (6.28 rad/s).

The values for the moduli at 1 Hz are presented in TABLE I, where G^*
35 is the complex modulus; G' the storage modulus; G'' the loss modulus; δ the phase angle between the loss and storage moduli; and $\tan \delta$ is G''/G' .

TABLE I

EXAMPLE No	G^* (Pa)	G' (Pa)	G'' (Pa)	$\tan \delta$
5	1	282	281	16.4
	2	37.3	37.2	2.95
	3	390	389	20.6
	4	72.6	72.4	4.67
	5	215	215	11.9
10	6	28.0	27.9	2.47
	7	60.9	60.8	4.44
	8	112	112	5.90
	9	167	167	8.34
	10	255	254	13.2
15	11	424	423	28.1
	12	343	343	19.2
	13	407	404	43.5
	14	458	452	74.8
	15	378	373	62.2
20	16	125	123	21.9
	17	199	196	35.2
	18	63.0	60.9	16.1
	19	23.3	21.9	8.12
	20	35.8	35.6	3.58
25	21	130	130	8.07
	22	154	154	10.0
	23	241	240	15.4
	24	189	188	11.0
	25	88.8	86.7	19.4
30	26	53.8	50.0	19.8
	27	359	359	16.5
	28	212	212	9.69
	29	172	172	8.58
	30	204	204	9.38
	31	216	215	10.8
	32	205	205	13.8

TABLE I (Continued)

	EXAMPLE No	G^* (Pa)	G' (Pa)	G'' (Pa)	$\tan \delta$
	33	279	272	59.5	0.219
	34	132	130	18.3	0.141
5	35	242	242	10.7	0.044
	36	201	200	10.2	0.051
	37	212	211	14.2	0.067
	38	158	158	8.95	0.057
	39	223	222	18.2	0.082
10	40	-	129	9.55	0.074
	41	-	117	9.97	0.085

CLAIMS

1. A water dispersible gel comprising:
 - (a) an effective amount of an ionic, water soluble agrochemical;
 - (b) an effective amount of a cross-linked polyacrylic acid;
 - 5 (c) water; and,
 - (d) an amount of a base sufficient to cause a mixture of (a), (b) and (c) to gel.
2. A water dispersible gel as claimed in claim 1, said gel comprising:
 - (a) an effective amount of an ionic, water soluble agrochemical;
 - 10 (b) an effective amount of a crosslinked polyacrylic acid;
 - (c) water; and,
 - (d) an amount of a base sufficient to cause the pH of the resulting gel to lie in the range 6 to 10.
3. A water dispersible gel as claimed in claim 1 or 2, said gel comprising:
 - (a) 1-60% by weight of an ionic, water soluble agrochemical;
 - (b) 1-4% by weight of a crosslinked polyacrylic acid;
 - (c) 30-80% by weight of water; and,
 - (d) 2-20% by weight of a base.
4. A water dispersible gel as claimed in claim 1, 2 or 3 wherein the crosslinked polyacrylic acid has a molecular weight in the range 5×10^5 to 5×10^6 .
5. A water dispersible gel as claimed in claim 1, 2, 3 or 4 wherein the base is an ammonium or alkali metal hydroxide, carbonate or bicarbonate; or an amine of formula $R^1R^2R^3N$ wherein R^1 , R^2 and R^3 are, independently, hydrogen or C_{1-6} alkyl [optionally substituted by C_{1-6} alkoxy, hydroxy, halogen, C_{1-6} haloalkoxy, C_{1-6} hydroxyalkoxy or C_{1-4} alkoxy(C_{1-6})alkoxy].
6. A water dispersible gel as claimed in claim 1, 2, 3, 4 or 5 wherein the ionic, water soluble agrochemical is a paraquat salt, a diquat

salt, or a salt or ester of glyphosate.

7. A water dispersible gel as claimed in claim 1, 2, 3, 4 or 5 wherein the ionic, water soluble agrochemical is paraquat dichloride, diquat dibromide, glyphosate isopropylammonium or glyphosate trimesium.
- 5 8. A containerisation system comprising a water dispersible gel, as claimed in any one of the preceeding claims, contained in a water-soluble or water dispersible bag.
9. A process forpreparing a water dispersible gel as claimed in claim 1, the process comprising mixing components (a), (b) and (c) and then
10 adding component (d) until the pH of the mixture is in the range 6-10.