



(12) UK Patent (19) GB (11) 2 154 950 (13) B

(54) Title of Invention

Liquid jet recording head and substrate therefore

(51) INT CL<sup>4</sup>; B41J 3/04

(21) Application No  
8502461

(22) Date of filing  
31 Jan 1985

(30) Priority data

(31) 59/014520

(32) 31 Jan 1984

(33) Japan (JP)

(43) Application published  
18 Sep 1985

(45) Patent published  
9 Nov 1988

(73) Proprietor(s)  
Canon Kabushiki Kaisha

(Incorporated in Japan)

30-2 3-chome Shimomaruko  
Ohta-ku  
Tokyo  
Japan

(72) Inventor(s)  
Masami Ikeda  
Makoto Shibata  
Hiroto Takahashi  
Hirokazu Komuro  
Hiroto Matsuda  
Hisanori Tsuda

(74) Agent and/or  
Address for Service  
Beresford & Co  
2-5 Warwick Court  
High Holborn  
London WC1R 5DJ

(52) Domestic classification  
(Edition J)  
B6F LQ

(56) Documents cited  
EP 0113950

(58) Field of search  
B6F

1/4

FIG. 1A







FIG. 1B





3/4

FIG. 3A




FIG. 3B





FIG. 3C



4/4

FIG. 4A




FIG. 4B





FIG. 4C



1 TITLE OF THE INVENTION

Liquid Jet Recording Head and substrate therefor.

BACKGROUND OF THE INVENTION5 Field of the Invention

This invention relates to a liquid jet recording head which ejects liquid to produce flying liquid droplets to record, and to a substrate therefor.

Description of the Prior Art

10 Ink jet recording methods (liquid jet recording methods) have recently attracted attention since noise upon recording is very little and a high speed recording is possible, and further, the recording can be made on plain paper without any special treatment such as fixation.

15 Among them, for example, a liquid jet recording method disclosed in Japanese Patent Laid-open No. 51837/1979 and German Patent Laid-open (DOLS) No. 2843064 is different from other liquid jet recording methods in point that heat energy is applied to liquid to produce a driving  
20 force for ejecting liquid droplets.

That is, the above-mentioned recording method comprises applying heat energy to a liquid to cause an abrupt increase in the volume of the liquid, ejecting the liquid from the orifice at the front of the recording head  
25 to form flying liquid droplets and attaching the droplets to a record receiving member to effect recording.

1           In particular, the liquid jet recording method  
disclosed in DOLS 2843064 cannot be only effectively  
suitable for so-called "drop-on-demand" recording methods,  
but also enables to realize easily a high density multi-  
5 orifice recording head of a full-line type, and therefore,  
images of high resolution and high quality can be produced  
at a high speed.

          The recording head portion of an apparatus used for  
the above-mentioned recording method comprises a liquid  
10 ejecting portion constituted of an orifice for ejecting  
liquid and a liquid flow path containing, as a part of the  
construction, a heat actuating portion communicated with  
the orifice and applying heat energy for ejecting liquid  
droplets to the liquid, and an electrothermal transducer  
15 for generating heat energy.

          The electrothermal transducer is provided with a  
pair of electrodes formed on a support and a resistive  
heater layer connected to the electrodes and having a  
region generating heat (heat generating portion) between  
20 the electrodes.

          A typical embodiment of the structure of such  
liquid jet recording head is shown in FIG. 1A and FIG. 1B.

          FIG. 1A is a partial front view of the liquid  
jet recording head viewed from the orifice side, and  
25 FIG. 1B is a partial cross-sectional view taken along  
the dot and dash line XY of FIG. 1A.

          Recording head 100 is constituted of orifice 104

1 and liquid ejecting portion 105 formed by bonding the  
surface of substrate 102 provided with electrothermal  
transducer to a grooved plate 103 having a predeter-  
mined number of grooves having a predetermined width and  
5 depth at a predetermined line density such that the  
grooved plate covers the substrate. In FIG. 1, the  
recording head has a plurality of orifices 104, but the  
present invention is not limited to such an embodiment  
and a recording head having a single orifice is also  
10 within the scope of the present invention.

Liquid ejecting portion 105 has orifice 104  
ejecting liquid at the end and heat actuating portion  
106 where heat energy generated by electrothermal trans-  
ducer is applied to liquid to form a bubble and an  
15 abrupt state change due to expansion and shrinkage of  
the volume occurs.

Heat actuating portion 106 is located above  
heat generating portion 107 of electrothermal transducer  
and a heat actuating surface 108 where heat gener-  
20 ating portion 107 contacts the liquid is the bottom  
surface of the heat actuating portion 106.

Heat generating portion 107 is constituted of  
resistive heater layer 110 provided on lower layer 109  
formed in substrate and upper layer 111 provided on  
25 resistive heater layer 110. Electrodes 112 and 113 are  
provided on the surface of resistive heater layer 110 for  
flowing electric current to the layer 110 to generate heat.



1 Electrode 113 is a selection electrode for selecting the  
heat generating portion of each liquid ejecting portion to  
generate heat, and electrode 112 is an electrode common to  
heat generating portions of liquid ejecting portions and is  
5 provided along the liquid flow path of each liquid ejecting  
portion.

Upper layer 111 serves to protect chemically and  
physically resistive heater layer 110 from the liquid at  
the heat generating portion 107 by isolating resistive  
10 heater layer 110 from the liquid in the liquid flow path at  
liquid ejecting portion 105 and further upper layer 111  
prevents electrodes 112 and 113 from shortcircuiting  
through the liquid. Thus, upper layer 111 serves to  
protect resistive heater layer 110. Upper layer 111 also  
15 serves to prevent electric leakage between adjacent elec-  
trodes. In particular, it is important to prevent electric  
leakage between selection electrodes and electrolytic  
corrosion of electrodes caused by electric current flowing  
in an electrode resulting from contact of an electrode  
20 under the liquid flow path with the liquid which happens by  
some cause. Therefore, such an upper layer 111 having a  
protective function is provided on at least an electrode  
which is disposed under a liquid flow path.

The upper layer is required to have various proper-  
25 ties depending on the position to be disposed. That is,  
for example, the following characteristics are required at  
heat generating portion 107:

- 1) heat resistance,
- 2) liquid resistance,
- 3) liquid penetration preventing property,
- 4) thermal conductivity,
- 5) oxidation preventing property,
- 6) insulating property, and
- 7) breakage preventing property.

At portions other than heat generating portion 107, sufficiently high liquid penetration preventing property, liquid resistance and breakage preventing property are required though the resisting property to thermal conditions is not required to be so good.

However, at present there is not any material for constituting the upper layer capable of sufficiently satisfying all the characteristics 1) - 7) as mentioned above. It is the present status that some of the conditions 1) - 7) are not severely requested.


Apart from the above, in the case of a liquid jet recording head of a multi-orifice type, since a number of fine electrothermal transducers are formed on the substrate simultaneously, formation of each layer of the substrate and removal of a part of the formed layer are repeated, and as a result, the surface on which each layer in the upper layer is to be formed becomes a fine uneven surface having step edge portions, and therefore, the step coverage property of the layers in the upper layer at the step edge portions becomes important. In other words, when the step coverage

1 property at the step edge portions is poor, penetration of  
the liquid occurs at the portions and causes electrolytic  
corrosion or dielectric breakdown. Further, when the  
formed upper layer suffers the formation of defects upon  
5 fabrication with a considerable probability, penetration of  
liquid occurs through the defect portion resulting in  
shortening the life of the electrothermal transducer to a  
great extent.

In view of the foregoing, it is required that the  
10 upper layer has a good step coverage property at the step  
edge, defects such as pinholes and the like occur in the  
formed layer with only a low probability and even if the  
defects are formed, the number of defects is negligibly  
small or less.


15 In order to satisfy those requisites, heretofore  
the upper layer has been produced by laminating the first  
protective layer composed of an inorganic insulating material  
and the second protective layer composed of an organic  
material, or the first protective layer is constituted of  
20 two layers, that is, an under layer composed of an inorganic  
insulating material and an above layer composed of an in-  
organic material of high toughness, relatively excellent  
mechanical strength and having adhesion and cohesion to  
the first protective layer and the second protective layer,  
25 such as metals and the like, or the third protective layer  
composed of an inorganic material such as metals and the  
like overlies the second protective layer.

However, it is very difficult that the upper layer  
having no defects is formed by the above-mentioned  
process. The liquid jet recording head satisfying all  
the requirements and having totally excellent  
5 durability for use has not yet been provided.



In accordance with one aspect of the present invention, there is provided a substrate for a liquid jet recording head, the substrate carrying an electrode arrangement in the form of a u-shape with a break being formed in the u-shape to provide a pair of electrodes, and a resistive heater layer coating and covering at least part of each electrode and bridging the break between the electrodes to form an electrothermal transducer.

In accordance with another aspect of the present invention, there is provided a liquid jet recording head having a substrate according to the <sup>first mentioned</sup> [third] aspect of the invention. \_\_\_\_\_



1 BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1A and B refer to a conventional liquid jet recording head, FIG. 1A shown schematically a partial front view and FIG. 1B is a partial cross-sectional view taken  
5 along a dot and dash line XY in FIG. 1A;

FIG. 2A and B refer to a liquid jet recording head according to the present invention, FIG. 2A shows schematically a partial front view, FIG. 2B is a partial cross-sectional view taken along a dot and dash line AA' in FIG. 2A;

10 FIGS. 3A, B and C are partial cross-sectional views taken along a dot and dash line AA' in FIG. 2A to show embodiments of the present invention;

FIGS. 4A, B and C are front views of embodiments of the present invention.

15

DESCRIPTION OF THE PREFERRED EMBODIMENTS

A liquid jet recording head of the present invention will be described in detail referring to the drawings.

FIG. 2A is a partial front view of a liquid jet  
20 recording head of the present invention viewed from the orifice side for explaining the main part of the structure of a preferable embodiment of the present invention and FIG. 2B shows a partial cross-sectional view taken along a dot and dash line in FIG. 2A. FIG. 2A and FIG. 2B  
25 correspond to FIG. 1A and FIG. 1B, respectively.

Liquid jet recording head 200 is mainly constituted of a substrate 202 provided with a predetermined number of

1 electrothermal transducer for liquid jet recording where  
heat is used for liquid ejection and a grooved plate 203  
having a predetermined number of grooves corresponding to  
the above-mentioned electrothermal transducers 204 - 1,  
5 204 - 2 and 204 - 3 are liquid flow paths.

Substrate 202 and grooved plate 203 are bonded at  
predetermined portions with adhesives or the like to form  
liquid flow path 215 defined by the portion of substrate  
202 where electrothermal transducer is provided and the  
10 groove of grooved plate 203, and the liquid flow path 215  
has heat actuating portion 206.

Substrate 202 is constituted of support 214 composed  
of silicon, glass, ceramics or the like, lower layer 209  
overlying support 206 and composed of  $\text{SiO}_2$  or the like,  
15 common electrode 212, selection electrode 213, resistive  
heater layer 210 overlying each electrodes, and upper layer  
211 overlying resistive heater layer 210.

The electrothermal transducer comprises heat  
generating portion 207 as the main portion. The heat  
20 generating portion 207 is constituted of support 214, lower  
layer 209, resistive heater layer 210 and upper layer 211  
successively formed. The surface of upper layer 211 (heat  
actuating surface 208) directly contacts the liquid filled  
in liquid flow path 215.

25 Upper layer 211 is constituted of inorganic materials  
relatively excellent in electric insulating property, thermal  
conductivity, and heat resistance, for example, inorganic

1 oxides such as  $\text{SiO}_2$  and the like and inorganic nitrides such  
as  $\text{Si}_3\text{N}_4$  and the like.

As described above, the upper layer may be formed  
with a combination of the first protective layer, the  
5 second protective layer, the third protective layer.

As materials constituting the first protective layer,  
there are preferably used inorganic insulating materials  
relatively excellent in thermal conductivity and heat  
resistance, for example, inorganic oxides such as  $\text{SiO}_2$  and  
10 the like, transition metal oxides such as titanium oxide,  
vanadium oxide, niobium oxide, molybdenum oxide, tantalum  
oxide, tungsten oxide, chromium oxide, zirconium oxide,  
hafnium oxide, lanthanum oxide, yttrium oxide, manganese  
oxide and the like, metal oxides such as aluminum oxide,  
15 calcium oxide, strontium oxide, barium oxide, silicon oxide  
and the like and composites thereof, high resistance  
nitrides such as silicon nitride, aluminum nitride, boron  
nitride, tantalum nitride and the like and composites of  
these oxides and nitrides, and thin film materials, for  
20 example, semiconductors comprising amorphous silicon,  
amorphous selenium and the like which have low resistance  
as bulk, but may be made to have high resistance by a  
sputtering method, a CVD method, a vapor deposition method,  
a gas phase reaction method, a liquid coating method or the  
25 like.

As materials used for forming the third protective  
layer, in addition to Ta as mentioned above, there may be



1 mentioned the elements of Group IIIa of the periodic Table  
such as Sc, Y and the like, the elements of Group IVa such  
as Ti, Zr, Hf and the like, the elements of Group Va such  
as V, Nb and the like, the elements of the Group VIa such  
5 as Cr, Mo, W and the like, the elements of Group VIII such  
as Fe, Co, Ni and the like, alloys of the above-mentioned  
metals such as Ti-Ni, Ta-W, Ta-Mo-Ni, Ni-Cr, Fe-Co, Ti-W,  
Fe-Ti, Fe-Ni, Fe-Cr, Fe-Ni-Cr and the like, borides of the  
above-mentioned metals such as Ti-B, Ta-B, Hf-B, W-B and  
10 the like, carbides of the above-mentioned metals such as  
Ti-C, Zr-C, V-C, Ta-C, Mo-C, Cr-C and the like, silicides  
of the above-mentioned metals such as Mo-Si, W-Si, Ta-Si  
and the like, nitrides of the above-mentioned metals such  
as Ti-N, Nb-N, Ta-N and the like. Using these materials,  
15 the third protective layer may be formed by the procedure  
such as a vapor deposition method, a sputtering method, a  
CVD method and the like. The third protective layer may  
be composed of the above materials, alone or in combination.

The second protective layer is composed of an organic  
20 insulating material which is excellent in prevention of  
liquid penetration and liquid resistance, and further has  
preferably the following characteristics:

- (1) Good film shapeability,
- (2) Dense structure and free from pinholes,
- 25 (3) Not swelled with and not dissolved in the ink,
- (4) High insulating property when film-shaped,
- (5) High heat resistance,

1 and the like.

As the organic materials, there may also be used, for example, silicone resin, fluorine resin, aromatic polyamide, addition polymerization type polyimide, poly-  
5 benzimidazole, metal chelate polymer, titanate acid ester, epoxy resin, phthalic resin, thermosetting phenolic resin, p-vinylphenolic resin, Zirox resin, triazine resin, BT resin (addition polymerized resin of triazine resin and bismaleimide) or the like. Alternatively, it is also  
10 possible to form the second protective layer by vapor deposition of polyxylylene resin and derivatives thereof.

Further, the second protective layer may also be formed by film shaping according to a plasma polymerization using various organic monomers such as thiourea, thio-  
15 acetamide, vinyl ferrocene, 1,3,5-trichlorobenzene, chlorobenzene, styrene, ferrocene, pyrrole, naphthalene, pentamethylbenzene, nitrotoluene, acrylonitrile, diphenyl selenide, p-toluidine, p-xylene, N,N-dimethyl-p-toluidine, toluene, aniline, diphenyl mercury, hexamethylbenzene,  
20 malononitrile, tetracyanoethylene, thiophene, benzene-selenol, tetrafluoroethylene, ethylene, N-nitrosodiphenylamine, acetylene, 1,2,4-trichlorobenzene, propane and the like.

However, when a recording head of a high density  
25 multi-orifice type is manufactured, apart from the above-mentioned organic materials, it is desirable to use organic materials capable of being very easily processed by a fine

1 photolithography as materials for forming the second protective layer.

As examples of the organic materials, there may be preferably used, for example, polyimidoisoindoloquinazo-  
5 linedione (trade name; PIQ, produced by Hitachi Kasei Co., Japan), polyimide resin (trade name: PYRALIN, produced by Du Pont, U.S.A.), cyclized polybutadiene (trade name: JSR-CBR, CBR-M901, Japan Synthetic Rubber Co., Japan), Phtotonith (trade name: produced by Toray Co., Japan), other photo-  
10 sensitive polyimide and the like.

As the material constituting resistive heater layer 210, there may be used most materials capable of generating heat as desired by flowing electric current.

However, it is desirable that the materials are  
15 neither chemically changed by nor dissolved in the ink used and have high heat resistance.

As examples of the materials, there may be preferably used, for example, tantalum nitride, nichrome, silver-palladium alloy, silicon semiconductor, or a metal  
20 such as hafnium, lanthanum, zirconium, titanium, tantalum, tungsten, molybdenum, niobium, chromium, vanadium and the like, alloys thereof, borides thereof or the like.

Even if the ink in the liquid flow path contacts the substrate through cracks and pinholes formed in upper  
25 layer 211, these materials are passivated at the portion contacting the ink and a passive layer is formed. Therefore, the ink does not reach the electrode layer

1 and electrolytic corrosion does not occur. Thereby  
durability for the liquid jet recording head is improved.

Using the above-mentioned material, the resistive  
heater layer 210 may be formed by the procedure such as an  
5 electron beam method, a sputtering method and the like.

As the materials for constituting electrodes 212  
and 213, there may be effectively used most of conventional  
electrode materials, and there are mentioned, for example,  
Al, Ag, Au, Pt, Cu and the like. The electrodes may be  
10 formed at a predetermined position with a predetermined  
size, shape and thickness by means of vapor deposition or  
the like.

Lower layer 209 is provided so as to control mainly  
the transfer of heat generated at heat generating portion  
15 207 to support 214. The construction material is selected  
and the layer thickness is designed in such a way that the  
heat generated at heat generating portion 207 flows more to  
the heat actuating portion 206 side than to other portions  
when heat energy is applied to the liquid at heat actuating  
20 portion 206 while the heat remaining at heat generating  
portion 207 flows rapidly to the support 214 side when the  
electric current to electrothermal transducer is switched  
off.

As the material for constituting lower layer 209,  
25 there may be used inorganic materials represented by metal  
oxides such as  $\text{SiO}_2$ , zirconium oxide, tantalum oxide,  
magnesium oxide and the like.

1           Support 214 is composed of silicon, glass, ceramics  
or the like.

          As the materials for constituting the grooved plate  
203 and the common liquid chamber provided at the upstream  
5   portion of heat actuating portion 206, there may be used  
most of the materials satisfying the following conditions:  
i) the shape is hardly or not thermally affected during  
fabricating the recording head or under the circumstance of  
using the recording head; ii) a fine precise processing can  
10 be applied thereto and the surface accuracy can be easily  
obtained as desired; and iii) the resulting liquid paths can  
be processed to permit the liquid to flow smoothly in the  
paths.

          Representative materials for the above-mentioned  
15 purpose are preferably ceramics, glass, metals, plastics,  
silicon wafer and the like, and in particular, glass and  
silicon wafer are more preferable since they are easily  
processed, and have an appropriate degree of heat  
resistance, coefficient of thermal expansion and thermal  
20 conductivity. It is desired to apply to the outer surface  
of the circumference of orifice 204 a water repellent  
treatment where the liquid is aqueous and an oil repellent  
treatment where the liquid is non-aqueous, so as to prevent  
the liquid from leaking and flowing to the outside portion  
25 of orifice 204.

          The said orifice may be formed by adhering a photo-  
sensitive resin plate such as a dry film and the like to

1 substrate, forming a pattern by photolithography and then  
adhering the ceiling plate.

As described above, resistive heater layer 210 may  
be formed on the whole surface of electrodes 212 and 213 as  
5 shown in FIG. 3A, or only on the surface of electrodes 212  
and 213 under the liquid flow path 215 as shown in FIG. 3B.  
Alternatively, in case that dissolution of electrodes can be  
almost prevented by selecting appropriately the material of  
the upper layer 211 or an appropriate structure of the  
10 upper layer 211 composed of first protective layer 211-1  
and second protective layer or third protective layer 211-2,  
as shown in FIG. 3C, a sufficient effect can be obtained by  
providing resistive heater layer 210 only on a limited  
portion.

15 Further, the width of resistive heater layer 210 is  
most preferably wider than widths of electrodes 212 and 213  
as shown in FIG. 4A. However, as shown in FIG. 4B, it is  
necessary only that the surface of the electrodes is almost coated  
with resistive heater layer 210. Alternatively, the width  
20 of resistive heater layer 210 at the heat actuating portion  
may be narrower than that of the resistive heater layer  
coating the electrode as shown in FIG. 4C.

The liquid jet recording head of the present  
invention is illustrated by referring to the following  
25 Example.

#### Example

Liquid jet recording heads of the present invention

1 as shown in FIG. 2, FIG. 3A and FIG. 4A were manufactured as shown below.

An  $\text{SiO}_2$  film of 5  $\mu\text{m}$  thick was formed by thermally oxidizing an Si wafer. On the  $\text{SiO}_2$  film, Ti layer of 50  $\text{\AA}$   
5 thick and Al layer of 5,000  $\text{\AA}$  thick were deposited successively by an electron beam deposition. By photolithographic steps, the electrode was patterned to form electrodes 212 and 213.

As the next step, a resistive heater layer composed  
10 of  $\text{HfB}_2$  of 1500  $\text{\AA}$  thick was formed by sputtering and then, by photolithographic steps, a portion corresponding to the resistive heater layer was patterned with a resist, followed by etching a portion corresponding to heat actuating portion  
207 to form resistive heater layer 210. Size of the heat  
15 actuating surface was 30  $\mu\text{m}$  in width and 150  $\mu\text{m}$  in length.

Then, upper layer 111 composed of  $\text{SiO}_2$  of 2.8  $\mu\text{m}$  thick was deposited by a high rate sputtering.

Grooved plate 203 composed of glass was adhered on the predetermined place of the substrate fabricated as  
20 described above. Size of liquid flow path 215 was 50  $\mu\text{m}$  in width and 50  $\mu\text{m}$  in height. The resulting liquid jet recording head ( $B_1$ ) and a conventional liquid jet recording head (A) were investigated for the rate of a breakdown (the number of open wire/all segments) by applying a pulse-shaped  
25 signal having 40 V, 10  $\mu\text{s}$  in pulse width and 5 kHz in repetition frequency to an ink (pH4-9) maintained at 60°C. The results are as shown in Table 1. The liquid jet

1 recording head of the present invention has excellent durability and can keep, over a long time, the good initial property for forming droplets.

The heads  $B_2$  and  $B_3$  were similarly fabricated using  
5 resistive heater layer 210 comprising  $TaN_2$  or Ta and were investigated for the rate of breakdown. As shown in Table 1, the results indicate that the heads  $B_2$  and  $B_3$  have excellent durability and can keep the good initial property for forming droplets over a long time.

10

Table 1

Type of head		Constructive material		Rate of breakdown			
		Electrode	Resistive heating element	$10^5$	$10^6$	$10^7$	$10^8$
A		Al	HfB <sub>2</sub>	5%	12%	32%	89%
B	1	Al	HfB <sub>2</sub>	0%	1%	5%	21%
	2	Al	TaN <sub>2</sub>	0%	0%	2%	17%
	3	Al	Ta	0%	0%	1%	17%

15  
20 The said resistive heater layer may be coated on the whole surface of the electrode, only on a portion corresponding to the liquid flow path or only on the heat actuating portion and its vicinity. The coating portion may be determined in accordance with a combination with the upper layer.

25 Width of the resistive heater layer overlying the electrode is not critical as far as it can almost cover the electrode. The width on the heat actuating surface where



1 an electrode is not provided may be narrower than that at a  
portion overlying the electrode. By constructing as  
described above, a rise of temperature at the boundary  
between the electrode and the resistive heater layer is  
5 suppressed and a recording head having a higher reliability  
can be provided.

10

15

20

25

CLAIMS:

1. A substrate for a liquid jet recording head, the substrate carrying an electrode arrangement in the form of a u-shape with a break being formed in the u-shape to provide a pair of electrodes, and a resistive heater layer coating and covering at least part of each electrode and bridging the break between the electrodes to form an electrothermal transducer.
2. A liquid jet recording head having a substrate carrying an electrode arrangement in the form of a u-shape with a break being formed in the u-shape to provide a pair of electrodes, and a resistive heater layer coating and covering at least part of each electrode and bridging the break between the electrodes to form an electrothermal transducer.
3. A liquid jet recording head comprising a substrate as claimed in claim 1 and a member which, with the substrate, defines a liquid flow path extending past the electrothermal transducer to a discharge orifice.

4. A head according to claim 3, wherein the resistive heater layer is provided under the liquid flow path.

5 5. A substrate or head according to any preceding claim, wherein the width of the resistive heater layer is narrowed between the electrodes.

10 6. A substrate or head according to any preceding claim, wherein the substrate has further an upper layer.

15 7. A substrate or head according to claim 6, wherein the upper layer is composed of inorganic insulating material.

20 8. A substrate or head according to claim 6, wherein the upper layer is composed of inorganic insulating material, organic material and inorganic material.

25 9. A substrate or head as claimed in claim 6, wherein the upper layer comprises inorganic insulating material inorganic material or organic material provided on at least a part of the upper portion of the electrodes and inorganic insulating material

provided on at least a part of the resistive heater layer between the electrodes.

5 10. A substrate or head as claimed in any preceding claim, wherein the electrodes and the resistive heater layer are formed successively on the substrate.

10 11. A substrate or head as claimed in any preceding claim, wherein the electrode arrangement is shaped substantially as shown in any of Figures 4A to 4C of the accompanying drawings.

15 12. A liquid recording head or substrate therefor substantially as described in the description with reference to Figures 2 to 4 of the drawings.

---

TIMED: 26/02/91 09:46:28

PAGE: 1

REGISTER ENTRY FOR GB2154950

Form 1 Application No GB8502461.0 filing date 31.01.1985

Priority claimed:

31.01.1984 in Japan - doc: 59014520

Title LIQUID JET RECORDING HEAD

Applicant/Proprietor

CANON KABUSHIKI KAISHA, Incorporated in Japan, 3-30-2 Shimomaruko,  
Ohta-ku, Tokyo, Japan

[ADP No. 00363119027]

Inventors

MASAMI IKEDA, 84-1 Morino 6-chome, Machida-shi, Tokyo, Japan

[ADP No. 00907329001]

MAKOTO SHIBATA, 203-18-403 Takamura, Hiratsuka-shi, Kanagawa-ken, Japan

[ADP No. 03466497001]

HIROTO TAKAHASHI, 1848 Ohkami, Hiratsuka-shi, Kanagawa-ken, Japan

[ADP No. 03466471001]

HIROKAZU KOMURO, 27-6 Mitsuke-cho, Hiratsuka-shi, Kanagawa-ken, Japan

[ADP No. 03488061001]

HIROTO MATSUDA, 3649-302 Kokubu, Ebina-shi, Kanagawa-ken, Japan

[ADP No. 03466489001]

HISANORI TSUDA, 78-3-104 Onna, Atsugi-shi, Kanagawa-ken, Japan

[ADP No. 03488079001]

Classified to

B6F

B41J

Address for Service

BERESFORD & CO, 2-5 Warwick Court, High Holborn, London, WC1R 5DJ, United  
Kingdom

[ADP No. 00001826001]

Publication No GB2154950 dated 18.09.1985

Examination requested 05.02.1986

Patent Granted with effect from 09.11.1988 (Section 25(1)) with title LIQUID  
JET RECORDING HEAD AND SUBSTRATE THEREFORE

---

\*\*\*\* END OF REGISTER ENTRY \*\*\*\*