



(86) Date de dépôt PCT/PCT Filing Date: 2012/09/28
(87) Date publication PCT/PCT Publication Date: 2013/04/04
(85) Entrée phase nationale/National Entry: 2014/03/26
(86) N° demande PCT/PCT Application No.: JP 2012/075230
(87) N° publication PCT/PCT Publication No.: 2013/047830
(30) Priorité/Priority: 2011/09/30 (JP2011-216967)

(51) Cl.Int./Int.Cl. *C22C 38/00* (2006.01),
C21D 9/46 (2006.01), *C22C 18/00* (2006.01),
C22C 38/60 (2006.01), *C23C 2/02* (2006.01),
C23C 2/06 (2006.01), *C23C 2/28* (2006.01)

(71) Demandeur/Applicant:
NIPPON STEEL & SUMITOMO METAL
CORPORATION, JP

(72) Inventeurs/Inventors:
WAKABAYASHI, CHISATO, JP;
AZUMA, MASAFUMI, JP;
FUJITA, NOBUHIRO, JP;
SANO, KOHICHI, JP

(74) Agent: GOUDREAU GAGE DUBUC

(54) Titre : FEUILLE D'ACIER GALVANISEE PAR IMMERSION A CHAUD A HAUTE RESISTANCE ET FEUILLE D'ACIER GALVANISEE PAR IMMERSION A CHAUD ALLIEE A HAUTE RESISTANCE, CHACUN AYANT UNE RESISTANCE A LATRACTION DE 980 MPa OU PLUS, UNE EXCELLENTE ADHESION DE PLACAGE, UNE EXCELLENTE APTITUDE AU FORMAGE ET D'EXCELLENTE PROPRIETES D'EXPANSION DES TROUS ET LEUR PROCEDE DE FABRICATION

(54) Title: HIGH-STRENGTH HOT-DIP GALVANIZED STEEL SHEET AND HIGH-STRENGTH ALLOYED HOT-DIP GALVANIZED STEEL SHEET HAVING EXCELLENT PLATING ADHESION, FORMALITY, AND HOLE EXPANDABILITY WITH TENSILE STRENGTH OF 980 MPa OR MORE AND MANUFACTURING METHOD THEREFOR

(57) **Abrégé/Abstract:**

A high-strength hot-dipped galvanized steel sheet which has a tensile strength of 980 MPa or more, while having excellent plating adhesion, formability and bore expanding properties. This high-strength hot-dipped galvanized steel sheet has a hot-dipped zinc plating layer on the surface of a matrix steel sheet, and the matrix steel sheet contains, in mass%, 0.05-0.4% of C, 0.01-3.0% of Si, 0.1-3.0% of Mn and 0.01-2.0% of Al, while satisfying $Si + Al > 0.5\%$ and suppressing P to 0.04% or less, S to 0.05% or less and N to 0.01% or less, with the balance made up of iron and unavoidable impurities. The microstructure of the matrix steel sheet contains 40% by volume or more of martensite and bainite in total, 8% by volume or more of residual austenite, with the balance made up of ferrite or ferrite and 10% by volume or less of pearlite. The martensite contains two or more of the three kinds of martensite (1), (2) and (3) in an amount of 10% by volume or more in total, and the hot-dipped zinc plating layer contains less than 7% by mass of Fe.



ABSTRACT

Provided is a high-strength hot-dip galvanized steel sheet having excellent plating adhesion, formability, and hole expandability with an ultimate tensile strength of 980 MPa or more, the hot-dip galvanized steel sheet comprising a hot-dip galvanized layer formed on a surface of a base steel sheet. The base steel sheet contains, by mass%, C: 0.05% to 0.4%; Si: 0.01% to 3.0%; Mn: 0.1% to 3.0%; Al: 0.01 to 2.0%; in which Si + Al > 0.5%, P: limited to 0.04% or less; S: limited to 0.05% or less; N: limited to 0.01% or less; and a balance including Fe and inevitable impurities, a microstructure of the base steel sheet contains 40% or more by total volume fraction of martensite and bainite, 8% or more by volume fraction of residual austenite, and a balance of the microstructure being ferrite or ferrite and 10% or less by volume fraction of pearlite. The martensite contains 10% or more by total volume fraction of two or more kinds of three kinds of martensites (1), (2), and (3), and the hot-dip galvanized layer contains less than 7 mass% of Fe.

HIGH-STRENGTH HOT-DIP GALVANIZED STEEL SHEET AND HIGH-STRENGTH
ALLOYED HOT-DIP GALVANIZED STEEL SHEET HAVING EXCELLENT
PLATING ADHESION, FORMABILITY, AND HOLE EXPANDABILITY WITH
TENSILE STRENGTH OF 980 MPa OR MORE AND MANUFACTURING METHOD
THEREFOR

[Technical Field]

[0001]

The present invention relates to a high-tensile steel sheet having excellent
formability (ductility and hole expandability) and to an alloyed hot-dip galvanized steel
sheet using TRIP (Transformation Induced Plasticity) phenomenon and a manufacturing
method thereof.

This application claims priority on Japanese Patent Application No.
2011-216967, filed on September 30, 2011, the content of which is incorporated herein by
reference.

[Background Art]

[0002]

High strengthening of a steel sheet which is a raw material has been in progress
so as to realize both of compatibility between a weight saving of a body, components, and
the like of a vehicle, and safety. Generally, when the strength of the steel sheet increases,
formability (ductility and hole expandability) is damaged. Therefore, the balance of
strength and formability is necessary in order to use the high-strength steel sheet for the
members of the vehicles. For this requirement, hitherto, a so-called TRIP steel sheet
using transformation induced plasticity of residual austenite has been suggested (for
example, refer to Patent Literature 1 and Patent Literature 2). The high strength steel
sheet for the vehicle requires corrosion resistance depending on components to be applied.
An alloyed hot-dip galvanized steel sheet is applied to such a case. However, Si is
added to the TRIP steel to improve the ductility. When the Si concentrated on the

surface of the steel sheet oxidizes, the TRIP steel has a problem in that galvanizing faults easily occur at the time of hot-dip galvanizing.

[0003]

A manufacturing method of a high-strength alloyed hot-dip galvanized steel sheet has been disclosed in Patent Literatures 3 and 4 which can achieve wettability improvement of plating and reduction of alloying temperature by performing Ni pre-plating on an Si-added high strength steel sheet and working a surface layer to activate. In this method, a hot-dip galvanized steel sheet and an alloyed hot-dip galvanized steel sheet can be manufactured by re-heating and plating a cold-rolled steel sheet, in which a material as an original sheet is previously integrated, produced by a cold rolling-annealing process.

[0004]

In addition, a technique has been proposed in Patent Literature 5 which produces a high elongation-type alloyed hot-dip galvanized steel sheet by utilizing a Ni pre-plating technique. This method relates to manufacturing a high-strength steel sheet having excellent corrosion resistance by making steel consisting of ferrite and martensite by controlling steel components, annealing conditions, alloying hot-dip galvanizing conditions or the like and then performing hot-dip galvanizing.

[0005]

However, in the hot-dip galvanized steel sheet and the alloyed hot-dip galvanized steel sheet, the martensite, which is once generated, is softened when the steel sheet is re-heated in the galvanizing process, and thus a desired strength cannot be obtained. In this way, it is difficult to achieve both of high strengthening and formability, and a hot-dip galvanized steel sheet and an alloyed hot-dip galvanized steel sheet having good corrosion resistance with high tensile strength of 980 MPa or more and excellent formability have been desired.

[Prior Art Literature(s)]

[Patent Literature(s)]

[0006]

[Patent Literature 1] JP 61-217529A

5 [Patent Literature 2] JP 5-59429A

[Patent Literature 3] JP 2526320B

[Patent Literature 4] JP 2526322B

[Patent Literature 5] JP 2006-283071A

[Summary of the Invention]

10 [Problem(s) to Be Solved by the Invention]

[0007]

The present invention is to solve the above-described problems and to provide a high-strength hot-dip galvanized steel sheet and an alloyed hot-dip galvanized steel sheet having excellent ductility and hole expandability by combining a rolling process with heat treatment in a hot-dip galvanizing line.

15

[Means for Solving the Problem(s)]

[0008]

The present inventors examined in detail on a structure control due to heat treatment and effects of working and heat treatment with respect to various steels in which contents of C, Si, and Mn are varied. As a result, the present inventors have found that a steel sheet having unique structures can be obtained by working and heat treatment using heat treatment in continuous annealing, rolling working, and heat treatment during subsequent plating treatment. In addition, the inventors have found that the steel sheet can have ultimate tensile strength of 980 MPa or more which has been a problem until now, excellent formability (ductility and hole expandability), and plating property.

25

[0009]

The gist of the present invention are as follows.

[1] A high-strength hot-dip galvanized steel sheet having excellent plating adhesion, formability, and hole expandability with an ultimate tensile strength of 980 MPa or more, the hot-dip galvanized steel sheet comprising a hot-dip galvanized layer formed on a surface of a base steel sheet,

wherein the base steel sheet contains: by mass%,

C: 0.05% to 0.4%;

Si: 0.01% to 3.0%;

10 Mn: 0.1% to 3.0%;

Al: 0.01 to 2.0%; in which Si + Al > 0.5%

P: limited to 0.04% or less;

S: limited to 0.05% or less;

N: limited to 0.01% or less; and

15 a balance including Fe and inevitable impurities,

a microstructure of the base steel sheet contains 40% or more by total volume fraction of martensite and bainite, 8% or more by volume fraction of residual austenite, and a balance of the microstructure being ferrite or ferrite and 10% or less by volume fraction of pearlite,

20 the martensite contains 10% or more by total volume fraction of two or more kinds of three kinds of martensites (1), (2), and (3) below, and

the hot-dip galvanized layer contains less than 7 mass% of Fe,

the martensite (1): C concentration (when there is a cementite precipitation, also including C in cementite); CM1 is less than 0.8 mass%, and nano-indentation test hardness Hit1 satisfies Expression 1.

$$\text{Hit1}/\{-982.1 \times (\text{CM1})^2 + 1676 \times \text{CM1} + 189\} \leq 0.50 \cdots \text{Expression 1}$$

the martensite (2): C concentration (when there is a cementite precipitation, also including C in cementite); CM2 is 0.8 mass% or more, and nano-indentation test hardness Hit2 satisfies Expression 2.

$$\text{Hit2}/\{-982.1 \times (\text{CM2})^2 + 1676 \times \text{CM2} + 189\} \leq 0.50 \cdots \text{Expression 2}$$

5 the martensite (3): C concentration (when there is a cementite precipitation, also including C in cementite); CM3 is 0.8 mass% or more, and nano-indentation test hardness Hit3 satisfies Expression 3.

$$0.5 < \text{Hit3}/\{-982.1 \times (\text{CM3})^2 + 1676 \times \text{CM3} + 189\} \leq 0.80 \cdots \text{Expression 3}$$

[0010]

10 [2] The high-strength hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to [1], wherein the base steel sheet further contains one or two or more of: by mass%,

Cr: 0.05 to 1.0%;

15 Mo: 0.05 to 1.0%;

Ni : 0.05 to 1.0%; and

Cu: 0.05 to 1.0%.

[0011]

[3] The high-strength hot-dip galvanized steel sheet having the excellent plating
20 adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to [1], wherein the base steel sheet further contains one or two or more of: by mass%,

Nb: 0.005 to 0.3%;

Ti: 0.005 to 0.3%; and

25 V: 0.01 to 0.5%.

[0012]

[4] The high-strength hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980

MPa or more according to [1], wherein the base steel sheet further contains B: 0.0001 to 0.1% by mass%.

[0013]

[5] The high-strength hot-dip galvanized steel sheet having the excellent plating
5 adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to [1], wherein the base steel sheet further contains one or two or more of: by mass%,

Ca: 0.0005 to 0.01%;

Mg: 0.0005 to 0.01%; and

10 REM: 0.0005 to 0.01%.

[0014]

[6] A high-strength alloyed hot-dip galvanized steel sheet having excellent plating
adhesion, formability, and hole expandability with an ultimate tensile strength of 980 MPa or more, the alloyed hot-dip galvanized steel sheet comprising an alloyed hot-dip
15 galvanized layer formed on a surface of a base steel sheet,

wherein the base steel sheet contains: by mass%,

C: 0.05% to 0.4%;

Si: 0.01% to 3.0%;

Mn: 0.1% to 3.0%;

20 Al: 0.01 to 2.0%; in which Si + Al > 0.5%

P: limited to 0.04% or less;

S: limited to 0.05% or less;

N: limited to 0.01% or less; and

a balance including Fe and inevitable impurities,

25 a microstructure of the base steel sheet contains 40% or more by total volume fraction of martensite and bainite, 8% or more by volume fraction of residual austenite, and a balance of the microstructure being ferrite or ferrite and 10% or less by volume fraction of pearlite,

the martensite contains 10% or more by total volume fraction of two or more kinds of three kinds of martensites (1), (2), and (3) below, and

the alloyed hot-dip galvanized layer contains 7 to 15 mass% of Fe,

the martensite (1): C concentration (when there is a cementite precipitation, also including C in cementite); CM1 is less than 0.8 mass%, and nano-indentation test hardness Hit1 satisfies Expression 1.

$$\text{Hit1}/\{-982.1 \times (\text{CM1})^2 + 1676 \times \text{CM1} + 189\} \leq 0.50 \cdots \text{Expression 1}$$

the martensite (2): C concentration (when there is a cementite precipitation, also including C in cementite); CM2 is 0.8 mass% or more, and nano-indentation test hardness Hit2 satisfies Expression 2.

$$\text{Hit2}/\{-982.1 \times (\text{CM2})^2 + 1676 \times \text{CM2} + 189\} \leq 0.50 \cdots \text{Expression 2}$$

the martensite (3): C concentration (when there is a cementite precipitation, also including C in cementite); CM3 is 0.8 mass% or more, and nano-indentation test hardness Hit3 satisfies Expression 3.

$$0.5 < \text{Hit3}/\{-982.1 \times (\text{CM3})^2 + 1676 \times \text{CM3} + 189\} \leq 0.80 \cdots \text{Expression 3}$$

[0015]

[7] The high-strength alloyed hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to [6], wherein the base steel sheet further contains one or two or more of: by mass%,

Cr: 0.05 to 1.0%;

Mo: 0.05 to 1.0%;

Ni : 0.05 to 1.0%; and

Cu: 0.05 to 1.0%.

25 [0016]

[8] The high-strength alloyed hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of

980 MPa or more according to [6], wherein the base steel sheet further contains one or two or more of: by mass%,

Nb: 0.005 to 0.3%;

Ti: 0.005 to 0.3%; and

5 V: 0.01 to 0.5%.

[0017]

[9] The high-strength alloyed hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to [6], wherein the base steel sheet further contains B: 0.0001
10 to 0.1% by mass%.

[0018]

[10] The high-strength alloyed hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to [6], wherein the base steel sheet further contains one or
15 two or more of: by mass%,

Ca: 0.0005 to 0.01%;

Mg: 0.0005 to 0.01%; and

REM: 0.0005 to 0.01%.

[0019]

20 [11] A manufacturing method of a high-strength hot-dip galvanized steel sheet having excellent plating adhesion, formability, and hole expandability with an ultimate tensile strength of 980 MPa or more, the manufacturing method comprising:

with respect to a steel billet containing: by mass%,

C: 0.05% to 0.4%;

25 Si: 0.01% to 3.0%;

Mn: 0.1% to 3.0%;

Al: 0.01 to 2.0%; in which $Si + Al > 0.5\%$

P: limited to 0.04% or less;

S: limited to 0.05% or less;

N: limited to 0.01% or less; and

a balance including Fe and inevitable impurities,

heating to 1200°C or higher and performing hot rolling at an Ar3 transformation

5 temperature or higher;

performing cold rolling on a base steel sheet after the hot rolling at a reduction ratio of 40 to 70%;

annealing the base steel sheet after the cold rolling at 730 to 900°C;

cooling the base steel sheet after the annealing to a temperature of 650 to 750°C
10 at an average cooling rate of 0.1 to 200°C/second, and cooling the base steel sheet to 450°C or lower from the temperature of 650 to 750°C at an average cooling rate of 20°C/second or faster;

holding the base steel sheet cooled to the 450°C or lower in a range of 350 to 450°C for 120 seconds or longer;

15 cooling the base steel sheet held in the range of 350 to 450°C to 70°C or lower at an average cooling rate of 5°C/second or faster;

rolling the base steel sheet cooled to the room temperature at an elongation percentage of 0.2 to 2%;

heating the rolled base steel sheet to “temperature of hot-dip galvanizing bath -
20 40”°C to “temperature of hot-dip galvanizing bath + 50”°C at an average temperature rising rate of 10°C/second or faster;

dipping and hot-dip galvanizing the base steel sheet heated to the “temperature of hot-dip galvanizing bath - 40”°C to “temperature of hot-dip galvanizing bath + 50”°C into a hot-dip galvanizing bath; and

25 cooling the hot-dip galvanized steel sheet, which is hot-dip galvanized, to 70°C or lower at an average cooling rate of 5°C/second or faster.

[0020]

[12] The manufacturing method of the high-strength hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to [11], wherein a hot-dip galvanizing bath flows at a flow rate of 10 m/min or more and 50 m/min or less at the time of the hot-dip galvanizing.

[0021]

[13] The manufacturing method of the high-strength hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to [11], wherein before being heated to the “temperature of hot-dip galvanizing bath - 40”°C to “temperature of hot-dip galvanizing bath + 50”°C, the base steel sheet is subjected to pickling, and then a surface of the base steel sheet is polished and removed to a depth of 0.1 μm or more and is pre-plated with 0.2 to 2g/m² of Ni.

[0022]

[14] A manufacturing method of a high-strength alloyed hot-dip galvanized steel sheet having excellent plating adhesion, formability, and hole expandability with an ultimate tensile strength of 980 MPa or more, the manufacturing method comprising:

with respect to a steel billet containing: by mass%,

C: 0.05% to 0.4%;

Si: 0.01% to 3.0%;

Mn: 0.1% to 3.0%;

Al: 0.01 to 2.0%; in which Si + Al > 0.5%

P: limited to 0.04% or less;

S: limited to 0.05% or less;

N: limited to 0.01% or less; and

a balance including Fe and inevitable impurities,

heating to 1200°C or higher and performing hot rolling at an Ar₃ transformation temperature or higher;

performing cold rolling on a base steel sheet after the hot rolling at a reduction ratio of 40 to 70%;

5 annealing the base steel sheet after the cold rolling at 730 to 900°C;

cooling the base steel sheet after the annealing to a temperature of 650 to 750°C at an average cooling rate of 0.1 to 200°C/second, and cooling the base steel sheet to 450°C or lower from the temperature of 650 to 750°C at an average cooling rate of 20°C/second or faster;

10 holding the base steel sheet cooled to the 450°C or lower in a range of 350 to 450°C for 120 seconds or longer;

cooling the base steel sheet held in the range of 350 to 450°C to 70°C or lower at an average cooling rate of 5°C/second or faster;

15 rolling the base steel sheet cooled to the room temperature at an elongation percentage of 0.2 to 2%;

heating the rolled base steel sheet to “temperature of hot-dip galvanizing bath - 40”°C to “temperature of hot-dip galvanizing bath + 50”°C at an average temperature rising rate of 10°C/second or faster;

20 dipping and hot-dip galvanizing the base steel sheet heated to the “temperature of hot-dip galvanizing bath - 40”°C to “temperature of hot-dip galvanizing bath + 50”°C into a hot-dip galvanizing bath and performing alloying-heating treatment at “temperature of hot-dip galvanizing bath - 40”°C or higher and 560°C or lower within 40 seconds; and

25 cooling the alloyed hot-dip galvanized steel sheet, which is subjected to the alloying-heating treatment, to 70°C or lower at an average cooling rate of 5°C/second or faster.

[0023]

[15] The manufacturing method of the high-strength alloyed hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the

ultimate tensile strength of 980 MPa or more according to [14], wherein a hot-dip galvanizing bath flows at a flow rate of 10 m/min or more and 50 m/min or less at the time of the hot-dip galvanizing.

[0024]

- 5 [16] The manufacturing method of the high-strength alloyed hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to [14], wherein before being heated to the “temperature of hot-dip galvanizing bath - 40”°C to “temperature of hot-dip galvanizing bath + 50”°C, the base steel sheet is subjected to pickling, and then a surface
10 of the base steel sheet is polished and removed to a depth of 0.1 μm or more and is pre-plated with 0.2 to 2g/m² of Ni.

[Effect(s) of the Invention]

[0025]

- According to the present invention, it is possible to obtain a hot-dip galvanized
15 steel sheet and an alloyed hot-dip galvanized steel sheet having excellent formability with high strength and to remarkably contribute to the industry.

[Mode(s) for Carrying out the Invention]

[0026]

The present invention will be described below in detail.

- 20 (Microstructure of base steel sheet)

First, microstructures of a base steel sheet according to the present invention will be described. The microstructures of the base steel sheet according to the present invention include bainite, martensite, and a residual austenite. Further, the martensite includes two or more kinds of three kinds of martensites (1), (2), and (3) defined below.

- 25 [0027]

Martensite (1): C concentration (when there is a cementite precipitation, also including C in cementite). CM1 is less than 0.8 mass% and nano-indentation test hardness Hit1 satisfies Expression 1.

$$\text{Hit1}/\{-982.1 \times (\text{CM1})^2 + 1676 \times \text{CM1} + 189\} \leq 0.50 \cdots \text{Expression 1}$$

Martensite (2): C concentration (when there is a cementite precipitation, also including C in cementite). CM2 is 0.8 mass% or more and nano-indentation test hardness Hit2 satisfies Expression 2.

$$5 \quad \text{Hit2}/\{-982.1 \times (\text{CM2})^2 + 1676 \times \text{CM2} + 189\} \leq 0.50 \cdots \text{Expression 2}$$

Martensite (3): C concentration (when there is a cementite precipitation, also including C in cementite). CM3 is 0.8 mass% or more and nano-indentation test hardness Hit3 satisfies Expression 3.

$$0.5 < \text{Hit3}/\{-982.1 \times (\text{CM3})^2 + 1676 \times \text{CM3} + 189\} \leq 0.80 \cdots \text{Expression 3}$$

10 [0028]

Although the detailed reason is unclear, when two or more kinds of martensites among these three kinds of martensites (1) to (3) are contained 10% or more by total volume fraction, both of strength and hole expandability are achieved. The martensite, which has the hardest structure of structures contained in the base steel sheet of the present invention, is essential to ensure ultimate tensile strength of 980 MPa or more. On the other hand, in a hole expanding test and a bending test, since the martensite is a starting point of void formation, it is known that the martensite deteriorates hole expandability. Therefore, in order to ensure the hole expandability, deformation is prevented from concentrating on a specific martensite grain by mixing two or more kinds of martensites among these three different kinds of martensites. As a result, a technique that does not deteriorate the hole expandability while contributing to higher strengthening has been found. This effect can be obtained when the total volume fraction of the two or more martensites among the three kinds of martensites is set to be 10% or more. From this reason, the lower limit of the volume fraction of the three kinds of martensites (1) to (3) was set to be 10%. Preferably, the lower limit is 15% or more.

25

[0029]

The martensite (1) is a tempered martensite, which is low in C concentration and is not so hard. The C concentration CM1 of the martensite (1) is less than 0.8 mass%.

When there is a cementite precipitation in the martensite (1), C in cementite which is precipitated in the martensite (1) is also contained. The cementite in the martensite mentioned herein may be either of a precipitation in or between martensite laths, so that the effect of the present invention is exhibited. This structure originates from a fresh martensite to be formed at the time of cooling to 70°C or lower after being held at 350 to 450°C in an annealing process of the manufacturing method of the present invention. The martensite (1) is a tempered martensite in which the fresh martensite formed at the time of cooling to 70°C or lower after being held at 350 to 450°C is tempered during dipping treatment into a hot-dip galvanizing bath or alloying treatment.

10 [0030]

The C concentration CM1 of the martensite (1) is less than 0.8 mass%. This also includes a case in which C concentration was reduced to less than 0.8 mass% when C in the fresh martensite was diffused into austenite during the dipping treatment into the hot-dip galvanizing bath or the alloying treatment and thus the fresh martensite was tempered even though C concentration of the fresh martensite was 0.8 mass% or more, in addition to a case in which C concentration of the fresh martensite formed at the time of cooling to 70°C or lower after being held at 350 to 450°C was less than 0.8 mass%.

[0031]

Since the martensite (1) has the C concentration CM1 as low as less than 0.8 mass% and is tempered, it is the softest among three kinds of martensites (1) to (3). Nano-indentation test hardness Hit1 of the martensite (1) satisfies Expression 1. When the volume fraction of the martensite (1) is 60% or more of a microstructure of the base steel sheet, a volume fraction of ferrite and residual austenite becomes too low, and the ductility deteriorates, so that the upper limit is preferably 60%.

25 [0032]

The martensite (2) has a high C concentration, but is martensite which is softened by tempering. C concentration CM2 of the martensite (2) is 0.8 mass% or more. When there is a cementite precipitation in the martensite (2), C in the cementite

which is precipitated in the martensite (2) is also contained. Similarly, the cementite in the martensite may be either of precipitation in or between martensite laths. The martensite (2) originates from strain-induced transformation martensite which is induced by the rolling work and into which a part of a residual austenite is transformed. While the base steel sheet is held at a temperature range of 350 to 450°C after annealing, bainite transformation of the microstructure in the base steel sheet proceeds and thus C is diffused into a non-transformed austenite. A residual austenite, in which C is concentrated, is formed in the base steel sheet which is cooled to 70°C or lower. By strain-induced transformation of the residual austenite, in which C is concentrated, by rolling, martensite which is the origin of the martensite (2) can be obtained. The Martensite (2) is a tempered martensite in which the strain-induced transformation martensite generated by the rolling is tempered during the dipping treatment into the hot-dip galvanizing bath or the alloying treatment.

[0033]

Like the martensite (1), the martensite (2) is a tempered martensite, but is harder than the martensite (1) since the C concentration is high. Nano-indentation test hardness Hit2 of the martensite (2) satisfies Expression 2. When a volume fraction of the martensite (2) is 40% or more of the microstructure of the base steel sheet, the ductility deteriorates, so that the upper limit is preferably set to be 60%.

[0034]

The martensite (3) is martensite which is high in C concentration, is not tempered, or is low in a quantity of tempering. C concentration CM3 of the martensite (3) is 0.8 mass% or more. When there is a cementite precipitation in the martensite (3), C in the cementite which is precipitated in the martensite (3) is also contained. Similarly, the cementite in the martensite may be either of precipitation in or between martensite laths. The martensite (3) is a fresh martensite which is formed by transforming at the time of cooling to 70°C or lower after the hot-dip galvanizing or the alloying-heating treatment. In addition, the martensite (3) is also martensite remaining in a state of fresh

martensite without being tempered substantially during the alloying-heating treatment or the alloying treatment (not in a state of martensites (1) and (2)).

[0035]

The martensite (3) is the hardest structure of three kinds of martensites (1) to (3).
5 Nano-indentation test hardness H_{it3} of the martensite (3) satisfies Expression 3. For this reason, the martensite (3) contributes to high strengthening, but deteriorates the hole expandability. Accordingly, in order to achieve both of the strength and formability, the upper limit of the martensite (3) is 10% in the volume fraction of the microstructure of the base steel sheet. However, when the volume fraction of the martensite (3) becomes too
10 small, it is difficult to ensure strength which is ultimate tensile strength of 980 MPa or more, so that the lower limit is preferably set to be 3% or more.

[0036]

Bainite is effective for ensuring the strength. When a high strength steel sheet having tensile strength exceeding 980 MPa contains martensite and bainite of 40% or
15 more by total volume fraction, it is possible to ensure the strength and to obtain the high hole expandability. When the total volume fraction is less than 40%, the tensile strength is less than 980 MPa. Accordingly, the lower limit was set to be 40%.

[0037]

The residual austenite is a structure to raise ductility, particularly uniformly
20 elongation by transformation-induced plasticity. In order to obtain particularly good elongation, it is necessary to contain the residual austenite of 8% or more by volume fraction. Furthermore, due to transform into martensite by working, the residual austenite also contributes to obtaining of the high strengthening.

[0038]

25 In the microstructure of the base steel sheet of the present invention, ferrite is not essential. However, since the ferrite causes the improvement of ductility, it may be contained. At the time of annealing, it is possible to control the volume fraction of ferrite by performing two-phase annealing. Furthermore, it is possible to control the

volume fraction of ferrite by cooling after annealing. However, when the fraction of ferrite increases, the strength decreases. Although the high strengthening can be obtained by precipitation strengthening and solid solution strengthening, the volume fraction of ferrite is preferably 40% or less.

5 [0039]

Pearlite may be contained as long as the volume fraction is 10% or less. When the volume fraction of pearlite exceeds 10%, the strength and ductility are reduced. Therefore, the upper limit was set to be 10%.

[0040]

10 Furthermore, each phase of the microstructures such as martensite, bainite, austenite, pearlite, and ferrite can be identified and their locations and volume fraction can be observed and quantitatively measured using an optical microscope having a magnification of 1000 times and a scanning and transmission electron microscope having a magnification of 1000 times to 100000 times after a cross section of the steel sheet in a
15 rolling direction or a cross section in the right angle direction of the rolling direction is etched using a Nital reagent and the reagent as disclosed in JP 59-219473A. The area fraction of each structure can be obtained by observing 20 or more fields and applying the point-count method or image analysis. Then, the obtained area fraction is defined as the volume fraction of each structure.

20 [0041]

The classification method of three kinds of martensites (1) to (3) is hardness and C concentration. The hardness may be obtained by measuring nano-indentation testing hardness for three or more points in martensite grains and calculating an average hardness Hit. In the base steel sheet according to the present invention, since a large amount of
25 additive elements are contained, a crystal grain diameter is small. Moreover, in the base steel sheet according to the present invention, there is a case in which an indentation size is greater than the grain diameter of martensite grains in measurement using a Vickers hardness test. Therefore, hardness measurement of a micro-region was performed by a

nano-indenter. Samples cut out parallel to the rolling direction are embedded and then are subjected to mirror-polishing and electrolytic polishing. Then, the hardness measurement was performed on the polished samples. As test conditions, an indentation depth was measured under the condition of 50 nm using a Berkovich-type indenter.

5 Furthermore, this test method is small in an indentation depth, and is sensitive to relation between the grain diameter of martensite and the indentation size, or surface irregularities. Therefore, as a preliminary test, the electrolytic polishing in various conditions and the hardness measurement in the condition with varying an indentation depth are performed, and conditions for obtaining a most reproducible good value was set as test conditions.

10 [0042]

The C concentration of martensite grains may be measured by any measuring method which guarantees precision under the condition of obtaining an accurate decomposition concentration. For example, the C concentration of martensite grains can be obtained by carefully measuring the C concentration at a pitch of 0.5 μm or below
15 using EPMA attached to FE-SEM. Therefore, martensites (1) to (3) are classified according to the hardness and the C concentration.

[0043]

Furthermore, in order to distinguish these martensites (1) to (3), Expressions 1 to 3 use a relational expression between amounts of C CM1 to CM3 and nano-indentation
20 test hardness Hit in each martensite. Denominators of the left sides of Expressions 1, 2, and 3, which are input values of C concentration represent hardness of carbides-free martensite (fresh martensite) of the C concentration. The hardness of the martensite contained in the base steel sheet of the present invention becomes lower than the hardness of a fresh martensite by precipitation of cementite at grains and tempering. Therefore, the
25 classification is performed by taking a ratio between hardness of a fresh martensite of denominator and hardness of martensite of a steel sheet.

[0044]

(Chemical composition of base steel sheet)

Next, a description of reasons for restricting the amounts of the compositions of the base steel sheet in the present invention will be described. Moreover, % in the
5 composition represents % by mass.

[0045]

C: C is added as an element which increases strength of steel and stabilizes a residual austenite to improve ductility. When the content is less than 0.05%, it is difficult to ensure tensile strength of 980 MPa or more. Ductility, weldability, and
10 toughness are remarkably deteriorated by excessive addition exceeding 0.40%. Therefore, the content of C was set to be 0.05 to 0.4%. A more preferred range is 0.13% to 0.3%.

[0046]

Si: Si is an element useful for increasing the strength of the steel sheet by
15 solid-solution strengthening. In addition, Si is an essential element which has an effect for promoting concentration of C in austenite during bainite transformation and generates a residual austenite while annealing, in order to suppress the formation of cementite. These effects are not exhibited when the content is less than 0.01% and scale exfoliation and chemical convertibility generated in hot rolling are remarkably deteriorated by
20 excessive addition exceeding 3.0%. Thus, the content of Si was set to be 0.01 to 3.0%.

[0047]

Mn: Mn is an element effective for improving hardenability. An effect of increasing the hardenability is not sufficiently exhibited when the content is less than 0.1% and the toughness is deteriorated by excessive addition exceeding 3.0%.
25 Accordingly, the content of Mn was set to be 0.1 to 3.0%.

[0048]

Al: Al is an element having a function of deoxidizer. In addition, Al is a ferrite stabilizing element like Si and may be also used as an alternative of Si. Such an effect is

not exhibited when the content is less than 0.01% and the toughness is deteriorated by excessive addition exceeding 2.0%. Therefore, the content of Al was set to be 0.01 to 2.0%.

[0049]

5 Al + Si: Al and Si are elements having the same functions of ferrite stabilization and cementite suppression. Accordingly, a total additive amount of Al and Si is important. When the total additive amount is 0.5% or less, the function of stabilizing the ferrite and suppressing the cementite becomes weak. Therefore, the content was added with an amount larger than 0.5%.

10 [0050]

 P: P is an impurity element which segregates at grain boundaries to make grain boundary strength lower, thereby deteriorating the toughness. Thus, the content is preferably reduced. The upper limit of the content of P was limited to 0.04% in consideration of a current refining technology and manufacturing costs. The lower limit value of P is not particularly determined, but when the lower limit value is less than 0.0001%, it is disadvantageous economically, so this value is preferably set to the lower limit value.

[0051]

 S: S is an impurity element which deteriorates hot workability and toughness, and the content is preferably reduced. Accordingly, the upper limit was limited to 0.05%. The lower limit value of S is not particularly determined, but when the lower limit value is less than 0.0001%, it is disadvantageous economically, so this value is preferably set to the lower limit value.

[0052]

25 N: N forms coarse nitrides to deteriorate bendability and hole expandability. Therefore, it is necessary to suppress the additive amount. The reason is because the tendency becomes remarkable when the content of N exceeds 0.01%. Thus, the content of N was in a range of 0.01% or less. In addition, this causes blowholes to occur at the

time of welding, so the less the better. The effect of the present invention is exhibited without particularly determining the lower limit, but when the content of N is less than 0.0005%, the manufacturing cost dramatically increases, so this value is a substantial lower limit.

5 [0053]

Further, one or two or more elements of Cr, Mo, Ni, and Cu may be added. These elements are elements effective for improving ductility and toughness. However, when the content of Cr, Mo, Ni, and Cu exceeds 1.0%, the toughness can be impaired due to an increase in strength. Accordingly, the upper limit of these elements was set to be 1.0%. Further, in order to improve the ductility and toughness, the necessary content of Cr is 0.05% or more, the necessary content of Mo is 0.05% or more, the necessary content of Ni is 0.05% or more, and the necessary content of Cu is 0.05% or more, so these values are set to the lower limit value, respectively.

[0054]

15 Further, one or two or more elements of Ti, Nb, and V may be added. These elements are elements which form fine carbonitrides and are effective for suppressing coarsening of crystal grains, ensuring the strength, and improving the toughness. In order to ensure the strength and to improve the toughness, it is necessary to add 0.005% or more Ti and Nb and 0.01% or more V. However, when these elements are 20 excessively added, a precipitate becomes coarse and the toughness may be deteriorated. Accordingly, the additive amount of Nb and Ti is preferably set to be 0.3% or less, and the additive amount of V is preferably set to be 0.5 or less.

[0055]

25 B: B is an element which segregates at grain boundaries to suppress grain boundary segregation of P and S. In addition, this element is also effective for improving the hardenability. However, when the content of B exceeds 0.1%, a coarse precipitate occurs at the grain boundaries to impair the hot workability and the toughness. Accordingly, the content of B is set to be 0.1% or lower. Further, in order to enhance

the ductility, toughness, and hot workability and to improve the hardenability by the strengthening of the grain boundaries, the addition of B is preferably 0.0001% or more.

[0056]

Further, one or two or more elements of Ca, Mg, and REM may be added.

5 These elements are elements effective for controlling sulfide forms to suppress the deterioration of the hot workability and toughness due to S. REM indicates a rare earth metal. However, even when these elements are excessively added, since the effect is saturated, it is preferable that 0.01% or less Ca, 0.01% or less Mg, and 0.01% or less REM be added, respectively. In order to improve the toughness, 0.0005% or more Ca,

10 0.0005% or more Mg, and 0.0005% or more REM are preferably added, respectively. Further, in the present invention, REM is generally added in a mischmetal, which in addition to La and Ce may also contain other lanthanoid series elements in combination. The effects of the invention are exhibited even when the lanthanoid series elements other than La and Ce are contained as inevitable impurities. However, the effects of the

15 present invention are exhibited even when metals such as La and Ce are added.

[0057]

(Chemical composition of hot-dip galvanized layer and alloyed hot-dip galvanized layer)

In the present invention, a hot-dip galvanized layer formed on the surface of the base steel sheet contains less than 7 mass% Fe, the balance being Zn and inevitable

20 impurities. In addition, an alloyed hot-dip galvanized layer contains 7 to 15 mass% Fe, and the balance being Zn and inevitable impurities. The hot-dip galvanized layer and the alloyed hot-dip galvanized layer may further contain Al of 0.01 to 0.5 mass% and more preferably, may contain Al of 0.05 to 0.3 mass%. Further, the galvanizing bath may contain Fe, Mg, Mn, Si, Cr and the like in addition to pure zinc and Al.

25 [0058]

In a case where spot weldability and a coating property are desired, it is possible to improve these properties by forming the alloyed hot-dip galvanized layer containing 7 to 15 mass% Fe on the surface of the base steel sheet. Specifically, when the base steel

sheet is subjected to the alloying treatment while being dipped in the galvanizing bath, Fe is incorporated into the galvanized layer, and thus the high-strength alloyed hot-dip galvanized steel sheet having an excellent coating property and spot weldability can be obtained. When the content of Fe after the alloying treatment is less than 7 mass%, the spot weldability becomes insufficient. On the other hand, when the content of Fe exceeds 15 mass%, the adhesion of the galvanized layer itself is impaired, and the galvanized layer is broken and dropped out in machining, thereby causing scratches when forming by adhering to a mold. Accordingly, the content of Fe contained in the galvanized layer during the alloying treatment is within a range of 7 to 15 mass%.

10 [0059]

Further, in a case where the alloying treatment is not performed, even when the content of Fe contained in the galvanized layer is less than 7 mass%, the corrosion resistance, the formability, and hole expandability which are effects obtained by the alloying are good except for the spot welding.

15 [0060]

Further, the galvanized layer may contain Al, Mg, Mn, Si, Cr, Ni, Cu or the like in addition to Fe.

[0061]

In order to measure the content of Fe and Al contained in the galvanized layer, a method of dissolving the galvanized layer with an acid and chemically analyzing the dissolved solution may be used. For example, with respect to the alloyed hot-dip galvanized steel sheet cut into 30 mm × 40 mm, only the galvanized layer is dissolved while suppressing elution of the base steel sheet with an inhibitor-added 5% HCl aqueous solution. Then, the content of Fe and Al is quantified using signal intensities obtained by ICP emission analysis of the dissolved solution and a calibration curve prepared from concentration-known solutions. Further, in consideration of measured variation of samples, an average value is employed obtained by measuring at least three samples which are cut out from the same alloyed hot-dip galvanized steel sheet.

[0062]

The coated amount of the plating is not particularly limited, but is preferably 5 g/m² or more in the coated amount on a single surface of the base steel sheet from the viewpoint of corrosion resistance. In addition, the coated amount on the single surface is preferably no greater than 100 g/m² from the viewpoint of ensuring the plating adhesion.

[0063]

(Manufacturing method of steel sheet)

Next, a manufacturing method will be described.

10 In the present invention, the steel consisting of the above compositions is casted by melting in a conventional manner. The obtained steel billet (cast slab) is subjected to hot rolling. The cast slab is directly cooled or once cooled and then is heated to 1200°C or higher, and the hot rolling is finished at an Ar₃ transformation temperature or higher.

[0064]

15 The base steel sheet (hot-rolled steel sheet) subjected to the hot rolling may be coiled at a temperature region of 700°C or lower. When the coiling temperature exceeds 700°C, the structure of the hot-rolled steel sheet becomes a coarse ferrite or pearlite structure. As a result, a structure of a final steel sheet becomes a non-uniform structure, and thus it is difficult to obtain good hole expandability. Therefore, the upper limit of the coiling temperature is set to be 700°C. More preferably, the upper limit is 650°C or lower and, most preferably, is 550°C at which bainite-single phase is formed. The lower limit of the coiling temperature is not particularly defined. However, when the lower limit is lower than 300°C, the strength of the hot-rolled sheet increases and causes interference of a cold rolling in some cases. Therefore, the lower limit is preferably 20 300°C or higher.

[0065]

Then, the base steel sheet (hot-rolled steel sheet) is subjected to pickling treatment as necessary and then is subjected to the cold rolling at a reduction ratio of 40

to 70%. In order to refine a microstructure after annealing, the cold rolling is performed at the reduction ratio of 40% or more. On the other hand, when the reduction ratio of the cold rolling exceeds 70%, a load is increased by work hardening to cause a loss of productivity. Accordingly, the reduction ratio of the cold rolling is set to be 40 to 70%.

5 [0066]

After the cold rolling, the base steel sheet is annealed at 730 to 900°C. In order to control the microstructure of the base steel sheet, a heating temperature of the annealing and cooling conditions are very important in the present invention. The annealing after the cold rolling is performed at the range of 730 to 900°C to obtain
10 austenite in which C is sufficiently concentrated. When the annealing temperature is lower than 730°C, carbides are melted and remain, and thus a required amount of austenite cannot be obtained. When the annealing temperature exceeds 900°C, it is uneconomical. Further, in a case where the annealing temperature exceeds 900°C, recrystallization proceeds and a grain diameter becomes larger, thereby deteriorating
15 toughness and ductility. Therefore, the annealing temperature is set to be 730 to 900°C.
[0067]

After being subjected to the annealing, the base steel sheet is cooled to a temperature of 600 to 750°C at an average cooling rate of 0.1 to 200°C/second. Thereafter, the base steel sheet is cooled to a temperature of 450°C or lower from a
20 temperature of 600 to 750°C at an average cooling rate of 20°C/second or faster. The purpose of cooling the base steel sheet to the temperature of 600 to 750°C at the average cooling rate of 0.1 to 200°C/second from the temperature region of the annealing is to suppress formation of pearlite which occurs during the cooling process. When the cooling rate is slower than 0.1°C/second, it is difficult to avoid pearlite transformation
25 and a part or all of the austenite is transformed into the pearlite, so that it is difficult to obtain the high strength of 980 MP or more. Therefore, the average cooling rate from the temperature region of the annealing to the temperature of 600 to 750°C is set to be 0.1°C/second or faster. On the other hand, the cooling at the cooling rate of

200°C/second or faster causes not only saturation of the effect but also excessive facility investment, so that economic efficiency becomes poor. Therefore, the upper limit of the cooling rate is set to be 200°C/second.

[0068]

5 When the cooling rate from the temperature of 600 to 750°C to the temperature of 450°C or lower is slow, bainite transformation proceeds and a large amount of carbides are formed in the bainite structure, so that the austenite is decomposed and thus the ductility becomes weak. In addition, since three kinds of martensites (1) to (3) may not be obtained, the balance of the strength and the hole expandability is low. For this
10 reason, it is necessary to cool at the average cooling rate of 20°C/second or faster. Furthermore, the upper limit is not limited, but when the cooling rate is excessively raised, manufacturing cost increases, and thus the upper limit is preferably 200°C/second or slower.

[0069]

15 Next, the base steel sheet is held at the range of 350 to 450°C for 120 seconds or longer. Further, as described above, when the cooling is performed from the temperature of 600 to 750°C to the temperature of 450°C or lower, a cooling stop temperature is set to be 350°C or higher, and then the base steel sheet may be held at the range of 350 to 450°C for 120 seconds or longer. Alternatively, when the cooling is
20 performed from the temperature of 600 to 750°C to the temperature of 450°C or lower, the cooling stop temperature is set to be lower than 350°C, and then the base steel sheet is re-heated and may be held at the range of 350 to 450°C for 120 seconds or longer. The reason is because the holding at the temperature region of 350 to 450°C is to control the stability of austenite. When the holding time is short, the stabilization of austenite is not
25 achieved and a residual austenite 8% or more by volume fraction cannot be obtained. As a result, the balance of the strength and the ductility will be failed. On the other hand, the holding for a long time causes excessive stabilization of the residual austenite, and thus martensite is not formed in the cooling process to room temperature to be

subsequently performed and three kinds of martensites (1) to (3) are not obtained. Accordingly, the holding time is preferably set to be 1000 seconds or shorter.

[0070]

Subsequently, the base steel sheet is cooled once to 70°C or lower at the average
5 cooling rate of 5°C/second or faster. A cooling attainment temperature may be room temperature. However, since the attainment temperature varies depending on the season, the attainment temperature may be 70°C or lower in terms of securing materials and may vary depending on the season. In addition, the average cooling rate up to 70°C needs to be set to be 5°C/second or faster. The upper limit is not particularly determined, but the
10 cooling at the cooling rate over 200°C/second causes not only saturation of the effect but also large facility investment, so that economic efficiency becomes poor. Therefore, the upper limit of the cooling rate is preferably set to be 200°C/second or slower. For this reason, a part of austenite is transformed into martensite. By performing such heat treatment, a composite structure of bainite, a residual austenite, and martensite can be
15 obtained. However, ferrite may be partially contained. Further, the martensite obtained by the cooling up to the room temperature is a fresh martensite which is the origin of the martensite (1).

[0071]

Next, the base steel sheet cooled to 70°C or lower is rolled. A part of residual
20 austenite in the base steel sheet is transformed by the rolling working, and thus a strain-induced transformation martensite is generated. Thus, the strain-induced transformation martensite obtained by the rolling is the origin of the martensite (2). The austenite remaining at the room temperature contains C of 0.8 mass% or more, and the strain-induced transformation martensite formed by the transformation of the above
25 austenite becomes hard. In order to obtain a sufficient strain-induced transformation martensite, an elongation percentage (reduction ratio) of the rolling is set to be 0.2 to 2%. The effect is not sufficient when the elongation percentage is less than 0.2%, and the

yield ratio is significantly increases and the elongation deteriorates when the elongation percentage exceeds 2%.

[0072]

Next, after being subjected to Ni pre-plating as necessary, the base steel sheet is
5 subjected to galvanizing or galvanizing and alloying-heating treatment. In the case of
performing the Ni pre-plating, after the base steel sheet is subjected to the pickling, the
surface of the base steel sheet is removed by polishing to 0.1 μm or more in depth and
then Ni is pre-plated on the surface of the base steel sheet with 0.2 to 2 g/m^2 . In order to
suppress of galvanizing faults and perform the alloying, the surface of the steel sheet is
10 preferably subjected to the polishing or the Ni pre-plating. The reason is because oxides
are easily formed on the surface of the base steel sheet and the galvanizing faults and the
alloying treatment delay of the hot-dip galvanizing easily occur through a plurality of
heating treatment processes.

After the annealing, oxides of Si, Mn and the like exist in the surface layer of the
15 base steel sheet in some cases. When these oxides exist, even if the base steel sheet is
assumed to be subjected to the Ni pre-plating, the galvanizing faults occur in some cases.
For this reason, it is necessary to remove the oxides by performing the polishing. Since
the effect becomes remarkable by polishing to 0.1 μm or more in depth from the surface
layer of the base steel sheet, a polishing quantity is set to be 0.1 μm . The upper limit is
20 not particularly determined. However, since the steel sheet becomes thin and product
yield is reduced according to the polishing quantity, the polishing quantity is preferably
small.

When a Ni-coated amount is set to be 0.2 to 2 g/m^2 , the galvanizing faults are
suppressed at the time of subsequent hot-dip galvanizing. In the Ni-coated amount of
25 less than 0.2 g/m^2 , since the effect of suppressing the galvanizing faults is not sufficiently
obtained, the lower limit thereof is set to be 0.2 g/m^2 . The effect of suppressing the
galvanizing faults can be obtained without specifically determining the upper limit, but
the upper limit exceeding 2.0 g/m^2 causes not only saturation of the effect but also

excessive facility investment, so it is undesirable that the economic efficiency becomes poor. In addition, this requires the excessive facility investment or an operation dropped extremely in sheet-passing speed is required, so it is undesirable that the economic efficiency becomes poor.

5 [0073]

A temperature of the base steel sheet to be dipped in the hot-dip galvanizing bath is in a range from a temperature that is lower by 40°C compared with the temperature of the hot-dip galvanizing bath to a temperature that is higher by 50°C compared with the temperature of the hot-dip galvanizing bath. When the temperature of the base steel
10 sheet to be dipped is below “temperature of hot-dip galvanizing bath - 40” °C, the heat loss upon dipping into the galvanizing bath becomes large and a part of the molten zinc is solidified, thereby leading to a deterioration of the galvanized external appearance in some cases. In addition, when the temperature of the base steel sheet is above “temperature of hot-dip galvanizing bath + 50”°C, operational problems associated with a
15 temperature rise of the galvanizing bath are induced. Further, the temperature of the galvanizing bath is managed to 440 to 470°C. The decrease in temperature of the galvanizing bath leads to solidification of the hot-dip galvanizing existing in the bath and becomes a cause of the galvanizing faults or becomes a cause of appearance deterioration.
[0074]

20 Thus, the rolled base steel sheet should be heated to the “temperature of hot-dip galvanizing bath - 40”°C to the “temperature of hot-dip galvanizing bath + 50”°C. Here, the base steel sheet is heated at an average temperature rising rate of 10°C/second or higher. Here, when the heating rate is slower than 10°C/second, the surface of the base steel sheet is polished and removed while the Ni pre-plating and the induced strain is
25 relaxed, so that alloying-promoting effect cannot be obtained. In addition, when the heating temperature is lower than the “temperature of hot-dip galvanizing bath - 40”, the galvanizing faults easily occur during the hot-dip galvanizing. When the heating temperature is above the “temperature of hot-dip galvanizing bath + 50”°C, the surface of

the base steel sheet is polished and removed and the induced strain is relaxed, so that the alloying-promoting effect cannot be obtained.

[0075]

In a hot-dip galvanizing tank, it is preferable that a jet flow of 10 m/min or more
5 and 50 m/min or less be provided in the galvanizing bath to suppress the galvanizing faults and to promote the alloying. Scum, which is an oxide film of Zn or Al, is floated on the surface of the galvanizing bath. When the oxide film remains on the surface of the base steel sheet in large amounts, the scum adheres to the surface of the base steel sheet at the time of dipping in the galvanizing bath and the galvanizing faults easily occur.
10 Further, the scum adhering to the steel sheet causes not only the galvanizing faults but also the alloying delay.

[0076]

This property is particularly remarkable in the steel sheet containing a lot of Si and Mn. The detailed mechanism is unclear, but it is considered that the galvanizing
15 faults and the alloying delay are facilitated by reacting between the oxide of Si or Mn, which is formed on the surface of the base steel sheet, and the scum that is similarly the oxide. The reason for setting the flow rate of the jet flow to be 10 m/min or more and 50 m/min or less is because the suppressing effect of the galvanizing faults due to the jet flow cannot be obtained at the flow rate slower than 10 m/min. The reason for setting
20 the flow rate to be 50 m/min or less is because the suppressing effect of the galvanizing faults is saturated and a high cost due to the excessive facility investment is also avoided.

[0077]

In addition, the galvanizing bath may contain Fe, Al, Mg, Mn, Si, Cr and the like in addition to pure zinc.

25 [0078]

Then, when the base steel sheet is subjected to the hot-dip galvanizing or the hot-dip galvanizing and the alloying treatment by dipping in the hot-dip galvanizing bath, the martensite in the base steel sheet is tempered. That is, as described above, the fresh

martensite which is the origin of the martensite (1) and the strain-induced transformation martensite which is the origin of the martensite (2) are contained in the base steel sheet to be dipped into the hot-dip galvanizing bath. When the base steel sheet is subjected to the dipping and the alloying heat treatment in the hot-dip galvanizing bath, the fresh
5 martensite and the strain-induced transformation martensite formed previously in the base steel sheet are tempered. As a result, the martensite (1) and the martensite (2) are formed.

[0079]

Next, the hot-dip galvanized steel sheet subjected to the hot-dip galvanizing or
10 the alloyed hot-dip galvanized steel sheet subjected to the hot-dip galvanizing and the alloying treatment is cooled to 70°C or lower. The cooling attainment temperature may be set to be room temperature. However, since the attainment temperature varies depending on the season, the attainment temperature may be 70°C or lower in terms of securing materials and may vary depending on the season. In addition, the average
15 cooling rate up to 70°C needs to be set to be 5°C/second or faster. The upper limit is not particularly determined, but the cooling at the cooling rate over 200°C/second causes not only the saturation of the effect but also the large facility investment, so that it is economically undesirable. Therefore, the upper limit of the cooling rate is preferably set to be 200°C/second or slower. By the cooling, a part of residual austenite in the base
20 steel sheet is transformed into martensite. The martensite generated in this way becomes a martensite (3) which has the hardest structure.

[0080]

In only the heat treatment, only the decomposition of the residual austenite is caused. However, in the present invention, the steel sheet is previously subjected to the
25 rolling and thus the residual austenite is further processed. As a result, a part of residual austenite is transformed into martensite while the cooling after the heat treatment. The martensite (3) obtained as a result becomes a reinforcing structure to achieve high strengthening. The detailed mechanism is unclear, but when the structure of the steel

sheet subjected to the rolling was compared with the structure of the steel sheet, which was not subjected to temper rolling, in detail, this martensite was not observed in the steel sheet which was not subjected to the rolling. For this reason, it is assumed that a dislocation induced while the rolling contributes to the martensite transformation at the time of the heat treatment and subsequent treatment.

[0081]

Furthermore, in order to obtain the martensite (3), it is necessary to heat the base steel sheet to the temperature of “temperature of hot-dip galvanizing bath - 40” (°C) or higher and 560°C or lower. In the heating at the “temperature of hot-dip galvanizing bath - 40” (°C) or lower, the martensite cannot be obtained while the cooling to be performed subsequently. On the other hand, when the base steel sheet is heated to the temperature exceeding 560°C, carbides are remarkably precipitated and the austenite is decomposed, and thus it is difficult to obtain the amount of residual austenite which is required for elongation improvement. For this reason, in the case of performing the hot-dip galvanizing, the heating temperature of the base steel sheet is set to be 560°C or lower. In addition, when the time required for the alloying heat treatment is long, the austenite is decomposed. Accordingly, an alloying treatment time is preferably set to be 40 seconds or shorter.

[0082]

Further, in a facility such as a continuous hot-dip galvanizing facility for continuously performing the heat treatment and plating, the steel sheet is not cooled to the room temperature in a middle course and is not subjected to the rolling in a middle course. Consequently, structure controls of separately manufacturing three kinds of martensites as in the present invention and of ensuring the residual austenite could not be performed. Accordingly, it was difficult to achieve all of the strength, ductility, and hole expandability with a high level.

[0083]

In addition, when the surface layer of the base steel sheet is pre-plated with Ni after being polished and removed to 0.1 μm or thicker, the alloying is promoted during the alloying-heating treatment after the galvanizing to lower the heating temperature at the time of the alloying treatment. For this reason, the cementite is not generated during the alloying-heating treatment and the deterioration of the hole expandability is avoided. The mechanism of the alloying promotion is unclear, but it is considered that the surface is activated due to the strain induced into the surface layer of the steel sheet by the polishing. Examples of methods of polishing and removing the surface layer of the base steel sheet may include brush polishing, sandpaper polishing, or mechanical polishing. The method of the Ni pre-plating may be any one of electroplating, dipping-plating, and spraying-plating, and plating weight is preferably about 0.2 to 2 g/m^2 . When the polishing and removal amount of the surface layer of the steel sheet is 0.1 μm or less and the Ni pre-plating is not performed, or when the pre-plating weight is 0.2 g/m^2 or less or 2 g/m^2 , the promotion effect of the alloying is not obtained and the alloying temperature is inevitably raised. Thus, as described below, the deterioration of the hole expandability is not prevented. In order to further obtain the promotion effect of the alloying, the polishing and removal amount of the surface layer of the steel sheet is preferably set to be 0.5 μm or more.

[0084]

Further, in the case of manufacturing the alloyed hot-dip galvanized steel sheet, an effective Al concentration in the galvanizing bath is preferably controlled in the range of 0.05 to 0.500 mass% to control the properties of the galvanized layer. Here, the effective Al concentration in the galvanizing bath is a value obtained by subtracting a Fe concentration in the galvanizing bath from the Al concentration in the galvanizing bath.

[0085]

When the effective Al concentration is less than 0.05 mass%, dross significantly occurs and a good appearance cannot be obtained. On the other hand, the effective Al

concentration is more than 0.500 mass, the alloying is delayed and the productivity is decreased. From this reason, the upper limit of the effective Al concentration in the galvanizing bath is preferably set to be 0.500 mass%.

[0086]

5 In order to improve the coating property and weldability, the surfaces of the hot-dip galvanized steel sheet and the alloyed hot-dip galvanized steel sheet of the present invention may be subjected to upper layer plating and to a variety of treatments, for example, a chromate treatment, a phosphate treatment, a lubricity-improving treatment, a weldability-improving treatment or the like.

10 [0087]

After the hot-dip galvanizing and the alloying-heating treatment, the rolling is preferably performed for the purpose of the final shape straightening and the loss of yield-point elongation. When the elongation percentage is less than 0.2%, the effect is not sufficient. On the other hand, when the elongation percentage exceeds 1%, the yield
15 ratio dramatically increases and the elongation deteriorates. Therefore, the elongation percentage is preferably set to be 0.2 to 1%. In addition, before dipping into the galvanizing bath, the steel sheet may be subjected to the pickling after the annealing to remove scales generated while annealing.

[Example(s)]

20 [0088]

The effects of the present invention will be now described in more detail using Example. Incidentally, conditions of the examples are condition examples employed for confirming the applicability and effects of the present invention, and the present invention is not limited to these condition examples. The present invention can employ various
25 conditions as long as the object of the present invention is achieved without departing from the gist of the present invention.

[0089]

A hot-dip galvanized steel sheet and an alloyed hot-dip galvanized steel sheet were manufactured under conditions indicated in Tables 2 and 3 by casting steel having compositions indicated in Table 1. First, steel slabs having each composition were heated to a slab heating temperature ($^{\circ}\text{C}$) and then the hot rolling was finished at a finish rolling temperature ($^{\circ}\text{C}$). The obtained hot-rolled steel sheet was coiled at a coiling temperature ($^{\circ}\text{C}$) and then was subjected to the cold rolling indicated by a cold rolling ratio (%). Further, since a sheet shape is poor when the steel sheet was subjected to the cold rolling at a cold rolling ratio of 30% (cold rolling ratio less than 40%) and occurrence of scratches was concerned when the sheet subsequently passed through an annealing facility, the sheet-passing was abandoned. In addition, when the cold rolling was performed at a cold rolling ratio of 80% (cold rolling ratio exceeding 70%), the rolling load became a maximum value and a predetermined sheet thickness was not obtained, so that the cold rolling at the cold rolling ratio of 80% was abandoned.

After the cold rolling, the base steel sheet was annealed at the annealing temperature ($^{\circ}\text{C}$), was cooled (primary cooling) to a primary cooling temperature ($^{\circ}\text{C}$) at a primary cooling rate ($^{\circ}\text{C}/\text{sec.}$), and then was cooled (secondary cooling) to a cooling stop temperature ($^{\circ}\text{C}$) at a secondary cooling rate ($^{\circ}\text{C}/\text{sec.}$). Then, the base steel sheet was held at a holding temperature ($^{\circ}\text{C}$) for a holding time (sec.).

Thereafter, the base steel sheet was cooled to 70°C or lower for the average cooling rate of $5^{\circ}\text{C}/\text{second}$ or faster and then was rolled at a rolling ratio (elongation percentage) (%). The sheet thickness was 1.4 mm. Thereafter, the surface of the base steel sheet was polished and removed up to a depth of a surface polishing quantity (μm) and then was subjected to the Ni pre-plating with the Ni pre-plating weight (g/m^2).

Next, the base steel sheet was heated to the heating temperature ($^{\circ}\text{C}$) at a temperature rising rate ($^{\circ}\text{C}/\text{sec.}$) and then was subjected to the hot-dip galvanizing by dipping into the hot-dip galvanizing bath. In addition the base steel sheet was subjected to the alloying-heating treatment for an alloying time (sec.) at the alloying temperature

(°C), as necessary. Further, the speed of the jet flow (m/min) in the galvanizing bath was provided in a hot-dip galvanizing tank. In addition, the temperature of the galvanizing bath was managed to 440 to 470°C.

Thereafter, the base steel sheet was cooled to 70°C or lower at the average cooling rate of 5°C/second or faster.

[0090]

Mechanical properties, hole expandability (λ), a galvanized external appearance, an alloying degree, and plating adhesion of the obtained hot-dip galvanized steel sheet and the alloyed hot-dip galvanized steel sheet were estimated (Table 4). The mechanical properties were estimated by a tensile test based on JIS Z 2241. Tensile strength (TS) and total elongation (EL) were calculated from a stress-strain curve of the tensile test. Then, TSxEL and TSx λ as an indication of workability were calculated. The hole expandability was estimated by performing a hole expanding test based on Japan Iron and Steel Federation Standard JFS T 1001 to measure a hole expanding ratio. It was determined that the formability was good when the TSxEL was 17000 MPa·% or more and the TSx λ 40000 MPa·% or more. The galvanized external appearance was estimated as marks ○ and × by determining the presence or absence of the galvanizing faults through visual observation. Here, the mark ○ indicates that no galvanizing fault is present, and the mark × indicates that the galvanizing faults are present. The alloying Fe% indicates a mass% of Fe contained in the galvanized layer. In the alloyed hot-dip galvanized steel sheet subjected to the alloying treatment, the content of 7 to 15% Fe indicates that the alloying has well advanced. In the hot-dip galvanized steel sheet which is not subjected to the alloying treatment, the content of Fe may be 7% or less.

[0091]

Experiments No. a, ba, bt, c, d, e, fa, g, ha, ht, i, j, k, l, m, n, and o are the present invention examples in which all of the properties pass and the steel sheet of the aimed property is obtained. On the other hand, in other Experiments No., in which

composition or manufacturing method is out of the range of the present invention, several properties fail to pass.

[0092] [Table 1]

Steel type No.	C	Si	Mn	P	S	N	Al	Al+Si	Others	Note
1	0.13	1.5	2.7	0.01	0.002	0.004	0.015	1.515	-	Inventive steel
2	0.18	1.5	2.4	0.012	0.003	0.0033	0.018	1.518	-	Inventive steel
3	0.19	2.7	1.6	0.011	0.004	0.0043	1.213	3.913	Cr:0.96	Inventive steel
4	0.18	0.1	2.5	0.013	0.004	0.0022	0.51	0.61	Ce:0.01,La:0.002, V:0.4	Inventive steel
5	0.28	1.8	1.6	0.012	0.01	0.0022	0.576	2.376	-	Inventive steel
6	0.27	0.6	2.4	0.01	0.0013	0.0024	1.751	2.351	Mg:0.0008	Inventive steel
7	0.23	1.7	2.5	0.02	0.0023	0.0029	0.019	1.719	Ca:0.008	Inventive steel
8	0.35	1.6	2.4	0.01	0.0014	0.0034	0.785	2.385	-	Inventive steel
9	0.19	1.5	1.9	0.02	0.002	0.0041	0.58	2.08	Ti:0.03	Inventive steel
10	0.19	1.4	1.7	0.03	0.001	0.002	0.46	1.86	B:0.001	Inventive steel
11	0.18	1.3	1.8	0.02	0.002	0.0024	0	1.3	Mo:0.1	Inventive steel
12	0.2	1.8	2.6	0.03	0.001	0.0033	0.08	1.88	Cr:0.8	Inventive steel
13	0.19	1.7	2.5	0.013	0.0015	0.0012	0.023	1.723	Nb:0.051	Inventive steel
14	0.21	1.5	2.4	0.006	0.0042	0.0043	0.033	1.533	Ti:0.056, B:0.0053	Inventive steel
15	0.19	1.8	1.8	0.011	0.0032	0.0027	0.016	1.816	Mo:0.33	Inventive steel
16	0.7	2.4	2.3	0.013	0.0047	0.0039	0.032	2.432	-	Comparative steel
17	0.18	3.4	2.5	0.014	0.0037	0.0015	0.048	3.448	-	Comparative steel
18	0.25	2	3.5	0.014	0.0049	0.0012	0.069	2.069	Ca:0.015	Comparative steel
22	0.19	1.75	2.64	0.08	0.0015	0.005	2.36	4.11	Ca:0.003	Comparative steel
23	0.35	0.1	2.4	0.08	0.0015	0.005	0.164	0.264	-	Comparative steel
24	0.09	2.87	1.8	0.0022	0.0006	0.002	0.02	2.89	Cr:1.8	Comparative steel
25	0.11	1.7	2.9	0.0006	0.0007	0.0003	0.08	1.78	Ti:0.9	Comparative steel

Underlines indicate that a numeral value is out of the range of the present invention

[0093] [Table 2]

Experiment No.	Steel type No.	Slab heating temperature [°C]	Finish rolling temperature [°C]	Coiling temperature [°C]	Cold rolling ratio [%]	Annealing temperature [°C]	Primary cooling temperature [°C]	Primary cooling rate [°C/sec]	Secondary cooling rate [°C/sec]	Cooling stop temperature [°C]	Note
a	1	1230	900	500	50	880	690	1.2	120	370	Present invention steel
ba	2	1230	890	640	55	820	680	1.9	50	290	Present invention steel
bb	2	1220	890	650	55	700	670	10.7	60	380	Comparative steel
bc	2	1200	900	590	55	790	520	1.5	120	380	Comparative steel
bd	2	1180	920	620	55	800	650	0.03	180	370	Comparative steel
be	2	1200	910	570	55	810	670	1.2	8	400	Comparative steel
bf	2	1230	930	630	55	810	740	1.8	60	370	Comparative steel
bg	2	1200	890	580	55	820	710	1.2	50	350	Comparative steel
bh	2	1190	920	600	55	810	730	1.6	60	420	Comparative steel
bi	2	1210	890	590	55	800	740	1.5	50	400	Comparative steel
bj	2	1220	880	580	55	820	710	2.7	70	380	Comparative steel
bk	2	1210	890	600	55	810	720	2.3	80	390	Comparative steel
bl	2	1200	970	600	55	820	710	3.8	120	390	Comparative steel
bm	2	1230	930	600	55	820	710	3.8	100	400	Comparative steel
bn	2	1210	920	610	55	830	680	3.8	120	390	Comparative steel
bo	2	1200	900	640	55	820	680	4.5	60	420	Comparative steel
bp	2	1200	880	530	55	820	680	1.2	80	70	Comparative steel
bq	2	1250	920	540	55	830	690	1.2	80	50	Comparative steel
br	2	1240	920	580	55	820	680	1.2	80	500	Comparative steel
bs	2	1230	900	600	55	820	680	1.2	70	580	Comparative steel
bt	2	1230	920	580	55	820	690	1.2	120	320	Present invention steel
c	3	1210	880	550	57	880	690	3.4	80	360	Present invention steel
d	4	1230	930	500	49	850	690	1.8	70	430	Present invention steel
e	5	1230	950	500	60	870	690	2.9	60	400	Present invention steel
fa	6	1230	890	500	48	880	720	13.5	50	390	Present invention steel
fb	6	1220	870	600	50	680	680	2.4	100	400	Comparative steel
fc	6	1200	890	540	50	820	530	2.4	120	400	Comparative steel
fd	6	1190	900	490	50	800	650	0.06	140	410	Comparative steel
fe	6	1200	930	590	50	840	670	1.6	6	390	Comparative steel
ff	6	1230	890	560	50	850	720	2.4	80	430	Comparative steel
fg	6	1200	900	630	50	840	700	1.6	60	450	Comparative steel
fh	6	1220	960	590	50	850	720	2.2	50	370	Comparative steel
fi	6	1220	950	560	50	840	710	1.6	70	390	Comparative steel
fj	6	1200	920	590	50	860	690	2.8	100	400	Comparative steel
fk	6	1210	900	630	50	830	720	2.4	130	400	Comparative steel
fl	6	1240	960	420	50	840	700	5.6	120	390	Comparative steel
fm	6	1180	890	550	50	850	690	2.4	90	390	Comparative steel
fn	6	1200	900	490	50	840	710	6.2	80	390	Comparative steel
fo	6	1210	910	500	50	830	710	2.4	60	400	Comparative steel
fp	6	1230	930	550	50	810	700	2.4	70	70	Comparative steel
fq	6	1210	880	600	50	810	680	2.4	70	50	Comparative steel
fr	6	1240	900	590	50	810	680	2.4	60	520	Comparative steel
fs	6	1220	910	610	50	810	680	2.4	60	590	Comparative steel
g	7	1250	900	600	49	830	680	10.8	70	410	Present invention steel
ha	8	1250	980	550	50	880	740	16.4	100	420	Present invention steel
hb	8	1220	910	560	50	650	680	1.6	120	380	Comparative steel
hc	8	1180	890	600	50	840	530	1.6	100	380	Comparative steel
hd	8	1200	900	620	50	830	660	0.06	160	400	Comparative steel
he	8	1190	940	550	50	800	690	1.4	4	400	Comparative steel
hf	8	1210	890	590	50	780	730	1.6	80	380	Comparative steel
hg	8	1200	920	600	50	810	680	1.8	50	370	Comparative steel
hh	8	1190	910	570	50	830	710	2.4	60	410	Comparative steel
hi	8	1200	900	580	50	860	720	2.8	190	400	Comparative steel
hj	8	1190	880	480	50	780	740	2.4	100	390	Comparative steel
hk	8	1200	950	550	50	810	700	2.6	80	390	Comparative steel
hl	8	1210	920	540	50	820	710	4.8	60	380	Comparative steel
hm	8	1190	890	600	50	830	700	5.8	70	360	Comparative steel
hn	8	1200	960	620	50	820	730	2.6	70	430	Comparative steel
ho	8	1200	930	580	50	830	720	1.6	80	400	Comparative steel
hp	8	1230	900	600	50	780	680	1.6	80	70	Comparative steel
hq	8	1250	880	610	50	780	680	1.6	80	50	Comparative steel
hr	8	1200	930	600	50	780	690	1.2	60	520	Comparative steel
hs	8	1220	920	590	50	780	680	1.2	60	600	Comparative steel
ht	8	1200	880	570	50	780	660	2.1	80	200	Present invention steel
i	9	1230	920	630	50	840	690	2.5	120	410	Present invention steel
j	10	1210	890	620	50	840	680	2.4	90	400	Present invention steel
k	11	1230	870	650	45	850	690	1.9	60	400	Present invention steel
l	12	1250	930	550	60	860	690	10.9	80	390	Present invention steel
m	13	1220	940	530	50	840	680	5.4	90	390	Present invention steel
n	14	1230	910	560	50	850	680	8.2	100	380	Present invention steel
o	15	1240	950	600	50	860	690	6.2	90	430	Present invention steel
p	16	1250	950	500	60	810	730	1.9	60	430	Comparative steel
q	17	1230	960	600	50	780	700	1.8	120	400	Comparative steel
r	18	1260	920	650	50	840	650	2.5	70	420	Comparative steel
v	22	1200	890	450	50	850	680	10.9	80	410	Comparative steel
w	23	1260	910	490	50	850	630	11.3	80	390	Comparative steel
x	24	1240	900	420	50	850	670	15.4	120	370	Comparative steel
y	25	1230	900	560	50	850	620	13.5	100	380	Comparative steel

Underlines indicate that a numeral value is out of the range of the present invention

[0094] [Table 3]

Experiment No.	Steel type No.	Holding temperature [°C]	Holding time at 350 to 450°C [sec]	Reduction ratio [%]	Surface polishing quantity [μm]	Ni pre-plating weight [g/m ²]	Speed of jet flow in galvanizing bath [m/min]	Temperature rising rate [°C/sec]	Heating temperature [°C]	Alloying time [sec]	Alloying temperature [°C]	Note
a	1	370	150	0.4	0.15	0.21	20	12.4	435	15	475	Present invention steel
ba	2	400	180	0.4	0.16	0.32	15	11.4	462	24	480	Present invention steel
bb	2	380	178	0.6	0.35	1.4	10	16.8	495	20	490	Comparative steel
bc	2	380	162	0.2	0.7	0.9	45	25.3	437	35	505	Comparative steel
bd	2	370	250	0.3	0.15	0.4	20	22.1	421	30	523	Comparative steel
be	2	400	420	0.4	0.21	0.3	20	24.5	460	25	510	Comparative steel
bf	2	370	10	0.2	0.36	0.2	25	26.5	468	31	545	Comparative steel
bg	2	350	240	0	0.21	0.2	25	25.3	478	24	490	Comparative steel
bh	2	420	240	2.8	0.22	0.4	20	28.4	469	19	500	Comparative steel
bi	2	400	120	0.3	0	1.3	20	22.2	458	25	510	Comparative steel
bj	2	380	150	0.2	0.15	0.08	20	24.6	423	15	520	Comparative steel
bk	2	390	240	0.3	0.12	0.8	4	17.6	485	20	500	Comparative steel
bl	2	390	150	0.2	0.15	1.5	20	3.2	427	19	540	Comparative steel
bm	2	400	150	0.3	0.15	1.5	25	20.5	390	15	520	Comparative steel
bn	2	390	150	0.4	0.46	1.5	20	22.4	456	130	520	Comparative steel
bo	2	420	150	0.3	0.46	1.5	20	10.5	450	15	620	Comparative steel
bp	2	360	150	0.4	0.22	0.4	15	12.4	450	20	510	Comparative steel
bq	2	90	150	0.4	0.24	0.4	15	20.3	460	20	500	Comparative steel
br	2	450	150	0.4	0.18	0.4	20	12.4	460	20	500	Comparative steel
bs	2	520	150	0.4	0.21	0.4	20	12.4	450	20	510	Comparative steel
bt	2	380	220	0.3	0.24	2.24	15	14.8	510	25	520	Present invention steel
c	3	360	170	0.4	0.17	0.26	20	20.6	486	35	520	Present invention steel
d	4	430	120	0.2	0.26	1.24	20	16.8	425	21	560	Present invention steel
e	5	400	190	0.3	0.13	1.87	15	10.4	437	13	590	Present invention steel
fa	6	390	400	0.3	0.24	1.44	25	16.5	480	14	490	Present invention steel
fb	6	400	500	0.4	0.22	0.4	30	10.8	480	20	480	Comparative steel
fc	6	400	260	0.3	0.23	0.3	15	16.8	470	16	490	Comparative steel
fd	6	410	500	0.4	0.16	0.6	10	16.8	460	24	480	Comparative steel
fe	6	390	500	0.3	0.26	0.3	15	16.8	450	30	500	Comparative steel
ff	6	430	0	0.3	0.2	0.4	15	10.5	480	16	500	Comparative steel
fg	6	450	180	0	0.16	0.3	20	16.8	480	24	490	Comparative steel
fh	6	370	200	1.6	0.12	0.4	15	20.4	450	30	500	Comparative steel
fi	6	390	500	0.8	0.04	0.3	25	12.4	460	8	540	Comparative steel
fj	6	400	250	0.8	0.16	0	20	10.9	450	16	510	Comparative steel
fk	6	400	125	0.7	0.32	0.3	7	20.4	460	30	490	Comparative steel
fl	6	390	240	0.6	0.18	0.2	20	1.8	480	24	490	Comparative steel
fm	6	390	330	0.9	0.2	0.4	45	16.8	370	30	480	Comparative steel
fn	6	390	500	0.7	0.16	0.5	20	20.5	490	200	540	Comparative steel
fo	6	400	330	0.8	0.22	0.5	20	30.7	500	28	650	Comparative steel
fp	6	370	200	0.2	0.43	0.22	20	10.6	520	28	500	Comparative steel
fq	6	80	200	0.6	0.62	0.45	20	20.8	510	28	500	Comparative steel
fr	6	450	200	0.4	0.26	0.25	20	25.4	500	28	490	Comparative steel
fs	6	540	200	0.3	0.14	0.31	20	20.4	500	24	500	Comparative steel
g	7	410	300	0.2	0.34	0.58	30	18.4	470	30	-	Present invention steel
ha	8	420	260	0.2	0.16	0.24	20	19.3	459	-	-	Present invention steel
hb	8	380	250	0.4	0.12	0.6	20	20.3	455	20	490	Comparative steel
hc	8	380	260	0.3	0.18	0.3	15	19.6	460	30	500	Comparative steel
hd	8	400	180	1	0.22	0.4	30	14.5	470	20	510	Comparative steel
he	8	400	470	0.4	0.18	0.3	25	20.5	480	28	520	Comparative steel
hf	8	380	0	0.9	0.24	0.3	25	10.8	455	24	490	Comparative steel
hg	8	370	190	0	0.24	0.4	20	15.6	480	20	480	Comparative steel
hh	8	410	320	2.2	0.16	0.3	15	16.8	500	24	490	Comparative steel
hi	8	400	450	0.8	0.06	0.4	30	30.8	460	45	500	Comparative steel
hj	8	390	260	0.7	0.18	0.05	40	20.4	460	20	510	Comparative steel
hk	8	390	180	0.8	0.24	0.4	5	18.6	480	30	480	Comparative steel
hl	8	380	220	0.5	0.16	0.8	20	0.8	500	20	470	Comparative steel
hm	8	360	180	0.6	0.12	1.6	50	18.2	290	24	480	Comparative steel
hn	8	430	460	0.8	0.16	0.8	25	20.8	460	200	510	Comparative steel
ho	8	400	280	0.3	0.16	0.6	10	26.8	480	30	630	Comparative steel
hp	8	350	330	0.4	0.22	0.4	15	10.8	470	30	480	Comparative steel
hq	8	80	330	0.5	0.14	0.3	20	20.5	450	24	480	Comparative steel
hr	8	450	330	0.4	0.32	0.2	15	14.6	470	45	480	Comparative steel
hs	8	550	330	0.3	0.28	0.6	20	14.9	460	30	480	Comparative steel
ht	8	380	640	0.4	0.62	0.2	30	16.8	460	30	510	Present invention steel
i	9	410	180	0.4	0.15	0.32	20	11.4	460	24	480	Present invention steel
j	10	400	190	0.2	0.19	0.22	20	25.5	450	35	490	Present invention steel
k	11	400	250	0.3	0.26	0.99	20	36.5	455	21	550	Present invention steel
l	12	390	280	0.5	0.24	1.5	20	19.7	449	-	-	Present invention steel
m	13	390	800	0.4	0.18	0.23	20	20.8	460	-	-	Present invention steel
n	14	380	260	0.3	0.11	0.33	20	8.8	450	16	530	Present invention steel
o	15	430	300	0.6	0.06	0.27	20	30.9	455	9	-	Present invention steel
p	16	430	120	0.3	0.16	1.55	40	10.6	462	15	480	Comparative steel
q	17	400	130	0.4	0.24	1.24	20	10.8	435	16	479	Comparative steel
r	18	420	250	0.5	0.52	1.5	20	12.5	458	17	510	Comparative steel
v	22	410	250	0.2	0.12	0.24	10	10.8	428	30	490	Comparative steel
w	23	390	260	0.7	0.12	0.26	15	15.5	437	25	475	Comparative steel
x	24	370	200	0.6	0.15	0.35	25	18.6	461	19	480	Comparative steel
y	25	380	120	0.4	0.15	0.45	30	14.6	478	-	-	Comparative steel

Underlines indicate that a numeral value is out of the range of the present invention

[0095] [Table 4]

Experi- ment No.	Bainite [%]	Martensite ① [%]	Martensite ② [%]	Martensite ③ [%]	Bainite + Martensite [%]	Residual austenite [%]	Ferrite [%]	Pearlite [%]	TS[MPa]	EL[%]	λ[% &]	TSxEL	TSxλ	Galvanized external appearance	Alloying Fe [%]	Note
a	47	14	3	0	64	8	28	0	987	23	59	22701	58233	○	7.8	Present invention steel
ba	32	4	4	3	43	9	38	10	1013	25	48	25325	48624	○	10.4	Present invention steel
bb	0	0	0	0	0	0	100	0	683	21	67	14343	45761	○	10.5	Comparative steel
bc	23	0	0	0	23	0	62	15	743	18	29	13374	21547	○	11.1	Comparative steel
bd	23	0	0	0	23	0	55	22	789	15	25	11835	19725	○	11.9	Comparative steel
be	38	0	0	0	38	0	49	13	824	16	29	13184	23896	○	11.2	Comparative steel
bf	11	33	14	2	60	2	38	0	1139	11	24	12529	27336	○	10.9	Comparative steel
bg	35	10	0	0	45	16	39	0	1037	26	24	26962	24888	○	8.9	Comparative steel
bh	34	6	12	0	52	3	37	8	923	16	55	14768	50765	○	9.3	Comparative steel
bi	40	6	4	3	53	8	39	0	984	25	45	24600	44280	×	11.3	Comparative steel
bj	38	5	4	3	50	9	41	0	989	23	43	22747	42527	×	11.5	Comparative steel
bk	40	5	4	3	52	10	38	0	982	23	51	22586	50082	×	9.4	Comparative steel
bl	41	5	4	2	52	8	39	1	981	21	41	20601	40221	×	12.3	Comparative steel
bm	43	4	5	3	55	9	36	0	989	23	44	22747	43516	×	11.9	Comparative steel
bn	40	4	4	0	48	4	37	11	923	14	51	12922	47073	○	13.9	Comparative steel
bo	38	5	0	0	43	0	39	18	886	18	39	15948	34554	○	16.3	Comparative steel
bp	8	52	0	0	60	0	40	0	1033	11	23	11363	23759	○	10.7	Comparative steel
bq	7	55	0	0	62	2	36	0	1078	9	32	9702	34496	○	10.2	Comparative steel
br	33	5	0	0	38	0	39	23	834	17	42	14178	35028	○	9.9	Comparative steel
bs	22	0	0	0	22	0	46	32	753	16	46	12048	34638	○	10.6	Comparative steel
bt	29	10	7	6	52	9	39	0	1001	22	65	22022	65065	○	12.8	Present invention steel
c	53	6	3	3	65	11	24	0	1108	21	49	23268	54292	○	11.6	Present invention steel
d	55	8	4	0	67	10	23	0	1239	20	45	24780	55755	○	12.4	Present invention steel
e	48	8	7	3	66	13	21	0	1249	16	30	19984	37470	○	8.7	Present invention steel
fa	45	11	11	9	76	14	10	0	1280	16	32	20480	40960	○	7.9	Present invention steel
fb	0	0	0	0	0	0	100	0	712	20	72	14240	51264	○	8.6	Comparative steel
fc	28	0	0	0	28	0	54	18	775	19	42	14725	32550	○	8.8	Comparative steel
fd	24	0	0	0	24	0	49	27	793	17	38	13481	30134	○	8.3	Comparative steel
fe	42	0	0	0	42	0	33	25	843	15	32	12645	26976	○	9.5	Comparative steel
ff	10	65	3	0	78	4	18	0	1298	9	24	11682	31152	○	9.7	Comparative steel
fg	47	11	0	0	58	23	19	0	1345	15	14	20175	18830	○	8.9	Comparative steel
fh	45	11	27	0	83	2	15	0	1019	8	40	8152	40760	○	11.3	Comparative steel
fi	42	12	9	6	69	12	19	0	1216	15	35	18240	42560	×	12.1	Comparative steel
fj	43	11	9	6	69	13	18	0	1224	14	40	17136	48960	×	11.4	Comparative steel
fk	44	11	10	0	65	14	11	10	1265	13	33	16445	41745	×	10.9	Comparative steel
fl	41	12	11	6	70	11	19	0	1274	16	34	20384	43316	×	9.6	Comparative steel
fm	42	12	12	5	71	12	17	0	1293	15	38	19395	49134	×	9.7	Comparative steel
fn	41	13	8	6	68	0	16	16	805	18	41	14490	33005	○	14.7	Comparative steel
fo	41	11	0	0	52	0	16	32	785	19	42	14915	32970	○	17.2	Comparative steel
fp	11	58	0	0	69	3	28	0	1352	7	9	9464	12168	○	9.2	Comparative steel
fq	9	60	0	0	69	1	30	0	1397	6	4	8382	5588	○	9.6	Comparative steel
fr	39	0	0	0	39	0	38	23	821	17	30	13957	24630	○	9.6	Comparative steel
fs	28	0	0	0	28	0	40	32	782	18	24	14076	18768	○	9.9	Comparative steel
g	49	11	6	0	66	12	22	0	1021	24	51	24504	52071	○	2.8	Present invention steel
ha	52	13	10	7	82	18	0	0	1450	14	31	20300	44950	○	2.7	Present invention steel
hb	0	0	0	0	0	0	100	0	759	20	59	15180	44781	○	9.6	Comparative steel
hc	26	0	0	0	26	0	37	37	824	18	37	14832	30488	○	10.2	Comparative steel
hd	19	0	0	0	19	0	34	47	793	16	32	12688	25376	○	10.5	Comparative steel
he	37	0	0	0	37	0	32	31	857	13	30	11141	25710	○	10.9	Comparative steel
hf	0	55	12	0	67	15	18	0	1652	4	7	6608	11564	○	9.9	Comparative steel
hg	34	15	0	0	49	29	22	0	1523	13	7	19799	10661	○	9.8	Comparative steel
hh	52	14	29	0	95	5	0	0	1221	10	36	12210	43956	○	10.2	Comparative steel
hi	54	11	9	8	82	18	0	0	1434	13	32	18642	45888	×	11.4	Comparative steel
hj	42	11	8	6	67	15	18	0	1426	13	33	18538	47058	×	10.7	Comparative steel
hk	53	13	11	8	85	15	0	0	1462	14	34	20468	49708	×	10	Comparative steel
hl	52	12	10	8	82	18	0	0	1489	14	31	20846	46159	×	8.6	Comparative steel
hm	55	14	10	6	85	15	0	0	1482	13	38	19266	56316	×	8.1	Comparative steel
hn	62	13	11	9	95	5	0	0	1162	11	29	12782	33698	○	13.8	Comparative steel
ho	52	24	0	0	76	0	0	24	1125	7	32	7875	36000	○	16.8	Comparative steel
hp	12	61	0	0	73	3	24	0	1589	6	4	9534	6356	○	10.1	Comparative steel
hq	13	60	0	0	73	0	27	0	1601	5	1	8005	1601	○	9.7	Comparative steel
hr	35	7	0	0	42	0	39	19	923	16	28	14768	25844	○	11.9	Comparative steel
hs	33	0	0	0	33	0	43	24	885	16	25	14160	22125	○	9.9	Comparative steel
ht	20	21	6	4	51	21	28	0	1356	15	35	20340	47460	○	10.3	Present invention steel
i	52	4	4	3	63	10	27	0	1185	17	45	20145	53325	○	10.4	Present invention steel
j	51	9	4	0	64	10	26	0	1205	16	46	19280	55430	○	11.6	Present invention steel
k	54	4	3	4	65	9	26	0	989	23	50	22747	49450	○	12.4	Present invention steel
l	50	8	4	4	66	8	26	0	1201	17	35	20417	42035	○	2.7	Present invention steel
m	55	5	3	4	67	9	24	0	1186	19	39	22534	46254	○	1.6	Present invention steel
n	44	8	6	5	63	10	27	0	1208	17	34	20536	41072	○	11.6	Present invention steel
o	51	6	7	7	71	9	20	0	1226	16	36	19616	44136	○	1.7	Present invention steel
p	0	63	22	0	85	15	0	0	1950	5	3	9750	5850	○	10.5	Comparative steel
q	16	5	5	3	29	10	61	0	945	18	26	17010	24570	×	6.8	Comparative steel
r	10	75	13	0	98	2	0	0	1523	9	29	13707	44167	○	8.9	Comparative steel
v	16	0	0	0	16	13	71	0	894	17	24	15198	21456	○	10.7	Comparative steel
w	92	8	0	0	100	0	0	0	927	11	62	10197	57474	○	12.5	Comparative steel
x	62	21	11	3	97	3	0	0	862	18	24	15516	20688	○	11.8	Comparative steel
y	5	0	0	0	5	0	95	0	1342	7	16	9394	21472	○	2.1	Comparative steel

Underlines indicate that a numeral value is out of the range of the present invention

[Industrial Applicability]

[0096]

5 The present invention provides the high-strength galvanized steel sheet having excellent formability with the ultimate tensile strength of 980 MPa or more, which is suitable for the structural member, the reinforcing member, and the suspension member of automobiles. Accordingly, the present invention can be expected to greatly contribute to the lighter-weight of automobiles and is extremely high in effect in industry.

CLAIMS

[Claim 1]

A high-strength hot-dip galvanized steel sheet having excellent plating adhesion, formability, and hole expandability with an ultimate tensile strength of 980 MPa or more,

5 the hot-dip galvanized steel sheet comprising a hot-dip galvanized layer formed on a surface of a base steel sheet,

wherein the base steel sheet contains: by mass%,

C: 0.05% to 0.4%;

Si: 0.01% to 3.0%;

10 Mn: 0.1% to 3.0%;

Al: 0.01 to 2.0%; in which Si + Al > 0.5%

P: limited to 0.04% or less;

S: limited to 0.05% or less;

N: limited to 0.01% or less; and

15 a balance including Fe and inevitable impurities,

a microstructure of the base steel sheet contains 40% or more by total volume fraction of martensite and bainite, 8% or more by volume fraction of residual austenite, and a balance of the microstructure being ferrite or ferrite and 10% or less by volume fraction of pearlite,

20 the martensite contains 10% or more by total volume fraction of two or more kinds of three kinds of martensites (1), (2), and (3) below, and

the hot-dip galvanized layer contains less than 7 mass% of Fe,

the martensite (1): C concentration (when there is a cementite precipitation, also including C in cementite); CM1 is less than 0.8 mass%, and nano-indentation test

25 hardness Hit1 satisfies Expression 1.

$$\text{Hit1}/\{-982.1 \times (\text{CM1})^2 + 1676 \times \text{CM1} + 189\} \leq 0.50 \cdots \text{Expression 1}$$

the martensite (2): C concentration (when there is a cementite precipitation, also including C in cementite); CM2 is 0.8 mass% or more, and nano-indentation test hardness Hit2 satisfies Expression 2.

$$\text{Hit2}/\{-982.1 \times (\text{CM2})^2 + 1676 \times \text{CM2} + 189\} \leq 0.50 \cdots \text{Expression 2}$$

5 the martensite (3): C concentration (when there is a cementite precipitation, also including C in cementite); CM3 is 0.8 mass% or more, and nano-indentation test hardness Hit3 satisfies Expression 3.

$$0.5 < \text{Hit3}/\{-982.1 \times (\text{CM3})^2 + 1676 \times \text{CM3} + 189\} \leq 0.80 \cdots \text{Expression 3}$$

10 [Claim 2]

The high-strength hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to claim 1, wherein the base steel sheet further contains one or two or more of: by mass%,

15 Cr: 0.05 to 1.0%;
Mo: 0.05 to 1.0%;
Ni : 0.05 to 1.0%; and
Cu: 0.05 to 1.0%.

20 [Claim 3]

The high-strength hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to claim 1, wherein the base steel sheet further contains one or two or more of: by mass%,

25 Nb: 0.005 to 0.3%;
Ti: 0.005 to 0.3%; and
V: 0.01 to 0.5%.

[Claim 4]

The high-strength hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to claim 1, wherein the base steel sheet further contains B: 0.0001 to 0.1% by mass%.

[Claim 5]

The high-strength hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to claim 1, wherein the base steel sheet further contains one or two or more of: by mass%,

Ca: 0.0005 to 0.01%;

Mg: 0.0005 to 0.01%; and

REM: 0.0005 to 0.01%.

[Claim 6]

A high-strength alloyed hot-dip galvanized steel sheet having excellent plating adhesion, formability, and hole expandability with an ultimate tensile strength of 980 MPa or more, the alloyed hot-dip galvanized steel sheet comprising an alloyed hot-dip galvanized layer formed on a surface of a base steel sheet,

wherein the base steel sheet contains: by mass%,

C: 0.05% to 0.4%;

Si: 0.01% to 3.0%;

Mn: 0.1% to 3.0%;

Al: 0.01 to 2.0%; in which $Si + Al > 0.5\%$

P: limited to 0.04% or less;

S: limited to 0.05% or less;

N: limited to 0.01% or less; and

a balance including Fe and inevitable impurities,

a microstructure of the base steel sheet contains 40% or more by total volume fraction of martensite and bainite, 8% or more by volume fraction of residual austenite, and a balance of the microstructure being ferrite or ferrite and 10% or less by volume fraction of pearlite,

the martensite contains 10% or more by total volume fraction of two or more kinds of three kinds of martensites (1), (2), and (3) below, and

the alloyed hot-dip galvanized layer contains 7 to 15 mass% of Fe,

the martensite (1): C concentration (when there is a cementite precipitation, also including C in cementite); CM1 is less than 0.8 mass%, and nano-indentation test hardness Hit1 satisfies Expression 1.

$$\text{Hit1}/\{-982.1 \times (\text{CM1})^2 + 1676 \times \text{CM1} + 189\} \leq 0.50 \cdots \text{Expression 1}$$

the martensite (2): C concentration (when there is a cementite precipitation, also including C in cementite); CM2 is 0.8 mass% or more, and nano-indentation test hardness Hit2 satisfies Expression 2.

$$\text{Hit2}/\{-982.1 \times (\text{CM2})^2 + 1676 \times \text{CM2} + 189\} \leq 0.50 \cdots \text{Expression 2}$$

the martensite (3): C concentration (when there is a cementite precipitation, also including C in cementite); CM3 is 0.8 mass% or more, and nano-indentation test hardness Hit3 satisfies Expression 3.

$$0.5 < \text{Hit3}/\{-982.1 \times (\text{CM3})^2 + 1676 \times \text{CM3} + 189\} \leq 0.80 \cdots \text{Expression 3}$$

[Claim 7]

The high-strength alloyed hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to claim 6, wherein the base steel sheet further contains one or two or more of: by mass%,

Cr: 0.05 to 1.0%;

Mo: 0.05 to 1.0%;

Ni : 0.05 to 1.0%; and

Cu: 0.05 to 1.0%.

[Claim 8]

5 The high-strength alloyed hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to claim 6, wherein the base steel sheet further contains one or two or more of: by mass%,

Nb: 0.005 to 0.3%;

10 Ti: 0.005 to 0.3%; and

V: 0.01 to 0.5%.

[Claim 9]

15 The high-strength alloyed hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to claim 6, wherein the base steel sheet further contains B: 0.0001 to 0.1% by mass%.

[Claim 10]

20 The high-strength alloyed hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to claim 6, wherein the base steel sheet further contains one or two or more of: by mass%,

Ca: 0.0005 to 0.01%;

25 Mg: 0.0005 to 0.01%; and

REM: 0.0005 to 0.01%.

[Claim 11]

A manufacturing method of a high-strength hot-dip galvanized steel sheet having excellent plating adhesion, formability, and hole expandability with an ultimate tensile strength of 980 MPa or more, the manufacturing method comprising:

- 5 with respect to a steel billet containing: by mass%,
C: 0.05% to 0.4%;
Si: 0.01% to 3.0%;
Mn: 0.1% to 3.0%;
Al: 0.01 to 2.0%; in which $Si + Al > 0.5\%$
- 10 P: limited to 0.04% or less;
S: limited to 0.05% or less;
N: limited to 0.01% or less; and
a balance including Fe and inevitable impurities,
heating to 1200°C or higher and performing hot rolling at an Ar3 transformation
- 15 temperature or higher;
performing cold rolling on a base steel sheet after the hot rolling at a reduction ratio of 40 to 70%;
annealing the base steel sheet after the cold rolling at 730 to 900°C;
cooling the base steel sheet after the annealing to a temperature of 650 to 750°C
- 20 at an average cooling rate of 0.1 to 200°C/second, and cooling the base steel sheet to 450°C or lower from the temperature of 650 to 750°C at an average cooling rate of 20°C/second or faster;
holding the base steel sheet cooled to the 450°C or lower in a range of 350 to 450°C for 120 seconds or longer;
- 25 cooling the base steel sheet held in the range of 350 to 450°C to 70°C or lower at an average cooling rate of 5°C/second or faster;
rolling the base steel sheet cooled to the room temperature at an elongation percentage of 0.2 to 2%;

heating the rolled base steel sheet to “temperature of hot-dip galvanizing bath - 40”°C to “temperature of hot-dip galvanizing bath + 50”°C at an average temperature rising rate of 10°C/second or faster;

dipping and hot-dip galvanizing the base steel sheet heated to the “temperature
5 of hot-dip galvanizing bath - 40”°C to “temperature of hot-dip galvanizing bath + 50”°C into a hot-dip galvanizing bath; and

cooling the hot-dip galvanized steel sheet, which is hot-dip galvanized, to 70°C or lower at an average cooling rate of 5°C/second or faster.

10 [Claim 12]

The manufacturing method of the high-strength hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to claim 11, wherein a hot-dip galvanizing bath flows at a flow rate of 10 m/min or more and 50 m/min or less at the
15 time of the hot-dip galvanizing.

[Claim 13]

The manufacturing method of the high-strength hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the
20 ultimate tensile strength of 980 MPa or more according to claim 11, wherein before being heated to the “temperature of hot-dip galvanizing bath - 40”°C to “temperature of hot-dip galvanizing bath + 50”°C, the base steel sheet is subjected to pickling, and then a surface of the base steel sheet is polished and removed to a depth of 0.1 μm or more and is pre-plated with 0.2 to 2g/m² of Ni.

[Claim 14]

A manufacturing method of a high-strength alloyed hot-dip galvanized steel sheet having excellent plating adhesion, formability, and hole expandability with an ultimate tensile strength of 980 MPa or more, the manufacturing method comprising:

5 with respect to a steel billet containing: by mass%,

C: 0.05% to 0.4%;

Si: 0.01% to 3.0%;

Mn: 0.1% to 3.0%;

Al: 0.01 to 2.0%; in which $Si + Al > 0.5\%$

10 P: limited to 0.04% or less;

S: limited to 0.05% or less;

N: limited to 0.01% or less; and

a balance including Fe and inevitable impurities,

15 heating to 1200°C or higher and performing hot rolling at an Ar3 transformation temperature or higher;

performing cold rolling on a base steel sheet after the hot rolling at a reduction ratio of 40 to 70%;

annealing the base steel sheet after the cold rolling at 730 to 900°C;

20 cooling the base steel sheet after the annealing to a temperature of 650 to 750°C at an average cooling rate of 0.1 to 200°C/second, and cooling the base steel sheet to 450°C or lower from the temperature of 650 to 750°C at an average cooling rate of 20°C/second or faster;

holding the base steel sheet cooled to the 450°C or lower in a range of 350 to 450°C for 120 seconds or longer;

25 cooling the base steel sheet held in the range of 350 to 450°C to 70°C or lower at an average cooling rate of 5°C/second or faster;

rolling the base steel sheet cooled to the room temperature at an elongation percentage of 0.2 to 2%;

heating the rolled base steel sheet to “temperature of hot-dip galvanizing bath - 40”°C to “temperature of hot-dip galvanizing bath + 50”°C at an average temperature rising rate of 10°C/second or faster;

dipping and hot-dip galvanizing the base steel sheet heated to the “temperature
5 of hot-dip galvanizing bath - 40”°C to “temperature of hot-dip galvanizing bath + 50”°C into a hot-dip galvanizing bath and performing alloying-heating treatment at “temperature of hot-dip galvanizing bath - 40”°C or higher and 560°C or lower within 40 seconds; and

cooling the alloyed hot-dip galvanized steel sheet, which is subjected to the alloying-heating treatment, to 70°C or lower at an average cooling rate of 5°C/second or
10 faster.

[Claim 15]

The manufacturing method of the high-strength alloyed hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the
15 ultimate tensile strength of 980 MPa or more according to claim 14, wherein a hot-dip galvanizing bath flows at a flow rate of 10 m/min or more and 50 m/min or less at the time of the hot-dip galvanizing.

[Claim 16]

20 The manufacturing method of the high-strength alloyed hot-dip galvanized steel sheet having the excellent plating adhesion, formability, and hole expandability with the ultimate tensile strength of 980 MPa or more according to claim 14, wherein before being heated to the “temperature of hot-dip galvanizing bath - 40”°C to “temperature of hot-dip galvanizing bath + 50”°C, the base steel sheet is subjected to pickling, and then a surface
25 of the base steel sheet is polished and removed to a depth of 0.1 μm or more and is pre-plated with 0.2 to 2g/m² of Ni.