



(86) Date de dépôt PCT/PCT Filing Date: 2006/12/29  
(87) Date publication PCT/PCT Publication Date: 2007/07/12  
(85) Entrée phase nationale/National Entry: 2008/05/07  
(86) N° demande PCT/PCT Application No.: US 2006/049624  
(87) N° publication PCT/PCT Publication No.: 2007/079246  
(30) Priorité/Priority: 2005/12/30 (US60/755,197)

(51) Cl.Int./Int.Cl. *C09J 127/14* (2006.01),  
*C09D 127/14* (2006.01), *C09D 127/16* (2006.01),  
*C09J 127/16* (2006.01)  
(71) Demandeur/Applicant:  
E. I. DU PONT DE NEMOURS AND COMPANY, US  
(72) Inventeurs/Inventors:  
DEBERGALIS, MICHAEL, US;  
SNOW, LARRY GLEN, US  
(74) Agent: TORYS LLP

(54) Titre : FILMS REVETUS DE FLUOROPOLYMERES UTILISABLES DANS DES MODULES PHOTOVOLTAIQUES  
(54) Title: FLUOROPOLYMER COATED FILMS USEFUL FOR PHOTOVOLTAIC MODULES

(57) **Abrégé/Abstract:**

A fluoropolymer coated film comprising polymeric substrate film and fluoropolymer coating on the polymeric substrate film. The fluoropolymer coating comprises fluoropolymer selected from homopolymers and copolymers of vinyl fluoride and homopolymers and copolymers of vinylidene fluoride polymer blended with compatible adhesive polymer comprising functional groups selected from carboxylic acid, sulfonic acid, aziridine, anhydride, amine, isocyanate, melamine, epoxy, hydroxy, anhydride and mixtures thereof. The polymeric substrate film comprises functional groups on its surface that interact with the compatible adhesive polymer to promote bonding of the fluoropolymer coating to the substrate film.



## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
12 July 2007 (12.07.2007)

PCT

(10) International Publication Number  
**WO 2007/079246 A3**

## (51) International Patent Classification:

**C09J 127/14** (2006.01)      **C09D 127/14** (2006.01)  
**C09J 127/16** (2006.01)      **C09D 127/16** (2006.01)

## (21) International Application Number:

PCT/US2006/049624

## (22) International Filing Date:

29 December 2006 (29.12.2006)

## (25) Filing Language:

English

## (26) Publication Language:

English

## (30) Priority Data:

60/755,197      30 December 2005 (30.12.2005)      US

(71) **Applicant** (for all designated States except US): **E. I. DU PONT DE NEMOURS AND COMPANY** [US/US]; 1007 Market Street, Wilmington, Delaware 19898 (US).

## (72) Inventors; and

(75) **Inventors/Applicants** (for US only): **DEBERGALIS, Michael** [US/US]; 6362 Bridlewood Drive South, East Amherst, New York 14051 (US). **SNOW, Larry, Glen** [US/US]; 146 East Main Street, Leroy, New York 14482 (US).

(74) **Agent**: **HENDRICKSON, John, S.**; E. I. du Pont de Nemours and Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, Delaware 19805 (US).

(81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

## (88) Date of publication of the international search report:

23 August 2007

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) **Title**: FLUOROPOLYMER COATED FILMS USEFUL FOR PHOTOVOLTAIC MODULES

(57) **Abstract**: A fluoropolymer coated film comprising polymeric substrate film and fluoropolymer coating on the polymeric substrate film. The fluoropolymer coating comprises fluoropolymer selected from homopolymers and copolymers of vinyl fluoride and homopolymers and copolymers of vinylidene fluoride polymer blended with compatible adhesive polymer comprising functional groups selected from carboxylic acid, sulfonic acid, aziridine, anhydride, amine, isocyanate, melamine, epoxy, hydroxy, anhydride and mixtures thereof. The polymeric substrate film comprises functional groups on its surface that interact with the compatible adhesive polymer to promote bonding of the fluoropolymer coating to the substrate film.



**WO 2007/079246 A3**



**TITLE OF INVENTION****FLUOROPOLYMER COATED FILMS USEFUL FOR PHOTOVOLTAIC  
MODULES**

5

**FIELD OF INVENTION**

This invention relates to forming a fluoropolymer coated film which is useful as a backsheet in a photovoltaic module.

**BACKGROUND OF THE INVENTION**

10

Photovoltaic cells are used to produce electrical energy from sunlight, offering a green alternative to traditional methods of electricity generation. These solar cells are built from various semiconductor systems which must be protected from environmental effects such as moisture, oxygen, and UV light. The cells are usually jacketed on both  
15 sides by encapsulating layers of glass and/or plastic films forming a multilayer structure known as a photovoltaic module. Fluoropolymer films are recognized as an important component in photovoltaic modules due to their excellent strength, weather resistance, UV resistance, and moisture barrier properties. Especially useful in these modules are film composites  
20 of fluoropolymer film and polyester film which act as a backing sheet for the module. Such composites have traditionally been produced from preformed films of fluoropolymer, specifically polyvinyl fluoride (PVF), adhered to polyester substrate film, specifically polyethylene terephthalate. When fluoropolymer such as PVF is used as a backing sheet to the  
25 module, its properties significantly improve module life, allowing module warranties of up to 25 years. Fluoropolymer backing sheets are frequently employed in the form of laminate with polyethylene terephthalate (PET) films, typically with the PET sandwiched between two fluoropolymer films.

30

However, laminates of preformed fluoropolymer films on polymeric substrates having a bond which will not delaminate after years of outdoor exposure are difficult to make. Prior art systems such as U.S. Patent 3,133,854 to Simms, U.S. Patent 5,139,878 to Kim *et al.*, and US 6,632,518 to Schmidt *et al.* describe primers and adhesives for preformed films that will produce durable laminate structures. However, these

processes require the application of at least one adhesive layer, or both a primer and adhesive layer, prior to the actual lamination step. The lamination step then requires the application of heat and pressure to form the laminate. Therefore, prior art laminates using preformed fluoropolymer  
5 films are expensive to manufacture and/or require capital intensive equipment. Because preformed fluoropolymer films must have sufficient thickness to provide strength for handling during manufacture and subsequent processing, the resulting laminates may also incorporate thick expensive layers of fluoropolymer, i.e., thicker than are necessary for an  
10 effective protective layer.

### **SUMMARY OF THE INVENTION**

The invention provides a fluoropolymer coated film comprising polymeric substrate film and fluoropolymer coating on the polymeric  
15 substrate film. The fluoropolymer coating comprises fluoropolymer selected from homopolymers and copolymers of vinyl fluoride and homopolymers and copolymers of vinylidene fluoride polymer blended with compatible adhesive polymer comprising functional groups selected from carboxylic acid, sulfonic acid, aziridine, anhydride, amine, isocyanate,  
20 melamine, epoxy, hydroxy, anhydride and mixtures thereof. The polymeric substrate film comprises functional groups on its surface that interact with the compatible adhesive polymer to promote bonding of the fluoropolymer coating to the substrate film.

The invention provides a fluoropolymer coated polymer film  
25 with fewer overall processing steps than manufacturing laminates with preformed fluoropolymer films while providing strong adhesion to the substrate and good durability to the fluoropolymer coated substrate. In addition, providing the fluoropolymer in the form of a coating enables thinner fluoropolymer layers if desired to save cost. Employing  
30 fluoropolymer coatings also enables the incorporation of additives into the fluoropolymer layer tailored to the intended use of the fluoropolymer coated film, e.g., fillers which improve barrier properties.



## **DETAILED DESCRIPTION OF THE INVENTION**

### **Fluoropolymers**

Fluoropolymers useful in the fluoropolymer coated film in accordance with the invention are selected from homopolymers and copolymers of vinyl fluoride (VF) and homopolymers and copolymers of vinylidene fluoride (VF<sub>2</sub>) polymer. Preferably, the fluoropolymer is selected from homopolymers and copolymers of vinyl fluoride comprising at least 60 mole % vinyl fluoride and homopolymers and copolymers of vinylidene fluoride comprising at least 60 mole % vinylidene fluoride. More preferably, the fluoropolymer is selected from homopolymers and copolymers of vinyl fluoride comprising at least 80 mole % vinyl fluoride and homopolymers and copolymers of vinylidene fluoride comprising at least 80 mole % vinylidene fluoride. Blends of the fluoropolymers with nonfluoropolymers, e.g., acrylic polymers, may also be suitable for the practice of the invention. Homopolymer polyvinyl fluoride (PVF) and homopolymer polyvinylidene fluoride (PVDF) are well suited for the practice of the invention.

For the practice of the invention with VF copolymers or VF<sub>2</sub> copolymers, comonomers can be either fluorinated or nonfluorinated or mixtures thereof. By the term "copolymers" is meant copolymers of VF or VF<sub>2</sub> with any number of additional fluorinated monomer units so as to form dipolymers, terpolymers, tetrapolymers, etc. If nonfluorinated monomers are used, the amount used should be limited so that the copolymer retains the desirable properties of the fluoropolymer, i.e., weather resistance, solvent resistance, barrier properties, etc. Preferably, fluorinated comonomers are used including fluoroolefins, fluorinated vinyl ethers, or fluorinated dioxoles. Examples of useful fluorinated comonomers include tetrafluoroethylene (TFE), hexafluoropropylene (HFP), chlorotrifluoroethylene (CTFE), trifluoroethylene, hexafluoroisobutylene, perfluorobutyl ethylene, perfluoro (propyl vinyl ether) (PPVE), perfluoro (ethyl vinyl ether) (PEVE), perfluoro (methyl vinyl ether) (PMVE), perfluoro-2,2-dimethyl-1,3-dioxole (PDD) and perfluoro-2-methylene-4-methyl-1,3-dioxolane (PMD) among many others.

Homopolymer PVDF coatings can be formed from a high molecular weight PVDF. Blends of PVDF and alkyl (meth)acrylates polymers can be used. Polymethyl methacrylate is particularly desirable. Typically, these blends can comprise 50-70% by weight of PVDF and 30-  
5 50% by weight of alkyl (meth)acrylate polymers, preferably, polymethyl methacrylate. Such blends may contain compatibilizers and other additives to stabilize the blend. Such blends of polyvinylidene fluoride, or vinylidene fluoride copolymer, and acrylic resin as the principal components are described in U.S. patents 3,524,906; 4,931,324; and  
10 5,707,697.

Homopolymer PVF coatings can be formed from a high molecular weight PVF. Suitable VF copolymers are taught by US Patents 6,242,547 and 6,403,740 to Uschold.

#### 15 Compatible Adhesive Polymers

The compatible adhesive polymers employed in the fluoropolymer coated film according to the invention comprise functional groups selected from carboxylic acid, sulfonic acid, aziridine, amine, isocyanate, melamine, epoxy, hydroxy, anhydride and mixtures thereof.  
20 The compatible adhesive polymer preferably has (1) a backbone composition that is compatible with the fluoropolymer in the composition and (2) pendant functionality capable of reacting with complementary functional groups on a substrate film surface. The compatibility of the adhesive polymer backbone with the fluoropolymer will vary but is  
25 sufficiently compatible so that the adhesive polymer can be introduced into the fluoropolymer in the desired amount to secure the fluoropolymer coating to the substrate film. In general however, homo and copolymers derived largely from vinyl fluoride and vinylidene fluoride will show compatibility characteristics that will favor acrylic, urethane, aliphatic  
30 polyester, polyester urethane, acrylamide, urea and polycarbonate backbones having the functional groups described above.

The free radical addition polymers derived from acrylic and acrylamide monomers are well suited to the introduction of pendant functional groups using the wealth of functional monomers available.



Some representatives include glycidyl acrylate and methacrylate for the introduction of epoxy groups. These can then be converted into reactive aminoalcohol groups by reaction of the epoxy functional acrylic with ammonia or primary alkylamines. Carboxylic acid, isocyanate, hydroxy  
5 and anhydride functionalities are all available using acrylic / methacrylic acid, isocyanatoethyl methacrylate, hydroxyethyl methacrylate or maleic anhydride respectively. Numerous other functional monomers are available for functional group introduction as is well known in the art.

Preferred compatible adhesive polymers are amine functional  
10 polymers, more preferably, amine functional acrylic polymers.

#### Pigments and Fillers

If desired, various color, opacity and/or other property effects can be achieved by incorporating pigments and fillers into the  
15 fluoropolymer coating composition dispersion during manufacture. Pigments preferably are used in amounts of about 1 to about 35 wt% based on fluoropolymer solids. Typical pigments that can be used include both clear pigments, such as inorganic siliceous pigments (silica pigments, for example) and conventional pigments. Conventional pigments that can  
20 be used include metallic oxides such as titanium dioxide, and iron oxide; metal hydroxides; metal flakes, such as aluminum flake; chromates, such as lead chromate; sulfides; sulfates; carbonates; carbon black; silica; talc; china clay; phthalocyanine blues and greens, organo reds; organo maroons and other organic pigments and dyes. Preferred are pigments  
25 that are stable at high temperatures during processing. It is also preferable that the type and amount of pigment is selected to prevent any significant adverse affects on the desirable properties of fluoropolymer coating, e.g., weatherability.

Pigments can be formulated into a millbase by mixing the  
30 pigments with a dispersing resin that may be the same as or compatible with the fluoropolymer composition into which the pigment is to be incorporated. Pigment dispersions can be formed by conventional means, such as sand grinding, ball milling, attritor grinding or two-roll milling. Other additives, while not generally needed or used, such as fiber glass

and mineral fillers, anti-slip agents, plasticizers, nucleating agents, and the like, can be incorporated.

#### UV Additives and Thermal Stabilizers

5                   The fluoropolymer coating compositions may contain one or more light stabilizers as additives. Light stabilizer additives include compounds that absorb ultraviolet radiation such as hydroxybenzophenones and hydroxybenzotriazoles. Other possible light stabilizer additives include hindered amine light stabilizers (HALS) and  
10                   antioxidants. Thermal stabilizers can also be used if desired.

#### Barrier Particles

                  In a preferred embodiment, the fluoropolymer coating composition includes barrier particles. Preferably, the particles are  
15                   platelet-shaped particles. Such particles tend to align during application of the coating and, since water, solvent and gases such as oxygen cannot pass readily through the particles themselves, a mechanical barrier is formed in the resulting coating which reduces permeation of water, solvent and gases. In a photovoltaic module, for example, the barrier particles  
20                   substantially increase the moisture barrier properties of the fluoropolymer and enhance the protection provided to the solar cells. If used, barrier particles are preferably present in the amount of about 0.5 to about 10% by weight based on the total dry weight of the fluoropolymer composition in the coating.

25                   Examples of typical platelet shaped filler particles include mica, glass flake and stainless steel flake, and aluminum flake. The platelet shaped particles are preferably mica particles, including mica particles coated with an oxide layer such as iron or titanium oxide. These particles have an average particle size of about 10 to 200  $\mu\text{m}$ , preferably 20 -100  
30                    $\mu\text{m}$ , with no more than 50% of the particles of flake having average particle size of more than about 300  $\mu\text{m}$ . The mica particles coated with an oxide layer are described in U. S. Patent Nos. 3,087,827 (Klenke and Stratton); 3,087,828 (Linton); and 3,087,829 (Linton). The micas



described in these patents are coated with oxides or hydrous oxides of titanium, zirconium, aluminum, zinc, antimony, tin, iron, copper, nickel, cobalt, chromium, or vanadium. Mixtures of coated micas can also be used.

5

#### Fluoropolymer Coating Composition Formulation

The fluoropolymer coating compositions may contain the fluoropolymer either in the form of a solution or dispersion of the fluoropolymer. Typical solutions or dispersions for the fluoropolymer are prepared using solvents which have boiling points high enough to avoid bubble formation during the film forming/drying process. For polymers in dispersion form, a solvent which aids in coalescence of the fluoropolymer is preferable. The polymer concentration in these solutions or dispersions is adjusted to achieve a workable viscosity of the solution and will vary with the particular polymer, the other components of the composition, and the process equipment and conditions used. Preferably, for solutions the fluoropolymer is present in an amount of about 10 wt% to about 25 wt% based the total weight of the composition. For dispersions, the fluoropolymer is preferably present in an amount of about 25 wt% to about 50 wt% based the total weight of the composition.

The form of the polymer in the coating composition is dependent upon the type of fluoropolymer and the solvent used. Homopolymer PVF is normally in dispersion form. Homopolymer PVDF can be in dispersion or solution form dependent upon the solvent selected. For example, homopolymer PVDF can form stable solutions at room temperature in many polar organic solvents such as ketones, esters and some ethers. Suitable examples include acetone, methylethyl ketone (MEK) and tetrahydrofuran (THF). Depending upon comonomer content and the solvent selected, copolymers of VF and VF2 may be used either in dispersion or solution form.

In one preferred form of the invention using homopolymer polyvinyl fluoride (PVF), suitable coating formulations are prepared using dispersions of the fluoropolymer. The nature and preparation of dispersions are described in detail in U.S. Patents 2,419,008; 2,510,783;

and 2,599,300. Preferred PVF dispersions are formed in dimethyl acetamide, propylene carbonate,  $\gamma$ -butyrolactone, N-methyl pyrrolidone, and dimethylsulfoxide.

To prepare the fluoropolymer coating composition in dispersion form, the fluoropolymer and the compatible adhesive polymer and, optionally one or more dispersants and/or pigments, are generally first milled together in a suitable solvent. Alternatively, the various components are milled or appropriately mixed separately. Components which are soluble in the solvent such as the compatible adhesive polymer do not require milling.

A wide variety of mills can be used for the preparation of the dispersion. Typically, the mill employs a dense agitated grinding medium, such as sand, steel shot, glass beads, ceramic shot, Zirconia, or pebbles, as in a ball mill, an ATTRITOR® available from Union Process, Akron, Ohio, or an agitated media mill such as a "Netzsch" mill available from Netzsch, Inc., Exton, Pennsylvania. The dispersion is milled for a time sufficient to cause deagglomeration of the PVF. Typical residence time of the dispersion in a Netzsch mill ranges from thirty seconds up to ten minutes.

The adhesive polymer is employed in the coating composition at a level sufficient to provide the desired bonding to the polymeric substrate film but below the level at which the desirable properties of the fluoropolymer would be significantly adversely affected. Preferably, coating composition contains about 1 to about 40 wt % adhesive polymer, more preferably about 1 to about 25 wt% adhesive polymer, and most preferably 1 to about 20 wt% adhesive polymer, based on the weight of the fluoropolymer.

#### Substrate Films and Primers

Polymeric substrate films used in this invention may be selected from a wide number of polymers, with thermoplastics being preferred. The polymeric substrate film comprises functional groups on its surface that interact with the compatible adhesive polymer to promote



bonding of the fluoropolymer coating to the substrate film. The polymeric substrate film is preferably a polyester, and more preferably a polyester selected from the group consisting of polyethylene terephthalate, polyethylene naphthalate and a coextrudate of polyethylene terephthalate/  
5 polyethylene naphthalate.

Fillers may also be included in the substrate film, where their presence may improve the physical properties of the substrate, for example, higher modulus and tensile strength. They may also improve adhesion of the fluoropolymer to the substrate film. One exemplary filler is  
10 barium sulfate, although others may also be used.

The surface of the polymeric substrate film which is to be coated may naturally possess functional groups suitable for bonding as in hydroxy and/or carboxylic acid in a polyester film or amine and/or acid functionality in a polyamide film. Many polymeric substrate films may  
15 need or would further benefit from activation however, and this may be achieved by surface treatment. That is, the surface can be made receptive by forming functional groups of carboxylic acid, sulfonic acid, aziridine, amine, isocyanate, melamine, epoxy, hydroxy, anhydride and/or mixtures thereof on the surface. The activation can be achieved by chemical  
20 exposure such as to a gaseous Lewis acid such as  $\text{BF}_3$  or to sulfuric acid or to hot sodium hydroxide. Preferably, the surface can be activated by exposing one or both surfaces to an open flame while cooling the opposite surface. Activation can also be achieved by subjecting the film to a high frequency, spark discharge such as corona treatment or atmospheric  
25 nitrogen plasma treatment.

In a preferred embodiment of this invention, a primer layer is deposited on the polymer substrate film and provides the functional groups that interact with the compatible adhesive polymer in the fluoropolymer coating composition to promote bonding of the fluoropolymer coating to  
30 the substrate film. Suitable primers may include polyamines, polyamides, acrylamide polymers (especially amorphous acrylamides), polyethyleneimines, ethylene copolymers or terpolymers, acid-modified polyolefins (e.g. maleated polyolefins), acrylate or methacrylate polymers (e.g., emulsion polymers), polyester (e.g., dispersions), polyurethanes

(e.g., dispersions), epoxy polymers, epoxyacrylic oligomers, and mixtures thereof. An example of this is the introduction of amine functionality by the application of a polyethyleneimine primer coating. A second example is coextrusion of an acid or anhydride functional thermoplastic polymer, such  
5 as the polymer sold by the DuPont Company under the trademark BYNEL®, with the base PET substrate film. When primers are used on, for example, PET substrate films which are stretched during manufacture, the primer can be applied either before or after the substrate film has been stretched.

10

#### Coating Application

The fluoropolymer compositions for making the fluoropolymer coated film in accordance with the present invention can be applied as a liquid directly to suitable polymeric substrate films by conventional coating  
15 means with no need to form a preformed film. Techniques for producing such coatings include conventional methods of casting, dipping, spraying and painting. When the fluoropolymer coating contains fluoropolymer in dispersion form, it is typically applied by casting the dispersion onto the substrate film, using conventional means, such as spray, roll, knife,  
20 curtain, gravure coaters, or any other method that permits the application of a uniform coating without streaks or other defects. Spray and roller applications are the most convenient application methods. The dry coating thickness of cast dispersion is preferably about 2.5  $\mu\text{m}$  (0.1 mil) and about 250  $\mu\text{m}$  (10 mils), preferably between about 13  $\mu\text{m}$  (0.5 mil) to  
25 about 130  $\mu\text{m}$  (5 mils).

After application, the wet solutions or dispersion are dried to remove the solvent and coalesced thermally if necessary to form the fluoropolymer coating on the substrate film. With some compositions in which the fluoropolymer is in solution form, the compositions can be  
30 coated onto substrate films and allowed to air dry at ambient temperatures. Although not necessary to produce a coalesced film, heating is generally desirable to dry the coating more quickly. Drying temperature thus preferably in the range of about 25°C (ambient



conditions) to about 200°C (oven temperature – the film temperature will be lower). The temperature used should also be sufficient to promote the interaction of the functional groups in the adhesive polymer with the functional groups of the polymeric substrate film to provide secure bonding of the fluoropolymer coating to the substrate film. This temperature varies widely with the adhesive polymer employed and the functional groups of substrate film and can range from room temperature to oven temperatures in excess of that required for the coalescence of fluoropolymers in dispersion form as discussed below.

When the fluoropolymer in the composition is in dispersion form, it is necessary for the solvent to be removed and also for the fluoropolymer to be heated to a sufficiently high temperature that the fluoropolymer particles coalesce into a continuous film. Preferably, fluoropolymer in the coating is heated to temperature of about 150°C to about 250°C. The solvent used preferably aids in coalescence, i.e., enables a lower temperature to be used for coalesce than would be necessary with no solvent present. Thus, the conditions used to coalesce polymer will vary with the fluoropolymer used, the thickness of the cast dispersion and the substrate film, and other operating conditions. For homopolymer PVF coatings and residence times of about 1 to about 3 minutes, oven temperatures of about from 340°F (171°C) to about 480°F (249°C) can be used to coalesce the film, and temperatures of about 380°F (193°C) to about 450°F (232°C) have been found to be particularly satisfactory. The oven air temperatures, of course, are not representative of the temperatures reached by the fluoropolymer coating which will be lower.

In a preferred form of the invention, the fluoropolymer coating composition is applied to a substrate film. Preferably, the substrate film includes a primer layer providing functional groups that interact with said compatible adhesive polymer to promote bonding. Preferably, the substrate film is polyester such a polyethylene terephthalate, polyethylene naphthalate or a coextrudate of polyethylene terephthalate/polyethylene naphthalate. In another preferred form of the invention, the fluoropolymer

coating is applied to both surfaces of the substrate film. This can be performed simultaneously on both sides of the polymeric substrate film or alternately, the coated substrate film can be dried, turned to the uncoated side and resubmitted to the same coating head to apply coating to the  
5 opposite side of the film to achieve coating on both sides of the film.

### Photovoltaic Modules

Fluoropolymer coated films made in accordance with the invention are especially useful in photovoltaic modules. A typical  
10 construction for a photovoltaic module includes a thick layer of glass as a glazing material. The glass protects solar cells comprising crystalline silicon wafers and wires which are embedded in a moisture resisting plastic sealing compound such as cross-linked ethylene vinyl acetate. Alternatively thin film solar cells can be applied from various  
15 semiconductor materials, such as CIGS (copper-indium-gallium-selenide), CTS (cadmium-tellurium-sulfide), a-Si (amorphous silicon) and others on a carrier sheet which is also jacketed on both sides with encapsulant materials. Adhered to the encapsulant is a backsheet. Fluoropolymer coated films made in accordance with the invention are useful for such  
20 backsheets. The fluoropolymer coating comprises fluoropolymer selected from homopolymers and copolymers of vinyl fluoride and homopolymers and copolymers of vinylidene fluoride polymer blended with compatible adhesive polymer containing functional groups selected from carboxylic acid, sulfonic acid, aziridine, anhydride, amine, isocyanate, melamine,  
25 epoxy, hydroxy, anhydride and mixtures thereof. The polymeric substrate film comprises functional groups on its surface that interact with the compatible adhesive polymer to promote bonding of the fluoropolymer coating to the substrate film. The polymeric substrate film is preferably a polyester, and more preferably a polyester selected from the group  
30 consisting of polyethylene terephthalate, polyethylene naphthalate and a coextrudate of polyethylene terephthalate/polyethylene naphthalate. Polyester provides electrical insulation and moisture barrier properties, and is an economical component of the back sheet. Preferably both surfaces of the polymeric substrate film is coated with fluoropolymer



creating a sandwich of polyester between two layers of coating of fluoropolymer. Fluoropolymer films provide excellent strength, weather resistance, UV resistance, and moisture barrier properties to the backsheet.

5

## **EXAMPLES**

### **Test Methods**

#### **180 Degree Peel Strength**

10 Peel strengths are measured using a Model 4201 Instron at 2"/min, recording the peak value and averaging 3 samples (ASTM D1876-01 T-Peel Test). If samples easily peeled by hand during the peel initiation step a value of 0 was recorded.

#### **15 Humidity Cabinet Peel Test**

After removal from the humidity cabinet the samples are scored with a razor knife and a straight edge to produce ¼" wide strips. The 1" overhang is used as a handle and this tab is pulled at roughly a 180 degree angle with slow even tension until either the film breaks or a peel results. Film breaks and peels at either the EVA / glass or EVA / fluoropolymer coating interfaces are considered passing results. Peels between the fluoropolymer coating and the PET substrate are considered failures.

#### **25 Cross-Hatch Adhesion**

After removal from the humidity cabinet the samples are scored with a razor knife, aided by a stainless steel template, to make 11 parallel cuts about 3/32 inch (2.4 mm) apart through the film to the glass surface. This procedure is repeated at right angles to the first cuts to produce a grid of 100 squares. A strip of transparent tape (3M Brand No. 467 PSA tape), 0.75 by 2.16 inch (1.9 by 5.5 cm), is pressed firmly over the scribed area with the tape oriented in a parallel direction to the scribed lines. The tape is then pulled off at a 90° angle rapidly but without jerking. Any failure

30

between the fluoropolymer coating and the PET substrate is considered a failure.

Water Vapor Transmission Rate (WVTR)

- 5                      Water Vapor Transmission Rate is measured using a Mocon Permatron-W® 700 Instrument at 37.8°C and a permiant relative humidity of 100%.

**Examples 1 – 5**

- 10                      Examples 1 to 5 illustrate bonding PVF based coatings containing an amine functional acrylic adhesive or an epoxy functional acrylic adhesive being used to coat polyethylene terephthalate (PET) films previously primed with either polyethyleneimine (PEI) or ethylene acrylic acid copolymer (EAA). Results show that in general more adhesive  
15                      polymer is better. Results indicate that no significant bonding is achieved in the absence of the adhesive polymer.



**PVF based Coating Formulations****Table 1: Fluoropolymer Coating Formulations**

| Formulation | PVF Dispersion* | Adhesive Polymer**       | Amount Adhesive Polymer | Wt% Adhesive based on PVF |
|-------------|-----------------|--------------------------|-------------------------|---------------------------|
| A           | 20.0            | Amine functional acrylic | 2.8                     | 10                        |
| B           | 20.0            | Amine functional acrylic | 5.6                     | 20                        |
| C           | 20.0            | Epoxy functional acrylic | 2.2                     | 10                        |
| D           | 20.0            | Epoxy functional acrylic | 4.4                     | 20                        |
| E           | 20.0            | None                     | 0                       | 0                         |

\* PVF (available from DuPont) previously dispersed into propylene carbonate (available from Huntsman) at 42% solids

5 \*\* amine functional acrylic is methyl methacrylate / 2-hydroxy-3-aminopropyl methacrylate 97.8 / 2.2 at 30% solids in 2-propanol / toluene 55/45.

\*\* Epoxy functional acrylic is methyl methacrylate / glycidyl methacrylate 98 / 2 at 38% solids in 2-propanol / toluene 55/45.

10

**PET + Primer Substrates****Table 2: Substrates with PEI Coatings**

| Substrate | PET thickness (microns) | PEI          | Coating Thickness (nm) |
|-----------|-------------------------|--------------|------------------------|
| Sample 1  | 100                     | Lupasol® P   | 20                     |
| Sample 2  | 100                     | Lupasol® SKA | 20                     |
| Sample 3  | 100                     | Lupasol® SKA | 40                     |

15

**Table 3: Substrates with EAA Coatings**

| Substrate | PET thickness (microns) | Coating Thickness (nm) |
|-----------|-------------------------|------------------------|
| Sample 4  | 100                     | 40                     |
| Sample 5  | 100                     | 80                     |

**Procedure**

1. Ingredients of Table 1 are combined and agitated 15 minutes on a paint shaker to mix.
- 5 2. Draw downs of the mixtures in Table 1 are prepared on each of the 4 mil PET webs in Tables 2 and 3 using a 12 mil draw down knife to produce approximately 1.2 mil dry fluoropolymer coatings.
3. A heavy bead of pure PVF dispersion (42% in propylene carbonate) is applied along 1 edge of the wet draw down to help facilitate peel testing.
- 10 4. The coated webs are clamped into metal frames and placed into preheated ovens at either 200°C or 220°C for 3 minutes.
5. The coalesced and dried films are removed from the ovens and allowed to cool.
- 15 6. One inch strips are cut perpendicular to the heavy PVF bead.
7. A scalpel is used to initiate peeling at the PVF bead.
8. Peel strengths are measured using a Model 4201 Instron at 2"/min, recording the peak value and averaging 3 samples (ASTM D1876-01 T-Peel Test). If samples easily peeled by hand during the peel
- 20 initiation step a value of 0 was recorded.



**Table 4: Peel Testing Results**

| Example | Substrate | Fluoropolymer Formulation | 200°C Bake Temp Peel Strength (KG/in) | 220°C Bake Temp Peel Strength (KG/in) |
|---------|-----------|---------------------------|---------------------------------------|---------------------------------------|
| 1A      | Sample 1  | A                         | 0                                     | 0                                     |
| 1B      | Sample 1  | B                         | 0                                     | 0.76                                  |
| 1C      | Sample 1  | C                         | 0                                     | 0                                     |
| 1D      | Sample 1  | D                         | 1.18                                  | 1.14*                                 |
| 1E      | Sample 1  | E                         | 0                                     | 0                                     |
| 2A      | Sample 2  | A                         | 0.78                                  | 0.57                                  |
| 2B      | Sample 2  | B                         | 1.2                                   | 1.47                                  |
| 2C      | Sample 2  | C                         | 0                                     | 0                                     |
| 2D      | Sample 2  | D                         | 1.46                                  | 1.28*                                 |
| 2E      | Sample 2  | E                         | 0                                     | 0                                     |
| 3A      | Sample 3  | A                         | 0                                     | 0.59                                  |
| 3B      | Sample 3  | B                         | 1.36                                  | 1.26                                  |
| 3C      | Sample 3  | C                         | 0                                     | 0                                     |
| 3D      | Sample 3  | D                         | 1.48                                  | 1.42*                                 |
| 3E      | Sample 3  | E                         | 0                                     | 0                                     |
| 4A      | Sample 4  | A                         | 1.39                                  | 1.44                                  |
| 4B      | Sample 4  | B                         | 1.53                                  | 1.33                                  |
| 4C      | Sample 4  | C                         | 0                                     | 1.07                                  |
| 4D      | Sample 4  | D                         | 1.29                                  | 1.35*                                 |
| 4E      | Sample 4  | E                         | 0                                     | 0                                     |
| 5A      | Sample 5  | A                         | 1.15                                  | 1.35                                  |
| 5B      | Sample 5  | B                         | 1.44                                  | 1.59                                  |
| 5C      | Sample 5  | C                         | 1.2                                   | 1.13                                  |
| 5D      | Sample 5  | D                         | 0                                     | 1.38*                                 |
| 5E      | Sample 5  | E                         | 0                                     | 0                                     |

\* denotes formulation / substrate / bake temperature combinations that survive the 1000 hr 85°C / 85% humidity cabinet test (only selected samples are tested).

5

## Humidity Cabinet Testing

### Sample Preparation

Fluoropolymer coated PET substrates are prepared in the same manner as those of examples 1 through 5 with the exception that

10

the edge bead of step 3 was omitted. After removing the samples from the oven and allowing them to cool, the fluoropolymer coating side is corona treated using a hand held lab corona treater. The corona treated sample was then laminated to a glass panel (4"x 8" x1/8") using the following procedure.

The following sandwich is placed on a vacuum plate with a 1" fluoropolymer coated PET overhang:

----- fluoropolymer coated PET film with fluoropolymer coating face  
 10 down  
 - - - - reactive EVA film  
 ----- glass panel

1. The sandwich is centered and covered with a silicone rubber pad
2. A metal frame is placed on the rubber pad and vacuum applied for 20 minutes
3. The sandwich + vacuum plate is placed into a room temperature oven and heating begun to a target of 150°C.
4. The sample is held at 150°C for 20 minutes
5. The sample is removed from the oven, vacuum released and allowed to cool
6. The resulting laminates are placed into a paint sample rack in a humidity cabinet controlled at 85°C / 85% humidity.
7. Samples are exposed to the humidity cabinet for 1000 hours and then examined for adhesion using both peel testing and a cross hatch tape test.

### Examples 6-9

Examples 6-9 illustrate PVF coating compositions containing an amine function acrylic adhesive being used to coat PET films primed with polyallylamine primer.



**Example 6**

Example 6 illustrates the application of a white PVF coating to both sides of unpigmented and pigmented PET film primed with a polyallylamine primer.

5 A white PVF coating formulation is prepared from the formula in the following Table 5. The thermal stabilizer solution listed in Table 5 is prepared from 4.0 wt % Irganox® 1035 (Ciba), 1 wt % Weston® THOP (Crompton) and 95 wt % propylene carbonate. The amine function acrylic  
10 methacrylate/glycidyl methacrylate (98/2) with ammonia to convert the glycidyl groups into 2-hydroxy-3-aminopropyl groups to produce a primary amine functional acrylic polymer in a solvent of toluene and isopropanol.

**Table 5**

| Ingredient                     | Wet wt. | Dry wt. | Wt% based on PVF |
|--------------------------------|---------|---------|------------------|
| PVF dispersion (40% in PC)     | 58.55   | 23.42   | N.A.             |
| White pigment dispersion       | 23.55   | 10.65   | 45.5             |
| Thermal stabilizer sol'n       | 2.9     | 0.15    | 0.66             |
| Amine functional acrylic sol'n | 14.43   | 4.32    | 18.4             |

15

Using a doctor blade, the white PVF coating formulation is coated on a 2 mil unpigmented PET film primed with a polyallylamine primer and on barium sulfate pigmented 3.8 mil wide PET film primed with a polyallylamine primer. The coatings are baked in a preheated oven for  
20 10 min at 200°C for 10 minutes. The cooled coated films are then coated on the opposite side with the same PVF formulation and are baked 15 min at 200°C. Table 6 shows the range of resultant dry film thicknesses for coatings on pigmented and unpigmented PET films:

**Table 6**

| sample | PET Pigmented? | film thickness (mils) |                 |                 |
|--------|----------------|-----------------------|-----------------|-----------------|
|        |                | PET                   | 1st PVF Coating | 2nd PVF Coating |
| 1      | Yes            | 3.8                   | 1               | 0.7             |
| 2      | Yes            | 3.8                   | 1.2             | 1.5             |
| 3      | No             | 2                     | 1               | 1               |
| 4      | No             | 2                     | 1.2             | 1.3             |
| 5      | No             | 2                     | 1               | 1               |
| 6      | No             | 2                     | 1.2             | 1.3             |
| 7      | Yes            | 3.8                   | 0.7             | 1               |
| 8      | Yes            | 3.8                   | 1.2             | 1               |

**Example 7**

5                    Example 7 illustrates the application of a PVF coating containing pearlescent barrier particles of mica to both sides of unpigmented and pigmented PET film primed with a polyallylamine primer.

A pearlescent PVF coating formulation is prepared from the formula in the following Table 7:

10

**Table 7**

|   | Wt %  |
|---|-------|
| PVF Dispersion                            | 43.03 |
| Mearlin® Sparkle 139P (Englehard)         | 10.63 |
| Thermal Stabilizer Solution               | 2.13  |
| Amine functional acrylic polymer solution | 10.63 |
| Propylene Carbonate                       | 33.58 |

15                    Using a doctor blade, the pearlescent PVF coating formulation is coated on a 2 mil wide, unpigmented PET film primed with a polyallylamine primer and on a 3.8 mil wide, barium sulfate pigmented PET film primed with a polyallylamine primer. These coatings are baked in a preheated oven for 10 min at 200°C for 10 minutes. The cooled coated films are then coated on the opposite side with the same PVF formulation and baked 15 min at 200°C. Table 8 shows the range of resultant dry coating thicknesses:

20



**Table 8**

| sample | PET Pigmented? | film thickness (mils) |                 |                 |
|--------|----------------|-----------------------|-----------------|-----------------|
|        |                | PET                   | 1st PVF Coating | 2nd PVF Coating |
| 1      | Yes            | 3.8                   | 0.8             | 0.5             |
| 2      | Yes            | 3.8                   | 0.7             | 1               |
| 3      | Yes            | 3.8                   | 1               | 1.7             |
| 4      | Yes            | 3.8                   | 0.7             | 1.6             |
| 5      | Yes            | 3.8                   | 0.95            | 1.05            |
| 6      | Yes            | 3.8                   | 0.7             | 1               |
| 7      | Yes            | 3.8                   | 1.2             | 1               |
| 8      | Yes            | 3.8                   | 1.2             | 1.1             |
| 9      | No             | 2                     | 1               | 1               |
| 10     | No             | 2                     | 0.9             | 1               |
| 11     | No             | 2                     | 1               | 1               |
| 12     | No             | 2                     | 1.3             | 1.45            |
| 13     | No             | 2                     | 1.3             | 1.5             |

**Example 8**

5                    In Example 8, the vapor barrier properties of two side coated PET films of Example 6 (sample 7) and Example 7 (sample 2) having white pigmented and mica pigmented fluoropolymer coatings, respectively, are evaluated by measuring the Water Vapor Transmission Rate (WVTR). Table 9 shows the improvement of vapor barrier properties when using  
10                    barrier particles such as mica, as indicated by a lower WVTR value.

**Table 9**

| Side 1<br>Pigment | Side 2<br>Pigment | PVF/PET/PVF<br>thicknesses<br>(mils) | WVTR<br>g/m <sup>2</sup> /day |
|-------------------|-------------------|--------------------------------------|-------------------------------|
| white             | white             | 0.7/3.8/1.0                          | 5.53                          |
| pearl             | pearl             | 0.7/3.8/1.0                          | 2.052                         |

**Example 9**

15                    In Example 9, the shrinkage properties of white two side coated PET samples made according to Example 6 (sample 1) are compared with samples of PET films with conventional preformed PVF films laminated to both sides. The former contained a filler (barium sulfate) in the PET  
20                    substrate, while the latter did not. Table 10 shows the measured shrinkage data at various temperatures.

**Table 10**

|     | % Change in Machine Direction Dimension as a function of Temperature    |                         |
|-----|---|-------------------------|
| ° F | Two side Coated Film  | Two side Laminated Film |
| 25  | 0.000   | 0.000                   |
| 50  | 0.000   | 0.000                   |
| 100 | 0.000   | -0.084                  |
| 150 | -0.083  | -0.669                  |
| 200 | -0.083  | -3.177                  |
|     |   |                         |
|     | % Change in Transverse Direction Dimension as a function of Temperature |                         |
| ° F | Two side Coated Film  | Two side Laminated Film |
| 25  | 0.000   | 0.000                   |
| 50  | 0.000   | -0.083                  |
| 100 | 0.084   | -0.083                  |
| 150 | 0.000   | -0.166                  |
| 200 | 0.084   | -2.912                  |

Note: Two side Coated film layer thicknesses (mils) 1/3.8/0.7

5 Two side laminated film layer thicknesses (mils) 1.5/3/1.5

**Example 10**

Example 10 illustrates the application of a white pigmented and an unpigmented polyvinylidene (PVDF) coating to one side of an unpigmented and a pigmented PET film primed with a polyallylamine primer.

The unpigmented PVDF coating formulation is prepared from the following components shown in Table 11:

15

**Table 11**

| Material   | Source   | Wt %  |
|--|----------|-------|
| Polyvinylidene Fluoride  | Aldrich  | 21.03 |
| Amine functional acrylic polymer solution (1)  | DuPont   | 32.9  |
| Propylene Carbonate  | Huntsman | 46.07 |
| (1) Methyl methacrylate/glycidyl methacrylate (98/2) post reacted with ammonia to convert the glycidyl groups into 2-hydroxy-3-aminopropyl groups to produce a primary amine functional acrylic polymer in a solvent of toluene and isopropanol. |          |       |

The mixture is dispersed on a paint shaker in the presence of 3 mm glass beads for 10 minutes.



The white pigmented coating formulation is prepared from the following components shown in Table 12:

**Table 12**

|   | Material               | Wt %  |
|---|------------------------|-------|
| 5 | Clear PVDF Formulation | 78.32 |
|   | White dispersion       | 21.68 |

Using a 7 mil doctor blade, both the clear PVDF formulation and the white PVDF formulation are coated on unpigmented 2 mil PET film and pigmented 3.8 mil PET film primed with a polyallylamine primer using a 7-mil doctor blade. A comparison 3.8 mil unprimed PET is similarly coated. The coated films were baked in a preheated 400°F convection oven for 5 minutes. After cooling, a scalpel was used to attempt to remove the PVF films from PET films. Both the pigmented and unpigmented films could be peeled from unprimed PET but could not be peeled from primed PET.

**CLAIMS****What is claimed is:**

1. A fluoropolymer coated film comprising:  
5                   a polymeric substrate film; and  
                  a fluoropolymer coating on said polymeric substrate film,  
said fluoropolymer coating comprising fluoropolymer selected from  
homopolymers and copolymers of vinyl fluoride and homopolymers and  
copolymers of vinylidene fluoride polymer blended with compatible  
10           adhesive polymer comprising functional groups selected from carboxylic  
acid, sulfonic acid, aziridine, anhydride, amine, isocyanate, melamine,  
epoxy, hydroxy, anhydride and mixtures thereof;  
                  said polymeric substrate film comprising functional groups  
on its surface that interact with said compatible adhesive polymer to  
15           promote bonding of said fluoropolymer coating to said substrate film.
2. The fluoropolymer coated film of claim 1 wherein said  
polymeric substrate film comprises a primer layer on its surface providing  
said functional groups that interact with said adhesive to promote bonding  
20           of said fluoropolymer coating to said substrate film.
3. The fluoropolymer coated film of claim 1 wherein said  
functional groups on the surface of said polymeric substrate film are  
selected from carboxylic acid, sulfonic acid, aziridine, amine, isocyanate,  
25           melamine, epoxy, hydroxy, anhydride and mixtures thereof.
4. The fluoropolymer coated film of claim 1 wherein said  
compatible adhesive polymer is a functional acrylic polymer.
- 30           5. The fluoropolymer coated film of claim 1 wherein said  
compatible adhesion-promoting polymer is an amine functional acrylic  
polymer.



6. The fluoropolymer coated film of claim 1 wherein said fluoropolymer is selected from homopolymers and copolymers of vinyl fluoride comprising at least 60 mole % vinyl fluoride and homopolymers and copolymers of vinylidene fluoride comprising at least 60 mole % vinylidene fluoride.

7. The fluoropolymer coated film of claim 1 wherein said fluoropolymer is selected from homopolymers and copolymers of vinyl fluoride comprising at least 80 mole % vinyl fluoride and homopolymers and copolymers of vinylidene fluoride comprising at least 80 mole % vinylidene fluoride.

8. The fluoropolymer coated film of claim 1 wherein said fluoropolymer coating comprises about 1 to about 40 weight % of said compatible adhesive polymer based on fluoropolymer solids content.

9. The fluoropolymer coated film of claim 1 wherein said fluoropolymer coating further comprises pigment.

10. The fluoropolymer coated film of claim 1 wherein said fluoropolymer coating further comprises about 1 to about 35 weight % of pigment based on fluoropolymer solids content.

11. The fluoropolymer coated film of claim 1 wherein said fluoropolymer coating is on both surfaces of said substrate film.

12. The fluoropolymer coated film of claim 2 wherein said substrate film comprises polyester.

13. The fluoropolymer coated film of claim 9 wherein said primer comprises a polymer selected from polyallylamine/melamine polymer, polyethylene imine polymer, ethylene acrylic acid copolymer, and acid modified polyolefin.

14. The fluoropolymer coated film of claim 1 wherein said fluoropolymer coating has a thickness of about 0.1 to about 2.0 mils.

15. The fluoropolymer coated film of claim 1 wherein said  
5 substrate film has a thickness of about 0.5 to about 10 mils.

16. The fluoropolymer coated film of claim 1 wherein said primer layer has a thickness of about 20 to about 100 nm.

10 17. The fluoropolymer coated film of claim 1 wherein the surface of said substrate film is activated.

18. The fluoropolymer coated film of claim 1 wherein said substrate film comprises filler.

15

19. A photovoltaic module comprising the fluoropolymer coated film of claim 1 as backsheet.