



US007208010B2

(12) **United States Patent**
Shanley et al.

(10) **Patent No.:** **US 7,208,010 B2**

(45) **Date of Patent:** **Apr. 24, 2007**

(54) **EXPANDABLE MEDICAL DEVICE FOR
DELIVERY OF BENEFICIAL AGENT**

4,300,244 A	11/1981	Bokros
4,531,936 A	7/1985	Gordon
4,542,025 A	9/1985	Tice et al.
4,580,568 A	4/1986	Gianturco

(75) Inventors: **John F. Shanley**, Redwood City, CA
(US); **Neal L. Eigler**, Pacific Palisades,
CA (US); **Kinam Park**, West Lafayette,
IN (US); **Elazer R. Edelman**,
Brookline, MA (US)

(Continued)

FOREIGN PATENT DOCUMENTS

(73) Assignee: **Conor Medsystems, Inc.**, Menlo Park,
CA (US)

CA 2234787 4/1998

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

(Continued)

OTHER PUBLICATIONS

(21) Appl. No.: **09/948,989**

Amy C. Richards Grayson et al. "Multi-pulse Drug Delivery From a
Resorbable Polymeric Microchip Device". Nature Materials., vol. 2,
Nov. 2003, pp. 767-770.

(22) Filed: **Sep. 7, 2001**

(Continued)

(65) **Prior Publication Data**

US 2002/0082680 A1 Jun. 27, 2002

Primary Examiner—Alvin J. Stewart

Assistant Examiner—Javier G. Blanco

(74) *Attorney, Agent, or Firm*—Cindy A. Lynch

Related U.S. Application Data

(63) Continuation-in-part of application No. 09/688,092,
filed on Oct. 16, 2000, now abandoned.

(60) Provisional application No. 60/314,259, filed on Aug.
20, 2001.

(51) **Int. Cl.**
A61F 2/06 (2006.01)

(52) **U.S. Cl.** **623/1.42**; 623/1.44; 623/1.46;
427/2.24

(58) **Field of Classification Search** 623/1.15–1.17,
623/1.39, 1.42–1.46; 427/2.24, 2.25; 606/194
See application file for complete search history.

(56) **References Cited**


U.S. PATENT DOCUMENTS

3,657,744 A 4/1972 Ersek

(57) **ABSTRACT**

An expandable medical device has a plurality of elongated
struts joined together to form a substantially cylindrical
device which is expandable from a cylinder having a first
diameter to a cylinder having a second diameter. At least one
of the plurality of struts includes at least one opening
extending at least partially through a thickness of the strut.
A beneficial agent is loaded into the opening within the strut
in layers to achieve desired temporal release kinetics of the
agent. Alternatively, the beneficial agent is loaded in a shape
which is configured to achieve the desired agent delivery
profile. A wide variety of delivery profiles can be achieved
including zero order, pulsatile, increasing, decrease, sinu-
soidal, and other delivery profiles.

63 Claims, 9 Drawing Sheets



U.S. PATENT DOCUMENTS					
4,650,466 A	3/1987	Luther	5,575,771 A	11/1996	Walinsky
4,733,665 A	3/1988	Palmaz	5,578,075 A	11/1996	Dayton
4,739,762 A	4/1988	Palmaz	5,593,434 A	1/1997	Williams
4,776,337 A	10/1988	Palmaz	5,595,722 A	1/1997	Grainger et al.
4,800,882 A	1/1989	Gianturco	5,599,844 A	2/1997	Grainger et al.
4,824,436 A	4/1989	Wollinsky	5,605,696 A	2/1997	Eury et al.
4,834,755 A	5/1989	Silvestrini et al.	5,607,442 A	3/1997	Fischell et al.
4,955,878 A	9/1990	See et al.	5,609,629 A	3/1997	Fearnot et al.
4,957,508 A	9/1990	Kaneko et al.	5,616,608 A	4/1997	Kinsella et al.
4,960,790 A	10/1990	Steele et al.	5,617,878 A	4/1997	Taheri
4,969,458 A	11/1990	Witkor	5,618,299 A	4/1997	Khosravi et al.
4,989,601 A	2/1991	Marchosky et al.	5,624,411 A	4/1997	Tuch
4,990,155 A	2/1991	Wilkoff et al.	5,628,787 A	5/1997	Mayer
4,994,071 A	2/1991	MacGregor	5,643,314 A	7/1997	Carpenter et al.
5,019,090 A	5/1991	Pinchuk	5,665,591 A	9/1997	Sonenshein et al.
5,049,132 A	9/1991	Shaffer et al.	5,667,764 A	9/1997	Kopia et al.
5,053,048 A	10/1991	Pinchuk	5,674,278 A	10/1997	Boneau
5,059,166 A	10/1991	Fischell et al.	5,679,400 A	10/1997	Tuch
5,059,178 A	10/1991	Ya et al.	5,697,971 A	12/1997	Fischell et al.
5,059,211 A	10/1991	Stack et al.	5,707,385 A	1/1998	Williams
5,078,726 A	1/1992	Kreamer	5,713,949 A	2/1998	Jayaraman
5,092,841 A	3/1992	Spears	5,716,981 A	2/1998	Hunter et al.
5,102,417 A	4/1992	Palmaz	5,725,548 A	3/1998	Jayaraman
5,157,049 A	10/1992	Haugwitz et al.	5,725,549 A	3/1998	Lam
5,171,217 A	12/1992	March et al.	5,733,330 A	3/1998	Cox
5,171,262 A	12/1992	MacGregor	5,733,925 A	3/1998	Kunz et al.
5,176,617 A	1/1993	Fischell et al.	5,741,293 A	4/1998	Wijay
5,195,984 A	3/1993	Schatz	5,759,192 A	6/1998	Saunders
5,197,978 A	3/1993	Hess	5,766,239 A	6/1998	Cox
5,213,580 A	5/1993	Slepian et al.	5,769,883 A	6/1998	Buscemi et al.
5,234,456 A	8/1993	Silvestrini	5,770,609 A	6/1998	Grainger et al.
5,242,399 A	9/1993	Lau et al.	5,773,479 A	6/1998	Grainger et al.
5,286,254 A	2/1994	Shapland et al.	5,776,181 A	7/1998	Lee et al.
5,292,512 A	3/1994	Schaefer et al.	5,776,184 A	7/1998	Tuch
5,304,121 A	4/1994	Sahatjian	5,797,898 A *	8/1998	Santini, Jr. et al. 604/890.1
5,314,688 A	5/1994	Kauffman et al.	5,800,507 A	9/1998	Schwartz
5,342,348 A	8/1994	Kaplan	5,811,447 A	9/1998	Kunz et al.
5,342,621 A	8/1994	Eury	5,817,152 A	10/1998	Birdsall et al.
5,344,426 A	9/1994	Lau et al.	5,824,045 A	10/1998	Alt
5,380,299 A	1/1995	Fearnot et al.	5,824,049 A	10/1998	Ragheb et al.
5,383,892 A	1/1995	Cardon et al.	5,827,322 A	10/1998	Williams
5,383,928 A	1/1995	Scott et al.	5,837,008 A	11/1998	Berg et al.
5,403,858 A	4/1995	Bastard et al.	5,837,313 A	11/1998	Ding et al.
5,407,683 A	4/1995	Shively	5,843,117 A	12/1998	Alt et al.
5,415,869 A	5/1995	Straubinger et al.	5,843,120 A	12/1998	Israel et al.
5,419,760 A	5/1995	Narciso	5,843,172 A	12/1998	Yan
5,439,446 A	8/1995	Barry	5,843,175 A	12/1998	Frantzen
5,439,686 A	8/1995	Desai et al.	5,843,741 A	12/1998	Wong et al.
5,441,515 A	8/1995	Khosravi et al.	5,853,419 A	12/1998	Imran
5,441,745 A	8/1995	Presant et al.	5,855,600 A	1/1999	Alt
5,443,496 A	8/1995	Schwartz et al.	5,868,781 A	2/1999	Killion
5,443,497 A	8/1995	Venbrx	5,873,904 A	2/1999	Ragheb et al.
5,443,500 A	8/1995	Sigwart	5,876,419 A	3/1999	Carpenter et al.
5,447,724 A	9/1995	Helmus et al.	5,882,335 A	3/1999	Leone et al.
5,449,373 A	9/1995	Pinchasik et al.	5,886,026 A	3/1999	Hunter et al.
5,449,513 A	9/1995	Yokoyama et al.	5,922,020 A	7/1999	Klein et al.
5,457,113 A	10/1995	Cullinan et al.	5,922,021 A	7/1999	Jang
5,460,817 A	10/1995	Langley et al.	5,928,916 A	7/1999	Keogh
5,462,866 A	10/1995	Wang	5,935,506 A	8/1999	Schmitz et al.
5,464,450 A	11/1995	Buscemi et al.	5,945,456 A	8/1999	Grainger et al.
5,464,650 A	11/1995	Berg et al.	5,957,971 A	9/1999	Schwartz
5,472,985 A	12/1995	Grainger et al.	5,964,798 A	10/1999	Imran
5,473,055 A	12/1995	Mongelli et al.	5,968,092 A	10/1999	Buscemi et al.
5,499,373 A	3/1996	Richards et al.	5,972,027 A	10/1999	Johnson
5,523,092 A	6/1996	Hanson et al.	5,976,182 A	11/1999	Cox
5,534,287 A	7/1996	Lukic	5,980,551 A	11/1999	Summers et al.
5,545,208 A	8/1996	Wolff et al.	5,980,972 A	11/1999	Ding
5,545,210 A	8/1996	Hess et al.	5,981,568 A	11/1999	Kunz et al.
5,545,569 A	8/1996	Grainger et al.	5,984,957 A	11/1999	Laptewicz, Jr. et al.
5,551,954 A	9/1996	Buscemi et al.	5,992,769 A	11/1999	Wise et al.
5,556,413 A	9/1996	Lam	5,994,341 A	11/1999	Hunter et al.
			6,007,517 A	12/1999	Anderson
			6,017,363 A	1/2000	Hojeibane

US 7,208,010 B2

Page 3

6,019,789 A	2/2000	Dinh et al.	6,585,765 B1 *	7/2003	Hossainy et al. 623/1.45
6,022,371 A	2/2000	Killion	6,599,928 B2	7/2003	Kunz et al.
6,030,414 A	2/2000	Taheri	6,613,084 B2	9/2003	Yang
6,042,606 A	3/2000	Frantzen	6,627,246 B2	9/2003	Mehta et al.
6,056,722 A	5/2000	Jayaraman	6,638,302 B1	10/2003	Curcio et al.
6,063,101 A	5/2000	Jacobsen et al.	6,645,547 B1	11/2003	Shekalim et al.
6,071,305 A	6/2000	Brown et al.	6,656,162 B2	12/2003	Santini et al.
6,074,659 A	6/2000	Kunz et al.	6,660,034 B1 *	12/2003	Mandrusov et al. 623/1.42
6,083,258 A	7/2000	Yadav	6,663,881 B2	12/2003	Kunz et al.
6,087,479 A	7/2000	Stamler et al.	6,673,385 B1	1/2004	Ding et al.
6,096,070 A	8/2000	Ragheb et al.	6,682,545 B1	1/2004	Kester
6,099,561 A	8/2000	Alt	6,702,850 B1	3/2004	Byun et al.
6,120,535 A	9/2000	McDonald et al.	6,712,845 B2	3/2004	Hossainy
6,120,536 A	9/2000	Ding et al.	6,713,119 B2	3/2004	Hossainy et al.
6,120,847 A	9/2000	Yang et al.	6,716,444 B1	4/2004	Castro et al.
6,121,027 A	9/2000	Clapper et al.	6,719,881 B1	4/2004	Hunter et al.
6,123,861 A	9/2000	Santini et al.	6,720,350 B2	4/2004	Kunz et al.
6,140,127 A	10/2000	Sprague	6,723,373 B1	4/2004	Narayanan et al.
6,153,252 A	11/2000	Hossainy et al.	6,730,064 B2	5/2004	Ragheb et al.
6,156,062 A	12/2000	McGuinness	6,730,116 B1	5/2004	Wolinsky et al.
6,159,488 A	12/2000	Nagler et al.	2001/0000802 A1	5/2001	Soykan et al.
6,171,609 B1	1/2001	Kunz	2001/0018469 A1	8/2001	Chen et al.
6,174,326 B1	1/2001	Kitaoka et al.	2001/0027340 A1	10/2001	Wright et al.
6,193,746 B1	2/2001	Strecker	2001/0029351 A1	10/2001	Falotico et al.
6,206,914 B1	3/2001	Soykan et al.	2001/0034363 A1	10/2001	Li et al.
6,206,915 B1	3/2001	Fagan et al.	2001/0044648 A1	11/2001	Wolinsky et al.
6,206,916 B1	3/2001	Furst	2001/0044652 A1	11/2001	Moore
6,231,600 B1	5/2001	Zhong	2002/0002400 A1	1/2002	Drasler et al.
6,239,118 B1	5/2001	Schatz et al.	2002/0005206 A1	1/2002	Falotico et al.
6,240,616 B1	6/2001	Yan	2002/0007209 A1	1/2002	Scheerder et al.
6,241,762 B1	6/2001	Shanley	2002/0007213 A1	1/2002	Falotico et al.
6,245,101 B1	6/2001	Drasler et al.	2002/0016625 A1	2/2002	Falotico et al.
6,249,952 B1	6/2001	Ding	2002/0022876 A1	2/2002	Richter et al.
6,254,632 B1 *	7/2001	Wu et al. 623/1.15	2002/0028243 A1	3/2002	Bates et al.
6,268,390 B1	7/2001	Kunz	2002/0032414 A1	3/2002	Ragheb et al.
6,273,908 B1	8/2001	Ndondo-Lay	2002/0038145 A1	3/2002	Jang
6,273,910 B1	8/2001	Limon	2002/0068969 A1	6/2002	Shanley et al.
6,273,913 B1	8/2001	Wright et al.	2002/0071902 A1	6/2002	Ding et al.
6,280,411 B1	8/2001	Lennox	2002/0072511 A1	6/2002	New et al.
6,290,673 B1	9/2001	Shanley	2002/0082679 A1	6/2002	Sirhan et al.
6,293,967 B1	9/2001	Shanley	2002/0082680 A1	6/2002	Shanley et al.
6,299,604 B1	10/2001	Ragheb et al.	2002/0082682 A1	6/2002	Barclay et al.
6,306,166 B1	10/2001	Barry et al.	2002/0094985 A1	7/2002	Hermann et al.
6,306,421 B1	10/2001	Kunz et al.	2002/0123801 A1 *	9/2002	Pacetti et al. 623/1.46
6,309,414 B1	10/2001	Rolando et al.	2002/0127263 A1	9/2002	Carlyle et al.
6,312,460 B2	11/2001	Drasler et al.	2002/0142039 A1	10/2002	Claude
6,358,556 B1	3/2002	Ding et al.	2002/0155212 A1 *	10/2002	Hossainy 427/2.25
6,358,989 B1	3/2002	Kunz et al.	2002/0193475 A1	12/2002	Hossainy et al.
6,379,381 B1 *	4/2002	Hossainy et al. 623/1.42	2003/0028244 A1	2/2003	Bates et al.
6,395,326 B1	5/2002	Castro et al.	2003/0036794 A1	2/2003	Ragheb et al.
6,399,144 B2	6/2002	Dinh et al.	2003/0050687 A1	3/2003	Schwade et al.
6,403,635 B1	6/2002	Kinsella et al.	2003/0060877 A1	3/2003	Falotico et al.
6,423,092 B2	7/2002	Datta et al.	2003/0068355 A1	4/2003	Shanley et al.
6,429,232 B1	8/2002	Kinsella et al.	2003/0077312 A1	4/2003	Schmulewicz et al.
6,451,051 B2	9/2002	Drasler et al.	2003/0083646 A1	5/2003	Sirhan et al.
6,475,237 B2	11/2002	Drasler et al.	2003/0086957 A1	5/2003	Hughes et al.
6,491,666 B1	12/2002	Santini et al.	2003/0088307 A1	5/2003	Shulze et al.
6,491,938 B2	12/2002	Kunz et al.	2003/0100865 A1	5/2003	Santini et al.
6,497,916 B1	12/2002	Taylor et al.	2001/0125803	7/2003	Vallana et al.
6,500,859 B2	12/2002	Kinsella et al.	2003/0125803 A1 *	7/2003	Vallana et al. 623/1.42
6,503,954 B1	1/2003	Bhat et al.	2003/0157241 A1	8/2003	Hossainy et al.
6,506,411 B2	1/2003	Hunter et al.	2003/0176915 A1	9/2003	Wright et al.
6,506,437 B1	1/2003	Harish et al.	2003/0181973 A1	9/2003	Sahota
6,515,009 B1	2/2003	Kunz et al.	2003/0199970 A1	10/2003	Shanley
6,537,256 B2	3/2003	Santini et al.	2003/0204239 A1	10/2003	Carlyle et al.
6,544,544 B2	4/2003	Hunter et al.	2003/0216699 A1	11/2003	Falotico
6,551,838 B2 *	4/2003	Santini, Jr. et al. 436/174	2004/0073296 A1	4/2004	Epstein et al.
6,558,733 B1 *	5/2003	Hossainy et al. 427/2.24	2004/0122505 A1	6/2004	Shanley
6,562,065 B1	5/2003	Shanley	2004/0122506 A1	6/2004	Shanley et al.
6,569,441 B2	5/2003	Kunz et al.	2004/0127976 A1	7/2004	Diaz
6,569,688 B2	5/2003	Sivan et al.			
6,572,642 B2	6/2003	Rinaldi et al.			
6,585,764 B2	7/2003	Wright et al.			

2004/0127977 A1 7/2004 Shanley

FOREIGN PATENT DOCUMENTS

DE	202 00 220	4/2002
EP	0294905	12/1988
EP	0 335 341	10/1989
EP	0335341	10/1989
EP	0 353 341	2/1990
EP	0 375 520	6/1990
EP	0375520	6/1990
EP	0 470 246	2/1992
EP	0 470 569	2/1992
EP	0470569	2/1992
EP	0551182	7/1993
EP	0 566 245	10/1993
EP	0 567 816	11/1993
EP	0567816	11/1993
EP	0568310	11/1993
EP	0604022	6/1994
EP	0623354	11/1994
EP	0 627 226	12/1994
EP	0627226	12/1994
EP	0 679 373	11/1995
EP	0679373	11/1995
EP	0716836	6/1996
EP	0 734 698	10/1996
EP	0734698	10/1996
EP	0 747 069	12/1996
EP	0752885	1/1997
EP	0 770 401	5/1997
EP	0 706 376	6/1997
EP	0706376	6/1997
EP	0797963	10/1997
EP	0832655	4/1998
EP	0850651	7/1998
EP	0 897 700	2/1999
EP	0897700	2/1999
EP	0 950 386	10/1999
EP	0566245	10/1999
EP	1 118 325	7/2001
EP	1 132 058	9/2001
EP	1 172 074	1/2002
EP	1181943	2/2002
EP	1 223 305	7/2002
EP	1222941	7/2002
EP	1 236 478	9/2002
EP	0711158	3/2003
FR	2 764 794	12/1998
WO	WO-9001969	3/1990
WO	WO 90/13332	11/1990
WO	WO-9013332	11/1990
WO	WO 91/10424	7/1991
WO	WO-9110424	7/1991
WO	WO 91/11193	8/1991
WO	WO-9111193	8/1991
WO	WO 91/12779	9/1991
WO	WO-9112779	9/1991
WO	WO-9200747	1/1992
WO	WO 92/12717	8/1992
WO	WO-9212717	8/1992
WO	WO-921586	9/1992
WO	WO 9215286	9/1992
WO	WO 93/06792	4/1993
WO	WO-9306792	4/1993
WO	WO-9311120	6/1993
WO	WO-9407529	4/1994
WO	WO 94/21308	9/1994
WO	WO-9421308	9/1994
WO	WO 94/24961	11/1994
WO	WO-9424961	11/1994
WO	WO-9424962	11/1994
WO	WO 95/03036	2/1995

WO	WO 95/03795	2/1995
WO	WO-9503036	2/1995
WO	WO-9503795	2/1995
WO	WO 95/24908	9/1995
WO	WO-9524908	9/1995
WO	WO 96/03092	2/1996
WO	WO-9603092	2/1996
WO	WO 96/25176	8/1996
WO	WO 96/29028	9/1996
WO	WO-9629028	9/1996
WO	WO 96/32907	10/1996
WO	WO 97/04721	2/1997
WO	WO-9704721	2/1997
WO	WO-9710011	3/1997
WO	WO 98/08566	3/1998
WO	WO 98/18407	5/1998
WO	WO 98/19628	5/1998
WO	WO-9818407	5/1998
WO	WO-9819628	5/1998
WO	WO 98/23228	6/1998
WO	WO 98/23244	6/1998
WO	98/36784	8/1998
WO	WO 98/58600	12/1998
WO	WO-9858600	12/1998
WO	WO 99/15108	4/1999
WO	WO 99/16386 A1 *	4/1999
WO	WO 99/16477	4/1999
WO	WO-9915108	4/1999
WO	WO 99/44536	9/1999
WO	WO 99/49928	10/1999
WO	WO-9949928	10/1999
WO	WO 99/55396	11/1999
WO	WO 00/10613	3/2000
WO	WO-0010622	3/2000
WO	WO 00/45744	8/2000
WO	WO 00/69368	11/2000
WO	WO 00/71054	11/2000
WO	01/17577	3/2001
WO	WO 01/45862	6/2001
WO	WO-0145763	6/2001
WO	WO 01/49338	7/2001
WO	WO-0152915	7/2001
WO	WO 01/87376	11/2001
WO	WO 02/17880	3/2002
WO	02/26281	4/2002
WO	WO-0226162	4/2002
WO	WO-0241931 A2	5/2002
WO	WO-0241931 A3	5/2002
WO	WO-02087586	11/2002
WO	WO-03018083	3/2003
WO	WO-04043510	5/2004
WO	WO-04043511	5/2004

OTHER PUBLICATIONS

Hakan Emanuelsson et al., The Jostent Coronary Stent Range, Ch. 19.

Bonnie L. Hiatt, et al. "The Drug-Eluting Stent: Is It the Holy Grail?" Reviews in Cardiovascular Medicine. (2001) vol. 2, No. 4, pp. 190-196.

Jennifer L. West, "Drug Delivery—Pulsed Polymers", Nature Materials, vol. 2, Nov. 2003, pp. 709-710.

Patrick W. Serruys, et al., "Heparin-Coated Palmaz-Schatz Stents in Human Coronary Arteries" Circulation, 1996; 93:412-422.

Ran Kornowski, et al. (Washington Hospital, Wash. D.C.); "Slow-Release Taxol Coated GR11 Stents Reduce Neointima Formation in a Porcine Coronary in-Stent Restenosis Model"; Abstract from the American Heart Association's 70th Scientific Sessions (Nov. 9-12, 1997).

U.S. Appl.No. 09/688,092 filed Oct. 16, 2000, Shanley.

U.S. Appl. No. 09/948,987 filed Sep. 7, 2001, Shanley.

* cited by examiner




FIG. 1




FIG. 2




FIG. 3








FIG. 9




FIG. 10




FIG. 11A




FIG. 11B




FIG. 12




FIG. 13




FIG. 14




FIG. 15A




FIG. 15B




FIG. 15C




FIG. 16A




FIG. 16B




FIG. 17A




FIG. 16C




FIG. 17B




FIG. 18A




FIG. 18B




FIG. 18C





FIG. 19



1

EXPANDABLE MEDICAL DEVICE FOR DELIVERY OF BENEFICIAL AGENT

CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation-in-part of U.S. application Ser. No. 09/688,092, filed Oct. 16, 2000, now abandoned, which is incorporated herein in its entirety. This application also claims priority to U.S. Provisional Application Ser. No. 60/314,259, filed Aug. 20, 2001 which is incorporated herein in its entirety.

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention relates to tissue-supporting medical devices, and more particularly to expandable, non-removable devices that are implanted within a bodily lumen of a living animal or human to support the organ and maintain patency, and that can deliver a beneficial agent to the intervention site.

2. Summary of the Related Art

In the past, permanent or biodegradable devices have been developed for implantation within a body passageway to maintain patency of the passageway. These devices are typically introduced percutaneously, and transported transluminally until positioned at a desired location. These devices are then expanded either mechanically, such as by the expansion of a mandrel or balloon positioned inside the device, or expand themselves by releasing stored energy upon actuation within the body. Once expanded within the lumen, these devices, called stents, become encapsulated within the body tissue and remain a permanent implant.

Known stent designs include monofilament wire coil stents (U.S. Pat. No. 4,969,458); welded metal cages (U.S. Pat. Nos. 4,733,665 and 4,776,337); and, most prominently, thin-walled metal cylinders with axial slots formed around the circumference (U.S. Pat. Nos. 4,733,665; 4,739,762; and 4,776,337). Known construction materials for use in stents include polymers, organic fabrics and biocompatible metals, such as, stainless steel, gold, silver, tantalum, titanium, and shape memory alloys such as Nitinol.

U.S. Pat. Nos. 4,733,665; 4,739,762; and 4,776,337 disclose expandable and deformable interluminal vascular grafts in the form of thin-walled tubular members with axial slots allowing the members to be expanded radially outwardly into contact with a body passageway. After insertion, the tubular members are mechanically expanded beyond their elastic limit and thus permanently fixed within the body. U.S. Pat. No. 5,545,210 discloses a thin-walled tubular stent geometrically similar to those discussed above, but constructed of a nickel-titanium shape memory alloy ("Nitinol"), which can be permanently fixed within the body without exceeding its elastic limit. All of these stents share a critical design property: in each design, the features that undergo permanent deformation during stent expansion are prismatic, i.e., the cross sections of these features remain constant or change very gradually along their entire active length. These prismatic structures are ideally suited to providing large amounts of elastic deformation before permanent deformation commences, which in turn leads to sub-optimal device performance in important properties including stent expansion force, stent recoil, strut element stability, stent securement on delivery catheters, and radio-

2

U.S. Pat. No. 6,241,762, which is incorporated herein by reference in its entirety, discloses a non-prismatic stent design which remedies the above mentioned performance deficiencies of previous stents. In addition, preferred embodiments of this patent provide a stent with large, non-deforming strut and link elements, which can contain holes without compromising the mechanical properties of the strut or link elements, or the device as a whole. Further, these holes may serve as large, protected reservoirs for delivering various beneficial agents to the device implantation site.

Of the many problems that may be addressed through stent-based local delivery of beneficial agents, one of the most important is restenosis. Restenosis is a major complication that can arise following vascular interventions such as angioplasty and the implantation of stents. Simply defined, restenosis is a wound healing process that reduces the vessel lumen diameter by extracellular matrix deposition and vascular smooth muscle cell proliferation, and which may ultimately result in renarrowing or even reocclusion of the lumen. Despite the introduction of improved surgical techniques, devices and pharmaceutical agents, the overall restenosis rate is still reported in the range of 25% to 50% within six to twelve months after an angioplasty procedure. To treat this condition, additional revascularization procedures are frequently required, thereby increasing trauma and risk to the patient.

Some of the techniques under development to address the problem of restenosis include irradiation of the injury site and the use of conventional stents to deliver a variety of beneficial or pharmaceutical agents to the wall of the traumatized vessel. In the latter case, a conventional stent is frequently surface-coated with a beneficial agent (often a drug-impregnated polymer) and implanted at the angioplasty site. Alternatively, an external drug-impregnated polymer sheath is mounted over the stent and co-deployed in the vessel.

While acute outcomes from radiation therapies appeared promising initially, long term beneficial outcomes have been limited to reduction in restenosis occurring within a previously implanted stent, so-called 'in-stent' restenosis. Radiation therapies have not been effective for preventing restenosis in de novo lesions. Polymer sheaths that span stent struts have also proven problematic in human clinical trials due to the danger of blocking flow to branch arteries, incomplete apposition of stent struts to arterial walls and other problems. Unacceptably high levels of MACE (Major Adverse Cardiac Events that include death, heart attack, or the need for a repeat angioplasty or coronary artery bypass surgery) have resulted in early termination of clinical trials for sheath covered stents.

Conventional stents with surface coatings of various beneficial agents, by contrast, have shown promising early results. U.S. Pat. No. 5,716,981, for example, discloses a stent that is surface-coated with a composition comprising a polymer carrier and paclitaxel (a well-known compound that is commonly used in the treatment of cancerous tumors). The patent offers detailed descriptions of methods for coating stent surfaces, such as spraying and dipping, as well as the desired character of the coating itself: it should "coat the stent smoothly and evenly" and "provide a uniform, predictable, prolonged release of the anti-angiogenic factor." Surface coatings, however, can provide little actual control over the release kinetics of beneficial agents. These coatings are necessarily very thin, typically 5 to 8 microns deep. The surface area of the stent, by comparison is very large, so that

the entire volume of the beneficial agent has a very short diffusion path to discharge into the surrounding tissue.

Increasing the thickness of the surface coating has the beneficial effects of improving drug release kinetics including the ability to control drug release and to allow increased drug loading. However, the increased coating thickness results in increased overall thickness of the stent wall. This is undesirable for a number of reasons, including increased trauma to the vessel wall during implantation, reduced flow cross-section of the lumen after implantation, and increased vulnerability of the coating to mechanical failure or damage during expansion and implantation. Coating thickness is one of several factors that affect the release kinetics of the beneficial agent, and limitations on thickness thereby limit the range of release rates, durations, and the like that can be achieved.

In addition to sub-optimal release profiles, there are further problems with surface coated stents. The fixed matrix polymer carriers frequently used in the device coatings typically retain approximately 30% of the beneficial agent in the coating indefinitely. Since these beneficial agents are frequently highly cytotoxic, sub-acute and chronic problems such as chronic inflammation, late thrombosis, and late or incomplete healing of the vessel wall may occur. Additionally, the carrier polymers themselves are often highly inflammatory to the tissue of the vessel wall. On the other hand, use of bio-degradable polymer carriers on stent surfaces can result in the creation of "virtual spaces" or voids between the stent and tissue of the vessel wall after the polymer carrier has degraded, which permits differential motion between the stent and adjacent tissue. Resulting problems include micro-abrasion and inflammation, stent drift, and failure to re-endothelialize the vessel wall.

Another significant problem is that expansion of the stent may stress the overlying polymeric coating causing the coating to plastically deform or even to rupture, which may therefore effect drug release kinetics or have other untoward effects. Further, expansion of such a coated stent in an atherosclerotic blood vessel will place circumferential shear forces on the polymeric coating, which may cause the coating to separate from the underlying stent surface. Such separation may again have untoward effects including embolization of coating fragments causing vascular obstruction.

SUMMARY OF THE INVENTION

In view of the drawbacks of the prior art, it would be advantageous to provide a stent capable of delivering a relatively large volume of a beneficial agent to a traumatized site in a vessel while avoiding the numerous problems associated with surface coatings containing beneficial agents, without increasing the effective wall thickness of the stent, and without adversely impacting the mechanical expansion properties of the stent.

It would further be advantageous to have such a stent, which also significantly increases the available depth of the beneficial agent reservoir.

It would also be advantageous to have methods of loading various beneficial agents or combinations of beneficial agents into these deep reservoirs, which provided control over the temporal release kinetics of the agents.

In accordance with one aspect of the invention, an expandable medical device includes a plurality of elongated struts, said plurality of elongated struts joined together to form a substantially cylindrical device which is expandable from a cylinder having a first diameter to a cylinder having a second diameter, said plurality of struts each having a strut

width in a circumferential direction and a strut thickness in a radial direction, at least one opening in at least one of the plurality of struts, and at least one beneficial agent provided in the at least one opening in a plurality of layers.

In accordance with a further aspect of the present invention, an expandable medical device includes a plurality of elongated struts, said plurality of elongated struts joined together to form a substantially cylindrical device which is expandable from a cylinder having a first diameter to a cylinder having a second diameter, said plurality of struts each having a strut width in a circumferential direction and a strut thickness in a radial direction, at least one opening in at least one of the plurality of struts, and at least one beneficial agent provided in the at least one opening. A shape of the beneficial agent is configured to achieve a desired agent delivery profile.

In accordance with another aspect of the present invention, an expandable medical device for treating cardiac arrhythmias includes an expandable cylindrical device having a plurality of struts, a plurality of openings in the plurality of struts, and a chemically ablative agent provided in the openings. The openings are configured to deliver the chemically ablative agent to tissue surrounding the expandable cylindrical device without permanently trapping any agent in the openings.

In accordance with an additional aspect of the present invention, an expandable medical device for treating cardiac arrhythmias includes an expandable cylindrical device having a plurality of struts, a plurality of openings in the plurality of struts, and an anti-arrhythmic drug and a non-biodegradable carrier provided in the openings. The openings are configured to deliver the anti-arrhythmic drug to tissue surrounding the cylindrical device over an extended time period.

In accordance with another aspect of the present invention, a method of forming an expandable medical device includes providing an expandable medical device with a plurality of struts, said plurality of struts joined together to form a substantially cylindrical device which is expandable from a cylinder having a first diameter to a cylinder having a second diameter, forming at least one opening in at least one of the plurality of struts, and delivering at least one beneficial agent into the at least one opening in a plurality of layers.

BRIEF DESCRIPTION OF THE DRAWINGS

The invention will now be described in greater detail with reference to the preferred embodiments illustrated in the accompanying drawings, in which like elements bear like reference numerals, and wherein:

FIG. 1 is a perspective view of a tissue supporting device in accordance with a first preferred embodiment of the present invention;

FIG. 2 is an enlarged side view of a portion of the device of FIG. 1;

FIG. 3 is an enlarged side view of a tissue supporting device in accordance with a further preferred embodiment of the present invention;

FIG. 4 is an enlarged side view of a portion of the stent shown in FIG. 3;

FIG. 5 is an enlarged cross section of an opening;

FIG. 6 is an enlarged cross section of an opening illustrating beneficial agent loaded into the opening;

FIG. 7 is an enlarged cross section of an opening illustrating a beneficial agent loaded into the opening and a thin coating of a beneficial agent;

5

FIG. 8 is an enlarged cross section of an opening illustrating a beneficial agent loaded into the opening and thin coatings of different beneficial agents on different surfaces of the device;

FIG. 9 is an enlarged cross section of an opening illustrating a beneficial agent provided in a plurality of layers;

FIG. 10 is an enlarged cross section of an opening illustrating a beneficial agent and a barrier layer loaded into the opening in layers;

FIG. 11A is an enlarged cross section of an opening illustrating a beneficial agent, a biodegradable carrier, and a barrier layer loaded into the opening in layers;

FIG. 11B is a graph of the release kinetics of the device of FIG. 11A;

FIG. 12 is an enlarged cross section of an opening illustrating different beneficial agents, carrier, and barrier layers loaded into the opening;

FIG. 13 is an enlarged cross section of an opening illustrating a beneficial agent loaded into the opening in layers of different concentrations;

FIG. 14 is an enlarged cross section of an opening illustrating a beneficial agent loaded into the opening in layers of microspheres of different sizes;

FIG. 15A is an enlarged cross section of a tapered opening illustrating a beneficial agent loaded into the opening;

FIG. 15B is an enlarged cross section of the tapered opening of FIG. 15A with the beneficial agent partially degraded;

FIG. 15C is a graph of the release kinetics of the device of FIGS. 15A and 15B;

FIG. 16A is an enlarged cross section of an opening illustrating a beneficial agent loaded into the opening in a shape configured to achieve a desired agent delivery profile;

FIG. 16B is an enlarged cross section of the opening of FIG. 16A with the beneficial agent partially degraded;

FIG. 16C is a graph of the release kinetics of the device of FIGS. 16A and 16B;

FIG. 17A is an enlarged cross section of an opening illustrating the beneficial agent loaded into the opening and a spherical shape;

FIG. 17B is a graph of the release kinetics of the device of FIG. 17A;

FIG. 18A is an enlarged cross section of an opening illustrating a plurality of beneficial agent layers and a barrier layer with an opening for achieving a desired agent delivery profile;

FIG. 18B is an enlarged cross section of the opening of FIG. 18A with the agent layers beginning to degraded;

FIG. 18C is an enlarged cross section of the opening of FIG. 18A with the agent layers further degraded; and

FIG. 19 is an enlarged cross section of an opening illustrating a plurality of cylindrical beneficial agent layers.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Referring to FIGS. 1 and 2, a tissue supporting device in accordance with one preferred embodiment of the present invention is shown generally by reference numeral 10. The tissue supporting device 10 includes a plurality of cylindrical tubes 12 connected by S-shaped bridging elements 14. The bridging elements 14 allow the tissue supporting device to bend axially when passing through the tortuous path of the vasculature to the deployment site and allow the device to bend when necessary to match the curvature of a vessel wall to be supported. Each of the cylindrical tubes 12 has a

6

plurality of axial slots 16 extending from an end surface of the cylindrical tube toward an opposite end surface.

Formed between the slots 16 is a network of axial struts 18 and links 22. The struts 18 and links 22 are provided with openings for receiving and delivering a beneficial agent. As will be described below with respect to FIGS. 9–17, the beneficial agent is loaded into the openings in layers or other configurations which provide control over the temporal release kinetics of the agent.

Each individual strut 18 is preferably linked to the rest of the structure through a pair of reduced sections 20, one at each end, which act as stress/strain concentration features. The reduced sections 20 of the struts function as hinges in the cylindrical structure. Since the stress/strain concentration features are designed to operate into the plastic deformation range of generally ductile materials, they are referred to as ductile hinges 20. The ductile hinges 20 are described in further detail in U.S. Pat. No. 6,241,762, which has been incorporated herein by reference.

With reference to the drawings and the discussion, the width of any feature is defined as its dimension in the circumferential direction of the cylinder. The length of any feature is defined as its dimension in the axial direction of the cylinder. The thickness of any feature is defined as the wall thickness of the cylinder.

The presence of the ductile hinges 20 allows all of the remaining features in the tissue supporting device to be increased in width or the circumferentially oriented component of their respective rectangular moments of inertia—thus greatly increasing the strength and rigidity of these features. The net result is that elastic, and then plastic deformation commence and propagate in the ductile hinges 20 before other structural elements of the device undergo any significant elastic deformation. The force required to expand the tissue supporting device 10 becomes a function of the geometry of the ductile hinges 20, rather than the device structure as a whole, and arbitrarily small expansion forces can be specified by changing hinge geometry for virtually any material wall thickness. The ability to increase the width and thickness of the struts 18 and links 22 provides additional area and depth for the beneficial agent receiving openings.

In the preferred embodiment of FIGS. 1 and 2, it is desirable to increase the width of the individual struts 18 between the ductile hinges 20 to the maximum width that is geometrically possible for a given diameter and a given number of struts arrayed around that diameter. The only geometric limitation on strut width is the minimum practical width of the slots 16 which is about 0.002 inches (0.0508 mm) for laser machining. Lateral stiffness of the struts 18 increases as the cube of strut width, so that relatively small increases in strut width significantly increase strut stiffness. The net result of inserting ductile hinges 20 and increasing strut width is that the struts 18 no longer act as flexible leaf springs, but act as essentially rigid beams between the ductile hinges. All radial expansion or compression of the cylindrical tissue supporting device 10 is accommodated by mechanical strain in the hinge features 20, and yield in the hinge commences at very small overall radial expansion or compression.

The ductile hinge 20 illustrated in FIGS. 1 and 2 is exemplary of a preferred structure that will function as a stress/strain concentrator. Many other stress/strain concentrator configurations may also be used as the ductile hinges in the present invention, as shown and described by way of example in U.S. Pat. No. 6,241,762. The geometric details of the stress/strain concentration features or ductile hinges 20

can be varied greatly to tailor the exact mechanical expansion properties to those required in a specific application.

Although a tissue supporting device configuration has been illustrated in FIG. 1 which includes ductile hinges, it should be understood that the beneficial agent may be contained in openings in struts having a variety of designs including the designs illustrated in U.S. Provisional Patent Application Ser. No. 60/314,360, filed Aug. 20, 2001 and U.S. patent application Ser. No. 09/948,987, filed on Sep. 7, 2001, which are incorporated herein by reference. The present invention incorporating beneficial agent openings may also be used with other known stent designs.

As shown in FIGS. 1–4, at least one and more preferably a series of openings 24 are formed by laser drilling or any other means known to one skilled in the art at intervals along the neutral axis of the struts 18. Similarly, at least one and preferably a series of openings 26 are formed at selected locations in the links 22. Although the use of openings 24 and 26 in both the struts 18 and links 22 is preferred, it should be clear to one skilled in the art that openings could be formed in only one of the struts and links. Openings may also be formed in the bridging elements 14. In the embodiment of FIGS. 1 and 2, the openings 24, 26 are circular in nature and form cylindrical holes extending through the width of the tissue supporting device 10. It should be apparent to one skilled in the art, however, that openings of any geometrical shape or configuration could of course be used without departing from the scope of the present invention. In addition, openings having a depth less than the thickness of the device may also be used.

The behavior of the struts 18 in bending is analogous to the behavior of an I-beam or truss. The outer edge elements 32 of the struts 18, shown in FIG. 2, correspond to the I-beam flange and carry the tensile and compressive stresses, whereas the inner elements 34 of the struts 18 correspond to the web of an I-beam which carries the shear and helps to prevent buckling and wrinkling of the faces. Since most of the bending load is carried by the outer edge elements 32 of the struts 18, a concentration of as much material as possible away from the neutral axis results in the most efficient sections for resisting strut flexure. As a result, material can be judiciously removed along the axis of the strut so as to form openings 24, 26 without adversely impacting the strength and rigidity of the strut. Since the struts 18 and links 22 thus formed remain essentially rigid during stent expansion, the openings 24, 26 are also non-deforming.

The openings 24, 26 in the struts 18 may promote the healing of the intervention site by promoting regrowth of the endothelial cells. By providing the openings 24, 26 in the struts, 18, the cross section of the strut is effectively reduced without decreasing the strength and integrity of the strut, as described above. As a result, the overall distance across which endothelial cell regrowth must occur is also reduced to approximately 0.0025–0.0035 inches, which is approximately one-half of the thickness of a conventional stent. It is further believed that during insertion of the expandable medical device, cells from the endothelial layer may be scraped from the inner wall of the vessel by the openings 24, 26 and remain therein after implantation. The presence of such endothelial cells would thus provide a basis for the healing of the vessel wall.

The openings 24, 26 are loaded with an agent, most preferably a beneficial agent, for delivery to the vessel wall which the tissue supporting device 10 is supporting.

The terms “agent” and “beneficial agent” as used herein are intended to have their broadest possible interpretation and are used to include any therapeutic agent or drug, as well

as inactive agents such as barrier layers or carrier layers. The terms “drug” and “therapeutic agent” are used interchangeably to refer to any therapeutically active substance that is delivered to a bodily conduit of a living being to produce a desired, usually beneficial, effect. The present invention is particularly well suited for the delivery of antiproliferatives (anti-restenosis agents) such as paclitaxel and rapamycin for example, and antithrombins such as heparin, for example.

The beneficial agents used in the present invention include classical small molecular weight therapeutic agents commonly referred to as drugs including all classes of action as exemplified by, but not limited to: antiproliferatives, antithrombins, antiplatelet, antilipid, anti-inflammatory, and anti-angiogenic, vitamins, ACE inhibitors, vasoactive substances, antimetotics, metallo-proteinase inhibitors, NO donors, estradiols, anti-sclerosing agents, alone or in combination. Beneficial agent also includes larger molecular weight substances with drug like effects on target tissue sometimes called biologic agents including but not limited to: peptides, lipids, protein drugs, enzymes, oligonucleotides, ribozymes, genetic material, prions, virus, bacteria, and eucaryotic cells such as endothelial cells, monocyte/macrophages or vascular smooth muscle cells to name but a few examples. Other beneficial agents may include but not be limited to physical agents such as microspheres, microbubbles, liposomes, radioactive isotopes, or agents activated by some other form of energy such as light or ultrasonic energy, or by other circulating molecules that can be systemically administered.

The embodiment of the invention shown in FIGS. 1 and 2 can be further refined by using Finite Element Analysis and other techniques to optimize the deployment of the beneficial agent within the openings of the struts and links. Basically, the shape and location of the openings 24, 26 can be modified to maximize the volume of the voids while preserving the relatively high strength and rigidity of the struts 18 with respect to the ductile hinges 20.

FIG. 3 illustrates a further preferred embodiment of the present invention, wherein like reference numerals have been used to indicate like components. The tissue supporting device 100 includes a plurality of cylindrical tubes 12 connected by S-shaped bridging elements 14. Each of the cylindrical tubes 12 has a plurality of axial slots 16 extending from an end surface of the cylindrical tube toward an opposite end surface. Formed between the slots 16 is a network of axial struts 18 and links 22. Each individual strut 18 is linked to the rest of the structure through a pair of ductile hinges 20, one at each end, which act as stress/strain concentration features. Each of the ductile hinges 20 is formed between an arc surface 28 and a concave notch surface 29.

At intervals along the neutral axis of the struts 18, at least one and more preferably a series of openings 24' are formed by laser drilling or any other means known to one skilled in the art. Similarly, at least one and preferably a series of openings 26' are formed at selected locations in the links 22. Although the use of openings 24', 26' in both the struts 18 and links 22 is preferred, it should be clear to one skilled in the art that openings could be formed in only one of the struts and links. In the illustrated embodiment, the openings 24' in the struts 18 are generally rectangular whereas the openings 26' in the links 22 are polygonal. It should be apparent to one skilled in the art, however, that openings of any geometrical shape or configuration could of course be used, and that the shape of openings 24, 24' may be the same or different from the shape of openings 26, 26', without departing from the scope of the present invention. As

described in detail above, the openings **24'**, **26'** may be loaded with an agent, most preferably a beneficial agent, for delivery to the vessel in which the tissue support device **100** is deployed. Although the openings **24'**, **26'** are preferably through openings, they may also be recesses extending only partially through the thickness of the struts and links.

The relatively large, protected openings **24**, **24'**, **26**, **26'**, as described above, make the expandable medical device of the present invention particularly suitable for delivering agents having more esoteric larger molecules or genetic or cellular agents, such as, for example, protein drugs, enzymes, antibodies, antisense oligonucleotides, ribozymes, gene/vector constructs, and cells (including but not limited to cultures of a patient's own endothelial cells). Many of these types of agents are biodegradable or fragile, have a very short or no shelf life, must be prepared at the time of use, or cannot be pre-loaded into delivery devices such as stents during the manufacture thereof for some other reason. The large through-openings in the expandable device of the present invention form protected areas or receptors to facilitate the loading of such an agent either at the time of use or prior to use, and to protect the agent from abrasion and extrusion during delivery and implantation.

The volume of beneficial agent that can be delivered using through openings is about 3 to 10 times greater than the volume of a 5 micron coating covering a stent with the same stent/vessel wall coverage ratio. This much larger beneficial agent capacity provides several advantages. The larger capacity can be used to deliver multi-drug combinations, each with independent release profiles, for improved efficacy. Also, larger capacity can be used to provide larger quantities of less aggressive drugs and to achieve clinical efficacy without the undesirable side-effects of more potent drugs, such as retarded healing of the endothelial layer.

Through openings also decrease the surface area of the beneficial agent bearing compounds to which the vessel wall surface is exposed. For typical devices with beneficial agent openings, this exposure decreases by a factors ranging from about 6:1 to 8:1, by comparison with surface coated stents. This dramatically reduces the exposure of vessel wall tissue to polymer carriers and other agents that can cause inflammation, while simultaneously increasing the quantity of beneficial agent delivered, and improving control of release kinetics.

FIG. 4 shows an enlarged view of one of the struts **18** of device **100** disposed between a pair of ductile hinges **20** having a plurality of openings **24'**. FIG. 5 illustrates a cross section of one of the openings **24'** shown in FIG. 4. FIG. 6 illustrates the same cross section when a beneficial agent **36** has been loaded into the opening **24'** of the strut **18**. Optionally, after loading the opening **24'** and/or the opening **26'** with a beneficial agent **36**, the entire exterior surface of the stent can be coated with a thin layer of a beneficial agent **38**, which may be the same as or different from the beneficial agent **36**, as schematically shown in FIG. 7. Still further, another variation of the present invention would coat the outwardly facing surfaces of the stent with a first beneficial agent **38** while coating the inwardly facing surfaces of the stent with a different beneficial agent **39**, as illustrated in FIG. 8. The inwardly facing surface of the stent would be defined as at least the surface of the stent which, after expansion, forms the inner passage of the vessel. The outwardly facing surface of the stent would be defined as at least the surface of the stent which, after expansion, is in contact with and directly supports the inner wall of the vessel. The beneficial agent **39** coated on the inner surfaces may be a barrier layer which prevents the beneficial agent **36**

from passing into the lumen of the blood vessel and being washed away in the blood stream.

FIG. 9 shows a cross section of an opening **24** in which one or more beneficial agents have been loaded into the opening **24** in discrete layers **50**. One method of creating such layers is to deliver a solution comprising beneficial agent, polymer carrier, and a solvent into the opening and evaporating the solvent to create a thin solid layer of beneficial agent in the carrier. Other methods of delivering the beneficial agent can also be used to create layers. According to another method for creating layers, a beneficial agent may be loaded into the openings alone if the agent is structurally viable without the need for a carrier. The process can then be repeated until each opening is partially or entirely filled.

In a typical embodiment, the total depth of the opening **24** is about 125 to about 140 microns, and the typical layer thickness would be about 2 to about 50 microns, preferably about 12 microns. Each typical layer is thus individually about twice as thick as the typical coating applied to surface-coated stents. There would be at least two and preferably about ten to twelve such layers in a typical opening, with a total beneficial agent thickness about 25 to 28 times greater than a typical surface coating. According to one preferred embodiment of the present invention, the openings have an area of at least 5×10^{-6} square inches, and preferably at least 7×10^{-6} square inches.

Since each layer is created independently, individual chemical compositions and pharmacokinetic properties can be imparted to each layer. Numerous useful arrangements of such layers can be formed, some of which will be described below. Each of the layers may include one or more agents in the same or different proportions from layer to layer. The layers may be solid, porous, or filled with other drugs or excipients.

FIG. 9 shows the simplest arrangement of layers including identical layers **50** that together form a uniform, homogeneous distribution of beneficial agent. If the carrier polymer were comprised of a biodegradable material, then erosion of the beneficial agent containing carrier would occur on both faces of the opening at the same time, and beneficial agent would be released at an approximately linear rate over time corresponding to the erosion rate of the carrier. This linear or constant release rate is referred to as a zero order delivery profile. Use of biodegradable carriers in combination with through openings is especially useful, to guarantee 100% discharge of the beneficial agent within a desired time without creating virtual spaces or voids between the radially outermost surface of the stent and tissue of the vessel wall. When the biodegradable material in the through openings is removed, the openings may provide a communication between the strut-covered vessel wall and the blood stream. Such communication may accelerate vessel healing and allow the ingrowth of cells and extracellular components that more thoroughly lock the stent in contact with the vessel wall. Alternatively, some through-openings may be loaded with beneficial agent while others are left unloaded. The unloaded holes could provide an immediate nidus for the ingrowth of cells and extracellular components to lock the stent into place, while loaded openings dispense the beneficial agent.

The advantage of complete erosion using the through openings over surface coated stents opens up new possibilities for stent-based therapies. In the treatment of cardiac arrhythmias, such as atrial fibrillation both sustained and paroxysmal, sustained ventricular tachycardia, super ventricular tachycardia including reentrant and ectopic, and

sinus tachycardia, a number of techniques under development attempt to ablate tissue in the pulmonary veins or some other critical location using various energy sources, e.g. microwaves, generally referred to as radio-frequency ablation, to create a barrier to the propagation of undesired electrical signals in the form of scar tissue. These techniques have proven difficult to control accurately. A stent based therapy using through openings, biodegradable carriers, and associated techniques described herein could be used to deliver a chemically ablative agent in a specific, precise pattern to a specific area for treatment of atrial fibrillation, while guaranteeing that none of the inherently cytotoxic ablating agent could be permanently trapped in contact with the tissue of the vessel wall.

If, on the other hand, the goal of a particular therapy is to provide a long term effect, beneficial agents located in openings provide an equally dramatic advantage over surface coated devices. In this case, a composition comprising a beneficial agent and a non-biodegradable carrier would be loaded into the through openings, preferably in combination with a diffusion barrier layer as described below. To continue the cardiac arrhythmias example, it might be desirable to introduce a long-term anti-arrhythmic drug near the ostia of the pulmonary veins or some other critical location. The transient diffusion behavior of a beneficial agent through a non-biodegradable carrier matrix can be generally described by Fick's second law:

$$\frac{\partial C_x}{\partial t} = \frac{\partial}{\partial x} \left[D \frac{\partial C_x}{\partial x} \right]$$

Where C is the concentration of beneficial agent at cross section x, x is either the thickness of a surface coating or depth of a through opening, D is the diffusion coefficient and t is time. The solution of this partial differential equation for a through opening with a barrier layer will have the form of a normalized probability integral or Gaussian Error Function, the argument of which will contain the term

$$\frac{x}{2\sqrt{Dt}}$$

To compare the time intervals over which a given level of therapy can be sustained for surface coatings vs. through openings, we can use Fick's Second Law to compare the times required to achieve equal concentrations at the most inward surfaces of the coating and opening respectively, i.e. the values of x and t for which the arguments of the Error Function are equal:

$$\frac{x}{2\sqrt{Dt_1}} = \frac{x_2}{2\sqrt{Dt_2}} \Rightarrow \frac{x_1^2}{x_2^2} = \frac{t_1}{t_2}$$

The ratio of diffusion times to achieve comparable concentrations thus varies as the square of the ratio of depths. A typical opening depth is about 140 microns while a typical coating thickness is about 5 micron; the square of this ratio is 784, meaning that the effective duration of therapy for through openings is potentially almost three orders of magnitude greater for through openings than for surface coatings of the same composition. The inherent non-linearity of such

release profiles can in part be compensated for in the case of through openings, but not in thin surface coatings, by varying the beneficial agent concentration of layers in a through opening as described below. It will be recalled that, in addition to this great advantage in beneficial agent delivery duration, through openings are capable of delivering a 3 to 10 times greater quantity of beneficial agent, providing a decisive overall advantage in sustained therapies. The diffusion example above illustrates the general relationship between depth and diffusion time that is characteristic of a wider class of solid state transport mechanisms.

Beneficial agent that is released to the radially innermost or inwardly facing surface known as the lumen facing surface of an expanded device may be rapidly carried away from the targeted area, for example by the bloodstream, and thus lost. Up to half of the total agent loaded in such situations may have no therapeutic effect due to being carried away by the bloodstream. This is probably the case for all surface coated stents as well as the through opening device of FIG. 9.

FIG. 10 shows a device in which the first layer 52 is loaded into a through opening 24 such that the inner surface of the layer is substantially co-planar with the inwardly facing surface 54 of the cylindrical device. The first layer 52 is comprised of a material called a barrier material which blocks or retards biodegradation of subsequent layers in the inwardly facing direction toward the vessel lumen, and/or blocks or retards diffusion of the beneficial agent in that direction. Biodegradation of other layers or beneficial agent diffusion can then proceed only in the direction of the outwardly facing surface 56 of the device, which is in direct contact with the targeted tissue of the vessel wall. The barrier layer 52 may also function to prevent hydration of inner layers of beneficial agent and thus prevent swelling of the inner layers when such layers are formed of hygroscopic materials. The barrier layer 52 may further be comprised of a biodegradable material that degrades at a much slower rate than the biodegradable material in the other layers, so that the opening will eventually be entirely cleared. Providing a barrier layer 52 in the most inwardly facing surface of a through-opening thus guarantees that the entire load of beneficial agent is delivered to the target area in the vessel wall. It should be noted that providing a barrier layer on the inwardly facing surface of a surface-coated stent without openings does not have the same effect; since the beneficial agent in such a coating cannot migrate through the metal stent to the target area on the outer surface, it simply remains trapped on the inner diameter of the device, again having no therapeutic effect.

Barrier layers can be used to control beneficial agent release kinetics in more sophisticated ways. A barrier layer 52 with a pre-determined degradation time could be used to deliberately terminate the beneficial agent therapy at a pre-determined time, by exposing the underlying layers to more rapid bio-degradation from both sides. Barrier layers can also be formulated to be activated by a separate, systemically applied agent. Such systemically applied agent could change the porosity of the barrier layer and/or change the rate of bio-degradation of the barrier layer or the bulk beneficial agent carrier. In each case, release of the beneficial agent could be activated by the physician at will by delivery of the systemically applied agent. A further embodiment of physician activated therapy would utilize a beneficial agent encapsulated in micro-bubbles and loaded into device openings. Application of ultrasonic energy from an exterior of the body could be used to collapse the bubbles at a desired time, releasing the beneficial agent to diffuse to the outwardly facing surface of the reservoirs. These activation techniques can be used in conjunction with the release kinetics control

13

techniques described herein to achieve a desired drug release profile that can be activated and/or terminated at selectable points in time.

FIG. 11A shows an arrangement of layers provided in a through opening in which layers **50** of a beneficial agent in a biodegradable carrier material, are alternated with layers **58** of the biodegradable carrier material alone, with no active agent loaded, and a barrier layer **52** is provided at the inwardly facing surface. As shown in the release kinetics plot of FIG. 11B, such an arrangement releases beneficial agent in three programmable bursts or waves achieving a stepped or pulsatile delivery profile. The use of carrier material layers without active agent creates the potential for synchronization of drug release with cellular biochemical processes for enhanced efficacy.

Alternatively, different layers could be comprised of different beneficial agents altogether, creating the ability to release different beneficial agents at different points in time, as shown in FIG. 12. For example, in FIG. 12, a layer **60** of anti-thrombotic agent could be deposited at the inwardly facing surface of the stent, followed by a barrier layer **52** and alternating layers of anti-proliferatives **62** and anti-inflammatories **64**. This configuration could provide an initial release of anti-thrombotic agent into the bloodstream while simultaneously providing a gradual release of anti-proliferatives interspersed with programmed bursts of anti-inflammatory agents to the vessel wall. The configurations of these layers can be designed to achieve the agent delivery bursts at particular points in time coordinated with the body's various natural healing processes.

A further alternative is illustrated in FIG. 13. Here the concentration of the same beneficial agent is varied from layer to layer, creating the ability to generate release profiles of arbitrary shape. Progressively increasing the concentration of agent in the layers **66** with increasing distance from the outwardly facing surface **56**, for example, produces a release profile with a progressively increasing release rate, which would be impossible to produce in a thin surface coating.

Another general method for controlling beneficial agent release kinetics is to alter the beneficial agent flux by changing the surface area of drug elution sources as a function of time. This follows from Fick's First Law, which states that the instantaneous molecular flux is proportional to surface area, among other factors:

$$J = D \frac{\partial C}{\partial x} \Rightarrow \frac{\partial N}{\partial t} = A D \frac{\partial C}{\partial x}$$

Where $\partial N/\partial t$ is the number of molecules per unit time, A is the instantaneous drug eluting surface area, D is the diffusivity, and C is the concentration. The drug eluting surface area of a surface coated stent is simply the surface area of the stent itself. Since this area is fixed, this method of controlling release kinetics is not available to surface coated devices. Through openings, however, present several possibilities for varying surface area as a function of time.

In the embodiment of FIG. 14, beneficial agent is provided in the openings **24** in the form of microspheres, particles or the like. Individual layers **70** can then be created that contain these particles. Further, the particle size can be varied from layer to layer. For a given layer volume, smaller particle sizes increase the total particle surface area in that layer, which has the effect of varying the total surface area of the beneficial agent from layer to layer. Since the flux of drug molecules is proportional to surface area, the total drug flux can be adjusted from layer to layer by changing the

14

particle size, and the net effect is control of release kinetics by varying particle sizes within layers.

A second general method for varying drug eluting surface area as a function of time is to change the shape or cross-sectional area of the drug-bearing element along the axis of the opening. FIG. 15A shows an opening **70** having a conical shape cut into the material of the stent itself. The opening **70** may then be filled with beneficial agent **72** in layers as described above or in another manner. In this embodiment, a barrier layer **74** may be provided on the inwardly facing side of the opening **70** to prevent the beneficial agent **72** from passing into the blood stream. In this example, the drug eluting surface area A_t would continuously diminish (from FIG. 15A to FIG. 15B) as the bio-degradable carrier material erodes, yielding the elution pattern of FIG. 15C.

FIG. 16A shows a simple cylindrical through-opening **80** in which a preformed, inverted cone **82** of beneficial agent has been inserted. The rest of the through opening **80** is then back-filled with a biodegradable substance **84** with a much slower rate of degradation or a non-biodegradable substance, and the inwardly facing opening of the through opening is sealed with a barrier layer **86**. This technique yields the opposite behavior to the previous example. The drug-eluting surface area A_t continuously increases with time between FIG. 16A and 16B, yielding the elution pattern of FIG. 16C.

The changing cross section openings **70** of FIG. 15A and the non-biodegradable backfilling techniques of FIG. 16A may be combined with any of the layered agent embodiments of FIGS. 9–14 to achieve desired release profiles. For example, the embodiment of FIG. 15A may use the varying agent concentration layers of FIG. 13 to more accurately tailor a release curve to a desired profile.

The process of preforming the beneficial agent plug **82** to a special shape, inserting in a through opening, and back-filling with a second material can yield more complex release kinetics as well. FIG. 17A shows a through opening **90** in which a spherical beneficial agent plug **92** has been inserted. The resulting biodegradation of the sphere, in which the cross sectional surface area varies as a sinusoidal function of depth, produces a flux density which is roughly a sinusoidal function of time, FIG. 17B. Other results are of course possible with other profiles, but none of these more complex behaviors could be generated in a thin, fixed-area surface coating.

An alternative embodiment of FIGS. 18A–18C use a barrier layer **52'** with an opening **96** to achieve the increasing agent release profile of FIG. 16C. As shown in FIG. 18A, the opening **24** is provided with an inner barrier layer **52** and multiple beneficial agent layers **50** as in the embodiment of FIG. 10. An additional outer barrier layer **52'** is provided with a small hole **96** for delivery of the agent to the vessel wall. As shown in FIGS. 18B and 18C, the beneficial agent containing layers **50** degrade in a hemispherical pattern resulting in increasing surface area for agent delivery over time and thus, an increasing agent release profile.

FIG. 19 illustrates an alternative embodiment in which an opening in the tissue supporting device is loaded with cylindrical layers of beneficial agent. According to one method of forming the device of FIG. 19, the entire device is coated with sequential layers **100**, **102**, **104**, **106** of beneficial agent. The interior surface **54** and exterior surface **56** of the device are then stripped to remove the beneficial agent on these surfaces leaving the cylindrical layers of beneficial agent in the openings. In this embodiment, a central opening remains after the coating layers have been deposited which allows communication between the outer surface **56** and inner surface **54** of the tissue supporting device.

15

In the embodiment of FIG. 19, the cylindrical layers are eroded sequentially. This can be used for pulsatile delivery of different beneficial agents, delivery of different concentrations of beneficial agents, or delivery of the same agent. As shown in FIG. 19, the ends of the cylindrical layers 100, 102, 104, 106 are exposed. This results in a low level of erosion of the underlying layers during erosion of an exposed layer. Alternatively, the ends of the cylindrical layers may be covered by a barrier layer to prevent this low level continuous erosion. Erosion rates of the cylindrical layers may be further controlled by contouring the surfaces of the layers. For example, a ribbed or star-shaped pattern may be provided on the radially inner layers to provide a uniform surface area or uniform erosion rate between the radially inner layers and the radially outer layers. Contouring of the surfaces of layers may also be used in other embodiments to provide an additional variable for controlling the erosion rates.

While the invention has been described in detail with reference to the preferred embodiments thereof, it will be apparent to one skilled in the art that various changes and modifications can be made and equivalents employed, without departing from the present invention.

The invention claimed is:

1. An expandable medical device comprising:
 - a plurality of elongated struts, said plurality of elongated struts joined together to form a substantially cylindrical device which is expandable from a cylinder having a first diameter to a cylinder having a second diameter, said plurality of struts each having a strut width in a circumferential direction and a strut thickness in a radial direction;
 - at least one strut opening in at least one of the plurality of struts, the strut opening extending through the strut with the strut opening having a substantially constant cross section from a radially outermost surface of the strut to a radially innermost end of the strut opening; and
 - at least one beneficial agent provided in the at least one strut opening in a plurality of layers, wherein the beneficial agent is provided into the at least one opening without coating the outermost surface.
2. The expandable medical device according to claim 1, wherein said at least one strut opening comprises a plurality of strut openings.
3. The expandable medical device according to claim 1, wherein said plurality of beneficial agent layers include layers of different chemical compositions.
4. The expandable medical device according to claim 3, wherein said different chemical compositions include a barrier composition and an active beneficial agent composition.
5. The expandable medical device according to claim 4, wherein said barrier composition has an opening formed therein.
6. The expandable medical device according to claim 3, wherein said different chemical compositions include different active beneficial agents.
7. The expandable medical device according to claim 6, wherein said different active beneficial agents include anti-thrombotic agents and anti-proliferative agents.
8. The expandable medical device according to claim 1, wherein said plurality of beneficial agent layers include layers of beneficial agent having the same chemical composition in different concentrations.

16

9. The expandable medical device according to claim 1, wherein said plurality of beneficial agent layers include a baffle layer at a radially innermost location in the at least one opening.

10. The expandable medical device according to claim 1, wherein the plurality of beneficial agent layers include a baffle layer between two active beneficial agent layers.

11. The expandable medical device according to claim 1, wherein said beneficial agent is formulated to be activated by a systemically applied agent.

12. The expandable medical device according to claim 11, wherein said systemically applied agent is ultrasound.

13. The expandable medical device according to claim 11, wherein said systemically applied agent is a chemical agent.

14. The expandable medical device according to claim 1, wherein the beneficial agent is contained in microspheres.

15. The expandable medical device according to claim 14, wherein said plurality of layers include layers with microspheres of different sizes.

16. The expandable medical device according to claim 1, wherein the strut opening has a shape configured to vary the release rate of a beneficial agent over time.

17. The expandable medical device according to claim 1, wherein the beneficial agent is provided in the at least one opening in a biodegradable carrier.

18. The expandable medical device according to claim 1, wherein the beneficial agent is configured to diffuse from a carrier in the opening.

19. The expandable medical device according to claim 1, wherein the beneficial agent layers include a bio-degradable barrier layer configured to terminate a therapy at a predetermined time.

20. The expandable medical device according to claim 1, wherein the beneficial agent is paclitaxel.

21. The expandable medical device according to claim 1, wherein the beneficial agent is rapamycin.

22. The expandable medical device according to claim 1, wherein the plurality of beneficial agent layers are substantially cylindrical.

23. The expandable medical device according to claim 1, further comprising a barrier layer at a first surface of the plurality of struts which substantially prevents an active beneficial agent from being delivered from the at least one strut opening to the first surface of the struts.

24. The expandable medical device according to claim 23, wherein the barrier layer is coated on the device.

25. The expandable medical device according to claim 23, wherein the barrier layer is loaded in the strut openings.

26. The expandable medical device according to claim 1, wherein the beneficial agent is a protein drug.

27. The expandable medical device according to claim 1, wherein the plurality of layers of beneficial agent are arranged on top of one another in the radial direction.

28. The expandable medical device according to claim 1, wherein the beneficial agent is an anti-thrombotic agent.

29. The expandable medical device according to claim 1, wherein the beneficial agent is an anti-inflammatory agent.

30. The expandable medical device according to claim 1, wherein the beneficial agent is an antimetabolic agent.

31. The expandable medical device according to claim 1, wherein the beneficial agent is an anti-platelet agent.

32. An expandable medical device comprising:

a plurality of elongated struts, said plurality of elongated struts joined together to form a substantially cylindrical device which is expandable from a cylinder having a first diameter to a cylinder having a second diameter,

17

said plurality of elongated struts each having a strut width in a circumferential direction and a strut thickness in a radial direction;

at least one opening in at least one of the plurality of struts; and

at least one beneficial agent provided in the at least one opening in a plurality of layers, wherein the beneficial agent is provided into the at least one opening without coating a radially outermost surface of the strut, wherein the at least one opening comprises a plurality of openings containing the beneficial agent and a plurality of openings extending through the struts and remaining open.

33. A method of forming an expandable medical device, the method comprising:

providing an expandable medical device with a plurality of struts, said plurality of struts joined together to form a substantially cylindrical device which is expandable from a cylinder having a first diameter to a cylinder having a second diameter;

forming at least one strut opening in at least one of the plurality of struts, the strut opening extending through the strut with the strut opening having a substantially constant cross section from a radially outermost surface of the strut to a radially innermost end of the strut opening; and

delivering at least one beneficial agent into the at least one strut opening in a plurality of layers without coating the outermost surface.

34. The method according to claim 33, wherein said at least one strut opening comprises a plurality of strut openings.

35. The method according to claim 33, wherein the beneficial agent delivered is paclitaxel.

36. The method according to claim 33, wherein the beneficial agent delivered is rapamycin, or an analogue or derivative thereof.

37. The method according to claim 33, further comprising positioning a barrier layer to substantially prevent an active beneficial agent from being delivered from the strut openings to one side of the medical device while allowing active beneficial agent to be delivered to another side of the medical device.

38. The method according to claim 37, wherein the barrier layer is coated on the device.

39. The method according to claim 37, wherein the barrier layer is loaded in the strut openings.

40. The method according to claim 33, wherein the beneficial agent is a protein drug.

41. An expandable medical device comprising:

a substantially cylindrical, expandable medical device formed of a plurality of struts;

a plurality of openings in the plurality of struts, the openings extending through the struts with the openings having a substantially constant cross section from a radially outermost surface of the strut to a radially innermost surface of the strut;

a beneficial agent provided in the plurality of openings; and

a barrier layer provided in the plurality of openings and configured to substantially prevent delivery of the beneficial agent to a first side of the medical device while allowing delivery of the beneficial agent to a second side of the medical device, wherein the beneficial agent and barrier layer are provided into the at least one opening without coating the outermost surface.

18

42. The expandable medical device according to claim 41, wherein the barrier layer is positioned adjacent an inner surface of the substantially cylindrical medical device.

43. The expandable medical device according to claim 41, wherein the barrier layer is coated on the device.

44. The expandable medical device according to claim 41, wherein the barrier layer is loaded in the openings.

45. The expandable medical device according to claim 41, wherein the expandable medical device is a stent.

46. The expandable medical device according to claim 41, wherein the beneficial agent is paclitaxel.

47. The expandable medical device according to claim 41, wherein the beneficial agent is rapamycin, or an analogue or derivative thereof.

48. The expandable medical device according to claim 41, wherein the beneficial agent is a protein drug.

49. The expandable medical device according to claim 41, wherein the beneficial agent and barrier layers are arranged on top of one another in the radial direction.

50. The expandable medical device according to claim 41, wherein the beneficial agent is an anti-thrombotic agent.

51. The expandable medical device according to claim 41, wherein the beneficial agent is an anti-inflammatory agent.

52. The expandable medical device according to claim 41, wherein the beneficial agent is an antimetabolic agent.

53. The expandable medical device according to claim 41, wherein the beneficial agent is an anti-platelet agent.

54. An expandable medical device comprising:

an expandable cylindrical device having a plurality of struts;

a plurality of through openings in the plurality of struts, each opening having a radial innermost end and a radial outermost end;

a beneficial agent provided in the plurality of through openings in a plurality of degradable beneficial agent layers; and

a barrier layer provided at the radial innermost end of the plurality of through openings, the barrier layer degrading more slowly than the beneficial agent layers, and the barrier layer substantially preventing fluid passage there through, wherein the beneficial agent layers and barrier layer are provided into the last one opening without a radially outermost surface of the strut.

55. The expandable medical device according to claim 54, wherein the barrier layer is loaded in the plurality of through openings.

56. The expandable medical device according to claim 54, wherein the beneficial agent is paclitaxel.

57. The expandable medical device according to claim 54, wherein the beneficial agent is rapamycin.

58. The expandable medical device according to claim 54, wherein the beneficial agent is a protein drug.

59. The expandable medical device according to claim 54, wherein the plurality of degradable beneficial agent layers are arranged on top of one another in the radial direction.

60. The expandable medical device according to claim 54, wherein the beneficial agent is an anti-thrombotic agent.

61. The expandable medical device according to claim 54, wherein the beneficial agent is an anti-inflammatory agent.

62. The expandable medical device according to claim 54, wherein the beneficial agent is an antimetabolic agent.

63. The expandable medical device according to claim 54, wherein the beneficial agent is an anti-platelet agent.