



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C08L 95/00	A1	(11) International Publication Number: WO 94/22957 (43) International Publication Date: 13 October 1994 (13.10.94)
(21) International Application Number: PCT/CA94/00174 (22) International Filing Date: 28 March 1994 (28.03.94) (30) Priority Data: 9306517.5 29 March 1993 (29.03.93) GB (71) Applicant (for all designated States except US): POLYPHALT INC. [CA/CA]; Suite 119, 4 Lansing Square, Willowdale, Ontario M2J 5A2 (CA). (72) Inventors; and (75) Inventors/Applicants (for US only): LIANG, Zhi-zhong [CN/CA]; 22 Macklem Avenue, Toronto, Ontario M6J 3M2 (CA). WOODHAMS, Raymond, T. [CA/CA]; 33 The Palisades, Toronto, Ontario M6S 2W9 (CA). SMITH, James, W. [CA/CA]; 33 Airdrie Road, Toronto, Ontario M4G 1L8 (CA). (74) Agent: STEWART, Michael, I.; Sim & McBurney, Suite 701, 330 University Avenue, Toronto, Ontario M5G 1R7 (CA).		(81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, GE, HU, JP, KG, KP, KR, KZ, LK, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: STABILIZED BITUMEN COMPOSITIONS (57) Abstract <p>Two or more different polymeric materials are stably incorporated into bitumen by effecting steric stabilization of a polyolefin, such as polyethylene, and by dispersing the other polymer, such as a styrene-butadiene-styrene copolymer, an ethylene-vinyl acetate copolymer or an EPDM copolymer in the stabilized polyethylene-bitumen composition. The ability to incorporate different polymeric materials in bitumen permits desirable modifications to the properties of the composition to be effected. In addition, different properties can be attained by modifying processing parameters.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

TITLE OF INVENTIONSTABILIZED BITUMEN COMPOSITIONS

The present invention relates to the provision of
5 stable dispersions of polymeric materials in bitumen for
a variety of applications and methods of producing the
same.

BACKGROUND TO THE INVENTION

The combination of two or more polymer types into
10 bitumen is considered desirable from the standpoint of
obtaining improvements in properties that may not be
possible with a single modifier. By providing a blend of
the two or more types of polymers, it is conceivable that
improvement in properties can be achieved over a greater
15 range of expected pavement service conditions.

While this goal is highly desirable, heretofore it
has been difficult to achieve this result because of the
inherent incompatibility of bitumen and the polymeric
materials to be incorporated therein. In addition,
20 different polymers, which, when used independently, are
compatible with the bitumen, in combination, interfere
with the compatibility of each other and/or the final
system.

Various procedures have been attempted to improve
25 the compatibility of bitumen and polymers, for example,
by the use of low molecular weight copolymers, process
oils, and by the use of specific processing conditions to
promote chemical reactions, such as cross-linking.

In International patent application no. WO 93/07219
30 (corresponding to U.S. Serial No. 863,734 filed April 6,
1992), assigned to The University of Toronto Innovations
Foundation and the disclosure of which is incorporated
herein by reference, there is described the stabilization
of dispersed polyethylene and other olefin polymers in
35 bitumen for imparting improved properties to such
asphalt. The polyethylene is maintained in a dispersed
state by using a steric stabilizer which is anchored to
the dispersed particles and which is compatible with the
liquid medium. Such an arrangement maintains the

dispersed polyethylene particles spaced from each other in the bitumen, and inhibits separation of the particulate phase from the liquid phase by the progressive coalescence of dispersed particles.

5 In particular, a stable dispersion of polyolefin particles in bitumen may be formed by employing a functionalized diene rubber which is covalently bonded to a functionalized polyethylene, with or without liquid polybutadiene. Cross-linking of the unsaturated
10 structure in the functionalized butadiene molecular chain to the bitumen forms an extended polybutadiene-based network with a partially cross-linked structure anchored to each of the polymer particles by compatibility of the functionalized polyethylene with the polymer particles
15 and swollen by the bitumen phase, to provide a gel envelope about the polymer particles, which prevents coalescence of the polymer particles.

SUMMARY OF INVENTION

It has now been surprisingly found that a wide range
20 of copolymers may be incorporated into the bitumen composition containing stabilized polyethylene or other polyolefin described in WO 93/07219 and such copolymer resists separation from the bitumen. The present invention, therefore, permits two or more different
25 polymeric materials to be incorporated into bitumen and to remain stably dispersed therein.

Accordingly, in one aspect of the present invention, there is provided a bitumen composition, comprising bitumen, at least one polyolefin sterically stabilized in
30 the bitumen, and at least one additional polymeric material stably incorporated into the composition.

These stable novel bituminous compositions permit improved performance and a versatility of formulation design which has not previously been possible, while also
35 providing for compositions from which the polymer components do not separate.

In addition, it has been found that a wide variety of properties may be achieved, independent of the formulation utilized, depending on the sequence of addition of the polyolefin, copolymer and stabilizer to the bitumen and variations in other processing parameters, such as mixing time, temperature and rate of shear.

GENERAL DESCRIPTION OF INVENTION

The term "bitumen" used herein has its conventional technical meaning and means a class of black or dark-colored (solid, semi-solid or viscous) cementitious substances, natural or manufactured, composed principally of high molecule weight hydrocarbons of which asphalts, tars, pitches and asphaltites are typical. The term "asphalt" as used herein has its conventional technical meaning and means a dark, brown to black, cementitious material, solid or semi-solid in consistency, in which the predominant constituents are bitumen that occur in nature, as such, or are obtained as residue in petroleum refining. The bituminous material employed herein may arise from a variety of sources, including straight and vacuum residue, mixtures of vacuum tower wash oil, paraffin distillate and aromatic and naphthenic oils. Other asphaltic materials, such as rock asphalt, naturally-occurring asphalt and coal tar pitch, also may be used.

As described above, the present invention enables two or more different forms of polymeric materials to be stably incorporated into bitumen in order to expand the useful temperature range of the bitumen composition. One polymer component of the composition comprises a polyolefin, which is preferably polyethylene, but may comprise other olefin homopolymers and copolymers of ethylene and other olefin monomers. Such polyolefin or mixture of two or more polyolefins, is stably incorporated into the bitumen in the form of a particulate phase dispersed in the bitumen by the

mechanism of steric stabilization, as fully described in WO 93/07219, referred to above. As described therein, a bifunctional or biocompatible molecule is employed which has one component bonded to the polyolefin and another
5 component soluble in the bitumen.

As described in WO 93/07219, the polyolefin component of the composition preferably comprises polyethylene. Such polyethylene may comprise low density, linear low density or high density polyethylenes
10 and may comprise polyethylene blends, such as are obtained in pelletized, flaked or powdered recycled material. In general, dispersion of the polyolefin component is effected with the bitumen above the melting point of the polyolefin, generally from about 100° to
15 about 250°C, preferably about 130° to about 200°C, for a time sufficient to form a stable composition, which may be about 0.1 to about 3.5 hours, usually about 0.25 to about 1 hour.

One or more additional polymers are incorporated
20 into such composition. Such polymers are generally copolymers and may contain residual unsaturation. Such copolymers are often incompatible with bitumen and hence normally separate or coalesce rapidly when stirring of the composition is stopped. However, in accordance with
25 the invention, when such copolymers are incorporated into the stabilized polyolefin compositions, they become stabilized and resist separation from the bitumen. Some copolymers which can be employed herein are already somewhat compatible with bitumen or can be rendered so by
30 suitable processing. The presence of the dispersed polyethylene phase in bituminous compositions comprising such materials at worst does not destabilize such materials and frequently may improve such stability.

The manner in which the copolymers become stabilized
35 in the composition depends on the nature of the polymer employed, and may include entanglement, physical

entrapment, chemical cross-linking or combinations of two or more of such mechanisms.

Copolymers which may be incorporated into the bituminous compositions according to the invention

5 include:

- styrenic copolymers, such as styrene-butadiene rubber (SBR), styrene-butadiene-styrene block copolymers (SBS), styrene-ethylene-butadiene-styrene block copolymers (SEBS) and styrene-isoprene-styrene
10 block copolymers (SIS);
- olefinic copolymers, such as polypropylene copolymers, ethylene-vinyl acetate copolymers (EVA), ethylene methylacrylate copolymers (EMA) and ethylene propylene diene copolymers (EPDM).
- 15 - other polymers, such as nitrile-butadiene rubber (NBR), polyvinylchloride (PVC), polyisobutene, and polybutadiene (PB).

Mixtures of two or more of such polymers may be incorporated into the bituminous compositions along with
20 the polyolefin. The compositions of the invention may but do not necessarily employ components, such as process oils, which render the polymers more compatible with the bitumen.

In general, the choice of the polymer to be
25 incorporated into the bitumen is influenced by the following parameters, as well as possibly others:

- the asphalt chemical composition
- the molecular weight of the asphalt
- the molecular weight of the polymer(s)
- 30 - the shear force applied during mixing of the components
- the ratio of constituents of the copolymer, such as the mole ratio of E:VA in EVA

The polymeric materials may be present in the bitumen
35 composition in the form of particle dispersions, strand-like dispersions, solutions and combinations in which the (co)polymer(s) is stabilized against separation.

In general, at low polymer loadings, the bitumen comprises a continuous phase in which the polymer is dispersed. However, at higher polymer loadings, a phase inversion may occur, whereby the polymer becomes the continuous phase.

One effect which has been observed in connection with the compositions of the invention is that, by employing such copolymers in conjunction with the stabilization system described in WO 93/07219, a decreased amount of copolymer material is required to achieve comparable modification to the properties of the bitumen. For example, about 2.5 wt.% of SBS is sufficient to provide the same elastic recovery as bitumen not having the stabilization system hereof to which about 4 wt.% SBS is added, thereby achieving a considerable cost saving with respect to the copolymeric component.

In addition, as can be seen from the specific Examples below, it has been found that the viscosity and other properties of the modified bitumen can be varied for the same or essentially the same quantities of the same components, depending on the order of mixing of the components in formation of the bitumen composition. The compositions of the present invention may be utilized in a wide variety of applications as a result of the diversity of properties achieved by employing different compositional components and mode of formation.

The various alternative procedures of order of mixing and composition of components may be employed with other copolymer components as well as when such copolymer components are omitted and/or when polyethylene is omitted, for example, where two or more copolymers are stabilized.

Rather than form a concentrate in bitumen as described above, a concentrate may be formed in oil or other medium and the concentrate in this form may be

introduced to the bitumen, along with the polymer and/or copolymer components.

Within the context of this invention, the manner by which the final dispersion is achieved varies according to the nature of the copolymers and/or homopolymers and the process conditions employed. Depending on the application to which the bitumen composition of the invention is to be put, the quantities of polyolefin and of copolymer incorporated into the bitumen may be varied widely. Preferably, the amount of polyethylene, when present in the composition, may vary from about 0.5 to about 20 wt.% while that for the copolymer, when present in the composition, may vary from about 0.5 to about 20 wt.%. For example, with SBR and SBS copolymers, added to impart elasticity, the amount of copolymer employed may range from about 1 to about 15 wt.%.

In addition to these components, there may also be incorporated into the bituminous composition or dispersed phase comprising dissociated rubber vulcanate network, particularly prepared from scrap crumb rubber, such as automobile tyre crumb rubber, as fully described in International application PCT/CA93/00562 filed December 29, 1993, in the joint names of ourselves and University of Toronto Innovations Foundation, the disclosure of which is incorporated herein by reference.

The stabilized bitumen compositions of the present invention also may be incorporated into other systems. For example, the stabilized bitumen compositions may be incorporated into the manufacture of rubber and plastic compounded compositions, such as in an amount of about 5 to about 50 wt.%. Alternatively, the stabilized bitumen compositions may be provided in the form of emulsions, with the continuous phase being aqueous or organic. Masterbatch compositions comprising bitumen and stabilized polymers may be compounded with fillers and/or polymers and the compounded composition may be pelletized to produce a pelletized composition for subsequent

incorporation into compositions for a variety of industrial uses. The compositions described herein may be utilized in a variety of asphalt applications, including all types of paving, preformed paving bricks, roofing membranes, shingles, waterproofing membranes, sealants, caulks, potting resins and protective finishes.

In one embodiment of the invention for dispersion of the polyethylene, maleinized polyethylene, liquid polybutadiene (as required), amino-terminated poly(butadiene-co-acrylonitrile) or amino-terminated polybutadiene and elemental sulfur may be dispersed in bitumen. For a conventional hot mix asphalt paving application, a preferred ratio of maleinized polyethylene to bitumen is from about 0.05 to about 10 percent by weight, more preferably, from about 0.5 to about 2 percent by weight, and a preferred ratio of amino-functionalized butadiene based copolymer is from about 0.01 wt.% to about 3 wt.%, more preferably about 0.05 to about 2 wt.%. The amount of liquid butadiene may be preferably in the range of about 0.02 to about 15 wt.%, more preferably from about 0.1 to about 6 wt.%, of bitumen. The amount of sulfur is preferably between about 0.05 percent and about 10 percent of the total mixture, by weight, preferably about 0.1 to about 5 wt.%. For other application, for example, roofing, the relative proportions and total amounts of components may vary.

Paving materials generally include aggregate, such as crushed stone pebbles, sand etc, along with the bitumen composition. Similarly, other additives to the bitumen composition may be employed, dependent on the end use to which the bituminous composition is put. For example, a roofing material may be obtained by the addition of suitable fillers, such as asbestos, carbonates, silica, wood fibres, mica, sulfates, clays, pigments and/or fire retardants, such as chlorinated waxes. For crack-filler applications, an oxide may be advantageously added.

EXAMPLES

In the Examples which follow, the stability of the polymer modified binders during hot storage was evaluated based on (i) the results of observation under an optical
5 microscope equipped with temperature controlled hot stage to observe the difference in morphology of samples, and/or (ii) separation testing of conditioned asphalt samples. The conditioning procedure consists of placing approximately 50 grams of polymer-asphalt binder in ¾"
10 copper tubes and storing such tubes in a vertical position at 160°C in an oven for 2 to 3 days. Following hot storage a viscosity ratio was determined by comparing the viscosity of the binder from the top section of the tube with the binder from the bottom section of the tube.
15 Ratios in the range of 0.80 to 1.20 are generally considered indicative of acceptable stability.

Example 1

This Example illustrates the incorporation of copolymeric materials into bitumen compositions.

20 Compositions were prepared by a two-step procedure, in which a concentrate first was formed and then the concentrate was diluted with asphalt and adding, while stirring, polymer to be stabilized. In this Example, the asphalt employed was Lloydminster, Penetration 85/100.

25 The concentrate was prepared by dispersing functionalized polyethylene (Fusabond E-110, MI=40, anhydride content: 0.08g mole/Kg of resin) in asphalt at 170°C for 10 minutes, adding a mixture of amine-terminated poly(butadiene-co-acrylonitrile) copolymer
30 (liquid, acrylonitrile content 10%, amine equiv. at 1200) and polybutadiene (Ricon 134, MW=12,000) while mixing for 15 minutes at 180°C, and adding sulfur while mixing the asphalt for 1.5 hours at 190°C to 200°C. The resulting concentrate then was diluted with the same asphalt to
35 form a homogenous binder to which was added polyethylene (PE) (low density, melt flow index = 5) to be stabilized.

Various polymers then were added to the resulting composition in the following manner:

5 SBS (S:B=30/70, MW=350,000, Mn=140,000): disperse SBS in asphalt composition 190°C for 30 minutes and at 200° to 240°C for a further 30 minutes.

EVA (Cil 1240A, VA=12% by weight, melt flow index=10): disperse EVA in asphalt composition at 180°C for 30 minutes.

10 EPDM (Royalene 552, EP ratio 75/25, Morney viscosity ML 1+4 at 125°C = 50): disperse EPDM in asphalt composition at 200°C for one hour.

EP/PP (recycled diaper waste - PE/PP ratio 60:40 (comingled blend): disperse EP/PP in asphalt composition at 170°C for 1 hour

15 Mixing in all Examples was effected in a Brinkman Polytron homoganizer (Model PT45/80) mixer.

Details of the compositions formed in a series of experiments are set forth in Table I below. In these various experiments, the "c" experiments are control
20 experiments, the "a" experiments are examples of compositions according to the present invention and the "b" experiments are examples of compositions according to WO 93/07219.

The various samples were subjected to testing and
25 the results obtained are set forth in Table II below. As may be seen from these results, the SBS was processed under conditions in which it was relatively stably introduced to the asphalt (Experiment 1(c)) and the presence of the stabilizer alone (Experiment 1(b)) and
30 stabilizer and polyethylene (Experiment 1(a)) did not adversely affect such stability.

In the case of EVA, in the absence of stabilizer, the copolymer readily coalesced and separated from the asphalt (Experiment 2(c)). With stabilizer alone
35 (Experiment 2(b)) and stabilizer and polyethylene (Experiment 2(a)), the EVA was stably incorporated into the composition and did not tend to coalesce or separate from the asphalt, as evidenced by visual observation and as can be seen from the viscosity ratio following

conditioning. For EPDM, similar results were obtained as for EVA. The EPDM was more difficult to disperse in the asphalt than EVA, and hence the conditions employed for dispersion were slightly modified. In the case of the comingled blend of EP/PP (60:40 with about 1.0% TiO₂), the blend was stably incorporated into the bitumen (Experiment 4(a)) while, in the absence of stabilizer, the dispersed polymers (PE and PP) rapidly coalesced when agitation was stopped.

10 Example 2

This Example illustrates the addition of polyethylene and SBS to unmodified asphalt.

In a 1 liter mixing vessel, 92 parts of asphalt (Caltex Class 170, penetration at 25°C = 85 dmm, Viscosity at 135°C = 0.32 pa.s., Ring and Ball Softening point = 45°C) were heated to 180°C. Then, 5 parts of polyethylene (PE, low density, melt flow index = 5) and 3 parts of styrene-butadiene-styrene (SBS S:B - 30/70, Mw = 350,000, Mn = 140,000) were added respectively and dispersed into the hot liquid asphalt for 60 minutes. After mixing was stopped, the PE dispersed droplets and SBS dispersed phase rapidly coalesced respectively in the hot liquid asphalt. Both PE and SBS migrated towards the surface of the liquid asphalt during 24 hr hot storage at 180°C to form a viscous polymer layer. This lack of stability against gross phase separation is typical of polyolefin and styrenic copolymer dispersions in hot liquid asphalt. Polyethylene and SBS tend to coalesce without any synergistic assistance to each other to prevent such phase separation.

30 Example 3

This Example comprises Examples A-1, A-2 and A-3, B-1 and B-2 (Table III), and illustrates the results obtained when SBS is incorporated into asphalt under different processing conditions. As may be seen from the results below, at equivalent levels of SBS and PE, vastly differing results can be obtained.

Example A-1

0.5 part of maleinized polyethylene was dispersed in 18.2 parts of asphalt (Caltex Class 170) at about 170°C for 10 min. Following this, 0.7 part of polybutadiene and 0.4 part of an amine terminated poly(butadiene-co-acrylonitrile) copolymer (ATBN) were added and mixed at around 180°C for 25 mins, then, 0.6 part of sulfur was blended in for 15 min. To this stirred mixture, was added 71.7 parts of asphalt for dilution and further mixing for 50 min. Finally, recycled low density polyethylene (RLDPE) and SBS elastomers were added in sequence and mixed under high shear at about 200°C for 35 min (for RLDPE) and for 25 min (for SBS) respectively, forming a bituminous composition wherein polymer components were stabilized against phase separation. The performance was evaluated and shown in Table III.

Example A-2

The procedure of Example A-2 was repeated with a different sequence of addition of the additives to asphalt to form the same final composition with a controlled mixing time of 160 min. Using the same materials as in Example A-1, 0.5 part of maleinized polyethylene, 0.7 part of the polybutadiene and 0.4 part of the amine terminated poly(butadiene-co-acrylonitrile) copolymer were dispersed in 18.2 parts of asphalt for 35 min. 0.2 part of sulfur was added to the mixture and mixed at about 190°C for 40 min. Then, 71.7 parts of asphalt was added for 5 min. dilution. After that, 5 parts of RLDPE with 0.4 part of sulfur was added and dispersed at around 200°C for 60 min. followed by the addition and mixing of 3 parts of SBS for further 20 min to obtain a stabilized bituminous composition. The evaluation result was shown in Table III.

Example A-3

Using the same materials as in Example A-1, after 0.5 part of the maleinized polyethylene, 0.7 part of the polybutadiene and 0.4 part of the amine functionalized

poly(butadiene-co-acrylonitrile) copolymer were dispersed in 18.2 parts of asphalt for 35 min, 74.7 parts of asphalt which had been preblended with 4% of SBS at around 180°C for 30 min. was used to dilute the mixture
5 for 5 min. Then, 0.6 part of sulfur was added and reacted at about 200°C for 70 min and 3 parts of RLDPE was mixed into the mixture for further 20 min to produce a stabilized polymer-bitumen composition. The evaluation on this product is given in Table III.

10 Example B-1

Using the same materials as in Example A-1, asphalt (92.5% by wt) was preblended with the maleinized polyethylene (2.5% by wt), the polybutadiene (3.7% by wt) and amine terminated poly(butadiene-co-acrylonitrile)
15 (1.3% by wt) copolymer at around 180°C for 40 min. The preblend was added, while stirring, to the same amount of asphalt which had been treated with 3% by weight of sulfur. Then, 20.2 parts of the resultant mixture was diluted with 71.8 parts of asphalt for 10 min. Finally,
20 5 parts of RLDPE and 3 parts of SBS were added in order and dispersed at about 185°C for 60 min to produce a stabilized polymer-bitumen composition. The evaluation result is shown in Table III.

Example B-2

25 Using the same materials as in Example B-1, 10.1 parts of the preblend was mixed with the same amount (10.1 parts) of asphalt which had been treated with 4% (by wt) of sulfur, then the mixture was diluted and mixed with 71.8 parts of asphalt for 5 min. Finally, 5 parts
30 of RLDPE followed by 3 parts of SBS was added and dispersed under a high shear for 120 min at about 190°C, to produce a stabilized polymer-bitumen composition.

SUMMARY OF DISCLOSURE

In summary of this disclosure, the present invention
35 provides modified stabilized bituminous compositions in which copolymers and/or homopolymers are stably incorporated to modify the properties of the bitumen

composition. Modifications are possible within the scope of this invention.

TABLE I

designation		SBS			EVA			EPDM			Comingled PE/PP	
Ingredient	phr	1a	1b	1c	2a	2b	2c	3a	3b	3c	4a	4c
SBS		2	2	2	-	-	-	-	-	-		
EVA		-	-	-	2	2	2	-	-	-		
EPDM		-	-	-	-	-	-	2	2	2		
PE/PP		-	-	-	-	-	-	-	-	-	3	3
PE		2	-	-	2	-	-	2	-	-		
AC-Lloyd-minster 85/100		94.4	86.36	98	92.80	94.73	98	92.80	94.73	98.0	94.6	97
FPE		0.48	0.49	-	0.96	0.98	-	0.96	0.98	-	0.7	-
ATBN		0.32	0.33	-	0.64	0.65	-	0.64	0.65	-	0.5	-
LPBD		0.64	0.65	-	1.28	1.31	-	1.28	1.31	-	1.0	-
Sulfur		0.16	0.17	-	0.32	0.33	-	0.32	0.33	-	0.2	-

TABLE II

		SAMPLE BEFORE STORAGE			SAMPLE AFTER STORAGE			
		Penetration (dmm @ 25°C)	Viscosity (cp @ 135°C)	S.P. (R&B °C)	Storage Period (hrs)	Viscosity at top (V _t) (cp @ 135°C)	Viscosity at bottom (V _b) (cp @ 135°C)	Viscosity Ratio (V _t /V _b)
SAMPLES	Copolymer							
control		90	550	45				
1a	SBS	47	3650	63	48	4600	4800	0.96
1b	SBS	43	2750	65	48	2025	2075	0.98
1c	SBS	67	1900	59	48	1550	1550	1.00
2a	EVA	62	3100	58	72	2700	2785	0.97
2b	EVA	65	2400	56	72	1875	1925	0.97
2c	EVA	74	1000	52	72	1550	825	1.88
3a	EPDM	59	4225	59	48	3550	3650	0.97
3b	EPDM	55	2600	52	48	2225	2225	1.00
3c	EPDM	73	950	50	48	1250	750	1.60
4a	PE/PP	70	2025	55	48	1900	1700	1.12
4c	PE/PP	65	1050	54	48	1075	800	1.34

TABLE III

	Example 2				
	Group A			Group B	
Component, phr	A-1	A-2	A-3	B-1	B-2
Asphalt	89.9	89.9	89.9	90.7	90.7
Fusabond E-110	0.5	0.5	0.5	0.3	0.3
LPBD	0.7	0.7	0.7	0.4	0.4
ATEN	0.4	0.4	0.4	0.3	0.3
Sulfur	0.6	0.6	0.6	0.3	0.4
SBS	3.0	3.0	3.0	3.0	3.0
PE	5.0	5.0	5.0	5.0	5.0
Performance					
Penetration dmm at 25°C	40	38	26	23	5
Torsoral Recovery % at 25°C	-	-	-	9	-*
Viscosity Pa.s. at 135°C	9.4	7.5	11.4	3.75	4.4#
Softening Point (R&B) (°C)	74	77	75	67.3	91.5
Elastic Recovery Pa.s. at 60°C	-	-	-	11.3	53.6
Viscosity Pa.s. at 60°C	-	-	-	5,055	181,900

* = too rigid at 25°C to be tested.

= test at 165°C.

CLAIMS

1. A bituminous composition comprising:
bitumen,
at least one polyolefin sterically stabilized in the bitumen, and
at least one additional polymeric material stably incorporated into the bitumen.
2. The composition of claim 1 wherein said polyolefin comprises polyethylene in dispersed particulate form.
3. The composition of claim 2 wherein said polyethylene is sterically stabilized in said bitumen by a steric stabilizer molecule comprising a bitumen-compatible polymer interlinked with a polyolefin.
4. The composition of claim 3 wherein said at least one additional polymeric material comprises a copolymer.
5. The composition of claim 4 wherein said copolymer is elastomeric.
6. The composition of claim 5 wherein said elastomeric copolymer comprises a styrenic copolymer or an olefinic copolymer.
7. The composition of claim 6 wherein said styrenic copolymer is an SBR, SBS, SEBS or SIS copolymer.
8. The composition of claim 6 wherein said olefin copolymer is an EVA, EMA, EPDM or polypropylene copolymer.
9. The composition of claim 3 wherein said polyethylene is present in said composition in an amount of from about 0.5 to about 20 wt.% and said elastomeric copolymer is present in said composition in an amount of from about 0.5 to about 20 wt.%.
10. The composition of claim 9 wherein said elastomeric copolymer is an SBS or SBR copolymer present in an amount of about 1 to about 15 wt.%.
11. The composition of claim 3 wherein said at least one additional polymers material is stably incorporated into the bitumen by entanglement, physical entrapment,

chemical cross-linking or combination of two or more of such mechanisms.

12. A method of forming a composition, which comprises:
dissolving a functionalized diene in a solvent,
dispersing a functionalized polyolefin in said solvent,

reacting said functionalized polyolefin and said functionalized diene so as to bind one end of said olefinic polymer to said diene,

dispersing a polyolefin in a molten form in said solvent, and

dispersing at least one additional polymer in said solvent to provide steric stabilization of said polyolefin and stable incorporation of the at least one additional polymer.

13. The method of claim 12 wherein said solvent is bitumen.

14. The method of claim 12 wherein said solvent is an oil compatible with bitumen and the composition resulting from said method is dispersed in bitumen.

INTERNATIONAL SEARCH REPORT

Inter. Appl. Application No
PCT/CA 94/00174

A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 C08L95/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 162 561 (EXXON RESEARCH AND ENGINEERING) 27 November 1985 see page 5, line 5 - page 11, line 15; claims 1,6,7 ---	1
P,X	WO,A,93 07219 (UNIVERSITY OF TORONTO) 15 April 1993 cited in the application see page 6, line 12 - page 17, line 11; claims; examples ---	1-5
A	EP,A,0 300 284 (FACHINI) 25 January 1989 see claims ---	1
A	EP,A,0 321 189 (POLYSAR) 21 June 1989 see page 3, line 11 - page 4, line 10; claims 1,2 ---	1
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

8 June 1994

Date of mailing of the international search report

17. 06. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Bourgonje, A

INTERNATIONAL SEARCH REPORT

Inter. Appl. No.
PCT/CA 94/00174

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 009 432 (COMPOSANTS INDUSTRIALISES DU BATIMENT) 2 April 1980 see page 4, line 1 - page 5, line 26; claims 1-6 ---	1,5-7
A	FR,A,2 364 961 (ELF UNION) 14 April 1978 see page 1, line 28 - page 5, line 8 -----	1,3

INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter. Appl. No.

PCT/CA 94/00174

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
EP-A-0162561	27-11-85	AU-B-	579147	17-11-88
		AU-A-	4109685	17-10-85
		CA-A-	1274331	18-09-90
		DE-A-	3561887	21-04-88
		JP-A-	60261806	25-12-85
		US-A-	4728683	01-03-88

WO-A-9307219	15-04-93	US-A-	5280064	18-01-94
		AU-A-	2665292	03-05-93
		CN-A-	1072939	09-06-93
		FI-A-	941448	13-04-94

EP-A-0300284	25-01-89	DE-A-	3878329	25-03-93

EP-A-0321189	21-06-89	US-A-	4837252	06-06-89
		CA-A-	1327085	15-02-94
		DE-D-	3888128	07-04-94

EP-A-0009432	02-04-80	FR-A-	2436160	11-04-80
		AT-T-	855	15-04-82
		AU-B-	515129	19-03-81
		AU-A-	5071879	08-05-80
		CA-A-	1098243	24-03-81
		JP-C-	1200234	05-04-84
		JP-A-	55040786	22-03-80
		JP-B-	58033276	19-07-83
		OA-A-	6337	30-06-81
		US-A-	4282127	04-08-81

FR-A-2364961	14-04-78	AT-B-	371139	10-06-83
		BE-A-	858771	16-01-78
		CA-A-	1106997	11-08-81
		CH-A-	624988	31-08-81
		DE-A, C	2741776	23-03-78
		GB-A-	1556946	05-12-79
		JP-C-	1379917	28-05-87
		JP-A-	53037725	07-04-78
		JP-B-	61045664	09-10-86
		NL-A-	7710224	21-03-78
		SE-B-	424736	09-08-82

INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter. nal Application No

PCT/CA 94/00174

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR-A-2364961		SE-A- 7710411 US-A- 4154710	18-03-78 15-05-79
