



(86) Date de dépôt PCT/PCT Filing Date: 2010/03/25
 (87) Date publication PCT/PCT Publication Date: 2010/09/30
 (85) Entrée phase nationale/National Entry: 2011/09/15
 (86) N° demande PCT/PCT Application No.: JP 2010/002111
 (87) N° publication PCT/PCT Publication No.: 2010/109869
 (30) Priorités/Priorities: 2009/03/27 (JP2009-080082);
 2010/02/24 (JP2010-038810)

(51) Cl.Int./Int.Cl. *H01M 4/58* (2010.01),
C01B 25/45 (2006.01), *H01M 4/36* (2006.01)
 (71) Demandeur/Applicant:
 SUMITOMO OSAKA CEMENT CO., LTD., JP
 (72) Inventeurs/Inventors:
 NAKANO, MASATSUGU, JP;
 YAMAZAKI, AKINORI, JP
 (74) Agent: BCF LLP

(54) Titre : PROCEDE DE PRODUCTION DE MATERIAU ACTIF D'ELECTRODE POSITIVE POUR BATTERIE AU LITHIUM-ION, MATERIAU ACTIF D'ELECTRODE POSITIVE POUR BATTERIE AU LITHIUM-ION, ELECTRODE POUR BATTERIE AU LITHIUM-ION, ET BATTERIE AU LITHIUM-ION
 (54) Title: METHOD OF MANUFACTURING POSITIVE ELECTRODE ACTIVE MATERIAL FOR LITHIUM ION BATTERY, POSITIVE ELECTRODE ACTIVE MATERIAL FOR LITHIUM ION BATTERY, ELECTRODE FOR LITHIUM ION BATTERY, AND LITHIUM ION BATTERY

(57) **Abrégé/Abstract:**

Disclosed is a method for producing a positive electrode active material for a lithium ion battery, which is characterized by comprising: a step for preparing a mixture that contains (A) Li_3PO_4 , or an Li source and a phosphoric acid source, (B) at least one source selected from the group consisting of an Fe source, an Mn source, a Co source and an Ni source, water and a water-soluble organic solvent having a boiling point of not less than 150°C, said mixture being adjusted to contain (A) and (B) in such amounts that LiMPO_4 (wherein M represents at least one element selected from the group consisting of Fe, Mn, Co and Ni) is produced from (A) and (B) in the mixture at a concentration not less than 0.5 mol/L but not more than 1.5 mol/L; and a step for producing fine LiMPO_4 particles having an average primary particle diameter of not less than 30 nm but not more than 80 nm by reacting (A) and (B) under high-temperature high-pressure conditions.

ABSTRACT

A method of manufacturing a positive electrode active material for lithium ion batteries, comprising: preparing a mixture containing (A) Li_3PO_4 , or a Li source and a phosphoric acid source, (B) at least one selected from a group of a Fe source, a Mn source, a Co source and a Ni source, water and an aqueous organic solvent having a boiling point of 150 °C or more, wherein the amounts of (A) and (B) in the mixture are adjusted to amounts necessary to manufacture therefrom LiMPO_4 (wherein M represents at least one selected from the group of Fe, Mn, Co and Ni) at a concentration of 0.5 to 1.5 mol/L; and generating the fine particles of LiMPO_4 (wherein M represents at least one selected from the group of Fe, Mn, Co and Ni) having an average primary particle diameter of 30 to 80 nm by reacting the (A) and the (B) at a high temperature and a high pressure.

METHOD OF MANUFACTURING POSITIVE ELECTRODE ACTIVE MATERIAL
FOR LITHIUM ION BATTERY, POSITIVE ELECTRODE ACTIVE MATERIAL FOR
LITHIUM ION BATTERY, ELECTRODE FOR LITHIUM ION BATTERY, AND
LITHIUM ION BATTERY

5

TECHNICAL FIELD

[0001]

The present invention relates to a method of manufacturing a positive electrode active material for lithium ion batteries, a positive electrode active material for lithium ion batteries, an electrode for lithium ion batteries, and a lithium ion battery.

10

The present application claims priorities based on Japanese Patent Application No. 2009-080082, filed in Japanese Patent Office on March 27, 2009, and Japanese Patent Application No. 2010-038810, filed in Japanese Patent Office on February 24, 2010, the contents of which are incorporated by reference herein.

15

BACKGROUND ART

[0002]

In comparison to aqueous electrodes in the related art such as a Ni-Cd electrode or a Ni-H electrode, non-aqueous lithium ion electrodes have a high energy density and can be easily reduced in size, and therefore non-aqueous lithium ion electrodes are widely used for mobile devices such as mobile phones, mobile information terminals, and personal computers. As a positive electrode material for non-aqueous lithium ion batteries, currently, LiCoO_2 has been put into practical use and is commonly used.

20

However, when LiCoO_2 is used as it is as a positive electrode material for non-aqueous lithium ion batteries in the field of large-sized batteries or the like that are mounted on hybrid vehicles, electric vehicles, and uninterruptible power systems which

25

are expected to be developed in the future, a variety of problems may occur as described below.

One of those problems is the difficulties in the resource and cost aspects in stably procuring a large amount of cobalt (Co) since LiCoO_2 includes cobalt (Co), which
5 is a rare metal.

In addition, since LiCoO_2 generates oxygen at a high temperature, safety should be sufficiently considered in preparation for the cases of abnormal heat generation or short-circuiting in a battery, and therefore it is highly risky to apply LiCoO_2 to large-sized batteries without sufficiently considering safety.

10 [0003]

As a result, in recent years, instead of a positive electrode active material using LiCoO_2 , positive electrode materials which are cheap and safe, and have a phosphate backbone have been suggested. Among them, LiFePO_4 having an olivine structure is gaining attention as a positive electrode material which is safe and also has no problem in
15 the resource and cost aspects, and is being studied and developed across the world (For example, see Patent document 1, Non-Patent document 1, or the like).

Olivine-type positive electrode materials represented by LiFePO_4 contain iron (Fe). In comparison to cobalt and manganese, iron is a rich natural resource and thus is cheap. In addition, due to the covalent bonding between phosphorous and oxygen, the
20 olivine structure does not emit oxygen at a high temperature unlike cobalt-based positive electrode active materials such as LiCoO_2 , and is also a material excellent in terms of stability.

[0004]

However, even for LiFePO_4 having the above advantages, problems have been
25 pointed out in the characteristics aspect.

One problem is a low conductivity thereof, but in relation to which a number of attempts to improve the conductivity have been carried out in recent years by, particularly, forming the complex of LiFePO_4 and carbon, coating carbon on the surface of LiFePO_4 , or the like.

5 Another problem is a low degree of diffusion of lithium ions during charging and discharging. For example, in compounds having a layered structure such as LiCoO_2 , or a spinel structure such as LiMnO_2 , lithium ions diffuse in two dimension or three dimension during charging and discharging; however, in compounds having an olivine structure such as LiFePO_4 , lithium diffuses only in one dimension. Furthermore, the
10 electrode reaction during charging and discharging is a two-phase reaction in which LiFePO_4 and FePO_4 are repeatedly converted, and therefore LiFePO_4 is considered to be disadvantageous for high-speed charging and discharging.

[0005]

As methods for solving the above problems, the method which is considered to
15 be most effective is the reduction of the diameters of LiFePO_4 particles. That is, even when lithium ions diffuse in one dimension, if diffusion distance is shortened by the reduction of particle diameters, it is considered that an increase in the speed of charging and discharging can be coped with.

In the past, as a method of synthesizing LiFePO_4 , the solid-phase method was
20 used. In the solid-phase method, since raw materials of LiFePO_4 are mixed in a stoichiometric proportion and then are fired in an inert atmosphere, there are problems in that LiFePO_4 having a desired composition cannot be obtained without the skilled selection of firing conditions, and it is difficult to control particle diameters such that it is difficult to reduce particle diameters. Here, as a method of reducing the particle
25 diameters of LiFePO_4 , studies regarding a liquid-phase synthesis method in which a

hydrothermal reaction is used are underway.

[0006]

The advantage of the hydrothermal reaction is that highly pure products can be obtained at a markedly low temperature in comparison to a solid-phase reaction.

5 However, in the hydrothermal reaction, the control of particle diameters is strongly dependent on factors related to reaction conditions such as a reaction temperature or time. In addition, when the control is performed using the above factors, the performance of a manufacturing apparatus strongly affects the control, which causes difficulties in reproducibility.

10 Therefore, as a method of generating the fine particles of LiFePO_4 by the hydrothermal reaction, a method is suggested in which organic acid or ion such as CH_3COO^- , SO_4^{2-} or Cl^- is also fed to a solvent, or Li is excessively added during the hydrothermal reaction, thereby obtaining the fine particles of single-phase LiFePO_4 (for example, see Patent document 2 and Non-patent document 2). In addition, a method is
15 suggested in which reaction intermediates are mechanically crushed so as to obtain the fine particles of LiFePO_4 having small particle diameters (Patent document 3).

[0007]

However, discharge voltage of LiFePO_4 is low, and thus is considered as an electrode material not suitable for uses in which a high output is required, for example,
20 electric tools and hybrid vehicles. As a result, as positive electrode materials having the olivine structure other than LiFePO_4 , LiMnPO_4 , LiCoPO_4 or the like, which are positive electrode materials that can use the stability of the olivine structure and can be used at a high voltage, are considered as alternatives.

Prior art documents

25 Patent documents

[0008]

Patent document 1: Japanese Patent No. 3484003

Patent document 2: Japanese Unexamined Patent Application, First Publication
No. 2008-66019

5 Patent document 3: Japanese Unexamined Patent Application Publication
(Translation of PCT Application) No.-2007-511458

Non Patent document

[0009]

10 Non-Patent document 1: "Phospho-olivine as Positive-Electrode Material for
Rechargeable Lithium Batteries," by A. K. Padhi et al., P 1188, Issue 4, Vol. 144, J.
Electrochem. Soc. (1997)

15 Non-Patent document 2: "Synthesis of LiFePO_4 cathode active material for
Rechargeable Lithium Batteries by Hydrothermal Reaction," by Keisuke Shiraishi,
Young Ho Rho and Kiyoshi Kanamura, P. S58 to S62, Issue 1305, Suppl. 112, J. Ceram.
Soc. Jpn (2004).

DISCLOSURE OF INVENTION

Problem to be solved by the Invention

[0010]

20 In the method in which the fine particles of LiFePO_4 are generated by a
hydrothermal reaction in the related art as described above, the fine particles of LiFePO_4
are reliably obtained, and desired load characteristics are also improved, but there are
problems in that the initial discharge capacity is degraded, and, furthermore, high-speed
charging and discharging characteristics are degraded.

25 Those phenomena are considered to result from the wide particle size

distribution of the fine particles of LiFePO_4 generated. Due to the wide particle size distribution, the possibility of the presence of amorphous ultrafine particles, which do not contribute to charging and discharging, is increased such that the initial discharge capacity is degraded, and, furthermore, high-speed charging and discharging characteristics are degraded.

In addition, in positive electrode materials in which LiMnPO_4 , LiCoPO_4 or the like is used, certainly, the discharge voltage is high, and a high output is obtained, but there is a problem in that the conductivity is lower than that of LiFePO_4 . Therefore, it is necessary to further reduce the resistivity and particle diameters of the positive electrode materials, but such characteristics have not yet been sufficiently fulfilled.

[0011]

The present invention has been made in consideration of the above circumstances, and the object of the present invention is to provide a method of manufacturing a positive electrode active material for lithium ion batteries; a positive electrode active material for lithium ion batteries; an electrode for lithium ion batteries; and a lithium ion battery; wherein the average primary particle diameter of fine particles of LiMPO_4 (wherein M represents one or two or more kinds selected from the group of Fe, Mn, Co and Ni) is controlled so that fine particles of LiMPO_4 having a narrow particle size distribution can be obtained, the initial discharge capacity can be improved, and furthermore, high-speed charging and discharging characteristics can be improved.

[0012]

As a result of thorough studies for solving the above problems, the present inventors paid attention to a solvothermal method which has been gaining attention in recent years as a method of synthesizing nano particles, and combined this method into the hydrothermal synthesis reaction of LiMPO_4 (wherein M represents one or two or

more kinds selected from the group of Fe, Mn, Co and Ni) when the fine particles of LiMPO_4 are generated using the hydrothermal reaction. Then, the inventors found an unexpected excellent result in which, by substituting a part of water, which is used as a solvent, with an aqueous organic solvent during the hydrothermal reaction, the particle diameters and crystallinity of the fine particles of the obtained LiMPO_4 can be controlled according to the types or substituted amount of the aqueous organic solvent, and, furthermore, the battery characteristics can be controlled, and completed the present invention.

Means for solving the problem

10 [0013]

The method of manufacturing a positive electrode active material for lithium ion batteries according to the present invention, is characterized in that the method includes: reacting a mixture at a high temperature and a high pressure, wherein the mixture contains Li_3PO_4 or a Li source and a phosphoric acid source, and one or two or more kinds selected from a group of a Fe source, a Mn source, a Co source and a Ni source, in amounts necessary to generate from 0.5 to 1.5 mol/L of LiMPO_4 (wherein M represents one or two or more kinds selected from the group of Fe, Mn, Co and Ni), and also contains water and an aqueous organic solvent having a boiling point of 150 °C or more, to generate fine particles of LiMPO_4 (wherein M represents one or two or more kinds selected from the group of Fe, Mn, Co and Ni) having an average primary particle diameter of from 30 to 80 nm.

In more detail, the method of manufacturing a positive electrode active material for lithium ion batteries is characterized in that the method includes:

preparing a mixture containing (A) Li_3PO_4 , or a Li source and a phosphoric acid source; (B) at least one selected from a group of a Fe source, a Mn source, a Co source

and a Ni source; water; and an aqueous organic solvent having a boiling point of 150 °C or more; wherein the amounts of (A) and (B) in the mixture are adjusted to amounts necessary to manufacture therefrom LiMPO_4 (wherein M represents at least one selected from the group of Fe, Mn, Co and Ni) at a concentration of more than or equal to 0.5 mol/L and less than or equal to 1.5 mol/L; and

generating fine particles of LiMPO_4 (wherein M represents one or two or more kinds selected from the group of Fe, Mn, Co and Ni) having an average primary particle diameter of from 30 to 80 nm by reacting the (A) and the (B) at a high temperature and a high pressure.

10 [0014]

The aqueous organic solvent is preferably at least one selected from multivalent alcohols, amides, esters and ethers.

The content of the aqueous organic solvent is preferably from 3 to 30% by mass of the total mass of the mixture.

15 [0015]

The positive electrode active material for lithium ion batteries according to the present invention is characterized in that the material is obtained by the method of manufacturing a positive electrode active material for lithium ion batteries according to the present invention.

20 [0016]

The electrode for lithium ion batteries according to the invention is characterized in that the electrode is formed by coating carbon on the positive electrode active material for lithium ion batteries according to the present invention.

[0017]

25 The lithium ion battery according to the present invention is characterized in that

the battery comprises the electrode for lithium ion batteries according to the present invention as a positive electrode.

Effects of Invention

[0018]

5 According to the method of manufacturing a positive electrode active material for lithium ion batteries of the present invention, a mixture containing Li_3PO_4 , or a Li source and a phosphoric acid source, and one or two or more kinds selected from a group of a Fe source, a Mn source, a Co source and a Ni source, in amounts necessary to generate from 0.5 to 1.5 mol/L of LiMPO_4 (wherein M represents one or two or more
10 kinds selected from the group of Fe, Mn, Co and Ni), and also containing water and an aqueous organic solvent having a boiling point of 150 °C or more is reacted at a high temperature and a high pressure. Therefore, the fine particles of LiMPO_4 (wherein M represents one or two or more kinds selected from the group of Fe, Mn, Co and Ni) having an average primary particle diameter of from 30 to 80 nm are generated, and it is
15 possible to efficiently generate the fine particles of LiMPO_4 (wherein M represents one or two or more kinds selected from the group of Fe, Mn, Co and Ni) having a small average primary particle diameter and a narrow particle size distribution. Furthermore, the average primary particle diameter of the fine particles of the LiMPO_4 can be controlled by changing the types and content of the aqueous organic solvent.

20 [0019]

 According to the positive electrode active material for lithium ion batteries of the present invention, since the fine particles of LiMPO_4 (wherein M represents one or two or more kinds selected from the group of Fe, Mn, Co and Ni) have an average primary particle diameter in a range of 30 to 80 nm and a small particle size distribution,
25 it is possible to improve the initial discharge capacity and, furthermore, to improve

high-speed charging and discharging characteristics.

[0020]

According to the electrode for lithium ion batteries of the present invention, since the positive electrode active material for lithium ion batteries of the present invention is coated with carbon, it is possible to improve the conductivity of the positive electrode active material.

[0021]

According to the lithium ion battery of the present invention, since the electrode for lithium ion batteries of the present invention is provided as the positive electrode, it is possible to improve the conductivity of the positive electrode. Accordingly, it is possible to improve initial discharge capacity, and also improve high-speed charging and discharging characteristics.

BRIEF DESCRIPTION OF THE DRAWINGS

15

[0022]

FIG. 1 is a field emission scanning electron microscope (FE-SEM) image showing a positive electrode active material of Example 2 of the present invention.

FIG. 2 is a field emission scanning electron microscope (FE-SEM) image showing a positive electrode active material of Comparative Example 1.

BEST MODE FOR CARRYING OUT THE INVENTION [0023]

The present invention relates to a method of manufacturing a positive electrode active material for lithium ion batteries, a positive electrode active material for lithium ion batteries, an electrode for lithium ion batteries and a lithium ion battery. In more detail, the present invention relates to a method of manufacturing a positive electrode

25

active material for lithium ion batteries in which the discharge capacity can be improved by controlling the average primary particle diameter of the fine particles of LiFePO_4 , a positive electrode active material for lithium ion batteries obtained by the above method, an electrode for lithium ion batteries and a lithium ion battery, wherein the electrode and
5 the battery uses said positive electrode active material for lithium ion batteries.

[0024]

Embodiments for carrying out the method of manufacturing a positive electrode active material for lithium ion batteries, the positive electrode active material for lithium ion batteries, the electrode for lithium ion batteries, and the lithium ion battery according
10 to the present invention will be described.

The embodiments are detailed description for better understanding of the gist of the present invention, and, unless specified otherwise, the present invention is not limited thereto. For example, unless particularly limited, conditions or the like such as materials, amounts, types, number, sizes, or temperature, may be varied, added, and
15 omitted according to necessity.

[0025]

“Method of manufacturing a positive electrode active material for lithium ion batteries”

The method of manufacturing a positive electrode active material for lithium ion
20 batteries according to the embodiment is a method in which a mixture which contains Li_3PO_4 , or a Li source and a phosphoric acid source, and one or two or more kinds selected from a group of a Fe source, a Mn source, a Co source, and a Ni source, in amounts necessary to generate from 0.5 to 1.5 mol/L of LiMPO_4 (wherein M represents one or two or more kinds selected from a group of Fe, Mn, Co and Ni), and also contains
25 water and an aqueous organic solvent having a boiling point of 150 °C or more, is reacted

at a high temperature and a high pressure so that the fine particles of LiMPO_4 (wherein M represents one or two or more kinds selected from the group of Fe, Mn, Co and Ni) having an average primary particle diameter of 30 nm or more and 80 nm or less are generated.

5 Hereinafter, the fine particles of LiMPO_4 (wherein M represents one or two or more kinds selected from the group of Fe, Mn, Co and Ni) will be referred to simply as “the fine particles of LiMPO_4 .”

[0026]

When the fine particles of LiMPO_4 are synthesized by a hydrothermal reaction,
10 there are methods in which a Li source such as Li salt, a phosphoric acid source such as PO_4 salt, and an M source such as M salt (wherein M represents one or two or more kinds selected from a group of Fe, Mn, Co and Ni) are used as synthesis raw materials; in which Li_3PO_4 that has been obtained by reacting a Li source and a phosphoric acid source is used, and, furthermore, an M source is used; and in which a phosphate of M
15 that has been obtained by reacting an M source and a phosphoric acid source is used, and, furthermore, a Li source is used.

However, among the phosphates of M, $\text{Fe}_3(\text{PO}_4)_2$ is liable to be oxidized, and thus is difficult to be handled. In the present invention, it is preferable to use Li_3PO_4 and Fe(II) salt as raw materials.

20 In the method in which a Li source, an M source and a phosphoric acid source are used, since Li_3PO_4 is generated in the initial phase of the reaction, the method becomes equivalent to the method in which Li_3PO_4 is used. Therefore, a method is preferable in which, in the beginning, Li_3PO_4 is synthesized, and then the Li_3PO_4 and an M source are hydrothermally reacted so as to synthesize the fine particles of LiMPO_4
25 (wherein M represents one or two or more kinds selected from a group of Fe, Mn, Co and

Ni).

[0027]

Next, a preferable method of manufacturing the fine particles of the LiMPO_4 will be described in detail.

5 1. Manufacture of a lithium phosphate (Li_3PO_4) slurry

Firstly, a Li source and a phosphoric acid source are fed into water, and the Li source and the phosphoric acid source are reacted to generate lithium phosphate (Li_3PO_4), so that a lithium phosphate (Li_3PO_4) slurry is generated. The Li source and the phosphoric acid source are selected according to necessity, but it is preferable to adjust
10 the amounts or ratios thereof so that no unreacted Li source or phosphoric acid source remain.

[0028]

The Li source refers to a substance that contains at least a lithium element and can supply lithium ion in order to manufacture a target compound. As the Li source,
15 hydroxides of Li or salts of Li are preferable, and examples of the hydroxides of Li include lithium hydroxide (LiOH). In addition, examples of the salts of Li include lithium inorganic acid salts such as lithium carbonate (Li_2CO_3) and lithium chloride (LiCl), lithium organic acid salts such as lithium acetate (LiCH_3COO) and lithium oxalate ($(\text{COOLi})_2$), and hydrates thereof, and one or two or more kinds selected from the
20 above groups are preferably used.

[0029]

The phosphoric acid source refers to a substance that contains at least phosphoric acid and can supply phosphoric acid ion in order to manufacture a target compound. As the phosphoric acid source, one or two or more kinds selected from a
25 group of phosphoric acid such as orthophosphoric acid (H_3PO_4) and metaphosphoric acid

(HPO₃), ammonium dihydrogenphosphate (NH₄H₂PO₄), diammonium hydrogen phosphate ((NH₄)₂HPO₄), ammonium phosphate ((NH₄)₃PO₄) and hydrates thereof are preferably used. Among them, orthophosphoric acid, ammonium dihydrogenphosphate and diammonium hydrogen phosphate are preferable since they have a relatively high
5 purity and their compositions are easily controlled.

A slurry may be manufactured by directly adding Li₃PO₄ to water.

[0030]

2. Manufacture of a mixture of lithium phosphate (Li₃PO₄) and a M source

A M source and a reducing agent are added to the lithium phosphate (Li₃PO₄)
10 slurry obtained in the above manner to produce a mixture. The M source is selected according to necessity, but it is preferable to adjust the amount and ratio thereof so that no unreacted M source remains.

The M source refers to a substance that contains at least M and can supply M ion in order to manufacture a target compound. Herein, M represents Fe, Mn, Co and/or Ni.
15 As the M source, salts of M are preferable, and, for example, one or two or more kinds selected from a group of ferrous chloride (FeCl₂), ferrous sulfate (FeSO₄), ferrous acetate (II) (Fe(CH₃COO)₂), manganese (II) chloride (MnCl₂), manganese (II) sulfate (MnSO₄), manganese (II) acetate (Mn(CH₃COO)₂), manganese (II) nitrate (Mn(NO₃)₂), cobalt (II) chloride (CoCl₂), cobalt (II) sulfate (CoSO₄), cobalt (II) acetate (Co(CH₃COO)₂), nickel
20 (II) chloride (NiCl₂), nickel (II) sulfate (NiSO₄), nickel (II) acetate (Ni(CH₃COO)₂) and hydrates thereof are preferably used.

[0031]

A reaction concentration, that is, the concentration of Li₃PO₄ and the M source in the mixture is preferably 0.5 mol/L or more and 1.5 mol/L or less, and more preferably
25 0.7 mol/L or more and 1.2 mol/L or less, wherein they are contained in an amount

converted to generate LiMPO_4 . The concentration may be controlled to be in a preferable range by newly adding water to the mixture before the reaction starts at a high temperature and a high pressure.

The reason is that, when the reaction concentration is less than 0.5 mol/L, LiMPO_4 having large particle diameters is liable to be generated, and it is highly likely that load characteristics may be degraded due to the reasons as described above. On the other hand, when the reaction concentration exceeds 1.5 mol/L, there is a possibility that the mixture may not be sufficiently stirred, and thus the reaction may not proceed sufficiently such that unreacted substances remain, making it difficult to obtain single-phase LiMPO_4 , whereby the mixture cannot be used as an electrode material.

In the present invention, the concentration of materials wherein they are contained in an amount converted to generate LiMPO_4 means a concentration of materials which are used to manufacture LiMPO_4 . Raw materials are selected so that the concentration of the finally manufactured LiMPO_4 falls in a range of 0.5 to 1.5 mol/L. Here, the concentration of any of the raw materials may be outside the range of 0.5 to 1.5 mol/L. For example, the concentration of Li_3PO_4 or the M source in the mixture, which will be subjected to a reaction at a high temperature and a high pressure, is preferably from 0.5 to 1.5 mol/L, and more preferably 0.7 to 1.2 mol/L. On the other hand, when lithium chloride is used as the Li source and phosphoric acid is used as the phosphoric acid source to prepare Li_3PO_4 , the concentration of the used lithium chloride may be outside the above range, for example, may be 3 mol/L or the like. However, it is preferable to select the mixing ratio of materials so that no unreacted materials remain.

[0032]

As a solvent used for the mixture, a mixed solvent of water and an aqueous organic solvent having a boiling point of 150 °C or more is used. The upper limit of the

boiling point of an aqueous organic solvent that can be used for the present invention is not limited; however, as a rough standard, generally 300 °C or lower is preferable.

As the aqueous organic solvent, one or a mixture of two or more kinds selected from a group of multivalent alcohols such as ethylene glycol, propylene glycol, hexylene glycol or glycerine, amides such as formamide, N-methylformamide, 2-pyrrolidine or
5 N-methyl-2-pyrrolidinone, esters such as γ -butyrolactone and ethers such as diethylene glycol, ethylene glycol monobutyl ether (butyl cellosolve), can be used.

Among them, multivalent alcohols are preferable, and ethylene glycol is particularly preferable.

10 [0033]

The mixed solvent can be obtained by substituting a part of water with an aqueous organic solvent, before the reaction starts at a high temperature and a high pressure. It is preferable that an aqueous organic solvent is substituted such that the content of the aqueous organic solvent with respect to the total mass supplied to the
15 hydrothermal reaction, that is, with respect to the total mass of the mixture, is from 3 to 30% by mass, more preferably 5 to 15% by mass, and even more preferably 7 to 10% by mass.

When the substitution amount of the aqueous organic solvent, that is, the content of the aqueous organic solvent is less than 3% by mass, the fine particles of LiMPO_4
20 generated and battery characteristics are substantially the same as those when the solvent is only water, and therefore the effect of substitution is not obtained. On the other hand, when the substitution amount exceeds 30% by mass, salts are generated as byproducts and act as impurities, which causes deterioration of battery characteristics.

As such, the amount of the aqueous organic solvent is defined with respect to the
25 total mass supplied to the hydrothermal reaction, that is, the total mass of the mixture.

For example, '5% by mass' means that water in the reaction system which is as much as 5% by mass of the mass supplied to the hydrothermal reaction is substituted with an aqueous organic solvent.

[0034]

5 3. Hydrothermal synthesis of the mixture

The aforementioned mixture is reacted (hydrothermally synthesized) under the condition of a high temperature and a high pressure, and a reaction product including the fine particles of LiMPO_4 is obtained.

10 The condition of a high temperature and a high pressure is not particularly limited as long as the condition is within the scope of temperature, pressure, and time in which the fine particles of LiMPO_4 are generated. The reaction temperature can be arbitrarily selected, and can be higher than 100 °C and 300 °C or less, preferably from 120 to 250 °C and more preferably from 150 to 220 °C.

15 However, the reaction temperature preferably does not exceed the boiling point of the aqueous organic solvent which is used to substitution. The reason is that, when the aqueous organic solvent is exposed to a high temperature condition significantly exceeding the boiling point thereof in a pressurized vessel, the aqueous organic solvent is decomposed so as to abruptly increase the pressure in the reaction vessel, which may lead to a problem in terms of safety.

20 [0035]

In addition, the pressure during the reaction can be arbitrarily selected, and can be, for example, higher than 0.1 MPa and 10 MPa or less, preferably from 0.2 to 4.0 MPa, and more preferably from 0.4 to 2.5 MPa. The reaction time can be arbitrarily selected, and is preferably 1 to 24 hours, and more preferably 3 to 12 hours, although it is also
25 dependent on the reaction temperature.

[0036]

4. Separation of the fine particles of LiMPO_4

The reaction product including the aforementioned fine particles of LiMPO_4 is separated into the fine particles of LiMPO_4 and a Li-containing liquid waste (a solution including unreacted Li) by an appropriate method such as decantation, centrifugation or filter filtration.

The separated fine particles of LiMPO_4 are dried by an arbitrary method, for example, dried for 3 hours or more at 40 °C or more using a drying equipment, whereby it is possible to efficiently obtain the fine particles of LiMPO_4 having an average primary particle diameter of from 30 to 80 nm. The average primary particle diameter can be obtained by the SEM image evaluation of the fine particles.

[0037]

“Positive electrode active material for lithium ion batteries”

The average primary particle diameter of the fine particles of LiMPO_4 obtained in the above conditions is from 30 to 80 nm. As such, by using the fine particles of LiMPO_4 having a small average primary particle diameter as a positive electrode active material for lithium ion batteries, the diffusion distance of Li becomes short, and the improved high-speed charging and discharging characteristics can be achieved in an electrode for lithium ion batteries and a lithium ion battery provided with the positive electrode active material for lithium ion batteries.

[0038]

Here, when the average primary particle diameter is 30 nm or more, there is no case in which the particles are fractured by structural changes caused by the insertion and detachment of Li, and the specific surface area becomes significantly large such that the surface activity is extremely increased. Therefore, the amount of a joining agent that

combines the fine particles does not need to be large, and, consequently, there is no problematic case in which the packing density of the positive electrode is significantly decreased, or the conductivity is significantly degraded. On the other hand, when the average primary particle diameter is 80 nm or less, the internal resistance of the positive electrode active material does not become large, and the migration of Li ions is also not delayed, whereby problem in which the discharge capacity is decreased or the like does not occur.

[0039]

“Electrode for lithium ion batteries and lithium ion battery”

In order to use the aforementioned positive electrode active material for lithium ion batteries for a lithium ion battery, particularly as a positive electrode active material for the positive electrode in a lithium ion rechargeable battery, the surfaces of the fine particles of LiMPO_4 are preferably coated with carbon.

When the surfaces thereof are coated with carbon, the conductivity, which is the previously described problem of LiFePO_4 , is improved, and favorable results can be obtained which are suitable as battery characteristics.

[0040]

The method of carbon coating can be arbitrarily selected. For example, a method can be used in which the fine particles of LiMPO_4 are mixed with a carbon source such as a water-soluble monosaccharide or polysaccharide, or a water-soluble polymer compound; a film is formed uniformly on the surfaces of the fine particles of LiFePO_4 using a drying method such as the evaporative drying method, the vacuum drying method, the spray drying method and the freeze drying method, and subsequently, is fired under an inert atmosphere and a temperature at which the carbon source is decomposed so as to generate carbon; and a conductive carbon film is formed on the

surfaces of the fine particles of LiMPO_4 .

[0041]

The firing temperature can be arbitrarily selected. The temperature is dependent on the type of the carbon source, but is preferably in a range of 500 to 1000 °C, and more preferably 700 to 800°C.

At a low temperature of lower than 500°C, the decomposition of the carbon source is not sufficient, and the generation of the conductive carbon film becomes insufficient, which causes resistance in the battery, whereby there is a possibility that the battery characteristics may be adversely affected. On the other hand, at a high temperature exceeding 1000°C, the particle growth of the fine particles of LiMPO_4 proceeds such that the fine particles are coarsened, and there is a possibility that high-speed charging and discharging characteristics may be significantly degraded due to the diffusion speed of Li which is a problem of the particles of LiFePO_4 .

As such, by coating the fine particles of LiMPO_4 , which is the positive electrode active material for lithium ion batteries, with carbon, the fine particles of LiMPO_4 become preferable for a lithium ion battery, particularly as a positive electrode active material for the positive electrode in a lithium ion rechargeable battery.

[0042]

By using the electrode formed using the carbon-coated fine particles of LiMPO_4 for a positive electrode, and, furthermore, providing a negative electrode, an electrolyte, and a separator, a lithium ion battery can be obtained.

In the lithium ion battery, the positive electrode is formed using the carbon-coated fine particles of LiMPO_4 obtained by coating the surfaces of the fine particles of LiMPO_4 , which has an average primary particle diameter of 30 nm or more

and 80 nm or less, with a conductive carbon film. Therefore, the initial discharge capacity is improved, and high-speed charging and discharging characteristics are also excellent.

Examples

5 [0043]

Hereinafter, the present invention will be described specifically with reference to examples and comparative examples, but the present invention is not limited to the examples.

[0044]

10 Example 1

3 mol of lithium chloride (LiCl) and 1 mol of phosphoric acid (H_3PO_4) were added to 1 L of pure water and stirred to obtain a lithium phosphate (Li_3PO_4) slurry.

Next, 1 mol of ferrous chloride (FeCl_2) was added to the slurry, a part of water included in the slurry was substituted with ethylene glycol so that the content of the ferrous chloride became 10% by mass with respect to the total mass supplied to the hydrothermal reaction. Furthermore, water was further added to the mixture so as to produce a total amount of 2 L (the total mass supplied to the hydrothermal reaction) of fluid including raw materials. When the reaction concentration of the fluid including raw materials was converted to that of LiFePO_4 , the reaction concentration was 0.5 mol/L in terms of LiFePO_4 .

[0045]

Next, in order to perform the hydrothermal reaction, the fluid was provided in an autoclave, and, after an inert gas was introduced, the fluid was hydrothermally reacted for 6 hours at 180 °C and 1.2 MPa. After that, the fluid was filtered and separated into solid and liquid.

Next, the same amount of water as the mass of the separated solid was added so as to suspend the solid, an operation that separates solid and liquid by filtration was performed three times to wash the solid.

5 5 g of polyethylene glycol and 150 g of pure water were added to 150 g (in terms of solid content) of the obtained cake-like LiFePO_4 , and a crushing and dispersion treatment was performed for 12 hours by a ball mill using zirconia beads having a diameter of 5 mm as media, thereby preparing a uniform slurry.

[0046]

Next, the slurry was sprayed in the atmosphere of 180 °C and thus dried to
10 obtain granular materials having an average particle diameter of about 6 μm . The granular materials were fired for 1 hour under an inert atmosphere at 750 °C so as to manufacture a positive electrode active material for lithium ion batteries of Example 1.

[0047]

Example 2

15 Except that the reaction concentration of the fluid including raw materials was set to 1.0 mol/L in terms of LiFePO_4 , that is, the amounts of the raw materials (lithium chloride, phosphoric acid and ferrous chloride) were doubled respectively, and adjustment was made so that the total amount of the fluid became 2 L, a positive electrode active material for lithium ion batteries of Example 2 was manufactured based
20 on Example 1.

[0048]

Example 3

Except that the reaction concentration of the fluid including raw materials was set to 1.5 mol/L in terms of LiFePO_4 , that is, the amounts of the raw materials were
25 increased to 1.5 times respectively, and adjustment was made so that the total amount of

the fluid became 2 L, a positive electrode active material for lithium ion batteries of Example 3 was manufactured based on Example 1.

[0049]

Example 4

5 Except that the reaction concentration of the fluid including raw materials was set to 1.0 mol/L in terms of LiFePO_4 , and the substitution amount of ethylene glycol was set to 3% by mass with respect to the total mass supplied to the hydrothermal reaction, a positive electrode active material for lithium ion batteries of Example 4 was manufactured based on Example 2.

10 [0050]

Example 5

Except that the reaction concentration of the fluid including raw materials was set to 1.0 mol/L in terms of LiFePO_4 , and the substitution amount of ethylene glycol was set to 30% by mass with respect to the total mass supplied to the hydrothermal reaction, a positive electrode active material for lithium ion batteries of Example 5 was manufactured based on Example 2.

[0051]

Example 6

20 Except that the reaction concentration of the fluid including raw materials was set to 1.0 mol/L in terms of LiFePO_4 , glycol was used instead of ethylene glycol, and the substitution amount of glycol was set to 10% by mass with respect to the total mass supplied to the hydrothermal reaction, a positive electrode active material for lithium ion batteries of Example 6 was manufactured based on Example 2.

[0052]

25 Example 7

Except that the reaction concentration of the fluid including raw materials was set to 1.0 mol/L in terms of LiFePO_4 , diethylene glycol was used instead of ethylene glycol, and the substitution amount of diethylene glycol was set to 10% by mass with respect to the total mass supplied to the hydrothermal reaction, a positive electrode active material for lithium ion batteries of Example 7 was manufactured based on Example 2.

[0053]

Example 8

Except that the reaction concentration of the fluid including raw materials was set to 1.0 mol/L in terms of LiFePO_4 , N-methyl-2-pyrrolidone was used instead of ethylene glycol, and the substitution amount of N-methyl-2-pyrrolidone was set to 10% by mass with respect to the total mass supplied to the hydrothermal reaction, a positive electrode active material for lithium ion batteries of Example 8 was manufactured based on Example 2.

[0054]

Example 9

Except that the reaction concentration of the fluid including raw materials was set to 1.0 mol/L in terms of LiFePO_4 , γ -butyrolactone was used instead of ethylene glycol, and the substitution amount of γ -butyrolactone was set to 10% by mass with respect to the total mass supplied to the hydrothermal reaction, a positive electrode active material for lithium ion batteries of Example 9 was manufactured based on Example 2.

[0055]

Example 10

Except that ferrous chloride (FeCl_2) was substituted with manganese (II) chloride (MnCl_2), and the reaction concentration of the fluid including raw materials was set to 1.0 mol/L in terms of LiMnPO_4 , a positive electrode active material for lithium ion

batteries of Example 10 was manufactured based on Example 2.

[0056]

Example 11

Except that ferrous chloride (FeCl_2) was substituted with cobalt (II) chloride
5 (CoCl_2), and the reaction concentration of the fluid including raw materials was set to 1.0
mol/L in terms of LiCoPO_4 , a positive electrode active material for lithium ion batteries
of Example 11 was manufactured based on Example 2.

[0057]

Example 12

10 Except that ferrous chloride (FeCl_2) was substituted with nickel (II) chloride
(NiCl_2), and the reaction concentration of the fluid including raw materials was set to 1.0
mol/L in terms of LiNiPO_4 , a positive electrode active material for lithium ion batteries
of Example 12 was manufactured based on Example 2.

[0058]

15 Comparative Example 1

Except that the reaction concentration of the fluid including raw materials was
set to 1.0 mol/L in terms of LiFePO_4 , and the substitution by ethylene glycol was not
performed, a positive electrode active material for lithium ion batteries of Comparative
Example 1 was manufactured based on Example 2.

20 [0059]

Comparative Example 2

Except that the reaction concentration of the fluid including raw materials was
set to 0.3 mol/L in terms of LiFePO_4 , and the amounts of the raw materials were reduced
respectively, a positive electrode active material for lithium ion batteries of Comparative
25 Example 2 was manufactured based on Example 2.

[0060]

Comparative Example 3

Except that the reaction concentration of the fluid including raw materials was set to 2.0 mol/L in terms of LiFePO_4 , and the amounts of the raw materials were increased respectively, a positive electrode active material for lithium ion batteries of Comparative Example 3 was manufactured based on Example 2.

[0061]

Comparative Example 4

Except that the reaction concentration of the fluid including raw materials was set to 1.0 mol/L in terms of LiFePO_4 , and the substituting amounts of ethylene glycol was set to 1.5% by mass with respect to the total mass supplied to the hydrothermal reaction, a positive electrode active material for lithium ion batteries of Comparative Example 4 was manufactured based on Example 2.

[0062]

Comparative Example 5

Except that the reaction concentration of the fluid including raw materials was set to 1.0 mol/L in terms of LiFePO_4 , and the substituting amounts of ethylene glycol was set to 50% by mass with respect to the total mass supplied to the hydrothermal reaction, a positive electrode active material for lithium ion batteries of Comparative Example 5 was manufactured based on Example 2.

[0063]

Comparative Example 6

Except that ferrous chloride (FeCl_2) was substituted with manganese (II) chloride (MnCl_2), the reaction concentration of the fluid including raw materials was set to 1.0 mol/L in terms of LiMnPO_4 , and the substitution by ethylene glycol was not

performed, a positive electrode active material for lithium ion batteries of Comparative Example 6 was manufactured based on Example 2.

[0064]

Comparative Example 7

5 Except that ferrous chloride (FeCl_2) was substituted with cobalt (II) chloride (CoCl_2), the reaction concentration of the fluid including raw materials was set to 1.0 mol/L in terms of LiCoPO_4 , and the substitution by ethylene glycol was not performed, a positive electrode active material for lithium ion batteries of Comparative Example 7 was manufactured based on Example 2.

10 [0065]

Comparative Example 8

15 Except that ferrous chloride (FeCl_2) was substituted with nickel (II) chloride (NiCl_2), the reaction concentration of the fluid including raw materials was set to 1.0 mol/L in terms of LiNiPO_4 , and the substitution by ethylene glycol was not performed, a positive electrode active material for lithium ion batteries of Comparative Example 8 was manufactured based on Example 2.

[0066]

[Evaluation of the positive electrode active material for lithium ion batteries]

20 For each of the positive electrode active materials of Examples 1 to 12 and Comparative Examples 1 to 8, the average primary particle diameter and the specific surface area were measured by the methods below.

(1) Average primary particle diameter

25 An field emission scanning electron microscope (FE-SEM) image was photographed at a 50 thousand times magnification using a field emission scanning electron microscope (FE-SEM), 20 fine particles were randomly selected from a scope of

a single view on the FE-SEM image, and the average value of the measured values of the particle diameters of the fine particles were used as the average primary particle diameter.

[0067]

5 (2) Specific surface area

The specific surface area (m^2/g) of the positive electrode active material was measured using the specific surface area measuring equipment BELSORP II (manufactured by BEL Japan).

10 The characteristics of each of the positive electrode active materials of Examples 1 to 9 and Comparative Examples 1 to 5 are shown in Table 1, and the characteristics of each of the positive electrode active materials of Examples 10 to 12 and Comparative Examples 6 to 8 are shown in Table 2, respectively.

15 In addition, the field emission scanning electron microscope (FE-SEM) image of the positive electrode active material of Example 2 is shown in FIG. 1, and the field emission scanning electron microscope (FE-SEM) image of the positive electrode active material of Comparative Example 1 is shown in FIG. 2, respectively.

[0068]

Table 1

	Organic solvent		Substitution amount (% by mass)	Reaction concentration (mol/L)	Average primary particle diameter (nm)	Specific surface area (m ² /g)
	Composition					
Example 1	Ethylene glycol		10	0.5	65	11
Example 2	Ethylene glycol		10	1.0	45	15
Example 3	Ethylene glycol		10	1.5	60	14
Example 4	Ethylene glycol		3	1.0	70	9
Example 5	Ethylene glycol		30	1.0	30	16
Example 6	Glycerin		10	1.0	60	11
Example 7	Diethylene glycol		10	1.0	60	11
Example 8	N-methyl-2-pyrrolidinone		10	1.0	55	12
Example 9	γ -butyrolactone		10	1.0	60	11
Comparative Example 1	-		-	1.0	500	4
Comparative Example 2	Ethylene glycol		10	0.3	400	5
Comparative Example 3	Ethylene glycol		10	2.0	.*	.*
Comparative Example 4	Ethylene glycol		1.5	1.0	400	5
Comparative Example 5	Ethylene glycol		50	1.0	40	15

*: Subgrain phase was generated

[0069]

Table 2

	Element M	Organic solvent		Reaction concentration (mol/L)	Average primary particle diameter (nm)	Specific surface area (m ² /g)
		Composition	Substituting amount (% by mass)			
Example 10	Mn	Ethylene glycol	10	1.0	50	12
Example 11	Co	Ethylene glycol	10	1.0	50	12
Example 12	Ni	Ethylene glycol	10	1.0	50	13
Comparative Example 6	Mn	-	-	1.0	500	5
Comparative Example 7	Co	-	-	1.0	600	5
Comparative Example 8	Ni	-	-	1.0	800	4

[0070]

[Manufacture of a lithium ion rechargeable battery]

The following treatments were performed on each of the positive electrode active materials of Examples 1 to 12 and Comparative Examples 1 to 8 to manufacture a lithium ion rechargeable battery of each of Examples 1 to 12 and Comparative Examples 1 to 8.

Firstly, 90 parts by mass of the positive electrode active material, 5 parts by mass of acetylene black as a conduction aid, 5 parts by mass of polyvinylidene fluoride (PVDF) as a binder, and N-methyl-2-pyrrolidone (NMP) as a solvent were mixed.

Next, the mixture was kneaded using a 3-roll mill so as to manufacture a positive electrode active material paste.

[0071]

Next, the positive electrode active material paste was coated on a 30 μm -thick aluminum current collector foil, and then was dried at 100 °C under a reduced pressure, thereby manufacturing a 30 μm -thick positive electrode.

Next, the positive electrode was formed into a 2 cm^2 disk by punching, and was dried under a reduced pressure. After that, a lithium ion rechargeable battery was manufactured under a dry argon atmosphere using the positive electrode, a negative electrode and a stainless steel 2016 coin cell.

In the battery, metallic lithium as the negative electrode, a porous polypropylene film as the separator, and a solution obtained by mixing 1 mole of LiPF_6 with a solution in which ethylene carbonate (EC) and diethyl carbonate (DEC) had been mixed in a ratio of 3 to 7 as the electrolytic solution were used.

[0072]

[Battery charging and discharging test]

Battery charging and discharging tests were performed using the lithium ion rechargeable batteries of Examples 1 to 12 and Comparative Examples 1 to 8.

Herein, the cutoff voltages were set to 2.0 to 4.0 V for Examples 1 to 9 and Comparative Examples 1 to 5 (M = Fe), 2.0 to 4.5 V for Example 10 and Comparative Example 6 (M = Mn), 2.0 to 5.0 V for Example 11 and Comparative Example 7 (M = Co), and 2.0 to 5.5 V for Example 12 and Comparative Example 8 (M = Ni). In the measurement of the initial discharge capacity, charging was performed at 0.1 C, and discharging was performed at 0.1 C.

[0073]

Furthermore, for Examples 1 to 9 and Comparative Examples 1 to 5 (M = Fe), as the measurement of the other discharge capacity, tests were performed in which charging was performed at 0.2 C, and discharge capacities were measured respectively at 0.1 C, 0.2 C, 5 C, 8 C, and 12 C. In addition, the rate (%) of the discharge capacity at 5 C to the discharge capacity at 0.2 C was used as the discharge retention rate (5C/0.2C retention rate). The discharge retention rate was determined such that the more favorable, the closer it approached to 100%.

The discharge capacities and the discharge retention rates (5C/0.2C retention rate) of Examples 1 to 9 and Comparative Examples 1 to 5 are shown in Table 3, and the initial discharge capacities (0.1C/0.1C) of Examples 10 to 12 and Comparative Examples 6 to 8 are shown in Table 4, respectively.

[0074]

Table 3

	Discharge capacity (mAh/g)					5 C/0.2 C retention rate (%)
	0.1 C/0.1 C	0.2 C/0.2 C	0.2 C/5 C	0.2 C/8 C	0.2 C/12 C	
Example 1	158	155	141	119	100	91
Example 2	157	156	140	123	99	90
Example 3	157	155	141	120	101	91
Example 4	159	156	140	115	93	90
Example 5	159	156	142	123	106	91
Example 6	157	155	138	118	101	89
Example 7	158	156	140	121	103	90
Example 8	157	155	138	117	99	89
Example 9	156	154	137	116	98	89
Comparative Example 1	158	156	120	100	60	77
Comparative Example 2	158	155	121	98	58	78
Comparative Example 3	.*	.*	.*	.*	.*	.*
Comparative Example 4	158	156	125	103	70	80
Comparative Example 5	151	142	118	100	70	83

*: Subgrain phase was generated, and it was not possible to manufacture an electrode.

[0075]

Table 4

	Initial discharge capacity (mAh/g) (0.1 C/0.1 C)
Example 10	100
Example 11	110
Example 12	60
Comparative Example 6	10
Comparative Example 7	40
Comparative Example 8	8

[0076]

According to Tables 1 to 4 and FIGS. 1 and 2, the following was found.

(1) As shown in Examples 1 to 12, it was confirmed that the average primary particle diameter of the positive electrode active material can be controlled in a range of 30 nm to 80 nm by substituting a part of water included in the slurry with an aqueous organic solvent.

(2) It was possible to confirm that, in the positive electrode active materials of Examples 1 to 12, the specific surface areas were increased in comparison to the positive electrode active material of Comparative Example 1; however, in the lithium ion rechargeable batteries of Examples 1 to 9, the initial discharge capacities and the discharge retention rates (5C/0.2C retention rate) were improved in comparison to the lithium ion rechargeable battery of Comparative Example 1, and the improvement of the discharging and charging characteristics and the securing of the initial discharge capacity were achieved.

In addition, it was possible to confirm that, in the lithium ion rechargeable batteries of Examples 10 to 12, the initial discharge capacities (0.1C/0.1C) were improved in comparison to the lithium ion rechargeable batteries of Comparative Examples 6 to 8, and the initial discharge capacities were secured.

(3) In Comparative Example 2 in which the reaction concentration of the raw material fluid was smaller than the range of the present invention, Comparative Example 2 exhibited the significantly large average primary particle diameter and the degraded discharging retention rate as compared with Example 2. In Comparative Example 3 in which the reaction concentration of the fluid including raw materials was larger than the range of the present invention, subgrain phase was generated as impurities, and it was not possible to manufacture an electrode.

(4) In Comparative Example 4 in which the mass of the aqueous organic solvent in the total mass of the mixture was smaller than the preferable range of the present invention, Comparative Example 4 exhibited the significantly large average primary particle diameter and the degraded discharging retention rate as compared with Example 2. In Comparative Example 5 in which the mass of the aqueous organic solvent in the total mass of the mixture was larger than the preferable range of the present invention, the average primary particle diameter was small, but the discharge retention rate was degraded.

Aforementioned Examples showed cases in which tests were performed under the conditions of constant temperature and constant pressure, but it was confirmed that the effects of the present application could be stably obtained even under other high-temperature and high-pressure conditions.

INDUSTRIAL APPLICABILITY

[0077]

The present invention provides a method of manufacturing a positive electrode active material for lithium ion batteries, a positive electrode active material for lithium ion batteries, an electrode for lithium ion batteries and a lithium ion battery, wherein the average primary particle diameter of the fine particles of LiMPO_4 (wherein M represents one or two or more kinds selected from the group of Fe, Mn, Co and Ni) is controlled to improve the initial discharge capacity or high-speed charging and discharging characteristics.

The method of manufacturing a positive electrode active material for lithium ion batteries according to the present invention is a method in which a mixture, which contains Li_3PO_4 or a Li source and a phosphoric acid source, and one or two or more

kinds selected from a group of a Fe source, a Mn source, a Co source and a Ni source, wherein they are included in an amount in terms of 0.5 to 1.5 mol/L of LiMPO_4 (wherein M represents one or two or more kinds selected from the group of Fe, Mn, Co and Ni), and also contains water and an aqueous organic solvent having a boiling point of 150 °C or more, is reacted at a high temperature and a high pressure to generate the fine particles of LiMPO_4 (wherein M represents one or two or more kinds selected from the group of Fe, Mn, Co and Ni) having an average primary particle diameter of from 30 to 80 nm. Accordingly, it is possible to improve the charging and discharging characteristics and secure the initial discharge capacity by applying the obtained positive electrode active material for lithium ion batteries to lithium ion batteries, particularly to the positive electrodes in lithium ion rechargeable batteries, and therefore the present invention has an extremely large industrial meaning.

CLAIMS

1. A method of manufacturing a positive electrode active material for lithium ion batteries, comprising:

5 preparing a mixture containing (A) Li_3PO_4 , or a Li source and a phosphoric acid source; (B) at least one selected from a group of a Fe source, a Mn source, a Co source and a Ni source; water; and an aqueous organic solvent having a boiling point of 150 °C or more,

wherein the amounts of (A) and (B) in the mixture are adjusted to amounts
10 necessary to manufacture therefrom LiMPO_4 (wherein M represents at least one selected from the group of Fe, Mn, Co and Ni) at a concentration of more than or equal to 0.5 mol/L and less than or equal to 1.5 mol/L; and

generating fine particles of LiMPO_4 (wherein M represents at least one selected from the group of Fe, Mn, Co and Ni) having an average primary particle diameter of 30
15 to 80 nm by reacting the (A) and the (B) at a high temperature and a high pressure.

2. The method of manufacturing a positive electrode active material for lithium ion batteries according to Claim 1,

wherein the aqueous organic solvent is at least one selected from multivalent
20 alcohols, amides, esters and ethers.

3. The method of manufacturing a positive electrode active material for lithium ion batteries according to Claim 1,

wherein the content of the aqueous organic solvent is 3 to 30% by mass of the
25 total mass of the mixture.

4. A positive electrode active material for lithium ion batteries obtained by the method of manufacturing a positive electrode active material for lithium ion batteries according to Claim 1.

5

5. An electrode for lithium ion batteries,
wherein the electrode is the positive electrode active material for lithium ion batteries according to Claim 4, on which carbon is coated.

10

6. A lithium ion battery, which comprises the electrode for lithium ion batteries according to Claim 5 as the positive electrode.

7. The method of manufacturing a positive electrode active material for lithium ion batteries according to Claim 1,

15

wherein the high temperature is more than or equal to 120°C and less than or equal to 250°C, and the high pressure is more than or equal to 0.2 MPa and less than or equal to 4.0 MPa.

8. The method of manufacturing a positive electrode active material for lithium ion batteries according to Claim 1,

20

wherein the Li source is at least one selected from a group consisting of lithium hydroxide, lithium carbonate, lithium chloride, lithium acetate, lithium oxalate and hydrates thereof; the phosphoric acid source is at least one selected from a group consisting of orthophosphoric acid, metaphosphoric acid, ammonium

25

dihydrogenphosphate, diammonium hydrogen phosphate, ammonium phosphate and

hydrates thereof; the Fe source is at least one selected from a group consisting of ferrous chloride, ferrous sulfate, ferrous acetate and hydrates thereof; the Mn source is at least one selected from a group consisting of manganese (II) chloride, manganese (II) sulfate, manganese (II) acetate, manganese (II) nitrate and hydrates thereof; the Co source is at
5 least one selected from a group consisting of cobalt (II) chloride, cobalt (II) sulfate, cobalt (II) acetate and hydrates thereof; and the Ni source is at least one selected from a group consisting of nickel (II) chloride, nickel (II) sulfate, nickel (II) acetate and hydrates thereof.

Application number / Numéro de demande: JP2010 002111

Figures: 1-2

Pages: 1

Unscannable items received with this application
(Request original documents in File Prep. Section on the 10th floor)

Documents reçu avec cette demande ne pouvant être balayés
(Commander les documents originaux dans la section de la préparation
des dossiers au 10ième étage)