

(19) AUSTRALIAN PATENT OFFICE

(54) Title
Zinc oxide powder aggregates present in circular, ellipsoidal, linear and branched form

(51)⁶ International Patent Classification(s)
C01G 9/03 (2006.01) ^{8BMEP} **C09C**
C09C 1/04 (2006.01) 1/04
C01G 9/03 20060101ALI2005100
20060101AFI2005100 ^{8BMEP}
PCT/EP2004/009752

(21) Application No: 2004274149 (22) Application Date: 2004 .09 .02

(87) WIPO No: W005/028565

(30) Priority Data

(31) Number	(32) Date	(33) Country
103 43 728.2	2003 .09 .22	DE

(43) Publication Date : 2005 .03 .31

(71) Applicant(s)
Evonik Degussa GmbH

(72) Inventor(s)
Katusic, Stipan; Albers, Peter; Miess, Horst; Kramer, Michael; Kress,
Peter; Zimmermann, Guido

(74) Agent/Attorney
Spruson & Ferguson, Level 35 St Martins Tower 31 Market Street, Sydney, NSW, 2000

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
31 March 2005 (31.03.2005)

PCT

(10) International Publication Number
WO 2005/028565 A1

(51) International Patent Classification⁷: **C09C 1/04**,
C01G 9/03

(21) International Application Number:
PCT/EP2004/009752

(22) International Filing Date:
2 September 2004 (02.09.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
103 43 728.2 22 September 2003 (22.09.2003) DE

(71) Applicant (for all designated States except US): **DE-
GUSSA AG** [DE/DE]; Bennigsenplatz 1, 40474 Düssel-
dorf (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **KATUSIC, Stip-
pan** [DE/DE]; Berliner Ring 20, 65779 Kelkheim (DE).
KRAMER, Michael [DE/DE]; Dresdener Strasse 30,
61137 Schöneck-Kilianstädten (DE). **KRESS, Peter**

[DE/DE]: Spessartstrasse 26, 63791 Karlstein (DE).
MEISS, Horst [DE/DE]; Bruchwaldstrasse 8, 63796 Kahl
(DE). **ZIMMERMANN, Guido** [DE/DE]; Castellstrasse
19a, 63454 Hanau (DE). **ALBERS, Peter** [DE/DE];
Kleinfellerstrasse 3, 63454 Hanau (DE).



(74) Common Representative: **DEGUSSA AG**; Intellectual
Property Management, PATENTE und MARKEN, Stan-
dort Hanau, Postfach 13 45, 63403 Hanau (DE).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AI, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DK, DM, DZ, EC, EE, EG, ES, FI, GB,
GD, GE, GH, GM, GT, GU, ID, IL, IN, IS, JP, KE, KG,
KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG,
MK, MN, MW, MX, MY, NA, NI, NO, NZ, OM, PG, PH,
PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,

[Continued on next page]

(54) Title: ZINC OXIDE POWDER AGGREGATES PRESENT IN CIRCULAR, ELLIPSOIDAL, LINEAR AND BRANCHED FORM



(57) Abstract: Pyrogenically prepared zinc oxide powder having a BET surface area of from 10 to 200 m²/g, which is in the form of aggregates, the aggregates being composed of particles having different morphologies, and 0-10 % of the aggregates being in a circular form, 30-50 % being in an ellipsoidal form, 30-50 % being in a linear form and 20-30 % being in a branched form. It is prepared by reacting a starting mixture containing zinc vapour, a combustible gas and steam or a mixture of steam and carbon dioxide in a flame with an oxygen-containing gas in an oxidation zone, cooling the hot reaction mixture in a quenching zone and separating the solid material from the gas stream, the amount of oxygen in the oxidation zone being greater than the amount necessary for the complete oxidation of the combustible gas and the zinc vapour. The zinc oxide powder can be used as a constituent of sun protection compositions for protection against UV radiation

WO 2005/028565 A1



FR, GB, GR, HU, IE, IT, LI, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NI, SN, TD, TG).

— *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

Declaration under Rule 4.17:

— *of inventorship (Rule 4.17(iv)) for US only*

Published:

— *with international search report*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

ZINC OXIDE POWDER AGGREGATES PRESENT IN CIRCULAR, ELLIPSOIDAL, LINEAR AND BRANCHED FORM

The invention relates to a zinc oxide powder, its preparation and use.

- 5 Zinc oxide powders are used in inks, surface coatings, in resins and fibres. An important sector is the use of zinc oxide powders in the cosmetic field, especially as a constituent of sun protection formulations.

- There are in principle two possibilities for synthesising zinc oxide powders, wet-chemical processes and gas-phase processes. In general, the zinc compounds used as starting material in wet-chemical processes are those which can be converted into zinc oxide by means of heat, such as, for example, zinc hydroxide, zinc oxalate or zinc carbonate.
- 10 The wet-chemical method usually has the disadvantage that the zinc oxide particles produced agglomerate to form larger units, which are undesirable especially in cosmetic applications. In addition, impurities resulting from process and starting materials cannot be removed from the finished product or can be removed only with great difficulty.

The process, which is usually carried out as a batch process, comprises filtering, drying and, optionally, grinding the particles and is relatively cost-intensive.

- 25 Gas-phase processes or pyrogenic processes permit a more inexpensive process. They include the French and American processes, according to which zinc oxide can be produced on a large scale.

In both processes, oxidation of zinc vapour is carried out.

- 30 Disadvantages of these processes are the formation of large aggregates of primary particles and a low BET surface area.

The prior art describes various possibilities for gas-phase synthesis with the aim of achieving a higher BET surface area, better transparency and higher UV protection.

Ultimately, a common feature of all these attempts is the oxidation of zinc vapour.

JP 56-120518 describes the oxidation of zinc vapour using air or oxygen, with the formation of non-aggregated, 5 needle-like zinc oxide particles. Such particles can often be incorporated into sun protection formulations only with difficulty.

US 6,335,002 describes the oxidation of zinc vapour using air or oxygen. By varying the process parameters, primary 10 particles of zinc oxide which are largely isotropic in form and have a low degree of aggregation should be formed. In the examples according to the invention of US 6,335,002, the aggregate diameters are from 0.47 to 0.55 μm . The zinc oxide powder has a BET surface area of from 10 to 200 m^2/g 15 and a tamped density of from 4 to 40 ml/g .

The oxidation of the zinc vapour is carried out in an atmosphere of an oxidising gas which contains oxygen and steam. Such an atmosphere can also be produced by burning an oxygen-containing gas with hydrogen or propane, an 20 excess of oxygen being used. Zinc vapour and the oxygen/steam mixture are injected separately by means of nozzles into a reactor, in which the oxidation takes place.

Overall, the prior art, irrespective of the preparation, offers numerous types of zinc oxide in the form of needles, 25 spheres, tetrahedrons, rods and flocks, as listed, for example, in US 5,441,226.

The prior art demonstrates the keen interest in zinc oxide, especially in its use as UV protection in sun protection formulations.

30 The object of the invention is to provide a zinc oxide powder which avoids the disadvantages of the prior art. In particular, it should exhibit high transparency while providing good UV protection. It should also be readily incorporable into dispersions. A further object is to 35 provide a process for the preparation of zinc oxide powder.

The invention provides a pyrogenically prepared zinc oxide powder having a BET surface area of from 10 to 200 m²/g, characterised in that

- it is in the form of aggregates,
- 5 - the aggregates being composed of particles having different morphologies,
- and
- 0-10 % of the aggregates being in a circular form,
- 30-50 % of the aggregates being in an ellipsoidal
10 form,
- 30-50 % of the aggregates being in a linear form,
- 20-30 % of the aggregates being in a branched form.

- Within the scope of the invention, particles are understood
- 15 as being the particles formed primarily in the pyrogenic preparation process. They join together during the reaction, with the formation of sintering surfaces, to form aggregates. It is important that the aggregates are composed of particles having different morphologies.
- 20 According to the definition, an aggregate is composed of particles which are the same or approximately the same, the primary particles (DIN 53206).

- The zinc oxide powder according to the invention, on the other hand, contains aggregates which consist of particles
- 25 having different morphologies, and are therefore not designated primary particles. Morphology is understood as meaning both isotropic and anisotropic particles. There may be, for example, spherical or largely spherical particles, bulb-like particles, rod-shaped particles or needle-shaped
- 30 particles. It is important that the aggregates consist of different particles, and the particles are joined together by sintering surfaces.

The BET surface area of the powder according to the invention may be from 20 to 60 m²/g.

The aggregates of the zinc oxide powder according to the invention are in circular, ellipsoidal, linear and branched forms. Figures 1a-c show typical forms of ellipsoidal, linear and branched aggregates of the zinc oxide powder according to the invention.

Preference may be given to zinc oxide powders which contain an approximately equal amount of from 30 to 40 % of ellipsoidal and linear forms and a smaller amount of branched forms of from 20 to 25 % and of circular forms of from 2 to 6 %. Figure 2 shows a TEM image of the powder according to the invention, and Figures 3a-d show a linear, branched, ellipsoidal and circular aggregate, respectively, of that powder.

The zinc oxide powder according to the invention may also have a tamped density, determined according to DIN ISO 787/11, of at least 150 g/l. A tamped density of from 250 to 350 g/l may be particularly preferred.

It is also possible for the zinc oxide powder according to the invention to consist of aggregates that have a mean projected aggregate surface area of less than 10,000 nm², an equivalent circle diameter (ECD) of less than 100 nm and a mean circumference of less than 600 nm. These values can be obtained by image analysis of approximately from 1000 to 2000 aggregates from TEM images.

Particular preference may be given to zinc oxide powders having a mean projected aggregate surface area of from 2000 to 8000 nm², an equivalent circle diameter (ECD) of from 25 to 80 nm and a mean circumference of from 200 to 550 nm.

In particular when using zinc oxide powder in cosmetic and pharmaceutical preparations, it is important to minimise harmful impurities. These include especially lead, cadmium, arsenic, iron, antimony and mercury.

The zinc oxide powder according to the invention may contain not more than 20 ppm of lead, not more than 3 ppm of arsenic, not more than 15 ppm of cadmium, not more than 200 ppm of iron, not more than 1 ppm of antimony and not
5 more than 1 ppm of mercury, in each case based on zinc oxide.

The invention further provides a process for the preparation of the zinc oxide powder according to the invention, which process is characterised in that

- 10 - a starting mixture containing zinc vapour, a combustible gas and the reaction products from the oxidation of the combustible gas with an oxygen-containing gas
- is reacted in a flame with an oxygen-containing gas
15 in an oxidation zone,
- the hot reaction mixture is cooled in a quenching zone and the solid material is separated from the gas stream,
- the amount of oxygen in the oxidation zone being
20 greater than the amount necessary for the complete oxidation of the combustible gas and the zinc vapour.

The manner in which the zinc vapour is provided is not limited. For example, zinc powder or another zinc compound
25 that yields zinc when subjected to heat treatment can be vaporised in a vaporiser and fed by means of a stream of inert gas into the apparatus containing the starting mixture. The starting mixture also contains a combustible gas, which may be hydrogen, methane, ethane or propane or a
30 mixture thereof, hydrogen being preferred. Also present in the starting mixture are steam and/or carbon dioxide, the reaction products from the combustion of the combustible gas. The starting mixture may preferably contain steam.

The mixture of zinc vapour, combustible gas and steam or steam/carbon dioxide, and also other inert gases, for example nitrogen, is transferred to an oxidation zone, where it reacts in a flame with an oxygen-containing gas in an oxidation zone. The amount of oxygen in the oxidation zone is greater than the amount necessary for the complete oxidation of the combustible gas and the zinc vapour. In the oxidation zone, the oxidation of the combustible gas, for example hydrogen, according to Eq. 1 and the oxidation of the zinc vapour according to Eq. 2 take place in parallel.





Figure 4 shows the sequence of the process according to the invention in diagrammatic form. In the Figure: A = starting mixture; B = oxidation zone; C = quenching zone; D = separation of solid material; 1 = zinc vapour; 2 = combustible gas; 3 = water or water/carbon dioxide; 4 = oxidising air; 5 = quenching air. Although water is formed in the oxidation of the combustible gas in the oxidation zone, the presence of water and/or carbon dioxide in the starting mixture has been found to be essential for the formation of the zinc oxide particles according to the invention. Water is preferred. Water and/or carbon dioxide can result, for example, from the oxidation of a combustible gas using oxygen.

The molar ratio of water to zinc vapour may preferably be from 15:1 to 35:1 and particularly preferably from 20:1 to 30:1.

It is also advantageous if the molar ratio of combustible gas to zinc vapour in the starting mixture is from 5:1 to 25:1. A ratio of from 10:1 to 20:1 is particularly advantageous.

When the starting mixture enters the oxidation zone, it may be advantageous for the molar ratio of oxygen to combustible gas to be from 3:1 to 20:1. A ratio of from 6:1 to 15:1 may be particularly advantageous.

- 5 When the starting mixture enters the oxidation zone, it may further be advantageous for the molar ratio of oxygen to zinc vapour to be from 5:1 to 30:1. A ratio of from 10:1 to 20:1 may be particularly advantageous.

The temperature of the starting mixture may be from 920°C
10 to 1250°C.

- In a preferred embodiment of the process according to the invention, zinc vapour can be obtained in a reductive vaporisation zone by vaporising zinc powder by means of a stream of inert gas in a centrally arranged pipe by means
15 of a flame arranged around the centrally disposed pipe, which flame is generated by reaction of a combustible gas and an oxygen-containing gas, the combustible gas being present in a stoichiometric excess relative to the oxygen content of the oxygen-containing gas.

- 20 In a particularly preferred embodiment of the process, the centrally arranged pipe is so adjusted that contact with the flame is avoided. A reductive vaporisation zone within the scope of the invention is understood as being a zone in which there prevails an atmosphere that is deficient in
25 oxygen. This prevents the zinc powder from being oxidised even before the vaporisation.

- The molar ratio of combustible gas to the oxygen content of the oxygen-containing gas in the reductive vaporisation zone may preferably be from 1.5:1 to 3.5:1 and particularly
30 preferably from 2:1 to 2.5:1.

The invention provides a further process for the preparation of the zinc oxide powder according to the invention, which process is characterised in that

- zinc powder is vaporised inside a reactor and oxidised to zinc oxide, wherein
- in a reductive vaporisation zone, zinc powder is metered with the aid of a stream of inert gas into a centrally arranged pipe which projects into the vaporisation zone of the reactor,
- is vaporised by means of an externally arranged flame which is generated by reaction of a combustible gas with an oxygen-containing gas,
- the combustible gas and the oxygen-containing gas being supplied in pipes arranged concentrically around the central pipe, and
- the centrally arranged pipe being longer than the pipes arranged concentrically around it, and
- the combustible gas being present in a stoichiometric excess relative to the oxygen content of the oxygen-containing gas,
- and then an excess of oxygen in the form of an oxygen-containing gas is fed into the gas stream from the reductive vaporisation zone, so that the excess combustible gas and the zinc vapour from the vaporisation zone are oxidised completely in the oxidation zone,
- then the hot reaction mixture is cooled in a quenching zone and the solid material is separated from the gas stream.

Figure 5 shows the apparatus for carrying out this process in diagrammatic form. In the Figure: A = reductive vaporisation zone; B = oxidation zone; C = quenching zone;

1 = zinc powder + inert gas; 2 = combustible gas, preferably hydrogen; 3 = air; 4 = oxidising air; 5 = quenching air.

The process according to the invention can preferably be carried out in such a manner that the molar ratio of combustible gas to the oxygen content of the oxygen-containing gas in the reductive vaporisation zone is from
5 1.5:1 to 3.5:1. This ratio may particularly preferably be from 2:1 to 2.5:1.

It may also be preferable for the molar ratio of oxygen to combustible gas on entry into the oxidation zone to be preferably from 3:1 to 20:1 and particularly preferably
10 from 6:1 to 15:1.

It may also be advantageous for the molar ratio of oxygen to zinc vapour on entry into the oxidation zone to be from 5:1 to 30:1. A ratio of from 10:1 to 20:1 may be particularly advantageous.

15 In order to achieve high purity of the zinc oxide powder, it is advantageous to use highly pure zinc powder as the starting material.

High purity is understood as meaning a purity of at least 99 %, in the case of special requirements a purity of at
20 least 99.9 %. In the case of a zinc oxide powder for cosmetic or pharmaceutical use in particular, attention is to be given to the amounts of lead (not more than 20 ppm), arsenic (not more than 3 ppm), cadmium (not more than 15 ppm), iron (not more than 200 ppm), antimony (not more
25 than 1 ppm) and mercury (not more than 1 ppm).

In the processes according to the invention, the temperature of the mixture to be oxidised on entering the oxidation zone is preferably from 920°C to 1250°C.

It may also be advantageous to limit the residence time of
30 the reaction mixture in the oxidation zone to from 5 milliseconds to 200 milliseconds, a range of from 10 milliseconds to 30 milliseconds being particularly advantageous.

The temperature in the quenching zone immediately before
35 the addition of the quenching air may preferably be from

600°C to 850°C, and the rate of cooling in the quenching zone may be from 1000 Kelvin/second to 50,000 Kelvin/second.

5 The invention relates also to the use of the zinc oxide powder according to the invention as a constituent of sun protection compositions for protection against UV radiation, as a vulcanisation aid, in plastics and surface coatings as a UV absorber, as a crosslinking agent or catalyst in the curing or polymerisation of plastics or
10 plastics monomers, in synthetic resins, in pharmaceutical and cosmetic preparations as an antifungal or antibacterial additive, in the preparation of ceramics, as a catalyst or catalyst support.

Examples:**Analytical methods**

The BET surface area is determined according to DIN 66131.

5 The TEM images are obtained using a Hitachi TEM device,
type H-75000-2. By means of the CCD camera of the TEM
device and subsequent image analysis, approximately from
1000 to 2000 aggregates are evaluated. The parameters are
defined in accordance with ASTM 3849-89. Analysis of the
10 form of the aggregates according to circular, ellipsoidal,
linear and branched is carried out according to Herd et
al., Rubber, Chem. Technol. 66 (1993) 491.
The tamped density is determined according to DIN ISO
787/11.

15 Example 1:

Example 1 is carried out in a reactor according to
Figure 4.

Zinc powder (510 g/h) is conveyed by means of a stream of
nitrogen (4.2 Nm³/h) into a reductive vaporisation zone in
20 which a hydrogen/air flame (hydrogen: 4.0 Nm³/h, air:
8.0 Nm³/h) is burning. The zinc powder is thereby
vaporised.

The reaction mixture comprising zinc vapour, hydrogen,
nitrogen and water flows into the oxidation zone, into
25 which 20 Nm³/h of air is added.

The temperature T1 before addition of the oxidising air is
956°C. Then 10 Nm³/h of quenching air are added. The
temperature T2 before addition of the quenching air is
648°C. The resulting zinc oxide powder is separated from
30 the gas stream by filtration.

Examples 2 to 4 are carried out analogously to Example 1.
The process parameters are to be found in Table 1.

Example 5 (comparison example):

Zinc powder (250 g/h) is conveyed by means of a stream of nitrogen (1.5 Nm³/h) into a vaporisation zone in which a hydrogen/air flame (hydrogen: 4.25 Nm³/h, air: 8.40 Nm³/h) is burning. The zinc powder is thereby vaporised. The reaction mixture comprising zinc vapour, hydrogen, nitrogen and water is then cooled to a temperature of 850°C in a nucleation zone by the metered addition of 1 Nm³/h of nitrogen. 5 m³/h of oxidising air and 34 Nm³/h of quenching air are then added, the reaction temperature falling to values of less than 400°C. The resulting zinc oxide powder is separated from the gas stream by filtration. Example 5 is to be found in the patent application having the application number DE 10212680 of 22.03.2002.

Example 6 (comparison example) is a commercially available zinc oxide powder from Nanophase, NanoTek® Zinc Oxide 99+%.

The process parameters for the preparation of the zinc oxide powders of Examples 1 to 4 are to be found in Table 1. The physico-chemical data of the zinc oxide powders of Examples 1 to 6 are to be found in Table 2.

Table 2 shows that the powders according to the invention of Examples 1 to 4 exhibit the claimed distribution of the aggregate forms into circular, linear, branched and ellipsoidal forms. The powders of Comparison Examples 5 and 6 do not exhibit this distribution.

The equivalent circle diameter (ECD) of the powders according to the invention of Examples 1 to 4 is less than 100 nm, the mean aggregate circumference is less than 600 nm and the mean aggregate surface area is less than 7500 nm².

Figures 3a-d show a linear, branched, ellipsoidal and circular aggregate, respectively, of the powder of Example 3.

- 5 The powder according to the invention can readily be incorporated into sun protection formulations. It exhibits high transparency and high UV protection.

Table 1: Process parameters in the preparation of ZnO

Example		1	2	3	4
Reductive vaporisation zone					
Zn powder	g/h mol/h	510 7.80	500 7.65	520 7.95	250 3.82
H ₂	Nm ³ /h mol/h	4.0 178.45	4.0 178.45	5.0 223.06	4.0 178.45
Air	Nm ³ /h mol O ₂ /h	8.0 74.95	6.8 49.65	10.0 93.69	8.0 74.95
H ₂ O from H ₂ +O ₂	mol/h	178.45	178.45	223.06	178.45
Carrier gas N ₂	Nm ³ /h mol/h	4.2 187.37	4.20 187.37	4.2 187.37	5.0 223.11
Excess of H ₂	mol/h	28.55	51.04	35.69	28.55
H ₂ /O ₂		2.38	2.80	2.38	2.38
H ₂ /Zn		13.27	15.00	16.26	27.06
H ₂ O/Zn		22.87	23.33	28.04	46.66
Temperature T1*	°C	956	980	1000	1060
Oxidation zone					
Air	Nm ³ /h mol O ₂ /h	20.0 187.37	16.0 149.90	15.0 140.53	25.0 233.82
O ₂ /H ₂ **		13.13	5.87	7.88	16.41
O ₂ /Zn**		24.02	19.60	17.67	61.24
Temperature T2*	°C	648	718	746	758
Quenching zone					
Air	Nm ³ /h mol/h	10.0 93.69	24.0 224.85	22.0 206.11	22.0 206.11

- * T1: temperature of the reaction mixture immediately before entering the oxidation zone; T2: temperature of the reaction mixture immediately before addition of the quenching air;
- ** O₂/H₂: stoichiometrically required amount for oxidation of H₂; O₂/Zn: stoichiometrically required amount for oxidation of Zn

Table 2: Physico-chemical data of the zinc oxide powders

Example		Examples according to the invention						Comparison examples	
		1	2	3	4	5	6		
BET surface area	m ² /g	27	25	25	75	20	16		
Number of aggregates		1877	1477	1147	2055	1466	1237		
Proportion of aggregates									
circular		4	3	5	9	7	10		
ellipsoidal	%	37	36	36	44	54	52		
linear		36	37	34	26	23	23		
branched		23	24	25	21	16	19		
Mean aggregate surface area	nm ²	4941	6835	7450	2470	15762	25360		
Equivalent circle diameter of the aggregates	nm	66	75	82	33	133	146		
Mean aggregate circumference	nm	445	497	526	222	759	790		
Tamped density	g/l	316	224	235	210	n.d.	n.d.		

*n.d. = not determined;

Patent claims

1. Pyrogenically prepared zinc oxide powder having a BET surface area of from 10 to 200 m²/g, characterised in that
 - 5 - it is in the form of aggregates,
 - the aggregates being composed of particles having different morphologies,
 - and
 - 0-10 % of the aggregates being in a circular form,
 - 10 - 30-50 % of the aggregates being in an ellipsoidal form,
 - 30-50 % of the aggregates being in a linear form,
 - 20-30 % of the aggregates being in a branched form.
2. Pyrogenically prepared zinc oxide powder according to claim 1, characterised in that the tamped density, determined according to DIN ISO 787/11, is at least 150 g/l.
3. Pyrogenically prepared zinc oxide powder according to claims 1 or 2, characterised in that the aggregates
 - 20 have
 - a mean projected aggregate surface area of less than 10,000 nm²
 - an equivalent circle diameter (ECD) of less than 100 nm and
 - 25 - a mean circumference of less than 600 nm.
4. Pyrogenically prepared zinc oxide powder according to claims 1 to 3, characterised in that the amount of lead is not more than 20 ppm, the amount of arsenic is not more than 3 ppm, the amount of cadmium is not more than 15 ppm, the amount of iron is not more than 200 ppm, the amount of antimony is not more than 1 ppm and the amount of mercury is not more than 1 ppm.
5. Process for the preparation of the zinc oxide powder according to claims 1 to 4, characterised in that

- a starting mixture containing zinc vapour, a combustible gas and steam or a mixture of steam and carbon dioxide
 - is reacted in a flame with an oxygen-containing gas in an oxidation zone,
 - the hot reaction mixture is cooled in a quenching zone and the solid material is separated from the gas stream,
 - the amount of oxygen in the oxidation zone being greater than the amount necessary for the complete oxidation of the combustible gas and the zinc vapour.
- 5
- 10
- 15
- 20
- 25
- 30
6. Process according to claim 5, characterised in that the zinc vapour is obtained in a reductive vaporisation zone by vaporising zinc powder by means of a stream of inert gas in a centrally arranged pipe by means of an externally arranged flame which is generated by reaction of a combustible gas and an oxygen-containing gas, the combustible gas being present in a stoichiometric excess relative to the oxygen content of the oxygen-containing gas.
7. Process for the preparation of the zinc oxide powder according to claims 1 to 4, characterised in that the vaporisation of the zinc powder and the oxidation to zinc oxide are carried out inside a reactor, wherein
- in a reductive vaporisation zone, zinc powder is metered in a centrally arranged pipe by means of a flame arranged around the centrally disposed pipe, in which the flame is generated by reaction of a combustible gas with an oxygen-containing gas,
 - the combustible gas and the oxygen-containing gas being supplied in separate pipes arranged concentrically around the central pipe, and

- the combustible gas being present in a stoichiometric excess relative to the oxygen content of the oxygen-containing gas,
 - and then an excess of oxygen in the form of an oxygen-containing gas is fed into the gas stream from the reductive vaporisation zone, so that the excess combustible gas and the zinc vapour from the vaporisation zone are oxidised completely in the oxidation zone,
 - then the hot reaction mixture is cooled in a quenching zone and the solid material is separated from the gas stream.
8. Use of the pyrogenically prepared zinc oxide powder according to claims 1 to 4 as a constituent of sun protection compositions for protection against UV radiation, as a vulcanisation aid, in plastics and surface coatings as a UV absorber, as a crosslinking agent or catalyst in the curing or polymerisation of plastics or plastics monomers, in synthetic resins, in pharmaceutical and cosmetic preparations as an antifungal or antibacterial additive, in the preparation of ceramics, as a catalyst or catalyst support.





Fig. 2




Fig. 3a




Fig. 3b




Fig. 3c




Fig. 3d

