



US008956700B2

(12) **United States Patent**
Taxacher et al.

(10) **Patent No.:** **US 8,956,700 B2**
(45) **Date of Patent:** **Feb. 17, 2015**

(54) **METHOD FOR ADHERING A COATING TO A SUBSTRATE STRUCTURE**

(75) Inventors: **Glenn Curtis Taxacher**, Simpsonville, SC (US); **Andres Garcia Crespo**, Greenville, SC (US); **Herbert Chidsey Roberts, III**, Simpsonville, SC (US)

(73) Assignee: **General Electric Company**, Schenectady, NY (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **13/276,713**

(22) Filed: **Oct. 19, 2011**

(65) **Prior Publication Data**

US 2013/0101806 A1 Apr. 25, 2013

(51) **Int. Cl.**

C23C 4/02 (2006.01)

F01D 5/14 (2006.01)

F01D 5/28 (2006.01)

B05D 3/10 (2006.01)

(52) **U.S. Cl.**

CPC . **C23C 4/02** (2013.01); **B05D 3/102** (2013.01);
F01D 5/14 (2013.01); **F01D 5/288** (2013.01);
F05D 2230/90 (2013.01)

USPC **427/309**; 427/307; 427/327; 427/330

(58) **Field of Classification Search**

USPC 427/307, 327, 328
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,574,924 A 4/1971 Dibble
3,627,444 A 12/1971 Lentz

3,638,464 A 2/1972 Winter et al.
3,646,471 A 2/1972 DeMent
3,732,031 A 5/1973 Bowling et al.
3,778,241 A 12/1973 Winter et al.
3,857,750 A 12/1974 Winter et al.
3,944,782 A 3/1976 Metcalfe et al.
3,988,913 A 11/1976 Metcalfe et al.
4,042,162 A 8/1977 Meginnis et al.
4,097,294 A 6/1978 Rice et al.

(Continued)

FOREIGN PATENT DOCUMENTS

EP 0448339 A1 9/1991
EP 0256790 B1 8/1992

(Continued)

OTHER PUBLICATIONS

Search Report and Written Opinion from EP Application No. 12179583.5 dated Jan. 30, 2013.



Primary Examiner — David Turocy

(74) *Attorney, Agent, or Firm* — Cantor Colburn LLP

(57) **ABSTRACT**

A method for adhering a coating to a substrate structure comprises selecting a substrate structure having an outer surface oriented substantially parallel to a direction of radial stress, modifying the outer surface to provide a textured region having steps to adhere a coating thereto, and applying a coating to extend over at least a portion of the textured region, wherein the steps are oriented substantially perpendicular to the direction of radial stress to resist deformation of the coating relative to the substrate structure. A rotating component comprises a substrate structure having an outer surface oriented substantially parallel to a direction of radial stress. The outer surface defines a textured region having steps to adhere a coating thereto, and a coating extends over at least a portion of the textured region. The steps are oriented substantially perpendicular to the direction of radial stress to resist creep.

16 Claims, 8 Drawing Sheets



(56)

References Cited

U.S. PATENT DOCUMENTS

4,188,811 A	2/1980	Brimm	6,913,186 B2	7/2005	Vyas
4,208,170 A	6/1980	Tucker et al.	6,923,623 B2	8/2005	Cleveland et al.
4,335,997 A	6/1982	Ewing et al.	6,941,973 B2	9/2005	Hehmann
4,411,730 A	10/1983	Fishter et al.	6,952,095 B1	10/2005	Goldfine et al.
4,589,176 A	5/1986	Rosman et al.	7,033,448 B2	4/2006	Groh et al.
4,605,452 A	8/1986	Gemma et al.	7,043,819 B1	5/2006	Arnold
4,659,288 A	4/1987	Clark et al.	7,094,444 B2	8/2006	Rigney et al.
4,802,823 A	2/1989	Decko et al.	7,163,136 B2	1/2007	Hempstead
4,889,355 A	12/1989	Trimble	7,207,869 B2	4/2007	James
4,932,147 A	6/1990	David	7,230,421 B2	6/2007	Goldfine et al.
4,986,949 A	1/1991	Trimble	7,247,000 B2	7/2007	Cahoon et al.
5,060,842 A	10/1991	Qureshi et al.	7,255,531 B2	8/2007	Ingistov
5,063,662 A	11/1991	Porter et al.	7,293,326 B2	11/2007	Hawkins et al.
5,083,371 A	1/1992	Leibfried et al.	7,441,331 B2	10/2008	Hudson et al.
5,158,733 A	10/1992	Trimble	7,487,641 B2	2/2009	Frechette et al.
5,160,822 A	11/1992	Aleshin	7,497,663 B2	3/2009	McRae et al.
5,176,499 A	1/1993	Damlis et al.	7,589,526 B2	9/2009	Goldfine et al.
5,193,314 A	3/1993	Wormley et al.	7,618,240 B2	11/2009	Saltman et al.
5,273,708 A	12/1993	Freeman	7,625,184 B2	12/2009	Jay et al.
5,356,264 A	10/1994	Watson et al.	7,632,072 B2	12/2009	Sheffield
5,419,971 A *	5/1995	Skelly et al. 428/612	7,637,010 B2	12/2009	Burgess et al.
5,465,780 A	11/1995	Muntner et al.	7,648,334 B2	1/2010	Hurst et al.
5,503,532 A	4/1996	Schilling	7,648,340 B2	1/2010	Sadler et al.
5,537,814 A	7/1996	Nastuk et al.	7,686,571 B1	3/2010	Matheny
5,545,003 A	8/1996	O'Connor et al.	7,709,057 B2	5/2010	Fusaro, Jr. et al.
5,584,663 A	12/1996	Schell et al.	7,722,329 B2	5/2010	Clarke
5,622,638 A	4/1997	Schell et al.	7,736,704 B2	6/2010	Chandra et al.
5,641,014 A	6/1997	O'Connor et al.	7,740,948 B1	6/2010	Alvin
5,643,474 A	7/1997	Sangeeta	7,741,576 B2	6/2010	Trimmer et al.
5,649,806 A	7/1997	Sricca et al.	7,762,534 B2	7/2010	Ouellette et al.
5,810,552 A	9/1998	Frasier	7,763,356 B2	7/2010	Berczik et al.
5,916,638 A	6/1999	Zajchowski et al.	7,771,160 B2	8/2010	Shi et al.
5,924,483 A	7/1999	Frasier	7,785,098 B1	8/2010	Appleby et al.
5,932,940 A	8/1999	Epstein et al.	7,841,834 B1 *	11/2010	Ryznic 416/224
5,998,755 A	12/1999	Zajchowski et al.	7,858,205 B2	12/2010	Allen et al.
6,049,978 A	4/2000	Arnold	7,862,262 B2	1/2011	Sasu et al.
6,071,363 A	6/2000	O'Connor et al.	7,910,225 B2	3/2011	Taylor
6,077,002 A	6/2000	Lowe	7,927,714 B2	4/2011	Carter et al.
6,139,303 A	10/2000	Reed et al.	7,980,052 B1	7/2011	Paulino
6,146,692 A	11/2000	Sangeeta et al.	7,981,520 B2	7/2011	Bewlay et al.
6,177,038 B1	1/2001	Reed et al.	7,993,704 B2	8/2011	Raybould et al.
6,199,746 B1	3/2001	Dupree et al.	2001/0008323 A1	7/2001	Reed et al.
6,206,642 B1	3/2001	Matheny et al.	2002/0076488 A1	6/2002	Park et al.
6,224,361 B1	5/2001	Reed et al.	2002/0174528 A1	11/2002	Prevey, III
6,244,327 B1	6/2001	Frasier	2003/0027495 A1	2/2003	Shaw
6,248,399 B1	6/2001	Hehmann	2003/0034379 A1	2/2003	Jackson et al.
6,251,315 B1	6/2001	Reed et al.	2003/0041801 A1	3/2003	Hehmann
6,255,000 B1	7/2001	O'Connor et al.	2003/0068222 A1	4/2003	Cunha et al.
6,287,080 B1	9/2001	Evans et al.	2003/0069321 A1	4/2003	Lin et al.
6,299,935 B1	10/2001	Park et al.	2003/0088980 A1	5/2003	Arnold
6,302,649 B1	10/2001	Mukira et al.	2003/0134040 A1	7/2003	Fusaro, Jr. et al.
6,329,633 B1	12/2001	Lamm et al.	2003/0170489 A1	9/2003	Allen et al.
6,331,217 B1	12/2001	Burke et al.	2003/0223861 A1	12/2003	Morrison et al.
6,354,799 B1	3/2002	Mukira et al.	2004/0009297 A1	1/2004	Fusaro, Jr. et al.
6,392,313 B1	5/2002	Epstein et al.	2004/0018299 A1	1/2004	Arnold et al.
6,394,750 B1	5/2002	Hiskes	2004/0031140 A1	2/2004	Arnold et al.
6,409,853 B1	6/2002	Thamboo et al.	2004/0035914 A1	2/2004	Hempstead
6,413,582 B1	7/2002	Park et al.	2004/0046003 A1	3/2004	Vyas
6,413,650 B1	7/2002	Dupree et al.	2004/0198852 A1	10/2004	Lin et al.
6,415,486 B1	7/2002	Prevey, III	2005/0031449 A1	2/2005	Cleveland et al.
6,454,536 B1	9/2002	Evans et al.	2005/0056354 A1	3/2005	Groh et al.
6,468,367 B1	10/2002	Mukira et al.	2005/0064146 A1	3/2005	Hollis et al.
6,490,899 B2	12/2002	Berthelet et al.	2005/0152805 A1	7/2005	Arnold et al.
6,511,630 B1	1/2003	Cartier et al.	2005/0186079 A1	8/2005	Ingistov
6,520,838 B1	2/2003	Shaw	2005/0221057 A1 *	10/2005	Hollis et al. 428/172
6,544,460 B2	4/2003	Reed et al.	2005/0241147 A1	11/2005	Arnold et al.
6,565,680 B1	5/2003	Jackson et al.	2005/0248339 A1	11/2005	Goldfine et al.
6,592,948 B1	7/2003	Fusaro, Jr. et al.	2005/0268463 A1	12/2005	Ouellette et al.
6,607,355 B2	8/2003	Cunha et al.	2006/0010871 A1	1/2006	Frechette et al.
6,622,570 B1	9/2003	Prevey, III	2006/0021184 A1	2/2006	Hawkins et al.
6,696,176 B2	2/2004	Allen et al.	2006/0029723 A1	2/2006	Rigney et al.
6,709,230 B2	3/2004	Morrison et al.	2006/0039788 A1	2/2006	Arnold et al.
6,753,634 B2	6/2004	Rehder	2006/0041448 A1	2/2006	Patterson et al.
6,846,574 B2 *	1/2005	Subramanian 428/595	2006/0042084 A1	3/2006	Hudson et al.
6,884,507 B2	4/2005	Lin et al.	2006/0082366 A1	4/2006	Goldfine et al.
			2006/0189265 A1	8/2006	James
			2006/0200963 A1	9/2006	Lutz
			2006/0248718 A1	11/2006	Szela et al.
			2006/0260125 A1	11/2006	Arnold et al.

(56)

References Cited**U.S. PATENT DOCUMENTS**

2007/0124933	A1	6/2007	Burgess et al.
2007/0154316	A1	7/2007	Clarke
2007/0154318	A1	7/2007	Saltman et al.
2007/0183895	A1	8/2007	Sheffield
2007/0183896	A1	8/2007	Jay et al.
2007/0183897	A1	8/2007	Sadler et al.
2007/0183898	A1	8/2007	Hurst et al.
2007/0224401	A1	9/2007	Telander
2007/0236214	A1	10/2007	Goldfine et al.
2008/0011810	A1	1/2008	Burford
2008/0028607	A1	2/2008	Lamphere et al.
2008/0101959	A1	5/2008	McRae et al.
2008/0127450	A1	6/2008	Hawkins et al.
2008/0206000	A1	8/2008	Sasu et al.
2008/0223099	A1	9/2008	David
2008/0247635	A1	10/2008	Davis et al.
2008/0247636	A1	10/2008	Davis et al.
2008/0277384	A1	11/2008	Trimmer et al.
2008/0298975	A1	12/2008	James et al.
2009/0142221	A1	6/2009	Strangman
2009/0315540	A1	12/2009	Goldfine et al.
2009/0324401	A1 *	12/2009	Calla 415/200
2010/0012004	A1	1/2010	Telander
2010/0104433	A1	4/2010	Shi et al.
2010/0119871	A1	5/2010	Feng et al.
2010/0172760	A1	7/2010	Ammann
2010/0175218	A1	7/2010	Hawkins et al.
2010/0285269	A1	11/2010	Telander

FOREIGN PATENT DOCUMENTS

EP	0520714	A1	12/1992
EP	0431019	B1	6/1994
EP	0475882	B1	3/1995
EP	0927773	A2	7/1999
EP	1002615	A2	5/2000
EP	1065296	A1	1/2001
EP	1091013	A1	4/2001
EP	1091021	A1	4/2001
EP	1225324	A2	7/2002
EP	0750957	B1	3/2003
EP	1302628	A2	4/2003
EP	0925844	B1	7/2003
EP	1367223	A2	12/2003
EP	1002619	B1	7/2004
EP	1447208	A2	8/2004
EP	1049562	B1	2/2005

EP	1505255	A2	2/2005
EP	1010776	B1	4/2005
EP	1533396	A2	5/2005
EP	0920575	B1	6/2005
EP	1090711	B1	8/2005
EP	1143106	B1	8/2005
EP	1342803	B1	8/2005
EP	1514632	B1	2/2006
EP	0992310	B1	5/2006
EP	1090710	B1	5/2006
EP	1261455	B1	8/2006
EP	1236534	B1	9/2006
EP	1002617	B1	10/2006
EP	1840239	A1	10/2007
EP	1854903	A1 *	11/2007
EP	1890010	A2	2/2008
EP	1002616	B1	5/2008
EP	1074331	B1	6/2008
EP	1721697	B1	8/2008
EP	1002618	B1	10/2008
EP	1714741	B1	10/2008
EP	1629938	B1	3/2009
EP	1705338	B1	5/2009
EP	1792680	B1	10/2009
EP	1510279	B1	2/2010
EP	1743731	B1	6/2010
EP	2204544	A2	7/2010
EP	2022587	B1	10/2010
EP	2275645	A2	1/2011
GB	1378009	A	12/1974
GB	2272453	A *	5/1994
WO	WO89/04789	A1	6/1989
WO	WO90/02479	A2	3/1990
WO	WO91/12111	A1	8/1991
WO	WO98/02643	A1	1/1998
WO	WO99/21680	A2	5/1999
WO	WO00/17490	A2	3/2000
WO	WO01/22076	A1	3/2001
WO	WO01/64397	A2	9/2001
WO	WO01/64398	A2	9/2001
WO	WO2005/061854	A1	7/2005
WO	WO2005/075894	A1	8/2005
WO	WO2006/015309	A2	2/2006
WO	WO2007/085912	A2	8/2007
WO	WO2007/093851	A2	8/2007
WO	WO2007/125382	A2	11/2007
WO	WO2007/141596	A2	12/2007
WO	WO2008/035135	A2	3/2008
WO	WO2008/090394	A2	7/2008
WO	WO2010/036801	A2	4/2010

* cited by examiner

FIG. 1




FIG. 2




FIG. 3

300




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13





FIG. 14



1

METHOD FOR ADHERING A COATING TO A SUBSTRATE STRUCTURE

FEDERAL RESEARCH STATEMENT

This invention was made with Government support under Contract No. DE-FC26-05NT42643, awarded by the US Department of Energy (DOE). The Government has certain rights in this invention.

BACKGROUND OF THE INVENTION

The subject matter disclosed herein relates to systems and methods for adhering coatings to substrate structures and more particularly to a method for reducing inelastic deformation of coatings applied to rotating components.

In rotating machines, such as turbine engines, components often include a coating to achieve a desirable performance, durability and/or life attribute of the components. For example, coatings may be configured to resist oxidation, erosion, heat transfer, contamination, and/or other processes. Such components typically comprise a substrate structure configured to satisfy a first set of design objectives and a coating that is bonded to an outer surface of the substrate structure, with the coating being configured to satisfy a second set of design objectives. The design objectives for a substrate structure may address mass limitations, structural requirements, and aerodynamic shape considerations while the design objectives for a coating may address different considerations such as adhesion to, and protection of, the substrate structure. Thus, the substrate structure typically, though not exclusively, comprises a different material than that of the coating. As a result, a rate of thermal expansion for the substrate structure may differ from a rate of thermal expansion for the coating, causing stresses at the bonds between the substrate structure and the coating.

In rotating machines, such as turbine engines, rotating machinery may be subjected to large radial accelerations, causing sustained high forces within their subject components. In addition, some components, such as turbine blades, may also be subjected to high temperatures. As a result, bonds between the substrate structure and the coating may be challenged. In some cases, the stresses applied to coated components can cause viscous or inelastic deformations in the coatings relative to the substrate structures (i.e., creep), with such deformations typically occurring in the direction of the loads. In rotating components, the direction of the loads is typically the radial direction.

Therefore, those skilled in the art seek new systems and methods for reducing inelastic deformation of coatings on rotating components.

BRIEF DESCRIPTION OF THE INVENTION

According to one aspect of the invention, a method for adhering a coating to a substrate structure comprises selecting a substrate structure having an outer surface oriented substantially approximately parallel to a direction of radial stress, modifying the outer surface to provide a textured region having steps to adhere a coating thereto, and applying a coating to extend over at least a portion of the textured region and to adhere to the outer surface, wherein the steps are oriented substantially perpendicular to the direction of radial stress so as to resist deformation of the coating relative to the substrate structure.

According to another aspect of the invention, a rotating component comprises a substrate structure having an outer

2

surface oriented substantially approximately parallel to a direction of radial stress. The outer surface defines a textured region having steps to adhere a coating thereto, and a coating extends over at least a portion of the textured region and adheres to the outer surface. The steps are oriented substantially perpendicular to the direction of radial stress so as to resist deformation of the coating relative to the substrate structure.

These and other advantages and features will become more apparent from the following description taken in conjunction with the drawings.

BRIEF DESCRIPTION OF THE DRAWING

The subject matter, which is regarded as the invention, is particularly pointed out and distinctly claimed in the claims at the conclusion of the specification. The foregoing and other features and advantages of the invention are apparent from the following detailed description taken in conjunction with the accompanying drawings in which:

FIG. 1 is a drawing of an exemplary substrate structure ready to be modified so as to include steps in accordance with the invention;

FIG. 2 is a drawing of an exemplary substrate structure that has been modified so as to include steps in accordance with the invention;

FIG. 3 is a drawing of an exemplary substrate structure that has been modified so as to include steps in accordance with the invention;

FIG. 4 is an enlarged drawing of a step as shown in FIG. 3;

FIG. 5 is a drawing of an exemplary substrate structure that has been modified so as to include steps in accordance with the invention;

FIG. 6 is an enlarged drawing of a step as shown in FIG. 5;

FIG. 7 is a drawing of an exemplary substrate structure that has been modified so as to include steps in accordance with the invention;

FIG. 8 is an enlarged drawing of a step as shown in FIG. 7;

FIG. 9 is a drawing of an exemplary substrate structure that has been modified so as to include steps in accordance with the invention;

FIG. 10 is an enlarged drawing of a step as shown in FIG. 9;

FIG. 11 is a drawing of an exemplary substrate structure that has been modified so as to include steps in accordance with the invention;

FIG. 12 is a drawing of an exemplary coated substrate structure that has been modified so as to include steps and a coating in accordance with the invention;

FIG. 13 is a drawing of an exemplary coated substrate structure that has been modified so as to include steps and a coating in accordance with the invention; and

FIG. 14 is a drawing of an exemplary coated substrate structure that has been modified so as to include steps and a coating in accordance with the invention.

The detailed description explains embodiments of the invention, together with advantages and features, by way of example with reference to the drawings.

DETAILED DESCRIPTION OF THE INVENTION

FIG. 1 shows an exemplary substrate structure **100** configured to operate as a turbine blade in a gas turbine engine. Accordingly, substrate structure **100** includes an airfoil section **110** oriented along a radial axis **120** and coupled to a blade root **135** configured with a dovetail shape for retention by a turbine disk. In accordance with aerodynamic consider-

3

ations, airfoil section **110** includes a thickened leading edge **112** and a relatively thin trailing edge **114**. Between leading edge **112** and trailing edge **114**, airfoil section **110** includes an outer surface **116** having a concave pressure side **117** and a convex suction side **118**. Substrate structure **100** also includes an inner shroud **130** positioned between airfoil section **110** and blade root **135**. Shroud **130** is oriented approximately perpendicular to radial axis **120** (i.e., in a circumferential orientation). In an exemplary embodiment, substrate structure **100** may comprise any material suitable for the environment and duty cycle in which substrate structure will perform. For example, substrate structure **100** may comprise steel, nickel, titanium, aluminum, chromium, molybdenum, and composite materials including those with carbon and/or silicon carbide fibers.

As shown in FIG. 2, similarly to the substrate structure **100** depicted in FIG. 1, an exemplary substrate structure **200** includes an airfoil section **210** oriented along a radial axis **220** and coupled to a blade root **235** configured with a dovetail shape for retention by a turbine disk. Substrate structure **200** also includes an inner shroud **230** positioned between airfoil section **210** and blade root **235**, and shroud **230** is oriented approximately perpendicular to radial axis **220** (i.e., in a circumferential orientation). Notably, an outer surface **216** of airfoil section **210** defines a series of steps **240** which form a textured region **242** covering, in this embodiment, the entirety of airfoil section **210** on both its concave pressure side **217** and its convex suction side **218**. Steps **240** are oriented substantially approximately parallel to one another and substantially perpendicular to the radial axis **220** of the substrate structure. In this embodiment, steps **240** extend from the leading edge **212** to the trailing edge **214** in an orientation that is also substantially approximately parallel to a direction of flow of a working fluid of the gas turbine engine in which the substrate structure **200** is to operate. Accordingly, in embodiments where an exterior surface of an applied coating reveals the steps of the textured region, the contours will be oriented along the streamlines of the flow, inducing less disruption than if the contours were oriented at an oblique angle to the streamlines.

It should be noted that, as used herein, the orientation of the radial axis **220** is defined by the orientation of the maximum stresses imposed on substrate structure **200** in operation, as installed in a turbine engine and as retained by a rotating turbine disk. Accordingly, as the substrate structure **200** rotates, the radial stresses imposed on the substrate structure **200** are, by definition, oriented along the radial axis **220**. Since the outer surface **216** of substrate structure **200** is oriented substantially approximately parallel to a direction of radial stress when viewed as a whole, a bond between the outer surface **216** and a coating applied over the outer surface is generally and primarily subjected to a shear stress. Thus, in the absence of steps **240**, the ability of the bond to resist creep is primarily dependent upon the strength of the bond in shear.

In an exemplary embodiment of the invention, however, since steps **240** are oriented substantially perpendicular to the radial axis **220**, and thus the direction of the radial stresses (i.e., the direction of maximum loading), the steps **240** provide a mechanism for assisting a coating to resist creep relative to the steps **240** and the textured region **242** they define on the outer surface **216** of substrate structure **200**. To accomplish this, the steps **240** (including their shapes, configurations, depths, orientations, and spacing) are configured to provide a series of buttresses (i.e., bearing surfaces) against which the coating may bear. As a result, the coating may resist

4

creep, at least locally adjacent to the bearing surfaces, through its strength in compression, thereby enabling the coating to better resist creep.

In an exemplary embodiment, the steps **240** may be shallow, square-edged, and/or recursive, and due to the substantially approximately parallel orientation of steps **240**, the textured region may bear a ruled appearance. The dimensions of the steps **240** are typically sufficiently great in magnitude that the textured region provides a stepped surface texture rather than merely a stepped grain structure, and the steps **240** thus provide a means for resisting viscous or inelastic deformation (i.e., creep) of any coating (such as a protective coating) that may be applied over or otherwise adhered to textured region **242**. Accordingly, the stepped surface of the textured region **242** acts as a self-bonding substrate to which a coating may be adhered.

To form the steps **240**, the outer surface **216** may be machined before application of a coating over the textured region **242** of the substrate structure **200**. Alternatively other methods known in the art may be used including mechanical grinding, laser cutting, chemical etching, burnishing, embossing, stamping, cold forming, casting, molding, or forging. In an exemplary embodiment, tooling used to form the steps **240**, such as a mold for casting or a mask for chemical etching or a tool for machining or embossing or stamping, is shaped to be complementary to the contours of the steps **240**. In another exemplary embodiment, steps **240** are formed through a series of machining and/or laser etching passes. Therefore, another exemplary tool is shaped to be complementary to a single step.

After a coating is applied over the textured region **242**, the coating may be configured to form a relatively uniform and smooth outer surface that is substantially free from steps or other discontinuities. Alternatively, an exterior surface of an applied coating may be configured so as to reveal the steps of the textured region, and the contours may be oriented to be aligned substantially with streamlines of the flow of the working fluid passing over the component. Exemplary coatings may be ceramic or metallic (e.g., containing nickel) and may be selected and/or configured so as to resist oxidation, erosion, heat transfer, and/or contamination that might otherwise impact the performance and/or life of the substrate structure, while bonding effectively to substrate structure **200**.

As shown in FIG. 3, a substrate structure **300** is disposed along a radial axis **320** such that an outer surface **316** of substrate structure **300** is oriented substantially approximately parallel to radial axis **320** and includes a series of steps **340** that are oriented substantially approximately parallel to one another and substantially perpendicular to the radial axis **320**. A coating **350** extends over the steps **340** that form the textured region of the outer surface **316**, and the coating **350** is bonded or adheres to the outer surface **316**. In this embodiment, the coating is configured to form a relatively uniform and smooth outer surface that is substantially free from steps or other discontinuities. It should be appreciated, however, that alternative embodiments are possible wherein an applied coating is configured to reveal the steps of the textured region. In some embodiments, the contours may also be oriented along the streamlines of the flow, inducing less disruption than if the contours were oriented at an oblique angle to the streamlines. These streamlines may or may not be oriented in parallel to the steps **340**.

As shown in FIG. 4, which depicts an enlarged section of the substrate structure **300** of FIG. 3, each step **340** includes a step nose **345** and a step knee **346**. Step nose **345** is a sharp corner defined by the intersection of shear surface **343** and bearing surface **344**. In this embodiment, bearing surface **344**

5

is approximately (e.g., within 15 degrees of being) perpendicular to radial axis 320, and shear surface 343 is approximately (e.g., within 15 degrees of being) parallel to radial axis 320. Accordingly, shear surface 343 and bearing surface 344 meet at step nose 345 where they form an approximate (e.g., between about 70 degrees and 110 degrees) 90 degree angle relative to one another. At step knee 346, which is a sharp inside corner, bearing surface 344 meets another shear surface 348 to form the step knee 346, which has a knee angle 342 of approximately about 90 degrees.

In operation with a coating applied over steps 340, and with a radial load applied to the coating, the coating may bear against the bearing surface 344 so as to resist creep. Therefore, the coating can rely upon its internal strength in compression while pressing against bearing surface 344 (rather than merely the shear strength of its bond with a surface such as the shear surfaces 343, 348) to resist creep relative to substrate structure 300. In an exemplary embodiment, the dimensions of the bearing wall are selected so as to achieve a desirable balance among design considerations including a rate of heat transfer through the coating, uniformity of the outer surface of the coating, mechanical integrity of the substrate structure and the coating, resistance to oxidation, resistance to erosion, resistance to contamination, and/or adhesion of the coating to the substrate structure, all at operational levels. The coating may be deposited at a thickness characteristic of a process selected from spraying, sintering, flame spraying, vapor deposition, sputtering, and electro-less coating.

As shown in FIG. 5, a substrate structure 400 is disposed along a radial axis 420 such that an outer surface 416 is oriented substantially approximately parallel to radial axis 420 and includes a series of steps 440 that are oriented substantially approximately parallel to one another and substantially perpendicular to the radial axis 420. As shown in FIG. 6, which depicts an enlarged section of the substrate structure 400 of FIG. 5, each step 440 includes a step nose 445 and a step knee 446. Step nose 445 is a sharp corner defined by the intersection of shear surface 443 and bearing surface 444. In this embodiment, bearing surface 444 is oriented at a relatively steep angle (e.g., approximately 45 degrees from perpendicular) relative to radial axis 420. Shear surface 443 is approximately (e.g., within 15 degrees of being) parallel to radial axis 420. Accordingly, shear surface 443 and bearing surface 444 meet at step nose 445 where they form an approximate 45 degree angle relative to one another.

At step knee 446, which is a sharp inside corner, bearing surface 444 meets another shear surface 448 to form the step knee 446, which has a knee angle 442 of approximately about 45 degrees. In operation with a coating applied over steps 440, and with a radial load applied to the coating, the coating may bear against the bearing surface 444 so as to resist creep. Therefore, the coating can rely upon its internal strength in compression while pressing against bearing surface 444 (rather than merely the shear strength of its bond with a surface such as the shear surfaces 443, 448) to resist creep relative to substrate structure 400.

As shown in FIG. 7, a substrate structure 500 is disposed along a radial axis 520 such that an outer surface 516 is oriented substantially approximately parallel to radial axis 520 and includes a series of steps 540 that are oriented substantially approximately parallel to one another and substantially perpendicular to the radial axis 520. As shown in FIG. 8, which depicts an enlarged section of the substrate structure 500 of FIG. 7, each step 540 includes a step nose 545 and a step knee 546. Step nose 545 is a sharp corner defined by the intersection of shear surface 543 and bearing surface 544. In

6

this embodiment, bearing surface 544 is approximately (e.g., within 15 degrees of being) perpendicular to radial axis 520, and shear surface 543 is approximately (e.g., within 15 degrees of being) parallel to radial axis 520. Accordingly, shear surface 543 and bearing surface 544 meet at step nose 545 where they form an approximate 90 degree angle relative to one another.

At step knee 546, which is a continuous inside corner, bearing surface 544 is gradually contoured to meet a similarly gradually contoured shear surface 548 to form the continuous step knee 546, which has a knee angle 542 of approximately about 90 degrees. In operation with a coating applied over steps 540, and with a radial load applied to the coating, the coating may bear against the bearing surface 544 so as to resist creep while reducing the potential for stress concentrations and discontinuities associated with a more sharply defined inside corner. Therefore, the coating can rely upon its internal strength in compression while pressing against bearing surface 544 (rather than merely the shear strength of its bond with a surface such as the shear surfaces 543, 548) to resist creep relative to substrate structure 500.

As shown in FIG. 9, a substrate structure 600 is disposed along a radial axis 620 such that an outer surface 616 is oriented substantially approximately parallel to radial axis 620 and includes a series of steps 640 that are oriented substantially approximately parallel to one another and substantially perpendicular to the radial axis 620. As shown in FIG. 10, which depicts an enlarged section of the substrate structure 600 of FIG. 9, each step 640 includes a step nose 645 and a step knee 646. Step nose 645 is a sharp corner defined by the intersection of shear surface 643 and bearing surface 644. In this embodiment, bearing surface 644 is approximately (e.g., within 15 degrees of being) perpendicular to radial axis 620, and shear surface 643 is approximately (e.g., within 15 degrees of being) parallel to radial axis 620. Accordingly, shear surface 643 and bearing surface 644 meet at step nose 645 where they form an approximate 90 degree angle relative to one another.

At step knee 646, which, as shown in FIG. 10, is a continuous inside corner, bearing surface 644 meets another shear surface 648 to form the step knee 646, which has a knee angle 642 of approximately about 90 degrees. It should be appreciated, however, that the profile of a step 640 may also be configured such that bearing surface 644 is substantially perpendicular to shear surface 643 while step knee 646 defines a discontinuous, sharp inside corner of approximately about 90 degrees, and a profile of shear surface 648 is substantially straight, oriented substantially parallel to shear surface 643. In operation with a coating applied over steps 640, and with a radial load applied to the coating, the coating may bear against the bearing surface 644 so as to resist creep. Therefore, the coating can rely upon its internal strength in compression while pressing against bearing surface 644 (rather than merely the shear strength of its bond with a surface such as the shear surfaces 643, 648) to resist creep relative to substrate structure 600.

As shown in FIG. 11, a turbine assembly 700 comprises a substrate structure 780 in the form of a turbine disk configured for retaining a plurality of turbine blades 710. An outer surface of substrate structure 780 defines a series of steps 740 which form a textured region 742 covering, in this embodiment, a substantial portion of substrate structure 780. Steps 740 are oriented substantially approximately parallel to one another and substantially perpendicular to a radial axis 720 of the substrate structure 780. Put another way, steps 740 are oriented substantially along a circumferential direction of the

7

substrate structure **780** so as to resist creep relative to substrate structure **780** due to stresses oriented in the radial direction.

FIG. **12** shows a cutaway of an exemplary substrate structure **1280** that has been modified so as to include steps **1240** and has had a coating **1290** applied so as to cover the steps **1240** and to produce a desirable exterior surface profile and finish. As one skilled in the art will appreciate, coating **1290** and substrate structure **1280** are selected and configured so as to meet specific design criteria and mission requirements of their particular application. For example, where a substrate structure **1280** is to be installed in a gas turbine engine, substrate structure **1280** is selected and configured so as to satisfy structural and/or other requirements that are associated with that installation, while coating **1290** is selected and configured so as to provide qualities such as protective qualities to the coated substrate. These qualities may qualities such as, but not limited to, thermal resistance or conductivity, oxidation resistance, erosion resistance, friction resistance or enhancement, surface tension, material strength, hardness, and permeation resistance (i.e., hermetic sealing). Similarly, FIG. **13** shows a cutaway drawing of another exemplary substrate structure **1380** that has been modified so as to include steps **1340** and has had a coating **1390** applied so as to cover the steps **1340** and produce a desirable external surface profile and finish. FIG. **14** shows another cutaway drawing of another exemplary substrate structure **1480** that has been modified so as to include steps **1440** and that has had a coating **1490** applied so as to cover the steps **1440**.

Accordingly, the invention provides systems and methods for reducing inelastic deformation of coatings on rotating components that operate at sufficiently high rotations and temperatures such that creep is a concern. Such components include, without limitation, turbine airfoils and disks. Thus, the invention provides a system and method for reducing creep on coatings, such as thermal barrier coatings, and/or oxidation resistant coatings applied to turbine blades/buckets in aviation and energy applications where gas path temperatures often exceed 2000 degrees F. Accordingly, the invention can enable substantial improvements in the durability and service life of rotating turbo machine components. The invention may also enable rotating components to operate at reduced levels of cooling flow, resulting in improvements in cycle efficiencies and power production.

While the invention has been described in detail in connection with only a limited number of embodiments, it should be readily understood that the invention is not limited to such disclosed embodiments. Rather, the invention can be modified to incorporate any number of variations, alterations, substitutions or equivalent arrangements not heretofore described, but which are commensurate with the spirit and scope of the invention. Additionally, while various embodiments of the invention have been described, it is to be understood that aspects of the invention may include only some of the described embodiments. Accordingly, the invention is not to be seen as limited by the foregoing description, but is only limited by the scope of the appended claims.

The invention claimed is:

1. A method for adhering a coating to a substrate structure, the method comprising:

selecting a substrate structure having an outer surface oriented substantially parallel to a direction of radial stress; modifying an entirety of the outer surface to provide a textured region having steps to adhere a coating thereto; and applying a coating to extend over at least a portion of the textured region and to adhere to the outer surface;

8

wherein the modifying of the outer surface comprises forming each of the steps to define a nose at which first ends of shear and bearing surfaces meet to define a first angle and a knee at which second ends of the shear and bearing surfaces meet to define a second angle oppositely oriented relative to the first angle,

the shear surface of each step being substantially straight along an entirety thereof and parallel with each of the respective shear surfaces of the other steps, the bearing surface of each step being curved along an entirety thereof and parallel with each of the respective bearing surfaces of the other steps such that corresponding portions of each of the steps are oriented in parallel with one another and each of the steps are oriented approximately perpendicular to the direction of radial stress so as to resist deformation of the coating relative to the substrate structure.

2. A method as described in claim **1**, further comprising orienting the steps approximately along a circumferential direction of the substrate structure.

3. A method as described in claim **1**, further comprising forming each of the steps so as to define the bearing surface against which a coating may bear so as to resist creep through compression of the coating.

4. A method as described in claim **3**, further comprising orienting the bearing surface within approximately 15 degrees relative to perpendicularity with respect to the direction of radial stress.

5. A method as described in claim **3**, further comprising orienting the bearing surface so as to form an angle that is less than about 90 degrees relative to the direction of radial stress.

6. A method as described in claim **3**, further comprising orienting the bearing surface so as to form an angle that is between about 90 degrees and about 45 degrees relative to the direction of radial stress.

7. A method as described in claim **3**, further comprising orienting the bearing surface approximately about 45 degrees relative to the direction of radial stress.

8. A method as described in claim **1**, further comprising forming each of the steps so as to define a discontinuous knee including a secondary shear surface recessed from the shear surface.

9. A method as described in claim **1**;

wherein said applying a coating is performed such that said coating adheres directly to the outer surface;

further comprising depositing the coating at a thickness characteristic of a process selected from spraying, sintering, flame spraying, vapor deposition, sputtering, and electro-less coating.

10. A method as described in claim **1**, wherein the substrate structure is a turbine airfoil.

11. A method as described in claim **1**, wherein the substrate structure is a turbine disk.

12. A method as described in claim **1**, wherein the modifying comprises machining the outer surface.

13. A method as described in claim **1**, wherein the modifying comprises one or more of grinding, laser cutting, chemical etching, burnishing, embossing, stamping, cold forming, casting, molding or forging the outer surface.

14. A method for adhering a coating to a substrate structure, the method comprising:

selecting a substrate structure having an outer surface oriented substantially parallel to a direction of radial stress; modifying an entirety of the outer surface to provide a textured region having steps to adhere a coating thereto, the modifying comprising forming each of the steps to define a nose at which first ends of shear and bearing

9

surfaces meet to define a first angle and a knee at which second ends of the shear and bearing surfaces meet to define a second angle, which is oppositely oriented relative to the first angle; and

applying a coating to extend over at least a portion of the textured region and to adhere to the outer surface, wherein the steps are oriented approximately perpendicular to the direction of radial stress so as to resist deformation of the coating relative to the substrate structure and the first and second angles are acute and of substantially equal magnitude such that the nose overhangs the knee of each step relative to a direction defined perpendicularly with respect to the direction of radial stress.

15. The method according to claim 14, wherein the steps are parallel and each of the first and second angles of each of the steps are acute and of substantially equal magnitude.

16. A method for adhering a coating to a substrate structure, the method comprising:

selecting a substrate structure having an outer surface oriented substantially parallel to a direction of radial stress;

10

modifying an entirety of the outer surface to provide a textured region having grooves to adhere a coating thereto, the modifying comprising forming each of the grooves to define a nose at which first ends of shear and bearing surfaces meet to define a first angle and a knee at which second ends of the shear and bearing surfaces meet to define a second angle, which is oppositely oriented relative to the first angle; and

applying a coating to extend over at least a portion of the textured region and to adhere to the outer surface;

wherein the shear surface of each step is substantially straight along an entirety thereof and parallel with each of the respective shear surfaces of the other steps, the bearing surface of each step is curved along an entirety thereof and parallel with each of the respective bearing surfaces of the other steps and the steps are oriented approximately perpendicular to the direction of radial stress so as to resist deformation of the coating relative to the substrate structure.

* * * * *