

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(10) International Publication Number
WO 2012/143023 A1

(43) International Publication Date
26 October 2012 (26.10.2012)

- (51) International Patent Classification:
C08F 10/06 (2006.01)
- (21) International Application Number:
PCT/EP2011/005368
- (22) International Filing Date:
24 October 2011 (24.10.2011)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
11003388.3 21 April 2011 (21.04.2011) EP
- (71) Applicant (for all designated States except US):
BOREALIS AG [AT/AT]; IZD Tower, Wagramerstrasse
17-19, A-1220 Wien (AT).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **KOCK, Cornelia**
[AT/AT]; Strausstrasse 6, A-4055 Pucking (AT).
DOSHEV, Petar [BG/AT]; Am Herzog Wilhelm Weg 9,
Top II, A-4040 Linz (AT).
- (74) Agent: **SCHINDELE, Claus**; Kador & Partner, Corneli-
usstrasse 15, 80469 München (DE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: POLYPROPYLENE HOMOPOLYMERS WITH HIGH HEAT DEFLECTION TEMPERATURE, HIGH STIFFNESS AND FLOWABILITY

(57) Abstract: The invention relates to a polypropylene composition showing a high melt flow rate and simultaneously high stiffness and a process for the production thereof. The invention further relates to a material comprising the inventive polypropylene.



WO 2012/143023 A1

Polypropylene homopolymers with high heat deflection temperature, high stiffness and flowability

The present invention relates to polypropylene compositions with very high melt flow rate and a process for producing the same. The present invention is further concerned with materials comprising polypropylene compositions of very high melt flow rate and use of such very high melt flow rate polypropylene compositions.

Background

The need for polypropylene homopolymers with excellent stiffness at high flowability is constantly increasing as down-gauging and light-weighting become more important with the need for saving energy resources. High flowability polypropylenes are typically used in moulding and particularly the automotive business where injection moulding is the preferred conversion-process. Especially for glass fibre applications high flow homopolymer with good mechanical properties and high thermal stability is required.

The production of ultra high MFR polypropylene homopolymers may be achieved by controlling the reaction conditions such that a fraction of molecules having relatively short chains is obtained. However, increasing the fraction of molecules having relatively short chains is detrimental to impact strength. Another problem makes a solution even more complex. Higher stiffness of polypropylene is conventionally accompanied by higher shrinkage. Shrinkage, being a measure for three-dimensional stability in moulding, is related with the applicability for moulding applications.

From a process perspective, the provision of polypropylene having a high flowability and simultaneously high stiffness is challenging. Increasing the hydrogen concentration in the polymerization reactor can result in considerably high amount of amorphous material limiting crystallinity and insofar stiffness. A known concept of overcoming these limitations is the use of external donors. External donors increase the hydrogen response and can significantly increase the production rate to crystalline material. However, donors resulting in a better

hydrogen response yield materials with lower isotacticity, and insofar lower stiffness.

From a general perspective, stiffness is mainly influenced by the crystal structure which is mainly influenced by chain regularity and further by molecular weight. The crystal structure is inter alia reflected by the lamella thickness being directly measurable by stepwise isothermal segregation technique (SIST). Stepwise isothermal segregation technique (SIST) is a stepwise fractioning by crystallization when cooling the molten sample.

Heterophasic polypropylenes having a matrix phase and a dispersed rubber phase also have stiffness values far below the desired range originating from the dispersed phase. EP 2174980 discloses such materials produced by a triple reactor cascade.

Similar limitations as to stiffness also hold for bimodal polypropylene random copolymers such as disclosed in WO2011/000557.

US 2004/0116629 discloses an ultra high melt flow polypropylene resin obtained by either an internal diether based donor such as Mitsui RK-100 and Mitsui RH-200 or an external donor such cyclohexylmethyl dimethoxysilane (CMDs), dicyclopentyl dimethoxysilane (CPDS), diisopropyl dimethoxysilane (DIDS), cyclohexylisopropyl dimethoxysilane (CIDS), and di-t-butyl dimethoxysilane (DTDS). Though the obtained polypropylenes have relatively high crystallinity, the mechanical properties still need to be improved.

Thus, there is still the need for a polypropylene having high stiffness at a given very high melt flow rate and additionally acceptable good shrinkage values.

Summary of the Invention

The present invention is based on the surprising finding that these objects can be achieved when the amount of lamellas having a thickness within a range of 24.2 to 84.6 nm is above 40 % in a SIST measurement. The present invention is further based on the surprising finding that the negative side effects of the use of external donors yielding higher hydrogen response can be overcome by incorporating a relatively high amount of high molecular weight material having

a comparatively moderate molecular weight. In yet another aspect, it has been surprisingly found that the limitations of conventional ultra high melt flow polypropylene compositions can be overcome when the high molecular weight fraction is present in a relatively high amount but has a relatively moderate molecular weight.

The present invention insofar provides

a polypropylene composition comprising a polypropylene base resin, the polypropylene base resin having

lamellas of a thickness from 24.2 nm to 84.6 nm in an amount of at least 40% when measured by stepwise isothermal segregation technique (SIST); and

a molecular weight distribution broadness M_w/M_n , as calculated from gel permeation chromatography, of at least 5, and

the polypropylene composition having an MFR_2 measured according to ISO 1133 (230 °C, 2.16 kg load) of at least 50 g/10 min;


and a tensile modulus of 2000 MPa or higher when measured according to ISO 527-2 using injection moulded test specimens as described in EN ISO 1873-2 (dog bone shape, 4 mm thickness).

The present invention further provides a polypropylene composition

having a tensile modulus of 2000 MPa or higher when measured according to ISO 527-2 using injection moulded test specimens as described in EN ISO 1873-2 (dog bone shape, 4 mm thickness)

obtainable by a process comprising,

polymerizing propylene in the presence of a catalyst system including a Ziegler Natta catalyst and either diethylaminomethyl triethoxysilane (donor U)



or dicyclopentanedimethoxysilane (DCPDMS, donor D) as an external donor, the mole ratio of Al/external donor being in the range of 0.5 to 50 whereby,

- (i) a first intermediate polypropylene with an MFR₂ in the range of 200 to 2000 g/10 min (ISO 1133; 230 °C, 2.16 kg load) is formed in a first reaction zone;
- (ii) the first intermediate polypropylene is further polymerized in a second reaction zone to form a second intermediate polypropylene having an MFR₂ in the range of 80 to 800 g/10min (ISO 1133; 230 °C, 2.16 kg load);
- (iii) the second intermediate polypropylene is further polymerized in a third reaction zone to form the third intermediate polypropylene having an MFR₂ in the range of 50 to 300 g/10min (ISO 1133; 230 °C, 2.16 kg load);

and optionally compounding the third intermediate polypropylene to form the polypropylene composition having an MFR₂ in the range of 50 to 300 g/10min (ISO 1133; 230 °C, 2.16 kg load).

In yet another aspect, the present invention provides a material comprising the polypropylene composition according to the present invention and a filler.

The present invention is further concerned with the use of the inventive polypropylene composition for increasing the temperature resistance.

Definitions

Polypropylene composition denotes a composition consisting of at least 98.0 wt.-% polypropylene base resin and up to 2.0 wt.-% additives. Preferably the additives are selected from antioxidants, acid scavengers, UV stabilizers, α -nucleating agents, slip agents, antistatic agents and combinations thereof.

Polypropylene base resin denotes all polypropylenes in the polypropylene compositions.

The amount of a certain lamella thickness range in percent is the relative percentage of the lamella thicknesses within this range with respect to all lamella thicknesses within the sample.

Catalyst system denotes the combination of the catalyst and the co-catalyst.

Reaction zone is a locally delimited zone where the reaction takes place. Usually each reaction zone will be formed by one reactor.

Increasing the temperature resistance shall mean an increase as to the temperature resistance either over a base material or, when the inventive polypropylene composition substitutes another composition.

Detailed Description

It has been surprisingly found that a relatively high amount of above 40 % of lamellas having a thickness within a range of 24.2 to 84.6 nm with respect to the whole lamella thickness range, as obtained in a SIST measurement is advantageous as to several aspects.

In a SIST measurement the melt enthalpy is recorded as function of temperature and evaluated through measuring the melt enthalpy of fractions melting within temperature intervals of 10 °C in the range from 50 to 200 °C. The melting curve of the polypropylene crystallized this way is used for calculating the lamella thickness distribution according to the Thomson-Gibbs equation. Details are given in the experimental part.

An amount of above 40 % with respect to lamella thickness within a range of 24.2 to 84.6 nm allows polypropylene compositions having an excellent balance of properties. In a first aspect, flowability such as reflected by melt flow rate, is very high. The significantly better flowability enables the use of the polypropylene compositions in moulding applications, particularly injection moulding applications.

The excellent flowability is further accompanied by high stiffness. High stiffness is important for numerous polypropylene uses.

Preferably the polypropylene base resin according to the present invention has an amount of above 45 % of lamella thicknesses within a range of 24.2 to 84.6 nm with respect to the whole lamella thickness range, as obtained in a SIST measurement.

Further preferably the polypropylene base resin according to the present invention has an amount of below 35 % of lamella thicknesses within a range of 14.09 to 24.16 nm nm with respect to the whole lamella thickness range, as obtained in a SIST measurement.

The polypropylene composition according to the present invention preferably has an MFR₂ measured according to ISO 1133 (230°C, 2.16 kg load) of at least 60g/10 min, more preferably at least 69 g/10 min, most preferably more than 125 g/10 min. The upper MFR₂ will usually be lower than or equal to 300 g/10 min and more conventionally lower than or equal to 280 g/10 min.

The polypropylene base resin according to the present invention preferably has a melting temperature of at least 162 °C, more preferably at least 164 °C and most preferably at least 165 °C all melting temperatures being measured by DSC analysis.

The polypropylene base resin according to the present invention preferably has an xylene soluble content XS (23° C, ISO 6427) of 2.5 wt.-% or lower, more preferably 2.2 wt.-% or lower and most preferably 2.1 wt.-% or lower.

The polypropylene base resin according to the present invention is further preferably characterized by a pentad isotacticity when measured by NMR of higher than 97.0%, more preferably higher than 98.0% and most preferably higher than 98.5%.

In another aspect, the polypropylene base resin according to the present invention preferably has a crystallization temperature T_{CR} as measured by DSC of 125 °C or higher.

When the crystallinity of the polypropylene is not sufficient, the stiffness will be moderate.

In yet another aspect the polypropylene base resin is characterized by a single T_g when subjected to DSC analysis.

The polypropylene base resin according to the present invention preferably has a molecular weight distribution broadness M_w/M_n of 5.0 to 15.0, preferably of 5.0 to 10.0, most preferably 5.0 to 8.0, determined by GPC according to ISO 16014-4 2003. The molecular weight distribution broadness reflects the broadness of the molecular weight distribution.

Moreover, the polypropylene base resin according to the present invention preferably has a weight average molecular weight M_w of the polypropylene of 125 000 g/mol or lower determined by GPC according to ISO 16014-4 2003, more preferably a M_w of 150 000 g/mol or lower, preferably of 130 000 g/mol or lower, and most preferably of 120 000 g/mol or lower, all M_w values being determined by GPC according to ISO 16014-4 2003. Usually the weight average molecular weight M_w of the polypropylene base resin will be 50 000 g/mol or higher.

The polypropylene composition according to the present invention preferably has a tensile modulus as determined according to ISO 527-2 on injection-moulded test specimens (dog bone shape, 4 mm thickness) as described in EN ISO 1873-2 of at least 2050 MPa, more preferably of at least 2100 MPa, even more preferably at least 2200 MPa, most preferably of at least 2250 MPa.


The polypropylene base resin according to the present invention preferably has an ethylene content of below 1.5 wt.-%, more preferably below 1.0 wt.-%.

The inventive polypropylene base resin most preferably is a homopolymer.

The polypropylene composition is preferably obtainable by a process as described in the following. The present invention is insofar concerned with polypropylene compositions obtainable by the process as described in the following.

The polymerization for obtaining the inventive polypropylene composition is effected in the presence of a catalyst system including a Ziegler Natta catalyst and

either diethylaminomethyl triethoxysilane (donor U)



or dicyclopentanedimethoxysilane (DCPDMS, donor D)

the mole ratio of Al/external donor being in the range of 0.5 to 50. More preferably, the mole ratio of Al/external donor is in the range of 2.0 to 40, even more preferably in the range of 5.0 to 30 and most preferably in the range of 8.0 to 15. These ranges refer to the total external donor fed into the reaction zones. A skilled person will understand that the feed of the external donor can be split over the three reaction zones.

In a first reaction zone a first intermediate polypropylene with an MFR₂ in the range of at 200 to 2000 g/10 min, preferably 300 to 1500 g/10 min, more preferably 350 to 1100 g/10 min and most preferably 375 to 900 g/10 min (ISO 1133; 230°C, 2.16 kg load) is formed.

This intermediate polypropylene contributes to 30 to 70 wt.-% to the total polypropylene as obtained after the third reactor and also denoted "third intermediate polypropylene". More preferably the first intermediate polypropylene contributes to 35 to 65 wt.-% and most preferably 40 to 62 wt.-% to the total polypropylene as obtained after the third reactor and also denoted "third intermediate polypropylene".

The first intermediate polypropylene is transferred to a second reaction zone and further polymerized to form a second intermediate polypropylene having an MFR₂ in the range of 80 to 800 g/10min, preferably 100 to 600 g/10 min, more preferably 200 to 550 g/10 min, and most preferably 250 to 500 g/10 min (ISO 1133; 230 °C, 2.16 kg load); forming the second intermediate polypropylene.

Preferably 20 to 50 wt.-% of the total polypropylene before compounding, i.e. of third intermediate polypropylene is produced in the second reaction zone; more preferably 22 to 45 wt.-% and most preferably 23 to 42 wt.-%.

The product obtained in the second reaction zone is transferred to the third reaction zone and further polymerized forming the third intermediate polypropylene.

Preferably, the second intermediate polypropylene is further polymerized in the third reaction zone to form the third intermediate polypropylene having an MFR_2 in the range of 50 to 300 g/10min (ISO 1133; 230 °C, 2.16 kg load), more preferably an MFR_2 in the range of 60 to 280 g/10min (ISO 1133; 230 °C, 2.16 kg load), and most preferably in the range of 65 to 250 g/10min (ISO 1133; 230 °C, 2.16 kg load).

It is self-explanatory that the reaction conditions in the different reaction stages are different. Thus, the first, second and third intermediate polypropylene differ at least as to one physical characteristic. Preferentially, the second intermediate polypropylene has an MFR_2 of up to $0.9 \cdot MFR_2$ (first intermediate polypropylene) as the upper limit and an MFR_2 of at least $0.3 \cdot MFR_2$ (first intermediate polypropylene) as the lower limit.

Preferably 10 to 25 wt.-% of the total polypropylene before compounding, i.e. of third intermediate polypropylene is produced in the third reaction zone; more preferably 12 to 22 wt.-% and most preferably 13 to 20 wt.-%. The fraction produced in the third reaction zone preferably has an MFR_2 as calculated from the MFR_2 of the third intermediate polypropylene and the MFR_2 of the second intermediate polypropylene in the range of 1 to 20 g/10min, preferably in the range of 2 to 15 g/10min, most preferably in the range of 3 to 12 g/10min. The method of calculation is given in the experimental part.

Optionally and preferably the third intermediate polypropylene is subjected to a compounding step. The compounding is operated under conditions that the final melt flow rate MFR_2 is modified to a degree of less than 10% with respect to the melt flow rate MFR_2 of the third intermediate product. Preferably, additives in an amount of up to 2 wt% with respect to the final composition may be added. Preferably, the additives are selected from the group of antioxidants acid scavengers, UV stabilizers, α -nucleating agents, slip agents, antistatic agents and combinations thereof.

The polypropylene composition obtainable by this process is preferably characterized by the features as described above with respect to the inventive polypropylene composition. Thus, all preferred ranges as to ethylene content, molecular weight distribution, broadness M_w/M_n , MFR_2 , tensile modulus, lamella thickness distribution, xylene soluble content XS, pentad isotacticity, and crystallization temperature T_{CR} .


The present invention is further concerned with a process as described above and a process as described in the following.

As regards the catalyst system, the donor plays an important role for producing high MFR compositions.

Suitable catalysts are Ziegler-Natta catalysts containing at least Ti, Cl, Mg and Al. Preferably a prepolymerized heterogeneous catalyst is used. Preferably the polypropylene base resin is obtained by a multistage polymerization process, as described above, in the presence of a catalyst system comprising as component (i) a Ziegler-Natta procatalyst which contains a trans-esterification product of a lower alcohol and a phthalic ester.

The procatalyst used according to the invention is preferably prepared by

- a) reacting a spray crystallized or emulsion solidified adduct of MgCl_2 and a C_1 - C_2 alcohol with TiCl_4
- b) reacting the product of stage a) with a dialkylphthalate of formula (I)



wherein $\text{R1}'$ and $\text{R2}'$ are independently at least a C_5 alkyl

under conditions where a transesterification between said C_1 to C_2 alcohol and said dialkylphthalate of formula (I) takes place to form the internal donor

- c) washing the product of stage b) or
- d) optionally reacting the product of step c) with additional TiCl_4 .

The procatalyst is produced as defined for example in the patent applications WO 87/07620, WO 92/19653, WO 92/19658 and EP 0 491 566. The content of these documents is herein included by reference.

First an adduct of MgCl_2 and a C_1 - C_2 alcohol of the formula $\text{MgCl}_2 \cdot n\text{ROH}$, wherein R is methyl or ethyl and n is 1 to 6, is formed. Ethanol is preferably

used as alcohol. The adduct, which is first melted and then spray crystallized or emulsion solidified, is used as catalyst carrier.

In the next step the spray crystallized or emulsion solidified adduct of the formula $\text{MgCl}_2 \cdot n\text{ROH}$, wherein R is methyl or ethyl, preferably ethyl and n is 1 to 6, is contacted with TiCl_4 to form a titanized carrier, followed by the steps of

- adding to said titanised carrier

(i) a dialkylphthalate of formula (I) with $\text{R1}'$ and $\text{R2}'$ being independently at least a C_5 -alkyl, like at least a C_8 -alkyl,

or preferably


(ii) a dialkylphthalate of formula (I) with $\text{R1}'$ and $\text{R2}'$ being the same and being at least a C_5 -alkyl, like at least a C_8 -alkyl,

or more preferably

(iii) a dialkylphthalate of formula (I) selected from the group consisting of propylhexylphthalate (PrHP), dioctylphthalate (DOP), di-isodecylphthalate (DIDP), and ditridecylphthalate (DTDP), yet more preferably the dialkylphthalate of formula (I) is a dioctylphthalate (DOP), like di-isooctylphthalate or diethylhexylphthalate, in particular diethylhexylphthalate,

to form a first product,

- subjecting said first product to suitable transesterification conditions, i.e. to a temperature above 100°C , preferably between 100 to 150°C , more preferably between 130 to 150°C , such that said methanol or ethanol is transesterified with said ester groups of said dialkylphthalate of formula (I) to form preferably at least 80 mol-%, more preferably 90 mol-%, most preferably 95 mol.-%, of a dialkylphthalate of formula (II)



with R1 and R2 being methyl or ethyl, preferably ethyl,

the dialkylphthalate of formula (II) being the internal donor and

- recovering said transesterification product as the procatalyst composition (component (i)).

The adduct of the formula $\text{MgCl}_2 \cdot n\text{ROH}$, wherein R is methyl or ethyl and n is 1 to 6, is in a preferred embodiment melted and then the melt is preferably injected by a gas into a cooled solvent or a cooled gas, whereby the adduct is crystallized into a morphologically advantageous form, as for example described in WO 87/07620.

This crystallized adduct is preferably used as the catalyst carrier and reacted to the procatalyst useful in the present invention as described in WO 92/19658 and WO 92/19653.

As the catalyst residue is removed by extracting, an adduct of the titanised carrier and the internal donor is obtained, in which the group deriving from the ester alcohol has changed. In case sufficient titanium remains on the carrier, it will act as an active element of the procatalyst. Otherwise the titanization is repeated after the above treatment in order to ensure a sufficient titanium concentration and thus activity.

Preferably the procatalyst used according to the invention contains not more than 2.5 wt.-% of titanium, preferably not more than 2.2% wt.-% and more preferably not more than 2.0 wt.-%. Its donor content is preferably between 4 to 12 wt.-% and more preferably between 6 and 10 wt.-%.

More preferably the procatalyst used according to the invention has been produced by using ethanol as the alcohol and dioctylphthalate (DOP) as


dialkylphthalate of formula (I), yielding diethyl phthalate (DEP) as the internal donor compound.

Still more preferably the catalyst used according to the invention is the BCF20P catalyst of Borealis (prepared according to WO 92/19653 as disclosed in WO 99/24479; especially with the use of dioctylphthalate as dialkylphthalate of formula (I) according to WO 92/19658) or the catalyst Polytrack 8502, commercially available from W.R. Grace, Columbia MA, USA.

For the production of the polypropylene base resin according to the invention the catalyst system used preferably comprises in addition to the special Ziegler-Natta procatalyst an organometallic cocatalyst as component (ii).

Accordingly it is preferred to select the cocatalyst from the group consisting of trialkylaluminum, like triethylaluminum (TEA), dialkyl aluminum chloride and alkyl aluminum sesquichloride.


Component (iii) of the catalyst system used is an external donor represented by formula (I) or (II)



wherein R^5 represents a branched-alkyl group having 3 to 12 carbon atoms, preferably a branched-alkyl group having 3 to 6 carbon atoms, or a cyclo-alkyl having 4 to 12 carbon atoms, preferably a cyclo-alkyl having 5 to 8 carbon atoms.

It is in particular preferred that R^5 is selected from the group consisting of isopropyl, iso-butyl, iso-pentyl, tert.-butyl, tert.-amyl, neopentyl, cyclopentyl, cyclohexyl, methylcyclopentyl and cycloheptyl.

Formula (IIIb) is defined by



wherein R_x and R_y can be the same or different and represent a hydrocarbon group having 1 to 12 carbon atoms.


R_x and R_y are independently selected from the group consisting of linear aliphatic hydrocarbon group having 1 to 12 carbon atoms, branched aliphatic hydrocarbon group having 1 to 12 carbon atoms and cyclic aliphatic hydrocarbon group having 1 to 12 carbon atoms. It is in particular preferred that R_x and R_y are independently selected from the group consisting of methyl, ethyl, n-propyl, n-butyl, octyl, decanyl, iso-propyl, iso-butyl, iso-pentyl, tert.-butyl, tert.-amyl, neopentyl, cyclopentyl, cyclohexyl, methylcyclopentyl and cycloheptyl.

More preferably both R_x and R_y are the same, yet more preferably both R_x and R_y are an ethyl group.

As mentioned above, the external donor of formula (II) is preferably diethylaminomethyltriethoxysilane.

For obtaining polypropylene compositions having very high melt flow rate (for example $MFR_2 > 120$ g/10 min), the external donor is preferably of formula (I), like dicyclopentyl dimethoxy silane $[Si(OCH_3)_2(cyclo-pentyl)_2]$ or diisopropyl dimethoxy silane $[Si(OCH_3)_2(CH(CH_3)_2)_2]$. Most preferably, the external donor is dicyclopentyl dimethoxy silane.

In a further embodiment, the Ziegler-Natta procatalyst can be modified by polymerising a vinyl compound in the presence of the catalyst system, comprising the special Ziegler-Natta procatalyst (component (i)), an external donor (component (iii)) and optionally a cocatalyst (component (ii)), which vinyl compound has the formula:



wherein R_3 and R_4 together form a 5- or 6-membered saturated, unsaturated or aromatic ring or independently represent an alkyl group comprising 1 to 4 carbon atoms, and the modified catalyst is used for the preparation of the heterophasic propylene copolymer according to this invention. The polymerized vinyl compound can act as an α -nucleating agent.

Concerning the modification of the catalyst, reference is made to the international applications WO 99/24478, WO 99/24479 and particularly WO 00/68315, incorporated herein by reference with respect to the reaction conditions concerning the modification of the catalyst as well as with respect to the polymerization reaction.

The Ziegler-Natta system may be e.g. an inorganic halide (e.g. MgCl_2) supported titanium catalyst, together with an aluminium alkyl (e.g. triethylaluminium) cocatalyst.

From a functional perspective, the external donors are limited to donors having suitable hydrogen response. As described above, standard silane donors such as dicyclopentylmethoxysilane (DCPDMS donor D), cyclohexylmethylmethoxysilane (CHMDMS or donor C) may be used as external donors for the production of the inventive polypropylene base resin having a final melt flow rate MFR_2 (ISO 1133, 230 °C, 2.16kg load) in the range of 60 g/10min to 90 g/10min.

For polypropylene base resins and compositions according to the present invention having a final melt flow rate MFR_2 (ISO 1133, 230 °C, 2.16kg load) of more than 90 g/10min external donors with even better hydrogen response are required. The most preferred donor for polypropylene compositions having an MFR_2 (ISO 1133, 230 °C, 2.16kg load) of more than 90 g/10min is diethylaminomethyl triethoxysilane (often denoted as Donor U).

Preferred catalyst systems are described in EP 0 491 566 A1 or in EP 0 591 224 A1 being incorporated by reference herewith. Concerning the modification of the catalyst, reference is made to the international applications WO 99/24478, WO 99/24479 and particularly WO 00/68315, incorporated herein by reference with respect to the reaction conditions concerning the modification of the catalyst.

The mole ratio of Al/external donor usually is in the range of 2.0 to 40. Preferably the mole ratio of Al/external donor usually is in the range of 5.0 to 30 and, most preferable, in the range of 8.0 to 15.

A preferred Ziegler Natta catalyst is of the type BCF20P (proprietary specification of Borealis AG) with diethylaminomethyltriethoxysilane as external donor (donor U), an Al/Ti ratio (mol/mol) of 200 and an Al/donor ratio (mol/mol) of 8 to 15.

The present invention is further concerned with a material comprising the polypropylene composition as described herein and a filler.

Apart from the advantages mentioned above, it has been surprisingly found that the materials comprising the inventive polypropylene composition having inter alia an MFR₂ measured according to ISO 1133 (230 °C, 2.16 kg load) of at least 50 g/10 min and a filler remain their excellent balance of stiffness and melt flow rate even when blended with further polypropylene having an ethylene content of below 1.5 wt.-% and an melt flow rate MFR₂ measured according to ISO 1133 (230 °C, 2.16 kg load) of at least 10 g/10 min.

In other words, the surprisingly high stiffness of the materials for a given melt flow rate of the polymer base resin is maintained even for materials containing a base resin having an melt flow rate MFR₂ measured according to ISO 1133 (230 °C, 2.16 kg load) of lower than 50 g/10 min.

The present invention insofar is also concerned with a material comprising a polypropylene composition and a filler, whereby the polypropylene composition consists of

a first polypropylene base resin,

a second polypropylene base resin, and

additives,

the first and the second polypropylene base resin being present in a total amount of 96 wt.-%, and

the additives being present in an amount of up to 4 wt.-%, with respect to the sum of polypropylene base resins and additives

wherein the first polypropylene base resin has

lamellas of a thickness from 24.2 nm to 84.6 nm in an amount of at least 40% when measured by stepwise isothermal segregation technique (SIST); and

a molecular weight distribution broadness Mw/Mn as calculated from gel permeation chromatography according to ISO 16014-4 2003, of at least 5, and

the polypropylene composition having an MFR₂ measured according to ISO 1133 (230 °C, 2.16 kg load) of at least 50 g/10 min ; and

a tensile modulus of 2000 MPa or higher when measured according to ISO 527-2 using injection moulded test specimens T as described in EN ISO 1873-2 (dog bone shape, 4 mm thickness), and

wherein the second polypropylene base resin has

an MFR₂ measured according to ISO 1133 (230 °C, 2.16 kg load) of at least 10 g/10 min and an ethylene content of below 1.5 wt.-%.


All preferred ranges as specified for the base resin above also comply for the first base resin in the material. All embodiments denoted preferred are incorporated by reference also with respect to the material including a first base resin, a second base resin and additives.

The second polypropylene base resin preferably has an ethylene content of below 1.0 wt.-%, more preferably below 0.5 wt.-%.

Preferably the inventive material consists of the polypropylene composition as described and a filler.

The second polypropylene base resin is preferably obtainable by a process comprising,

polymerizing propylene in the presence of a catalyst system including a Ziegler Natta catalyst and diethylaminomethyl triethoxysilane



or dicyclopentane dimethoxysilane (CD P PDMS) as an external donor

the mole ratio of Al/external donor in the range of 3 to 8

whereby,

- (i) a first intermediate polypropylene with an MFR₂ of 100 g/10 min to 250 g/10min (ISO 1133; 230 °C, 2.16 kg load) is formed in a first reaction zone;
- (ii) the first intermediate polypropylene is further polymerized in a second reaction zone to form a second intermediate polypropylene having an MFR₂ of 20 to 90 g/10min (ISO 1133; 230 °C, 2.16 kg load);
- (iii) the second intermediate polypropylene is further polymerized in a third reaction zone to form the third intermediate polypropylene having an MFR₂ of 10 to 49 g/10min (ISO 1133; 230 °C, 2.16 kg load);

and optionally compounding the third intermediate polypropylene to form the second polypropylene base resin having an MFR₂ of 10 to 49 g/10min or higher (ISO 1133; 230 °C, 2.16 kg load).

Further preferably, the first base resin and the second base resin are present in a weight ratio of from 15:85 to 85:15, more preferably 15:85 to 50:50.

The fillers are preferably selected from fibers and tablets. Preferably the filler is a mineral filler, more preferably an anisotropic mineral filler.

In a preferred embodiment the filler is selected from talc, mica and wollastonite. More preferably the filler is talc.

The filler preferably has a median particle size d₅₀ [mass percent] determined by sedimentation techniques of equal or more than 0.5 micrometer, more preferably equal or more than 0.8 micrometer, most preferably equal or more than 1.0 micrometer. The particle size d₅₀ [mass percent] determined by sedimentation techniques preferably does not exceed 5.0 micrometer, more preferably does not exceed 4.0 micrometer.

Typical examples for commercially available talc products are Luzenac A7C, Steamic T1CA, Jetfine 3CA and HAR (high aspect ratio) talc.

In another preferred embodiment the filler is selected from glass and carbon fibers.

The preferred glass fibers to be used for preparing the inventive materials are chopped glass fibers having a length of 3 to 15 mm, more preferably 3 to 10 mm. In preferred embodiments the materials are prepared by glass fibers having lengths of about 4.5 mm.

The glass fibers preferably have diameters of 10 to 20 micrometers.

The glass fibers in another aspect preferably are amino-silane or silane coated. Amino-silane or silane coated glass fibers are commercially available and have become an industrial standard. Typical examples for commercially available glass fibers are Vetrotex EC13 4.5 mm 968 or PPG MaxiChop 3299 EC13 4.5 mm.

When glass fibers are used, the material usually will contain also at least one adhesion promoter, preferably a maleic anhydride functionalized polypropylene. A typical example for an adhesion promoter is Exxelor PO1020. The amount of adhesion promoter depends on the amount of glass fiber and preferably will amount to $(0.03 \times \text{amount of glass fiber})$ to $(0.10 \times \text{amount of glass fiber})$. Thus when 20 wt.-% glass fibers (with respect to the total material) are used, the adhesive promoter preferably will be used in an amount of 0.6 to 2.0 wt.-% with respect to the total material. When 40 wt.-% glass fibers (with respect to the total material) are used, the adhesive promoter preferably will be used in an amount of 1.2 to 4.0 wt.-% with respect to the total material.

The inventive materials preferably include 15 to 45 wt.-% of filler, more preferably 20 to 40 wt.-%.

The inventive materials typically comprise up to 4 wt.-% of additives. Additives are preferably selected from the group of acid scavengers, antioxidants, hindered amine light stabilizers (HALS), slip agents (SA) and pigments.

In the inventive materials, further advantages are obtained. Particularly the balance of shrinkage and crystallinity is enhanced. High crystallinity is usually accompanied by high, i.e. undesirable shrinkage being a measure for dimensional stability. The inventive polypropylene compositions nevertheless allow lowest shrinkage when used with fillers.

In yet another aspect the present invention is concerned with the use of the inventive polypropylene compositions for increasing temperature resistance. Increasing shall mean an improvement of temperature resistance with respect to commercial products such as conventional polypropylene homopolymers like HK060AE commercially available from Borealis Polyolefine GmbH, Austria, characterized by an MFR2 (ISO 1133) of 125 g/10min and a heat deflection temperature (ISO 75 B) of 90°C or Moplen HP500V commercially available from LyondellBasell Industries, The Netherlands, characterized by an MFR2 (ISO 1133) of 120 g/10min and a heat deflection temperature (ISO 75 B) of 90°C.

Experimental part

Measurement methods

a) Molecular weight distribution from gel permeation chromatography (GPC)

The weight average molecular weight M_w and the molecular weight distribution ($MWD = M_w/M_n$ wherein M_n is the number average molecular weight and M_w is the weight average molecular weight) is measured by a method based on ISO 16014-1:2003 and ISO 16014-4:2003. A Waters Alliance GPCV 2000 instrument, equipped with refractive index detector and online viscosimeter was used with 3 x TSK-gel columns (GMHXL-HT) from TosoHaas and 1,2,4-trichlorobenzene (TCB, stabilized with 200 mg/L 2,6-Di tert butyl-4-methylphenol) as solvent at 145 °C and at a constant flow rate of 1 mL/min. 216.5 μ L of sample solution were injected per analysis. The column set was calibrated using relative calibration with 19 narrow MWD polystyrene (PS) standards in the range of 0.5 kg/mol to 11 500 kg/mol and a set of well characterised broad polypropylene standards (the Mark-Houwink constant K : $9.54 \cdot 10^{-5}$ and a : 0.725 for PS, and K : $1.91 \cdot 10^{-4}$ and a : 0.725 for PP). All samples were prepared by dissolving 5 - 10 mg of polymer in 10 mL (at 160 °C) of stabilized TCB (same as mobile phase) and keeping for 3 hours with continuous shaking prior sampling in into the GPC instrument. The ratio of M_w and M_n is a measure of the broadness of the distribution, since each is influenced by the opposite end of the "population".

b) Melt Flow Rate

The melt flow rate is measured as the MFR_2 in accordance with ISO 1133 (230°C, 2.16 kg load) for polypropylene and is indicated in g/10 min. The MFR is an indication of the flowability, and hence the processability, of the polymer. The higher the melt flow rate, the lower the viscosity of the polymer.

The calculation of melt flow rate MFR_2 of the polypropylene produced in the third reaction zone (R3) is performed as follows:

$$MFR(R3) = 10^{\left[\frac{\log(MFR(PP3)) - w(PP2) \times \log(MFR(PP2))}{w(R3)} \right]}$$

wherein

$w(PP2)$ is the weight fraction of the second intermediate polypropylene, i.e. the product of the first and the second reaction zone (PP2),

$w(R3)$ is the weight fraction of the polypropylene produced in the third reaction zone (R3),

$MFR(PP2)$ is the melt flow rate MFR_2 [in g/10min] measured according ISO 1133 at 230 °C of the second intermediate polypropylene, i.e. the product of the first and the second reaction zone (PP2),

$MFR(PP3)$ is the melt flow rate MFR_2 [in g/10min] measured according ISO 1133 at 230 °C of the third intermediate polypropylene,

$MFR(R3)$ is the calculated melt flow rate MFR_2 (230 °C) [in g/10min] of the polypropylene produced in the third reaction zone (R3).

c) Xylene soluble fraction

The xylene soluble fraction (XS) as defined and described in the present invention is determined as follows: 2.0 g of the polymer are dissolved in 250 ml p-xylene at 135 °C under agitation. After 30 minutes, the solution was allowed to cool for 15 minutes at ambient temperature and then allowed to settle for 30 minutes at 25 ± 0.5 °C. The solution was filtered with filter paper into two 100 ml flasks. The solution from the first 100 ml vessel was evaporated in nitrogen flow and the residue dried under vacuum at 90 °C until constant weight is reached. The xylene soluble fraction (wt%) can then be determined as follows:

$$XS = (100 \times m1 \times V0) / (m0 \times V1),$$

wherein $m0$ designates the initial polymer amount (g), $m1$ defines the weight of residue (g), $V0$ defines the initial volume (ml) and $V1$ defines the volume of the analyzed sample (ml).

d) Differential Scanning Calorimetry (DSC)

The melting temperature T_m , crystallisation temperature T_c and melting enthalpy H_m are measured with a Mettler TA820 differential scanning calorimetry device (DSC) on 3 ± 0.5 mg samples in accordance with ISO 11357-3:1999. Crystallisation and melting temperatures are obtained during $10^\circ\text{C}/\text{min}$ cooling and heating scans between 30°C and 225°C . Melting and crystallisation temperatures were taken as the peaks of the endotherms and exotherms.

e) Stepwise Isothermal Segregation Technique (SIST)

The isothermal crystallisation for SIST analysis was performed in a Mettler TA 820 DSC on 3 ± 0.5 mg samples at decreasing temperatures between 200°C and 105°C .

- (i) the samples were melted at 225°C for 5 min.,
- (ii) then cooled with $80^\circ\text{C}/\text{min}$ to 145°C
- (iii) held for 2 hours at 145°C ,
- (iv) then cooled with $80^\circ\text{C}/\text{min}$ to 135°C
- (v) held for 2 hours at 135°C ,
- (vi) then cooled with $80^\circ\text{C}/\text{min}$ to 125°C
- (vii) held for 2 hours at 125°C ,
- (viii) then cooled with $80^\circ\text{C}/\text{min}$ to 115°C
- (ix) held for 2 hours at 115°C ,
- (x) then cooled with $80^\circ\text{C}/\text{min}$ to 105°C
- (xi) held for 2 hours at 105°C .

After the last step the sample was cooled down with $80^\circ\text{C}/\text{min}$ to -10°C and the melting curve was obtained by heating the cooled sample at a heating rate of $10^\circ\text{C}/\text{min}$ up to 200°C . All measurements were performed in a nitrogen atmosphere. The melt enthalpy is recorded as function of temperature and evaluated through measuring the melt enthalpy of fractions melting within temperature intervals of 10°C in the range from 50 to 200°C .

The melting curve of the material crystallised this way can be used for calculating the lamella thickness distribution according to Thomson-Gibbs equation.

$$T_m = T_0 \left(1 - \frac{2\sigma}{\Delta H_0 \cdot L} \right)$$

where $T_0=457\text{K}$, $\Delta H_0 = 134 \times 10^6 \text{ J/m}^3$, $\sigma = 0,049.6 \text{ J/m}^2$ and L is the lamella thickness in nm. An inversion of this formula results in

$$L = 0.74 \cdot 457 / (457 - T_m) \text{ nm}$$

The amount of a certain lamella thickness range is obtained by relating the relative enthalpy integral of said fraction to the total enthalpy. Further details of the method can be found in the following two references incorporated by reference herewith:

J.A. Parker, D.C. Bassett, R.H. Olley, P. Jaaskelainen; On high pressure crystallization and the characterization of linear low-density polyethylenes;
A.Wlochowicz, M. Eder; Distribution of lamella thicknesses in isothermally crystallized polypropylene and polyethylene by differential scanning calorimetry; Polymer 1984, 25 (9), 1268-1270

f) Determination of isotacticity

The ^{13}C -NMR spectra of polypropylenes were recorded on Bruker 400MHz spectrometer at 130°C from samples dissolved in 1,2,4-trichlorobenzene/benzene- d_6 (90/10 wt/wt). All spectra were recorded using a ^{13}C optimised 10 mm extended temperature probehead at 125°C using nitrogen gas for all pneumatics. For the pentad analysis the assignment is done according to the methods described in literature: (T. Hayashi, Y. Inoue, R. Chūjō, and T. Asakura, Polymer 29 138-43 (1988). and Chujo R, et al, Polymer 35 339 (1994). The NMR-measurement was used for determining the mmmm pentad concentration in a manner well known in the art.

g) Tensile Test

The tensile properties are determined according to ISO 527-2 (23°C) using injection molded specimens as described in EN ISO 1873-2 (dog bone shape, 4 mm thickness). Tensile modulus is determined in the linear range of the stress/strain curve at a cross head speed of 1 mm/min; the test is then continued at a cross head speed of 10 mm/min until the sample breaks,

determining tensile strength results from as the maximum force measured divided by the cross-sectional area of the test specimen.

h) Shrinkage measurement

The shrinkage was determined on injection moulded circular disks (diameter 180 mm, thickness 3 mm). The center-gated specimens were moulded applying two different holding pressure times (10 and 20 seconds). 96 h after the production of samples the dimensional change radial and tangential to the flow front was measured for both disks. The average shrinkage for both holding pressure times is reported as final result.

i) Heat deflection temperature (HDT)

HDT is measured on injection moulded test specimen as described in EN ISO 1873-2 (80 x 10 x 4 mm³) that are placed in a heating bath, resting horizontally on two supports according to ISO 75B. A constant load (0.45 MPa) is applied in the centre of the specimen (three-point bending) and the bath temperature is raised at a constant rate. The temperature of the bath at which the flexural deflection of the loading point has reached a predefined level is the heat deflection temperature of the material.

Experiments

Inventive polypropylene compositions IE1 to IE4 have been produced in a Borstar™ pilot plant using one liquid-phase loop reactor and two gas phase reactors under conditions as shown in Table 1. The first reaction zone was a loop reactor and the second and third reaction zones were gas phase reactors. The catalyst system was a vinylcyclohexyl (VCH)-modified catalyst of the type BCF20P, prepared according to Example 1 of WO99/24479 in combination with a triethylaluminum (TEA) cocatalyst and either dicyclopentyl dimethoxysilane (donor D) or diethylaminotriethoxysilane (donor U) as an external donor at a ratio TEA/propylene of 0.2 g/kg and TEA/donor ratios as indicated in the table.

Table1:

		IE1	IE2	IE3	IE4
	Catalyst	BCF20P BNT	BCF20P BNT	BCF20P BNT	BCF20P BNT
	B1 Donor type	D	U	U	U
	B1 Al/donor ratio (mol/mol)	14	10	9	10
LOOP	B2 MFR ₂ (g/10 min)	255	315	427	512
	B2 XS (%)	2.6	3.2	2.1	2.4
	B2 amount total (%)	41	43	44	57
GPR1	B3 MFR ₂ (g/10 min)	125	119	260	420
	B3 XS (%)	1.6	1.8	2.1	1.9
	B3 MFR ₂ (g/10 min) made in GPR1	60	41	152	272
	B3 amount total (%)	40	40	40	26
GPR2	B4 XS (%)	1.5	1.5	1.9	1.9
	B4 MFR ₂ (g/10 min) made in GPR2	5	5	7	6
Product					
	XS PP product (%)	1.5	1.6	2	2
	MFR₂ PP product (g/10 min)	68	73	150	230

The inventive polypropylene compositions were tested as shown in Table 2. Comparative Example CE1 is the commercial high crystallinity PP homopolymer HF955MO having an MFR₂ of 20 g/10min from Borealis Polyolefine GmbH (Austria), and CE2 is the commercial PP homopolymer HK060AE having an MFR₂ of 125 g/10min from Borealis Polyolefine GmbH (Austria).

Table 2:

		CE1	CE2	IE1	IE2	IE3	IE4
		HF955	HK060				
		MO*	AE				
MFR ₂	g/10min	20	125	68	73	150	230
T _m (DSC)	°C	167	161	166	167	167	166
H _m (DSC)	J/g	119	112	123	119	104	129
T _{CR} (DSC)	°C	131	113	127	127	127	127
M _w (SEC)	kg/mol	230	180	117	116	n.d.	87
M _w /M _n (SEC)	-	4.8	5.0	6.4	6.8	n.d.	6.3
Tens. Modulus	MPa	2200	1600	2257	2271	2270	2332
Tens. Strength	MPa	42	36	44	44	39	39
Lamellae fraction 24.16-84.55 nm (SIST)	%	38	2.5	42	49	48	55
Pentad isotacticity (¹³ C-NMR)	mol%	98.0	95.0	99.1	98.4	98.5	98.4
HDT	°C	114	90	114	115	118	120
Shrinkage radial	%	1.74	1.60	1.79	1.8	1.83	1.86
Shrinkage tangential	%	1.68	1.54	1.74	1.75	1.79	1.80

(* - contains 0.4 wt%
talc, n.d. – not
determined)

For blending purposes a further composition has been produced.

Table 3

		BE5
	Catalyst	BCF20P BNT
	B1 Donor type	D
	B1 Al/donor ratio (mol/mol)	5
LOOP	B2 MFR ₂ (g/10 min)	136
	B2 XS (%)	1.6
	B2 amount total (%)	40.5
GPR1	B3 MFR ₂ (g/10 min)	60
	B3 XS (%)	1.6
	B3 MFR ₂ (g/10 min) made in GPR1	26
	B3 amount total (%)	40.5
GPR2	B4 XS (%)	1.3
	B4 MFR ₂ (g/10 min) made in GPR2	0.25
Product		
	XS PP product (%)	1.3
	MFR₂ PP product (g/10 min)	20

IE3 was blended with varying parts of BE5 and the fillers talc and glass fiber respectively as shown in the following table.

Table 4

All amounts given in parts per weight

Description	CE3	CE4	CE5	CE6	CE7	IE5	IE6	IE7	IE8	IE9
	standard homo-PP blend	standard homo-PP Blend Talc filled	standard homo-PP blend Talc filled	standard homo-PP blend GF filled	standard homo-PP blend GF-filled	Inventive blend	Inventive blend Talc filled	Inventive blend Talc filled	Inventive blend GF filled	Inventive blend GF-filled
HG265FB	77.05	62.05	46.05	61.65	44.45	0	0	0	0	0
HK060AE	21	16	12	16	12	0	0	0	0	0
IE3 (cf. Table 2)	0	0	0	0	0	29.05	23.05	17.05	23.65	16.45
BE5 (cf. Table 3)	0	0	0	0	0	69	55	41	54	40
STEAMIC T1CA		20	40				20	40		
GLASS 1.1				20	40				20	40
Adhesive promoter				0.8	2.0				0.8	2.0
MB 95-BLACK 7-PE-40	1.4	1.4	1.4	1	1	1.4	1.4	1.4	1	1
Irganox B 225	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25	0.25
Antistatic/Antifogging agent	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2
acid scavenger	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1

HG265FB was a standard polypropylene homopolymer produced by Borealis having an melt flow rate (230°C, 2.16kg) of 26 (g/10 min) and a melting temperature of 161 °C.

HK060AE was a standard polypropylene homopolymer produced by Borealis having an melt flow rate (230°C, 2.16kg) of 125 (g/10 min), a tensile modulus of 1600 MPa (ISO 527-2; 1mm/min).

Steamic T1CA was talc "Steamic T1 C A" produced by Luzenac having a d50(Sedigraph5100) of 1.8 micrometer and a d95(Sedigraph5100) of 6.2 micrometer (measured on compacted material)

Glass 1.1 was glass fiber "EC13 4.5 mm Vetrotex 968" by Vetrotex; fibre diameter 13 micrometer, fibre length 4.5 mm.

Exxelor PO1020 produced by Exxon was used as the adhesive promoter

MB95-BLACK-7-PE-40 was a carbon black masterbatch for coloring (Cabot Plasblak PE1639, 40% carbon black)

Dimodan ML90-1 was used as the antistatic/antifogging agent

Calcium stearate (Faci) was used as the acid scavenger.

Table 5

	unit	CE3	CE4	CE5	CE6	CE7	IE5	IE6	IE7	IE8	IE9
Description		standard homo-PP blend	standar d homo- PP Blend Talc filled	standar d homo- PP blend Talc filled	standa rd homo- PP blend GF filled	standa rd homo- PP blend GF- filled	Inventive blend	Inventi ve blend Talc filled	Inventi ve blend Talc filled	Inventi ve blend GF filled	Inventi ve blend GF- filled
MFR	g/10m in	30	30	33	12	7	32	31	30	12	7
ASH CONTENT	wt-%		19	37	20	40		19	37	20	40
FILLER CONTENT	wt-%		21	40				21	40		
TENSILE MODULUS	MPa	1668	3091	5039	5127	9641	2153	3602	5614	5860	10372
TENSILE STRENGTH	MPa	37	35	35	87	128	42	38	37	96	135
T. STRAIN AT T. STRENGTH	%	8	4	2	3	3	6	3	2	3	3
T. STRESS AT BREAK	MPa	31	30	34	87	128	36	33	36	96	135
T. STRAIN AT BREAK	%	18	9	2	3	3	10	6	2	3	3
NIS (23 °C)	kJ/m ²	1.8	2.1	1.3	7.9	11.5	1.4	1.6	1.3	7.5	10.7
TYPE OF FAILURE	None	C	C	C	H	H	C	C	C	H	H
NIS (-20°C)	kJ/m ²	-	1.1	1.3	7.2	10.3	-	1.1	1.3	7.5	10.6
TYPE OF FAILURE	None	-	C	C	C	C	-	C	C	C	C

SH RADIAL	%	1.71	1.3	0.88	0.98	0.47	1.78	1.58	0.92	1.16	0.54
SH TANGENTIAL	%	1.64	1.14	0.75	0.49	0.31	1.68	1.44	0.8	0.59	0.47
SH DIFFERENCE	%	0.07	0.16	0.13	0.49	0.16	0.1	0.14	0.12	0.57	0.06

It can be seen that the excellent balance of properties is maintained in the materials even when the melt flow rate is adjusted via a blending composition (e.g. BI5) to moderate values. Particularly the tensile modulus of IE6 was surprisingly increased compared to CE4, whereas all other properties remained on the same level. Both materials IE6 and CE4 had the same melt flow rate and identical filler content.

The same surprising result was obtained with materials containing glass fibre. Inventive material IE8 showed a tensile modulus of 5860 MPa, whereas CE6 only had a tensile modulus of 5127 MPa.

Claims

1. A polypropylene composition comprising a polypropylene base resin, the polypropylene base resin having


lamellas of a thickness from 24.2 nm to 84.6 nm in an amount of at least 40% when measured by stepwise isothermal segregation technique (SIST); and

a molecular weight distribution broadness M_w/M_n as calculated from gel permeation chromatography according to ISO 16014-4 2003, of at least 5, and

the polypropylene composition having an MFR_2 measured according to ISO 1133 (230 °C, 2.16 kg load) of at least 50 g/10 min ; and

a tensile modulus of 2000 MPa or higher when measured according to ISO 527-2 using injection moulded test specimens T as described in EN ISO 1873-2 (dog bone shape, 4 mm thickness).
2. The polypropylene composition according to claim 1, wherein the polypropylene base resin has a melting temperature of at least 162 °C according to DSC analysis.
3. The polypropylene composition according to claim 1 or 2, wherein the polypropylene base resin has a xylene soluble content XS (23° C, ISO 6427) is 2.5 wt.-% or lower.
4. The polypropylene composition according to any one of the preceding claims, wherein the pentad isotacticity when measured by NMR is higher than 97%.
5. The polypropylene composition according to any one of the preceding claims, wherein the crystallization temperature T_{CR} as measured by DSC is 125 °C or higher.
6. The polypropylene composition according to any one of the preceding claims, wherein the polypropylene base resin has a molecular weight distribution broadness M_w/M_n of 5 to 8 determined by GPC according to ISO 16014-4 2003.

7. The polypropylene composition according to any one of the preceding claims, wherein the weight average molecular weight M_w of the polypropylene base resin is 130 000 g/mol or lower determined by GPC according to ISO 16014-4 2003.
8. The polypropylene composition according to any of the preceding, wherein the polypropylene base resin is a homopolymer.
9. Polypropylene composition having a tensile modulus of 2000 MPa or higher when measured according to ISO 527-2 using injection moulded test specimens T as described in EN ISO 1873-2 (dog bone shape, 4 mm thickness) obtainable by a process comprising,
polymerizing propylene in the presence of a catalyst system including a Ziegler Natta catalyst and diethylaminomethyl triethoxysilane



or dicyclopentane dimethoxysilane (CD P PDMS) as an external donor
the mole ratio of Al/external donor in the range of 5 to 30
whereby,

- (i) a first intermediate polypropylene with an MFR_2 of 200 g/10 min to 2000 g/10min (ISO 1133; 230 °C, 2.16 kg load) is formed in a first reaction zone;
- (ii) the first intermediate polypropylene is further polymerized in a second reaction zone to form a second intermediate polypropylene having an MFR_2 of 80 to 800 g/10min (ISO 1133; 230 °C, 2.16 kg load);
- (iii) the second intermediate polypropylene is further polymerized in a third reaction zone to form the third intermediate polypropylene having an MFR_2 of 50 to 300 g/10min (ISO 1133; 230 °C, 2.16 kg load);


and optionally compounding the third intermediate polypropylene to form the polypropylene composition having an MFR_2 of 50 to 300 g/10min (ISO 1133; 230 °C, 2.16 kg load).

10. The polypropylene composition according to claim 11, wherein 30 to 70 wt.-% of the third intermediate polypropylene is produced in the first reaction zone; and

optionally wherein 20 to 25 wt.-% of the third intermediate polypropylene is produced in the second reaction zone; and

optionally wherein 10 to 25 wt.-% of the third intermediate polypropylene is produced in the third reaction zone.

11. Polypropylene composition according to claims 9 or 10 comprising a polypropylene base resin having a molecular weight distribution broadness M_w/M_n as calculated from gel permeation chromatography according to ISO 16014-4 2003, of at least 5 and the polypropylene composition having a tensile modulus of 2000 MPa or higher when measured according to ISO 527-2 using injection moulded test specimens (dog bone shape, 4 mm thickness) as described in EN ISO 1873-2.
12. Process for the production of a polypropylene composition according to any of the preceding claims in the presence of a catalyst system including a Ziegler Natta catalyst and diethylaminomethyl triethoxysilane



as an external donor, whereby the

mole ratio of Al/external donor is in the range of 5 to 30.

13. Process according to claim 12, whereby external donor is feed to the second reaction zone and/or the third reaction zone.
14. Material comprising the polypropylene composition according to any of claims 1 to 11 and a filler.
15. Material comprising a polypropylene composition and a filler, whereby the polypropylene composition consists of a first polypropylene base resin, a second polypropylene base resin in a total amount of 96 wt.-% with respect to the total polypropylene composition and additives in an amount of up to 4 wt.-% with respect to the total polypropylene composition,

wherein the first polypropylene base resin has

lamellas of a thickness from 24.2 nm to 84.6 nm in an amount of at least 40% when measured by stepwise isothermal segregation technique (SIST);and

a molecular weight distribution broadness M_w/M_n as calculated from gel permeation chromatography according to ISO 16014-4 2003, of at least 5, and

the polypropylene composition having an MFR_2 measured according to ISO 1133 (230 °C, 2.16 kg load) of at least 50 g/10 min ; and


a tensile modulus of 2000 MPa or higher when measured according to ISO 527-2 using injection moulded test specimens T as described in EN ISO 1873-2 (dog bone shape, 4 mm thickness), and

wherein the second polypropylene base resin has

an MFR_2 measured according to ISO 1133 (230 °C, 2.16 kg load) of at least 10 g/10 min and an ethylene content of below 1.5 wt.-%.

16. Material according to claim 15, wherein the second polypropylene base resin is obtainable by a process comprising,

polymerizing propylene in the presence of a catalyst system including a Ziegler Natta catalyst and diethylaminomethyl triethoxysilane



or dicyclopentane dimethoxysilane (CD P PDMS) as an external donor
the mole ratio of Al/external donor in the range of 3 to 8
whereby,

- (i) a first intermediate polypropylene with an MFR_2 of 100 g/10 min to 250 g/10min (ISO 1133; 230 °C, 2.16 kg load) is formed in a first reaction zone;
- (ii) the first intermediate polypropylene is further polymerized in a second reaction zone to form a second intermediate polypropylene having an MFR_2 of 20 to 90 g/10min (ISO 1133; 230 °C, 2.16 kg load);
- (iii) the second intermediate polypropylene is further polymerized in a third reaction zone to form the third intermediate polypropylene having an MFR_2 of 10 to below 50 g/10min (ISO 1133; 230 °C, 2.16 kg load);

and optionally compounding the third intermediate polypropylene to form the second polypropylene base resin having an MFR₂ of 10 to below 50 g/10min (ISO 1133; 230 °C, 2.16 kg load).

17. Material according to claim 14, 15 or 16, wherein the filler is a fiber optionally selected from glass fibers and carbon fibers.
18. Material according to claim 14, 15 or 16 wherein the filler is talc.
19. Use of a composition according to any of claims 1 to 11 for increasing the temperature resistance.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2011/005368

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08F10/06
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C08F C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)
EP0-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 2 174 980 A1 (BOREALIS AG [AT]) 14 April 2010 (2010-04-14) examples 1,2 table 2 paragraphs [0042], [0056] -----	1-19
A	WO 2011/000557 A1 (BOREALIS AG [AT]; DOSHEV PETAR [AT]; JAEAEKELAEINEN PIRJO [FI]; KHEIR) 6 January 2011 (2011-01-06) example 2 -----	1-19

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance
"E" earlier document but published on or after the international filing date
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
"O" document referring to an oral disclosure, use, exhibition or other means
"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
"&" document member of the same patent family

Date of the actual completion of the international search

11 November 2011

Date of mailing of the international search report

22/11/2011

Name and mailing address of the ISA/
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Queste, Sébastien

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2011/005368

Patent document cited in search report		Publication date		Patent family member(s)		Publication date
EP 2174980	A1	14-04-2010	CN	102165006 A		24-08-2011
			EP	2174980 A1		14-04-2010
			KR	20110050695 A		16-05-2011
			WO	2010040492 A2		15-04-2010

WO 2011000557	A1	06-01-2011	AT	523558 T		15-09-2011
			EP	2281851 A1		09-02-2011
			ES	2368024 T3		11-11-2011
			WO	2011000557 A1		06-01-2011
