



Office de la Propriété

Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2228475 C 2008/10/14

(11)(21) **2 228 475**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(86) Date de dépôt PCT/PCT Filing Date: 1996/08/08
(87) Date publication PCT/PCT Publication Date: 1997/03/13
(45) Date de délivrance/Issue Date: 2008/10/14
(85) Entrée phase nationale/National Entry: 1998/02/02
(86) N° demande PCT/PCT Application No.: US 1996/012877
(87) N° publication PCT/PCT Publication No.: 1997/009725
(30) Priorités/Priorities: 1995/09/06 (US08/524,390);
1996/08/08 (US08/694,344)

(51) Cl.Int./Int.Cl. *C08L 71/03*(2006.01),
C08L 83/04(2006.01), *H01B 3/42*(2006.01),
H01B 3/46(2006.01), *H02G 15/068*(2006.01)

(72) Inventeurs/Inventors:
HEYER, THOMAS J. D., US;
WANDMACHER, ROBERT A., US

(73) Propriétaire/Owner:
MINNESOTA MINING AND MANUFACTURING
COMPANY, US

(74) Agent: SMART & BIGGAR

(54) Titre : MATERIAU PERMETTANT DE REGULER LA CONTRAINTE ELECTRIQUE D'EPIHALOHYDRINE

(54) Title: EPIHALOHYDRIN ELECTRICAL STRESS CONTROLLING MATERIAL

(57) Abrégé/Abstract:

A non-tacky electrical stress control material comprising a) 100 parts of a resin component containing: 1) from 20 % to 80 % of an epihalohydrin polymer, and 2) correspondingly, from 80 % to 20 % of an insulating silicone polymer having a $\tan \delta$ of less than one; b) from 10 to 200 parts of a filler, said filler being nonconductive at room temperature, selected from the group consisting of barium titanate and hydrated aluminum silicate; and c) from 0 to 30 parts of a plasticizer.

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : H01B 3/42, 3/46, C08L 71/03, 83/04 // (C08L 71/03, 83:04) (C08L 83/04, 71:03)		A1	(11) International Publication Number: WO 97/09725
(21) International Application Number: PCT/US96/12877		(43) International Publication Date: 13 March 1997 (13.03.97)	
(22) International Filing Date: 8 August 1996 (08.08.96)			
(30) Priority Data:			(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).
08/524,390	6 September 1995 (06.09.95)	US	
08/694,344	8 August 1996 (08.08.96)	US	
(71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).			Published <i>With international search report.</i>
(72) Inventors: HEYER, Thomas, J., D.; 6801 River Place Boulevard, Austin, TX 78726-9000 (US). WANDMACHER, Robert, A.; 6801 River Place Boulevard, Austin, TX 78726-9000 (US).			
(74) Agents: NEAVEILL, Darla, P. et al.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).			

(54) Title: EPIHALOHYDRIN ELECTRICAL STRESS CONTROLLING MATERIAL

(57) Abstract

A non-tacky electrical stress control material comprising a) 100 parts of a resin component containing: 1) from 20 % to 80 % of an epihalohydrin polymer, and 2) correspondingly, from 80 % to 20 % of an insulating silicone polymer having a $\tan \delta$ of less than one; b) from 10 to 200 parts of a filler, said filler being nonconductive at room temperature, selected from the group consisting of barium titanate and hydrated aluminum silicate; and c) from 0 to 30 parts of a plasticizer.

EPIHALOHYDRIN ELECTRICAL STRESS CONTROLLING MATERIAL**Background of the Invention****Field of the Invention**

The present invention relates to non-tacky conformable material suitable for 5 use as a void filling, electrical stress controlling material. Specifically, it relates to nontacky core-loadable epihalohydrin polymer compositions which exhibit effective stress control when used at the edge of a semi-conductive shield in a termination either alone or in conjunction with a high dielectric constant tube.

Description of the Art

10 Heat-recoverable rubbery tubular articles and elastically recoverable tubular articles are widely used to cover power cables or conduits. Such articles are useful where insulation, sealing and/or encapsulation are required. A typical elastically recoverable article is a rubber insulating sleeve which is provided with an inner support or "core" which holds the article in a deformed shape. The tube is placed over a cable, 15 and the core is unwound, and removed. The article then recovers toward an original shape.

Various compositions have been used in coordination with such articles to provide electrical stress control and sometimes to bond them to various types of pipe and tubing, e.g., mastics, tapes, and greases as in U.S. Patent Nos. 4,017,652, and 20 4,383,131.

U.S. Patent 4,363,842 discloses elastomeric pre-stretched tubes formed from EP or EPDM with a variety of fillers including carbon black, conductive particles and the like, including carbon black, and aluminum flakes. Barium titanate is disclosed for providing stability of permittivity over a wide range of electrical stresses; barium 25 titanate does not provide higher permittivity to the elastomeric tubes.

Heat-recoverable articles may also be provided on an inner tube, which breaks and allows the elastomeric member to recover. These articles are heated with a hot air gun or torch, to initiate recovery.

Both types of articles may recover around the cable joint or termination (or 30 other substrate) tightly in areas, and have air pockets between the cable and the

substrate about which it is recovered in other areas, such as a semiconducting layer edge, which is highly undesirable. Sealing compositions, such as greases, adhesives, and the like have been used with these articles to reduce or eliminate such air pockets. Many of such compositions have been adhesives which have bonded between the 5 recoverable articles and the substrate about which it is recovered.

EP Patent 0424 090 B1 discloses an elastomeric covering for connections in electrical cables having a conformable material interposed between the prestretched tube and the core, whereby when the core is removed, the elastic forces change the shape and dimensions of the material to correspond to the underlying surface. No 10 electrical properties are disclosed, and a broad range of materials are simply listed.

U.S. Patent 4,378,463 discloses an adhesive for use in heat recoverable products in areas of electrical stress. The adhesive comprises an epihalohydrin polymer, a tackifier, a catalyst, and a particulate filler. The composition bonds the heat-recoverable article to the substrate, and also provides electrical stress relief. No 15 polymer blends are disclosed.

However, the above composition has some disadvantages. First, it must be provided separately, and cannot be preloaded into the splice or termination as the composition will adhere thereto or to the core and either prevent its removal when it is time to initiate recovery or deform and fracture during removal, causing the formation 20 of large air pockets.

Applicant has now discovered that a non-tacky stress control material containing an epihalohydrin polymer, and an insulative polymer having a $\tan \delta$ of less than 1, and having certain fillers provides unique electrical properties for use in stress control, i.e., excellent permittivity. Such compositions exhibit synergism between the 25 combination of polymers and the fillers not seen when only one type of polymer is used with the same fillers. The materials have significantly improved results on electrical properties such as permittivity, alternating current voltage withstand tests, impulse withstand, and/or $\tan \delta$ values.

Further, compositions of the invention may be aged in cable oil and neither 30 swell nor lose their electrical properties.

60557-5742

The compositions may be used alone inside the insulator of an electrical cable, and are suitable for preloading in an elastically shrinkable tube such as a splice cover or termination supported on a removable rigid core, or underneath a pre-stretched elastomeric or heat shrinkable stress control tube.

5

Summary of the Invention

The present invention provides a non-tacky electrical stress control material comprising

- a) 100 parts of a resin component containing
 - 1) from 20% to 80% of an epihalohydrin polymer, and
 - 2) correspondingly, from 80% to 20% of a silicone polymer having a $\tan \delta$ of less than one,
- b) from 10 to 200 parts of a filler, said filler being nonconductive at room temperature, selected from the group consisting of barium titanate and hydrated aluminum silicate, and
- c) from 0 to 30 parts of a plasticizer.

Preferred non-tacky electrical stress control materials comprise

- a) 100 parts of a resin component containing
 - 1) from 20% to 80% of an epihalohydrin polymer, and
 - 2) correspondingly, from 80% to 20% of a silicone polymer having a $\tan \delta$ of less than one,
- b) from 80 to 120 parts barium titanate, and
- c) from 0 to 30 parts of a plasticizer.

60557-5742

According to one aspect of the present invention, there is provided a non-tacky electrical stress control material comprising a) about 100 parts of by weight of a resin component containing 1) from about 20% by weight to about 80% by weight of an epihalohydrin polymer, and 2) correspondingly, from about 80% by weight to about 20% by weight of an insulating silicone polymer having a $\tan \delta$ of less than one, such silicone being a gum silicone having a durometer of from about 5 to about 30, b) from about 10 to 200 parts by weight per hundred parts by weight resin component of barium titanate, and c) from 0 to 30 parts by weight of a plasticizer.

The following terms have the defined meanings when used herein.

15 1. The term "elastically shrinkable" means that an article so described is in a stretched or radially expanded condition and will shrink to another condition when permitted to do so, with no heat required.

20 2. The term "cold-shrinkable" is synonymous with the term "elastically shrinkable".

3. The term "core" refers to the supporting article upon which the elastically shrinkable article is deformed in a radially expanded or stretched condition.

4. The terms "insulator" and "insulative polymer" means a polymer with a volume resistivity greater than 10^{10} ohm-cm.
5. The term "epihalohydrin polymer" includes homopolymers, copolymers, terpolymers, etc.
6. The term "tan delta" or "tan δ " refers to the electrical dissipation factor.
7. The term "permittivity" or "relative permittivity" is the ratio of electric flux generated by an electrical field in a medium to that generated by the field in a vacuum.
8. The term "dielectric constant" is synonymous to relative permittivity.

10 All ratios, parts, and percents described herein are by weight, unless otherwise specifically stated.

Detailed Description of the Invention

The materials of the invention comprise a resin component which consists of a blend of two polymeric resins; epihalohydrin polymers and insulating silicone polymers

15 having a tan δ of less than 1.

Epihalohydrin polymers suitable for use in the compositions of the invention are the elastomeric polymers of an epihalohydrin in homopolymer or copolymer form. Such polymers are prepared by polymerization of the monomeric material in mass or in solution with organometallic catalysts, and may be homopolymers, copolymers, terpolymers, etc. Examples of homopolymers include epichlorohydrin, or epibromohydrin; useful copolymers include copolymers of epihalohydrins with alkylene oxides, and copolymers with epoxides, e.g., propylene oxide, ethylene oxide, butene oxide, and epoxy ethers such as ethylglycidyl ether, allylglycidyl ether and the like. Such polymers are available from Zeon Chemicals, Inc.

25 Preferred epihalohydrin polymers include copolymers with alkylene oxides, particularly ethylene and propylene oxides.

The resin component also contains an insulating silicone polymer having a tan δ of less than one. Useful silicones include silicones which are fluid at room temperature and gum silicones; gum silicones preferred for easy compounding and processability; 30 most preferred are those gum silicones having a durometer of from 5 to 30.

Surprisingly, silicone polymers having a durometer of 5 or more can be mixed with the

epihalohydrin, and provide a product which exhibits faster flow, lower viscosity and a lower plasticity. The preferred silicones also exhibit a plasticity of less than 250, preferably less than 230.

Commercially available silicone elastomers include those fluid silicones 5 available as Dow Corning DC 10,000, and the like, and gum silicones available as Elastosil® R300/40, and Wacker 7805 and 7815 from Wacker Silicones Corporation; Silastic® GP31 from Dow Corning, and the like.

The silicone polymer and the epihalohydrin are present in the resin component at a ratio of from 20:80 to 80:20, preferably from about 70:30 to about 30:70.

10 Formulations comprising less than 20% insulative polymer may be useful in some applications but exhibit high $\tan \delta$ values, which is undesirable for high voltage applications.

The composition contains from 10 to 200 parts per hundred resin (pph) of at 15 least one particulate filler selected from fillers which are nonconductive at room temperature. Preferred fillers are aluminum silicate and barium titanate. Preferred materials comprise from 25 to 100 parts aluminum silicate or from 50 to 200 parts barium titanate. The most preferred filler is barium titanate. These resin blends show synergistic behavior with these fillers. Barium titanate is available from Ferro Corp. as Transelco 219-3, and hydrated aluminum silicate is available from J.M. Huber as 20 Suprex®.

Materials of the invention exhibit significant improvements in electrical properties. Barium titanate containing materials exhibit improvement in permittivity and alternating load current withstand voltage, i.e., preferred materials exhibit both 25 permittivities of above 15 and $\tan \delta$ of less than 4, preferably around 1. Further, terminations employing materials of the invention show improvements in AC withstand; withstanding about 100 kV, terminations employing preferred materials withstand about 110 kV, as opposed to 95 kV or less for current conventional electrical stress control materials on 25 kV cable.

Further, there are two failure modes possible in such testing and impulse 30 withstand testing; external flashover, and internal degradation of the material caused by heat. External flashover is preferred as the termination or joint is not destroyed and

remains functional after the arc extinguishes. Terminations or joints using materials of the invention have a failure mode of flashover as opposed to those using conventional sealants which have a degradation failure mode.

Finally, materials of the invention show stability and integrity even when aged 5 in oil for extended periods of time at high temperatures. Terminations or joints formed from the materials of the invention will exhibit identical electrical properties, or even improved properties and structural integrity even after being immersed in polybutene oil (the type used in paper insulated lead cables) for 90 days at 90°C. Conventional materials, such as those containing EP or EPDM type rubbers will swell after such 10 aging and lose the electrical properties, such as dielectric constant.

Hydrated aluminum silicate containing materials exhibit superior tan δ values while retaining useful permittivities.

Materials of the invention may also comprise a plasticizer. Useful plasticizers include aliphatic, naphthenic, and aromatic petroleum based hydrocarbon oils; cyclic 15 olefins (such as polycyclopentadiene); polyalphaolefins (such as hydrogenated polymerized decene-1), hydrogenated terphenyls or other terpene derivatives; polypropylene oxide mono- and di-esters, cyclopentadiene copolymers with fatty acid esters; phosphate esters and mono-, di-, and poly-esters, (such as trimellitates, phthalates, benzoates, fatty acid ester derivatives, fatty acid ester alcohols, dimer acid 20 esters, glutarates, adipates, sebacates, polymeric polyesters, rosin esters, acrylate esters, epoxidized fatty acid esters, and the like) and mixtures thereof.

Preferred plasticizers include phosphate esters and polyesters and polyethers such as adipates, phthalates, azelates, and the like, i.e., dioctylphthalate, and 25 dioctylazelate. The latter is available from C.P. Hall, as Plasthall® DOZ. The plasticizer may be present in an amount up to 30 parts per hundred parts of resin.

The stress control materials may also include up to 15 parts (pph resin) of metal flake or other conductive filler such as aluminum flake, or copper flake.

Aluminum flake, such as that available from Silberline Mfg. Company as Silvex® 620-25-A, is preferred.

30 Materials of the invention may also contain minor amounts of other adjuvants such as antioxidants, dyes, pigments, flame retardants, release aids and the like so long

as the addition does not negatively affect the electrical properties. Useful antioxidants include Agerite® MA, available from R. H. Vanderbilt Co. Useful process aids include fatty acids such as ATMERTM 103, available from ICI Americas, and Kemamide® U, available from Humko Chemicals.

5 Materials of the invention are especially useful in medium or high voltage power cables. The composition of the invention may be used alone, e.g., placed under an insulator of such cable in the region of the semiconductive cutback to fill voids. However, many cable joints or terminations use a pre-stretched stress control tube as well. Typically, pre-stretched tubes are provided on a rigid easily removable core.

10 The core can be external or internal; however internal cores are preferable. Typical cores are such as those described in U.S. Patent 3,515,798. Preferred terminations comprise a coordinated two-component or three-component stress-control system where the inner component is the conformable material of the invention, and the outer component is the high permittivity tubing. Alternatively, two layer structures include

15 the material of the invention and an outer layer which is an insulator having high permittivity. A possible third layer is a polymeric insulator, typically a pre-stretched tube such as those described in U.S. Patent No. 4,363,842.

When materials of the invention are used in such terminations, the electrical stress control is greatly improved, which allows a significant reduction in the required

20 length of the termination. i.e., at least 20% reduction, which reduces costs and installation space requirements. Preferred materials may allow a length reduction of 40% or more. The application of silicone grease is no longer required, nor is the application of tape or other sealing materials at the ends of the termination, as it may be sealed with the stress control material, which is core loadable, permitting its

25 automatic delivery. Materials of the invention are typically loaded at thickness of from about 1.25 mm to about 3 mm, preferably from about 2 to about 3 mm.

Compositions of the invention are prepared by mixing the ingredients and then pressed, extruded, injection molded or calendered into the final form desired. The final product can be provided as sheets, shaped articles, or in putty form, as desired for the

30 application.

The following examples are for illustrative purposes only, and are not meant to be limiting. One skilled in the art will easily think of variations within the scope of the invention, which is solely that defined by the claims.

Test Methods

5

Alternating Current Withstand and
Basic Impulse Withstand Voltage Tests

The International Society of Electrical and Electronic Engineers (IEEE) sets the United States standard for high voltage cable; the test is conducted per IEEE-48. In order to determine the limit of AC withstand, AC withstand voltage is increased in 10 steps of 5 kV per hour until flashover or internal degradation breakdown occurs. In order to determine the limit of impulse withstand, impulse voltage is raised in steps until flashover or internal degradation breakdown occurs.

Electrical Properties

15 Electrical properties (permittivity, $\tan \delta$) were tested according to ASTM-D150 using an impedance measurement method. The electrical properties were tested at an electrical stress of about 3 kV/cm to about 20 kV/cm.

Probe Tack Test

The probe test was performed according to ASTM D-2979.

20 Rubber Property-Plasticity and Recovery (Parallel Plate Method)

This test was performed according to ASTM D926-93, procedure A.

Adhesion to Core

25 For this test, a stress control material was placed onto a rigid core for an elastically shrinkable splice or termination by means of finger pressure. The core was then unwound, and the material was observed for deformation, fracture and adhesion to the core.

For samples which survived such test without deformation or fracture, another identical sample was placed on the core and an elastically shrinkable splice cover was

placed onto the core. The sample was stored for 3 months, and then the core was unwound, and the material checked for deformation, fracture and adhesion to the core.

Examples

Example 1

5

Preparation of the Material

86.87 g of Hydrin® C-45, 115.15 g of Dow-Corning Silastic® GP3 silicone elastomer, 20.20 gms of dioctyl azelate, available as Plasthall DOZ®, 72.73 gm of Transelco 219-3 barium titanate, 2 gm Kemamide® U, and 3 gm of Silcogum® black 095 black pigment were placed in the order listed, with the barium titanate being added 10 in two steps in an internal Banbury® mixer at 60-80 rpm and each ingredient permitted to mix before adding the next. After all ingredients were added, the ingredients were mixed until the batch temperature reached at least 70°C. The batch was then dropped from the mixer and placed in sheet form onto a two roll mill, adding any material remaining in the pan.

15 Other materials were prepared on a two roll mill by setting the roll temperature to 60°C, adding the epichlorohydrin, and allowing it to band both rolls, and then mix for about two minutes. The silicone was then added, and mixed until the color was even. The barium titanate and plasticizer were added together, and mixed until dispersed. The pigment was added and mixed. The batch was then removed and 20 allowed to cool.

Preparation of Test Samples

Samples of from 1 mm to 3 mm in thickness were prepared by pressing between parallel metal plates in a hydraulic or pneumatic press, using shims to set the final plate separation.

25 First, the material was made as described above, and then a sample was cut, placed between the plates and pressed for 5 minutes. The sample was then inspected carefully to ensure no foreign matter or entrapped air was visible, as clean samples are required to insure proper dielectric testing.

Examples 2-4 and Comparative Examples C5-C8

These formulations of the invention were compounded as described in Example 1, except with differing ratios of resins and differing fillers. Suprex® clay is hydrated aluminum silicate, available from J.M. Huber Co. Example 4 contains no plasticizer.

5 During processing of various batches of material for Example C6, the batches became "nervy", i.e., it lost its smooth flowability and was lumpy, and difficult to further process into slabs or sheets. Clearly, processing time is critical, and good primary and secondary processing is very difficult to achieve with this material.

Table 1

Ingredient/Example No. (pph*)	1	2	3	4	C5	C6	C7	8
Hydrin®	50	50	50	50	84	50	---	30
Silastic® GP31	50	50	50	50	16	50	60	---
Wacker R300/30	---	---	---	---	---	---	---	70
Nordel 1440	---	---	---	---	---	---	40	---
Hectorite Clay	---	---	---	---	4	20	---	---
Plasthall DOZ®	10	10	10	---	5	---	---	---
Suprex® Clay	---	---	29	---	---	---	---	---
BaTiO ₂	60	60	---	60	---	---	60	100
Aluminum Flake	8	---	---	8.5	---	---	8.5	---
Kemamide® U	2	2	2	2	2	2	2	3
SilicoBlack 95	3	3	3	3	3	3	3	3

10 *parts per hundred resin

The formulations described in Table 1 were then made into samples and electrical properties were tested. Results of those tests are shown in Table 2.

Example 4 was also tested in a termination having a tubular design, with a 21.6 cm insulation shield cutback, an overall length of approximatly 33 cm. The electrical stress control material was placed into the termination at a thickness of 2 mm. The termination was tested on a 25 kV 1/0 AWG cable, Jacketed Concentric Neutral. The AC Withstand was 120 kV with the failure mode being flashover, and the Maximum Impulse Withstand was +195 kV, and -196 kV, for Positive and Negative polarities, respectively.

Example C7 is an embodiment of U.S. Patent No. 4,363,842 (Nelson). As is shown in Table 2 below, a material using a silicone/EPDM construction rather than the silicone epihalohydrin blend resins of the invention. Such material does not have a good dielectric constant even when 8.5 parts of aluminum flake is added, only reaching 5 4.47.

It is desirable to have a combination of a dielectric constant above 9, preferably above 10, and a $\tan \delta$ of less than 4. Note that for the comparative examples C5 and C7, this combination is not met, while each of the examples of the invention meets these criteria. C5 becomes resistive, e.g., at high stresses, which is extremely 10 undesirable. Comparative example C6 shows reasonable electrical properties; however, as noted above, processing of this material is very difficult.

Table 2

Elec Properties/Example No.	1	2	3	4	C5	C6	C7
$\tan \delta$ *	2.9	2.8	0.77	2.9	58	3.3	.022
dielectric constant*	49	36	11	49.2	28	17.7	4.47

*These numbers are the average dielectric constant and dissipation factor, $\tan \delta$, over electrical stresses from 3,000-20,000 v/cm.

15

Example 8

A sample was made according to the invention containing the following ingredients; 30 parts Hydrin® C-45, and 70 parts Wacker R300/30 silicone, 100 pph Transelco BaTiO₂, 3 pph Kemamide® U, and 3 pph Silicogum Black 0.095. The composition was tested for electrical properties as discussed above, and found to have 20 an average dielectric constant of 35, and an average $\tan \delta$ of 0.97. The sample had an average plasticity according to ASTM D926-93 of 235.

The sample was then aged in cable oil, i.e., polybutene oil for 90 days and 90°C. The dielectric constant rose an average of 2% after such aging.

Example C9

25 An example of the mastic disclosed in U.S. Patent 4,378,463 was prepared as described. This sample along with samples 1, 2 and 3 of the invention were subjected to the probe tack test. Example C9 had an adhesion to the core such that upon

unwinding the core, the adhesive deformed and fractured along the separating helical core weld lines, and remained firmly adhered to the unwound core strand.

The Examples of the invention all allowed unwind without any visible deformation or fracture, and did not adhere to the core. Further samples of Examples 5 1-3 were then placed upon cores, and elastically shrinkable material of U.S. Patent No. 4,363,842 was placed thereover. These were stored at ambient temperatures for 60 and 90 days, and then removed. The electrical stress control material even after such storage associated with the elastomerically shrinkable material and did not adhere to the core, nor were any deformations or fractures visible.

10 A room temperature probe tack was also run on Example C9, and Examples 1-3. The results were as shown in Table 3.

Table 3

Ex.	Temp (°C)	Dwell Time (s)	Probe Speed (cm/s)	Sample Holder	Max. Force (g)	Comments
C9	23	100	0.01	aluminum	101	did not debond
C9*	23	20	0.01	aluminum	283	did not debond
1	23	100	0.01	aluminum	Not Applicable	no adhesion

*Steel backing used to limit deformation of material.

Example 10

15 A sample was made according to the invention containing the following ingredients: 30 parts Hydrin® C-45, and 70 parts Wacker 7805 silicone, 100 pph Transelco BaTiO₂, 3 pph Kemamide® U, and 3 pph Silicogum Black 0.095. The composition was tested for electrical properties as discussed above, and found to have an average dielectric constant of 28.34 and an average tan δ of 0.85. The sample had 20 an average plasticity according to ASTM D926-93 of 208.

60557-5742

CLAIMS:

1. A non-tacky electrical stress control material comprising

a) about 100 parts of by weight of a resin

5 component containing

1) from about 20% by weight to about 80% by weight of an epihalohydrin polymer, and

10 2) correspondingly, from about 80% by weight to about 20% by weight of an insulating silicone polymer having a $\tan \delta$ of less than one, such silicone being a gum silicone having a durometer of from about 5 to about 30,

15 b) from about 10 to 200 parts by weight per hundred parts by weight resin component of barium titanate, and

15 c) from 0 to 30 parts by weight of a plasticizer.

2. A non-tacky electrical stress control material according to claim 1, wherein said resin component comprises from 30% to 70% of an epihalohydrin polymer, and correspondingly, from 70% to 30% of said insulating silicone 20 polymer.

3. A non-tacky electrical stress control material according to claim 1 or 2, wherein said plasticizer is selected from the group consisting of trimellitates, phthalates, benzoates, fatty acid ester derivatives, fatty acid ester alcohols, dimer acid esters, glutarates, adipates, sebacates, polymeric polyesters, rosin esters and acrylate esters.

60557-5742

4. A non-tacky electrical stress control material according to any one of claims 1 to 3, further comprising from 1 part to 15 parts per hundred parts of the resin component, of a metal flake.

5 5. A non-tacky electrical stress control material according to claim 4, wherein said metal flake is aluminum flake.

6. A non-tacky electrical stress control material according to claim 5, comprising from 50 to 200 parts of the 10 barium titanate.

SMART & BIGGAR

PATENT AGENTS

OTTAWA, CANADA