

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C10L 1/18	A1	(11) International Publication Number: WO 96/11998 (43) International Publication Date: 25 April 1996 (25.04.96)
(21) International Application Number: PCT/US94/11619 (22) International Filing Date: 14 October 1994 (14.10.94) (60) Parent Application or Grant (63) Related by Continuation US 08/083,826 (CON) Filed on 25 June 1993 (25.06.93) (71) Applicant (for all designated States except US): EXCELLENE LIMITED [VU/VU]; Security Trustees Ltd., George Vasaris & Co., 1st floor, Law House, Kumul Highway, Port Vila (VU). (72) Inventor; and (75) Inventor/Applicant (for US only): FRITZ, James, Edward [US/US]; 271 Crutcher Road, Port Townsend, WA 98368 (US). (74) Agent: BEACH, Robert, W.; 2919 West Dravus Street, Seattle, WA 98199 (US).		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ). Published <i>With international search report.</i>
(54) Title: FORTIFIED HYDROCARBON AND PROCESS FOR MAKING AND USING THE SAME (57) Abstract Fortified hydrocarbon torch gas is a mixture of a major portion by weight of hydrocarbon base gas such as liquefied petroleum gas (LPG) or natural gas and additive selected from 1,2-ethanediol, 1,2-propanediol, 1,3-butanediol, glycerol, diethylene glycol, ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol dimethyl ether, ethyl acetate, n-propyl alcohol, isopropyl alcohol, n-butyl alcohol, isobutyl alcohol, sec butyl alcohol, propionaldehyde, and butyraldehyde.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

FORTIFIED HYDROCARBON
AND PROCESS FOR MAKING AND USING THE SAME

Technical Field

The present invention relates to hydrocarbon
5 gas for use in cutting and/or welding torches fortified
by the addition of an additive or conditioner,
particularly a double additive.

Background Art

Various attempts have been made heretofore to
10 improve gas used in cutting and/or welding torches by
adding an additive or a double additive to them. These
prior art gases have been composed of various
hydrocarbons from methane to octane and some have
included propane and butane. Harris U.S. patent No.
15 1,565,935, issued December 15, 1925, for example,
fortified a wet casinghead gas composed of methane,
ethane, propane, butane and hexane by the addition of
ethyl ether [diethyl ether] $[(C_2H_5)_2O$ or $C_4H_{10}O]$ or
methyl ether [dimethyl ether] $[(CH_3)_2O]$. Another
20 patent that proposed to add ethyl ether, also called
ethyl oxide, to a gas including propane or butane and
propane is White U.S. patent No. 2,513,769, issued July
4, 1950.

British patent specification No. 813,981,
25 published May 27, 1959 (Oxy-Ferrolene Limited)
proposes to add to hydrocarbon gas an oxygen-containing
compound such as isopropyl ether [diisopropyl ether]
 $[(CH_3)_2CH_2O$ or $(C_3H_7)_2$ or $C_6H_{14}O]$, methyl isopropyl
ether, methyl propyl ether $[(CH_3)CH_2CH_2OCH_3$ or $C_4H_{10}O]$,
30 normal propyl ether, ethanol $[CH_3CH_2OH]$ and methanol
 $[CH_3OH]$. This British patent also suggests the
incorporation of more than one compound but does not
suggest any specific double compounds.

Seley U.S. patent No. 2,411,759, issued
35 November 26, 1946, does suggest the use of double

additives, namely, ethyl oxide [diethyl ether or ethyl ether] $[(C_2H_5)_2O]$ and benzine [benzene] $[C_6H_6]$. White U.S. patent No. 2,951,750, issued September 6, 1960, refers to the prior double additives for torch gas of
5 dimethyl ether [methyl ether] $[(CH_3)_2O]$ and benzine [benzene] $[C_6H_6]$ at column 1, lines 21 to 25, presumably as disclosed in the Seley patent, and then proposes the use of the double additive of propylene oxide [1,2-epoxy propane] $[C_3H_6O]$ and dimethyl ether
10 $[(CH_3)_2O]$ at column 1, lines 55 to 62, instead of using benzine and dimethyl ether.

In addition, Kessler U.S. patent No. 3,591,355, issued July 6, 1971, proposed the addition of methanol $[CH_3OH]$ to a gas containing propane or a
15 double additive to torch gas composed of a liquid alkanol such as methanol and a mixture of alkanes such as pentane and isopentane. White U.S. patent No. 3,989,479, issued November 2, 1976, also proposed the addition of methanol and British patent specification
20 No. 569,108, accepted May 4, 1945, proposed the addition of ammonia. This British patent also recommended increasing the amount of propane in producer gas, water gas, Mond gas and other commercially available gas mixtures in which methane
25 predominated.

Medsker U.S. patent No. 2,908,599, issued October 13, 1959, stated that methyl borate and acetone had been used previously in a fuel for torch use citing U.S. patent No. 2,281,910. The Medsker patent proposed
30 a mixture of methyl borate and hexane as an additive for a gaseous fuel. The Bialosky et al. patent No. 2,281,910, issued May 5, 1942, discloses a liquid flux containing methyl borate and a ketone, such as acetone $[CH_3COCH_3]$ or methyl ethyl ketone [1,2-butanone]
35 $[CH_3CH_2COCH_3]$, to be subjected to a stream of acetylene, hydrogen or similar combustible gas for coating the work with boric acid or oxide.

German Offenlegungsschrift No. 24 55 727,
published May 28, 1975, proposes a multitude of
additions for fortifying hydrocarbons including higher
mono-, di- and polyalcohols having 5 to 20 carbon atoms
in each molecule. It is stated at page 12, line 24
that:

The preferred alcohols are the mono-, di- and
polyalcohols of the C₅ to C₈ hydrocarbons
which . . . contain pentanols, hexanols,
heptanols, octanols, pentenols, hexenols,
heptenols and octenols.

Belgian patent No. PV 35 394A, issued January
13, 1967, discloses a method and device for obtaining a
fuel mixture of homogeneous composition by spraying
into a gaseous aliphatic hydrocarbon fuel such as
propane alone or mixed with propylene a conditioning
liquid composed of five classes of ingredients, namely:

- (a) a component of fuel in liquid form which is
the same as the base fuel
- (b) a combustion activator which can be ethyl
ether or a halogeno-ether, particularly a
chloroether;
- (c) a high calorific value liquid hydrocarbon for
enhancing the evaporation of the activator
and which is soluble in the activator, such
as 2-methyl-butane having the formula
 $\text{CH}_3\text{CH}_2\text{CH}(\text{CH}_3)_2$ in an amount approximately
equal to the amount of activator, i.e.,
between 1% and 12%, and preferably between 5%
and 10% of the weight of the fuel used;
- (d) a liquid oxidation catalyst, preferably
selected from among the constituents of
pyridine bases, particularly the
alkylpyridines where the alkyl groups are of
low molecular weight in an amount between
0.1% and 1% of the weight of fuel; and
- (e) a hydrotrope which can be a terpenic
hydrocarbon, preferably being mixed with a

phenylcarbinol or a carbinol alkyl ether, as well as with an aliphatic ester of carboxylic aromatic acid, preferably methyl salicylate.

This five-component conditioning liquid mixture is
5 sprayed into the gaseous fuel at the moment that it is used, so that there will be no preferential vaporization of any of the constituents of the conditioning liquid.

Belgian patent of addition No. BE-A-697,274,
10 issued June 30, 1967, which constitutes an addition to the principal patent No. PV 35 394, discloses the use of an alternative type of combustion activator in the five-component conditioning liquid of the main patent which is sprayed into the gaseous fuel.

15 Instead of using ethyl ether or a halogeno-ether as disclosed by the main patent for the activator component, the patent of addition uses as a combustion activator a hydrocarbon-oxygenated derivative, particularly an aliphatic hydrocarbon belonging to the
20 group of esters, ketones and olefin oxides having the general formula $C_nH_mO_p$ where n is an integer between 2 and 6, m is an integer between $2n - 2$ and $2n + 2$, and p is equal to 1 or 2. The specific activators disclosed are:

25 acetone (C_3H_6O)
ethyl methyl ketone (C_4H_8O)
mesityl oxide [4-methyl-3-penten-2-one]
 $(CH_3)_2C=CHCOCH_3$ ($C_6H_{10}O$)
ethyl acetate ($C_4H_8O_2$)
30 ethylene oxide (C_2H_4O)
propylene oxide (C_3H_6O)
butylene oxide [1,2-epoxybutane] (C_4H_8O)

The principal torch gas used heretofore has been acetylene which is comparatively expensive,
35 difficult to store and to transport, requires the use of almost pure oxygen with it and forms persistently adherent scoria when used for cutting ferrous metal.

Also, methyl ethyl ketone (MEK) has been used by itself heretofore as an additive for torch gas.

Disclosure of the Invention

A principal object of this invention is to provide a simple additive for fortifying hydrocarbon torch gas so as to have characteristics superior to those of acetylene, especially for cutting ferrous metal, and also for welding. Such object also includes providing fortified hydrocarbon having characteristics superior to those of hydrocarbon fortified only by the addition of methyl ethyl ketone.

A particular object is to provide a torch gas which will have high flame temperature and intense heating capability.

A further object is to provide torch gas that can be stored and transported easily and economically.

Another object is to provide a torch gas having a base gas which is readily available in almost the entire world, can be provided more economically and is easy to fortify for enhancing its attributes.

It is also an object to provide a torch gas enabling ferrous metal to be cut faster and cleaner.

Another object is to provide a gas that can be used by torches for cutting under water at considerable depths.

An additional object is to provide a gas that can be used for torch cutting more economically because it will combine effectively with oxygen containing a higher proportion of adulterating gases which cannot be used with acetylene.

The foregoing objects can be accomplished by utilizing liquefied petroleum gas fortified with methyl ethyl ketone and with lower pluraloxyhydrocarbons, namely dioxy- and trioxyhydrocarbons having two to four carbon atoms in each molecule or with a combination of additions from such pluraloxyhydrocarbons and/or

selected lower monooxyhydrocarbons having three or four carbon atoms in each molecule.

Description of the Best Mode

Liquefied petroleum gas (LPG) is the preferred base gas for the fortified torch gas of the present invention because of its high butane and propane content. Both the *n*-butane and isobutane isomers of butane are usually present in LPG, but a substantial amount of butane may have been removed from LPG sold as fuel because of the demand from industry for butane derivatives, in which case the LPG is composed largely of propane. It is, however, desirable that there be a reasonable proportion of butane in the LPG, such as from 5% to 40%.

Alternatively, the base gas could be propane or butane alone or any mixture of these gases or propylene or other gaseous hydrocarbon.

The additive or conditioner used to fortify the base gas may be simply a combination of methyl ethyl ketone (MEK), otherwise known as 2-butanone, having the formula $\text{CH}_3\text{COCH}_2\text{CH}_3$ and a lower pluraloxyhydrocarbon. MEK is a liquid with a boiling point of 70.6 degrees C. and a specific gravity of 0.805 at 20 degrees C.

LPG must be stored under pressure to keep it in a liquid state, but relatively heavy pressurized storage tanks and handling equipment for LPG is commercially practical and customary.

Without being fortified, LPG mixed with oxygen is not very effective for torch cutting and welding, not nearly as effective as acetylene gas mixed with substantially pure oxygen, but by enriching the base LPG with an effective additive the flame temperature is considerably increased and the heating capability is greatly improved.

The amount of additive used will depend on the extent to which it is desired to improve the

characteristics of the base gas, but the amount would be 3% to 10% of the base gas by weight. Where a combination of MEK and a lower pluraloxyhydrocarbon is used, preferably 3% to 5% of MEK and 2% or 3% of the lower pluraloxyhydrocarbon is appropriate as the sole additive.

The procedure for combining the additive with the LPG is simple. The fortifying liquid is simply mixed with the hydrocarbon in liquid form. The additive which is liquid at normal temperatures is supplied to the storage tank in which the LPG under liquefying pressure is to be stored or transported. It is quite practical to supply the additive to standard 55-gallon drums.

If more additive is supplied than about 6% of the base gas by weight, such additive should be supplied in conjunction with a catalyst, preferably activated carbon in the form of powder, granules or pellets to insure homogeneous mixing. The activated carbon is amorphous, preferably having been produced from coal or petroleum coke. Alternative catalysts that can be used are platinum, cupric oxide and granular silver carried by a suitable carrier.

The amount of activated carbon used is not critical, but it should be placed in the bottom of a storage container to facilitate mixing of the additive with the hydrocarbon base gas when it is supplied to the container under pressure. An amount of such catalyst between 1% and 5% of the weight of the additive would be satisfactory. The resulting liquid mixture of base gas and additive or conditioner will be azeotropic at normal temperatures so that the fortified torch gas evaporated from the fortified liquid mixture will be homogeneous when it is released from the storage container to the torch without the addition of other hydrocarbon gas or being supplied to other hydrocarbon gas.

In order to provide an effective cutting flame, it is necessary to supply to an acetylene torch oxygen that is in substantially pure form, such as at least 99% oxygen by volume. Satisfactory cutting temperatures can be provided by mixing with the fortified base gas of the present invention less pure oxygen such as oxygen having a purity of approximately 95%, the adulterant being nitrogen, carbon dioxide and other gas components of air. Even when oxygen having a purity as low as 90% is used, the flame temperature of base LPG of approximately 5,000 degrees F. (2,760 degrees C.) can be raised to approximately 5,800 degrees F. (3204.44 degrees C.) to 6,000 degrees F. (3315.56 degrees C.) by use of the base LPG fortified by additives according to the present invention. Such impure oxygen can be produced economically by compressing air to about 4,000 psi, chilling it to minus 360 degrees F. (minus 217.78 degrees C.) which liquefies the air and then allowing the temperature of the liquefied air to rise gradually while venting the container to release the nitrogen component of the liquefied air which vaporizes at minus 320 degrees F. (minus 195.56 degrees C.) leaving the oxygen in liquid form.

In other processes for producing impure oxygen, nitrogen of the air is removed by zeolite resulting in oxygen of 90% to 95% purity.

An advantage of using the fortified base gas of the present invention over acetylene for cutting ferrous metal is that a clean precise kerf is obtained. Oxyacetylene cutting produces a hard scoria persistently adherent to the work which increases the heating required and usually must subsequently be chipped off the work. Utilization of the fortified torch gas of the present invention produces a soft friable scoria which is sloughed off the work and out of the kerf as the cutting progresses to leave a

narrower clean kerf with virgin metal along opposite margins of the kerf.

A particular advantage which the fortified torch gas of the present invention has is that it can be used for flame cutting under water to a depth of 300 feet. The use of the oxyacetylene torch is limited to 20 feet (6.1 meters) under water because at pressures to which it would be necessary to subject the gas to enable it to be dispensed to the cutting torch at greater depths the acetylene will explode. Consequently, the only alternative that has been available for cutting under water at depths greater than about 20 feet prior to use of MEK as an additive to hydrocarbon gas has been the use of a carbon arc, the action of which is slow and the use of which is dangerous.

While the use of MEK has been beneficial in expediting cutting of metal, the use of MEK enhanced by the addition of tert-butyl alcohol (TBA) has increased the cutting speed from 5% to 10%, and the use of MEK and methyl tetra-butyl ether (MTBE) in combination has increased the cutting speed to 20% to 25% faster than where MEK has been used alone as an additive and about 15% faster than the cutting speed where the MEK has been enhanced with TBA. Use of MEK in conjunction with a lower pluraloxyhydrocarbon is preferable.

Use of hydrocarbon gas such as LPG for soldering, brazing or light metal cutting is rendered more effective if the additive of the present invention is mixed with the gas. For such use it is preferable to use less additive than in the case of torch gas for cutting or welding thick metal. For soldering, brazing or light cutting, an amount of additive within the range of 2% to 5% by weight is adequate, and such an amount can be mixed sufficiently intimately with the hydrocarbon gas without the use of a catalyst.

As alternatives to the use of a combination of MEK and a lower pluraloxyhydrocarbon described above

the additive of the present invention may be simply a single lower pluraloxyhydrocarbon, namely, a dioxy- or trioxyhydrocarbon having from 2 to 4 carbon atoms in the molecule and which may be an alcohol, an ether or an acetate. Particular examples of such pluraloxyhydrocarbons are specified in the tables below:

	<u>Name</u>	<u>Formula</u>	<u>Formula Weight</u>
	<u>Dihydric Alcohols (Diols)</u>		
10	1,2-ethanediol HOCH ₂ CH ₂ OH, also called ethylene glycol	C ₂ H ₆ O ₂	Formula Weight 62
	1,2-propanediol CH ₃ CH(OH)CH ₂ OH, also called propylene glycol	C ₃ H ₈ O ₂	Formula Weight 76
15	1,3 butanediol CH ₃ CH(OH)CH ₂ CH ₂ OH, also called 1,3 butylene glycol	C ₄ H ₁₀ O ₂	Formula Weight 90

Trihydric Alcohols

	glycerol HOCH ₂ CH(OH)CH ₂ OH	C ₃ H ₈ O ₃	Formula Weight 92
20	diethylene glycol HOCH ₂ CH ₂ OCH ₂ CH ₂ OH, also called bis (2-hydroxyethyl) ether	C ₄ H ₁₀ O ₃	Formula Weight 106

Dioxyethers

25	ethylene glycol monomethyl ether CH ₃ OCH ₂ CH ₂ OH, also called 2-methoxyethanol	C ₃ H ₈ O ₂	Formula Weight 76
----	---	--	-------------------

ethylene glycol monoethyl ether $C_4H_{10}O_2$

Formula Weight 90

$CH_3CH_2OCH_2CH_2OH$, also called 2-ethoxyethanol

ethylene glycol dimethyl ether $C_4H_{10}O_2$

Formula Weight 90

$CH_3OCH_2CH_2OCH_3$, also called 1,2 dimethoxyethane

Acetates

ethyl acetate $C_4H_8O_2$ Formula Weight 88

$CH_3COOC_2H_5$, also called acetic ester or

acetic ether

The effect of various monooxyhydrocarbons to enhance the combustion of torch gases when used alone is varied and unpredictable. The following lower monooxyhydrocarbons are reasonably beneficial in combination or in combination with pluraloxyhydrocarbon as enhancing additives without the use of other additive components. Such monooxyhydrocarbons will have three or four carbon atoms in a molecule.

Name Formula Formula Weight

Monohydric Alcohols

n-propyl alcohol C_3H_8O Formula Weight 60

$CH_3CH_2CH_2OH$, also called 1-propanol

isopropyl alcohol C_3H_8O Formula Weight 60

$(CH_3)_2CHOH$, also called 2-propanol

n-butyl alcohol $C_4H_{10}O$ Formula Weight 74

$CH_3CH_2CH_2CH_2OH$, also called 1-butanol

12

isobutyl alcohol $C_4H_{10}O$ Formula Weight 74
(CH_3)₂CHCH₂OH, also called 2-methyl-1-propanol

sec butyl alcohol $C_4H_{10}O$ Formula Weight 74
CH₃CH₂CH(OH)CH₃, also called 2-butanol

5

Ketones

methyl ethyl ketone C_4H_8O Formula Weight 72
CH₃COCH₂CH₃, also called 2-butanone

Aldehydes

10 propionaldehyde C_3H_6O Formula Weight 58
CH₃CH₂CHO, also called 1-propanal

butyraldehyde C_4H_8O Formula Weight 72
CH₃CH₂CH₂CHO

15 While a single one of the monooxyhydrocarbons listed
above does not individually enhance LPG, butane or
propane gas sufficiently to be comparable to acetylene
for use in cutting or welding, the combination of two
or three additives selected from the
monooxyhydrocarbons specified above and the
dioxhydrocarbons and trioxyhydrocarbons will provide
20 greater enhancement than any one of such chemicals
alone.

Also, while it is practical to utilize a
single pluraloxyhydrocarbon as an additive, better
results are obtained by combining pluraloxyhydrocarbons
25 with each other or with a monooxyhydrocarbon of a
suitable type without using other components in the
additive.

For example, while LPG enhanced with 3% by
weight of the base gas of either 1,2 ethanediol or

ethylene glycol monomethyl ether will enable a perfect cut of steel to be made as rapidly as by the use of acetylene, a cutting operation in which the base gas is enhanced with 3% by weight of each of such additives
5 will enable an excellent cut to be made at a rate faster than could be obtained using acetylene.

Also, as good and almost as fast a cut can be obtained by using as an additive 3% by weight of the base gas of 1,2-ethanediol and 2% by weight of the base
10 gas of methyl ethyl ketone. Comparable results can be obtained by using 3% by weight of the base gas of ethylene glycol monomethyl ether and n-propyl alcohol.

While mention has been made of using 2% or 3% of each of two oxyhydrocarbons specified above in
15 combination, it is also possible to obtain good enhancement by using a combination of 2% by weight of the base gas of each of three of the oxyhydrocarbons specified above.

Claims

1. Fortified hydrocarbon torch gas which is mixture of a major portion by weight of hydrocarbon base gas and additive consisting essentially of a minor portion by weight of additive selected from the group consisting of dioxyhydrocarbons and trioxyhydrocarbons having 2 to 4 carbon atoms in a molecule.

2. The torch gas defined in claim 1, in which the amount of additive is within the range of 0.5% to 13% of the hydrocarbon base gas by weight.

3. The torch gas defined in claim 1, in which the amount of additive is within the range of 3% to 7% of the hydrocarbon base gas by weight.

4. The torch gas defined in claim 1, in which the additive is only one dioxyhydrocarbon or trioxyhydrocarbon.

5. The torch gas defined in claim 4, in which the additive is selected from the group consisting of 1,2-ethanediol, 1,2-propanediol, 1,3 butanediol, glycerol, diethylene glycol, ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol dimethyl ether and ethyl acetate.

6. Fortified hydrocarbon torch gas which is a mixture of a major portion by weight of hydrocarbon base gas and a minor portion by weight of additive which additive consists essentially of two or more components selected from the group consisting of 1,2-ethanediol, 1,2-propanediol, 1,3 butanediol, glycerol, diethylene glycol, ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol dimethyl ether, ethyl acetate, n-propyl alcohol,

isopropyl alcohol, n-butyl alcohol, isobutyl alcohol, sec butyl alcohol, methyl ethyl ketone, propionaldehyde, and butyraldehyde.

7. Fortified hydrocarbon torch gas which is an azeotropic mixture of a major portion by weight of hydrocarbon base gas and a minor portion by weight of additive selected from the group consisting of 1,2-ethanediol, 1,2-propanediol, 1,3 butanediol, glycerol, diethylene glycol, ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol dimethyl ether and ethyl acetate.

8. Fortified hydrocarbon torch gas which is an azeotropic mixture of a major portion by weight of hydrocarbon base gas maintained in liquid form under pressure and a minor portion by weight of fortifying liquid additive selected from the group consisting of 1,2-ethanediol, 1,2-propanediol, 1,3 butanediol, glycerol, diethylene glycol, ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol dimethyl ether and ethyl acetate.

9. Fortified hydrocarbon torch gas which is a mixture of a major portion by weight of hydrocarbon base gas and additive consisting essentially of a minor portion by weight of dioxyether having not more than 4 carbon atoms in a molecule.

10. Fortified hydrocarbon torch gas which is a mixture of a major portion by weight of hydrocarbon base gas and additive consisting essentially of a minor portion by weight of additive selected from the group consisting of ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol dimethyl ether and ethyl acetate.

11. Fortified hydrocarbon torch gas which is a mixture of a major portion by weight of hydrocarbon base gas and a minor portion by weight of additive which additive consists essentially of at least one alcohol component selected from the group consisting of 1,2-ethanediol, 1,2-propanediol, 1,3 butanediol, glycerol, diethylene glycol, n-propyl alcohol, isopropyl alcohol, n-butyl alcohol, isobutyl alcohol and sec butyl alcohol, and at least a second component selected from the group consisting of ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol dimethyl ether, ethyl acetate, methyl ethyl ketone, propionaldehyde, and butyraldehyde.

12. Fortified hydrocarbon torch gas which is an azeotropic mixture of a major portion by weight of hydrocarbon base gas maintained in liquid form under pressure and a minor portion by weight of fortifying liquid additive selected from the group consisting of ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol dimethyl ether and ethyl acetate.

13. The torch gas defined in any one of claims 1 to 12, in which the base gas is LPG (liquid petroleum gas).

14. The torch gas defined in any one of claims 1 to 12, in which the hydrocarbon base gas is natural gas.

15. The process of making fortified hydrocarbon for use as torch gas by supplying to hydrocarbon base gas maintained in liquid form under pressure additive consisting essentially of additive selected from the group consisting of dioxyhydrocarbons and trioxyhydrocarbons having 2 to 4 carbon atoms in a

molecule, which additive is supplied to the hydrocarbon base as the only additive.

16. The process of making fortified hydrocarbon for use as torch gas by supplying to hydrocarbon base gas maintained in liquid form under pressure additive consisting essentially of two or more chemicals selected from the group consisting of 1,2-ethanediol, 1,2-propanediol, 1,3 butanediol, glycerol, diethylene glycol, ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol dimethyl ether, ethyl acetate, n-propyl alcohol, isopropyl alcohol, n-butyl alcohol, isobutyl alcohol, sec butyl alcohol, methyl ethyl ketone, propionaldehyde, and butyraldehyde as the only additive.

17. The process of torch cutting ferrous metal which comprises supplying to hydrocarbon base gas maintained in liquid form under pressure fortifying liquid additive selected from the group consisting of 1,2-ethanediol, 1,2-propanediol, 1,3 butanediol, glycerol, diethylene glycol, ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol dimethyl ether and ethyl acetate to form an azeotropic liquid mixture, vaporizing such azeotropic fortified torch gas liquid mixture, and supplying a gas mixture vaporized from such fortified torch gas liquid mixture and oxygen to a torch.

18. The process of torch cutting ferrous metal which comprises supplying to hydrocarbon base gas maintained in liquid form under pressure fortifying additive selected from the group consisting of ethylene glycol monomethyl ether, ethylene glycol monoethyl ether, ethylene glycol dimethyl ether and ethyl acetate to form an azeotropic liquid mixture, vaporizing such azeotropic fortified torch gas liquid mixture, and

supplying a gas mixture vaporized from such fortified torch gas liquid mixture and oxygen to a torch.

19. The process defined in any one of claims 15 to 18, including supplying LPG as the hydrocarbon base gas.

20. The process defined in any one of claims 15 to 18, including supplying natural gas as the hydrocarbon base gas.

21. The process defined in any one of claims 15 to 18, including supplying additive within the range of 0.5% to 13% of the hydrocarbon base gas by weight.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US94/11619

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : C10L 1/18

US CL : 044/401, 438, 446, 448

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 048/197 FM; 044/401, 438, 446, 448

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A, 5,236,467 (Fritz) 17 August 1993 See Abstract	1-21
A	US,A, 5,232,464 (Klezi) 03 August 1993 See Col. 4, lines 28-34	1-21
A	UK,A, 0,569,108 (Hobbs) 04 May 1945 See page 2 line 110	1-21
A	US,A, 3,869,262 (Mayerhoffer et al) 04 March 1975 See Abstract	1-21
Y	DE,A, 24 55 727 (Flamex) 28 May 1975 See Abstract	1-21

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	
A document defining the general state of the art which is not considered to be of particular relevance	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
E earlier document published on or after the international filing date	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
O document referring to an oral disclosure, use, exhibition or other means	*Z* document member of the same patent family
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

16 FEBRUARY 1995

Date of mailing of the international search report

10 MAR 1995

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

JACQUELINE V. HOWARD

Telephone No. (703) 308-2514