

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
13 March 2008 (13.03.2008)

PCT

(10) International Publication Number
WO 2008/030177 A1

(51) International Patent Classification:

C23C 14/04 (2006.01) *C23C 14/06* (2006.01)

B23B 51/02 (2006.01) *C23C 30/00* (2006.01)

(74) Agent: **HÄGGLÖF, Henrik**; Sandvik Intellectual Property AB, S-811 81 Sandviken (SE).

(21) International Application Number:

PCT/SE2007/050621

(22) International Filing Date:

5 September 2007 (05.09.2007)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

102006042226.0 6 September 2006 (06.09.2006) DE

(71) Applicant (for all designated States except US): **SANDVIK INTELLECTUAL PROPERTY AB** [SE/SE]; S-811 81 Sandviken (SE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **ÅSTRAND, Maria** [SE/SE]; Överbacka, S 743 91 Storvreta (SE). **MÜLLER, Peter** [DE/DE]; Hasselmannring 15, 61352 Bad Homburg (DE). **SCHNEIDER, Thomas** [DE/DE]; Annastrasse 10, 66386 St. Ingbert (DE). **HEIL, Thomas** [DE/DE]; Udo-Müller-Ring 67, 63486 Bruchköbel (DE).


(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

(54) Title: COATED DRILL AND A METHOD OF MAKING THE SAME



(57) Abstract: The present invention relates to a drill comprising a cemented carbide or high speed steel substrate and a coating wherein the coating comprises: - a first layer system having a multilayered structure covering substantially the whole active part of the drill, - a second layer system having a multilayered structure covering only the tip area of the drill. Drills according to the present invention have good wear resistance and improved properties when reconditioning the drill. The present invention also relates to a method of making a drill according to the present invention.

WO 2008/030177 A1

Coated drill and a method of making the same

The present invention relates to a twist drill for metal machining coated with a first and a second layer system, wherein the first layer system has been deposited over substantially the whole active part of the twist drill whereas the second layer system has been deposited only onto the tip area of the twist drill. The present invention also relates to a method of manufacturing such a twist drill according to the present invention.

Twist drills are often coated with a hard material to increase tool life by enhancing the wear resistance. A high wear resistance is advantageous at the tip area of the twist drill where the cutting takes place whereas properties like low friction and smoothness are advantageous on other parts of the twist drill, for example, to enhance chip transportation. The chip transport is particularly important when the drilled depth is relatively large compared to the nominal diameter. In some cases, by coating the chip flutes, the chip transport can, compared to an uncoated drill, even be decreased. Hence, achieving optimum properties for different parts of a twist drill can be difficult and several attempts have been made to accomplish this.

Another problem, which especially applies to twist drills coated along the cylindrical land, is referred to as pitting or pitting wear and includes spalling of the wear resistant coating on the cylindrical land and typically in the area close to the drill corner.

Pitting often includes not only spalling of the deposited coating but also part of the substrate from the twist drill. When the drill is used for the first time it is not a problem as the main cutting edge and the rake face, which are the areas determining the life time of the drill, are not affected by the pitting. The pitting appears at a small distance from the corner and the main cutting edge. However, when the drill is reconditioned it is often reduced somewhat in length and hence the worn region comes close to the cutting region and therefore the

pitting can be detrimental to the life time of a reconditioned drill. As cemented carbide twist drills are very expensive it is necessary that it can be cut, reground and recoated several times and hence pitting has to be minimized to enable this.

Recently, new types of hard coatings usually with a multilayered structure, particularly useful for the wear protection of the main cutting edge and the rake faces, have been developed. Unfortunately, such coatings are very strongly prone to such pitting formation.

EP 0 983 393 B describes aperiodic multilayered coatings which leads to an increased hardness and increased wear resistance of the cutting edge. An example of such coating is alternating TiN and (Ti,Al)N layers having an individual thickness in the nanometer range, 3-100 nm.

JP 7237046A describes a method of depositing a coating onto a drill where the coating becomes thicker in the tip area compared to the rest of the drill body. The difference in thickness is achieved by partly covering the drill with a loose fitting metal cylinder which causes a gradual decrease in the amount of deposited material further away from the drill tip.

US 6,688,817 B2 describes a drill that has been pretreated by applying an abrasive material to merely the tip, i.e. by a microblasting operation to roughen the surface. Thereafter substantially the whole drill is coated with a hard material. The coated drill will after coating have a larger surface roughness on the drill tip compared to the rest of the drill.

DE 196 02 030A describes a drill where only the tip has been coated, leaving the rest of the drill uncoated. The coating can be TiN, (Ti,Al)N or Ti(C,N).

An object of the present invention is to provide a twist drill with good wear resistance at the tip area and with good chip transportation properties in other parts of the twist drill.

Another object of the present invention is to provide a twist drill which is well adapted to reconditioning including regrinding and recoating.

Yet another object of the present invention is to provide a twist drill that is less prone to pitting formation.

It has surprisingly been found that, by providing a twist drill with a first layer system deposited over its whole active part and a second layer system deposited only at the tip area of the drill, these objects can be fulfilled. It has also been found that pitting formation is avoided not only because the second layer system covers a relatively small area but also because this second layer system is deposited onto the first layer system, not directly onto the substrate, whereby, even if this second layer system spalls, the first layer system is not affected.

Description of the drawings

FIG 1 and FIG. 2 show schematic drawings of a twist drill and its tip area wherein:

- 1-active part
- 2-tip area
- 3-chip flute
- 4-cylindrical land (margin)
- 5-main cutting edge
- 6-corner
- 7-rake face

Detailed description of the invention

The present invention relates to a coated twist drill comprising a substrate body, preferably of cemented carbide or high speed steel, and a coating comprising two layer systems. The first layer system is deposited substantially over the whole active part of the twist drill whereas the second layer system is deposited only onto the tip area of the twist drill. The tip area is defined as the area reaching from the tip of the drill up to a distance, towards the base of the drill, of 0.30 to 1.5 times the diameter of the drill.

The drill preferably has a diameter of 0.50 to 35 mm, more preferably 2.0 to 25 mm.

The first and second layer systems are both multilayered systems and the first and second layer system can be the same or different with regard to the thickness of the individual layers and the average chemical composition. By multilayered structure is herein meant a structure comprising at least 5, preferably at least 10 individual layers. However, it can comprise up to several thousand individual layers.

Each of the layer systems can be aperiodic, periodic or combinations thereof. The individual layer thickness in the layer systems can be between 0.5 to 200 nm.

The suitable total thickness of the first and second layer system respectively is determined by the chemical composition of the coating as well as by the exact geometry of the drill.

In one embodiment the total thickness of the first layer system measured on the peripheral surface is 0.5 μm to 5 μm , preferably 0.5 to 3 μm .

In another embodiment the total thickness of the second layer system measured on the peripheral surface is 0.5 μm to 5 μm , preferably 0.5 to 3 μm .

In another embodiment the total thickness of the second layer system measured on the peripheral surface is 3 μm to 7 μm , preferably 5 to 7 μm .

In one embodiment, the first and/or second layer system, can comprise an aperiodic structure, either throughout the whole layer system, or as one or more sections of the layer system.

By aperiodic is understood that the thickness of a particular individual layer in the multilayered structure does not depend on the thickness of an individual layer immediately beneath nor does it bear any relation to an individual layer above the particular individual layer. Hence, the multilayered structure does not have any repeat period in the sequence of individual layer thicknesses.

The composition of each individual layer in the multilayered structure cannot easily be measured without contribution from adjacent layers due to the low thickness. What can be measured is the average composition over the whole multilayer structure.

However, the composition of each individual layer can be estimated from the composition of the targets, the sources used for the individual layers during deposition, but that does not give an exact composition. When thicker layers have been deposited, thick enough to be analysed individually, it has been found that the composition of the deposited layers can differ with a few percentages compared to the composition of the target material. Due to this fact any composition of the individual layers of the multilayered structure according to the present invention mentioned herein after are estimations from the compositions of the targets used during the deposition.

If an aperiodic section is present in the first and/or second layer system, the thickness of each individual layer within the aperiodic section will vary due to the aperiodic nature. However, the thickness of the individual layers is larger than 0.5 nm but smaller than 100 nm, preferably larger than 1 nm but smaller than 50 nm, most preferably larger than 2 nm but smaller than 30 nm. The sum of any ten consecutive layers in such a multilayered structure is preferably less than 300 nm.

In one embodiment of the present invention, the first and/or second layer system comprises at least two, preferably at least five, aperiodic multilayered structures which are periodically alternated with thicker homogeneous layers. The thickness of the individual layers in the aperiodic multilayered structure is preferably 0.5 to 100 nm, more preferably 1 to 50 nm and most preferably 2 to 30 nm. The thickness of the homogeneous layers is preferably 25 to 200, more preferably 50 to 120 nm.

The individual layers of the first and/or second layer systems comprises metalnitrides where one or more of the metal elements are selected from titanium (Ti), aluminium (Al), silicon (Si), chromium (Cr), niobium (Nb), hafnium (Hf), vanadium (V), tantalum (Ta), molybdenum (Mo), zirconium (Zr), tungsten (W), preferably from titanium (Ti), aluminium (Al), silicon (Si), chromium (Cr).

In one embodiment of the present invention, the average stoichiometry for the first and/or second layer system, as measured on the peripheral surface of the twist drill by e.g. microprobe or EDS is $(\text{Ti}_a\text{Al}_b\text{Si}_c\text{Cr}_d)\text{N}$ where $0 < a < 0.90$, $0.10 < b < 0.70$, $0 \leq c < 0.15$, $0 \leq d < 0.30$, and $a+b+c+d=1$.

In one embodiment of the present invention, the first layer system is an aperiodic multilayered structure varying $(\text{Ti},\text{Al})\text{N}$ layers with different Ti-content wherein the average chemical composition of the layer system is $(\text{Ti}_x\text{Al}_{1-x})\text{N}$ where $0.30 < x < 0.70$, preferably $0.40 < x < 0.60$.

In another embodiment of the present invention the first layer system comprises at least two, preferably at least five, aperiodic multilayered structures varying $(\text{Ti},\text{Al})\text{N}$ layers with different Ti-content wherein the aperiodic multilayered structures are repeatedly alternated with $(\text{Ti},\text{Al})\text{N}$ homogeneous layers. The composition of the homogenous layers is $(\text{Ti}_y\text{Al}_{1-y})\text{N}$ where $0.35 < y < 0.65$, preferably $0.40 < y < 0.60$ and the average composition of the multilayered structure is $(\text{Ti}_z\text{Al}_{1-z})\text{N}$ where $0.50 < z < 0.90$, preferably $0.70 < z < 0.90$.

In yet another embodiment of the present invention, the second layer system is an aperiodic multilayered structure varying $(\text{Ti},\text{Al})\text{N}$ layers with different Ti-content wherein the average chemical composition of the layer system is $(\text{Ti}_x\text{Al}_{1-x})\text{N}$ where $0.30 < x < 0.70$, preferably $0.40 < x < 0.60$.

In yet another embodiment of the present invention, the second layer system is an aperiodic or periodic $(\text{Ti},\text{Si})\text{N}+(\text{Al},\text{Cr})\text{N}$ multilayered structure wherein the thickness of the individual layers is between 0.5 and 200 nm with an average chemical composition of $(\text{Ti}_a\text{Al}_b\text{Si}_c\text{Cr}_d)\text{N}$ where $0.30 < a < 0.75$, preferably $0.40 < a < 0.65$, where $0.20 < b < 0.45$, preferably $0.20 < b < 0.35$, where $0 < c < 0.15$, preferably $0.02 < c < 0.10$, where $0.02 < d < 0.25$, preferably $0.05 < d < 0.20$ and $a+b+c+d=1$.

In one embodiment of the present invention, the second layer system is an aperiodic multilayered structure varying $(\text{Ti},\text{Al})\text{N}$ layers having different Ti-content wherein the thickness of the

individual layers is between 0.5 and 30 nm, and wherein the average chemical composition is $(\text{Ti}_k\text{Al}_{1-k})\text{N}$ where $0.50 < k < 0.90$, preferably $0.70 < k < 0.90$.

For several reasons it is advantageous to provide the first and second layer systems with different colours. First, a different colour of the second layer system can be advantageous for wear detection. Since the tip area is subjected to extensive wear compared to other parts of the drill, visual wear detection is a big advantage. The visual detection is also advantageous in the area that is subjected to pitting. As it is necessary to remove the larger part of these worn regions when reconditioning, a colour facilitating visual detection is to prefer.

Different colours also give another advantage during reconditioning. Normally when recoating a drill with only one thick functional coating over the whole active part of the drill the total coating thickness increases for each recoating. An increased coating thickness on the margin will increase the wear on the margin, at a short distance from the corner. Hence, when the drill has been reconditioned several times it most likely has to be cut to a substantially shorter length to remove the severe wear. According to the present invention the second layer system is only applied to the tip area which is partly cut away when reconditioned and thus shifting the tip area further up the drill towards the shaft. This leads to a slower build-up of coating since parts only coated with the first layer system will enter the tip area and those parts will initially have no build-up. Since the wear on the margin is dependent of the thickness of the coating, less build-up will lead to less wear. This means that a drill according to the present invention do not have to be cut off as much as a conventional drill during reconditioning in order to remove the worn parts and could thus be reconditioned more times. During reconditioning it is thus a big advantage to have different colours of the first and second layer system to monitor the build-up of coating.

The colors of the first and second layer systems can be achieved by either choosing a coating having a specific intrinsic color, or, by depositing a thin top layer having giving the specific color.

In one embodiment of the present invention the first layer system further comprises a top layer of sufficient thickness, preferably 0.1-1 μm , of $\text{Ti}_{1-x}\text{Al}_x\text{N}$ where $0.40 \leq x \leq 0.70$, preferably $\text{Ti}_{0.33}\text{Al}_{0.67}\text{N}$ or $\text{Ti}_{0.50}\text{Al}_{0.50}\text{N}$ to give a visible, black intrinsic color.

In yet another embodiment of the present invention the second layer system further comprises a top layer, having a lighter color than the first layer system, of sufficient thickness, preferably 0.1-1 μm , preferably of $\text{Ti}_{0.75}\text{Al}_{0.25}\text{N}$, $\text{Ti}_{0.84}\text{Al}_{0.16}\text{N}$, $\text{Ti}_{0.90}\text{Si}_{0.10}\text{N}$ or TiN to give a visible, bronze or yellow intrinsic color.

The present invention also relates to a method of making a coated twist drill. The method comprises providing a substrate body with the shape of a twist drill preferably having a diameter of 0.5 to 35 mm, more preferably 2 to 25 mm, preferably of cemented carbide or high speed steel. Onto said substrate two layer systems are deposited using conventional PVD techniques, where the first layer system is deposited substantially over the whole active part of the drill whereas the second layer system is deposited only onto the tip area of the drill.

The first and second layer system can be the same or different with regard to thickness of the individual layers and chemical composition. Each of the layer systems can be aperiodic, periodic or combinations thereof. The individual layers of the layer systems are deposited so that the thickness preferably is between 0.5 to 200 nm.

In one embodiment of the present invention, the first and/or second layer system is deposited in such a way that it comprises an aperiodic structure, either throughout the whole layer system, or as one and more sections of the layer system.

The aperiodic structure, if such a section is present in a layer system, is obtained by, during the deposition process, randomly opening and closing shutters from individual layer

targets, or by randomly switching said targets on and off. Another conceivable method is by randomly rotating or moving the to-be-coated substrates, in front of said targets. This is preferably done by placing the substrates on a 3-fold rotating substrate table arranged in order to obtain the aperiodic structure. The 3-fold rotation can be adjusted with regard to rotating speed and rotating direction, clockwise or counter clockwise. The aperiodic section will because of this comprise individual layers with a thickness that will vary due to the aperiodic nature.

The aperiodic structure is preferably deposited in such a way that the thickness of the individual layers is larger than 0.5 nm but smaller than 100 nm, preferably larger than 1 nm but smaller than 50 nm, most preferably larger than 2 nm but smaller than 30 nm. The sum of any ten consecutive layers in such a multilayered structure is less than 300 nm.

In one embodiment of the present invention, the first and/or second layer system is deposited in such a way that it comprise at least two, preferably at least five, aperiodic multilayered structures which are periodically alternated with thicker homogeneous layers. The thickness of the individual layers in the aperiodic multilayered structure is preferably 0.5 to 100 nm, more preferably 1 to 50 nm and most preferably 2 to 30 nm. The thickness of the homogeneous layers is preferably 25 to 200, more preferably 50 to 120 nm.

After deposition of the first layer system, parts of the twist drills are shielded by placing them into tight fitting metal cylinders so that only the tip area is exposed for deposition of the second layer system. The tip area is defined as the area reaching from the tip of the drill up to a distance, towards the base of the drill, of 0.3 to 1.5 times the diameter of the drill.

The metal cylinder has a tight fit to the twist drill to avoid deposition on the inside of the metal cylinder but also to achieve a sharp and visible border to the second layer system. This gives good control of the total coating thickness in each point of the drill.

Finally, the drills are preferably post treated to obtain a smooth surface, by e.g. wet blasting, dry blasting, polishing, grinding, brushing etc.

The suitable total thickness of the first and second layer system respectively is determined by the chemical composition of the coating as well as by the exact geometry of the drill.

In one embodiment the total thickness of the first layer system measured on the peripheral surface is 0.5 μm to 5 μm , preferably 0.5 to 3 μm .

In another embodiment the total thickness of the second layer system measured on the peripheral surface is 0.5 μm to 5 μm , preferably 0.5 to 3 μm .

In yet another embodiment the total thickness of the second layer system measured on the peripheral surface is 3 μm to 7 μm , preferably 5 to 7 μm .

In one embodiment, after the deposition of the first layer system, the drills are subjected to an intermediate post treatment operation, using wet blasting.

Most PVD techniques can be used according the present invention. However, the first and second layer systems are preferably deposited using cathodic arc evaporation using two or three pairs of arc targets of alloys of one or more metal elements selected from titanium (Ti), aluminium (Al), silicon (Si), chromium (Cr), niobium (Nb), hafnium (Hf), vanadium (V), tantalum (Ta), molybdenum (Mo), zirconium (Zr) or tungsten (W), preferably selected from titanium (Ti), aluminium (Al), silicon (Si) and chromium (Cr) or mixtures thereof, in a N_2 or mixed N_2+Ar gas atmosphere.

In one embodiment, the targets used during deposition are chosen so that the average stoichiometry for the first and/or second layer system, as measured on the peripheral surface of the twist drill by e.g. microprobe or EDS is $(\text{Ti}_a\text{Al}_b\text{Si}_c\text{Cr}_d)\text{N}$ where $0 < a < 0.90$, $0.10 < b < 0.70$, $0 \leq c < 0.15$, $0 \leq d < 0.30$, and $a+b+c+d=1$.

In one embodiment of the present invention, the first layer system is deposited in such a way that it will comprise an

aperiodic multilayered structure varying (Ti,Al)N layers with different Ti-content wherein the average chemical composition of the layer system is $(\text{Ti}_x\text{Al}_{1-x})\text{N}$ where $0.30 < x < 0.70$, preferably $0.40 < x < 0.60$.

In another embodiment of the present invention the first layer system is deposited in such a way that it will comprise at least two, preferably at least five, aperiodic multilayered structures varying (Ti,Al)N layers with different Ti-content wherein the aperiodic multilayered structures are repeatedly alternated with (Ti,Al)N homogeneous layers. The composition of the homogeneous layers is $(\text{Ti}_y\text{Al}_{1-y})\text{N}$ where $0.35 < y < 0.65$, preferably $0.40 < y < 0.60$ and the average composition of the multilayered structure is $(\text{Ti}_z\text{Al}_{1-z})\text{N}$ where $0.50 < z < 0.90$, preferably $0.70 < z < 0.90$.

In yet another embodiment of the present invention, the second layer system is deposited in such a way that it will comprise an aperiodic multilayered structure varying (Ti,Al)N layers with different Ti-content wherein the average chemical composition of the layer system is $(\text{Ti}_x\text{Al}_{1-x})\text{N}$ where $0.30 < x < 0.70$, preferably $0.40 < x < 0.60$.

In yet another embodiment of the present invention the second layer system is deposited in such a way that it will comprise an aperiodic or periodic $(\text{Ti},\text{Si})\text{N}+(\text{Al},\text{Cr})\text{N}$ multilayered structure wherein the thickness of the individual layers is between 0.5 and 200 nm with an average chemical composition of $(\text{Ti}_a\text{Al}_b\text{Si}_c\text{Cr}_d)\text{N}$ where $0.30 < a < 0.75$, preferably $0.40 < a < 0.65$, where $0.20 < b < 0.45$, preferably $0.20 < b < 0.35$, where $0 < c < 0.15$, preferably $0.02 < c < 0.10$, where $0.02 < d < 0.25$, preferably $0.05 < d < 0.20$ and $a+b+c+d=1$.

In yet another embodiment of the present invention, the second layer system is deposited in such a way that it will comprise an aperiodic multilayered structure varying (Ti,Al)N layers having different Ti-content wherein the thickness of the individual layers is between 0.5 and 30 nm, and wherein the average chemical composition is $(\text{Ti}_k\text{Al}_{1-k})\text{N}$ where $0.50 < k < 0.90$, preferably $0.70 < k < 0.90$.

In yet another embodiment, onto the first layer system, a top layer of sufficient thickness, preferably 0.1-1 μm , is deposited. The top layer preferably have a composition of $\text{Ti}_{1-x}\text{Al}_x\text{N}$ where $0.40 \leq x \leq 0.70$, preferably $\text{Ti}_{0.33}\text{Al}_{0.67}\text{N}$ or $\text{Ti}_{0.50}\text{Al}_{0.50}\text{N}$ to give a visible, black intrinsic color.

In yet another embodiment, onto the second layer system, a top layer, having a lighter color than the first layer system, of sufficient thickness, preferably 0.1-1 μm , is deposited. The top layer preferably has composition of $\text{Ti}_{0.75}\text{Al}_{0.25}\text{N}$, $\text{Ti}_{0.84}\text{Al}_{0.16}\text{N}$, $\text{Ti}_{0.90}\text{Si}_{0.10}\text{N}$ or TiN to give a visible, bronze or yellow intrinsic color.

Example 1 (invention)

Coated 8 mm drills according to the present invention were made by depositing a first and a second layer system, both having aperiodic multilayer structures, using reactive PVD arc discharge evaporation onto cemented carbide drills with a composition of 10 wt-% Co and balance WC. The multilayer structures were deposited from two arc targets, 1 and 2, with the drills mounted on a 3-fold rotating substrate table arranged in order to obtain the aperiodic structure. The arc evaporation was performed in an $\text{Ar}+\text{N}_2$ -atmosphere. After depositing the first layer system, the drills were subjected to a wet blasting treatment. Before depositing the second layer system, a part of the drill was shielded by a cylinder so that only the tip area of the drill was coated with the second layer system. The tip area was the area from the tip and approximately 10 mm from the tip. The composition of the two arc targets and the average composition of the first and second layer system are shown in Table 1.

The multilayered structure had a sequence of individual layers with an aperiodic, i.e. non-repetitive thickness. Cross section transmission electron microscopy investigation revealed that the individual nitride layer thicknesses ranged from 2 to 30 nm, and the total number of layers in each layer system exceeded 100.

Table 1

Drill No.	Layer system	Target 1	Target 2	Average chemical composition	Thickness (μm)
1 (inv.)	1 st	Ti _{0.75} Al _{0.25}	Ti _{0.33} Al _{0.67}	Ti _{0.50} Al _{0.50} N	1.2
	2 nd	Ti _{0.75} Al _{0.25}	Ti _{0.33} Al _{0.67}	Ti _{0.50} Al _{0.50} N	6.6

Example 2 (reference)

Coated 8 mm drills were made where the drills were either coated with only one layer system over the whole active part of the drill, or, coated with one layer system covering only the tip part of the drill. The layer systems both had aperiodic multilayer structures and were deposited using reactive PVD arc discharge evaporation onto cemented carbide drills with a composition of 10 wt-% Co and balance WC. The multilayer structures were deposited from two arc targets with the drills mounted on a 3-fold rotating substrate table arranged in order to obtain the aperiodic structure. The evaporation was performed in an Ar+N₂ gas mixture.

The tip area was the area from the tip and about 10 mm from the tip. The compositions of the two arc targets and the average composition of the layer systems are shown in Table 2.

The multilayered structure had a sequence of individual layers with an aperiodic, i.e. non-repetitive thickness. Cross section transmission electron microscopy investigation revealed that the individual nitride layer thicknesses ranged from 2 to 30 nm, and the total number of layers in each layer system exceeded 100.

Table 2

Drill No.	Layer system	Target 1	Target 2	Average chemical composition	Thickness (μm)
Ref. 1	1 st	Ti _{0.75} Al _{0.25}	Ti _{0.33} Al _{0.67}	Ti _{0.50} Al _{0.50} N	1.2
	2 nd	-		-	-
Ref. 2	1 st	-		-	-
	2 nd	Ti _{0.75} Al _{0.25}	Ti _{0.33} Al _{0.67}	Ti _{0.50} Al _{0.50} N	6.6

Example 3

Drills made according to Example 1 were compared to Ref. 1 in Example 2. Two drills of each drill type were tested in a drilling operation during the following cutting conditions:

Work piece material:	Tool Steel, 42CrMo4
Operation:	Drilling
V_c m/min	130
Feed mm/rev	0.30
V_f mm/min	1460
t_1 mm	20
Note:	Wet conditions, emulsion 6%

The results can be seen below. The tool life travel is an average of two tests.

Table 3

Drill type No.	Tool life travel(m)
1 (Invention)	55
Ref. 1	31

Example 4

A drill made according to the present invention was compared to Ref. 2. Two drills of each drill type were tested in a drilling operation during the following cutting conditions:

Work piece material:	Tool Steel, 42CrMo4
Operation:	Drilling
V_c m/min	130
Feed mm/rev	0.30
V_t mm/min	1460
t_1 mm	20
Note:	Wet conditions, emulsion 6%

The results can be seen below. The tool life travel is an average of two tests.

Table 4

Drill type No	Tool life travel (m)
1 (Invention)	55
Ref. 2	40

Example 5

A drill made according to the present invention was compared to two different competitor drills, Comp. 1 and Comp. 2, which are suitable for this type of drilling operation. Two drills of each drill type were tested in a drilling operation during the following cutting conditions:

Work piece material:	Tool Steel, 55NiCrMoV6
Operation:	Drilling
V_c m/min	140
Feed mm/rev	0.30
V_t mm/min	1573
t_1 mm	38
Note:	Wet conditions, emulsion 6%

The results can be seen below. The tool life travel is an average of two tests.

Table 5

Drill type No	Tool life travel (m)
1 (Invention)	58
Comp. 1	13
Comp. 2	22

Claims

1. A twist drill comprising a cemented carbide or high speed steel substrate and a coating c h a r a c t e r i s e d in that the coating comprises:

- a first layer system having a multilayered structure covering substantially the whole active part of the drill,
- a second layer system having a multilayered structure covering only the tip area of the drill.

2. A twist drill according to claim 1, c h a r a c t e r i s e d in that the tip area of the drill is defined as the distance from the tip to a distance towards the base of drill of 0.3 to 1.5 times the diameter of the drill.

3. A twist drill according to claim 1 or 2, c h a r a c t e r i s e d in that the first layer system and second layer systems comprises of metalnitrides where the metal elements are selected from titanium (Ti), aluminium (Al), silicon (Si), chromium (Cr), niobium (Nb), hafnium (Hf), vanadium (V), tantalum (Ta), molybdenum (Mo), zirconium (Zr) or tungsten (W) and mixtures thereof.

4. A twist drill according to any of the preceding claims c h a r a c t e r i s e d in that the first and/or second layer system comprises one or more sections having an aperiodic structure.

5. Method of making a twist drill c h a r a c t e r i s e d in

- providing a cemented carbide or high speed steel substrate and;
- depositing a first layer system having a multilayered structure onto the whole active part of the drill by using conventional PVD techniques, and
- depositing a second layer system having a multilayered structure onto the tip area of the drill using conventional PVD techniques.

6. A method according to claim 5, characterised in that parts of the drill are shielded by a tight fitting cylinder prior to depositing of the second layer system.

7. A method according to any of claims 5 or 6 characterised in that the tip area of the drill is defined as the distance from the tip as 0.3 to 1.5 times the diameter of the drill.

8. A method according to any of claims 5 to 7, characterised in that the first and second layer systems are deposited using cathodic arc evaporation using arc targets of alloys of metal elements selected from titanium (Ti), aluminium (Al), silicon (Si), chromium (Cr), niobium (Nb), hafnium (Hf), vanadium (V), tantalum (Ta), molybdenum (Mo), zirconium (Zr) or tungsten (W) or mixtures thereof.

FIG. 1





FIG. 2



INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE2007/050621

A. CLASSIFICATION OF SUBJECT MATTER

IPC: see extra sheet

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC: C23C, B23B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-INTERNAL, WPI DATA, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JP 61279409 A, SUMITOMO ELECTRIC IND CO, 1986-12-10: (abstract) Retrieved from: WPI database, WEEK 198704 AN 1987-024432 --	1-8
A	JP 2006082206 A, SUMITOMO DENKO HARD METAL KK, 2006-03-30: (abstract) Retrieved from: WPI database, WEEK 200625, AN 2006-236693 --	1-8
A	JP 2005052953 A, NACHI FUJIKOSHI CORP, 2005-03-03: (abstract) Retrieved from: WPI database, WEEK 200519 AN 2005-176608 --	1-8

☒ Further documents are listed in the continuation of Box C.☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

19 December 2007

Date of mailing of the international search report

19 -12- 2007

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Mats Raidla/ELY
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE2007/050621

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP 3170215 A, MITSUBISHI MATERIALS CORP, 1991-07-23: (abstract) Retrieved from: WPI database, WEEK 199135 AN 1991-258051 --	1-8
A	JP 61288910 A, SUMITOMO ELECTRIC IND CO, 1986-12-19: (abstract) Retrieved from: WPI database, WEEK 198705 AN 1987-032862 -- -----	1-8

International patent classification (IPC)**C23C 14/04** (2006.01)**B23B 51/02** (2006.01)**C23C 14/06** (2006.01)**C23C 30/00** (2006.01)**Download your patent documents at www.prv.se**

The cited patent documents can be downloaded at www.prv.se by following the links:

- In English/Searches and advisory services/Cited documents (service in English) or
- e-tjänster/anförda dokument(service in Swedish).

Use the application number as username.

The password is **BQVHGMMNJIJ**.

Paper copies can be ordered at a cost of 50 SEK per copy from PRV InterPat (telephone number 08-782 28 85).

Cited literature, if any, will be enclosed in paper form.