

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(10) International Publication Number
WO 2015/028852 A1

(43) International Publication Date
5 March 2015 (05.03.2015)

- (51) **International Patent Classification:**
A61L 2/00 (2006.01)
- (21) **International Application Number:**
PCT/IB20 14/000309
- (22) **International Filing Date:**
13 March 2014 (13.03.2014)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
2827/MUM/2013 29 August 2013 (29.08.2013) EST
- (71) **Applicant: GREEN IMPACT HOLDING AG** [CH/CH];
Alte Steinhäuserstrasse 1, CH-6330 Cham/Zug (CH).
- (72) **Inventors: SWAMY, Rohini;** 18 Shivtirth Nr 1., 6 B Desai Road, Mumbai 400 026 (IN). **SWAMY, Sanjeev;** 18 Shivtirth Nr 1., 6 B Desai Road, Mumbai 400 026 (IN).
- (74) **Agent: BARDEHLE PAGENBERG;** Dr. Christof Karl, Prinzregentenplatz 7, 81675 München (DE).
- (81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,

HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to the identity of the inventor (Rule 4.1 7(i))
- as to applicant's entitlement to apply for and be granted a patent (Rule 4.1 7(H))

Published:

- with international search report (Art. 21(3))



WO 2015/028852 A1

(54) **Title:** A DISINFECTANT COMPOSITION FOR TEXTILE AND RELATED SUBSTRATES, AND METHOD OF TREATING A SUBSTRATE TO PROVIDE DISINFECTING ANTIBACTERIAL, ANTIVIRAL AND ANTIFUNGAL, WASH DURABLE, OPTIONALLY ENHANCED WITH MULTIFUNCTIONAL PROPERTIES

(57) **Abstract:** A disinfectant textile composition having antimicrobial, wash durable, optionally enhanced with multifunctional properties, comprising, substrate, disinfecting agents, antiviral agents, antifungal agents, emulsifying agents, vehicle,

TITLE

A disinfectant composition for textile and related substrates, and method of treating a substrate to provide disinfecting antibacterial, antiviral and antifungal, wash durable, optionally enhanced with multifunctional properties.

FIELD OF THE INVENTION

The present invention relates to a disinfecting antimicrobial textile having essential features such as wash durability and capability for addition of multifunctional enhancements with wash durable disinfecting antimicrobial properties.

BACKGROUND OF THE INVENTION

There is a long felt need to provide effective, durable, and long lasting disinfecting characteristics to textiles used particularly for homes, hospitals, hotels, offices, industrial environments, military, police, humans, and pets etc., as they are subject to contamination by bacteria, viruses and fungi. The prevalent environment in these locations can result in the textile being not only a fertile breeding ground for these pathogens, but also a perfect substrate from which these pathogens can be spread to others resulting in infections, maybe even death, higher operational costs and waste through redundancy and rot.

Textiles are used for a variety of purposes and in a variety of environments. As such, there is a very realistic danger of microbiological contamination on the textile surfaces. Additionally, danger of staining of apparel due to ketchup, blood, sputum, honey, human excreta and moisture are also problems faced by users in various circumstances. Not only do such stains look ugly, but they also are fertile breeding grounds for various harmful bacteria, fungi and viruses on the textile surface and in its cross section.

On the inner surface of the textile, dead tissue, sweat, humidity and moisture aids the growth and spread of various pathogens. Also, garments such as jackets and overcoats, which directly don't come in contact with the skin, are also susceptible to infection transfer through contact with the inner garments, which are possibly infected. As such, it is evident that textile contamination by microbiological pathogens is a major cause for concern.

Security and military personnel, stewardesses and other airline personnel are especially prone to disease and skin problems as they may have to wear the same clothing for more than one day. Military personnel may have to wear their apparel for as much as 28 days at a stretch. Not only do these soiled apparel cause health problems to the wearer but are also the breeding grounds for the spread of bacteria, fungi and virus based diseases.

In the context of the hospitals, the presence of microbes is far more threatening. Due to the nature of the environment these textiles are used in, the needs of the textiles are much more specialized. Apart from the regular textiles worn by doctors, nurses, patients and other personnel in hospitals, doctor's clinics and other such locations, textiles used in the form of scrubs, gowns, lab coats, bed sheets and pillow cases carry microbes in various proportions. Patients sleep on sheets and pillow cases that have extremely high risk of contamination due to bacterial and microbial growth resulting from excretions of the body. The mattresses and pillows are also likely to become infected due to the fact that these aren't washed. They, in turn, can transmit infection to the patient. Sheets, pillow covers, gowns, and curtains are subjected to contamination from open wounds and other medical conditions, such as coughing, wheezing, etc. Patients' gowns are contaminated by sweat and/ or human excretion such as urine, stool and vomit. This leads to the growth of microorganisms like bacteria, viruses and fungi. Healthcare workers are very often subjected to the contamination either from soiled textiles used by patients or due to excretions of the body. Medical personnel are major causes of transmitting bacterial infection from one patient to another. Current medical textiles offer no barrier protection. Provided herein below are current situations and problems thereof in hospitals:

- a. Hospital or Healthcare transmitted diseases to a great extent are textile based transmissions.
- b. Doctors and Patients tend to infect each other through textile contact.
- c. Current methods of washing lead to damage of the textile.
- d. Pillows, mattresses and curtains are rarely washed or disinfected.
- e. Post wash bacteria growth is instantaneous.

- f. Body residues like sweat and dead skin are breeding grounds for bacteria.

Laundry washing of regular textiles leads to excess consumption of water. Moreover, huge quantities of detergents are used to launder the clothes, and this process is excessively time consuming due to long laundry wash times. There is also a pressing need to address this problem by creating textiles which require lesser amounts of water, time and detergents to clean.

Apart from disinfection, multifunctional capabilities such as anti-staining, moisture management, sweat transportation, abrasion resistance, insect and mosquito repellent, fire retardant, antistatic, anti-pilling, UV protection and soil release are also highly desirable in textiles, as they offer many synergistic benefits to the user. These are easily adapted to the basic function of disinfection without causing any change in functionality.

Microbiologically potable water is a pressing need today. While there is availability of fresh water resources, the water therein is often found contaminated with E.Coli and a wide range of other disease causing microbes. Indeed, many freshwater sources are used by the local population for a variety of activities ranging from bathing, to washing of clothes, to bathing their cattle, etc. As such, the levels of contamination in most of these water resources are considerable. If used for drinking, such contaminated water could lead to outbreaks of diarrhea, cholera and a host of other diseases, as indeed evidenced by studies across the world. While systems do exist which can kill the waterborne microbiology using chemical dosing, the use of such chemicals over extended periods is harmful for the human body. Moreover, yet other systems that can separate or kill bacteria in water use electricity, which is not readily available in a large chunk of underdeveloped regions across the globe.

While many people have indigenously used textiles to sieve water and make it more potable, those textiles cannot kill microbiological pathogens. As such, there is a definite need to address the issue wherein microbiologically safe drinking water can be provided in a simple manner by combining the traditional technique of cloth filtration with a technology that can make the cloth disinfecting and able to kill disease causing microbes.

PRIOR ART OF THE INVENTION

USPT No. 2791518 describes a method of imparting microbial properties of articles such as textiles by immersing the article in a first aqueous solution containing a water soluble base nitrogen compound (ammonia) and a monovalent silver salt soluble in a said solution, followed by a second immersion in a second solution containing a second salt capable of ion exchange with the silver salt.

USPTO No. 527952 discloses a method of treating fibers to render them electrically conductive as well as anti bacterial comprising immersing the fibers in a bath containing an aqueous solution of a source of divalent copper ions, reducing agent, sodium thiosulphate and a source of iodide ions , where by copper iodide adsorbed into the fibers

USPTO No. 6962608, which teaches about a process for preparing an antimicrobial fiber, said process comprising a) immersing a textile in an aqueous treating solution comprising an organic acid, wherein said organic acid has a at least two carboxyl groups, b) treating said fiber with an oxidizing agent to produce a peroxy-carboxylic acid function, thereby preparing an antimicrobial textile containing an average of 6 weight percent of the organic acid, which not laundered at all demonstrated over 99% reduction of E.coli.

Therefore, the present invention solving the problems associated with the traditional use of textiles, the inventors of the alleged invention have developed a novel and inventive composition for treating the textiles and methods of making the solution as well as methods of treating textiles using the composition. Accordingly, the objectives of the invention are enumerated below,

The primary object of the present invention is to provide any textile or substrate disinfecting, antibacterial, antiviral, antifungal and wash durable properties.

Further object of the present invention is that the disinfectant textiles provide barrier protection to the wearer.

Further, important object of the present invention is that it will prohibit complete growth of bacteria, smells, odors etc.

Very important object of the present invention is that it will drastically reduce the washing costs.

SUMMARY OF THE INVENTION

In accordance with the present invention there is provided a textile comprising a substrate which is:

- i. So treated with a combination of one, several or all of a quaternary ammonium organosilane compound, and/or silver chloride and/or other

types of silver salts, and/or Poly-glucosamine , and/or propiconazole, and/or biocoated silver particles and/or poly-hexa-methylene-biguanide (herein after referred to also as "functional agents"), that the entire cross section of the substrate becomes antimicrobial, anti fungal and anti viral in nature and meets the prescribed standards to qualify as disinfecting.

- ii. So processed that the above chemistry is affixed onto the textile in a wash-durable, non-leaching manner.

The resultant fabric is mildly hydrophobic across its cross section.

The application of chemistry to the textile is done using exhaust, padding, coating or spraying processes. Drying of the textile is done using normal heat setting processes as available.

Additionally, the textile substrate can be made multifunctional by adding the required functional treatments along with the disinfecting coating, during the processing phase. In order to impart multifunctional capabilities the textiles may be treated on one or both sides of the textile, either separately or jointly, with the treating composition comprising at least one treating agent selected from the group consisting of water and oil repellents, abrasion resistant agents, antistatic agents, anti-pilling agents, easy care resins, wetting agents, wicking chemicals, softeners, mosquito repellants, UV protectors, soil releasing agents, viscosity modifiers, pH modifiers, emulsifying agents and vehicles thereof.

DESCRIPTION OF THE INVENTION:-

The present invention relates to providing disinfecting (antimicrobial) textiles in which the textiles (said to be a substrate) have been selected from a group consisting of woven, non woven, electro spun, drawn, bonded, crocheted or knitted textiles, and are useful for humans, animals, and the environment, in apparel, medical, home, hotels, furnishings (including upholstery), kitchen, table top, bathroom, automotive, bakeries, curtains, carpets, pet products and related applications. By textiles with disinfecting qualities we refer to the specific property wherein the textile can provide a reduction in bacterial (gram positive) contamination greater than 4 logs in less than 5 minutes as well as completely hinder the growth of Fungi.

It is an additional property obtained in the present invention to make the above-mentioned disinfecting textiles wash durable (long lasting) and functionally effective even after repeated wash cycles, mechanical rubbing, contact with liquids, or contact with vapors, with a mix of chemicals that allow for high levels of disinfecting activity, resulting in a disinfecting textile which has the capability to be additionally enhanced for multi functional capabilities.


It is an aspect of the present invention that the substrate, such as the textile substrate which needs to be treated, is typically selected from a non-limiting group of textiles consisting of natural or synthetic woven textile, drawn textile, knitted textile, crocheted textile, bonded textile or non woven textile.

The natural fabric is at least one selected from the group consisting of wool, cotton, silk, linen, hemp, ramie and jute. The formulation and the method of the present invention is also suitable for application to various textiles materials including synthetic fabric which is at least one selected from the group consisting of rayon, nylon, nonacrylic olefin acrylic polyester, PTFE, PP, PPE, carbon fiber, vinyon, saran, spandex, vinalon, aramids, modal, sulfar, polybenzimidazole fibre, PLA, lyocell, orlon, vectran and zylonacrylonitrile. The above fabric can be blended from any of the above mentioned fabrics/groups, for application of the composition followed by method of application.


The disinfecting treating composition for the textile substrate comprises of a combination of one, several or all of a quaternary ammonium organosilane compound, and/or silver chloride and/or other types of silver salts, and/or Polyglucosamine, and/or propiconazole, and/or biocoated silver particles and/or polyhexa-methylene-biguanide (herein after referred to also as "functional agents"), in a concentration range of between 0.1 to 10%, more specifically 0.1 to 4%, such that the entire cross section of the substrate becomes antimicrobial, antiviral and antifungal in nature and meets the prescribed standards to qualify as disinfecting.

Organosilane quaternary amine


Molecular Structure:



Silver acrylate salt




Polyhexamethylene Biguanide (PHMB)



In the further embodiment of the present invention the solution and / or composition comprising of anti viral agent used to prepare disinfecting textiles is atleast one selected from the group consisting of compound methyl alcohol, octadecylaminomethyl trihydroxysilylpropyl ammonium chloride and chloropropyl trihydroxysilane, poly-glucosamine, silver chloride based compound and silver chloride in aluminosilicate carrier base and polyhexamethylene biguanide, in a concentration range of between 1 ppm to 500ppm, depending on application, and


the polysaccharide or oligosaccharide or biocoated silver nanoparticles, in a concentration range of between 0.1 ppm to 150 ppm, depending on the application.

Chemical structure of polysaccharide




The antifungal agent is at least one selected from the group of thiabendazoles or propiconazoles in a concentration of range of between 0.5 ppm to 200 ppm, depending on application. These agents also impart a small amount of antibacterial and antiviral activity by supporting those functions through their anti fungal capabilities.

Chemical structure of Thiabendazole



Chemical structure of Propiconazole



Apart from above components the present invention further includes a cross-linking agent which is selected from the type of adducts of blocked isocyanate, in a concentration range of between 1 ppm to 300 ppm, depending on application.

A further embodiment of the present invention comprises an emulsifying agent, typically, the emulsifying agent is at least one selected from the group of polyoxyethylene monostearate, polyoxyethylene, sorbitan monolaurate, polyethylene glycol 400 monolaurate in a concentration of between 0.1 ppm to 200 ppm, depending on application.

The vehicle used to prepare the solution in accordance with present composition is water or any other solvent which is compatible with the mixture of the functional agents added in the solution to create the present composition.

The treated fabric is mildly hydrophobic across its cross section. The application of chemistry to the textile is done using exhaust, padding, coating or spraying processes. Drying of the textile is done using normal heat setting processes as available.

Additionally, the textile substrate can be made multifunctional by adding the required functional treatments along with the disinfecting coating, during the processing phase. In order to impart multifunctional capabilities the textiles may be treated on one or both sides of the textile, either separately or jointly, with the treating composition comprising at least one treating agent selected from the group consisting of water and oil repellents, abrasion resistant agents, antistatic agents, anti-pilling agents, easy care resins, wetting agents, wicking chemicals, softeners, mosquito repellants, UV protectors, soil releasing agents, viscosity modifiers, pH modifiers, emulsifying agents and vehicles thereof.

In accordance with the present invention there is provided for a process for preparing a textile treated with treating composition, comprising the following method steps:

- A batch of fabric is taken on the finishing machine by any one or several of four different application methods.

Padding method

- i. In which method a desired concentration of finishing liquor is prepared by ad-mixing various functional agents. This finishing liquor is then fed through a pump to the padding mangle trough.
- ii. Appropriate padding mangle pressure is predetermined at the time of laboratory testing prior to bulk production to obtain optimum wet pick up of the functional agents on to the textile to attain the required specifications. This is completely dependent on the quality of textile substrate, and cannot be otherwise generalized. The principle, however, is to attain enough pressure to optimize the wet pick up of the chemicals onto the textile.
- iii. At this stage an admixture of organosilane, silver salts and polyhexamethylene biguanide is applied to the textile in the desired concentration ranges as mentioned above, which when polymerized are mildly hydrophobic in nature.

Exhaust method

- i. A desired concentration of finishing liquor is prepared by ad-mixing various functional agents and textile substrate is treated by exhaust method means, treated in finishing liquor for specific time, temp and pH which is predetermined at the time of laboratory testing prior to bulk production to obtain optimum exhaustion of the functional agents onto the fabric to attain the required specifications.
- ii. At this stage an admixture of organosilane, silver salts and polyhexamethylene biguanide is applied to the textile in the desired

concentration ranges as mentioned above, which when polymerized are mildly hydrophobic in nature.

Coating method

- i. A desired concentration of finishing liquor is prepared by ad-mixing various functional agents. This finishing liquor is then fed through a pump to the knife coating machine.
- ii. The clearance between the textile and the knife is determined based on the required thickness of coating and the nature of the textile substrate in terms of its pick-up ability.
- iii. An admixture of organosilane, silver salts and polyhexamethylene biguanide is then additionally applied to the textile, using the knife coating technique, in the desired concentration ranges as mentioned above, which when polymerized are mildly hydrophobic in nature.

Spraying method

- i. A desired concentration of finishing liquor is prepared by ad-mixing various functional agents and textile substrate is sprayed with this liquor for a specific time and in temperature range of 20-90 degrees Centigrade depending on the nature of the textile substrate. The time for spraying is predetermined at the time of laboratory testing prior to bulk production to obtain optimum liquor pick-up onto the fabric to attain the required specifications of disinfection.
 - ii. An admixture of organosilane, silver salts and polyhexamethylene biguanide is subsequently sprayed on the textile in the desired concentration ranges as mentioned above, at a temperature range of between 20-90 degrees (depending on the nature of the textile substrate) which when polymerized are mildly hydrophobic in nature. The time of spraying is set to between 3 and 15 seconds.
2. Any one of the application processed fabric then passes through the stenter frame which provides heat of between 110°C-180°C with a dwell time of between 1-7 minutes, depending on the exact textile substrate and the nature of finished product application required, and the applied chemistry is partially polymerized onto the textile. The fabric is in a dry state. By this process the mildly hydrophobic fabric is then once again wound in a roll on the "A frame".
 3. A mixture of cross linking agents can optionally be poured in the finishing bath of the padding mangle. Appropriate padding mangle pressure is predetermined at the time of laboratory testing prior to bulk production to obtain optimum wet pick up of the functional agents onto the fabric to attain the required specifications.
 4. The fabric is then once again passed through the stenter frame for drying at a temperature of 110°C-180°C with a dwell time of 1-7 minutes depending on the

nature of the textile substrate used and the specific application requiring the textile. At this stage, the initial antimicrobial agents applied in the first step are fully polymerized due to the heat and therefore block the textile yarns from absorbing any further chemical agents into them. The moisture cross linker however is also attached and therefore the capability of additional chemicals being attached to the surface of the textile of the yarn, without penetrating the yarn in any significant way is achieved.

5. At this stage, the textile is disinfecting in nature and has the capability of attaching, to the surface of the textile or yarn, additional technologies depending on the application. The cross section of the textile is mildly hydrophobic but, due to the presence of the moisture cross linker, adhesion of additional chemicals on the surface of the textile is made possible.

The fixation of the chemicals by complete polymerization is a non-leaching and wash durable process. As such, the resultant textile can withstand several washes without losing efficacy.

The pre-treatment of the textile substrate includes:

1. Testing the textile at laboratory scale to verify and confirm that it meets the above selection criteria, prior to production.
2. Batching and stitching together of individual textile pieces on an "A" frame.
3. Thorough inspection of the textile for defects during batching

The invention will now be explained with the help of following non-limiting examples.

Example 1: Disinfecting textile for application in Water Filtration

0.5 to 2 % add-on of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 1 to 2% add-on of silver chloride based compound and 1 to 2% polyhexamethylene biguanide, 1 to 3% of polyglucosamine are applied onto the textile substrate through aqueous media by exhaust process at mildly acidic condition followed by heat treatment polymerization at between 130°C and 160°C, which imparts disinfecting property to textile substrate across the entire cross section along with mildly hydrophobic performance.

Example 2: Disinfecting textile for application in Kitchen Towels

10 to 20 g/l of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 10 to 20 g/l of silver chloride based compound, silver chloride in aluminosilicate carrier base, 10 to 20 g/l of polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by pad impregnation method with 60 to 80% wet pickup at mildly acidic condition followed by heat treatment polymerization at between 130°C and 160°C, which imparts antimicrobial property to textile substrate across the cross section which displays disinfectant like qualities along with mildly hydrophobic performance. 5 to 20 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 20 gm/lit thiabendazole, 5 to 20 gm/lit of poly-glucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at 120°C to 150°C, which gets bonded to the textile substrate from both sides and creates the reactant moiety to other functionality finishes that can make it superabsorbent.

Example 3: Disinfecting textile for application in Undergarments and socks

0.1 to 2% add-on of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 0.1 to 2% add-on of silver chloride based compound, silver chloride in aluminosilicate carrier base, 0.1% to 2% add-on polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by coating process at mildly acidic condition followed by heat treatment polymerization at between 130°C and 170°C, which imparts antimicrobial property to textile substrate across the entire cross section which displays disinfectant like qualities along with mildly hydrophobic performance. 5 to 20 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 18 gm/lit thiabendazole, 5 to 20 gm/lit of poly-glucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at 120°C to 160°C, which gets bonded to the textile substrate from both sides and creates the reactant moiety to other functionality finishes that can increase the absorbency of the garments.

Example 4: Disinfecting textile for application in Medical garments

where one sided sweat absorbency coating is required to be further applied 20 to 50 g/l of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 20 to 50 g/l of silver chloride based compound, silver chloride in aluminosilicate carrier base, and 20 to 50 g/l of polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by pad impregnation method with 60% to 80% wet pickup at mildly acidic condition followed by heat treatment polymerization at

between 110°C and 150°C, which imparts antimicrobial property to textile substrate across the cross section which displays disinfectant like qualities along with mildly hydrophobic performance. 5 to 15 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 20 gm/lit thiabendazole, 1 to 15 gm/lit of poly-glucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at between 110°C and 150°C, which gets bonded to the textile, in order to make it reactive to further coating for sweat absorbency.

Example 5: Disinfecting textile for application in Medical garments where both sides need to be made additionally repellent to water, blood and other fluids

0.5 to 2 % add-on of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 1 to 2% add-on of silver chloride based compound, silver chloride in aluminosilicate carrier base, and 1 to 2% polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by exhaust process at mildly acidic condition followed by heat treatment polymerization at between 120°C and 140°C, which imparts antimicrobial property to textile substrate across the entire cross section which displays disinfectant like qualities along with mildly hydrophobic performance.

5 to 20 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 20 gm/lit thiabendazole, 5 to 20 gm/lit of poly-glucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at between 120°C and 150°C, which gets bonded to the textile substrate from both sides and creates the reactant moiety to further apply the fluid repellent coating.

Example 6: Disinfecting textile for application in Military battle garments where the textile must be compatible to add insect repellent treatment

10 to 50 g/l of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 10 to 50 g/l of silver chloride based compound, silver chloride in aluminosilicate carrier base, 10 to 50 g/l of polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by pad impregnation method with 60 to 80% wet pickup at mildly acidic condition followed by heat treatment polymerization at between 120°C and 140°C, which imparts antimicrobial property to textile substrate across the cross section which displays disinfectant like qualities along with mildly hydrophobic performance. 5 to 20 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 20 gm/lit thiabendazole, 5 to 20 gm/lit of poly-glucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at between 120°C and 150°C, which gets bonded to the textile

substrate from both sides and creates the reactant moiety to apply insect repellent treatment.

Example 7: Disinfecting textile for application in Military battle garments where the textile must be compatible to add UV reflecting and water repellent treatment

0.5 to 2% add-on of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 1 to 2% add-on of silver chloride based compound, silver chloride in aluminosilicate carrier base, 1 to 2% add-on of polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by exhaust process at mildly acidic condition followed by heat treatment polymerization at between 130°C and 135°C, which imparts antimicrobial property to textile substrate across the entire cross section which displays disinfectant like qualities along with mildly hydrophobic performance, b) Cross linker 2 to 18 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 18 gm/lit thiabendazole, 5 to 20 gm/lit of poly-glucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at between 120°C and 140°C, which gets bonded to the textile substrate from both sides and creates the reactant moiety to add UV reflecting and water repellent treatment.

Example 8: Disinfecting textile for application in sweat absorbent T-shirts

2 to 5 % add-on of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 2 to 5% add-on of silver chloride based compound, silver chloride in aluminosilicate carrier base, are applied onto the textile substrate through aqueous media by exhaust process at mildly acidic condition followed by heat treatment polymerization at between 120°C and 130°C, which imparts antimicrobial property to textile substrate across the cross section which displays disinfectant like qualities along with mildly hydrophobic performance. 5 to 20 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 20 gm/lit thiabendazole, 5 to 20 gm/lit of poly-glucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at between 120°C and 150°C, which gets bonded to the textile substrate from both sides and creates the reactant moiety for other functionality finishes.

Example 9: Disinfecting textile for application in T-shirts with capability for water repellent, mosquito repellent and UV reflecting treatments

0.5 to 2% add-on of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 1 to 2% add-on of silver chloride based compound, silver chloride in

aluminosilicate carrier base, 1 to 2% add-on of polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by exhaust process at mildly acidic condition followed by heat treatment polymerization at between 120°C and 130°C, which imparts antimicrobial property to textile substrate across the entire cross section which displays disinfectant like qualities along with mildly hydrophobic performance. 5 to 20 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 20 gm/lit thiabendazole, 5 to 20 gm/lit of poly-glucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at between 120°C and 150°C, which gets bonded to the textile substrate from both sides and creates the reactant moiety to other functionality finishes.

Example 10: Disinfecting textile for application in Bedsheets for Hotel Industry with capability for addition of mosquito repellent treatment

1 to 5% add-on of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 1 to 2% add-on of silver chloride based compound, silver chloride in aluminosilicate carrier base, 1 to 5% add-on of polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by spraying process at mildly acidic condition followed by heat treatment polymerization at between 130°C and 160°C, which imparts antimicrobial property to textile substrate across the entire cross section which displays disinfectant like qualities along with mildly hydrophobic performance. 5 to 20 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 20 gm/lit thiabendazole, 5 to 20 gm/lit of poly-glucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at between 120°C and 150°C, which gets bonded to the textile substrate from both sides and creates the reactant moiety to other functionality finishes.

Example 11: Disinfecting textile for application in Bedsheets for Hotel Industry with capability for addition of flame retardant treatment

0.5 to 2% add-on of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 1 to 2% add-on of silver chloride based compound, silver chloride in aluminosilicate carrier base, 1 to 2% add-on of polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by exhaust process at mildly acidic condition followed by heat treatment polymerization at between 130°C and 160°C, which imparts antimicrobial property to textile substrate across the entire cross section which displays disinfectant like qualities along with mildly hydrophobic performance. 5 to 20 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 20 gm/lit thiabendazole, 5 to 20 gm/ lit of poly-

glucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at between 120°C and 150°C, which gets bonded to the textile substrate from both sides and creates the functionality necessary for addition of the flame retardant treatment.

Example 12: Disinfecting textile for application as curtains with capability for addition of flame retardant treatment and water repellency

10 to 50 g/l of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 10 to 50 g/l of silver chloride based compound, silver chloride in aluminosilicate carrier base, 10 to 50 g/l of polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by pad impregnation method with 60 to 80% wet pickup at mildly acidic condition followed by heat treatment polymerization at between 130°C and 160°C, which imparts antimicrobial property to textile substrate across the cross section which displays disinfectant like qualities along with mildly hydrophobic performance. 5 to 20 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 20 gm/lit thiabendazole, 5 to 20 gm/lit of polyglucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at between 120°C and 150°C, which gets bonded to the textile substrate from both sides and creates the reactant moiety to apply the desired finish.

Example 13: Disinfecting textile for application in children's clothing

10 to 50 g/l of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 10 to 50 g/l of silver chloride based compound, silver chloride in aluminosilicate carrier base, 10 to 50 g/l of polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by spraying method with 60 to 80% wet pickup at mildly acidic condition followed by heat treatment polymerization at between 120°C and 150°C, which imparts antimicrobial property to textile substrate across the cross section which displays disinfectant like qualities along with mildly hydrophobic performance.

Example 14: Disinfecting textile for application in school uniforms

0.5 to 2% add-on of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 1 to 2% add-on of silver chloride based compound, silver chloride in aluminosilicate carrier base, 1 to 2% add-on of polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by exhaust process at

mildly acidic condition followed by heat treatment polymerization at between 130°C and 150°C, which imparts antimicrobial property to textile substrate across the entire cross section which displays disinfectant like qualities along with mildly hydrophobic performance. 5 to 20 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 20 gm/lit thiabendazole, 5 to 20 gm/lit of poly-glucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at between 110°C to 160°C, which gets bonded to the textile substrate from both sides and creates the reactant moiety to other functionality finishes.

Example 15: Disinfecting textile for application in Hotel bathing towels

20 to 50 g/l of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 20 to 50 g/l of silver chloride based compound, silver chloride in aluminosilicate carrier base, and 20 to 50 g/l polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by pad impregnation method with 60% to 80% wet pickup at mildly acidic condition followed by heat treatment polymerization at between 120°C and 140°C, which imparts antimicrobial property to textile substrate across the cross section which displays disinfectant like qualities along with mildly hydrophobic performance.

Example 16: Disinfecting textile for application in Upholstery

0.5 to 2 % add-on of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 1 to 2% add-on of silver chloride based compound, silver chloride in aluminosilicate carrier base, and 1 to 2% polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by exhaust process at mildly acidic condition followed by heat treatment polymerization at between 110°C and 150°C, which imparts antimicrobial property to textile substrate across the entire cross section which displays disinfectant like qualities along with mildly hydrophobic performance. 5 to 20 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 20 gm/lit thiabendazole, 5 to 20 gm/lit of poly-glucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at between 120°C and 150°C, which gets bonded to the textile substrate from both sides and creates the reactant moiety for adding any other required treatment finishes.

Example 17: Disinfecting textile for application in Dog Beds with additional capacity for abrasion resistance treatment

0.5 to 2% add-on of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 1 to 2% add-on of silver chloride based compound, silver chloride in aluminosilicate carrier base, 1 to 2% add-on of polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by exhaust process at mildly acidic condition followed by heat treatment polymerization at between 130°C and 135°C, which imparts antimicrobial property to textile substrate across the entire cross section which displays disinfectant like qualities along with mildly hydrophobic performance. 5 to 20 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 20 gm/lit thiabendazole, 5 to 20 gm/lit of poly-glucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at 120°C to 150°C, which gets bonded to the textile substrate from both sides and creates the reactant moiety to add abrasion resistant treatment.

Example 18: Disinfecting textile for application in Diapers for incontinence

10 to 40 g/l of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 10 to 40 g/l of silver chloride based compound, silver chloride in aluminosilicate carrier base, and 10 to 40 g/l of polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by spraying method at mildly acidic condition followed by heat treatment polymerization at between 130°C and 145°C, which imparts antimicrobial property to textile substrate across the cross section which displays disinfectant like qualities along with mildly hydrophobic performance. 10 to 20 gm/lit of blocked isocyanate based thermoplastic polymer dispersion and 1 to 20 gm/lit thiabendazole, 5 to 15 gm/lit of poly-glucosamine oligosaccharide are applied onto the above antimicrobially treated textile substrate at between 110°C to 140°C, which gets bonded to the textile substrate from both sides and creates the reactant moiety to add the absorbent treatments required.

Example 19: Disinfecting textile for application in Air filtration systems

20 to 50 g/l of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 20 to 50 g/l of silver chloride based compound, silver chloride in aluminosilicate carrier base, are applied onto the textile substrate through aqueous media by pad impregnation method with 60% to 80% wet pickup at mildly acidic condition followed by heat treatment polymerization at between 130°C and 145°C, which imparts antimicrobial property to textile substrate across the cross section which displays disinfectant like qualities along with mildly hydrophobic performance.

Example 20: Disinfecting textile for application in Bandages

0.5 to 2% add-on of octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, 1 to 2% add-on of silver chloride based compound, silver chloride in aluminosilicate carrier base, 1 to 2% add-on of polyhexamethylene biguanide are applied onto the textile substrate through aqueous media by coating process at mildly acidic condition followed by heat treatment polymerization at between 110°C to 140°C, which imparts antimicrobial property to textile substrate across the entire cross section which displays disinfectant like qualities along with mildly hydrophobic performance.

We Claim,

1. A disinfectant composition for textile and related substrates, and method of treating a substrate to provide disinfecting antibacterial, antiviral and antifungal, wash durable, optionally enhanced with multifunctional properties, comprising:
substrate,

disinfecting agents

antiviral agents

antifungal agents

emulsifying agents

vehicle,


2. A composition as claimed in claim 1, wherein the substrate, is selected from the group consisting of natural or synthetic woven, knitted, crocheted, bonded or non woven textile,

3. A composition as claimed in claim 1 and 2, wherein the yarn is spun, electrospun, drawn or extruded, where the natural fabric is at least one selected from the group consisting of wool, cotton, silk linen, hemp, ramie and jute, and synthetic fabric is at least one selected from the group of rayon, nylon, non-acrylic olefin, acrylic polyester, PTFE, PP, PPE, carbon fiber, vinyon, saran, spandex, vinalon, aramids, modal, sulfar, polybenzimidazole fibre, PLA, lyocell, orlon, vectran and zylon acrylonitrile,

4. A composition as claimed in 2 and 3, wherein the fabric or yarn can be blended,

5. A composition as claimed in claim 1, wherein the disinfecting agent comprises of a combination of one, several or all of a quaternary ammonium organosilane compound, and/or silver chloride and/or other types of silver salts, and/or Polyglucosamine, and/or propiconazole, and/or biocoated silver particles and/or polyhexa-methylene-biguanide,

6. A composition as claimed in claim 1 & 5, wherein an organosilane quaternary amine and its derivative thereof, having the molecular structure,

Organosilane quaternary amine**Molecular Structure:**


is being taken in the range of 0.5%-5%, particularly between 0.1 to 2% more particularly between the range of 1 to 2%,

7. A composition as claimed in claim 6, wherein the organosilane can be an octadecylaminomethyl trihydroxysilylpropyl ammonium chloride, taken in the range of 5 to 50 gram by weight,

8. A composition as claimed in above claims, wherein the silver acrylate salt of the composition is been taken in the range of 0.1% to 5%, particularly between 0.1-2%, more


particularly between 0.5 to 2%

Silver acrylate salt



and the polyhexamethylene biguanide (PHMB) taken in the range of 1 to 2% , or 2 to 50 grams by weight,

Polyhexamethylene Biguanide (PHMB)



9. A composition as claimed in claim 1, wherein an anti viral agent used is selected from the group consisting of compound methyl alcohol, octadecylaminomethyl trihydroxysilylpropyl ammonium chloride and chloropropyl trihydroxysilane, polyglucosamine, silver chloride based compound and silver chloride in aluminosilicate carrier base and polyhexamethylene biguanide, in a concentration range of between 1 ppm to 500ppm, and the polysaccharide or oligosaccharide or biocoated silver nanoparticles, in a concentration range of between 0.1 ppm to 150 ppm,

10. A composition as claimed in claim 1, wherein the antifungal agent is at least one selected from the group of thiabendazoles or propiconazoles in a concentration of range of between 0.5 ppm to 200 ppm, Apart from above components the present invention further included with the cross-linking agent which are been selected from the type of adducts of blocked isocyanate, in a concentration range of between 1 ppm to 300 ppm, subject to depending on application

11. A composition as claimed in claim 1, wherein the emulsifying agent, is at least one selected from the group of polyoxyethylene monostearate, polyoxyethylene, sorbitan monolaurate, polyethylene glycol 400 monolaurate in a concentration of between 0.1 ppm to 200 ppm,

12. A composition as claimed in claim 1 wherein water, or any other solvent which is compatible with the mixture of the functional agents added to create the composition as claimed in claim 1, is used as a vehicle,

13. A method of treating the substrate using the composition comprising of the following methods,

Padding method wherein a desired concentration of liquor is prepared and then fed through a pump to the padding mangle trough, with a predetermined pressure to obtain optimum wet pick up of the functional agents on to the textile to attain the required specifications,

exhaust method wherein the substrate is treated in the finishing liquor for specific time, temperature and pH which is predetermined, to create the a finished textile which when polymerized is mildly hydrophobic in nature,

coating method, in which a the finishing liquor is fed through a pump to the knife coating machine, through a required thickness, between the textile and the knife,

spraying method, in which method a liquor is sprayed on the textile substrate for a specific time and in temperature range of 20-90 degrees Centigrade, wherein the finished textiles, when polymerized, are mildly hydrophobic in nature. The time of spraying is set to between 3 and 15 seconds,

14. A method as claimed in claim 12 wherein the textile passes through a mixture of cross linking agents poured in the finishing bath, followed by passing through the stenter frame which provides heat of between 110°C-180°C with a dwell time of between 1-7 minutes,

15. A method as claimed in claim 13, wherein the fabric is once again passed through the stenter frame for drying at a temperature of 110°C-180°C with a dwell time of 1-7 minutes , in order to penetrate the solution completely in to the textile and complete polymerization,

INTERNATIONAL SEARCH REPORT

International application No PCT/IB2014/000309

A. CLASSIFICATION OF SUBJECT MATTER
 INV. A61L2/00
 ADD..

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
 A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
 EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2007/065475 A1 (ELFERSY JACQUES [US]) 22 March 2007 (2007-03-22) paragraphs [0024] , [0026] paragraph [0239] - paragraph [0242] -----	1-15
X	W0 2005/023023 A1 (3M INNOVATIVE PROPERTIES CO [US]) 17 March 2005 (2005-03-17) page 8 , paragraph 1 ; examples 1-10 -----	1-15
X	W0 03/061721 A1 (3M INNOVATIVE PROPERTIES CO [US]) 31 July 2003 (2003-07-31) page 22, paragraph 2 page 24, paragraph 1 -----	1-15
X	US 2004/137067 A1 (NARANG UPVAN [US] ET AL) 15 July 2004 (2004-07-15) paragraph [0052]; claim 12 -----	1-15

Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents :

<p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier application or patent but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p>	<p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&" document member of the same patent family</p>
---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------	-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Date of the actual completion of the international search 23 September 2014	Date of mailing of the international search report 14/10/2014
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Tiercet, Marc

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/IB2014/000309

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2007065475	AI	22-03-2007	NONE

Wo 2005023023	AI	17-03-2005	AT 554664 T 15-05 -2012
		AU 2004270266	AI 17-03 -2005
		BR PI0414198	A 31-10 -2006
		CA 2538119	AI 17-03 -2005
		CN 1870912	A 29-11 -2006
		EP 1672989	AI 28-06 -2006
		EP 2308326	A2 13-04 -2011
		JP 2007504826	A 08-03 -2007
		KR 20060126456	A 07-12 -2006
		MX PA06002715	A 05-06 -2006
		US 2005084471	AI 21-04 -2005
		Wo 2005023023	AI 17-03 -2005
		ZA 200602884	A 28-11 -2007

wo 03061721	AI	31-07-2003	AT 369881 T 15-09 -2007
		AU 2002357790	B2 06-03 -2008
		BR 0215518	A 21-12 -2004
		CA 2473841	AI 31-07 -2003
		DE 60221900	T2 08-05 -2008
		EP 1465676	AI 13-10 -2004
		EP 1849487	A2 31-10 -2007
		ES 2290351	T3 16-02 -2008
		JP 4995406	B2 08-08 -2012
		JP 2005520812	A 14-07 -2005
		JP 2010227617	A 14-10 -2010
		KR 20040075080	A 26-08 -2004
		MX PA04006839	A 06-12 -2004
		US 2003194415	AI 16-10 -2003
		US 2005025794	AI 03-02 -2005
		wo 03061721	AI 31-07 -2003

US 2004137067	AI	15-07-2004	NONE
