



- (51) **International Patent Classification:**  
*B29C 67/00* (2006.01)
- (21) **International Application Number:**  
PCT/US2014/027775
- (22) **International Filing Date:**  
14 March 2014 (14.03.2014)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**  
61/781,997 14 March 2013 (14.03.2013) US
- (71) **Applicant:** INTERFACIAL SOLUTIONS IP, LLC  
[US/US]; 949 Antler Court, River Falls, Wisconsin 54022 (US).
- (72) **Inventors:** DEMUTH, Benjamin A.; 932 Sunset LN,  
River Falls, Wisconsin 54022 (US). PAWLOSKI, Adam  
R.; 9737 51st Street N., Lake Elmo, Minnesota 55042 (US).
- (74) **Agent:** SZYMANSKI, Brian E.; 949 Antler Court, River  
Falls, Wisconsin 54022 (US).
- (81) **Designated States** (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,

BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,  
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,  
HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,  
KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME,  
MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ,  
OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,  
SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM,  
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM,  
ZW.

- (84) **Designated States** (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ,  
UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,  
TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,  
EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,  
MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,  
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,  
KM, ML, MR, NE, SN, TD, TG).

**Published:**

- with international search report (Art. 21(3))
- before the expiration of the time limit for amending the  
claims and to be republished in the event of receipt of  
amendments (Rule 48.2(h))



WO 2014/152798 A1

(54) **Title:** CERAMIC SUPPORT STRUCTURE

(57) **Abstract:** A pre-ceramic support structure for additive manufacturing, that upon thermal processing, is soluble in various solvents.

## CERAMIC SUPPORT STRUCTURE

### TECHNICAL FIELD

[0001] The disclosure is related to the use of a melt processable pre-ceramic materials for applications as a support structure in additive manufacturing.

### BACKGROUND

[0002] Additive manufacturing technology, also recognized as three dimensional printing technology, builds three-dimensional objects through layer-by-layer deposition of thermoplastic materials. A plastic filament is utilized to deliver materials to an extrusion nozzle. The nozzle is heated to melt the material and can be moved in both horizontal and vertical directions by computer control. The three dimensional object is produced by extruding small beads of thermoplastic material to form layers. The layers of thermoplastic material harden after extrusion. Support materials are often employed to assist in building certain three dimensional objects. The support structures are thermoplastic materials that can be removed from contact with other extruded materials by physical or chemical means. Certain support materials are selectively soluble in certain liquids. The composition of a thermoplastic support materials and the liquid can be selected so that the liquid dissolves the support material, but not the intended material of construction for the desired object.

### SUMMARY

[0003] One embodiment involving additive manufacturing of ceramics is a process where thermoplastic filaments of pre-ceramic powders are extruded to form a three dimensional article. In certain applications of additive manufacturing, a sacrificial "support" layer is utilized to assist in forming "build" layers that create the intended three-dimensional product. The support layer will be subsequently removed to create a final object. During the additive manufacturing of ceramics in accordance with this disclosure, thermoplastic

polymers carry the pre-ceramic powders to form three-dimensional green ceramic parts that contain the thermoplastic binder. For purposes of this disclosure, the thermoplastic polymers with the pre-ceramic can be intended as either the support layer as well as the build layer. The parts are then subjected to a binder removal and sintering cycle during firing of the object, resulting in certain embodiments in ceramification. Due to the elevated temperatures for sintering, conventional thermoplastic support layers are not suitable simply because the temperatures are far above the degradation temperatures of the polymer. The degradation of the support structure in turn may adversely affect the build layer and the intended article. This has limited the types of three-dimensional ceramic objects produced utilizing conventional additive manufacturing practices.

[0004] This disclosure is directed to the use of a pre-sintered support layer or structure for additive manufacturing, that upon firing or sintering, is soluble in various solvents. The compositions are additive manufacturing feedstocks, having a polymeric matrix and a pre-ceramic compound, wherein the post-sintered support layer is soluble or removable in a solvent. In general, the feedstocks are produced using melt processing techniques to form filaments that are suitable in applications with additive manufacturing processes and equipment.

[0005] For purposes of this disclosure, ceramic means a material that has been subject to a thermal process, or firing, to form an anhydrous or substantially anhydrous material. A green ceramic is a material that has not been subjected to a thermal process. Green ceramifiable articles can be produced with additive manufacturing wherein a pre-sintered build layer is supported by a pre-sintered support layer. Upon firing of the green article, the polymeric binders from both the build and support layers are removed by thermal degradation, and in doing so, the build layer is transformed into a ceramic composition by additional thermal processing or sintering. The support layer maintains shape and structural support of the build layer during this process. With the removal of polymeric binder, the remaining material of the support layer is soluble or removable in a solvent. The entire object of the now ceramic support structure can be subject to a solvent where it is removed, thereby leaving the finished ceramic article formed by the build layer.

## DETAILED DESCRIPTION

[0006] A pre-sintered support structure for additive manufacturing can be used to assist in the formation of three-dimensional ceramic articles. The feedstocks for the pre-sintered support structure are produced using melt processing techniques to form, in certain embodiments, filaments that are suitable in applications with additive manufacturing processes and equipment. The support structure filaments are employed with build structure filaments to create three-dimensional objects by additive manufacturing.

[0007] In certain embodiments, green ceramifiable articles may be produced with additive manufacturing techniques. The green ceramifiable article is supported by a support composition of a polymeric matrix and a pre-ceramic compound. Upon firing of the green article at elevated temperatures, the entire object including the post sintered support structure can be subject to a solvent bath where the ceramic support structure is removed, thereby leaving the finished ceramic article.

[0008] The support layer feedstock intended as the support structure is primarily a pre-ceramic powder or powder blend in a polymeric matrix. The polymer serves as a binder for the pre-ceramic powder or powder blend. The polymeric matrix imparts the necessary strength for the creation of a molded or printed support structure. Additionally, it imparts the desired physical properties required to make the feedstock for the additive manufacturing process. The polymeric matrix may be any thermoplastic polymer capable of melt processing and functioning as a feedstock for additive manufacturing. They include both hydrocarbon and non-hydrocarbon polymers. In certain embodiments, the polymeric matrix may be a polyethylene, an ethylene-octene copolymer, or combinations thereof. Other non-limiting examples of polymeric matrices include other polyolefins, polylactic acid polymers, and acrylonitrile butadiene styrene polymers or combinations thereof. The polymeric matrix may be included in the pre-ceramic feedstock in amounts ranging from about 0.1% to about 25% by weight. In certain embodiments, the polymeric matrix may be included at about 0.5% to about 5% by weight. In some embodiments, the feedstock is generally in the form of an extruded filament.

[0009] The pre-ceramic materials suitable for additive manufacturing are powders or micron sized compounds that are soluble in either a pre-ceramic or sintered state in various solvents. In some embodiments, the pre-ceramic is an acid labile mineral capable of forming a semi - solid under high heat. The intended application suggests that in certain embodiments the support structure, upon formation, must not soften below 700 °C. Additionally, the support structure must not melt below 1200 °C. Non-limiting examples of pre-ceramic materials include calcium carbonate, sodium carbonate, sodium aluminate or calcium carbide. Those of ordinary skill in the art with knowledge of this disclosure are capable of selecting a specific material to match the intended additive manufacturing article. For example, in applications where sintering does not exceed 850 °C sodium carbonate may also be used. In applications exceeding the 950 °C limits of calcium carbonate, sodium aluminate may be used up to 1500 °C. In applications requiring extreme heat, calcium carbide may be employed, up to 2000 °C. The amount of pre-ceramic material in the feedstock may be at least 50%. In certain embodiments the pre-ceramic material is greater than 75% and even greater than 95%.

[0010] In some embodiments, a flux is used to reduce the overall melting point of the pre-ceramic material and thereby enhance the efficiency of the sintering process. The flux may be any glass or ceramic material, which flows below the softening point of the pre-ceramic material. Non-limiting examples of flux materials include glass frits comprised of boron trioxide, silicon oxide, zirconium dioxide, lithium oxide, fluorine, titanium dioxide, and combinations thereof. The flux may be included in the feedstock composition in amounts up to 20%. In one embodiment, a suitable flux is Ferro Frits 90 740 F from the Ferro Corporation, Frankfurt, DE. In another embodiment, the flux may include silicates with melting points from 600 °C to 1000 °C. The flux may be added to the feedstock during melt processing.

[0011] In alternative embodiment, various processing additives may be utilized in the formation of the feedstock. Non-limiting examples of processing aids include waxes, moisture scavengers, lubricants and debinders. The processing additives are included in the melt processable composition in an amount of about 0.5 wt% to about 5 wt%.

[0012] The components comprising the feedstock are blended and subjected to melt

processing. The feedstock can be pelletized and then subsequently formed into a filament suitable for additive manufacturing. In some embodiments, the filament has a modulus of approximately 300 MPa to 1600 MPa.

[0013] The melt processing of the feedstock is generally performed in a twin-screw extruder. In certain embodiments, the processing is performed in co-rotating, segmented twin-screw extruder. In such instances, the length:diameter ratio of the twin screw extruder is at least 32:1. In another embodiment, the length:diameter ratio of the twin screw extruder is at least 40:1. Typical temperature profiles may range from 120- 220 °C with typical screw speeds potentially in the range of about 200-300 RPM. Die pressures can be minimized to ensure incorporation of all pre-ceramic materials into the thermoplastic binder. Those who are skilled in the art will recognize preferred screw designs and temperature profiles to achieve optimal blending of the melt processable compositions of this invention.

[0014] The feedstock containing pre-ceramic materials is used in additive manufacturing as a support structure for ceramic articles. The support structure or layers are utilized with build layers to form a three-dimensional article or object. The materials are capable of withstanding the elevated temperatures necessary to place a green ceramic article into its desired ceramic form. Those of ordinary skill in the art are capable of selecting an appropriate feedstock to match a particular ceramic. Additionally, additive manufacturing equipment and techniques may be selected depending upon the desired finished article. One example of an additive manufacturing device is a Makerbot Replicator 2X additive manufacturing printer, available from Stratasys Ltd, Minneapolis, MN.

[0015] An article created with a pre-sintered build structure, along with the pre-sintered support structure or layer, is fired at elevated temperatures. During the firing of the green ceramic article the support structure or layers withstand the elevated temperatures and do not deform and thereby do not adversely affect the intended ceramic article. The support structure or layers may then be removed in suitable solvents. The removal of the support structure or layers results in the finished ceramic article. Suitable solvents will depend upon the pre-ceramic material used in the feedstock. Non-limiting examples include;

water, carbonated solutions, and acidic solutions. Those of ordinary skill in the art are capable of selecting a specific solvent based on the pre-ceramic material selected in the feedstock.

[0016]

#### EXAMPLES

Material	Supplier
PE1	Engage 8003, ethylene-octene copolymer, commercially available from Dow Chemical Corporation, Midland, MI.
Calcium Carbonate	GLC-1012d, 12 micron CaCO <sub>3</sub> , commercially available from Great Lakes Calcium, Green Bay, WI.

#### [0017] Compounding Procedure for Example 1

For Example 1, ethylene-octene copolymer resin PE1, and Calcium Carbonate powder were dry blended and then fed using a gravimetric feeder into a 27 mm co-rotating twin screw extruder (32:1, L:D) fitted with a strand die (commercially available from Leistritz Corporation, Allendale, NJ). Samples were processed with a screw rotational speed of 250 rpm using the following temperature profile: Zone 1-10 = 180 °C, Die = 160 °C. The resulting strands of extrudate were subsequently continuously processed onto a belt, cooled to room temperature by fans, and pelletized into 0.64 cm pellets. The resulting pellets were used to press 6 mm square plaques, 6 mm in depth.

#### [0018] Pressing Procedure for CE1 and Example 2

Plaques in Example 2 were made using a heated platen hydraulic press (commercially available from Dake Corporation, Grand Haven, MI). Approximately 110g of pellets from example 1 were spread in an aluminum frame equating to the dimensions previously listed, and covered with aluminum foil. The top and bottom platens, heated to 175 °C, were made to contact the pellets of example 1 in the aluminum frame for 3 min, under minimal pressure. After 3 min, 15 tons of pressure was applied to the material for 5 min, after which time, the material was removed and allowed to cool to room temperature at an unspecified rate. This procedure was repeated using, previously demonstrated, ceramifiable polymer to produce 10 x 10 x 0.6 cm plaques of CE1.

Three aluminum frames were stacked vertically. A plaque of CE1 was placed in the bottom. The plaque of example 1 was cut into a cross of equal legs, 5 cm wide with an outer diameter of 4 inches, fitting into the aluminum frame previously used. Pellets of a ceramifiable material used to make CE1 were placed in the cavities of the second frame. A third plaque of CE1 was placed on top and the sample pressing procedure was followed to make example 2. Example 2 having final dimensions of 10 x 10 x 0.6 cm, made of CE1 and having a cross of example 1 centered internally.

**[0019] Ceramification and Dissolution of Example 2 into Example 3**

Example 2 was heated in a muffle furnace (commercially available from ThermoFisher Scientific Corporation, Waltham, MA) to 950 °C for 20 min at an unspecified rate. This material was removed from the furnace and allowed to cool to room temperature at an unspecified rate. This conversion yielded a wholly ceramified, intact article of similar initial dimensions of example 2. Upon immersion in a water bath, the CaCO<sub>3</sub> material from example 1 was entirely dissolved leaving example 3 of dimensions equal to the CE1 material only, in example 2.

**[0020] Example 4**

A filament containing a pre-ceramic material suitable as a support layer, is extruded in a manner similar to that of Example 1, and wound onto a spool. A second filament containing a pre-ceramic material suitable as a build layer is also produced in a manner similar to Example 1 and wound onto a spool. The spools are loaded into a MakerBot Replicator 2X additive manufacturing printer, available from Stratasys Ltd, Minneapolis, MN. The filament from each spool is fed into the MakerBot 2X extruder nozzles in accordance with the printers loading procedures.

A CAD file of a three-dimensional article requiring a support layer and a build layer with 90° overhangs of the build layer is selected and loaded into the MakerBot 2X.

The loaded filaments are printed at temperature of about 160 to 200 °C and at printing speeds ranging between 20 and 100 mm/sec with acceleration enabled. The materials are

printed onto a standard Kapton tape heated to about 100 °C. Filament are printed with an infill between 5 and 95%. Layer heights are between 0.10 and 0.35 mm.

The printed article having a build and support layer constructed from pre-ceramic filaments is subjected to a thermal treatment. The printed article is placed in a muffle furnace and heated to about 450 °C, under an inert, oxidizing, or reducing gas, to thermally remove any thermoplastic material and water. The printed article is then further heated to in excess of 750 °C, under an inert, oxidizing, or reducing gas, to enable sintering and thereby create a ceramic, or substantially ceramic, article.

The article is cooled at an appropriate rate so as not to produce thermal cracking or warping. The article does not exhibit any warping of either the support layer or the build layer. The structure of the build layer is supported by the support layer material that remains post-thermal treatment. The article is then submersed in an appropriate solvent to dissolve or disperse the support layer. The article comprising the remaining build material is removed from solvent and dried.

[0021] Table 1 gives the formulations for example 1

[0022] Table 1. Formulation for Example 1

	PEI	CaCO <sub>3</sub>
CEI	25	75

**What is claimed is:**

1. A composition comprising an additive manufacturing feedstock having a polymeric matrix and a pre-ceramic material, wherein the pre-ceramic material is removable in a solvent.
2. A composition according to claim 1, wherein the polymeric matrix is one or more of polyolefins, polylactic acid polymers, and acrylonitrile butadiene styrene polymers or combinations thereof.
3. A composition according to claim 1, wherein the pre-ceramic material is calcium carbonate, sodium carbonate, sodium aluminate or combinations thereof.
4. A composition according to claim 1, further comprising one or more of a fluxing material, a polymer processing additive or combinations thereof.
5. A composition according to claim 4, wherein the fluxing material includes glass frits having boron trioxide, silicon oxide, zirconium dioxide, lithium oxide, fluorine, titanium dioxide, and combinations thereof.
6. A composition according to claim 1, wherein the solvent includes water, carbonated solutions, and acidic solutions.
7. A composition according to claim 1, wherein the additive manufacturing feedstock is suitable as a support structure.
8. A composition comprising a feedstock for additive manufacturing, wherein the feedstock is a polymeric matrix and a pre-ceramic material, the pre-ceramic material upon thermal processing is removable in a solvent.
9. A method comprising producing an article by additive manufacturing using a feedstock of a polymeric matrix and a pre-ceramic material, wherein the pre-ceramic material post-sintering is removable in a solvent.

10. A method comprising creating a green article with additive manufacturing wherein the green article has a build layer supported by a support layer derived from a polymeric matrix and a pre-ceramic material, wherein the pre-ceramic material is removable in a solvent.

11. A method according to claim 10, further comprising firing the green article.

12. A method according to claim 11, further comprising removing the support layer by a solvent.

13. A method according to claim 11, wherein the solvent includes water, carbonated solutions, and acidic solutions.

14. An article comprising a filament for additive manufacturing wherein the filament is a polymeric matrix and a pre-ceramic material, wherein the pre-ceramic material is removable in a solvent.

15. An article comprising a green ceramic article wherein the green ceramic article is supported by a support composition of a polymeric matrix and a pre-ceramic material, wherein the pre-ceramic material is removable in a solvent.

**A. CLASSIFICATION OF SUBJECT MATTER****B29C 67/00(2006.01)i**

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**Minimum documentation searched (classification system followed by classification symbols)  
B29C 67/00; G09G 5/02; B32B 3/00; C08L 33/02; B05D 1/38; D01F 8/04; C08L 25/08Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched  
Korean utility models and applications for utility models  
Japanese utility models and applications for utility modelsElectronic data base consulted during the international search (name of data base and, where practicable, search terms used)  
eKOMPASS(KIPO internal) & keywords: additive manufacturing, feedstock, polymeric matrix, pre-ceramic, solvent, fluxing, support**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2012-0258250 A1 (RODGERS, LUKE M.B.) 11 October 2012 See abstract; claims 1-20.	1-15
A	US 2012-0258250 A1 (RODGERS, LUKE M.B.) 11 October 2012 See abstract; claims 1-20.	1-15
A	WO 2010-045147 A2 (STRATASYS, INC.) 22 April 2010 See abstract; claims 1-20.	1-15
A	US 2006-0158456 A1 (ZINNIEL, ROBERT L. et al.) 20 July 2006 See abstract; claims 1-20.	1-15
A	US 2006-0158456 A1 (ZINNIEL, ROBERT L. et al.) 20 July 2006 See abstract; claims 1-20.	1-15

 Further documents are listed in the continuation of Box C. See patent family annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&amp;" document member of the same patent family

Date of the actual completion of the international search

18 August 2014 (18.08.2014)

Date of mailing of the international search report

**19 August 2014 (19.08.2014)**

Name and mailing address of the ISA/KR

International Application Division  
Korean Intellectual Property Office  
189 Cheongsu-ro, Seo-gu, Daejeon Metropolitan City, 302-701,  
Republic of Korea

Facsimile No. +82-42-472-7140

Authorized officer

HONG, Sung Ran

Telephone No. +82-42-481-5405



**INTERNATIONAL SEARCH REPORT**

Information on patent family members

International application No.

**PCT/US2014/027775**

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2012-0258250 A1	11/10/2012	EP 2694274 A1 US 8460755 B2 WO 2012-138842 A1	12/02/2014 11/06/2013 11/10/2012
US 2012-0231225 A1	13/09/2012	US 2013-224423 A1	29/08/2013
WO 2010-045147 A2	22/04/2010	CA 2740166 A1 CN 102186918 A EP 2350188 A2 JP 2012-509777 A KR 10-1313061 B1 KR 10-20110080161A US 2010-0096072 A1 US 2010-0100675 A1 US 8246888 B2 US 8499120 B2 WO 2010-045147 A3	22/04/2010 14/09/2011 03/08/2011 26/04/2012 30/09/2013 12/07/2011 22/04/2010 22/04/2010 21/08/2012 30/07/2013 10/06/2010
US 2006-0158456 A1	20/07/2006	CN 101449295 A CN 101449295 B EP 1846912 A2 EP 1846912 A4 JP 2008-538329 A JP 4731573 B2 US 2007-0229497 A1 US 7236166 B2 US 7502023 B2 WO 2006-078342 A2 WO 2006-078342 A3	03/06/2009 27/06/2012 24/10/2007 22/02/2012 23/10/2008 27/07/2011 04/10/2007 26/06/2007 10/03/2009 27/07/2006 25/09/2008