



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : C08F 36/18, 2/42</p>	<p>A1</p>	<p>(11) International Publication Number: WO 99/37696 (43) International Publication Date: 29 July 1999 (29.07.99)</p>
<p>(21) International Application Number: PCT/US99/01286 (22) International Filing Date: 22 January 1999 (22.01.99) (30) Priority Data: 60/072,218 22 January 1998 (22.01.98) US (71) Applicant: DUPONT DOW ELASTOMERS L.L.C. [US/US]; 300 Bellevue Parkway, Wilmington, DE 19809 (US). (72) Inventor: LYONS, Donald, Frederick; 2503 Teal Road, Wilmington, DE 19805 (US). (74) Agent: SCOTT, Patricia, M.; Dupont Dow Elastomers L.L.C., Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).</p>	<p>(81) Designated States: BR, CN, ID, JP, KR, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>	
<p>(54) Title: INHIBITOR COMPOSITION FOR CHLOROPRENE POLYMERIZATION</p> <p>(57) Abstract</p> <p>Polymerization inhibitor compositions for the emulsion polymerization of chloroprene comprise a 4-(lower alkoxy)phenol and a hindered bis(phenol)methane in a molar ratio in the range of 0.5/1-2.5/1. Discoloration resistant polychloroprene rubbers are produced.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakistan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

5

TITLE

INHIBITOR COMPOSITION FOR CHLOROPRENE POLYMERIZATION

10

BACKGROUND OF THE INVENTION

Field of the Invention

15 This invention relates to an inhibitor for the emulsion polymerization of chloroprene and a process for making a discoloration-resistant polychloroprene using such inhibitor.

Background Art

20 Chloroprene is a highly reactive monomer. Spontaneous free-radical polymerization is expected for uninhibited chloroprene monomer at ordinary temperatures (Encyclopedia of Polymer Science and Engineering, Volume 3, second edition, p. 442 (1985)).


25 Emulsion polymerization is the preferred way to accommodate the high polymerization rates of chloroprene and achieve high molecular weight. In order to control the polymerization reaction and prevent additional reactions after the desired molecular weight is reached, the polymerization reaction is usually not taken to full conversion of the chloroprene monomer. Rather, the reaction mixture is treated with an inhibitor, often referred to as a shortstop, 30 which effectively stops the polymerization at less than 100% conversion. The residual chloroprene monomer is then removed.

Known effective shortstops for the emulsion polymerization of chloroprene such as phenothiazine and para-tert-butyl catechol, are usually highly colored or photosensitizers. They lead to polychloroprenes which 35 discolor quickly under sunlight. Other materials disclosed as a shortstop or stabilizer for the emulsion polymerization of chloroprene include a class of bis(phenol)methane compounds which are substituted with alkyl radicals in the

5 positions ortho and para to each of the hydroxy groups (the “Rosahl compounds”), which are disclosed by Rosahl et al. in US Patent 3,074,899. While the “Rosahl” compounds do yield polymers with a low tendency to discolor, Applicant has found that they do not safely and effectively shortstop chloroprene polymerization when the “Rosahl” compounds are used as the sole
10 inhibitor. Further in US Patent 4,481,313, Banta et al. disclose that the emulsion polymerization of chloroprene can be shortstopped using phenolic antioxidants such as hydroquinone, 2,5-di-tert-amylhydroquinone, 4-tert-butyl-pyrocatechol, 4,4'-thiobis(6-tert-butyl-o-cresol) and 2,6-di-tert-butyl-4-phenylphenol. The phenolic antioxidants disclosed in US Patent 4,481,313 either cause
15 discoloration or have been found by Applicant to be ineffective shortstops.

SUMMARY OF THE INVENTION

The invention is directed to a polymerization inhibitor composition for
20 the emulsion polymerization of chloroprene comprising a 4-(C₁-C₃ alkoxy)phenol and a hindered bis(phenol)methane of the formula



5 wherein each R¹ is independently selected from the group consisting of C₁-C₁₂ alkyl radicals and each R² is independently selected from the group consisting of H and C₁-C₁₂ alkyl radicals, the molar ratio of the alkoxyphenol to the hindered bis(phenol)methane being 0.5/1 – 2.5/1.

Further, the invention is directed to a process for making a discoloration-
10 resistant polychloroprene comprising the steps of polymerizing chloroprene monomer in an aqueous emulsion and shortstopping the polymerization step by adding the above inhibitor composition. A minimum of 0.0003% of the total of alkoxyphenol and bis(phenol)methane are required for an effective shortstop, based on the weight of total initial monomer in the polymerization process.

15 DETAILED DESCRIPTION OF THE INVENTION

Applicant has found that 4-(C₁-C₃ alkoxy)phenol compounds (sometimes referred to as hydroquinone mono(C₁-C₃ alkyl)ether compounds) are about as effective as the Rosahl compounds for shortstopping the emulsion
20 polymerization of chloroprene and that neither completely halts polymerization when used as the sole inhibitor. More importantly, Applicant has further discovered that a composition containing both types of compounds is a surprisingly more effective shortstop than either one alone and the combination can completely halt polymerization.

25 Emulsion polymerization of chloroprene is well known. It is used conventionally to produce a variety of chloroprene rubbers. The term "polymers of chloroprene" or "chloroprene rubbers" encompasses polymers in which chloroprene is the major or predominant monomer and include chloroprene dipolymers, terpolymers and higher copolymers. Organic comonomers such as
30 2,3-dichloro-1,3-butadiene; acrylonitrile, methacrylonitrile, lower alkyl acrylates, lower alkyl methacrylates, acrylamides, methacrylamides, lower alkyl maleates and fumarates, acrylic acid, methacrylic acid, fumaric acid and maleic acid may be employed.

Usually, the total amount of comonomers will represent no greater than
35 25 mole percent of the total monomers and preferably will constitute less than

5 15 mole percent of the total monomers including chloroprene. The term
"monomer" as used is understood to include all polymerizable monomer
excluding any elemental sulfur that may be incorporated into the polymer. The
total amount of monomers is generally at least 50 mole percent chloroprene,
preferably less than 25 mole percent comonomer and more preferably less than
10 15 mole percent comonomer.

Any process for polymerizing chloroprene in aqueous emulsion which
does not interfere with the novel characteristics of this invention can be
employed. Processes and methods for the polymerization and recovery of
chloroprene are disclosed, for example, in the "Encyclopedia of Polymer
15 Science and Technology," supra, and in numerous patents such as U.S. Pat. Nos.
2,264,173 and 2,264,191 both issued on Nov. 25, 1941 and Whitby, "Synthetic
Rubber", 1954, p. 770. The polymerization may be conducted either batchwise
or continuously.

A typical process begins with a recipe which calls for an emulsifier,
20 water, chloroprene, comonomer as appropriate, either elemental sulfur or a
chain-transfer agent, and other additives for colloidal stability.

Conventional emulsifiers may be employed such as the salts of rosins
and rosin derivatives such as tall oil rosin (or resin), wood rosin,
disproportionated rosins and salts thereof. Rosin base emulsifiers are well
25 known to the art. A particularly preferred rosin emulsifier is wood rosin
(unmodified except for clean-up and sold by the Reichhold Chemicals as Nancy-
Wood Rosin).

In general practice, chloroprene is polymerized in the presence of either
elemental sulfur or a sulfur-containing chain-transfer agent. Elemental sulfur is
30 incorporated into the backbone of the polymer. Polysulfide bonds are
subsequently cleaved by a peptizing agent. The amount of sulfur can range from
as low as 0.1% or less based on polymerizable compounds (monomer) up to the
maximum proportion soluble in the non-aqueous phase under the conditions of
the polymerization, ordinarily about 0.2 to 2.5%, preferably in the range of 0.2

5 to 0.8 parts of sulfur per 100 parts of monomer, more preferably 0.3 to 0.65 parts thereof.

In contrast to elemental sulfur, chain transfer agents react with growing polymer chain ends resulting in termination and end-capping. Conventional chain-transfer agents include mercaptans such as dodecyl mercaptan and
10 disulfides such as alkylxanthogen disulfides. Generally, at least 0.05 parts, preferably 0.05-0.8 parts and most preferably 0.1-0.25 parts, chain transfer agent are used per 100 parts monomer.

The usual methods may be employed to prepare the aqueous emulsion of monomers, either elemental sulfur or chain-transfer agent, emulsifier and water.
15 A stabilizer for the emulsion, such as a sodium salt of a naphthalensulfonic acid-formaldehyde condensation product is generally added to the aqueous phase as well. The proportions in the aqueous emulsion are not critical but generally the monomer will be present in an amount such as from 30 to 60 percent by weight based on the total weight of the composition.


20 The pH of the aqueous emulsion for polymerization may be varied depending upon the particular emulsification system employed and can be acidic, neutral or alkaline; however, it is preferred to have a pH in the range of about 7 to 13.5.

An initiator is added to the emulsion. Conventional initiators for
25 chloroprene polymerization may be employed. Preferred initiators are water-soluble peroxide initiators of the organic or inorganic type. Examples of organic peroxides are benzoyl peroxide, cumene hydroperoxide, tertiary-butyl isopropylbenzene hydroperoxide, azo catalysts such as alpha-alpha-azo-bis-isobutyronitrile and the like. Suitable inorganic peroxides are salts of inorganic
30 per acids including persulfates, perborates or percarbonates, e.g., ammonium or potassium persulfate and hydrogen peroxide. A solution of potassium persulfate and sodium 2-anthraquinone sulfonate is most preferred. The initiator may be used in amounts required to bring about polymerization at any desired rate with

5 suitable ranges being from 0.001 to 0.5 parts by weight per 100 parts of polymerizable monomer.

The reaction progress is monitored, usually by gas-chromatographic analysis of unreacted chloroprene or by following the specific gravity change as a result of polymerization. Normally, the polymerization is stopped at less than
10 complete conversion of all the chloroprene monomer. When reaching the conversion goal, polymerization is stopped by adding a minimum of 0.0003%, based on the weight of total starting monomer (chloroprene plus comonomers) in the polymerization, of the inhibitor composition of the invention, which comprises a 4-(C₁-C₃ alkoxy)phenol and a hindered bis(phenol)methane of the

5 formula



10

15

wherein each R^1 is independently selected from the group consisting of C_1 - C_{12} alkyl radicals and each R^2 is independently selected from the group consisting of H and C_1 - C_{12} alkyl radicals. The alkyl radicals may be straight-chain, branched or cyclic. Each R^1 is preferably a C_3 - C_{12} branched alkyl or cycloalkyl radical, more preferably a C_3 - C_{12} branched alkyl radical. Each R^2 is preferably a C_1 - C_{12} alkyl radical, more preferably a C_1 - C_6 alkyl radical. The most preferred hindered bis(phenol)methane compounds are 2,2'-methylene-bis-(6-tert-butyl-4-methylphenol) and 2,2'-methylene-bis-(6-tert-butyl-4-ethylphenol). The preferred alkoxyphenol is 4-methoxyphenol. The molar ratio of the alkoxyphenol to the bis(phenol)methane in the inhibitor composition is in the range of 0.5/1 – 2.5/1, preferably 0.75/1 – 2.0/1.

If elemental sulfur has been included in the polymerization, the polymer is then broken down by peptization, in which the polysulfide bonds are cleaved. Conventional peptizing agents such as tetraalkyl thiuram disulfides may be employed.

5 Unreacted monomer is then stripped off, for example, using steam in a
turbannular flow as well know in the art as described in US Patent 2,467,769.
Typically the stripped latex is acidified and may either be stored in that form or
the chloroprene rubber isolated, for example, by continuously coagulating it as a
polymer film on a freeze roll as known in the art and described in US Patent
10 2,187,146. The resultant polymer film is washed and dried and resistant to
discoloration.

Chloroprene rubbers made according to this invention can be used in any
typical chloroprene rubber application. They are particularly useful in adhesive
compositions such as solution adhesives and graft adhesives. In the solution
15 adhesives, chloroprene polymer is dissolved in an organic solvent and blended
with tackifiers, antioxidants and metal oxides. In the graft adhesives,
chloroprene polymer is dissolved in an organic solvent and grafted with methyl
methacrylate. The resulting graft polymer (in solution) is blended with
tackifiers and antioxidants.

20 The following examples are presented to illustrate the invention and are
not intended to limit the scope thereof. In the examples parts and percents are by
weight unless otherwise specified. The parts by weight in the specification and
claims are based on original monomer present in the polymerization unless
specified otherwise.

25

Examples

Test Method

30 A solution of 2000 g CD (chloroprene monomer), 60 g disproportionated
rosin, and 4.4 g n-dodecyl mercaptan was emulsified with a solution of 1720.5 g
demineralized water, 9.5 g NaOH (100%), 3.0 g sodium sulfite, and 8.0 g
sulfonated naphthalene-formaldehyde condensation product. The emulsion was
brought to a temperature of 40°C and an initiator solution of 0.005% potassium
persulfate and 0.000125% sodium 2-anthraquinone sulfonate was added.
35 Initiator solution was added until the specific gravity of the emulsion reached

5 1.062. Between 15 and 50 grams of initiator solution was required to reach this specific gravity. At this point the desired shortstop was added. A sample of emulsion was withdrawn and its solid content measured as a weight percentage of the emulsion.

10 5 grams of a second initiator solution of 0.05% potassium persulfate and 0.00125% sodium 2-anthraquinone sulfonate was added and the emulsion temperature was maintained at 40°C for one hour. Then another sample was withdrawn for solids content measurement.

15 The solids content of the first sample was subtracted from the solids content of the second sample to determine the extent of conversion drift (i.e., the extent to which the amount of reacted monomer changed between measurements). A smaller conversion drift value indicates a more effective shortstop; maximum effectiveness for a shortstopping composition is indicated by 0.0 conversion drift (i.e. no additional conversion of monomer to polymer in the period between measurements). A maximum conversion draft value of 0.2 is
20 required for safe and effective shortstopping ability.

Example 1

A shortstop emulsion was prepared by mixing together 47.0 grams toluene, 3.0 grams (8.8×10^{-3} moles) 2,2'-methylene-bis(6-tert-butyl-4-
25 methylphenol), 47.0 grams demineralized water, 1.0 grams (8.0×10^{-3} moles) 4-methoxyphenol, and 2.0 grams of Duponol WAQE, a 30% solution of sodium lauryl sulfate, (Witco Corporation, Greenwich, Connecticut). This represents an alkoxyphenol: hindered bis(phenol)methane molar ratio of 0.9:1. 32.0 grams of this shortstop emulsion was used as shortstop for the test recipe. The difference
30 in solids content was 0.0.

Example 2

A shortstop emulsion was prepared by mixing together 46.5 grams toluene, 3.0 grams (8.8×10^{-3} moles) 2,2'-methylene-bis(6-tert-butyl-4-
35 methylphenol), 46.5 grams demineralized water, 2.0 grams (1.6×10^{-2} moles)

5 4-methoxyphenol, and 2.0 grams Duponol WAQE. This represents an alkoxyphenol: hindered bis(phenol)methane molar ratio of 1.8:1. 32.0 grams of this shortstop emulsion was used as shortstop for the test recipe. The difference in solids content was 0.0.

10 Example 3

A shortstop emulsion was prepared as in Example 1. 15.0 grams of this shortstop emulsion was used as shortstop for the test recipe. The difference in solids content was 0.10.

5 Comparative Example 1

A shortstop emulsion was prepared by mixing together 46.0 grams toluene, 3.0 grams (8.8×10^{-3} moles) 2,2'-methylene-bis(6-tert-butyl-4-methylphenol), 46.0 grams demineralized water, 3.0 grams (2.4×10^{-2} moles) 4-methoxyphenol, and 2.0 grams Duponol WAQE. This represents an
10 alkoxyphenol: hindered bis(phenol)methane molar ratio of 2.7:1. 32.0 grams of this shortstop emulsion was used as shortstop for the test recipe. The difference in solids content was 0.4. This demonstrates operation outside the preferred molar ratio of alkoxyphenol to bis(phenol)methane.

15 Comparative Example 2

A shortstop emulsion was prepared by mixing together 48.0 grams toluene, 3.0 grams 2,2'-methylene-bis(6-tert-butyl-4-methylphenol), 48.0 grams demineralized water, and 1.0 grams Duponol WAQE. 14.0 grams of this
20 shortstop emulsion was used as shortstop for the test recipe. The difference in solids content was 4.1. This demonstrates operation with hindered bis(phenol)methane alone.

Comparative Example 3


A shortstop emulsion was prepared by mixing together 48.0 grams
25 toluene, 48.0 grams demineralized water, 3.0 grams 4-methoxyphenol and 1.0 grams Duponol WAQE. 14.0 grams of this shortstop emulsion was used as shortstop for the test recipe. The difference in solids content was 3.9. This demonstrates operation with alkoxyphenol alone.

5

CLAIMS

What is claimed is:

1. A polymerization inhibitor composition for the emulsion
polymerization of chloroprene comprising a 4-(C₁-C₃ alkoxy)phenol and a
10 hindered bis(phenol)methane of the formula



15

20

wherein each R¹ is independently selected from the group consisting of C₁-C₁₂
alkyl radicals and each R² is independently selected from the group consisting of
25 H and C₁-C₁₂ alkyl radicals, the molar ratio of the alkoxyphenol to the hindered
bis(phenol)methane being in the range of 0.5/1 – 2.5/1.

2. The composition of claim 1 wherein the 4-(C₁-C₃ alkoxy)phenol
is 4-methoxyphenol.

3. The composition of claim 2 wherein each R¹ is independently
30 selected from the group consisting of C₃-C₁₂ branched alkyl and cycloalkyl
radicals.

- 5 4. The composition of claim 3 wherein the bis(phenol)methane is
2,2'-methylene-bis(6-tert-butyl-4-methylphenol).
5. The composition of claim 3 wherein the bis(phenol)methane is
2,2'-methylene-bis(6-tert-butyl-4-ethylphenol).
6. A process for making a discoloration-resistant polychloroprene
10 comprising the steps of polymerizing chloroprene monomer in an aqueous
emulsion and inhibiting the polymerization step by adding at least 0.0003%,
based on the weight of total starting monomer, of the composition of claim 1.
7. An adhesive composition comprising a polychloroprene made by
the process of Claim 6 and an organic solvent.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/01286

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 6 C08F36/18 C08F2/42

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 3 074 899 A (D ROSAHL ET AL.) 22 January 1963 cited in the application see column 2, line 11 - line 25; claim 2 ---	1,4,5
A	DATABASE WPI Section Ch, Week 7740 Derwent Publications Ltd., London, GB; Class A60, AN 77-71364Y XP002103587 & JP 52 100419 A (KYOWA GAS CHEM IND) , 23 August 1977 see abstract -----	1,2

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

° Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

25 May 1999

Date of mailing of the international search report

07/06/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Van Humbeeck, F

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 99/01286

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3074899 A	22-01-1963	DE 1104701 B GB 888993 A	
