



HU000035705T2

(19) **HU**(11) Lajstromszám: **E 035 705**(13) **T2****MAGYARORSZÁG**
Szellemi Tulajdon Nemzeti Hivatala**EURÓPAI SZABADALOM**
SZÖVEGÉNEK FORDÍTÁSA

(21) Magyar ügyszám: **E 14 800045** (51) Int. Cl.: **C08F220/28** (2006.01)
(22) A bejelentés napja: **2014. 11. 19.** **C08F265/06** (2006.01)
C08F283/06 (2006.01)
C08F220/34 (2006.01)
(96) Az európai bejelentés bejelentési száma: **EP 20140800045**
(97) Az európai bejelentés közzétételi adatai: **EP 3074438 A1** **2015. 06. 04.** (86) A nemzetközi (PCT) bejelentési szám: **PCT/EP 14/074957**
(97) Az európai szabadalom megadásának meghirdetési adatai: **EP 3074438 B1** **2017. 09. 06.** (87) A nemzetközi közzétételi szám: **WO 15078736**

(30) Elsőbbségi adatok: 13194689 2013. 11. 27. EP	(73) Jogosult(ak): BASF SE, 67056 Ludwigshafen am Rhein (DE) Henkel AG & Co. KGaA, 40589 Düsseldorf (DE)
(72) Feltaláló(k): PIRRUNG, Frank, 67269 Grünstadt (DE) KOU, Huiguang, 68519 Viernheim (DE) LANGENDÖRFER, Miriam, 67117 Limburgerhof (DE) ETTL, Roland, 68804 Altlußheim (DE) VACANO, Bernhard Ulrich von, 68165 Mannheim (DE) BARRELEIRO, Paula, 40593 Düsseldorf (DE) JUNKES, Christa, 40595 Düsseldorf (DE) ZIPFEL, Johannes, 40593 Düsseldorf (DE) GIESEN, Brigitte, 40265 Düsseldorf (DE) BESSLER, Cornelius, 40231 Düsseldorf (DE) HUTMACHER, Martina, 40629 Düsseldorf (DE)	(74) Képviselő: SBGK Szabadalmi Ügyvivői Iroda, Budapest

(54) **Random kopolimerek mosási eljárásban szennyezés eltávolító szerként**

Az európai szabadalom ellen, megadásának az Európai Szabadalmi Közlönyben való meghirdetésétől számított kilenc hónapon belül, felszólalást lehet benyújtani az Európai Szabadalmi Hivatalnál. (Európai Szabadalmi Egyezmény 99. cikk(1))

A fordítást a szabadalmas az 1995. évi XXXIII. törvény 84/H. §-a szerint nyújtotta be. A fordítás tartalmi helyességét a Szellemi Tulajdon Nemzeti Hivatala nem vizsgálta.



(11) **EP 3 074 438 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
06.09.2017 Bulletin 2017/36

(51) Int Cl.:
C08F 220/28 ^(2006.01) **C08F 220/34** ^(2006.01)
C08F 265/06 ^(2006.01) **C08F 283/06** ^(2006.01)

(21) Application number: **14800045.8**

(86) International application number:
PCT/EP2014/074957

(22) Date of filing: **19.11.2014**

(87) International publication number:
WO 2015/078736 (04.06.2015 Gazette 2015/22)

(54) **RANDOM COPOLYMERS AS SOIL RELEASE AGENTS IN LAUNDRY PROCESSES**

STATISTISCHE COPOLYMERE ALS SCHMUTZTRENNMITTEL IN WASCHVERFAHREN

COPOLYMÈRES STATISTIQUES UTILISÉS COMME AGENTS ANTISALISSURES DANS DES
PROCÉDÉS DE LAVAGE DU LINGE

(84) Designated Contracting States:
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

(30) Priority: **27.11.2013 EP 13194689**

(43) Date of publication of application:
05.10.2016 Bulletin 2016/40

(73) Proprietors:
• **BASF SE**
67056 Ludwigshafen am Rhein (DE)
• **Henkel AG & Co. KGaA**
40589 Düsseldorf (DE)

(72) Inventors:
• **PIRRUNG, Frank**
67269 Grünstadt (DE)
• **KOU, Huiguang**
68519 Viernheim (DE)
• **LANGENDÖRFER, Miriam**
67117 Limburgerhof (DE)
• **ETTL, Roland**
68804 Altlußheim (DE)

- **VACANO, Bernhard Ulrich von**
68165 Mannheim (DE)
- **BARRELEIRO, Paula**
40593 Düsseldorf (DE)
- **JUNKES, Christa**
40595 Düsseldorf (DE)
- **ZIPFEL, Johannes**
40593 Düsseldorf (DE)
- **GIESEN, Brigitte**
40265 Düsseldorf (DE)
- **BESSLER, Cornelius**
40231 Düsseldorf (DE)
- **HUTMACHER, Martina**
40629 Düsseldorf (DE)

(74) Representative: **BASF IP Association**
BASF SE
G-FLP-C006
67056 Ludwigshafen (DE)

(56) References cited:
EP-A1- 1 911 778 **WO-A1-00/20471**
WO-A1-2004/055075

EP 3 074 438 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The present invention relates to random copolymers obtainable by polymerization, the use of said random copolymers as soil release agents in laundry processes. Further aspects of the invention are a method for easier releasing soil from textiles in laundry processes and detergents containing said random copolymers.

[0002] In customary household washing methods, the problem exists that some types of soil and dirt are difficult to remove from textiles when using suboptimal detergent formulations and/or low wash temperatures, because these soils and dirt are strongly attached to the fiber surface or are strongly absorbed inside the fibers.


[0003] The use of several agents as soil release agents in laundry processes is known. Examples are carboxymethyl cellulose or anionic derivatives of polymers from terephthalic acid and polyethylene glycol (see e.g. E. Smulders in "Laundry Detergents" Wiley-VCH Verlag GmbH, 2002, page 88). Regarding soil release agents it is often assumed that these are deposited and accumulated on the fiber surface during laundry washing, thereby modifying the surface properties of the fibers. Soil and dirt that is subsequently deposited onto this modified fiber surface is easier released in a subsequent washing cycle.

[0004] EP 0 955 791 A1 discloses that hydrophobically modified polycarboxylate polymers are useful for promoting soil release from fabrics by contacting the fabrics with compositions comprising these polymers.

[0005] WO 2004/055075 A1 discloses a graft copolymer having a number average molecular weight of at least 10,000 comprising backbone units derived from an ethylenically unsaturated monomer, hydrophilic uncharged side chains and cationically chargeable or charged side chains containing a tertiary or quaternary nitrogen atom. These graft copolymers are used in a laundry detergent composition to promote the release of soil from textile fabrics during laundering.


[0006] The objective of the present invention is to provide random copolymers with improved properties for use as soil release agents in laundry processes. A further object is to provide liquid and powder detergent compositions suitable for that use.

[0007] It has now been found, surprisingly, that the mentioned objectives can be met to a great extent by a random copolymer obtainable by polymerization of at least one monomer according to formula (I):



in an amount of 1 to 70 mole%,
wherein n is ≥ 3

and
at least one monomer according to formula (II):



in an amount of 30 to 99 mole%.

[0008] In a preferred embodiment, n of the monomer according to formula (I) is between 3 and 120, preferably between 5 and 50 and even more preferably between 7 and 46.

[0009] In another preferred embodiment, n of the monomer according to formula (I) is selected from the group consisting of 7, 23 and 46.

[0010] In a further preferred embodiment, the monomer according to formula (I) is present in the amount of 5 to 70 mole% and the monomer according to formula (II) is present in the amount of 30 to 95 mole%. In a more preferred embodiment, the monomer according to formula (I) is present in the amount of 9 to 70 mole% and the monomer according to formula (II) is present in the amount of 30 to 91 mole%. In an even more preferred embodiment, the monomer according to formula (I) is present in the amount of 9 to 67 mole% and the monomer according to formula (II) is present in the

amount of 33 to 91 mole%. In another preferred embodiment, the monomer according to formula (I) is present in the amount of 5 to 60 mole% and the monomer according to formula (II) is present in the amount of 40 to 95 mole%. In a further preferred embodiment, the monomer according to formula (I) is present in the amount of 5 to 50 mole% and the monomer according to formula (II) is present in the amount of 50 to 95 mole%.

[0011] The copolymer of the present invention can be produced by polymerization. More precisely, the copolymer of the present invention can be prepared by using known polymerization methods as described, for example, in the Examples below or in US 4,170,582, US 2009/0234062 or US 7,687,554, as exemplified for emulsion and miniemulsion polymerizations, but without use of surfactants.

[0012] A suitable process for preparing a copolymer of the present invention comprises mixing the monomers according to formula (I) and (II) and an initiator; or mixing the monomers according to formula (I) and (II), water and an initiator to establish a premix; or mixing the monomers according to formula (I) and (II), or mixing the monomers according to formula (I) and (II) and water to establish a separate premix and independently a premix from the initiator and a suitable solvent. In a second step, the premix is added to water, wherein the monomers are polymerized to obtain the polymer. The polymerization time depends on the temperature and the desired final product properties but is preferably within the range of from 0.5 to 10 hours at temperatures at a range from 25 °C and 100 °C, more preferably between 50 °C and 90 °C.

[0013] As radical polymerization initiators, the usual free radical initiators can be used. Preferably the free radical initiator is a bis-azo compound, a persulfate, a peroxide or a hydroperoxide, or a redox initiator.

Specific preferred radical sources are 2,2'-azobisisobutyronitrile, 2,2'-azobis(2-methylbutyronitrile), 2,2'-azobis(2,4-dimethylvaleronitrile), 2,2'-azobis[2(2-imidazolin-2-yl)propane]dihydrochloride, 2,2'-azobis(4-methoxy-2,4-dimethylvaleronitrile), 1,1'-azobis(1-cyclohexanecarbonitrile), 2,2'-azobis(isobutyramide) dihydrate, 2-phenylazo-2,4-dimethyl-4-methoxyvaleronitrile, dimethyl-2,2'-azobisisobutyrate, 2-(carbamoylazo)isobutyronitrile, 2,2'-azobis(2,4,4-trimethylpentane), 2,2'-azobis(2-methylpropane), 2,2'-azobis(N,N'-dimethylene-isobutyramidine), free base or hydrochloride, 2,2'-azobis(2-amidinopropane), free base or hydrochloride, 2,2'-azobis{2-methyl-N-[1,1-bis(hydroxymethyl)ethyl]propionamide} or 2,2'-azobis-{2-methyl-N-[1,1-bis(hydroxymethyl)-2-hydroxyethyl]propionamide; acetyl cyclohexane sulphonyl peroxide, diisopropyl peroxy dicarbonate, t-amyl perneodecanoate, t-butyl perneodecanoate, t-butyl perpivalate, t-amylperpivalate, bis(2,4-dichlorobenzoyl)peroxide, diisononoyl peroxide, didecanoyl peroxide, dioctanoyl peroxide, dilauroyl peroxide, bis(2-methylbenzoyl) peroxide, disuccinic acid peroxide, diacetyl peroxide, dibenzoyl peroxide, t-butyl per 2-ethylhexanoate, bis-(4-chlorobenzoyl)-peroxide, t-butyl perisobutyrate, t-butyl permaleinate, 1,1-bis(t-butylperoxy)3,5,5-trimethylcyclohexane, 1,1-bis(t-butylperoxy)cyclohexane, t-butyl peroxy isopropyl carbonate, t-butyl perisononaoate, 2,5-dimethylhexane 2,5-dibenzoate, t-butyl peracetate, t-amyl perbenzoate, t-butyl perbenzoate, 2,2-bis(t-butylperoxy)butane, 2,2 bis(t-butylperoxy)propane, dicumyl peroxide, 2,5-dimethylhexane-2,5-di-t-butylperoxide, 3-t-butylperoxy 3-phenylphthalide, di-t-amyl peroxide, 3,5-bis(t-butylperoxy)3,5-dimethyl 1,2-dioxolane, di-t-butyl peroxide, 2,5-dimethylhexyne-2,5-di-t-butylperoxide, 3,3,6,6,9,9-hexamethyl 1,2,4,5-tetraoxa cyclononane, p-menthane hydroperoxide, pinane hydroperoxide, cumene hydroperoxide, t-butyl hydroperoxide, hydrogen peroxide, potassium persulfate, sodium persulfate or ammonium persulfate.

Preferred examples for oil-soluble and water soluble initiators are azobisisobutyro nitrile, 2,2'-azobis[2(2-imidazolin-2-yl)propane]dihydrochloride, potassium persulfate, sodium persulfate, ammonium persulfate, tert-butyl peroxy maleic acid, succinic acid peroxide, and tert-butyl hydroperoxide, benzoylperoxide, di-tert-butylperoxide, hydrogen peroxide, tert-butylperoxybenzoate and tert-butylperoxy-2-ethylhexanoate.

[0014] The radical generation can be facilitated by a redox system like using ascorbic acid or hydroxymethylsulfates in combination with some of the initiators above.

The suitable amount of polymerization initiator is from 0.01 to about 5% by weight on the basis of the total amount of the monomers used.

[0015] A further aspect of the present invention is the use of a random copolymer according to the present invention as soil release agent in aqueous laundry processes.

[0016] Typically the aqueous laundry process is a domestic laundry process. For example the textile subjected to such a laundry process may be made from polyester, polyacrylate, cotton, wool, polyamide or mixtures thereof; preferably it is made from cotton.

[0017] One other aspect of the present invention is a method for soil release from textiles during an aqueous laundry process, which method comprises the step of adding a random copolymer according to invention in an effective amount to a detergent in an aqueous laundry process.

[0018] The term "effective amount" means an amount of a random copolymer according to invention that is sufficient to release the soil from textiles in aqueous laundry processes. Preferably, the random copolymer is used as part of a detergent it preferably is present in an amount of from 0.01 % by weight to 5 % by weight, based on the weight of the total detergent composition.

[0019] Another aspect of the present invention is a detergent comprising a random copolymer according to the present invention.

[0020] When the random copolymer is used as part of a detergent it preferably is present in an amount of from 0.01 % by weight to 5 % by weight, based on the weight of the total detergent composition.

[0021] Also an aspect of the invention is a detergent comprising the random copolymer according to the invention in an amount of from 0.01 % by weight to 5 % by weight, preferably from 0.1 % by weight to 2 % by weight, based on the weight of the total detergent composition.

[0022] The detergent according to the invention can be, for example, a bleach-containing heavy-duty detergent, a detergent for delicate textiles, or a detergent for colored goods. It can be solid, such as a powder, granulate, or tablet, or liquid, such as a structured (i.e. turbid) or unstructured (i.e. clear) liquid detergent based on water and/or one or more of organic solvents.

[0023] The detergent will normally include at least one surfactant which may be anionic, cationic, nonionic or amphoteric.


[0024] The anionic surfactant can be, for example, a sulfate, sulfonate or carboxylate surfactant or a mixture thereof. Preference is given to alkylbenzenesulfonates, alkyl sulfates, alkyl ether sulfates, olefin sulfonates, fatty acid salts, alkyl and alkenyl ether carboxylates or to an α -sulfonic fatty acid salt or an ester thereof.

[0025] Preferred sulfonates are, for example, alkylbenzenesulfonates having from 10 to 20 carbon atoms in the alkyl radical, alkyl sulfates having from 8 to 18 carbon atoms in the alkyl radical, alkyl ether sulfates having from 8 to 18 carbon atoms in the alkyl radical, and fatty acid salts derived from palm oil or tallow and having from 8 to 18 carbon atoms in the alkyl moiety. The average molar number of ethylene oxide units added to the alkyl ether sulfates is from 1 to 20, preferably from 1 to 10. The cation in the anionic surfactants is preferably an alkaline metal cation, especially sodium or potassium, more especially sodium. Preferred carboxylates are alkali metal sarcosinates of formula $R_{19}-CON(R_{20})CH_2COOM_1$ wherein R_{19} is C_9-C_{17} alkyl or C_9-C_{17} alkenyl, R_{20} is C_1-C_4 alkyl and M_1 is an alkali metal, especially sodium.

[0026] The non-ionic surfactant may be, for example, a primary or secondary alcohol ethoxylate, especially a C_8-C_{20} aliphatic alcohol ethoxylated with an average of from 1 to 20 mol of ethylene oxide per alcohol group. Preference is given to primary and secondary $C_{10}-C_{15}$ aliphatic alcohols ethoxylated with an average of from 1 to 10 mol of ethylene oxide per alcohol group. Non-ethoxylated non-ionic surfactants, for example alkylpolyglycosides, glycerol monoethers and polyhydroxyamides (glucamide), may likewise be used.

[0027] In addition to or instead of anionic and/or non-ionic surfactants the composition may contain cationic surfactants. Possible cationic surfactants include all common cationic surface-active compounds, especially surfactants having a textile softening effect.

[0028] Non-limiting examples of cationic surfactants are given in the formulas below:



wherein

each radical R_{α} is independent of the others C_{1-6} -alkyl-, -alkenyl- or -hydroxyalkyl;

each radical R_{β} is independent of the others C_{8-28} -alkyl- or alkenyl;

R_{γ} is R_{α} or $(\text{CH}_2)_n-\text{T}-\text{R}_{\beta}$;

R_{δ} is R_{α} or R_{β} or $(\text{CH}_2)_n-\text{T}-\text{R}_{\beta}$;

$T = -\text{CH}_2-$, $-\text{O}-\text{CO}-$ or $-\text{CO}-\text{O}-$ and n is between 0 and 5.

[0029] Preferred cationic surfactants include hydroxyalkyl-trialkyl-ammonium-compounds, especially C_{12-18} alkyl(hydroxyethyl)dimethylammonium compounds, and especially preferred the corresponding chloride salts.

[0030] Detergents of the present invention may contain up to 15 wt-%, for example between 0.5 wt-% and 15 wt-% of the cationic surfactant, based on the total weight of the composition.

[0031] The total amount of surfactants is preferably from 1 to 50 wt-%, especially from 1 to 40 wt-% and more especially from 1 to 30 wt-% of the detergent.

[0032] As builder substance there come into consideration, for example, alkali metal phosphates, especially tripolyphosphates, carbonates and hydrogen carbonates, especially their sodium salts, silicates, aluminum silicates, polycarboxylates, polycarboxylic acids, organic phosphonates, aminoalkylenepoly(alkylenephosphonates) and mixtures


of such compounds.

[0033] Silicates that are especially suitable are sodium salts of crystalline layered silicates of the formula $\text{NaHSi}_t\text{O}_{2t+1} \cdot p\text{H}_2\text{O}$ or $\text{Na}_2\text{Si}_t\text{O}_{2t+1} \cdot p\text{H}_2\text{O}$ wherein t is a number from 1.9 to 4 and p is a number from 0 to 20.

[0034] Among the aluminum silicates, preference is given to those commercially available under the names zeolite A, B, X and HS, and also to mixtures comprising two or more of such components. Special preference is given to zeolite A.

[0035] Among the polycarboxylates, preference is given to polyhydroxycarboxylates, especially citrates, and acrylates, and also to copolymers thereof with maleic anhydride. Preferred polycarboxylic acids are nitrilotriacetic acid, ethylenediaminetetraacetic acid and ethylenediamine disuccinate either in racemic form or in the enantiomerically pure (S,S) form.

[0036] Phosphonates or aminoalkylenepoly(alkylenephosphonates) that are especially suitable are alkali metal salts of 1-hydroxyethane-1,1-diphosphonic acid, nitrilotris(methylenephosphonic acid), ethylenediaminetetramethylenephosphonic acid and diethylenetriaminepenta-methylenephosphonic acid, and also salts thereof. Also preferred polyphosphonates have the following formula




wherein

R_{18} is $\text{CH}_2\text{PO}_3\text{H}_2$ or a water soluble salt thereof and d is an integer of the value 0, 1, 2 or 3.

[0037] Especially preferred are the polyphosphonates wherein b is an integer of the value of 1.

[0038] As bleach component, which preferably is a peroxide bleach, there come into consideration hydrogen peroxide and compounds capable of yielding hydrogen peroxide in aqueous solutions, for example, the organic and inorganic peroxides known in the literature and available commercially that may bleach textile materials at conventional washing temperatures, for example at a temperature in the range of from 10 to 95°C. Preferably, however, inorganic peroxides are used, for example persulfates, perborates, percarbonates and/or persilicates.

[0039] Peroxide bleach compounds may be utilized alone or in conjunction with a peroxyacid bleach precursor and/or a bleach catalyst. Peroxy acids precursors are often referred to as bleach activators. Suitable bleach activators include the bleach activators, that carry O- and/or N-acyl groups and/or unsubstituted or substituted benzoyl groups. Preference is given to polyacylated alkylenediamines, especially tetraacetyleneethylenediamine (TAED); acylated glycolurils, especially tetraacetyl glycol urea (TAGU), N,N-diacetyl-N,N-dimethylurea (DDU); sodium-4-benzoyloxy benzene sulphonate (SBOBS); sodium-1-methyl-2-benzoyloxy benzene-4-sulphonate; sodium-4-methyl-3-benzoyloxy benzoate; trimethyl ammonium toluoyloxy-benzene sulphonate; acylated triazine derivatives, especially 1,5-diacetyl-2,4-dioxohexahydro-1,3,5-triazine (DADHT); compounds of formula (6):



wherein R_{22} is a sulfonate group, a carboxylic acid group or a carboxylate group, and wherein R_{21} is linear or branched ($\text{C}_7\text{-C}_{15}$)alkyl, especially activators known under the names SNOBS, SLOBS and DOBA; nitrile compounds that form perimine acids with peroxides also come into consideration as bleach activators. These bleach activators may be used in an amount of up to 12 wt-%, preferably from 2-10 wt-% based on the total weight of the composition.

[0040] It is also possible to use bleach catalysts, which are commonly known, for example transition metal complexes as disclosed in EP 1194514, EP 1383857 or WO04/007657. Further bleach catalysts are disclosed in: US 2001044401, EP 0458397, WO 9606154, EP 1038946, EP 0900264, EP 0909809, EP 1001009, WO 9965905, WO 0248301, WO 0060045, WO 02077145, WO 0185717, WO 0164826, EP 0923635, DE 19639603, DE102007017654, DE102007017657, DE102007017656, US 20030060388, EP 0918840B1, EP 1174491A2, EP 0805794B1, WO 9707192A1, US 6235695B1, EP 0912690B1, EP 832969B1, US 6479450B1, WO 9933947A1, WO 0032731A1, WO 03054128A1, DE102004003710, EP 1083730, EP 1148117, EP 1445305, US 6476996, EP 0877078, EP 0869171, EP 0783035, EP 0761809 and EP 1520910. If desired a bleach catalyst may be combined with a peroxyacid bleach precursor.

[0041] The detergent may comprise one or more optical brighteners, for example from the classes bis-triazinylamino-stilbenedisulfonic acid, bis-triazolyl-stilbenedisulfonic acid, bis-styryl-biphenyl or bis-benzofuranyl(biphenyl), α bis-benzoxalyl derivative, bis-benzimidazolyl derivative or coumarin derivative or a pyrazoline derivative.

[0042] The compositions may furthermore comprise one or more further additives. Such additives are, for example, dirt-suspending agents, for example sodium carboxymethylcellulose; pH regulators, for example alkali metal or alkaline earth metal silicates; foam regulators, for example soap; salts for adjusting the spray drying and the granulating properties, for example sodium sulfate; perfumes; and also, if appropriate, antistatics and softening agents such as, for example, smectite; pigments; and/or toning agents. These constituents should especially be stable to any bleaching agent, if such is employed.

[0043] If such auxiliaries are used they normally are added in a total amount of from 0.1 - 20 wt-%, preferably from 0.5 - 10 wt-%, especially from 0.5 - 5 wt-%, based on the total weight of the detergent.

[0044] Furthermore, the detergent may optionally also comprise enzymes. Enzymes can be added for the purpose of stain removal. The enzymes usually improve the action on stains caused by protein or starch, such as, for example, blood, milk, grass or fruit juices. Preferred enzymes are cellulases and proteases, especially proteases. Cellulases are enzymes that react with cellulose and its derivatives and hydrolyse them to form glucose, cellobiose and cellooligosaccharides. Cellulases remove dirt and, in addition, have the effect of enhancing the soft handle of the fabric.

[0045] Examples of customary enzymes include, but are by no means limited to, the following:

proteases as described in US 6,242 405, column 14, lines 21 to 32;

lipases as described in US 6,242,405, column 14, lines 33 to 46;

amylases as described in US 6,242,405, column 14, lines 47 to 56; and

cellulases as described in US 6,242,405, column 14, lines 57 to 64;

Commercially available detergent proteases, such as Alcalase[®], Esperase[®], Everlase[®], Savinase[®], Kannase[®] and Durazym[®], sold e.g. by NOVOZYMES A/S;

Commercially available detergent amylases, such as Termamyl[®], Duramyl[®], Stainzyme[®], Nata-lase[®], Ban[®] and Fungamyl[®], sold e.g. by NOVOZYMES A/S;

Commercially available detergent cellulases, such as Celluzyme[®], Carezyme[®] and Endolase[®], sold e.g. by NOVOZYMES A/S;

Commercially available detergent lipases, such as Lipolase[®], Lipolase Ultra[®] and Lipoprime[®], sold e.g. by NOVOZYMES A/S;

Suitable mannanases, such as Mannanaway[®], sold by NOVOZYMES A/S.

[0046] The enzymes, when used, may be present in a total amount of from 0.01 to 5 wt-%, especially from 0.05 to 5 wt-% and more especially from 0.1 to 4 wt-%, based on the total weight of the detergent.

[0047] Further preferred ingredients in a detergent according to the invention are dye-fixing agents and/or polymers which, during the washing of textiles, prevent staining caused by dyes in the washing liquor that have been released from the textiles under the washing conditions. Such polymers are preferably polyvinylpyrrolidones, polyvinylimidazoles or polyvinylpyridine-N-oxides, which may have been modified by the incorporation of anionic or cationic substituents, especially those having a molecular weight in the range of from 5000 to 60 000, more especially from 10 000 to 50 000.

If such polymers are used, they are usually used in a total amount of from 0.01 to 5 wt-%, especially from 0.05 to 5 wt-%, more especially from 0.1 to 2 wt-%, based on the total weight of the detergent formulation. Preferred polymers are those mentioned in WO-A-02/02865 (see especially page 1, last paragraph and page 2, first paragraph) and those in WO-A-04/05688.

[0048] It is also possible to employ a random copolymer according to the invention in combination with a conventional soil-release polymer obtainable from dicarboxylic acid and optionally polymeric diol, in order to further enhance the cleaning power of laundry detergents when washing fabrics. In the context of a detergent according to the invention, such combinations are also possible. The known polyester soil-release polymers that can be additionally incorporated or used include copolyesters of dicarboxylic acids, for example adipic acid, phthalic acid, terephthalic acid or sulfoisophthalic acid, with diols, for example ethylene glycol or propylene glycol, and optionally polydiols, for example polyethylene glycol or polypropylene glycol.

[0049] The detergent according to the invention may also optionally contain one or more heavy metal chelating agents, such as hydroxyethylidiphosphonate (HEDP). More generally, chelating agents suitable for use herein can be selected from the group consisting of amino carboxylates, amino phosphonates, polyfunctionally-substituted aromatic chelating agents and mixtures thereof. Other suitable chelating agents for use herein are the commercial DEQUEST series, and chelants from Nalco, Inc. Aminocarboxylates useful as optional chelating agents include ethylene-diaminetetraacetates, N-hydroxyethylethylenediaminetriacetates, nitrilotriacetates, ethylenediamine tetrapropionates, triethylenetetraaminehexacetates, diethylenetriamine-pentaacetates, and ethanoldiglycines, alkali metal, ammonium, and substituted ammonium salts thereof and mixtures thereof. Aminophosphonates are also suitable for use as chelating agents in the com-

positions of the invention when at least low levels of total phosphorus are permitted in detergent compositions, and include ethylenediaminetetrakis (methylenephosphonates). Further biodegradable sequestrants are, for example, aminoacid acetates, such as Trilon M (BASF) and Dis-solvine GL (AKZO), as well as asparaginic acid derivatives, such as Baypure CX. Preferably, the aminophosphonates do not contain alkyl or alkenyl groups with more than about 6 carbon atoms. A highly preferred biodegradable chelator for use herein is ethylenediamine disuccinate

[0050] ("EDDS"). If utilized, such chelating agents or transition-metal selective sequestrants will generally comprise from about 0.001 wt-% to about 10 wt-%, more preferably from about 0.05 wt-% to about 1 wt-% of the laundry detergent compositions herein.

[0051] A preferred detergent according to the invention may additionally contain a dispersant polymer. When present, a dispersant polymer is typically at levels in the range from 0 wt-% to about 25 wt-%, preferably from about 0.5 wt-% to about 20 wt-%, more preferably from about 1 wt-% to about 8 wt-% of the detergent.

[0052] Suitable polymers are preferably at least partially neutralized or alkali metal, ammonium or substituted ammonium (e.g., mono-, di- or triethanolammonium) salts of polycarboxylic acids. The alkali metal, especially sodium salts are most preferred. While the molecular weight of the polymer can vary over a wide range, it preferably is from about 1,000 to about 500,000, more preferably is from about 1,000 to about 250,000.

[0053] Unsaturated monomeric acids that can be polymerized to form suitable dispersant polymers include acrylic acid, maleic acid (or maleic anhydride), fumaric acid, itaconic acid, aconitic acid, mesaconic acid, citraconic acid and methylenemalononic acid. The presence of monomeric segments containing no carboxylate radicals such as methyl vinyl ether, styrene, ethylene, etc. is suitable provided that such segments do not constitute more than about 50 wt-% of the dispersant polymer.

[0054] Copolymers of acrylamide and acrylate having a molecular weight of from about 3,000 to about 100,000, preferably from about 4,000 to about 20,000, and an acrylamide content of less than about 50 wt-%, preferably less than about 20 wt-% of the dispersant polymer can also be used. Most preferably, such dispersant polymer has a molecular weight of from about 4,000 to about 20,000 and an acrylamide content of from about 0 wt-% to about 15 wt-%, based on the total weight of the polymer.

[0055] Particularly preferred dispersant polymers are low molecular weight modified polyacrylate copolymers. Such copolymers contain as monomer units: a) from about 90 wt-% to about 10 wt-%, preferably from about 80 wt-% to about 20 wt-% acrylic acid or its salts and b) from about 10 wt-% to about 90 wt-%, preferably from about 20 wt-% to about 80 wt-% of a substituted acrylic monomer or its salt and have the general formula:

$-\left[\left(C(R_a)C(R_b)C(O)OR_c \right) \right]$ wherein the apparently unfilled valencies are in fact occupied by hydrogen and at least one of the substituents R_a , R_b , or R_c , preferably R_a or R_b , is a 1 to 4 carbon alkyl or hydroxyalkyl group; R_a or R_b can be a hydrogen and R_c can be a hydrogen or alkali metal salt. Most preferred is a substituted acrylic monomer wherein R_a is methyl, R_b is hydrogen, and R_c is sodium.

[0056] A suitable low molecular weight polyacrylate dispersant polymer preferably has a molecular weight of less than about 15,000, preferably from about 500 to about 10,000, most preferably from about 1,000 to about 5,000. The most preferred polyacrylate copolymer for use herein has a molecular weight of about 3,500 and is the fully neutralized form of the polymer comprising about 70 wt-% acrylic acid and about 30 wt-% methacrylic acid.

Other dispersant polymers useful herein include the polyethylene glycols and polypropylene glycols having a molecular weight of from about 950 to about 30,000.

[0057] Yet other dispersant polymers useful herein include the cellulose sulfate esters such as cellulose acetate sulfate, cellulose sulfate, hydroxyethyl cellulose sulfate, methylcellulose sulfate, and hydroxypropylcellulose sulfate. Sodium cellulose sulfate is the most preferred polymer of this group.

[0058] Other suitable dispersant polymers are the carboxylated polysaccharides, particularly starches, celluloses and alginates.

[0059] Yet another group of acceptable dispersants are the organic dispersant polymers, such as poly-aspartate.

[0060] Organic solvents that can be used in a detergent according to the invention, especially when the latter are in liquid or paste form, include alcohols having from 1 to 4 carbon atoms, especially methanol, ethanol, isopropanol and tert-butanol, diols having from 2 to 4 carbon atoms, especially ethylene glycol and propylene glycol, and mixtures thereof, and the ethers derivable from the mentioned classes of compound. Such water-miscible solvents are present in the cleaning formulations according to the invention preferably in amounts not exceeding 20 wt-%, especially in amounts of from 1 wt-% to 15 wt-%.

[0061] The detergent formulations can take a variety of physical forms such as, for example, powder granules, tablets (tabs), gel and liquid. Examples thereof include, *inter alia*, conventional high-performance detergent powders, super-compact high-performance detergent powders, conventional heavy duty liquid detergents, highly concentrated gels and tabs.

[0062] The detergent may also be in the form of an aqueous liquid containing from 5 wt-% to 90 wt-%, preferably from 10 wt-% to 70 wt-%, of water, or in the form of a non-aqueous liquid containing no more than 5 wt-%, preferably from 0 wt-% to 1 wt-% of water. Non-aqueous liquid detergent formulations may comprise other solvents as carriers. Low

molecular weight primary or secondary alcohols, for example methanol, ethanol, propanol and isopropanol, are suitable for that purpose. The solubilising surfactant used is preferably a monohydroxy alcohol but polyols, such as those containing from 2 to 6 carbon atoms and from 2 to 6 hydroxy groups (e.g., 1,3-propanediol, ethylene glycol, glycerol and 1,2-propanediol) can also be used. Such carriers are usually used in a total amount of from 5 wt-% to 90 wt-%, preferably from 10 wt-% to 50 wt-%, based on the total weight of the detergent formulation. The detergent formulations can also be used in so-called "unit liquid dose" form.

[0063] The definitions and preferences given above apply equally for all aspects of the invention.

[0064] The following examples illustrate the invention.

[0065] Abbreviations:

- GPC: gel permeation chromatography
- MPEG: Methoxypolyethylene glycol, Poly(ethylene glycol) mono-methylether

Reagents:

[0066]

- MPEG 2000MA as 50% aqueous solution
- Bisomer S10W (MPEG 1000MA) as 50% aqueous solution
- MPEG 350MA as water-free liquid
- 2-(Methacryloyloxy)ethyl]trimethylammoniumchloride as 80% aqueous solution
- WAKO VA-44 (= 2,2'-Azobis[2-(2-imidazolin-2-yl)propane]dihydrochloride)
- AIBN (= 2,2'-Azobis(2-methylpropionitrile)

Methods:

[0067]

- **Solid content** was measured at 150°C by a Mettler Toledo HR73 Halogen dryer with samples of 0.5 g.
- **GPC** was measured against polyethyleneglycol standards in aqueous 0.02 mol/l formic acid and 0.2 mol/l KCl solution on a SUPREMA-Gel(HEMA) column at 35°C and 0.8 ml/min flow.
- **Colour numbers** were determined against the Gardner scale with a LICO 150 equipment from Hach-Lange

Example 1: Preparation of aqueous solutions of random copolymers according to the present invention

[0068] In a 350 ml round reaction flask with overhead stirrer, cooler, thermometer and dropping funnel, 95 g of demineralized water was placed and inertized with N₂, followed by heating to an inside temperature of 90°C.

The monomer blend was prepared by mixing 56.25 g of MPEG 350MA (100%, 67 mole%) and 23.44 g of 2-(Methacryloyloxy)ethyl]trimethylammoniumchlorid (80% in water, 33 mole%), followed by addition of a solution of 0.45 g of WAKO VA-44 (0.6% based on monomers) in 10 g of water, and homogenized. This premix was added over a period of 3 hours to the reactor kept at 90°C. Then the contents were stirred for another 3 hours at 80 - 90°C. The final product was obtained as an almost colorless viscous liquid, and was filtered over a 125 µ sieve.

According to analysis via ¹H-NMR the conversion of the acrylic bonds was complete.

Data of the polymer 1 of Example 1:

Solid content 30.2%
 GPC Mn = 26,400 g/mol, Mw = 51,200 g/mol
 Colour 2.9 Gardner units

[0069] In accordance to the process described in Example 1, the following samples were prepared on the same scale and are summarized in Table 1:

Table 1: Polymers

Polymer	MPEG xxxxMA	Mole% MPEG MA	Mole% DMAE- MA-MeCl	Wako VA-044	Solid content	Gard ner color	Mn Mw PD	Aspect
1	350	67	33	0.60	30.2	2.9	26400 51200 1.90	colorless slight hazy liquid
2	1000	38.5	61.5	0.60	30,7	0,8	22200 41000 1.80	colorless clear liquid
3	2000	23.9	76.1	0.60	29.3	1.3	25100 44800 1.80	colorless clear liquid
4	2000	16.1	83.9	0.60	29.8	0.6	25600 48000 1.90	colorless clear liquid
5	1000	23.8	76.2	0.60	30.4	1.2	26600 51100 1.90	colorless slight hazy liquid
6	1000	23.8	76.2	1.03	31.1	1.4	3500 21330 6.1	colorless clear liquid
7	350	62.5	37.5	1.34	30.3	0.1	770 6500 8.5	colorless clear liquid
8	2000	9.4	90.6	1.12	30.3	0.6	42400 81930 1.9	colorless slight hazy liquid

Comparative Example 1: Manufacture of copolymer according to Example 6 of Table 2 of WO 2004/055075 A1

[0070] In a 350 ml round reaction flask with overhead stirrer, cooler, thermometer, and dropping funnel 92 g of demineralized water was placed and inertized with N₂, followed by heating to an inside temperature of 90°C.

The monomer blend was prepared by mixing 148.3 g of MPEG 2000MA (50% in water, 90 mole%) and 1.08 g of 2-(Methacryloyloxy)ethyl]trimethyl ammoniumchloride (80% in water, 10 mole%), followed by addition of a solution of 0.45 g of WAKO VA-44 in 10 g of water. This premix was added over a period of 3 hours to the reactor kept at 90°C. Then the contents were stirred for another 1.5 hours at 80 - 90°C. The final product was obtained as an almost colorless viscous liquid, and was filtered over a 125 μ sieve.

Data of Comparative Example 3:

Solid content 33,0%
GPC Mn = 20,600 g/mol, Mw = 64,800 g/mol
Colour 0,4 Gardner units

Application Examples**Example 2: Testing of soil release effect of the random copolymers of the invention in liquid detergents**

[0071]

Washing machine: Miele W 918 Novotronic®

EP 3 074 438 B1

(continued)

Washing temperature: 20 °C
 Liquor volume: 17 l
 Water hardness: 16°dH (German hardness degree)
 Ballast textiles: Clean laundry (Pillow, tricot, dish towels); 3,5 kg including the test tex tiles

[0072] The laundry including the cotton and polyester test textiles was washed three times with a wash liquor comprising 75 ml of either detergent E1 or V1 (see composition in Table 2) according to the conditions given above. After the washing process, the laundry was air-dried.

Table 2: Detergent composition [weight %]:

	V1	E1
C12-14-fatty alcohol with 7 EO	7	7
C12-18-fatty acid, Na-salt	10	10
Boric acid	4	4
Citric acid	2	2
Propanediol	6	6
NaOH	3	3
Protease	0.6	0.6
Amylase	0.1	0.1
Random copolymer of Examples 1 to 8 or comparative copolymer	-	1.5
H ₂ O	ad 100	

[0073] Subsequently, the test textiles were soiled with standardized fat/pigments (A: Make-up; B: Lipstick; C: sebum) and the stained textiles were kept for 7 days at room temperature. The test textiles, together with the ballast textiles, were then washed with the wash liquors comprising the same detergent V1 or E1 (again in an amount of 75 ml) under the conditions given above. The CIE brightness Y of the test textiles was measured with a DATA-COLOR Spectra Flash SF500 remission spectrometer.

[0074] In Table 3 the performance results are shown (mean value of lightness Y of 6 washing procedures). A significant increase in Y of the stained test textiles was observed when using wash liquors comprising detergents with the random copolymers of the invention (E1). Thus, detergents comprising random copolymers of the invention (E1) have a significantly increased washing performance as compared to a detergent without such polymer (V1) or the comparative random copolymer as can be derived from Table 3.

Table 3: Performance results of liquid detergent

Detergent	MPEG xxxxMA	Mole% MPEGMA	Mole% DMAEMA-MeCl	Make-up on cotton	Lipstick on cotton	Sebum on cotton	Lipstick on polyester
V1 w/o polymer	-	-	-	40.0	39.4	39.5	41.2
E1 + comparative polymer 1	2000	90	10	41,6	42,3	39,9	43,1
E1 + polymer 1	350	67	33	46.5	44.1	44.5	45.8
E1 + polymer 2	1000	38.5	61.5	47.2	43.6	44.5	44.9
E1 + polymer 3	2000	23.9	76.1	43.9	43.2	42.7	43.6
E1 + polymer 4	2000	16.1	83.9	44.1	43.9	42.9	44.7

(continued)

Detergent	MPEG xxxxMA	Mole% MPEGMA	Mole% DMAEMA-MeCl	Make-up on cotton	Lipstick on cotton	Sebum on cotton	Lipstick on polyester
E1 + polymer 5	1000	23.8	76.2	44.7	43.9	44.2	45.1
E1 + polymer 6	1000	23.8	76.2	46.2	45.2	43.6	43.9
E1 + polymer 7	350	62.5	37.5	47.1	43.5	45.6	45.2
E1 + polymer 8	2000	9.4	90.6	46.1	44.0	43.5	45.1

Example 3: Testing of soil release effect of the random copolymers of the invention in powder detergents

[0075] Example 9 was repeated by substituting the detergents V1 and E1, respectively, by the powder detergents V2 and E2 (see composition in Table 4), which were used in amounts of 75 g per wash liquor.

Table 4: Detergent composition [weight %]:

	V2	E2
C ₁₂₋₁₈ -fatty alcohol with 7 EO	2	2
C ₁₂₋₁₈ -fatty alcohol sulfate with 7 EO, sodium salt	1.5	1.5
Linear alkylbenzol sulfonate, sodium salt	10	10
Sodium carbonate	20	20
Sodium hydrogen carbonate	6.5	6.5
Sodium disilicate	4	4
Sodium percarbonate	17	17
TAED	4	4
Polyacrylates, sodium salt	3	3
carboxymethylcellulose	1	1
Sodium phosphoante	1	1
Sodium sulfate	25	25
Mix of enzymes	1	1
Random copolymer of Examples 1 to 8 and comparative copolymer	-	1.5

[0076] In Table 5 the performance results are shown (mean value of brightness Y of 6 washing procedures). A significant increase in Y of the stained test textiles was observed when using wash liquors comprising detergents with the random copolymers of the invention (E2). Thus, detergents comprising random copolymers of the invention (E2) have a significantly increased washing performance as compared to a detergent without such polymer (V2) or the comparative random copolymer as can be derived from Table 5.

Table 5: Performance results of powder detergent

Detergent	MPEG xxxxMA	Mole% MPEGMA	Mole% DMAEMA-MeCl	Make-up on cotton	Lipstick on cotton	Sebum on cotton	Lipstick on polyester
V2 w/o polymer	-	-	-	46.2	44.8	47.8	49.0
E2 + comparative polymer 1	2000	90	10	47,8	46,8	48,9	50,9


(continued)

Detergent	MPEG xxxxMA	Mole% MPEGMA	Mole% DMAEMA-MeCl	Make-up on cotton	Lipstick on cotton	Sebum on cotton	Lipstick on polyester
E2 + polymer 1	350	67	33	52.2	49.7	50.4	53.0
E2+ polymer 2	1000	38.5	61.5	51.9	49.4	51.2	53.4
E2 + polymer 3	2000	23.9	76.1	50.7	48.4	50.1	51.4
E2 + polymer 4	2000	16.1	83.9	50.9	49.2	50.7	51.5
E2 + polymer 5	1000	23.8	76.2	53.4	50.2	50.9	53.8
E2 + polymer 6	1000	23.8	76.2	54.6	51.4	51.2	53.8
E2 + polymer 7	350	62.5	37.5	52.9	50.5	50.4	54.1
E2 + polymer 8	2000	9.4	90.6	51.4	49.9	49.6	52.8

Claims

1. A random copolymer obtainable by polymerization of

(i) at least one monomer according to formula (I):




(I)

in an amount of 1 to 70 mol%,

wherein n is ≥ 3

and

(ii) at least one monomer according to formula (II):



(II)

in an amount of 30 to 99 mol%.

2. The random copolymer according to claim 1, wherein n of the monomer according to formula (I) is between 5 and 50.

3. The random copolymer according to any one of claim 1 or 2, wherein n of the monomer according to formula (I) is selected from the group consisting of 7, 23 and 46.

4. The random copolymer according to any one of claims 1 to 3, wherein the monomer according to formula (I) is present in the amount of 5 to 70 mol% and the monomer according to formula (II) is present in the amount of 30 to 95 mol%.

5. Use of a random copolymer as defined in any one of claims 1 to 4 as soil release agent in aqueous laundry processes.
6. Detergent comprising a random copolymer as defined in any one of claims 1 to 5.

5


Patentansprüche

1. Statistisch aufgebautes Copolymer, erhältlich durch Polymerisation von

10

(i) mindestens einem Monomer gemäß Formel (I):

15




(I)

20

in einer Menge von 1 bis 70 Mol-%,
wobei $n \geq 3$ ist,
und

(ii) mindestens einem Monomer gemäß Formel (II):

25



(II)

30

in einer Menge von 30 bis 99 Mol-%.

35

2. Statistisch aufgebautes Copolymer nach Anspruch 1, wobei n des Monomers gemäß Formel (I) zwischen 5 und 50 liegt.
3. Statistisch aufgebautes Copolymer nach Anspruch 1 oder 2, wobei n des Monomers gemäß Formel (I) aus der Gruppe bestehend aus 7, 23 und 46 ausgewählt ist.
4. Statistisch aufgebautes Copolymer nach einem der Ansprüche 1 bis 3, wobei das Monomer gemäß Formel (I) in der Menge von 5 bis 70 Mol-% vorliegt und das Monomer gemäß Formel (II) in der Menge von 30 bis 95 Mol-% vorliegt.
5. Verwendung eines statistisch aufgebauten Copolymers gemäß einem der Ansprüche 1 bis 4 als Soil-Release-Mittel bei wässrigen Waschprozessen.
6. Waschmittel, umfassend ein statistisch aufgebautes Copolymer gemäß einem der Ansprüche 1 bis 5.

50


Revendications

1. Copolymère statistique, pouvant être obtenu par la polymérisation

55

(i) d'au moins un monomère répondant à la formule (I)

EP 3 074 438 B1




selon une quantité allant de 1 à 70% molaire,

où $n \geq 3$

et

(ii) d'au moins un monomère répondant à la formule (II)



selon une quantité allant de 30 à 99% molaire.

- 20
2. Copolymère statistique selon la revendication 1, dans lequel n du monomère répondant à la formule (I) est compris entre 5 et 50.

25

 - 3. Copolymère statistique selon l'une quelconque des revendications 1 ou 2, dans lequel n du monomère répondant à la formule (I) est choisi dans le groupe constitué par 7, 23 et 46.
 - 4. Copolymère statistique selon l'une quelconque des revendications 1 à 3, dans lequel le monomère répondant à la formule (I) est présent selon une quantité allant de 5 à 70% molaire, et le monomère répondant à la formule (II) est présent selon une quantité allant de 30 à 95% molaire.

30

 - 5. Utilisation d'un copolymère statistique tel que défini selon l'une quelconque des revendications 1 à 4, comme agent anti-salissures dans des procédés aqueux de blanchisserie.

35

 - 6. Détergent comprenant un copolymère statistique tel que défini selon l'une quelconque des revendications 1 à 5.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- EP 0955791 A1 [0004]
- WO 2004055075 A1 [0005]
- US 4170582 A [0011]
- US 20090234062 A [0011]
- US 7687554 B [0011]
- EP 1194514 A [0040]
- EP 1383857 A [0040]
- WO 04007657 A [0040]
- US 2001044401 A [0040]
- EP 0458397 A [0040]
- WO 9606154 A [0040]
- EP 1038946 A [0040]
- EP 0900264 A [0040]
- EP 0909809 A [0040]
- EP 1001009 A [0040]
- WO 9965905 A [0040]
- WO 0248301 A [0040]
- WO 0060045 A [0040]
- WO 02077145 A [0040]
- WO 0185717 A [0040]
- WO 0164826 A [0040]
- EP 0923635 A [0040]
- DE 19639603 [0040]
- DE 102007017654 [0040]
- DE 102007017657 [0040]
- DE 102007017656 [0040]
- US 20030060388 A [0040]
- EP 0918840 B1 [0040]
- EP 1174491 A2 [0040]
- EP 0805794 B1 [0040]
- WO 9707192 A1 [0040]
- US 6235695 B1 [0040]
- EP 0912690 B1 [0040]
- EP 832969 B1 [0040]
- US 6479450 B1 [0040]
- WO 9933947 A1 [0040]
- WO 0032731 A1 [0040]
- WO 03054128 A1 [0040]
- DE 102004003710 [0040]
- EP 1083730 A [0040]
- EP 1148117 A [0040]
- EP 1445305 A [0040]
- US 6476996 B [0040]
- EP 0877078 A [0040]
- EP 0869171 A [0040]
- EP 0783035 A [0040]
- EP 0761809 A [0040]
- EP 1520910 A [0040]
- US 6242405 B [0045]
- WO 0202865 A [0047]
- WO 0405688 A [0047]

Non-patent literature cited in the description


- **E. SMULDERS.** Laundry Detergents. Wiley-VCH Verlag GmbH, 2002, 88 [0003]

Random kopolimerek mosási eljárásban szennyezés eltávolító szerként

Szabadalmi igénypontok

1. Egy random kopolimer, mely

(i) 1-70 mol% legalább egy (I):




(I)

képletű monomer, ahol $n \geq 3$

és

(ii) 30-99 mol% legalább egy (II):



(II)

képletű monomer polimerizációjával állítható elő.

2. Az 1. igénypont szerinti random kopolimer, ahol az (I) képletű monomerben n értéke 5 és 50 közötti.

3. Az 1. igénypont szerinti random kopolimer, ahol az (I) képletű monomerben n értéke 7, 23 és 46 közül választott.

4. Az 1-3. igénypontok bármelyike szerinti random kopolimer, ahol az (I) képletű monomer 5-70 mol% mennyiségben van jelen, és a (II) képletű monomer 30-95 mol% mennyiségben van jelen.

5. Az 1-4. igénypontok bármelyike szerinti random kopolimer alkalmazása vizes mosási eljárásban szennyezés eltávolító szerként.

6. Mosószer, mely egy 1-5. igénypontok bármelyike szerinti random kopolimert tartalmaz.