



(22) Date de dépôt/Filing Date: 2012/04/02

(41) Mise à la disp. pub./Open to Public Insp.: 2012/10/29

(45) Date de délivrance/Issue Date: 2018/09/04

(30) Priorité/Priority: 2011/04/29 (US13/097,810)

(51) Cl.Int./Int.Cl. *E04D 1/26* (2006.01),
E04D 1/20 (2006.01), *E04D 5/00* (2006.01)


(72) Inventeurs/Inventors:
BELT, JAMES S., US;
ELLIOTT, BERT W., US

(73) Propriétaire/Owner:
OWENS CORNING INTELLECTUAL CAPITAL, LLC, US

(74) Agent: SMART & BIGGAR

(54) Titre : BARDEAU RENFORCE D'UNE ZONE DE CLOUS ET METHODE DE FABRICATION

(54) Title: SHINGLE WITH REINFORCED NAIL ZONE AND METHOD OF MANUFACTURING



(57) Abrégé/Abstract:

A roofing shingle is provided. The roofing shingles includes an overlay sheet including a headlap portion and a tab portion and an underlay sheet secured to the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet. A reinforcement material is secured to the headlap portion of the overlay sheet. The reinforcement material is configured to improve nail pull-through. The reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet a distance of about 0.12 inches or less.

ABSTRACT

A roofing shingle is provided. The roofing shingles includes an overlay sheet including a headlap portion and a tab portion and an underlay sheet secured to the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet. A reinforcement material is secured to the headlap portion of the overlay sheet. The reinforcement material is configured to improve nail pull-through. The reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet a distance of about 0.12 inches or less.

SHINGLE WITH REINFORCED NAIL ZONE AND METHOD OF MANUFACTURING

Inventor: James S. Belt and Bert W. Elliott

RELATED APPLICATIONS

[0001]

TECHNICAL FIELD

[0002] This invention relates to a shingle, such as a roofing shingle, and in particular, to a roofing shingle having an improved nail zone.

BACKGROUND OF THE INVENTION

[0003] Asphalt-based roofing materials, such as roofing shingles, roll roofing and commercial roofing, are installed on the roofs of buildings to provide protection from the elements, and to give the roof an aesthetically pleasing look. Typically, the roofing material is constructed of a substrate such as a glass fiber mat or an organic felt, an asphalt coating on the substrate, and a surface layer of granules embedded in the asphalt coating.

[0004] A common method for the manufacture of asphalt shingles is the production of a continuous sheet of asphalt material followed by a shingle cutting operation, which cuts the material into individual shingles. In the production of asphalt sheet material, either a glass fiber mat or an organic felt mat is passed through a coater containing hot liquid asphalt to form a tacky, asphalt coated sheet. Subsequently, the hot asphalt coated sheet is passed beneath one or more granule applicators, which discharge protective and decorative surface granules onto portions of the asphalt sheet material.

[0005] In certain types of shingles, it is especially desired that the shingles define a sufficiently wide area, often known in the industry as the "nail zone," in order to make installation of roofs using shingles, such as laminated shingles, more efficient and secure. One or more lines or other indicia painted or otherwise marked longitudinally on the surface of the shingle may define such a nail zone. It is especially desired that the shingles define a nail zone that allows the installers to have some latitude in the nail placement.

[0006] Additionally, the leading edge of some shingles may experience lift off in high wind situations. Therefore, there is also a need for shingles where the shingles have a sufficiently high nail pull-through value so that the installed shingles have improved performance in high wind situations.

SUMMARY OF THE INVENTION

[0007] One or more of the above objects as well as other objects not specifically enumerated can be achieved by a roofing shingle. In an embodiment, the roofing shingle includes an overlay sheet including a headlap portion and a tab portion and an underlay sheet secured to the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet. The overlay sheet has a non-uniform thickness. A reinforcement material is secured to the headlap portion of the overlay sheet. The reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet. The reinforcement material comprises a material and thickness that together with the headlap portion provide a nail pull-through value that is at least 13.3 percent greater than an otherwise identical shingle having no such reinforcement material. The reinforcement material is secured to a top surface of the headlap portion and extends beyond the overlapping regions of the headlap

portion and the underlay sheet a maximum distance of about 0.12 inches.

[0008] According to another embodiment, there is also provided a roofing shingle including an overlay sheet having a headlap portion and a tab portion. The overlay sheet has an overlay sheet height. An underlay sheet is secured to a bottom surface of the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet. The underlay sheet has a height equal to half of the overlay sheet height $\pm \frac{1}{8}$ inch. The overlay sheet has a non-uniform thickness. A reinforcement material is secured to a top surface of the headlap portion of the overlay sheet. The reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet. The reinforcement material comprises a material and thickness that together with the headlap portion provide a nail pull-through value that is greater than an otherwise identical shingle having no such reinforcement material. The reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet a maximum distance of about 0.12 inches.

[0009] According to a further embodiment, there is also provided a roofing shingle including an overlay sheet including a headlap portion and a tab portion and an underlay sheet secured to a bottom surface of the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet. The overlay sheet has a non-uniform thickness. A reinforcement material is secured to a top surface of the headlap portion. The reinforcement material comprises a material and thickness that together with the headlap portion provide a nail pull-through value that is greater than an otherwise identical shingle having no such reinforcement material. The reinforcement material has a height. The overlapping regions of the underlay sheet and the headlap portion of the overlay sheet have a height. The ratio of the height of the overlapping

regions to the height of the reinforcement material is in a range of from about 70% to about 100%.

[0010] According to another embodiment, there is also provided a roofing shingle having an overlay sheet including a mat and an asphalt coating applied to the mat, and defining a headlap portion and a tab portion; an underlay sheet including a mat and an asphalt coating applied to the mat, the underlay sheet being secured to the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet; and a woven reinforcement material secured directly to the asphalt coating on a rear surface of the headlap portion of the overlay sheet without extending into the tab portion. The woven reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay. The woven reinforcement material comprises a material and thickness together with the headlap portion provide a nail pull-through value that is greater than an otherwise identical shingle having no such reinforcement material. The shingle further includes a plurality of granules secured to the headlap portion of the overlay sheet and not secured to the woven reinforcement material. The woven reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet a maximum distance of about 0.12 inches.

[0010a] According to a further embodiment, there is also provided a roofing shingle having an overlay sheet including a mat and an asphalt coating applied to the mat, and defining a headlap portion and a tab portion; an underlay sheet including a mat and an asphalt coating applied to the mat, the underlay sheet being secured to the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet; and a woven reinforcement material secured directly to the asphalt coating on a rear surface of the headlap portion of the overlay sheet without extending into the tab portion.

The woven reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay. The woven reinforcement material comprises a material and thickness that together with the headlap portion provide a nail pull-through value that is within a range of from about 10 percent to about 100 percent greater than an otherwise identical shingle having no such reinforcement material. The woven reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet a maximum distance of about 0.12 inches.

[0010b] According to another embodiment, there is also provided a roofing shingle having an overlay sheet including a mat and an asphalt coating applied to the mat, and defining a headlap portion and a tab portion; an underlay sheet including a mat and an asphalt coating applied to the mat, the underlay sheet being secured to the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet; and a woven reinforcement material secured directly to the asphalt coating on a rear surface of the headlap portion of the overlay sheet without extending into the tab portion. The woven reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay. The woven reinforcement material comprises a material and thickness that together with the headlap portion provide a nail pull-through value that is greater than an otherwise identical shingle having no such reinforcement material. The tab portion of the overlay sheet includes a cutout having an upper edge spaced apart from a lower edge of the woven reinforcement material by a distance within a range of from about $\frac{1}{4}$ inch to about $\frac{3}{4}$ inch, and spaced apart from an upper edge of the woven reinforcement material by a distance within a range of from about $1\frac{3}{4}$ inches to about $2\frac{1}{4}$ inches. The woven reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet a maximum distance of about 0.12 inches.

[0010c] According to a further embodiment, there is also provided a roofing shingle having an overlay sheet including a mat and an asphalt coating applied to the mat, and defining an upper headlap portion and a lower tab portion; an underlay sheet including a mat and an asphalt coating applied to the mat, the underlay sheet being secured to the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet; and a reinforcement material secured directly to the asphalt coating of the headlap portion of the overlay sheet without extending into the tab portion to provide a reinforced nail zone along shingle longitudinal axis of the shingle. The reinforcement material comprises a material and thickness that together with the headlap portion provides a nail pull-through value that is greater than an otherwise identical shingle having no such reinforcement material. The shingle further includes a granular material secured to the headlap portion of the overlay sheet, with no granular material adhered to the reinforcement material. The reinforcement material has a thinner cross-section than the granular material, such that the reinforcement material forms a depression in an exterior surface of the headlap portion that extends along said longitudinal axis. At least about 70% of the reinforcement material is disposed on a dual-layer portion of the shingle.

[0010d] According to another embodiment, there is also provided a roofing shingle having an overlay sheet including a mat and an asphalt coating applied to the mat, and defining a headlap portion and a tab portion; an underlay sheet including a mat and an asphalt coating applied to the mat, the underlay sheet being secured to the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet; and a reinforcement material secured directly to the asphalt coating on the headlap portion of the overlay sheet without extending into the tab portion to provide a reinforced nail zone along a longitudinal axis of the shingle, wherein the reinforcement material

comprises a material and thickness that together with the headlap portion provide a nail pull-through value that is greater than an otherwise identical shingle having no such reinforcement material. The reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay, such that a first portion of the reinforcement material is disposed on a dual-layer portion of the shingle and a second portion of the reinforcement material is disposed on a single-layer portion of the shingle. At least about 70% of the reinforcement material is disposed on a dual-layer portion of the shingle.

[0011] Various objects and advantages of this invention will become apparent to those skilled in the art from the following detailed description of the various embodiments, when read in light of the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0012] Fig. 1 is a schematic elevational view of an apparatus for making shingles according to the invention.

[0013] Fig. 2 is a perspective view of a laminated shingle having a reinforcement member in accordance with this invention.

[0014] Fig. 3 is a schematic sectional view of a pair of laminated roofing shingles of the prior art stacked together, shown in exaggerated thickness to illustrate humping of the stacked shingles.

[0015] Fig. 4 is a schematic sectional view of a pair of laminated roofing shingles according to the invention stacked together, shown in exaggerated thickness to illustrate how the reinforcement members of adjacent shingles cooperate to reduce humping of the stacked shingles.

[0016] Fig. 5 is a cross-sectional view, in elevation, of a second embodiment of a laminated shingle having reinforcement material.

DETAILED DESCRIPTION OF THE INVENTION

Referring now to the drawings, there is shown in Fig. 1 an apparatus 10 for manufacturing an asphalt-based roofing material according to the invention. In the illustrated embodiment, the manufacturing process involves passing a continuous sheet 12 in a machine direction (indicated by the arrows)

through a series of manufacturing operations. The sheet usually moves at a speed of at least about 200 feet/minute (61 meters/minute), and typically at a speed within the range of between about 450 feet/minute (137 meters/minute) and about 800 feet/minute (244 meters/minute). The sheet, however, may move at any desired speed.

[0018] In a first step of the illustrated manufacturing process, a continuous sheet of substrate or shingle mat 12 is payed out from a roll 14. The substrate can be any type known for use in reinforcing asphalt-based roofing materials, such as a non-woven web of glass fibers. The shingle mat 12 may be fed through a coater 16 where an asphalt coating is applied to the mat 12. The asphalt coating can be applied in any suitable manner. In the illustrated embodiment, the mat 12 contacts a roller 17, that is in contact with a supply of hot, melted asphalt. The roller 17 completely covers the mat 12 with a tacky coating of hot, melted asphalt to define a first asphalt coated sheet 18. In other embodiments, however, the asphalt coating could be sprayed on, rolled on, or applied to the sheet by other means. Typically, the asphalt material is highly filled with a ground stone filler material, amounting to at least about 60 percent by weight of the asphalt/filler combination.

[0019] A continuous strip of a reinforcement material or tape 19, as will be described in detail herein, may then be payed out from a roll 20. The reinforcement tape 19 adheres to the first asphalt coated sheet 18 to define a second asphalt coated sheet 22. In one embodiment, the reinforcement tape 19 is attached to the sheet 18 by the adhesive mixture of the asphalt in the first asphalt coated sheet 18. The reinforcement tape 19, however, may be attached to the sheet 18 by any suitable means, such as other adhesives. In one embodiment, the tape 19 is formed from polyester. In another embodiment, the tape 19 is formed

from polyolefin, such as polypropylene or polyethylene. The tape 19, however, can be formed from any material for reinforcing and strengthening the nail zone of a shingle, such as, for example, paper, film, scrim material, and woven or non-woven glass.

[0020] The resulting second asphalt coated sheet 22 may then be passed beneath a series of granule dispensers 24 for the application of granules to the upper surface of the second asphalt coated sheet 22. The granule dispensers can be of any type suitable for depositing granules onto the asphalt coated sheet. A granule dispenser that can be used is a granule valve of the type disclosed in U.S. Patent No. 6,610,147 to Aschenbeck. The initial granule blender 26 may deposit partial blend drops of background granules of a first color blend on the tab portion of the second asphalt coated sheet 22 in a pattern that sets or establishes the trailing edge of subsequent blend drops of a second color blend (of an accent color) and a third color blend (of a different accent color). For purposes of this patent application, the first color blend and the background granules are synonymous. The use of initially applied partial blend drops to define the trailing edge of subsequent blend drops is useful where accurate or sharp leading edges are possible, but accurate trailing edges at high shingle manufacturing speeds are difficult.

[0021] As is well known in the art, blend drops applied to the asphalt coated sheet are often made up of granules of several different colors. For example, one particular blend drop that is supposed to simulate a weathered wood appearance might actually consist of some brown granules, some dark gray granules, and some light gray granules. When these granules are mixed together and applied to the sheet in a generally uniformly mixed manner, the overall appearance of weathered wood is achieved. For this reason, the blend drops are referred to as

having a color blend, which gives an overall color appearance. This overall appearance may be different from any of the actual colors of the granules in the color blend. Also, blend drops of darker and lighter shades of the same color, such as, for example, dark gray and light gray, are referred to as different color blends rather than merely different shades of one color.

[0022] As shown in Fig. 1, the series of dispensers 24 includes four color blend blenders 26, 28, 30, and 32. Any desired number of blenders, however, can be used. The final blender may be the background blender 34. Each of the blenders may be supplied with granules from sources of granules, not shown. After the blend drops are deposited on the second asphalt coated sheet 22, the remaining, uncovered areas are still tacky with warm, uncovered asphalt, and the background granules from the background blender 34 will adhere to the areas that are not already covered with blend drop granules. After all the granules are deposited on the second asphalt coated sheet 22 by the series of dispensers 24, the sheet 22 becomes a granule covered sheet 40.

[0023] In one embodiment, the reinforcement tape 19 includes an upper surface to which granules substantially will not adhere. The reinforcement tape 19, however, may include an upper surface to which granules will adhere. For example, the apparatus 10 may include any desired means for depositing granules onto substantially the entire second asphalt coated sheet 22, except for the portion of the second asphalt coated sheet 22 covered by the tape 19, as best shown in Fig. 2. Alternately, granules may be deposited onto substantially the entire second asphalt coated sheet 22, including the tape 19, but wherein the reinforcement tape 19 includes an upper surface to which granules substantially will not adhere.

[0024] The granule covered sheet 40 may then be turned around a slate drum 44 to press the granules into the asphalt coating and to temporarily invert the sheet so that the excess granules will fall off and will be recovered and reused. Typically, the granules applied by the background blender 34 are made up by collecting the backfall granules falling from the slate drum 44.

[0025] The granule covered sheet 40 may subsequently be fed through a rotary pattern cutter 52, which includes a bladed cutting cylinder 54 and a backup roll 56, as shown in Fig. 1. If desired, the pattern cutter 52 can cut a series of cutouts in the tab portion of the granule covered sheet 40, and cut a series of notches in the underlay portion of the granule covered sheet 40.

[0026] The pattern cutter 52 may also cut the granule covered sheet 40 into a continuous underlay sheet 66 and a continuous overlay sheet 68. The underlay sheet 66 may be directed to be aligned beneath the overlay sheet 68, and the two sheets may be laminated together to form a continuous laminated sheet 70. As shown in Fig. 1, the continuous underlay sheet 66 may be routed on a longer path than the path of the continuous overlay sheet 68. Further downstream, the continuous laminated sheet 70 may be passed into contact with a rotary length cutter 72 that cuts the laminated sheet into individual laminated shingles 74.

[0027] In order to facilitate synchronization of the cutting and laminating steps, various sensors and controls may be employed. For example, sensors, such as photo eyes 86 and 88 can be used to synchronize the continuous underlay sheet 66 with the continuous overlay sheet 68. Sensors 90 can also be used to synchronize the notches and cutouts of the continuous laminated sheet with the end cutter or length cutter 72.

[0028] In one embodiment, the reinforcement tape may be attached to the shingle mat 12 prior to the application of the asphalt coating, as shown at 19A in

Fig. 1. The tape 19A may be attached to the shingle mat 12 by any suitable means, such as hot, melted asphalt, or other adhesives.

[0029] In another embodiment, the reinforcement tape may be attached to the granule covered sheet 40, as shown at 19B in Fig. 1. The tape 19B may be attached to the granule covered sheet 40 by any suitable means, such as hot, melted asphalt, or other adhesives.

[0030] In another embodiment, the reinforcement tape may be attached to a lower surface (downwardly facing as viewed in Fig. 1) of the mat 12, the first asphalt coated sheet 18, the second asphalt coated sheet 22, or the granule covered sheet 40, as shown at 19C and 19D in Fig. 1. The tape 19C may be attached to the mat 12, the first asphalt coated sheet 18, the second asphalt coated sheet 22, or the granule covered sheet 40 by any suitable means, such as hot, melted asphalt, other adhesives, or suitable fasteners. In such an embodiment, the reinforcement tape 19C and 19D may be attached to the lower surface of the nail zone of either of the overlay sheet 68 or the underlay sheet 66, thereby reinforcing and strengthening the nail zone as described herein.

[0031] It will be understood, however, that in any of the embodiments described herein, reinforcement material may be applied as an extruded or liquid material, such as a polymer, that will adhere to the mat 12, the first sheet 18, the second sheet 22, the granule covered sheet 40, or the lower surface of the underlay sheet 66 or the overlay sheet 68. Additionally, the reinforcement material may be applied to the laminated roofing shingle 74, as described below.

[0032] Referring now to Fig. 2, a laminated roofing shingle is shown generally at 74. In the illustrated embodiment, the shingle 74 includes the overlay sheet 68 attached to the underlay sheet 66 and has a first end 74A and a second end 74B. The shingle 74 also includes a longitudinal axis A. The overlay

sheet 68 may include a headlap portion 76 and a tab portion 78. The headlap portion 76 may include a lower zone 76A and an upper zone 76B. The tab portion 78 defines a plurality of tabs 80 and cutouts 82 between adjacent tabs 80. In the illustrated embodiment, the tab portion 78 includes four tabs 80, although any suitable number of tabs 80 may be provided. The headlap portion 76 and the tabs 80 may include one or more granule patterns thereon. Each cutout 82 has a first height H1. In the illustrated embodiment, the cutouts 82 are shown as having the same height H1. It will be understood however, that each cutout 82 may be of different heights. A line B is collinear with an upper edge 82A of the cutouts 82 and defines an upper limit of an exposed region 84 of the underlay sheet 66. In the illustrated embodiment, the height of the exposed region 84 is equal to the first height H1, although the height of the exposed region 84 may be any desired height. In a shingle wherein the cutouts 82 have different heights, the line B may be collinear with an upper edge 82A of the cutout 82 having the largest height. In the illustrated embodiment, the overlay sheet 68 has a second height H2.

[0033] The reinforcement tape 19 may be disposed longitudinally on the headlap portion 76. In the illustrated embodiment, the tape 19 extends longitudinally from the first end 74A to the second end 74B of the shingle 74 within the lower zone 76A of the headlap portion 76. A lower edge 19A of the tape 19 may be spaced apart from the line B by a distance D1, and an upper edge 19B of the tape 19 may be spaced apart from the line B by a distance D2. In one embodiment, the distance D1 is within the range of from about $\frac{1}{4}$ inch to about $\frac{3}{4}$ inch. In another embodiment, the distance D1 is about $\frac{1}{2}$ inch. In one embodiment, the distance D2 is within the range of from about $1\frac{3}{4}$ inches to about $2\frac{1}{4}$ inches. In another embodiment, the distance D2 is about 2 inches.

The distances D1 and D2 may, however, be of any other desired length. For example, if desired, the tape 19 may substantially cover the entire headlap portion 76 of the overlay sheet 68. It will be further understood, however, that one or more additional lengths of tape may be disposed longitudinally on the headlap portion 76, such as shown by the phantom line 19' in Fig. 2. It will be understood that the reinforcement material need not extend from the first end 74A to the second end 74B of the shingle 74, and may be disposed in one or more sections or portions on the shingle 74.

[0034] The tape 19 defines a nail zone 98 and may include text such as "nail here •", as shown in Fig. 2. It will be understood, however, that any other text or other indicia may be included on the tape 19. It will also be understood that the tape 19 can be provided without such text or indicia. Such indicia on the tape 19 ensure that the nail zone 98 may be easily and quickly identified by the shingle installer.

[0035] In the embodiment illustrated in Fig. 2, the underlay sheet 66 includes a leading edge 66A and a trailing edge 66B and has a third height H3. In the illustrated embodiment, the trailing edge 66B of the underlay sheet 66 is spaced apart from the line B by a distance D3. As shown, the distance D3 is about 3/8 inch, however, the distance D3 may be any desired distance.

[0036] In the illustrated embodiment, the third height H3 of the underlay sheet 66 is less than one-half the second height H2 of the overlay sheet 68. The overlay sheet 68 and the underlay sheet 66 thereby define a two-layer portion of the laminated shingle 74 and a single-layer portion of the laminated shingle 74, wherein at least a portion of the tape 19 is adhered to the single-layer portion of the laminated shingle 74. Alternately, the third height H3 of the underlay sheet 66 may be equal to one-half the second height H2 of the overlay sheet 68, or

greater than one-half of the second height H2 of the overlay sheet 68. Such a relationship between the underlay sheet 66 and the overlay sheet 68 allows the tape 19 to be positioned such that a reinforced nail zone is provided at a substantially single-layer portion of the shingle 74.

[0037] In another embodiment of the invention, a layer of material, such as talc or sand, may be applied to the first asphalt coated sheet 18 shown in Fig. 1. The material may be applied by any desired means to an upper surface of the first asphalt coated sheet 18. In one embodiment, the material may be applied to the portion of the first asphalt coated sheet 18 that will become the portion of the overlay sheet 66 shown covered by the tape 19 in Fig. 2. Such a material may reduce tackiness of the portions of the second asphalt coated sheet 22 to which the material has been applied, and thereby provide a surface to which granules substantially will not adhere.

[0038] In the exemplary shingle 74 illustrated in Fig. 2, the shingle 74 may have a nail pull-through value, measured in accordance with a desired standard, such as prescribed by ASTM test standard D3462. For example, the shingle 74 may have a nail pull-through value that is greater than in an otherwise identical shingle having no such tape 19. In one embodiment, the shingle 74 may have a nail pull-through value within the range of from about ten percent to about 100 percent greater than in an otherwise identical shingle having no such tape 19. In another embodiment, the shingle 74 may have a nail pull-through value about 50 percent greater than in an otherwise identical shingle having no such tape 19.

[0039] In another embodiment, a shingle having a reinforcement tape 19 formed from polyester film having a thickness of about 0.5 mils, may have a nail pull-through value about 13.3 percent greater than in an otherwise identical shingle having no such tape 19.

[0040] In another embodiment, a shingle having a reinforcement tape 19 formed from polyester film having a thickness of about 3.0 mils, may have a nail pull-through value about 62.3 percent greater than in an otherwise identical shingle having no such tape 19.

[0041] In another embodiment, a shingle having a reinforcement tape 19 formed from polyester film having a thickness of about 4.0 mils, may have a nail pull-through value about 86.0 percent greater than in an otherwise identical shingle having no such tape 19.

[0042] In another embodiment, a shingle having a reinforcement tape 19 formed from polyester film having a thickness of about 5.0 mils, may have a nail pull-through value about 112.7 percent greater than in an otherwise identical shingle having no such tape 19.

[0043] Because there may be substantially no granules in the portion of the overlay sheet 68 covered by the tape 19, the weight of the shingle 74 may be reduced relative to an otherwise identical shingle having no such tape 19. For example, the weight of the exemplary shingle 74 illustrated in Fig. 2, may be reduced within the range of from about four percent to about six percent relative to the weight of an otherwise identical shingle having no such tape 19. The material and transportation cost may also be reduced.

[0044] Although the invention has been disclosed in the context of a laminated shingle 74, it will be understood that the reinforcement tape 19 may be attached to any other type of shingle, such as a single layer shingle.

[0045] As shown in Fig. 3, laminated roofing shingles 100 of the prior art are stacked in a bundle 102. Only a pair of such shingles 100 are illustrated in Fig. 3, with every other shingle 100 inverted and turned 180 degrees. It will be understood, however, that the shingles 100 may be stacked such that every other

of such shingles 100 are either inverted or turned 180 degrees, or both. This stacking method minimizes uneven build in the bundle 102 caused by the difference in thickness between the area of the shingle 100 that includes the underlay sheet 106 and the area that does not include the underlay sheet 106. A problem may occur, however, along a central area 108 of the bundle 102 because central areas 110 of the shingles 100 are double-layered, whereas the cutout portions 112 of the shingles 100 adjacent the central areas 110 are single-layered. The difference in thickness causes a ridge or hump 114 along the central area 108 of the bundle 102 that becomes progressively higher as the number of shingles 100 in the bundle 102 increases.

[0046] Fig. 4 is a schematic sectional view of a representative pair of stacked shingles 74 manufactured according to the present invention. As shown in Fig. 4, the laminated roofing shingles 74 are stacked such that every other of the shingles 74 is inverted and turned 180 degrees relative to an adjacent one of the shingles 74 to define a bundle 99. It will be understood, however, that the shingles 74 may be stacked such that every other of such shingles 74 are either inverted or turned 180 degrees, or both. The bundle 99 includes a central area 92. In the illustrated embodiment, the central area 92 includes the lower zones 76A and reinforcement tape 19 of each shingle 74, and includes the portion of each laminated roofing shingle 74 wherein the shingle 74 is double-layered. In contrast to the prior art shingles 100, when the laminated shingles 74 of the invention are stacked, the areas of the adjacent shingles 74 having no granules, such as the areas covered by the reinforcement tapes 19, cooperate to advantageously reduce humping in the central area 92 of the bundle of stacked shingles 74. As best shown in Fig. 4, the central area 92 of the bundle, as represented by the pair of shingles 74 illustrated, has a fourth height H4

substantially identical to a fifth height H5 of a remainder of the bundle outside of the central area 92.

[0047] Referring now to Fig. 5, a second embodiment of a laminated roofing shingle is shown generally at 174. In the illustrated embodiment, the shingle 174 includes an overlay sheet 168 attached to an underlay sheet 166. In the illustrated embodiment, the overlay sheet 168 and the underlay sheet 166 are the same as, or similar to, the overlay sheet 68 and the underlay sheet 66 described above and illustrated in Fig. 2. In other embodiments, the overlay sheet 168 and the underlay sheet 166 can be different from the overlay sheet 68 and the underlay sheet 66. The shingle 174 has a first end (not shown) and a second end (not shown). In the illustrated embodiment, the first and second ends of the shingle 174 are the same as, or similar to, the first end 74A and the second end 74B described above and illustrated in Fig. 2. In other embodiments, the first and second ends of the shingle 174 can be different from the first end 74A and the second end 74B. The shingle 174 also includes a longitudinal axis extending from the first end to the second end. In the illustrated embodiment, the longitudinal axis is the same as, or similar to, the longitudinal axis A described above and illustrated in Fig. 2. In other embodiments, the longitudinal axis of the shingle 174 can be different from the longitudinal axis A.

[0048] Referring again to Fig. 5, the overlay sheet 168 may include a headlap portion 176 and a tab portion 178. The headlap portion 176 may include a lower zone 176A and an upper zone 176B. The tab portion 178 defines a plurality of tabs 180 and cutouts (not shown) between adjacent tabs 180. Any suitable number of tabs 180 and cutouts may be provided. The headlap portion 176 may include any type of granule applied thereon, including headlap granules. The tabs 180 may include one or more granule patterns applied thereon. In the

illustrated embodiment, the shingle 174 can be formed in the same manner, or in a similar, manner to the manufacturing process described above and illustrated in Fig. 1. In other embodiments, the shingle 174 can be formed with other desired processes.

[0049] Referring again to Fig. 5, each cutout has a first height H101. It should be understood that the cutouts may be of the same first height H101 or different cutouts can have different first heights H101. The cutouts have an upper edge 182A that defines an upper limit of an exposed region (not shown) of the underlay sheet 166. In the illustrated embodiment, the height of the exposed region is equal to the first height H101, although the height of the exposed region may be any desired height. In a shingle wherein the cutouts have different heights, the upper edge 182A occurs with the cutout having the largest first height H101. In the illustrated embodiment, the overlay sheet 168 has a second height H102.

[0050] A reinforcement material 119 may be disposed longitudinally on the headlap portion 176. The reinforcement material 119 is configured to increase the pull-through of the nail zone in the same manner as the tape 19 described above and illustrated in Fig. 2. In the illustrated embodiment, the reinforcement material 119 is formed from woven fabric made from a polymeric material, such as the non-limiting example of polyethylene terephthalate (PET). In other embodiments, the reinforcement material 119 can be formed from other woven polymeric materials, such as for example, polyester, polyolefin or polypropylene. In still other embodiments, the reinforcement material 119 can be formed from any material configured to reinforce and strengthen the nail zone of a shingle, including the non-limiting example of paper, film, scrim material, and woven or non-woven glass.

[0051] In the illustrated embodiment, the reinforcement material 119 extends longitudinally from the first end to the second end of the shingle 174 within the lower zone 176A of the headlap portion 176. A lower edge 119A of the reinforcement material 119 may be spaced apart from the upper edge 182A of the cutouts by a first distance D101, and an upper edge 119B of the reinforcement material 119 may be spaced apart from the upper edge 182A of the cutouts by a second distance D102. In one embodiment, the first distance D101 is within the range of from about 0.06 inches to about 0.75 inches. In another embodiment, the first distance D101 is about 0.25 inches. In one embodiment, the second distance D102 is within the range of from about 1.06 inches to about 1.75 inches. In another embodiment, the second distance D102 is about 1.50 inches. The first and second distances, D101 and D102, may however, be of any other desired length. For example, if desired, the reinforcement material 119 may substantially cover the entire headlap portion 176 of the overlay sheet 168. It should be understood, however, that one or more additional lengths of reinforcement material may be disposed longitudinally on the headlap portion 176, such as shown in Fig. 2 by the phantom line 19'. In addition, the reinforcement material 119 need not extend from the first end to the second end of the shingle 174, and may be disposed in one or more sections or portions on the shingle 174.

[0052] The reinforcement material 119 defines a nail zone 198 and may include text or other indicia such as described above for the tape 19 as shown in Fig. 2.

[0053] In the embodiment illustrated in Fig. 5, the underlay sheet 166 includes a lower edge 166A and an upper edge 166B. The distance from the lower edge 166A to the upper edge 166B defines a third height H103. The upper edge 166B of the underlay sheet 166 is spaced apart from the upper edge 182A by a third

distance D103. In the illustrated embodiment, the third distance D103 is within the range of from about 1.06 inches to about 1.75 inches. In another embodiment, the third distance D103 is about 1.38 inches. However, the third distance D103 may be any desired distance.

[0054] Referring again to Fig. 5, the upper edge 166B of the underlay sheet 166 is spaced apart from the upper edge 119B of the reinforcement material 119 by a fourth distance D104. In the illustrated embodiment, the fourth distance D104 is within the range of from about 0.06 inches to about 0.50 inches. In another embodiment, the fourth distance D104 is about 0.12 inches. In still other embodiments, the fourth distance D104 can be zero. However, the fourth distance D104 may be any desired distance.

[0055] In the illustrated embodiment, the third height H103 of the underlay sheet 166 is approximately one-half of the second height H102 of the overlay sheet 168. The overlay sheet 168 and the underlay sheet 166 thereby define a two-layer portion of the laminated shingle 174 and a single-layer portion of the laminated shingle 174. Such a dimensional relationship between the underlay sheet 166 and the overlay sheet 168 allows the reinforcement material 119 to be positioned such that the nail zone 198 can extend near or over the single-layer portion of the shingle 74. The two-layer portion of the laminated shingle 174 that is covered by the reinforcement material 119 has a fourth height H104. In the illustrated embodiment, the fourth height H104 is in a range of from about 1.00 inches to about 1.75 inches. In other embodiments, the fourth height H104 can be other dimensions less than about 1.00 inches or more than about 1.75 inches.

[0056] Referring again to Fig. 5, the reinforcement material 119 has a fifth height H105. In the illustrated embodiment, the fifth height H105 is within the range of from about 1.06 inches to about 1.87 inches. In another embodiment,

the fifth height H105 is about 1.38 inches. However, the fifth height H105 may be any desired distance.

[0057] As discussed above, the relationship of the fourth height H104 and the fifth height H105 defines in part the extent to which the reinforcement material 119 extends beyond the two-layer portion of the shingle 174 and into the single layer portion of the shingle. In this regard, the term “coverage”, as used herein, is defined to mean the percentage of the reinforcement material 119 that covers the two-layer portion of the shingle 174. In other words, coverage is the ratio of the fourth height H104 to the fifth height H105. As one example, a fourth height H104 of 1.12 inches and a fifth height H105 of 1.25 inches provides a ratio of 90%, meaning the 90% of the reinforcement material 119 is positioned to cover the two-layer portion of the shingle 174. In the illustrated embodiment, the coverage of the reinforcement material 119 is in a range of from about 70% to about 100%. In other embodiments, the coverage can be in a range of from about 80% to about 95%. In still other embodiments, the coverage can be in a range of from about 85% to about 90%.

[0058] In the embodiment illustrated in Fig. 5, the shingle 174 may have a nail pull-through value that is the same as, or similar to, the nail pull-through value for the shingle 74 as described above and as shown in Fig. 2. Alternatively, the shingle 174 can have a nail pull-through value that is different from the nail pull-through value for the shingle 74.

[0059] In another embodiment, a shingle 174 having a reinforcement material 119 formed from woven polymeric materials having a thickness of about 0.5 mils, may have a nail pull-through value at least about 13 percent greater than in an otherwise identical shingle having no such reinforcement material 119.

[0060] In another embodiment, a shingle having a reinforcement material 119 formed from woven polymeric materials having a thickness of about 3.0 mils, may have a nail pull-through value about 62 percent greater than in an otherwise identical shingle having no such reinforcement material 119.

[0061] In another embodiment, a shingle having a reinforcement material 119 formed from woven polymeric materials having a thickness of about 4.0 mils, may have a nail pull-through value about 86 percent greater than in an otherwise identical shingle having no such reinforcement material 119.

[0062] In another embodiment, a shingle having a reinforcement material 119 formed from woven polymeric materials having a thickness of about 5.0 mils, may have a nail pull-through value about 112 percent greater than in an otherwise identical shingle having no such reinforcement material 119.

[0063] Because there may be substantially no granules in the portion of the overlay sheet 168 covered by the reinforcement material 119, the weight of the shingle 174 may be reduced relative to an otherwise identical shingle having no such reinforcement material 119. For example, the weight of the exemplary shingle 174 illustrated in Fig. 5, may be reduced within the range of from about four percent to about six percent relative to the weight of an otherwise identical shingle having no such reinforcement material 119. The material and transportation cost may also be reduced.

[0064] Although the invention has been disclosed in the context of a laminated shingle 174, it will be understood that the reinforcement material 119 may be attached to any other type of shingle, such as a single layer shingle.

[0065] The principle and mode of operation of this invention have been described in its various embodiments. However, it should be noted that this

invention may be practiced otherwise than as specifically illustrated and described without departing from its scope.

What is claimed is:

1. A roofing shingle comprising:

an overlay sheet including a headlap portion and a tab portion;

an underlay sheet secured to the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet;

wherein the overlay sheet has a non-uniform thickness; and

a reinforcement material secured to the headlap portion of the overlay sheet, wherein the reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet;

wherein the reinforcement material comprises a material and thickness that together with the headlap portion provide a nail pull-through value that is at least 13.3 percent greater than an otherwise identical shingle having no such reinforcement material; and

wherein the reinforcement material is secured to a top surface of the headlap portion and extends beyond the overlapping regions of the headlap portion and the underlay sheet a maximum distance of about 0.12 inches.

2. The roofing shingle of claim 1, wherein the underlay sheet has a uniform thickness.

3. The roofing shingle of claim 1, wherein the shingle provides an average nail pull-through value of at least 90 newtons when measured at a temperature of 23°C +/- 2°C.

4. The roofing shingle of claim 1, wherein the shingle provides an average nail pull-through value of at least 130 newtons when measured at a temperature of 23°C +/- 2°C.

5. The roofing shingle of claim 1, wherein the shingle provides an average nail pull-through value of at least 104 newtons when measured at a temperature of 23°C +/- 2°C.

6. The roofing shingle of claim 1, further including a plurality of granules secured to the headlap portion of the overlay sheet and not secured to the reinforcement material.

7. The roofing shingle of claim 1, wherein the reinforcement material is formed from a woven material.

8. The roofing shingle of claim 7, wherein the reinforcement material is formed from a polymeric material.

9. A roofing shingle comprising:

an overlay sheet including a headlap portion and a tab portion, wherein the overlay sheet has an overlay sheet height;

an underlay sheet secured to a bottom surface of the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet, wherein the underlay sheet has a height equal to half of the overlay sheet height $\pm \frac{1}{8}$ inch;

wherein the overlay sheet has a non-uniform thickness; and

a reinforcement material secured to a top surface of the headlap portion of the overlay sheet, wherein the reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet;

wherein the reinforcement material comprises a material and thickness that together with the headlap portion provide a nail pull-through value that is greater than an otherwise identical shingle having no such reinforcement material; and

wherein the reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet a maximum distance of about 0.12 inches.

10. A roofing shingle comprising:

an overlay sheet including a headlap portion and a tab portion;

an underlay sheet secured to a bottom surface of the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet;

wherein the overlay sheet has a non-uniform thickness; and

a reinforcement material secured to a top surface of the headlap portion, wherein the reinforcement material comprises a material and thickness that together with the headlap portion provide a nail pull-through value that is greater than an otherwise identical shingle having no such reinforcement material, wherein the reinforcement material has a height, wherein the overlapping regions of the underlay sheet and the headlap portion of the overlay sheet have a height, wherein the ratio of the height of the overlapping regions to the height of the reinforcement material is in a range of from about 70% to about 100%.

11. The roofing shingle of claim 10, wherein the ratio of the height of the overlapping regions to the height of the reinforcement material is in a range of from about 80% to about 95%.

12. The roofing shingle of claim 10, wherein the ratio of the height of the overlapping regions to the height of the reinforcement material is in a range of from about 85% to about 90%.

13. The roofing shingle of claim 10, wherein the underlay sheet has a uniform thickness.

14. The roofing shingle of claim 10, wherein the shingle provides an average nail pull-through value of at least 90 newtons when measured at a temperature of 23°C +/- 2°C.

15. The roofing shingle of claim 10, further including a plurality of granules secured to the headlap portion of the overlay sheet and not secured to the reinforcement material.

16. The roofing shingle of claim 10, wherein the material and thickness of the reinforcement material together with the headlap portion provide a nail pull-through value that is at least 13 percent greater than an otherwise identical shingle having no such reinforcement material.

17. The roofing shingle of claim 10, wherein the reinforcement material is formed from a woven material.

18. The roofing shingle of claim 17, wherein the reinforcement material is formed from a polymeric material.

19. A roofing shingle comprising:

an overlay sheet including a mat and an asphalt coating applied to the mat, and defining a headlap portion and a tab portion;

an underlay sheet including a mat and an asphalt coating applied to the mat, the underlay sheet being secured to the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet; and

a woven reinforcement material secured directly to the asphalt coating on a rear surface of the headlap portion of the overlay sheet without extending into the tab portion, wherein the woven reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay;

wherein the woven reinforcement material comprises a material and thickness that together with the headlap portion provide a nail pull-through value that is greater than an otherwise identical shingle having no such reinforcement material; and

wherein the shingle further includes a plurality of granules secured to the headlap portion of the overlay sheet and not secured to the woven reinforcement material;

wherein the woven reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet a maximum distance of about 0.12 inches.

20. The roofing shingle of claim 19, wherein the underlay sheet has a uniform thickness.

21. The roofing shingle of claim 19, wherein the overlay sheet has a non-uniform thickness.

22. The roofing shingle of claim 19, wherein the shingle provides an average nail pull-through value of at least 90 newtons when measured at a temperature of $23^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

23. The roofing shingle of claim 19, wherein the shingle provides an average nail pull-through value of at least 130 newtons when measured at a temperature of $23^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

24. The roofing shingle of claim 19, wherein the shingle provides an average nail pull-through value of at least 104 newtons when measured at a temperature of $23^{\circ}\text{C} \pm 2^{\circ}\text{C}$.

25. The roofing shingle of claim 19, wherein the woven reinforcement material is formed from a polymeric material.

26. The roofing shingle of claim 19, wherein the overlay member has a first height and the underlay member has a second height, the second height being one of less than one-half the first height and equal to one-half the first height.

27. The roofing shingle of claim 19, wherein the woven reinforcement material is positioned such that a reinforced nail zone is provided at a single-layer portion of the shingle.

28. The roofing shingle of claim 19, wherein the material and thickness of the woven reinforcement material together with the headlap portion provide a nail pull-through value that is at least about 13 percent greater than an otherwise identical shingle having no such reinforcement material.

29. The roofing shingle of claim 19, wherein the material and thickness of the woven reinforcement material together with the headlap portion provide a nail pull-through value within a range of from about 10 percent to about 100 percent greater than an otherwise identical shingle having no such reinforcement material.

30. The roofing shingle of claim 19, wherein the tab portion of the overlay sheet includes a cutout having an upper edge spaced apart from a lower edge of the woven reinforcement material by a distance within a range of from about 1/4 inch to about 3/4 inch.

31. The roofing shingle of claim 19, wherein the tab portion of the overlay sheet includes a cutout having an upper edge spaced apart from an upper edge of the woven reinforcement material by a distance within a range of from about 1¾ inch to about 2¼ inch.

32. A roofing shingle comprising:

an overlay sheet including a mat and an asphalt coating applied to the mat, and defining a headlap portion and a tab portion;

an underlay sheet including a mat and an asphalt coating applied to the mat, the underlay sheet being secured to the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet; and

a woven reinforcement material secured directly to the asphalt coating on a rear surface of the headlap portion of the overlay sheet without extending into the tab portion, wherein the woven reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay;

wherein the woven reinforcement material comprises a material and thickness that together with the headlap portion provide a nail pull-through value that is within a

range of from about 10 percent to about 100 percent greater than an otherwise identical shingle having no such reinforcement material;

wherein the woven reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet a maximum distance of about 0.12 inches.

33. The roofing shingle of claim 32, wherein the underlay sheet has a uniform thickness.

34. The roofing shingle of claim 32, wherein the overlay sheet has a non-uniform thickness.

35. The roofing shingle of claim 32, wherein the woven reinforcement material is formed from a polymeric material.

36. The roofing shingle of claim 32, wherein the overlay member has a first height and the underlay member has a second height, the second height being one of less than one-half the first height and equal to one-half the first height.

37. The roofing shingle of claim 32, wherein the woven reinforcement material is positioned such that a reinforced nail zone is provided at a single-layer portion of the shingle.

38. The roofing shingle of claim 32, wherein the tab portion of the overlay sheet includes a cutout having an upper edge spaced apart from a lower edge of the woven reinforcement material by a distance within a range of from about 1/4 inch to about 3/4 inch.

39. The roofing shingle of claim 32, wherein the tab portion of the overlay sheet includes a cutout having an upper edge spaced apart from an upper edge of the woven reinforcement material by a distance within a range of from about 1¾ inches to about 2¼ inches.

40. A roofing shingle comprising:

an overlay sheet including a mat and an asphalt coating applied to the mat, and defining a headlap portion and a tab portion;

an underlay sheet including a mat and an asphalt coating applied to the mat, the underlay sheet being secured to the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet; and

a woven reinforcement material secured directly to the asphalt coating on a rear surface of the headlap portion of the overlay sheet without extending into the tab portion, wherein the woven reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay;

wherein the woven reinforcement material comprises a material and thickness that together with the headlap portion provide a nail pull-through value that is greater than an otherwise identical shingle having no such reinforcement material; and

wherein the tab portion of the overlay sheet includes a cutout having an upper edge spaced apart from a lower edge of the woven reinforcement material by a distance within a range of from about $\frac{1}{4}$ inch to about $\frac{3}{4}$ inch, and spaced apart from an upper edge of the woven reinforcement material by a distance within a range of from about $1\frac{3}{4}$ inches to about $2\frac{1}{4}$ inches;

wherein the woven reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet a maximum distance of about 0.12 inches.

41. The roofing shingle of claim 40, wherein the overlay sheet has a non-uniform thickness.

42. The roofing shingle of claim 40, wherein the woven reinforcement material is positioned such that a reinforced nail zone is provided at a single-layer portion of the shingle.

43. The roofing shingle of claim 40, wherein the material and thickness of the woven reinforcement material together with the headlap portion provide a nail pull-through value that is within a range of from about 10 percent to about 100 percent greater than an otherwise identical shingle having no such reinforcement material.

44. A roofing shingle comprising:

an overlay sheet including a mat and an asphalt coating applied to the mat, and defining an upper headlap portion and a lower tab portion;

an underlay sheet including a mat and an asphalt coating applied to the mat, the underlay sheet being secured to the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet; and

a reinforcement material secured directly to the asphalt coating of the headlap portion of the overlay sheet without extending into the tab portion to provide a reinforced nail zone along shingle longitudinal axis of the shingle, wherein the reinforcement material comprises a material and thickness that together with the headlap portion provide a nail pull-through value that is greater than an otherwise identical shingle having no such reinforcement material;

wherein the shingle further includes a granular material secured to the headlap portion of the overlay sheet, with no granular material adhered to the reinforcement material, and wherein the reinforcement material has a thinner cross-section than the granular material, such that the reinforcement material forms a depression in an exterior surface of the headlap portion that extends along said longitudinal axis;

wherein at least about 70% of the reinforcement material is disposed on a dual-layer portion of the shingle.

45. The roofing shingle of claim 44, wherein the reinforcement material is secured directly to the asphalt coating on a rear surface of the headlap portion of the overlay sheet.

46. The roofing shingle of claim 44, wherein the reinforcement material is secured directly to the asphalt coating on a front surface of the headlap portion of the overlay sheet.

47. The roofing shingle of claim 44, wherein the distance between an upper edge of the tab portion of the overlay sheet and an upper edge of the reinforcement material is about $1\frac{3}{4}$ to about $2\frac{1}{4}$ inches.

48. The roofing shingle of claim 44, wherein the woven reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay sheet such that at least a portion of the reinforcement material extends along a single-layer portion of the shingle.

49. The roofing shingle of claim 44, wherein the woven reinforcement material extends along a single-layer portion of the shingle and at least a portion of the reinforcing material extends along the overlapping portions of the headlap portion and underlay sheet.

50. The roofing shingle of claim 44, wherein the reinforcement material extends into the overlapping regions of the headlap portion and the underlay sheet by a distance of no greater than $\frac{1}{8}$ inch.

51. The roofing shingle of claim 44, wherein the depression reduces a thickness of the shingle along the said longitudinal axis of the shingle.

52. The roofing shingle of claim 44, wherein the reinforcement material comprises a woven material.

53. The roofing shingle of claim 44, wherein the reinforcement material comprises a non-woven material.

54. A roofing shingle comprising:

an overlay sheet including a mat and an asphalt coating applied to the mat, and defining a headlap portion and a tab portion;

an underlay sheet including a mat and an asphalt coating applied to the mat, the underlay sheet being secured to the overlay sheet such that a region of the underlay sheet overlaps a region of the headlap portion of the overlay sheet; and

a reinforcement material secured directly to the asphalt coating on the headlap portion of the overlay sheet without extending into the tab portion to provide a reinforced nail zone along a longitudinal axis of the shingle, wherein the reinforcement material comprises a material and thickness that together with the headlap portion provide a nail pull-through value that is greater than an otherwise identical shingle having no such reinforcement material;

wherein the reinforcement material extends beyond the overlapping regions of the headlap portion and the underlay, such that a first portion of the reinforcement material is disposed on a dual-layer portion of the shingle and a second portion of the reinforcement material is disposed on a single-layer portion of the shingle;

wherein at least about 70% of the reinforcement material is disposed on a dual-layer portion of the shingle.

55. The roofing shingle of claim 54, wherein the headlap portion of the overlay sheet includes a depressed surface extending along said longitudinal axis of the shingle, with

a portion of the depressed surface being disposed on the single layer portion of the shingle.

56. The roofing shingle of claim 54, wherein the depressed surface is on a front surface of the headlap portion of the overlay sheet.

57. The roofing shingle of claim 54, wherein the depressed surface is on a rear surface of the headlap portion of the overlay sheet.

58. The roofing shingle of claim 54, wherein the depressed surface is covered by the reinforcement material.

59. The roofing shingle of claim 54, wherein the depressed surface reduces a thickness of the shingle along said longitudinal axis of the shingle.

60. The roofing shingle of claim 54, wherein the second portion of the reinforcement material is wider than the first portion of the reinforcement material.

61. The roofing shingle of claim 54, wherein the first portion of the reinforcement material extends into the dual-layer portion of the shingle by a distance of no greater than $\frac{1}{8}$ inch.

62. The roofing shingle of claim 54, wherein the reinforcement material comprises a woven material.

63. The roofing shingle of claim 54, wherein the reinforcement material comprises a non-woven material.




FIG. 1

Patent Agents
Smart & Biggar




FIG. 2

Patent Agents
Smart & Biggar




FIG. 3
(PRIOR ART)





FIG. 4

*Patent Agents
Smart & Biggar*



Patent Agents
Smart & Biggar

FIG. 5

