



- (51) International Patent Classification:
B29C 70/34 (2006.01) *B29C 33/38* (2006.01)
- (21) International Application Number:
PCT/US2013/059834
- (22) International Filing Date:
13 September 2013 (13.09.2013)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
13/663,815 30 October 2012 (30.10.2012) US
- (71) Applicant: **THE BOEING COMPANY** [US/US]; 100 North Riverside Plaza, Chicago, Illinois 60606-2016 (US).
- (72) Inventors: **KLINE, William Thomas**; 100 N. Riverside Plaza, Chicago, Illinois 60606 (US). **GROSS, Larry Earl**; 100 N. Riverside Plaza, Chicago, Illinois 60606 (US). **GHOSE, Sayata**; 100 N. Riverside Plaza, Chicago, Illinois 60606 (US).
- (74) Agents: **HALPERIN, Brett L.** et al.; The Boeing Company, P.O. Box 2515, MC 110-SD54, Seal Beach, California 90740-1515 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: COMPOSITE LAYER FORMING SYSTEM AND METHOD OF FORMING A COMPOSITE




FIG. 1

(57) Abstract: A method and apparatus for forming a stack of composite layers (102) into a desired shape is present. The stack of composite layers may be positioned on a tool (106) and a number of compressible supports (108) such that the stack of composite layers may be substantially flat on the tool and the stack of composite layers may be substantially flat on the number of compressible supports. A flexible sheet (116) may be placed on top of the stack of composite layers. A vacuum load may be applied on the stack of composite layers on the tool and the number of compressible supports using the flexible sheet such that consolidation of the stack of composite layers occurs to form a desired shape on the tool and the number of compressible supports compress during forming of the desired shape.

COMPOSITE LAYER FORMING SYSTEM AND METHOD OF FORMING A COMPOSITE

BACKGROUND INFORMATION

1. Field:

The present disclosure relates generally to composite materials and, in particular, to manufacturing composite parts. Still more particularly, the present disclosure relates to a method and apparatus for forming shapes in layers of composite materials.

2. Background:

Aircraft are being designed and manufactured with greater and greater percentages of composite materials. Composite materials may be used in aircraft to decrease the weight of the aircraft. This decreased weight improves performance features such as payload capacities and fuel efficiencies. Further, composite materials provide longer service life for various components in an aircraft.

Composite materials are strong, light-weight materials created by combining two or more functional components. For example, a composite material may include reinforcing fibers bound in a polymer resin matrix. The fibers may be unidirectional or may take the form of a woven cloth or fabric. The fibers and resins are arranged and cured to form a composite material.

Further, using composite materials to create aerospace composite structures potentially allows for portions of an aircraft to be manufactured in larger pieces or sections. For example, a fuselage in an aircraft may be created in cylindrical sections. Other examples include, without limitation, wing

sections joined to form a wing or stabilizer sections joined to form a stabilizer.

In manufacturing composite structures, layers of composite material are typically laid up on a tool. The layers of composite material may be comprised of fibers in sheets. These sheets may take the form of fabrics, tape, tows, or other suitable forms. In some cases, resin may be infused or pre-impregnated into the sheets. These types of sheets are commonly referred to as prepreg.

The different layers of prepreg may be laid up in different orientations and different numbers of layers may be used depending on the thickness of the composite structure being manufactured. These layers of prepreg may be laid up by hand or using automated lamination equipment such as a tape laminating machine or a fiber placement system.

A stack of the layers of preform composite material may be placed onto a tool for processing. This stack of composite layers may be referred to as a stack of composite layers and may take the form of a prepreg or preform. The stack of composite layers may be flat and may be placed onto a tool to shape the drape into a desired shape for a composite part.

A layer of flexible material in a flexible sheet may be placed over the stack of composite layers. This flexible material may be an elastomer vacuum bag. A vacuum may then be drawn to apply a vacuum load on the stack of composite layers. When the vacuum is applied, the flexible sheet may be pulled down through the vacuum around the tool to cause the stack of composite layers to change from a substantially flat shape to a desired shape for the composite part.

Oftentimes, the repeated forming of shapes from stacks of composite layers may result in the flexible sheet not performing as desired after a period of time. For example, the flexible

sheet may fail while forming a shape from a stack of composite layers. Repeated stress from being stretched over a tool may result in a tear or opening occurring in the flexible sheet. This failure may result in the tool being unavailable for use until the flexible sheet can be replaced with a new flexible sheet.

Therefore, it would be desirable to have a method and apparatus that takes into account at least some of the issues discussed above, as well as other possible issues.

SUMMARY

In one illustrative embodiment, a method for forming a stack of composite layers into a desired shape may be present. The stack of composite layers may be positioned on a tool and a number of compressible supports such that the stack of composite layers may be substantially flat on the tool and the stack of composite layers may be substantially flat on the number of compressible supports. A flexible sheet is placed on top of the stack of composite layers. A vacuum load may be applied on the stack of composite layers on the tool and the number of compressible supports using the flexible sheet such that consolidation of the stack of composite layers occurs to form the desired shape on the tool and the number of compressible supports compress during forming of the desired shape.

In another illustrative embodiment, an apparatus comprises a platform, a number of compressible supports, and a flexible sheet. The platform may be configured to receive a tool. The number of compressible supports may be configured to be placed on the platform in a number of locations such that a stack of composite layers positioned on the tool and the number of compressible supports may be substantially flat on the tool and

the stack of composite layers may be substantially flat on the number of compressible supports. The flexible sheet may be configured to be placed on top of the stack of composite layers such that a vacuum drawn on the flexible sheet results in the flexible sheet applying a vacuum load on the stack of composite layers on the tool and the number of compressible supports such that the stack of composite layers forms a desired shape on the tool and the number of compressible supports compress during forming of the desired shape.

In yet another illustrative embodiment, a method for forming a stack of composite layers into a desired shape for an aircraft part may be present. The stack of composite layers may be positioned on a tool and a number of compressible supports. A number of locations of the number of compressible supports may be configured to support a number of edges of the stack of composite layers. The number of locations of a number of compressible layers may support the number of edges of the stack of composite layers such that the stack of composite layers may remain substantially flat when heated prior to applying a vacuum load. The number of compressible supports may be comprised of a number of components selected from at least one of a foam, a polymer foam, an open cell foam, a closed cell foam, and a solid dispersed medium. The stack of composite layers may be a prepreg comprised of fabric layers with a thermoset resin infused into the fabric layers. A vacuum load may be applied on the stack of composite layers on the tool and the number of compressible supports. The stack of composite layers may form the desired shape on the tool and the number of compressible supports compress during forming of the desired shape. The desired shape may be formed by lowering a frame holding a flexible sheet comprised of silicon onto a platform on which the stack of composite layers may be located with the tool and the

number of compressible supports such that a seal may be formed between the frame and the platform in which the seal is sufficient to apply a vacuum to cause the flexible sheet to apply the vacuum load on the stack of composite layers, the number of compressible supports, and the tool; and drawing the vacuum on the flexible sheet such that the flexible sheet may apply the vacuum load on the stack of composite layers. The protective sheet may be located between the flexible sheet and the stack of composite layers. The stack of composite layers may be heated prior to applying the vacuum load. The stack of composite layers with the desired shape may be removed from the tool. The stack of composite layers may be moved to a curing system. The stack of composite layers may be cured to form the aircraft part with the desired shape. The desired shape may be selected from one of a channel with walls and a shape for a part selected from one of a stringer, a beam, and a rail in which a life of the flexible sheet may be increased using the number of compressible supports.

In still another illustrative embodiment, a shape forming system for manufacturing an aircraft part comprises a platform, a number of compressible supports, a flexible sheet, and a frame. The platform may be configured to receive a tool. The number of compressible supports may be configured to be placed on the platform such that a stack of composite layers positioned on the tool and the number of compressible supports in a number of locations may be substantially flat on the tool and the number of compressible supports. The number of locations of the number of compressible supports may be configured to support a number of edges of the stack of composite layers. The stack of composite layers may remain substantially flat when heated prior to applying a vacuum load. The number of compressible supports may be comprised of a number of components selected from at

least one of a foam, a polymer foam, an open cell foam, a closed cell foam, and a solid dispersed medium. The stack of composite layers may be a prepreg. The flexible sheet may be configured to be placed on top of the stack of composite layers such that a vacuum drawn on the flexible sheet may result in the flexible sheet applying the vacuum load on the stack of composite layers on the tool and the number of compressible supports such that the stack of composite layers forms a desired shape for the aircraft part on the tool and the number of compressible supports compress during forming of the desired shape. The frame holding the flexible sheet may form a seal with the platform when the frame with the flexible sheet is placed on the platform on top of the stack of composite layers on the tool and the number of compressible supports on the platform in which a life of the flexible sheet is increased using the number of compressible supports.

The features and functions can be achieved independently in various embodiments of the present disclosure or may be combined in yet other embodiments in which further details can be seen with reference to the following description and drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

The novel features believed characteristic of the illustrative embodiments are set forth in the appended claims. The illustrative embodiments, however, as well as a preferred mode of use, further objectives and features thereof, will best be understood by reference to the following detailed description of an illustrative embodiment of the present disclosure when read in conjunction with the accompanying drawings, wherein:

Figure 1 is an illustration of a shape forming system in accordance with an illustrative embodiment;

Figure 2 is an illustration of a compressible support in accordance with an illustrative embodiment;

Figures 3-6 are illustrations of the shaping of a stack of composite layers in accordance with an illustrative embodiment;

Figure 7 is an illustration of a stack of composite layers with a desired shape in accordance with an illustrative embodiment;

Figure 8 is an illustration of a compressible support in accordance with an illustrative embodiment;

Figure 9 is an illustration of a block diagram of a design environment in accordance with an illustrative embodiment;

Figure 10 is an illustration of a flowchart of a process for forming a stack of composite layers into a desired shape in accordance with an illustrative embodiment;

Figure 11 is an illustration of a more detailed flowchart of a process for forming a stack of composite layers into a desired shape in accordance with an illustrative embodiment;

Figure 12 is an illustration of an aircraft manufacturing and service method in accordance with an illustrative embodiment;

Figure 13 is an illustration of an aircraft in which an illustrative embodiment may be implemented; and

Figure 14 is an illustration of a block diagram of a data processing system in accordance with an illustrative embodiment.

DETAILED DESCRIPTION

The illustrative embodiments recognize and take into account one or more different considerations. For example, the illustrative embodiments recognize and take into account that the flexible sheet used when forming layers of composite material into a desired shape often takes the form of an

elastomer vacuum bag. The flexible sheet may be comprised of silicon which may have a desired level of elasticity such that the flexible sheet may be drawn around a tool to apply a vacuum load on the stack of composite layers to form a part with the desired shape.

The illustrative embodiments recognize and take into account that other components, other than the composite layers, may be used during the process of forming the composite layers into a desired shape, while the composite layers are in an uncured form. The repeated stretching of the flexible sheet also occurs around these other components in addition to the tool. The illustrative embodiments also recognize and take into account that other components other than a tool may be configured to reduce the amount of stretching of the flexible sheet that occurs to conform to the tool and components in applying a vacuum load to the stack of composite layers to cause the stack of composite layers to conform to the shape of the tool to form a desired shape for a part from a stack of composite layers.

For example, the illustrative embodiments recognize and take into account that supports may be present around the tool that aid in holding the stack of composite layers in a substantially flat or planar form prior to the flexible sheet applying a vacuum load on the stack of composite layers to shape the stack of composite layers into a desired shape from the substantially flat shape.

This substantially flat shape may be desirable to reduce inconsistencies in the shape of the stack of composite layers formed from applying the vacuum load prior to shaping the stack of composite layers through the application of a vacuum load. For example, when the stack of composite layers may have a substantially flat shape prior to the vacuum load being applied,

wrinkling may be reduced in the stack of composite layers during forming.

Thus, the illustrative embodiments provide a method and apparatus for forming a stack of composite layers into a desired shape for a composite part. In one illustrative embodiment, the stack of composite layers may be positioned on a tool with a number of compressible supports such that the stack of composite layers may be substantially flat on the tool and the stack of composite layers may be substantially flat on the number of compressible supports.

As used herein, a "number of" when used with reference to items means one or more items. For example, a number of compressible supports may be one or more compressible supports. A flexible sheet may be placed on top of the stack of composite layers. A vacuum load may be applied to the stack of composite layers on the tool and the number of compressible supports using the flexible sheet such that consolidation of the stack of composite layers occurs to form the desired shape of the tool and the number of compressible supports compress during the forming of the desired shape.

With reference now to the figures and, in particular, with reference to **Figure 1**, an illustration of a shape forming system is depicted in accordance with an illustrative embodiment. In this depicted example, shape forming system **100** may be used to shape stack of composite layers **102** into a desired shape. In this illustrative example, shape forming system **100** may be a composite layer forming system that may include shape forming machine **104**, tool **106**, and compressible supports **108**.

In this illustrative example, shape forming machine **104** may take the form of hot drape forming machine **110**. As illustrated, shape forming machine **104** may include platform **112**, frame **114**, and flexible sheet **116**. Flexible sheet **116** may be held in frame

114. Further, frame **114** may be moveable in the direction of arrow **118** toward platform **112**.

In this illustrative example, flexible sheet **116** may be an elastomer sheet. In particular, flexible sheet **116** may take the form of elastomer vacuum bag **120** attached to frame **114**. In these illustrative examples, flexible sheet **116** may be comprised of any polymer having an elastic property that allows for flexible sheet **116** to be deformed and substantially returned to its original shape.

In these illustrative examples, compressible supports **108** comprise compressible support **122** and compressible support **124**. Compressible support **122** and compressible support **124** may be located on surface **126** of platform **112**. Additionally, tool **106** may be also located on surface **126** of platform **112**. In this example, tool **106** may have height **127**.

In these illustrative examples, tool **106** may be located between a compressible supports **108** on surface **126** of platform **112**. The placement of tool **106** and compressible supports **108** may be such that stack of composite layers **102** may be placed onto tool **106** and compressible supports **108**. Specifically, a number of locations of a number of compressible supports **108** may be configured to support a number of edges of stack of composite layers **102**.

In these illustrative examples, stack of composite layers **102** may be comprised of fabric and a resin infused into the fabric. In particular, stack of composite layers **102** may take the form of prepreg **128**. Prepreg **128** may be comprised of fabric layers with a thermoset resin infused into the fabric layers.

In these illustrative examples, the positioning of compressible support **122** and compressible support **124** with respect to tool **106** may be such that stack of composite layers **102** may be substantially flat or planar when placed onto tool

106. As depicted, compressible support **122** provides support for side **130** of stack of composite layers **102**. Compressible support **124** provides support for side **132** of stack of composite layers **102**.

As depicted, side **130** may have height **131** and side **132** may have height **133**. Center **134** of stack of composite layers **102** may have height **135**.

Support provided by compressible support **122** and compressible support **124** may be such that height **131** of side **130** and height **133** of side **132** of stack of composite layers **102** remain substantially the same above surface **126** as height **135** of center **134** of stack of composite layers **102** on tool **106**. In other words, stack of composite layers **102** remains substantially flat and may have a substantially flat or planar shape.

In these illustrative examples, compressible supports **108** may be configured in accordance with an illustrative embodiment. The configuration of compressible supports **108** may be such that the life of flexible sheet **116** may be increased when processing stacks of composite layers such as stack of composite layers **102**. In other words, the life of flexible sheet **116** may be increased using compressible supports **108** to process stacks of composite layers such as stack of composite layers **102**.

Turning now to **Figure 2**, an illustration of a compressible support is depicted in accordance with an illustrative embodiment. In this depicted example, an isometric view of compressible support **122** from **Figure 1** is depicted. In this illustrative example, compressible support **122** may be an elongate member with a shape of a quadrilateral.

Compressible support **122** may have a substantially identical shape to compressible support **124** in **Figure 1**. In this illustrative example, compressible support **122** may have length **200**, height **202**, and width **204**. Length **200** may be at least the

same length as stack of composite layers **102** in **Figure 1**. Width **204** may be selected such that surface **206** may hold side **130** of stack of composite layers **102** when positioned on surface **126** of platform **112** relative to tool **106** in **Figure 1**. Height **202** may be selected such that height **131** of side **130** of stack of composite layers **102** may be substantially the same as height **135** at center **134** of stack of composite layers **102**.

In this illustrative example, height **202** of compressible support **122** may be, for example, without limitation, selected to be substantially equal to height **127** of tool **106**. The selection may be such that a tolerance of about +0.25 inches to about - 0.25 inches may be present between height **131** at side **130** of stack of composite layers **102** and height **135** at center **134** of stack of composite layers **102** as well as between height **133** at side **132** of stack of composite layers **102** and height **135** at center **134** of stack of composite layers **102** in some illustrative examples.

In these illustrative examples, compressible support **122** may be configured to be compressible in at least the direction of arrow **208**. Of course, compressible support **122** also may be compressible in other directions such as the direction of arrow **210** depending on the particular implementation.

Turning now to **Figures 3-6**, illustrations of the shaping of a stack of composite layers are depicted in accordance with an illustrative embodiment. As depicted in **Figure 3**, stack of composite layers **102** has been heated. As a result, stack of composite layers **102** may be less stiff than when in an unheated form. Stack of composite layers **102** may bend on side **130** and side **132** without compressible support **122** and compressible support **124** to provide support for side **130** and side **132** of stack of composite layers **102**. With compressible support **122** and compressible support **124**, stack of composite layers **102** may

be substantially flat or planar even though stack of composite layers **102** may have been heated for forming a shape for a part.

As depicted, frame **114** with flexible sheet **116** may have been lowered in the direction of arrow **118** toward platform **112**. In this illustrative example, flexible sheet **116** is not shown in order to see the components underneath flexible sheet **116**.

In this illustrative example, edge **300** of frame **114** may contact edge **302** of platform **112** when frame **114** may be further lowered toward platform **112**. In these illustrative examples, edge **300** and edge **302** may be configured to provide a seal when edge **300** and edge **302** contact each other. In these illustrative examples, edge **300** and edge **302** may include a sealant.

As depicted, protective sheet **304** has been placed onto surface **306** of stack of composite layers **102**. Protective sheet **304** may be configured to protect stack of composite layers **102** from contamination by flexible sheet **116** when flexible sheet **116** may be moved onto stack of composite layers **102**. In other words, protective sheet **304** may provide a barrier film between stack of composite layers **102** and flexible sheet **116**.

Protective sheet **304** may be comprised of a flexible material such as an elastomer, fiberglass, or some other suitable type of material that may be stretched during curing of stack of composite layers **102** such that the stretching does not cause a tear or opening in protective sheet **304**. In some illustrative examples, protective sheet **304** and/or an additional protective sheet may also be a peel ply. When protective sheet **304** functions as a peel ply, this peel ply may protect stack of composite materials **102** from dust, dirt, and other contaminants located on flexible sheet **116**.

An additional protective sheet (not shown) may be present between stack of composite layers **102** and tool **106** in addition to protective sheet **304**. The additional protective sheet (not

shown) also may prevent contamination of stack of composite layers **102** from tool **106**. In other illustrative embodiments, another protective sheet (not shown) may also be present between stack of composite layers **102** and compressible supports **108** depending on the particular implementation.

With reference now to **Figure 4**, an illustration of a flexible sheet on a stack of composite layers in a shape forming machine is depicted in accordance with an illustrative embodiment. In this illustrative example, flexible sheet **116** has been placed onto stack of composite layers **102**.

Flexible sheet **116**, however, does not directly contact stack of composite layers **102**. Protective sheet **304** (not shown) may be located between flexible sheet **116** and surface **306** of stack of composite layers **102**.

With flexible sheet **116** placed on top of stack of composite layers **102** and edge **300** of frame **114** in contact with edge **302** of platform **112**, stack of composite layers **102** may be ready to be formed into a shape for a part.

With frame **114** lowered onto platform **112**, seal **400** may be formed between frame **114** and platform **112**. Seal **400** may be formed between edge **300** of frame **114** and edge **302** of platform **112**. In these illustrative examples, seal **400** may be sufficient to apply a vacuum to cause flexible sheet **116** to apply a vacuum load on stack of composite layers **102**. In this illustrative example, a vacuum may be drawn in the space defined by frame **114** in flexible sheet **116** and surface **126** of platform **112**. In this illustrative example, the vacuum may be drawn from a vacuum source that may be located in platform **112** or in another location.

With reference now to **Figure 5**, an illustration of the processing of a stack of composite layers to form a shape for a part is depicted in accordance with an illustrative embodiment.

In this illustrative example, a vacuum load may be applied to stack of composite layers **102** on tool **106** and compressible supports **108**. This vacuum load may be generated by flexible sheet **116** in response to a vacuum being drawn in the space between flexible sheet **116** and surface **126** of platform **112**.

In this illustrative example, the vacuum load causes height **202** of compressible support **122** and height **500** of compressible support **124** to be reduced. Height **202** of compressible support **122** and height **500** of compressible support **124** may be reduced because of compression caused by the atmospheric pressure applied to flexible sheet **116** when the vacuum is drawn in the space between flexible sheet **116** and surface **126** of platform **112**.

As can be seen, side **130** and side **132** may still be supported by compressible support **122** and compressible support **124** although side **130** and side **132** may not be substantially planar with center **134**. In this example, the vacuum load applied to stack of composite layers **102** causes side **130** and side **132** to conform to side **502** and side **504** of tool **106**.

Turning now to **Figure 6**, an illustration of the processing of a stack of composite layers to form a shape for a part is depicted in accordance with an illustrative embodiment. In this illustration, the vacuum load applied to stack of composite layers **102** may cause side **130** and side **132** to be shaped or bent against side **502** and side **504** of tool **106**, respectively. As can be seen, side **130** and side **132** may no longer be supported by compressible support **122** and compressible support **124**, respectively.

In this view, stack of composite layers **102** may have desired shape **600**. Desired shape **600** may take many different forms. In this illustrative example, desired shape **600** may include a channel with walls as shown in **Figure 7**.

As depicted, desired shape **600** may be a stringer, a beam, a rail, or some other desirable shape for a composite part. After some period of time, the vacuum load may be removed from stack of composite layers **102**.

Frame **114** with flexible sheet **116** may be raised in the direction of arrow **602**. Thereafter, stack of composite layers **102** with desired shape **600** may be removed from tool **106**.

Further, when frame **114** with flexible sheet **116** may be moved in the direction of arrow **602**, compressible support **122** and compressible support **124** may substantially return to their original shapes. In other words, height **202** of compressible support **122** and height **500** of compressible support **124** may return substantially to the original height prior to application of a vacuum load.

Turning now to **Figure 7**, an illustration of a stack of composite layers with a desired shape is depicted in accordance with an illustrative embodiment. In this depicted example, stack of composite layers **102** with desired shape **600** may be removed from tool **106**. As can be seen, stack of composite layers **102** with desired shape **600** takes the form of stringer **700** in this illustrative example. Stringer **700** may be a composite stringer as depicted in this illustrative example. Stack of composite layers **102** with desired shape **600** may be placed onto another tool or curing system for curing stack of composite layers **102** to form a cured form of stringer **700**.

With reference now to **Figure 8**, an illustration of a compressible support is depicted in accordance with an illustrative embodiment. In this depicted example, compressible support **800** may be an example of another configuration of a compressible support in compressible supports **108** that may be used in shape forming system **100** in **Figure 1**.

As can be seen, compressible support **800** may have length **802**, height **804**, and stair-stepped width **806**. Stair-stepped width **806** may be smaller at top side **808** as compared to bottom side **810**.

Additionally, in this illustrative example, compressible support **800** may be comprised of number of compressible layers **812** that may be associated with each other. When one component is "associated" with another component, the association may be a physical association in these depicted examples. For example, a first component may be considered to be associated with a second component by being secured to the second component, bonded to the second component, mounted to the second component, welded to the second component, fastened to the second component, and/or connected to the second component in some other suitable manner.

The first component also may be connected to the second component using a third component. The first component may also be considered to be associated with the second component by being formed as part of and/or an extension of the second component.

The use of number of compressible layers **812** may be in contrast to the single component for compressible support **122** and compressible support **124** in **Figures 1-6**. In other words, a compressible support may be comprised of a single component or multiple components depending on the particular implementation. Further, with number of compressible layers **812**, each of the quadrilaterals may have a different level of compressibility depending on the particular implementation.

A different level of compressibility may be present when a variation in a form speed may be present. Form speed may be the time needed for stack of composite layers **102** to change shape to conform to a surface of tool **106** when a load such as a vacuum

load may be applied to stack of composite layers **102** using a device such as flexible sheet **116**. The variation in form speed may be present with a complex surface on tool **106**. In other words, the variation may occur when tool **106** may not be substantially planar.

The illustration of compressible support **122**, compressible support **124**, and compressible support **800** in the different figures are not meant to imply limitations to the manner in which different compressible supports may be implemented. In these illustrative examples, a compressible support may be selected as having various shapes and dimensions depending on tool **106** and stack of composite layers **102** to be shaped on tool **106**.

With reference now to **Figure 9**, an illustration of a block diagram of a design environment is depicted in accordance with an illustrative embodiment. In this depicted example, design environment **900** may include designer **902**. Designer **902** may be used to generate shape forming system design **904**. Shape forming system design **904** may be an example of a design for a shape forming system that may be used to shape stacks of composite layers. For example, shape forming system design **904** may be a design for shape forming system **100** and used to shape stack of composite layers **102** in **Figure 1**.

In this illustrative example, designer **902** may be implemented using hardware, software, or a combination of the two. When software is used, operations performed by designer **902** may be implemented in program code configured to be run on a processor unit. When hardware is employed, the hardware may include circuits that operate to perform operations in designer **902**. In these illustrative examples, the hardware may take the form of a circuit system, an integrated circuit, an application specific integrated circuit (ASIC), a programmable logic device,

or some other suitable type of hardware configured to perform a number of operations. With a programmable logic device, the device may be configured to perform the number of operations.

The device may be reconfigured at a later time or may be permanently configured to perform the number of operations.

Examples of programmable logic devices include, for example, a programmable logic array, a programmable array logic, a field programmable logic array, a field programmable gate array, and other suitable hardware devices.

In this illustrative example, designer **902** may be implemented using computer system **906**. Computer system **906** may be comprised of one or more computers. When more than one computer is present in computer system **906**, those computers may be in communication with each other over a communications medium such as a network (not shown).

As depicted, shape forming system design **904** may be generated using input **908**. In this depicted example, input **908** may include part design **910**. Part design **910** may be a design for composite part **912**. Composite part **912** may be, for example, without limitation, an aircraft part. In these illustrative examples, part design **910** for composite part **912** may include components **914**. Components **914** may be composite layers **916**. In this illustrative example, composite layers **916** may be arranged to form stack **918** of composite layers **916**.

In this illustrative example, the configuration of composite layers **916** in stack **918** may be described by parameters **920**. For example, parameters **920** may identify number **922** for composite layers **916**. In other words, number **922** may define how many layers may be present in composite layers **916** that form stack **918**. In addition, parameters **920** also may identify orientation **924** for number **922** of composite layers **916** and materials **926** for use in composite layers **916**.

Further, parameters **920** also may identify dimensions **930**. Dimensions **930** may include, for example, length **932** and width **934** for composite layers **916**. Another parameter in parameters **920** for composite part **912** may be shape **936** for stack **918** of composite layers **916**. In these illustrative examples, shape **936** may be, for example, without limitation, a hat shape for a stringer or some other suitable shape depending on the form of composite part **912**. These and other parameters in parameters **920** in part design **910** may be used by designer **902** to generate shape forming system design **904**.

In this illustrative example, shape forming system design **904** may include components **938** for shape forming system **939**. Components **938** may include, for example, shape forming machine **940**, tool **942**, compressible support **944**, and other suitable components.

In these illustrative examples, parameters **946** may be present for components **938**. For example, parameters **946** may identify source **948** for shape forming machine **940**. In this illustrative example, shape forming machine **940** may be available from various manufacturers or suppliers. Source **948** may be a manufacturer, a supplier, or other vendor of shape forming machines.

Tool **942** may have dimensions **950** and materials **952**. Dimensions **950** may be based on shape **936** for composite part **912**. Tool **942** also may be comprised of materials **952**. One or more of materials **952** may be used to form tool **942**. Materials **952** may include at least one of a metal, steel, titanium, polycarbonate, and other suitable types of materials.

In these illustrative examples, compressible support **944** also may have dimensions **958** and materials **960** in parameters **946**. Dimensions **958** may include, for example, without

limitation, length **962**, width **964**, height **966**, shape **968**, and other suitable dimensions.

In this illustrative example, height **966** may be based on the height of tool **942**. In particular, height **966** may be selected such that stack **918** of composite layers **916** have a substantially flat or planar shape when placed onto tool **942** for processing.

Materials **960** may be selected as materials that allow compression of compressible support **944**. The compression of compressible support **944** may be selected such that compressible support **944** compresses at desired rate **970**. Materials **960** for compressible support **944** may be selected from at least one of a foam, a polymer foam, an open cell foam, a closed cell foam, a solid dispersed medium, and other suitable materials.

With shape forming system design **904**, one or more components for a shape forming system may be generated. In particular, components such as compressible supports may be manufactured and designed for use with existing shape forming systems. With shape forming system design **904**, a shape forming system may be manufactured for use in shaping stacks of composite layers into desired shapes for composite parts.

The illustration of design environment **900** is not meant to imply physical or architectural limitations the manner in which a design environment may be implemented. Other components in addition to or in place of the ones illustrated may be used.

Some components may be excluded. Also, the blocks are presented to illustrate some functional components. One or more of these blocks may be combined, divided, or combined and divided into different blocks when implemented in an illustrative embodiment.

For example, shape forming system design **904** may only include a design for compressible support **944**. In other

illustrative examples, parameters **946** for shape forming machine **940** may be part of input **908**.

With reference now to **Figure 10**, an illustration of a flowchart of a process for forming a stack of composite layers into a desired shape is depicted in accordance with an illustrative embodiment. The process illustrated in **Figure 10** may be implemented using shape forming system **100** in **Figure 1**. In particular, the process may be used to generate a desired shape for stack of composite layers **102** in **Figure 1**.

The process begins by positioning stack of composite layers **102** on tool **106** and number of compressible supports **108** such that stack of composite layers **102** may be substantially flat on tool **106** and stack of composite layers **102** may be substantially flat on number of compressible supports **108** (operation **1000**). The process then places flexible sheet **116** on top of stack of composite layers **102** (operation **1002**).

Next, the process applies a vacuum load on stack of composite layers **102** on tool **106** in number of compressible supports **108** such that stack of composite layers **102** forms a desired shape on tool **106** and number of compressible supports **108** compressed during the forming of the desired shape (operation **1004**) with the process terminating thereafter.

Turning now to **Figure 11**, an illustration of a more detailed flowchart of a process for forming a stack of composite layers into a desired shape is depicted in accordance with an illustrative embodiment. The process illustrated in **Figure 11** may be implemented using shape forming system **100** in **Figure 1**. This process may be used to shape stack of composite layers **102** into a desired shape for a composite part.

The process begins by positioning tool **106** and number of compressible supports **108** on platform **112** of shape forming machine **104** (operation **1100**). Thereafter, the process heats

stack of composite layers **102** (operation **1102**). Stack of composite layers **102** may be prepreg **128** and may take the form of a hot drape when heated.

The process then positions stack of composite layers **102** on tool **106** on number of compressible supports **108** such that stack of composite layers **102** may be substantially flat on tool **106** and stack of composite layers **102** may be substantially flat on number of compressible supports **108** (operation **1104**). In these illustrative examples, stack of composite layers **102** may be substantially flat against tool **106**. Tool **106** may be substantially planar, have a curve, have a complex contour, or some other suitable shape. Next, the process places flexible sheet **116** on stack of composite layers **102** (operation **1106**).

The placement of flexible sheet **116** on top of stack of composite layers **102** may be performed such that seal **400** may be formed in the space between flexible sheet **116** and surface **126** of platform **112** on which stack of composite layers **102** may be located. The process then draws a vacuum on flexible sheet **116** such that flexible sheet **116** applies a vacuum load on stack of composite layers **102**, number of compressible supports **108**, and tool **106** (operation **1108**). In some cases, stack of composite materials **102** may be consolidated to remove voids, reduce volume, increase the fiber-to-volume ratio, or some combination thereof, depending on the particular implementation.

The process ceases supplying the vacuum load on stack of composite layers **102** (operation **1110**). Flexible sheet **116** may be removed (operation **1112**). Thereafter, stack of composite layers **102** with a desired shape may be removed from tool **106** (operation **1114**). In operation **1114**, stack of composite layers **102** may no longer be compressed with the removal of the vacuum load. By removing the compression, a decrease in fiber-to-volume ratio beyond desired values may be reduced or avoided.

Stack of composite layers **102** may be moved to a curing system (operation **1116**). Next, stack of composite layers **102** may be cured to form a composite part with the desired shape (operation **1118**) with the process terminating thereafter.

The flowcharts and block diagrams in the different depicted embodiments illustrate the architecture, functionality, and operation of some possible implementations of apparatuses and methods in an illustrative embodiment. In this regard, each block in the flowcharts or block diagrams may represent a module, a segment, a function, and/or a portion of an operation or step.

In these illustrative examples, one or more of the different operations may be performed using software running on a computer. Additionally, the operations may also be performed using hardware such as one or more circuits.

In some alternative implementations of an illustrative embodiment, the function or functions noted in the blocks may occur out of the order noted in the figures. For example, in some cases, two blocks shown in succession may be executed substantially concurrently, or the blocks may sometimes be performed in the reverse order, depending upon the functionality involved. Also, other blocks may be added in addition to the illustrated blocks in a flowchart or block diagram.

For example, the heating of the stack of composite layers in operation **1102** and the positioning for the stack of composite layers in the number of compressible supports in operation **1104** may be performed at substantially the same time or in reverse order. As another example, operations may also be included that place protective sheets between the stack of composite layers and the tool and between the stack of composite layers and the flexible sheet.

Illustrative embodiments of the disclosure may be described in the context of aircraft manufacturing and service method **1200** as shown in **Figure 12** and aircraft **1300** as shown in **Figure 13**. Forming of stack of composite layers **102** for composite parts in aircraft **1300** may occur during manufacturing and service method **1200**.

Turning first to **Figure 12**, an illustration of an aircraft manufacturing and service method is depicted in accordance with an illustrative embodiment. During pre-production, aircraft manufacturing and service method **1200** may include specification and design **1202** of aircraft **1300** in **Figure 13** and material procurement **1204**.

During production, component and subassembly manufacturing **1206** and system integration **1208** of aircraft **1300** in **Figure 13** takes place. Thereafter, aircraft **1300** in **Figure 13** may go through certification and delivery **1210** in order to be placed in service **1212**. While in service **1212** by a customer, aircraft **1300** in **Figure 13** may be scheduled for routine maintenance and service **1214**, which may include modification, reconfiguration, refurbishment, and other maintenance or service.

Each of the processes of aircraft manufacturing and service method **1200** may be performed or carried out by a system integrator, a third party, and/or an operator. In these examples, the operator may be a customer. For the purposes of this description, a system integrator may include, without limitation, any number of aircraft manufacturers and major-system subcontractors; a third party may include, without limitation, any number of vendors, subcontractors, and suppliers; and an operator may be an airline, a leasing company, a military entity, a service organization, and so on.

With reference now to **Figure 13**, an illustration of an aircraft is depicted in which an illustrative embodiment may be

implemented. In this example, aircraft **1300** may be produced by aircraft manufacturing and service method **1200** in **Figure 12** and may include airframe **1302** with plurality of systems **1304** and interior **1306**. Examples of systems **1304** include one or more of propulsion system **1308**, electrical system **1310**, hydraulic system **1312**, and environmental system **1314**. Any number of other systems may be included. Although an aerospace example may be shown, different illustrative embodiments may be applied to other industries, such as the automotive industry.

Apparatuses and methods embodied herein may be employed during at least one of the stages of aircraft manufacturing and service method **1200** in **Figure 12**. An illustrative embodiment may be implemented during component and subassembly manufacturing **1206** to shape stacks of composite layers into desired shapes that may be cured to form composite parts with desired shapes. Additionally, one or more illustrative embodiments also may be implemented during maintenance and service **1214**. The illustrative embodiments may be implemented to shape stacks of composite layers for manufacturing composite parts that may be used during maintenance, refurbishment, upgrades, and other operations that may be performed during maintenance and service **1214**.

Turning now to **Figure 14**, an illustration of a block diagram of a data processing system is depicted in accordance with an illustrative embodiment. Data processing system **1400** may be used to implement designer **902** in computer system **906** in **Figure 9**.

In this illustrative example, data processing system **1400** may include communications framework **1402**, which provides communications between processor unit **1404**, memory **1406**, persistent storage **1408**, communications unit **1410**, input/output

unit **1412**, and display **1414**. In this example, communication framework may take the form of a bus system.

Processor unit **1404** serves to execute instructions for software that may be loaded into memory **1406**. Processor unit **1404** may be a number of processors, a multi-processor core, or some other type of processor, depending on the particular implementation.

Memory **1406** and persistent storage **1408** may be examples of storage devices **1416**. A storage device may be any piece of hardware that may be capable of storing information, such as, for example, without limitation, data, program code in functional form, and/or other suitable information either on a temporary basis and/or a permanent basis. Storage devices **1416** may also be referred to as computer readable storage devices in these illustrative examples. Memory **1406**, in these examples, may be, for example, a random access memory or any other suitable volatile or non-volatile storage device. Persistent storage **1408** may take various forms, depending on the particular implementation.

For example, persistent storage **1408** may contain one or more components or devices. For example, persistent storage **1408** may be a hard drive, a flash memory, a rewritable optical disk, a rewritable magnetic tape, or some combination of the above. The media used by persistent storage **1408** also may be removable. For example, a removable hard drive may be used for persistent storage **1408**.

Communications unit **1410**, in these illustrative examples, provides for communications with other data processing systems or devices. In these illustrative examples, communications unit **1410** may be a network interface card.

Input/output unit **1412** allows for input and output of data with other devices that may be connected to data processing

system **1400**. For example, input/output unit **1412** may provide a connection for user input through a keyboard, a mouse, and/or some other suitable input device. Further, input/output unit **1412** may send output to a printer. Display **1414** provides a mechanism to display information to a user.

Instructions for the operating system, applications, and/or programs may be located in storage devices **1416**, which may be in communication with processor unit **1404** through communications framework **1402**. The processes of the different embodiments may be performed by processor unit **1404** using computer-implemented instructions, which may be located in a memory, such as memory **1406**.

These instructions may be referred to as program code, computer usable program code, or computer readable program code that may be read and executed by a processor in processor unit **1404**. The program code in the different embodiments may be embodied on different physical or computer readable storage media, such as memory **1406** or persistent storage **1408**.

Program code **1418** may be located in a functional form on computer readable media **1420** that may be selectively removable and may be loaded onto or transferred to data processing system **1400** for execution by processor unit **1404**. Program code **1418** and computer readable media **1420** form computer program product **1422** in these illustrative examples. In one example, computer readable media **1420** may be computer readable storage media **1424** or computer readable signal media **1426**.

In these illustrative examples, computer readable storage media **1424 may be** a physical or tangible storage device used to store program code **1418** rather than a medium that propagates or transmits program code **1418**.

Alternatively, program code **1418** may be transferred to data processing system **1400** using computer readable signal media

1426. Computer readable signal media **1426** may be, for example, a propagated data signal containing program code **1418**. For example, computer readable signal media **1426** may be an electromagnetic signal, an optical signal, and/or any other suitable type of signal. These signals may be transmitted over communications links, such as wireless communications links, optical fiber cable, coaxial cable, a wire, and/or any other suitable type of communications link.

The different components illustrated for data processing system **1400** are not meant to provide architectural limitations to the manner in which different embodiments may be implemented. The different illustrative embodiments may be implemented in a data processing system including components in addition to and/or in place of those illustrated for data processing system **1400**. Other components shown in **Figure 14** can be varied from the illustrative examples shown. The different embodiments may be implemented using any hardware device or system capable of running program code **1418**.

Thus, the illustrative embodiments provide a method and apparatus for shaping stacks of composite layers into desired shapes. The illustrative embodiments may increase the lifespan of flexible sheets that may be used to apply vacuum loads to stacks of composite layers. The illustrative embodiments use compressible supports that may reduce the amount of stretching that occurs when a vacuum load may be applied to a flexible sheet in shaping a stack of composite layers. In this manner, the cost of manufacturing composite parts and, in particular, maintenance for shape forming machines may be reduced using one or more illustrative embodiments.

The description of the different illustrative embodiments may have been presented for purposes of illustration and description, and may be not intended to be exhaustive or limited

to the embodiments in the form disclosed. Many modifications and variations will be apparent to those of ordinary skill in the art.

For example, although the illustrative examples for an illustrative embodiment are described with respect to an aircraft, an illustrative embodiment may be applied to other types of objects. The object may be, for example, without limitation, a mobile object, a stationary object, a land-based structure, an aquatic-based structure, and a space-based structure. More specifically, the platform, may be a surface ship, a tank, a personnel carrier, a train, a spacecraft, a space station, a satellite, a submarine, an automobile, a power plant, a bridge, a dam, a house, a manufacturing facility, a building, and other suitable objects.

Further, different illustrative embodiments may provide different features as compared to other illustrative embodiments. The embodiment or embodiments selected may be chosen and described in order to best explain the principles of the embodiments, the practical application, and to enable others of ordinary skill in the art to understand the disclosure for various embodiments with various modifications as may be suited to the particular use contemplated.

CLAIMS:

What is claimed is:

1. A method for forming a stack of composite layers (102) into a desired shape (600), the method comprising:

positioning the stack of composite layers (102) on a tool (106) and a number of compressible supports (108) such that the stack of composite layers (102) is substantially flat on the tool (106) and the stack of composite layers (102) is substantially flat on the number of compressible supports (108);

placing a flexible sheet (116) on top of the stack of composite layers (102); and

applying a vacuum load on the stack of composite layers (102) on the tool (106) and the number of compressible supports (108) using the flexible sheet (116) such that consolidation of the stack of composite layers (102) occurs to form the desired shape (600) on the tool (106) and the number of compressible supports (108) compress during forming of the desired shape (600).

2. The method of claim 1 further comprising:

heating the stack of composite layers (102) prior to applying the vacuum load.

3. The method of either claim 1 or claim 2, wherein the positioning step comprises:

positioning the stack of composite layers (102) on the tool (106) and the number of compressible supports (108), wherein a number of locations of the number of compressible supports (108) is configured to support a number of edges of the stack of composite layers (102).

4. The method of any preceding claim, wherein the number of locations of a number of compressible layers (812) supports the number of edges of the stack of composite layers (102) such that the stack of composite layers (102) remains substantially flat when heated prior to applying the vacuum load.

5. The method of any preceding claim, wherein the applying step comprises:

drawing a vacuum on the flexible sheet (116) such that the flexible sheet (116) applies the vacuum load on the stack of composite layers (102), the number of compressible supports (108), and the tool (106).

6. The method of claim 5, wherein a life of the flexible sheet (116) is increased using the number of compressible supports (108).

7. The method of claim 5, wherein placing the flexible sheet (116) on top of the stack of composite layers (102) comprises:

lowering a frame (114) holding the flexible sheet (116) onto a platform (112) on which the stack of composite layers (102) is located with the tool (106) and the number of compressible supports (108) such that a seal is formed between the frame (114) and the platform (112) in which the seal is sufficient to apply a vacuum to cause the flexible sheet (116) to apply the vacuum load on the stack of composite layers (102).

8. The method of claim 5, wherein the flexible sheet (116) is comprised of silicon.

9. The method of any preceding claim further comprising:

removing the stack of composite layers (102) with the desired shape (600) from the tool (106);

moving the stack of composite layers (102) to a curing system; and

curing the stack of composite layers (102) to form a composite part (912) with the desired shape (600).

10. The method of any preceding claim further comprising:

curing the stack of composite layers (102) with the desired shape (600) to form a part.

11. The method of any preceding claim, wherein the number of compressible supports (108) is comprised of a number of components (914) selected from at least one of a foam, a polymer foam, an open cell foam, a closed cell foam, and a solid dispersed medium.

12. The method of any preceding claim, wherein the stack of composite layers (102) is a prepreg (128).

13. The method of claim 12, wherein the prepreg (128) comprises fabric layers with a thermoset resin infused into the fabric layers.

14. The method of any preceding claim, wherein the desired shape (600) includes a channel with walls.

15. The method of any preceding claim, wherein the desired shape (600) is a shape for a part selected from one of a stringer, a beam, and a rail.

16. An apparatus comprising:

a platform (112) configured to receive a tool (106);

a number of compressible supports (108) configured to be placed on the platform (112) in a number of locations such that a stack of composite layers (102) positioned on the tool (106) and the number of compressible supports (108) is substantially flat on the tool (106) and the stack of composite layers (102) is substantially flat on the number of compressible supports (108); and

a flexible sheet (116) configured to be placed on top of the stack of composite layers (102) such that a vacuum drawn on the flexible sheet (116) results in the flexible sheet (116) applying a vacuum load on the stack of composite layers (102) on the tool (106) and the number of compressible supports (108) such that the stack of composite layers (102) forms a desired shape (600) on the tool (106) and the number of compressible supports (108) compress during forming of the desired shape (600).

17. The apparatus of claim 16, wherein the number of locations of the number of compressible supports (108) is configured to support a number of edges of the stack of composite layers (102) such that the stack of composite layers (102) remains substantially flat when heated prior to applying the vacuum load.

18. The apparatus of either claim 16 or claim 17 further comprising:

a frame (114) holding the flexible sheet (116), wherein the frame (114) with the flexible sheet (116) forms a seal with the platform (112) when the frame (114) with the flexible sheet (116) is placed on the platform (112) on top of the stack of composite layers (102) on the tool (106) and the number of

compressible supports (108) on the platform (112).

19. The apparatus of any of claims 16 to 18, wherein the number of compressible supports (108) is comprised of a number of components (914) selected from at least one of a foam, a polymer foam, an open cell foam, a closed cell foam, and a solid dispersed medium.

20. The apparatus of any of claims 16 to 19, wherein the stack of composite layers (102) is a prepreg (128).

21. A method for forming a stack of composite layers (102) into a desired shape (600) for an aircraft part, the method comprising:

positioning the stack of composite layers (102) on a tool (106) and a number of compressible supports (108) in which a number of locations of the number of compressible supports (108) is configured to support a number of edges of the stack of composite layers (102) in which the number of locations of a number of compressible layers (812) supports the number of edges of the stack of composite layers (102) such that the stack of composite layers (102) remains substantially flat when heated prior to applying a vacuum load; in which the number of compressible supports (108) is comprised of a number of components (914) selected from at least one of a foam, a polymer foam, an open cell foam, a closed cell foam, and a solid dispersed medium; and in which the stack of composite layers (102) is a prepreg (128) comprised of fabric layers with a thermoset resin infused into the fabric layers;

applying a vacuum load on the stack of composite layers (102) on the tool (106) and the number of compressible supports (108) such that the stack of composite layers (102) forms the

desired shape (600) on the tool (106) and the number of compressible supports (108) compress during forming of the desired shape (600) by:

lowering a frame (114) holding a flexible sheet (116) comprised of silicon onto a platform (112) on which the stack of composite layers (102) is located with the tool (106) and the number of compressible supports (108) such that a seal is formed between the frame (114) and the platform (112) in which the seal is sufficient to apply a vacuum to cause the flexible sheet (116) to apply the vacuum load on the stack of composite layers (102); and

drawing the vacuum on the flexible sheet (116) such that the flexible sheet (116) applies the vacuum load on the stack of composite layers (102), the number of compressible supports (108), and the tool (106);

heating the stack of composite layers (102) prior to applying the vacuum load;

removing the stack of composite layers (102) with the desired shape (600) from the tool (106);

moving the stack of composite layers (102) to a curing system; and

curing the stack of composite layers (102) to form the aircraft part with the desired shape (600) in which the desired shape (600) is selected from one of a channel with walls and a shape for a part selected from one of a stringer, a beam, and a rail in which a life of the flexible sheet (116) is increased using the number of compressible supports (108).

22. A shape forming system (100) for manufacturing an aircraft part, the shape forming system (100) comprising:

a platform (112) configured to receive a tool (106);

a number of compressible supports (108) configured to be placed on the platform (112) in a number of locations such that a stack of composite layers (102) positioned on the tool (106) and the number of compressible supports (108) is substantially flat on the tool (106) and the stack of composite layers (102) is substantially flat on the number of compressible supports (108) in which the number of locations of the number of compressible supports (108) is configured to support a number of edges of the stack of composite layers (102) such that the stack of composite layers (102) remains substantially flat when heated prior to applying a vacuum load; in which the number of compressible supports (108) is comprised of a number of components (914) selected from at least one of a foam, a polymer foam, an open cell foam, a closed cell foam, and a solid dispersed medium; and in which the stack of composite layers (102) is a prepreg (128);

a flexible sheet (116) configured to be placed on top of the stack of composite layers (102) such that a vacuum drawn on the flexible sheet (116) results in the flexible sheet (116) applying the vacuum load on the stack of composite layers (102) on the tool (106) and the number of compressible supports (108) such that the stack of composite layers (102) forms a desired shape (600) for the aircraft part on the tool (106) and the number of compressible supports (108) compress during forming of the desired shape (600); and

a frame (114) holding the flexible sheet (116) in which the frame (114) with the flexible sheet (116) forms a seal with the platform (112) when the frame (114) with the flexible sheet (116) is placed on the platform (112) on top of the stack of composite layers (102) on the tool (106) and the number of compressible supports (108) on the platform (112) in which a life of the flexible sheet (116) is increased using the number of compressible supports (108).

1/11




FIG. 1




FIG. 2




FIG. 3




FIG. 4







FIG. 5




6/11



7/11

FIG. 9



8/11




FIG. 10

9/11







FIG. 11

10/11



11/11



INTERNATIONAL SEARCH REPORT

International application No
PCT/US2013/059834A. CLASSIFICATION OF SUBJECT MATTER
INV. B29C70/34 B29C33/38
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
B29C B29D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2011/097554 A1 (KEHRL DAVID J [US] ET AL) 28 April 2011 (2011-04-28) paragraph [0069] - paragraph [0072]; figures 13-17	1-22
A	WO 96/19335 A1 (BOEING CO [US]) 27 June 1996 (1996-06-27) abstract; figure 1	1-22



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

7 January 2014

Date of mailing of the international search report

15/01/2014

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Pierre, Nathalie

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2013/059834

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2011097554	A1	28-04-2011	CA 2732391 A1 10-11-2011
			CN 102241275 A 16-11-2011
			EP 2386483 A2 16-11-2011
			JP 2011251677 A 15-12-2011
			US 2011097554 A1 28-04-2011
			US 2013084434 A1 04-04-2013

WO 9619335	A1	27-06-1996	AU 1440795 A 10-07-1996
			CA 2208036 A1 27-06-1996
			DE 69429118 D1 20-12-2001
			DE 69429118 T2 21-03-2002
			EP 0799123 A1 08-10-1997
			JP 3960621 B2 15-08-2007
			JP H10510773 A 20-10-1998
			WO 9619335 A1 27-06-1996
