



- (51) International Patent Classification:
B29C 35/00 (2006.01)
- (21) International Application Number:
PCT/US2012/048832
- (22) International Filing Date:
30 July 2012 (30.07.2012)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
61/574,151 28 July 2011 (28.07.2011) US
- (71) Applicant (for all designated States except US): **PLASAN CARBON COMPOSITES, INC.** [US/US]; 139 Shields Drive, Bennington, VT 05201 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **MURCH, Robert, W.** [US/US]; 545 Hampton Ct, Wixom, MI 48393 (US). **LOWNSDALE, Gary, R.** [US/US]; 417 Shawnee Place, Loudon, TN 37774 (US). **BARTOLOTTI, Douglas, L.** [US/US]; 2641 Jefferson Dr. Se, Grand Rapids, MI 49507 (US).
- (74) Agents: **FRANCIS, Christopher, M.** et al.; Howard & Howard Attorneys Pllc, 450 West Fourth Street, Royal Oak, MI 48067 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— of inventorship (Rule 4.17(iv))

Published:

— with international search report (Art. 21(3))

[Continued on next page]

(54) Title: THERMAL SYSTEM AND METHOD FOR RAPIDLY FORMING COMPOSITE ARTICLES




FIG. 18

(57) Abstract: A thermal system (20) for rapidly heating and cooling a mold surface (24) of a tool (26) comprises a heater-subsystem (40) in fluid communication with the tool (26). The heater- subsystem (40) comprises a heater (42), a tank (44), and a three-way valve (46). The tank (44) contains a mass of heated thermal fluid. The system (20) further comprises an exchanger- subsystem (49) in fluid communication with the heater- sub system (40) and the tool (26). The exchanger-subsystem (49) comprises an exchanger (51) and a three-way valve (53). The system (20) further comprises a chiller- sub system (48) in fluid communication with the exchanger- subsystem (49). The chiller-subsystem (48) comprises a chiller (50), a tank (52), and a three-way valve (54). The tank (52) contains a mass of cooled thermal fluid. A controller (56) can be used to control and/or instruct the subsystems (40,48,49). The system (20) and tool (26) can be used for forming a composite article (22), such as a carbon fiber composite (CFC) article (22). A method utilizing the system (20) is also provided.

WO 2013/016728 A1

- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))*

THERMAL SYSTEM AND METHOD FOR RAPIDLY FORMING COMPOSITE ARTICLES**CROSS REFERENCE TO RELATED APPLICATIONS**

[0001] This application claims the benefit of U.S. Provisional Patent Application Serial No. 61/574,151, filed on July 28, 2011 and entitled "SYSTEM FOR FORMING COMPOSITE ARTICLES", which is incorporated herein by reference in its entirety.

FIELD OF THE INVENTION

[0002] The present invention generally relates to a system and method for forming composite articles, and more specifically to a thermal system and method for forming carbon fiber composite articles.

DESCRIPTION OF THE RELATED ART

[0003] Carbon fiber composite (CFC) articles typically comprise two or more layers of a carbon fiber mat comprising carbon fiber filaments, which are impregnated by a plastic resin, in a final cured state. Conventional methods for forming CFC articles include vacuum bag molding, pressure molding, Virtual Engineered Composites (VEC) molding, autoclave molding, and resin transfer molding (RTM). Newer automotive industry regulations, including the Corporate Average Fuel Economy (CAFE), Head Impact Characteristic (HIC), and Pedestrian Protection, represent a challenge to conventional materials used in automobiles, such as steel. Relative to steel, CFC articles include an excellent combination of physical properties including strength, weight, and energy absorption. As such, CFC articles are able to meet these newer requirements, such as requirements for mass reduction and energy absorption.

[0004] Unfortunately, a major issue with conventional CFC articles is the amount of time it takes to manufacture CFC articles relative to conventional articles, such as those made out of steel. In addition, it can be time consuming and difficult to achieve CFC articles with aesthetically pleasing surfaces, such as "Class A" surfaces. As such, there remains an opportunity to provide improved methods and systems for forming CFC articles.

SUMMARY OF THE INVENTION AND ADVANTAGES

[0005] The present invention provides a thermal system for rapidly heating and cooling a mold surface of a tool. The thermal system comprises a heater-subsystem in fluid communication with the tool. The heater-subsystem comprises a heater for heating a first thermal fluid, a tank in fluid communication with the heater and containing a mass of heated first thermal fluid, and a three-way valve. The three-way valve is in fluid communication i) between the tank and the heater for re-circulating the first thermal fluid from the tank to the heater and ii) between the tank and the tool for directing the first thermal fluid from the tank to the tool. The thermal system further

comprises an exchanger-subsystem in fluid communication with the heater-subsystem and the tool. The exchanger-subsystem comprises an exchanger for cooling the first thermal fluid returning from the tool, and a three-way valve. The three-way valve is in fluid communication i) between the exchanger and the heater-subsystem for sending the first thermal fluid from the tool back to the heater-subsystem and ii) between the exchanger and the tool for directing the first thermal fluid from the tool to the exchanger. The thermal system further comprises a chiller-subsystem in fluid communication with the exchanger-subsystem. The chiller-subsystem comprises a chiller to cool a second thermal fluid, a tank in fluid communication with the chiller and containing a mass of cooled second thermal fluid, and a three-way valve. The three-way valve is in fluid communication i) between the tank and the chiller for re-circulating the second thermal fluid from the tank to the chiller and ii) between the tank and the exchanger-subsystem for directing the second thermal fluid from the tank to the exchanger. The tool can be used for forming a composite article, such as a carbon fiber composite article.

[0006] The present invention also provides a method of rapidly heating and cooling the mold surface of the tool. The method comprises the steps of providing the heater-subsystem, providing the exchanger-subsystem, providing the chiller-subsystem, and providing a controller. The controller is in communication with the tool and the subsystems for instructing the subsystems. The method further comprises the step of directing the mass of heated first thermal fluid from the tank of the heater-subsystem to the tool via the controller to heat the mold surface of the tool from a first temperature (T_1) to a second temperature (T_2) within a first period of time (T_{t1}). The method further comprises the step of directing the mass of heated first thermal fluid from the tank of the heater-subsystem to the mold surface of the tool via the controller to maintain the mold surface at T_2 for a second period of time (T_{t2}). The method further comprises the step of directing the mass of cooled second thermal fluid from the tank of the chiller-subsystem to the exchanger-subsystem via the controller to cool the first thermal fluid returning from the tool from T_2 to a third temperature (T_3) within a third period of time (T_{t3}). The mold surface of the tool heats at a rate of greater than about 60°F (~33°C) per minute and cools at a rate of greater than about 40°F (~22°C) per minute. $T_{t1} + T_{t2} + T_{t3}$ is no greater than about 20 minutes.

[0007] The present invention provides various benefits over conventional systems and methods for forming composite articles. For example, conventional methods, such as autoclaving, generally have cycle times that are well over an hour, typically cycle times of 75

minutes or longer. Such cycle times are the times in which the composite articles are formed within the autoclave (e.g. during cure of a resin).

[0008] In a typical autoclave process, preforms are disposed on tools, the tools are loaded into the autoclave, vacuum bags (or other vacuum means) are attached to the tools, the autoclave is closed, vacuum is applied, and the autoclave is heated and pressurized with nitrogen gas (N₂) for an extended period of time, e.g. 75+ minutes, to form the composite articles. N₂ is generally required to prevent flash fires in the autoclave due to exotherms. Additional time associated with loading, closing, opening, and unloading the autoclave further decreases output.

[0009] The autoclave takes a long time to heat and requires the use of N₂ for safety reasons. As such, energy costs associated with the autoclave tends to be high. In order to increase output of composite articles, autoclaves tend to be large in size, thereby having a large footprint. Such sizing of the autoclave also requires a large number of heavy and expensive tools, further adding to capital and manufacturing costs.

[0010] Autoclaves are also prone to making scrap parts. For example, if vacuum fails (or is interrupted) on one (or more) of the tools while in the autoclave, the composite article will cure in an improper configuration, e.g. a non-consolidated form. The vacuum cannot be reestablished until after the cure cycle is complete, which is too late to save the composite article. As such, the composite article(s) with vacuum problems must be scrapped after being removed from the autoclave.

[0011] Composite articles formed in autoclaves also tend to suffer from surfaces blemishes, such as pits of various location, diameter and depth. Such surface blemishes must be removed during finishing steps of the composite article, such as by filling and sanding, further adding to manufacturing costs.

[0012] The thermal system and method of the present invention provide one or more benefits over the prior art. The present invention provides for excellent temperature control relative to conventional autoclaving systems and methods. The present invention can provide reduced cycle times relative to autoclave cycles, which provides for increased output. Reduced energy costs may also be appreciated. A reduced footprint may be provided by the thermal system relative to large autoclaves. The same or similar chemistries and/or materials generally used for conventional autoclave methods, e.g. resins, may generally be used with the present invention, therefore not requiring chemistry or material redesign.

[0013] The present invention generally provides composite articles which have excellent surface properties that generally match those of carbon composite articles formed in an

autoclave. For example, surface blemishes (e.g. pits) are generally reduced in number and/or severity. In addition or alternatively, the present invention generally provides composite articles which have excellent mechanical properties that match or exceed those of carbon composite articles formed in an autoclave.

5

BRIEF DESCRIPTION OF THE DRAWINGS

[0014] Other advantages of the present invention will be readily appreciated, as the same becomes better understood by reference to the following detailed description when considered in connection with the accompanying drawings wherein:

10 [0015] Figure 1 is a schematic view of a thermal system having a heater-subsystem, a valve, a controller, a press, a tool disposed within the press, and a pressure tank;

[0016] Figure 2 is a schematic view of another embodiment of the thermal system having a heater-subsystem, a chiller-subsystem, valves, the controller, the press, the tool disposed within the press, and the pressure tank;

15 [0017] Figure 3 is a partially exploded perspective view of the tool, a vacuum canopy, and a preform of a composite article disposed between the tool and vacuum canopy;

[0018] Figure 4 is a cross-sectional end-view of the tool having a mold surface and tubing, the vacuum canopy attached to the tool, and the preform of the composite article disposed between the mold surface and vacuum canopy;

20 [0019] Figure 5 is a perspective view of a support table, the tool disposed on the support table, the vacuum canopy disposed on the tool, and the press having a platform and a cover;

[0020] Figure 6 is an enlarged perspective view detailing portions of the press and tool illustrated in Figure 5, with the press including a carrier and rams for moving the tool in and out of the press;

25 [0021] Figure 7 is a partial cross-sectional end-view of the press having a cavity defined between the platform and the cover, the tool having the mold surface and tubing, the vacuum canopy attached to the tool, and the preform of the composite article disposed between the mold surface and vacuum canopy;

30 [0022] Figure 8 is a perspective simplified environmental view of another embodiment of the press, support tables, and composite articles, with technicians disposing a preform of the composite article on a mold surface of the tool disposed on one of the support tables;

[0023] Figure 9 is a cross-sectional side-view of a mandrel having a mandrel surface and tubing, with pieces of a carbon fiber sheet being disposed on the mandrel surface, and a vacuum sheet being disposed over the pieces on the mandrel surface;

[0024] Figure 10 is a flow chart generally illustrating additional, optional, manufacturing steps for forming the composite article;

[0025] Figure 11 is a graph illustrating temperature, pressure, vacuum and heater profiles over time for an invention example of the composite article using the thermal system and press;

5 [0026] Figure 12 is another graph illustrating temperature, pressure, and vacuum profiles over time for another invention example of the composite article using the thermal system and press;

[0027] Figure 13 is another graph illustrating temperature, pressure, and vacuum profiles over time for another invention example of the composite article using the thermal system and press;

10 [0028] Figure 14 is a graph illustrating temperature, pressure, vacuum and heater profiles over time for a comparative example of a composite article using a conventional autoclave;

[0029] Figure 15 is a perspective view of a tool-connection system operatively connected to the tool, with the tool-connection system including connections for feed and return of thermal fluid to and from the tubing of the tool, connections for a vacuum and static line for pressure monitoring, and a connection for a resistive thermal device (RTD) for temperature monitoring and providing feedback;

15 [0030] Figure 16 is a perspective view of a press-connection system operatively connected to the cover of the press for coupling with the tool-connection system shown in Figure 15, with the press-connection system including connections for feed and return of thermal fluid through the cover of the press and to and from the tubing of the tool, connections for a vacuum and static line for pressure monitoring, and a connection for a RTD for temperature monitoring and providing feedback;

20 [0031] Figure 17 is a partial cross-sectional side-view of the press having the cavity defined between the platform and the cover, with the tool-connection system and the press-connection system coupled together such that thermal fluid can be communicated to and from the tool with the thermal system; and

[0032] Figure 18 is a schematic view of another embodiment of the thermal system having a heater-subsystem, a chiller-subsystem, an exchanger-subsystem, valves, the controller, the press, the tool disposed within the press, and the pressure tank.

DETAILED DESCRIPTION OF THE INVENTION

30 [0033] Referring to the Figures, wherein like numerals indicate like parts throughout the several views, a thermal system is generally shown at **20**. The thermal system **20** is hereinafter simply referred to as the system **20**. The system **20** can be used for forming various types of articles. The system **20** is useful for forming composite articles **22**, such as carbon fiber

reinforced plastics **22** or carbon fiber composite (CFC) articles **22**. CFC articles **22** are useful in many industries, such as in the automotive, marine, military defense, aeronautical, aerospace, and medical equipment industries.

5 **[0034]** The system **20** is especially useful for forming “Class A” CFC body panels **22** across entire vehicle platforms. Examples of body panels **22** and related parts include hoods, fenders, roofs, rockers, splitters, roof bows, dive planes, wings, mirror caps, deflectors, etc. Further examples of CFC articles **22** include deck-lids, battery applications, control arms, bumpers, cradles/sub-frames, and other structural components. The system **20** is not limited to forming any particular type of composite article **22**, or composite articles **22** for a particular industry, and
10 such composite articles **22** can be of various sizes, shapes, and use. The composite articles **22** are described further below.

[0035] The system **20** is useful for heating and cooling a mold surface **24** of a tool **26**. Specifically, the system **20** is useful for heating and cooling a fluid, with the fluid used for directly (or nearly directly) heating and cooling the mold surface **24** of the tool **26**. The system
15 **20** can be used in combination with or separate from the methods of the present invention. The invention methods are described further below, and can be used in combination with or separate from the system **20**.

[0036] The tool **26** can be a portion of a mold (e.g. a two-piece mold) where the tool **26** is a top mold and another tool is a bottom mold, or vice versa. The tool **26** is typically a one-piece
20 mold **26** (e.g. an open mold). The system **20** is generally associated with at least one type of the tool **26**, but may be associated with two or more different types of tools **26**, which can be the same as or different from each other. The tool **26** can be of various types, albeit possibly being modified for communicating with the system **20**.

[0037] In certain embodiments, the tool **26** is of the type (or similar to the type) generally used
25 in conventional autoclaves. However, the system **20** is not typically associated with an autoclave. In other words, the system **20** is generally free of an autoclave, as are the invention methods. In one embodiment, the tool **26** is of the type generally used for vacuum molding (or forming). In another embodiment, the tool **26** is of the type generally used for resin transfer molding (RTM). It is to be appreciated that other types of tools **26** can also be used.

30 **[0038]** The mold surface **24** and the tool **26** may be unitary, i.e., a single body. In certain embodiments, the mold surface **24** and the tool **26** are separate pieces joined together, e.g. by fasteners, by welding, etc. As such, different mold surfaces **24** may be used with different tools

26 or vice versa. This allows for interchangeability between different mold surfaces **24** and/or different tools **26** for forming different types of composite articles **22**.

[0039] The mold surface **24** of the tool **26** can be configured to have various shapes. Typically, the mold surface **24** is configured in a shape corresponding to a particular composite article **22** being made, e.g. a hood, a fender, a spoiler, etc. The mold surface **24** is not limited to any particular shape.

[0040] The mold surface **24** of the tool **26** is typically formed from a metallic material, which is useful for heat transfer, such as nickel, steel, etc. In certain embodiments, the mold surface **24** comprises a nickel alloy. **22**. In these embodiments, the mold surface **24** is generally rigid and inflexible (which is different from a rubber or “bladder” type mold surface). Metallic mold surfaces **24** generally have a high thermal conductivity, which allows for rapid heating and cooling of the mold surface **24**. This is especially true when utilized along with the system **20**. The mold surface **24** can be of various thicknesses, typically of from about 5 to about 20, from about 7.5 to about 15, or from about 10 to about 12.5, mm. Suitable mold surfaces **24** are commercially available from a variety of suppliers. Specific examples of mold surfaces **24** include those commercially available from Weber Manufacturing Team of Midland, Ontario, Canada, such as nickel shell mold surfaces **24**; Visioneering Inc. of Fraser, MI; and Models & Tools Inc. of Troy, MI, such as mold surfaces **24** formed from Invar (or “64FeNi”).

[0041] Referring to Figure 4, the tool **26** typically includes tubing **28** for communicating the fluid. The tubing **28** includes at least one input **30** for communicating fluid to the tubing **28** and at least one outlet **32** for communicating fluid from the tubing **28**. The tubing **28** is proximal or directly in contact with the mold surface **24** to expedite heat transfer between the tubing **28** and the mold surface **24**. The tubing **28** is useful for direct (rather than indirect) heating or cooling of the mold surface **24**. The tubing **28** may be formed into the tool **26** itself (such as by boring within the tool **26**), or attached within the tool **26** proximal the mold surface **24**, either to the tool **26** and/or to the mold surface **24**. The tubing **28** can be attached (e.g. to the mold surface **24**) in various fashions, such as by welding, fasteners, etc.

[0042] The tubing **28** can be arranged in various patterns and may be of equal or varying diameters. For example, if the mold surface **24** is complex in shape, a portion of the tubing **28** can be concentrated in more critical areas of the mold surface **24** to ensure proper heating and cooling of those areas. As alluded to above, the mold surface **24** may be of various configurations, and can be substantially planar, three-dimensional, or a combination of shapes. The tubing **28** can be configured likewise to provide for direct heating of the mold surface **24**.

The tool **26** may have one or more fasteners **34**, e.g. clamps **34**, for attaching a vacuum canopy **36** to the tool **26**. Various types of fasteners **34** may be employed. The vacuum canopy **36** is described further below. In other embodiments, a conventional vacuum bag (not shown) can be utilized.

5 [0043] The tubing **28** of the tool **26** is connected to piping **38** of the system **20** for communicating the fluid to and from the tool **26** and to and from the system **20** for heating and cooling the mold surface **24**. Various types of piping **38** can be employed. The piping **38** should be capable of handling the temperatures and pressures present in the system **20**. The piping **38** can be of various diameters. For example, the piping **38** can have a diameter of from about 0.5 to
10 about 4, about 0.75 to about 3, about 1 to about 2, or about 2, inches (or about 1.3 to about 10, about 1.9 to about 7.6, about 2.5 to about 5, or about 5, cm), outer diameter (OD).

[0044] The tubing **28** may have more than one input **30** and output **32**. For example, there may be two or more sets of discrete tubing **28** arrangements within the tool **26** for better control of heating and cooling of the mold surface **24**. Suitable tools **26** are commercially available from a
15 variety of suppliers. Specific examples of tools **26** include those commercially available from Weber Manufacturing Team, such as nickel shell tooling.

[0045] The fluid carried within the system **20** is typically a heat transfer fluid, which may also be referred to as a thermal fluid. Various types of fluids can be employed. Typically, the fluid used within at least the tool **26** is an oil, e.g. thermal oil, (rather than water) due to the
20 temperatures reached in the system **20**. Water may be used elsewhere in the system **20**, and combinations of thermal oil and water may be used in certain embodiments. Suitable fluids are commercially available from a variety of suppliers. Specific examples of fluids include those commercially available from Mokon of Buffalo, NY, including DELF450 and DELF600. Further examples of fluids include those commercially available from Multitherm of Malvern,
25 PA, including PG-1 and IG-4; from Paratherm Corp. of West Conshohocken, PA, including NF and HE; from Petro-Canada Products, including Calflo™ FG and Calflo™ HTF; from Solutia Inc. of St. Louis, MO, including Therminol® 66; and from Duratherm of Lewiston, NY, including Duratherm 450, Duratherm 600, and Duratherm Lite (or LT). The fluid should be capable of handling the temperatures of the system **20**, and may include a blend of two or more
30 different fluids. Typically, the system **20** is closed-loop; however, at times, the system **20** may have some amount of fluid added thereto or withdrawn therefrom.

[0046] Referring to Figure 1, which illustrates one embodiment of the system **20**, the system **20** comprises a heater-subsystem **40**. The heater-subsystem **40** is in fluid communication with

the tool **26**. The heater-subsystem **40** is useful for heating the mold surface **24** of the tool **26**. In certain embodiments, the heater-subsystem **40** can also be used for cooling the mold surface **24** of the tool **26**.

[0047] The heater-subsystem **40** comprises a heater **42**. The heater **42** is useful for heating the fluid within the system **20**. Various types of heaters **42** can be employed. The heater **42** should be capable of heating the fluid to temperatures of at least about 3°F (~ -16°C) to about 350°F (~177°C), or upwards of about 600°F (~315°C) to about 650°F (~343°C). Generally, the hotter the fluid coming into the tool **26**, the quicker the mold surface **24** heats. The heater **42** should also be capable of delivering various outputs of the fluid. Examples of suitable outputs are from about 10 to about 120, from about 20 to about 100, from about 40 to about 90, or about 60, gallons per minute (gpm) (or about 38 to about 454, about 76 to about 379, about 151 to about 341, or about 227, liters per minute). Suitable heaters **42** are commercially available from a variety of suppliers. Specific examples of heaters **42** include those commercially available from Mokon, including the HTF Series, e.g. the HTF 500 Series, the HTF 600 Series, the HTF HF-2 Series, and the ST Series, heaters. Gas fired heaters, such as those commercially available from Fulton Boiler Works, Inc. of Pulaski, New York, can also be used, e.g. a Fulton FT-0320-C Thermal Fluid Heater. As used herein, a tilde character (~) is meant to represent an approximation based, for example, on unit conversion from US to SI units.

[0048] The heater-subsystem **40** further comprises a tank **44**. The tank **44** of the heater-subsystem **40** is useful for containing a mass of heated fluid. The tank **44** of the heater-subsystem **40** serves as a heat buffer in the system **20**, as described further below. The tank **44** of the heater-subsystem **40** is in fluid communication with the heater **42**. Various types of tanks can be employed as the tank **44** of the heater-subsystem **40**. The tank **44** of the heater-subsystem **40** should be capable of holding fluid at temperatures of at least about 300°F (~157°C) to about 350°F (~177°C), and upwards of about 600°F (~315°C) to about 650°F (~343°C). Typically, the tank **44** of the heater-subsystem **40** should be rated for more than the highest temperature output of the heater **42**. In certain embodiments, the heater-subsystem **40** comprises two or more tanks (not shown). For example, the mass of fluid contained in one tank **44** may be at a different temperature than that of another tank **44**. This may be useful for buffering the system **20** with masses of heated fluid at different temperatures. The tank **44** is typically separate from the heater **42**, i.e., the tank **44** is distinguishable from an “internal” tank of the heater **42**, if present.

[0049] Generally, the tank **44** of the heater-subsystem **40** is insulated, either itself, and/or with a supplemental layer of insulation, to prevent cooling of the mass of heated fluid contained

therein by the ambient environment. Various types of insulation means can be employed. For example, the tank **44** of the heater-subsystem **40** can be wrapped with an insulated jacket. Piping **38** of the system **20**, or portions thereof, should also be wrapped or covered for purposes of insulation and safety. For example, the piping **38** running from the heater-subsystem **40** to the tool **26** can be insulated to prevent heat loss, burns, fires, etc.

[0050] The tank **44** of the heater-subsystem **40** can be of various sizes and shapes. It may be useful to reduce the surface area to volume ratio (SA:V) of the tank **44** of the heater-subsystem **40** to reduce heat loss; however, this is not required. The tank **44** of the heater-subsystem **40** should be sized to hold of from about 50 to about 250, from about 100 to about 225, from about 100 to about 200, or from about 100 to about 150, gallons of the fluid (or about 189 to about 946, from about 378 to about 852, from about 378 to about 757, or from about 378 to about 568, liters of the fluid). Generally, a larger size tank **44** provides for a greater heat buffer in the system **20**. Reference to the mass of heated fluid associated with the tank **44** of the heater-subsystem **40** may refer to a portion to an entirety of the heated fluid contained within the tank **44** at a given instance. The masses of fluid described herein may also be referred to as stored (thermal) energy masses.

[0051] The heater-subsystem **40** further comprises a valve **46** in fluid communication between the tank **44** of the heater-subsystem **40** and the heater **42**. Various types of valves **46** can be employed. Typically, the valve **46** is a three-way valve **46**. The three-way valve **46** of the heater-subsystem **40** is useful for re-circulating the fluid between the tank **44** of the heater-subsystem **40** and the heater **42**. This arrangement is useful for initially forming, maintaining, and/or recharging the mass of heated fluid in the tank **44** of the heater-subsystem **40**. For example, once a portion (or all) of the mass of heated fluid is fed to the tool **26**, fluid returning from the tool **26** can be fed to the heater **42** and then to the tank **44** of the heater-subsystem **40** to maintain or recharge the mass of heated fluid. The heated fluid may then be held or re-circulated in one or more passes between the heater **42** and the tank **44** of the heater-subsystem **40** to further increase or maintain temperature of the mass of heated fluid. This is also useful if the heater **42** can't keep up with demands of the tool **26** and/or the system **20**, where the mass of heated fluid serves as a buffer for the heater **42** to catch-up or recover. This is also useful for maintaining a near steady-state temperature of the fluid within the heater-subsystem **40** to meet ongoing demands of the tool **26** and the system **20**.

[0052] The three-way valve **46** of the heater-subsystem **40** is also in fluid communication between the tank **44** of the heater-subsystem **40** and the tool **26**. As such, the three-way valve **46**

of the heater-subsystem **40** is also useful for directing the fluid from the tank **44** of the heater-subsystem **40** to the tool **26**. This is especially useful for rapidly heating the mold surface **24** of the tool **26** as further described below. For example, the mass of heated fluid (or a portion thereof) can be fed to the tool **26** to rapidly heat the mold surface **24**. The mass of heated fluid provided by the tank **44** of the heater-subsystem **40** provides for a rapid change in temperature relative to what the heater **42** could achieve on its own by providing only heated fluid on demand. For example, the heater **42** may be burdened during ramping up of the mold surface **24** temperature and will take time to recover. The mass of heated fluid provides for a drastic change in temperature in a very short period of time, i.e., a maximum ΔT in the mold surface **24**, without putting the entire heating burden on the heater **42**.

[0053] Referring to Figure 18, another embodiment of the system **20** is shown. The three-way valve **46** of the heater-subsystem **40** is in fluid communication i) between the tank **44** and the heater **42** for re-circulating a first thermal fluid from the tank **44** to the heater **42** and ii) between the tank **44** and the tool **26** for directing the first thermal fluid from the tank **44** to the tool **26**. Optionally, the heater-subsystem **40** may include a tank bypass line **39** in this or other embodiments.

[0054] Referring to Figure 2, a related embodiment of the system **20** further comprises a chiller-subsystem **48**. As such, in certain embodiments, the system **20** comprises the heater- and chiller-subsystems **40,48**. In this embodiment, the chiller-subsystem **48** is in fluid communication with the tool **26**. The chiller-subsystem **48** is useful for cooling the mold surface **24** of the tool **26**. In embodiments where the heater-subsystem **40** may be used for cooling the mold surface **24** of the tool **26**, the chiller-subsystem **48** can also be used for further cooling the mold surface **24**. In other certain embodiments, the heater-subsystem **40** is used only for heating the mold surface **24**, and the chiller-subsystem **48** is used only for cooling the mold surface **24**. Other embodiments of the system **20** are described below, where the chiller-subsystem **48** is used in another location of the system **20**. In certain embodiments, the subsystems **40,48** are separate from each other; however, in other embodiments, the subsystems **40,48** are in fluid communication with each other, i.e., they share the fluid of the system **20**.

[0055] The chiller-subsystem **48** comprises a chiller **50**. The chiller **50** is useful for cooling the fluid within the system **20**. Various types of chillers **50** can be employed. The chiller **50** should be capable of cooling the fluid to temperatures of at least about 50°F (~10°C) to about 80°F (~27°C), and downwards of about -10°F (~ -23°C) to about 20°F (~ -7°C). The chiller **50** should also be capable of delivering various outputs of fluid, such as from about 10 to about 150, from

about 20 to about 125, from about 30 to about 100, from about 40 to about 75, ton chilling (where 1 ton chilling is about 12,000 BTUs per hour). Suitable chillers **50** are commercially available from a variety of suppliers. Specific examples of chillers **50** include those commercially available from Mokon, including the Iceman Series, e.g. the Iceman SC Series, the Iceman LT Series, the Iceman Dual Circuit, and the Iceman Full Range.

[0056] The chiller-subsystem **48** further comprises a tank **52**. The tank **52** of the chiller-subsystem **48** is useful for containing a mass of cooled fluid. The tank **52** of the chiller-subsystem **48** is in fluid communication with the chiller **50**. Various types of tanks can be employed as the tank **52** of the chiller-subsystem **48**. The tank **52** of the chiller-subsystem **48** should be able to hold fluid at temperatures of about -30°F (~ -34°C) to about -10°F (~ -23°C), or upwards of about 20°F (~ -7°C) to about 50°F (~10°C). Typically, the tank **52** of the chiller-subsystem **48** should be rated for less than the lowest temperature output of the chiller **50**. In certain embodiments, the chiller-subsystem **48** comprises two or more tanks (not shown). For example, the mass of fluid contained in one tank **52** may be at a different temperature than that of another tank **52**. This may be useful for buffering the system **20** with masses of cooled fluid at different temperatures.

[0057] Generally, the tank **52** of the chiller-subsystem **48** should be insulated, either itself, and/or with a supplemental layer of insulation, to prevent heating of the mass of cooled fluid contained therein by the ambient environment. Various types of insulation means can be employed as like described above with the tank **44** of the heater-subsystem **40**.

[0058] The tank **52** of the chiller-subsystem **48** can be of various sizes and shapes. It may be useful to reduce the SA:V of the tank **52** of the chiller-subsystem **48** to reduce heat gain; however, this is not required. The tank **52** of the chiller-subsystem **48** should be of a size to hold of from about 50 to about 200, from about 75 to about 150, or from about 100 to about 125, gallons of the fluid (or about 189 to about 946, from about 378 to about 852, from about 378 to about 757, or from about 378 to about 568, liters of the fluid). Generally, a larger size tank **52** provides for a greater cooling buffer in the system **20**. Reference to the mass of cooled fluid associated with the tank **52** of the chiller-subsystem **48** may refer to a portion to an entirety of the cooled fluid contained in the tank **52** at a given instance. The tank **52** is typically separate from the chiller **50**, i.e., the tank **52** is distinguishable from an “internal” tank of the chiller **50**, if present.

[0059] The chiller-subsystem **48** further comprises a valve **54** in fluid communication between the tank **52** of the chiller-subsystem **48** and the chiller **50**. Various types of valves **54** can be

employed. Typically, the valve **54** is a three-way valve **54**. The three-way valve **54** of the chiller-subsystem **48** is useful for re-circulating the fluid between the tank **52** of the chiller-subsystem **48** and the chiller **50**. This arrangement is useful for initially forming, maintaining, and/or recharging the mass of cooled fluid in the tank **52** of the chiller-subsystem **48**. For example, once a portion (or all) of the mass of cooled fluid is fed to the tool **26**, fluid returning from the tool **26** can be fed to the chiller **50** and then to the tank **52** of the chiller-subsystem **48** to maintain or recharge the mass of cooled fluid. The cooled fluid may then be held or re-circulated in one or more passes between the chiller **50** and the tank **52** of the chiller-subsystem **48** to further decrease or maintain temperature of the mass of cooled fluid. This is also useful if the chiller **50** can't keep up with demands of the tool **26** and/or the system **20**, where the mass of cooled fluid serves as a buffer for the chiller **50** to catch-up or recover. This is also useful for maintaining a near steady-state temperature of the fluid within the chiller-subsystem **48** to meet ongoing demands of the tool **26** and the system **20**.

[0060] The three-way valve **54** of the chiller-subsystem **48** is also in fluid communication between the tank **52** of the chiller-subsystem **48** and the tool **26**. As such, the three-way valve **54** of the chiller-subsystem **48** is also useful for directing the fluid from the tank **52** of the chiller-subsystem **48** to the tool **26**. This is especially useful for rapidly cooling the mold surface **24** of the tool **26** as further described below. For example, the mass of cooled fluid (or a portion thereof) can be fed to the tool **26** to rapidly cool the mold surface **24**. The mass of cooled fluid provided by the tank **52** of the chiller-subsystem **48** provides for a rapid change in temperature relative to what the chiller **50** could achieve on its own by providing only cooled fluid on demand. For example, the chiller **50** may be burdened during ramping down of the mold surface **24** temperature and will take time to recover. The mass of cooled fluid provides for a drastic change in temperature in a very short period of time, i.e., a maximum ΔT in the mold surface **24**, without putting the entire cooling burden on the chiller **50**.

[0061] Referring to Figure 18, the three-way valve **54** of the chiller-subsystem **48** is in fluid communication i) between the tank **52** and the chiller **50** for re-circulating a second thermal fluid from the tank **52** to the chiller **50** and ii) between the tank **52** and an exchanger-subsystem **49** for directing the second thermal fluid from the tank to an exchanger **51**. Optionally, the chiller-subsystem **48** may include the tank bypass line **39** in this or other embodiments. Typically, the second thermal fluid is water.

[0062] Referring to Figure 18, the system **20** further comprises the exchanger-subsystem **49**. The exchanger-subsystem **49** comprises the (heat) exchanger **51**. The exchanger **51** can be of

various types, such as a shell-and-tube, a shell-and-plate, etc. The exchanger-subsystem **49** further comprises a valve **53**. Typically, the valve **53** is a three-way valve **53**. In this embodiment, the system **20** typically includes at least one pump **55**. Various types of pumps can be utilized. The pump **55** is useful for circulating the fluid within the system **20** when the heater-subsystem **40** and chiller-subsystem **48** are closed off from the tool **26**, such as when recharging. Otherwise, the heater **42** can generally provide suitable pumping for the system **20**.

[0063] The exchanger **51** and three-way valve **53** of the exchanger-subsystem are useful for indirectly introducing cooled fluid to the tool **26**. In this embodiment, cooled fluid does not go directly to the tool **26**, but to the exchanger **51** wherein the cooled fluid is used to reduce the temperature of the heated fluid that is in direct contact with the tool **26**. In using the exchanger **51** to introduce cooled fluid to the tool **26**, this can provide for a smaller closed loop to be established thereby allowing the closed loop to be “set” to a fixed temperature via temperature feedback of the fluid in the loop and control of the valves **46,53,54**. For example, the valves **46,53,54** can be set such that the fluid flows through a check valve **57** via the pump **55** and around the smaller closed loop. Additional aspects of this embodiment are described further below.

[0064] As shown in Figure 18, the three-way valve **53** is in fluid communication i) between the exchanger **51** and the heater-subsystem **40** for sending the first thermal fluid from the tool **26** back to the heater-subsystem **40** and ii) between the exchanger **51** and the tool **26** for directing the first thermal fluid from the tool **26** to the exchanger **51**.

[0065] In general, the first thermal fluid is shared between the heater-subsystem **40** and the exchanger-subsystem **49**, the second thermal fluid is shared between the chiller-subsystem **48** and the exchanger-subsystem **49**, and the first thermal fluid is kept separate from the second thermal fluid. Typically, the first thermal fluid is thermal oil and the second thermal fluid is water, i.e., they are different from one another.

[0066] The system **20** is typically in communication with a controller **56**. The controller **56** is typically in communication with at least one of the subsystems **40,48,49** and the tool **26**, more typically in communication with all of the subsystems **40,48,49** and the tool **26**. Various types of controllers **56** can be employed. Typically, the controller **56** is a programmable logic controller (PLC) **56**, which may also be referred to as a programmable controller **56**. The controller **56** can communicate to components of the system **20** by various methods, such as by wire, by wireless, etc.

[0067] In certain embodiments, the system **20** further comprises a valve **58**, which is in addition to the valves **46,53,54** of the subsystems **40,48,49**. Various types of valves **58** can be employed. Typically, the valve **58** is a three-way valve **58**. Referring to Figure 2, the three-way valve **58** of the system **20** is in fluid communication between the tool **26** and both of the subsystems **40,48**. The three-way valve **58** is also in communication with the controller **56**. In this embodiment, the three-way valve **58** of the system **20** is useful for directing the fluid to the heater-subsystem **40** or to the chiller-subsystem **48** after returning from the tool **26**. Said another way, the controller **56** can direct fluid from the tool **26** to each of the subsystems **40,48** by controlling the three-way valve **58** of the system **20**, along with the three-way valves **46,54** of each of the subsystems **40,48**. Referring to Figure 18, the three-way valve **58** may optionally be utilized, i.e., as a supplemental valve **58**, such as in place of the check valve **57**.

[0068] It is to be appreciated that while “three-way” valves **46,53,54,58** may generally be referred to herein, the same flow control may be achieved by a combination of different types of valves and piping **38** arrangements which “mimic” a three-way valve. For example, a combination of two-way valves and piping **38** may be utilized to achieve the same flow control as achieved by a three-way valve. As another example, a plugged four-way valve may be utilized in place of a three-way valve. Such alternate arrangements for achieving the same (or similar) flow control are contemplated as being equivalent in function as the three-way valves **46,53,54,58** described herein.

[0069] The controller **56** is also useful for controlling flow of fluid in the system **20**. For example, the controller **56** can control a combination of the valves **58** of the system **20**, the valves **46,53,54** of the subsystems **40,48,49** the heater **42**, the chiller **50**, and/or the heat exchanger **49**, to direct fluid at various temperatures to and from the tool **26**.

[0070] The controller **56** is especially useful for directing the masses of the heated and cooled fluid from each of the subsystems **40,48**. Specifically, the controller **56** is useful for directing the mass of heated fluid from the tank **44** of the heater-subsystem **40** to rapidly heat the mold surface **24** of the tool **26**. The controller **56** is also useful for directing the mass of cooled fluid from the tank **52** of the chiller-subsystem **48** to rapidly cool the mold surface **24** of the tool **26** either directly to the tool **26**, such as in Figure 2, or indirectly via the exchanger-subsystem **51**, such as in Figure 18.

[0071] In certain embodiments, the controller **56** controls the three-way valves **46,53,54,58** to direct fluid from at least one of the tanks **44,52** to the tool **26** to heat or cool the mold surface **24** of the tool **26**. In further embodiments, the controller **56** controls the three-way valves

46,53,54,58 to re-circulate fluid in the other subsystem **40,48** to maintain the mass of heated or cooled fluid in the tank **44,52** of the other subsystem **40,48**. Re-circulating the fluid in the subsystem **40,48** can start before, after, or during heating or cooling of the mold surface **24** with the other subsystem **40,48**. As introduced above, the controller **56** can also be used to control fluid in the exchanger-subsystem **49**. The controller **56** can direct the fluid in the system **20** by opening and closing the three-way valves **46,53,54,58** in particular orders and/or at particular times. The three-way valves **46,53,54,58** may be opened and/or closed simultaneously and/or concurrently. While not shown, the controller **56** may also be in communication with other valves in the system **20** to control flow of the fluid.

[0072] A specific embodiment will now be described in the following few paragraphs. Referring to Figure 18, the controller **56** can be programmed to manipulate the subsystems **40,48,49** in various manners. In this embodiment, the controller **56** is generally programmed to instruct the three-way valve **46** of the heater-subsystem **40** at certain times such that the first thermal fluid re-circulates between the heater **42** and the tank **44** and bypasses the tool **26** to maintain the mass of heated first thermal fluid in the heater-subsystem **40**. At other times, the controller **56** is generally programmed to instruct the three-way valve **46** of the heater-subsystem **40** such that the first thermal fluid is directed from the heater-subsystem **40** and to the tool **26** to heat the mold surface **24** of the tool **26**.

[0073] In addition, the controller **56** is generally programmed to instruct the three-way valve **54** of the chiller-subsystem **48** at certain times such that the second thermal fluid re-circulates between the chiller **50** and the tank **52** and bypasses the exchanger-subsystem **49** to maintain the mass of cooled second thermal fluid in the chiller-subsystem **48**. At other times, the controller **56** is generally programmed to instruct the three-way valve **54** of the chiller-subsystem **48** such that the second thermal fluid is directed from the chiller-subsystem **48** to the exchanger-subsystem **49** to cool the first thermal fluid returning from the tool **26** and entering the exchanger-subsystem **51**.

[0074] In addition, the controller **56** is generally programmed to instruct the three-way valve **53** of the exchanger-subsystem **49** at certain times such that the first thermal fluid returning from the tool **26** is directed to the heater-subsystem **40** and bypasses the exchanger-subsystem **51** to reheat the first thermal fluid within the heater-subsystem **40**. At other times, the controller **56** is generally programmed to instruct the three-way valve **53** of the exchanger-subsystem **49** such that the first thermal fluid returning from the tool **26** is directed to the exchanger-subsystem to cool the first thermal fluid via the second thermal fluid from the chiller-subsystem **48**.

[0075] In certain embodiments, the fluid may be directed into the tool **26** in a countercurrent fashion relative to a coolest or warmest area of the mold surface **24**. For example, if one area of the mold surface **24** is initially the coolest relative to the remainder of the mold surface **24**, and the tool **26** is being heated, the controller **56** can direct heated fluid to this location to expedite temperature change of the location based on a large initial temperature gradient. It is to be appreciated that there are also instances where concurrent flow arrangements can be useful, such as for maintaining a temperature gradient across the mold surface **24**, or there may be instances where a combination of countercurrent and concurrent flow arrangements can be used. Typically, flow within the tubing **28** of the tool **26** is turbulent to promote greater thermal transfer between the mold surface **24** and the fluid within the tubing **28**. Turbulence may be imparted by various means, such as by use of helically corrugated piping **38** and/or tubing **28**.

[0076] While not shown, the system **20** may include one or more additional types of valves for regulating flow of the fluid within the system **20**. For example, one or more ball valves may be present for stopping/starting flow of the fluid in a portion of the system **20**. As another example, one or more gate valves and/or check valves may be present for preventing backflow of the fluid in a portion of the system **20**. As another example, one or more globe valves may be present for regulating flow rate of the fluid in a portion of the system **20**. If employed, the additional valves may be disposed in various locations of the system **20**. The valves of the system **20**, including the three-way valves **46,53,54,58**, may be manipulated in various ways, such as pneumatically, manually, electrically, magnetically, etc. In certain embodiments, electrical control is employed, pneumatic control is employed, or combinations thereof.

[0077] The system **20** can further comprise a relief valve **60**. The relief valve **60** may also be referred to as a pressure relief valve **60**, a pressure safety valve **60**, or a safety valve **60**. Various types of relief valves **60** (and their related systems) can be employed. The relief valve **60** is typically in fluid communication between the subsystems **40,48,49** and the tool **26**. The relief valve **60** is useful for relieving pressure of the fluid in the system **20**. For example, an upset in the system **20** may increase pressure of the fluid to an unsafe or undesirable level. As such, the relief valve **60** can compensate for such an occurrence by releasing a portion of the fluid in the system **20** to return the pressure of the fluid to a safe or desired level. The controller **56** may be in communication with the relief valve **60** to shut down the system **20** in the event that the relief valve **60** activates to prevent damage to the system **20**, press **64**, etc.

[0078] The system **20** may further comprise a strainer (not shown). Various types of strainers can be employed. The strainer useful for straining the fluid to prevent clogging or other issues in

the system **20** over time. The strainer can also be useful for imparting and/or maintaining turbulent flow of the fluid.

[0079] As introduced above, the system **20** may further comprise one or more pumps **55**. Various types of pumps can be employed, such as those generally used for moving heat transfer fluids. In certain embodiments, such as those lacking the exchanger-subsystem **51**, the heater **42** and chiller **50** generally provide sufficient pumping of the fluid.

[0080] Utilizing the system **20**, the mold surface **24** of the tool **26** can be heated at various rates. The rate of heating may be linear or curvilinear. For example, the rate of heating can increase at a decreasing rate, increase at an increasing rate, be substantially constant, or combinations thereof. Typically, the mold surface **24** heats at a rate of greater than about 60, greater than about 70, greater than about 80, greater than about 90, or greater than about 100, °F per minute (or greater than ~33, greater than ~39, greater than ~44, greater than ~50, or greater than ~56, °C per minute). In certain embodiments, the mold surface **24** can be heated at a rate upwards of about 300, about 250, about 225, or about 200, °F per minute (~167, ~139, ~125, or ~111, °C per minute).

[0081] Utilizing the system **20**, the mold surface **24** of the tool **26** can be cooled at various rates. The rate of cooling may be linear or curvilinear. For example, the rate of cooling can increase at a decreasing rate, increase at an increasing rate, be substantially constant, or combinations thereof. Typically, the mold surface **24** cools at a rate of greater than about 40, greater than about 50, greater than about 60, greater than about 70, greater than about 80, greater than about 90, or greater than about 100, °F per minute (or greater than ~22, greater than ~28, greater than ~33, greater than ~39, greater than ~44, greater than ~50, or greater than ~56, °C per minute). In certain embodiments, the mold surface **24** can be cooled at a rate upwards of about 200, about 175, or about 150, °F per minute (~111, ~97, or ~83, °C per minute)..

[0082] The present invention further provides a method. The method is useful for heating and cooling the mold surface **24** of the tool **26**. The method comprises the step of providing the heater-subsystem **40**. In certain embodiments, the method further comprises the step of providing the chiller-subsystem **48**. In various embodiments, the method further comprises the step of providing the exchanger-subsystem **49**. In various embodiments, the method further comprises the step of providing the controller **56**. Typically, the method further comprises the step of providing the tool **26**. The tool **26** can be provided manually or automatically. For example, the tool **26** may be provided by a technician or by a robot (not shown). The tool **26** and subsystems **40,48,49** can be as described above.

[0083] The method further comprises the step of directing the mass of heated fluid from the tank **44** of the heater-subsystem **40** to the tool **26**. The mass of heated fluid can be directed by the controller **56** communicating with the subsystems **40,48,49** and the three-way valve **58** of the system **20** as described above.

5 [0084] The mass of heated fluid heats the mold surface **24** of the tool **26** from a first temperature (T_1) to a second temperature (T_2) within a first period of time (Tt_1). T_1 can be various temperatures. For example, T_1 can be the temperature of the mold surface **24** at startup, i.e., the mold surface **24** can be at ambient (or room) temperature. Alternatively, T_1 can be the temperature of the mold surface **24** after a previous cycle of heating and cooling. As such, the
10 mold surface **24** may be hotter (or cooler) than ambient temperature. Typically, T_1 is from about 50 to about 125, from about 75 to about 125, from about 90 to about 125, or from about 100 to about 120, °F (~10 to ~52, ~24 to ~52, ~32 to ~52, or ~38 to ~49, °C).

[0085] Tt_1 can be various time periods. Typically, Tt_1 is short relative to subsequent time periods of heating and cooling. However, Tt_1 may also be longer than or equal to one or more
15 subsequent time periods of heating and cooling. Typically, Tt_1 is from about 1 to about 25, from about 1 to about 20, from about 1 to about 15, from about 1 to about 10, from about 2.5 to about 10, from about 2.5 to about 7.5, or from about 4 to about 6, minutes.

[0086] T_2 can be various temperatures. For example, T_2 can be the maximum temperature of the mold surface **24** reached during heating. Typically, T_2 is from about 250 to about 400, from
20 about 250 to about 375, from about 275 to about 375, from about 300 to about 375, or from about 325 to about 350, °F (~121 to ~204, ~121 to ~191, ~135 to ~191, ~149 to ~191, or ~163 to ~177, °C).

[0087] In general, the mass of heated fluid in the tank **44** of heater-subsystem **40** is at a temperature of about T_2 or higher. It is useful when the mass of the heated fluid is at least about
25 50°F (10°C) higher than T_2 to facilitate heat transfer between the mass and the mold surface **24** of the tool **26**, and more typically much higher than T_2 . In certain embodiments, the mass of heated fluid in the tank **44** of the heater-subsystem **40** is at a temperature of from about 250 to about 600, from about 300 to about 550, from about 350 to about 500, or from about 400 to about 450, °F (~121 to ~316, ~149 to ~288, ~177 to ~260, or ~204 to ~232, °C). Due to the
30 mass of heated fluid, the system **20** can rapidly heat the mold surface **24** of the tool **26** as described above.

[0088] The method further comprises the step of directing fluid from the heater-subsystem **40** to the mold surface **24** of the tool **26**. The fluid can be directed by the controller **56**

communicating with the subsystems **40,48** and the three-way valve **58** of the system **20**. The fluid maintains the mold surface **24** at about T_2 for a second period of time (Tt_2). The mold surface **24** can be maintained at T_2 or at an acceptable tolerance level, e.g. $Tt_2 \pm 15^\circ\text{F}$ ($\pm 9^\circ\text{C}$). Maintaining the mold surface **24** at about T_2 for Tt_2 is useful for curing resin of the composite article **22**. It is also believed to be useful for increasing surface properties of the composite article **22**. Thermostat modulation can be used for staying within the tolerance level.

[0089] Tt_2 can be various time periods. Typically, Tt_2 is shorter than Tt_1 . However, Tt_2 may also be longer than or equal to Tt_1 or a subsequent time period. Typically, Tt_2 is from about 1 to about 25, from about 1 to about 20, from about 1 to about 15, from about 1 to about 10, from about 1 to about 7.5, from about 1 to about 5, or from about 1 to about 2.5, minutes.

[0090] In certain embodiments, the method further comprises the step of maintaining the mold surface **24** of the tool **26** at an intermediate temperature (T_{1-2}) of between T_1 and T_2 . Typically, this step occurs prior to heating the mold surface **24** of the tool **26** to T_2 . T_{1-2} can be maintained by only feeding a portion of the mass of heated fluid to the mold surface **24** and/or by controlling overall temperature of the heater-subsystem **40**.

[0091] The fluid maintains the mold surface **24** at about T_{1-2} for a portion of Tt_1 ($Tt_{<1}$). The fluid can be directed by the controller **56** communicating with the subsystems **40,48** and the three-way valve **58** of the system **20**. The mold surface **24** can be maintained at T_{1-2} or at an acceptable tolerance level, e.g. $T_{1-2} \pm 15^\circ\text{F}$ ($\pm 9^\circ\text{C}$). It is believed that maintaining the mold surface **24** at about T_{1-2} for Tt_2 is useful for consolidating the composite article **22**. For example, resin of the composite article **22** reaches its minimum viscosity and/or thins to more readily flow into the carbon fiber mat of the composite article **22**. Such consolidation is believed to be useful for achieving mechanical properties and improving the Class A surface of body panels of the composite article **22**, if formed. Thermostat modulation can be used for staying within the tolerance level.

[0092] T_{1-2} can be various temperatures. For example, T_{1-2} can be in the middle of T_1 and T_2 , closer to T_1 , or closer to T_2 . Typically, T_{1-2} is from about 100 to about 350, from about 150 to about 325, from about 200 to about 300, from about 225 to about 275, or from about 235 to about 265, $^\circ\text{F}$ (~ 38 to ~ 177 , ~ 66 to ~ 163 , ~ 93 to ~ 149 , ~ 107 to ~ 135 , or ~ 113 to ~ 129 , $^\circ\text{C}$).

[0093] $Tt_{<1}$ can be various time periods, provided it is less than Tt_1 . Typically, Tt_{1-2} is longer than Tt_2 . However, Tt_{1-2} may also be shorter than or equal to Tt_2 or a subsequent time period. Typically, $Tt_{<1}$ is from about 1 to less than about 25, from about 1 to about 20, from about 1 to

about 15, from about 1 to about 10, from about 1 to about 7.5, from about 1 to about 5, or from about 1 to about 2.5, minutes. In certain embodiments, $Tt_{<1}$ is from 1 to less than 10 minutes.

[0094] In certain embodiments, such as the one of Figure 2, the method further comprises the step of directing the mass of cooled fluid from the tank **52** of the chiller-subsystem **48** to the tool **26** to cool the mold surface **24** of the tool **26** from about T_2 to a third temperature (T_3) within a third period of time (Tt_3). In other embodiments, the heater-subsystem **40** is used to cool the mold surface **24** in a similar manner. Typically, either one of these steps occurs after maintaining the mold surface **24** of the tool **26** at T_2 for Tt_2 . The mass of cooled fluid can be directed by the controller **56** communicating with the subsystems **40,48** and the three-way valve **58** of the system **20**. In other embodiments, such as the one of Figure 18, the method further comprises the step of directing the mass of cooled second thermal fluid from the tank **52** of the chiller-subsystem **48** to the exchanger-subsystem **49** via the controller **56** to cool the mold surface **24** of the tool **26** from T_2 to T_3 within Tt_3 .

[0095] T_3 can be various temperatures. For example, T_3 can be the temperature of the mold surface **24** at startup, i.e., the mold surface **24** can be at ambient (or room) temperature. T_3 is generally higher than ambient temperature. Typically, T_3 is from about 75 to about 150, from about 85 to about 140, from about 90 to about 130, or from about 100 to about 120, °F (~24 to ~66, ~29 to ~60, ~32 to ~54, or ~38 to ~49, °C).

[0096] Tt_3 can be various time periods. Typically, Tt_3 is long relative to previous time periods of heating. However, Tt_3 may also be longer than or equal to one or more previous time periods of heating. Typically, Tt_3 is from about 1 to about 25, from about 1 to about 20, from about 1 to about 15, from about 1 to about 10, from about 2.5 to about 10, from about 2.5 to about 7.5, or from about 4 to about 6, minutes.

[0097] In general, the mass of cooled fluid in the tank **52** of chiller-subsystem **48** is at a temperature of about T_3 or lower. It is useful when the mass of the cooled fluid is at least about 50°F lower than T_3 to facilitate heat transfer between the mold surface **24** of the tool **26** and the mass. In certain embodiments, the mass of the cooled fluid in the tank **52** of the chiller-subsystem **48** is at a temperature of from about 35 to about 70, about 40 to about 60, about 45 to about 55, or about 50, °F (~1.7 to ~21, ~4.4 to ~16, ~7 to ~13, or ~10, °C). As such, the system **20** can rapidly cool the mold surface **24** of the tool **26** with the mass of cooled fluid.

[0098] As described above, the method is useful for heating the mold surface **24** of the tool **26**. Typically, the mold surface **24** of the tool **26** heats at a rate of greater than about 60, about 70, about 80, about 90, about 100, about 110, about 120, about 130, about 140, about 150, about

160, about 170, or about 180, °F per minute (greater than ~33, greater than ~39, greater than ~44, greater than ~50, greater than ~56, greater than ~61, greater than ~67, greater than ~72, greater than ~78, greater than ~83, greater than ~89, greater than ~94, or greater than ~100, °C per minute).

5 [0099] As also described above, the method is useful for cooling the mold surface **24** of the tool **26**. Typically, the mold surface **24** of the tool **26** cools at a rate of greater than about 40, about 50, about 60, about 70, about 80, about 90, about 100, about 110, about 120, about 130, about 140, about 150, about 160, about 170, or about 180, °F per minute (greater than ~33, greater than ~39, greater than ~44, greater than ~50, greater than ~56, greater than ~61, greater than ~67, greater than ~72, greater than ~78, greater than ~83, greater than ~89, greater than ~94, or greater than ~100, °C per minute).

[00100] As introduced above, the controller **56** can be programmed with various control schemes to heat and cool the mold surface **24** using the subsystems **40,48,49** and three-way valve **58** of the system **20**, if utilized. For example, the controller **56** can be programmed to open or close one or more of the three-way valves **46,53,54,58** at certain times and/or at certain temperatures of the mold surface **24**. Such control methodology is useful for directing the fluid to the tool **26** and/or re-circulating the fluid as described above. As a starting point, control schemes of the controller **56** may be modeled off of control schemes generally used with autoclaves.

20 [00101] In certain embodiments, the controller **56** is programmed such that $Tt_1 \leq Tt_2$ or $Tt_1 \geq Tt_2$. In further embodiments, the controller **56** is programmed such that $Tt_1 \geq Tt_3$ or $Tt_1 \leq Tt_3$. Typically, $Tt_1 + Tt_2 + Tt_3$ is no greater than about 30, about 25, about 20, about 19, about 18, about 17.5, about 17, about 15, about 14, about 13.5, about 13, about 12.5, about 12, about 11, about 10, about 7.5, about 5, about 2.5, or about 2, minutes. In certain embodiments, $Tt_1 + Tt_2 + Tt_3$ is no greater than about 20 minutes, no greater than about 19 minutes, no greater than about 18 minutes, or no greater than about 17 minutes, and can be downwards of about 15, about 10, or about 5, minutes. Due to the direct heating and cooling of the mold surface **24** of the tool **26** via the system **20**, cycle time of making the composite articles **22** is greatly reduced relative to conventional methods, such as autoclaving.

30 [00102] The controller **56** typically measures temperature of the mold surface **24** by feedback from one or more resistive thermal device (RTD) (not shown) disposed proximal the mold surface **24**. The controller **56** can also measure temperature of the fluid by one or more RTDs

disposed in or proximal the piping **38** at one or more locations and/or by one or more RTDs disposed in or proximal the subsystems **40,48,49**. Various types of RTDs can be employed.

[00103] The present invention further provides a method of forming the composite article **22**. The method comprises the step of providing the tool **26**. The tool **26** can be as described above.

5 The method further comprises the step of providing a preform **62**. The preform **62** can be provided manually or automatically.

[00104] The preform **62** comprises a carbon fiber mat and a resin. Various types of carbon fiber mat can be employed, such as a continuous fiber mat. The carbon fiber mat may also be referred to as a fabric or a braid. The carbon fiber mat can include one or more layers of fibers, typically
10 at least two layers of fibers. The carbon fibers can be of various types, such as standard modulus, intermediate modulus, high modulus, or high strength, carbon fibers. In certain embodiments, the carbon fibers are unidirectional.

[00105] The carbon fiber mat can be substantially dry and/or a pre-preg. In certain embodiments, the carbon fiber mat is a carbon fiber pre-preg, which may also be referred to as a
15 prepreg. Suitable carbon fiber mats are commercially available from a variety of suppliers. Specific examples of carbon fiber mats include those commercially available from Toray Carbon Fibers America, Inc. of Flower Mound, TX, including the TORAYCA® Series, e.g. TORAYCA® T700S; and from Toray Composites (America), Inc., of Tacoma, WA. Further specific examples of carbon fiber mats include those commercially available from Advanced
20 Composites Group of Tulsa, OK; and from Grafil, Inc. of Sacramento, CA, including the GRAFIL Series and the PYROFIL™ Series, e.g. PYROFIL™ TR30S.

[00106] Various types of resins can be employed, including both thermoplastic and/or thermosetting resins. Typically, the resin is a thermosetting resin. Examples of suitable thermosetting resins include epoxy resins. In certain embodiments, the resin comprises an epoxy
25 resin. The resin can include (or be mixed) with one or more hardeners to promote cure of the resin. Various types of hardeners can be employed. The resin should be capable of curing in the time periods described above to utilize the rapid heating and cooling provided by the system **20**. Suitable resins are commercially available from a variety of suppliers. Specific examples of resins include those commercially available from Huntsman International LLC of Salt Lake
30 City, UT; from Toray Carbon Fibers America, Inc.; from Toray Composites (America), Inc., including G83 pre-preg resin; and from Advanced Composites Group, including MTM57 pre-preg resin.

[00107] As introduced above, the composite article **22** may be formed from a pre-preg, which is a carbon fiber mat previously infused with a resin, being either wet or dry, typically slightly wet. It is to be appreciated that if the pre-preg is employed, additional resin being the same or different from that of the pre-preg may be employed to form the composite article **22**.

5 Alternatively, just the resin provided with the pre-preg can be employed as the resin. Various types of pre-pregs can be employed. Specific examples of pre-pregs or pre-preg systems include those commercially available from Toray Composites (America), Inc., such as PC7831-190-1000; and from Advanced Composites Group, such as MTM57/CF3238.

[00108] The method further comprises the step of disposing the preform **62** on the mold surface **24** of the tool **26**. The preform **62** may be disposed manually or automatically. The method further comprises the step of heating the mold surface **24** of the tool **26** from T_1 to T_2 within Tt_1 . T_1 , T_2 , and Tt_1 can be as described above. Heating the mold surface **24** is useful for thinning the resin of the preform **62**. As such, the resin is better able to flow around, into, and within the carbon fiber mat. The mold surface **24**, and therefore, the preform **62**, can be heated with the system **20** as described above.

[00109] The method further comprises the step of applying pressure to the preform **62**. Pressure may be applied by various means. Typically, pressure is applied by a press **64**, as described further below. The pressure is applied from a first pressure (P_1) to a second pressure (P_2).

[00110] Pressure can be applied at various rates. The rate of pressurizing may be linear or curvilinear. For example, the rate of pressurizing can increase at a decreasing rate, increase at an increasing rate, be substantially constant, or combinations thereof. Typically, pressure is applied at a rate of greater than about 0.1, greater than about 0.2, greater than about 0.3, greater than about 0.4, greater than about 0.5, greater than about 0.6, greater than about 0.7, greater than about 0.8, greater than about 0.9, greater than about 1, greater than about 1.1, greater than about 1.2, greater than about 1.3, greater than about 1.4, greater than about 1.5, or greater than about 2, pounds per square inch (psi) per second (sec) (where 1 psi/sec is ~2.07 kPa/sec).

[00111] P_1 can be various pressures. For example, P_1 can be standard atmospheric pressure (~14.7 psi). Typically, P_1 is from about 0 to about 5, from about 0 to about 1, from about 0 to about 0.5, from about 0 to about 0.25, or from about 0 to about 0.1, psi gauge (psig) (where 1 psig is ~2.07 kPa gauge).

[00112] P_2 can be various pressures. For example, P_2 can be the maximum pressure reached during pressurizing. Typically, P_2 is from about 50 to about 150, from about 60 to about 140,

from about 70 to about 130, from about 80 to about 120, from about 90 to about 110, or about 100, psig.

[00113] The pressure is applied within a first period of time (Pt_1). Applying the pressure is useful for consolidating the preform **62**, especially after the resin has thinned via application of heat. Pt_1 can be various time periods. Typically, Pt_1 is short relative to subsequent time periods of pressurizing or depressurizing. However, Pt_1 may also be longer than or equal to one or more subsequent time periods of pressurizing or depressurizing. Typically, Pt_1 is from about 1 to about 25, from about 1 to about 20, from about 1 to about 15, from about 1 to about 10, from about 2.5 to about 10, from about 2.5 to about 7.5, or from about 4 to about 6, minutes.

[00114] The method further comprises the step of maintaining pressure at about P_2 for a second period of time (Pt_2). The pressure can be maintained at P_2 or at an acceptable tolerance level, e.g. $P_2 \pm 10$ psi (wherein 1 psi is ~ 2.07 kPa). Maintaining the pressure at about P_2 for Pt_2 is useful for further consolidation and curing the resin of the composite article **22**. Modulation can be used for staying within the tolerance level.

[00115] Pt_2 can be various time periods. Typically, Pt_2 is shorter than Pt_1 . However, Pt_2 may also be longer than or equal to Pt_1 or a subsequent time period. Typically, Pt_2 is from about 1 to about 25, from about 1 to about 20, from about 1 to about 15, from about 1 to about 10, from about 1 to about 7.5, from about 1 to about 5, or from about 1 to about 2.5, minutes.

[00116] In certain embodiments, the method further comprises the step of maintaining pressure at an intermediate pressure (P_{1-2}) of between P_1 and P_2 for a portion of Pt_1 ($Pt_{<1}$) prior to P_2 . Typically, this step occurs prior to pressurizing to P_2 . The pressure can be maintained at P_{1-2} or at an acceptable tolerance level, e.g. $P_{1-2} \pm 10$ psi. It is believed that maintaining the pressure at about P_{1-2} for $Pt_{<1}$ is useful for consolidating the composite article **22**. For example, the resin can be at its minimum viscosity or thinned to more readily flow within the carbon fiber mat of the preform **62**. Modulation can be used for staying within the tolerance level.

[00117] P_{1-2} can be various pressures. For example, P_{1-2} can be in the middle of P_1 and P_2 , closer to P_1 , or closer to P_2 . Typically, P_{1-2} is from about 25 to about 125, from about 35 to about 115, from about 45 to about 105, from about 50 to 100, from about 55 to about 95, from about 65 to about 85, or about 75, psig.

[00118] $Pt_{<1}$ can be various time periods, provided it is less than Pt_1 . Typically, Pt_{1-2} is longer than Pt_2 . However, Pt_{1-2} may also be shorter than or equal to Pt_2 or a subsequent time period. Typically, $Pt_{<1}$ is from about 1 to less than about 25, from about 1 to about 20, from about 1 to

about 15, from about 1 to about 10, from about 1 to about 7.5, from about 1 to about 5, or from about 1 to about 2.5, minutes.

[00119] The method further comprises the step of reducing pressure on the composite article 22. The method further comprises the step of cooling the mold surface 24 of the tool 26 to drop the mold surface 24 from about T_2 to T_3 within Tt_3 . The mold surface 24 of the tool 26 can be cooled with the system 20 as described above. The method further comprises the step of removing the composite article 22 from the mold surface 24 of the tool 26. The composite article 22 may be removed manually or automatically.

[00120] As described above, the system 20 can be used to heat and cool the mold surface 24 of the tool 26. The controller 56 can be programmed with various control schemes to heat and cool the mold surface 24 using the subsystems 40,48,49 and three-way valve 58 of the system 20, if utilized. The controller 56 can also be programmed to apply and remove pressure to the composite article 22 at various times and/or at various temperatures.

[00121] As alluded to above, pressure can be applied by various means. In certain embodiments, described further below, a pressure tank 66 is used along with the press 64 to apply pressure to the composite article 22. It is to be appreciated that reference to the composite article 22 herein may also refer to the preform 62 depending on its degree of formation.

[00122] In certain embodiments, the controller 56 is programmed such that $Tt_1 \leq Tt_2$ or $Tt_1 \geq Tt_2$. In further embodiments, the controller 56 is programmed such that $Tt_1 \geq Tt_3$ or $Tt_1 \leq Tt_3$.

The total of $Tt_1 + Tt_2 + Tt_3$ is as described above. In certain embodiments, the controller 56 is programmed such that $Pt_1 \leq Pt_2$ or $Pt_1 \geq Pt_2$. In further embodiments, the controller 56 is programmed such that $Pt_1 \leq Tt_1$ or $Pt_1 \geq Tt_1$. In yet further embodiments, the controller 56 is programmed such that $Pt_2 \leq Tt_1$ or $Pt_2 \geq Tt_1$. Typically, $(Pt_1 + Pt_2) \leq (Tt_1 + Tt_2 + Tt_3)$. Said another way, the total time for heating and cooling generally defines the total cycle time for forming the composite article 22.

[00123] Timing for each of the temperature and pressure time periods can be changed to alter surface and/or mechanical properties of the composite article 22. Specific heating, cooling, pressurizing, and depressurizing profiles, for making different types of composite articles 22, can be determined via routine experimentation. Examples of specific profiles are illustrated in Figures 11, 12, and 13, which are described further below. As described above, due to the direct heating and cooling of the mold surface 24 via the system 20, cycle time of making the composite article 22 is greatly reduced relative to conventional methods, e.g. autoclaving.

[00124] The present invention provides another method. The method is useful for forming the composite article **22**. The method comprises the steps of providing the tool **26** and the preform **62**. The tool **26** and preform **62** can be as described above.

[00125] The method further comprises the step of providing the press **64**. The press **64** can be situated proximal or distal each of the system **20**, the pressure tank **66**, and/or the controller **56**. The subsystems **40,48,49** of the system **20** can be situated proximal or distal each other. If utilized, the exchanger-subsystem **49** is typically proximal the press **64**. The controller **56** can be situated proximal or distal each of the subsystems **40,48,49** and the pressure tank **66**. As such, the system **20** offers flexibility in laying out each of its components.

[00126] Referring to Figures 5-7, the press **64** has a platform **68** and a cover **70** facing the platform **68**. The platform **68** of the press **64** is useful for supporting the tool **26**. The method further comprises the step of contacting (or coupling) the platform **68** with the cover **70** to define a cavity **72** between the cover **70** and the platform **68**. The cavity **72** may also be referred to as a plenum. Typically, the cover **70** and/or the platform **68** include a peripheral seal **74**, such as a peripheral gasket **74**, such that the cavity **72** is airtight. In this way, the cavity **72** is operable to maintain a pressurized and/or temperature controlled environment about the tool **26**. Various types of seals **74** can be employed. In these embodiments, the cover **70** is generally rigid and inflexible (which is different from a rubber or “bladder” type mold surface). Various types of presses **64** can be employed. The press **64** should be capable of handling the pressures described herein. Suitable presses **64** are commercially available from a variety of suppliers. Specific examples of presses **64** include those available from Globe Machine Manufacturing Company of Tacoma, WA.

[00127] Referring to Figure 3, the method further comprises the step of disposing the preform **62** on the mold surface **24** of the tool **26**. The method further comprises the step of disposing the vacuum canopy **36** on the tool **26** to define an envelope (not shown) between the vacuum canopy **36** and the mold surface **24** of the tool **26**. The preform **62** and the vacuum canopy **36** may be disposed manually or automatically.

[00128] The vacuum canopy **36** may also be referred to as a bag **36** or a sheet **36**. The vacuum canopy **36** can be formed from various materials, such as a polymeric material, e.g. a silicone. The vacuum canopy **36** can include a peripheral seal **78**, e.g. a peripheral gasket **78**, to assist in forming the envelope. In addition, or alternatively, putty **78** can be used. Various types of seals **78** and/or putty **78** can be employed. Typically, the envelope is airtight. The vacuum canopy **36** can include a peripheral frame **80** for adding rigidity and easing handling of the vacuum canopy

36. Handles (not shown) may be attached to the peripheral frame **80** for moving the vacuum canopy **36**. Clasps **82** can also be attached to the peripheral frame **80** to interact with the fasteners **34** of the tool **26**. The clasps **82** and fasteners **34** are useful for maintaining orientation of the vacuum canopy **36** on the tool **26**.

5 **[00129]** A release sheet (not shown) may be disposed between the vacuum canopy **36** and the preform **62** to prevent sticking. A release sheet or coating (not shown) may also be applied to the mold surface **24** to prevent the composite article **22** from sticking. Various types of release sheets and/or coatings may be employed. The release sheet may be formed from various materials, such as a polymeric film.

10 **[00130]** The method further comprises the step of disposing the tool **26** under the cover **70** such that it is within the cavity **72** of the press **64** once established. The tool **26** is generally disposed under the cover **70** of the press **64** prior to contacting the cover **70** to the platform **68** to establish the cavity **72**. The tool **26** generally takes up at least about 33%, at least about 50%, at least about 66%, at least about 75%, at least about 80%, at least about 85%, or at least about 90%, of
15 the overall volume of the cavity **72**, when disposed therein. As such, the remaining volume of the cavity **72** is typically small relative to the overall volume when the tool **26** is present. Inserts, partitions, or blocks (not shown) can be used to take up additional volume in the cavity, if desired.

[00131] Referring to Figures 5 and 6, a support table **84** is disposed next to the press **64**. The
20 support table **84** is useful for holding, loading, and unloading the tool **26**. Another support table **84** may be used on an opposite side of the press **64** for unloading, or just one support table **84** may be used.

[00132] A carrier **86** is disposed adjacent the platform **68**. The carrier **86** is generally on a chained track **88** and includes at least one hook **90** to engage the tool **26**, and typically includes
25 one hook **90** for engaging each side of the tool **26**. The carrier **86** is useful for pulling the tool **26** from the support table **84** onto the platform **68** of the press **64**, and under the cover **70** of the press **64**.

[00133] After the carrier **86** moves the tool **26** a majority of the way under the cover **70**, the carrier **86** moves out of the way of the cover **70**. The cover **70** then lowers down over the
30 platform **68** to engage (or couple to) the platform **68** and define the cavity **72**. Pistons **92** and/or gears **94** can be used to move the cover **70** of the press **64** up and down into place.

[00134] Once the cover **70** is in contact with the platform **68**, rams **96** disposed on the cover **70**, extend into the cover **70** and the cavity **72**. The rams **96** engage with receivers **98** on the tool **26**

and push the tool **26** further on the platform **68** to substantially center the tool **26** within the cavity **72**. At this point, the tool **26** is generally aligned such that it is in fluid communication with the system **20**. Such fluid communication from the tool **26** to the system **20** can be routed through the cover **70** and/or through the platform **68** of the press **64**. The press **64** can include one or more sensors (not shown) to ensure proper location of the tool **26** prior to lowering the cover **70** and/or prior to heating the mold surface **24**.

[00135] In certain embodiments, the system **20** includes a connection system for automatically coupling the press **64** and the tool **26**. The connection system is useful for communicating the thermal fluid to and from the tool **26** via the system **20**. Referring to Figure 15, a tool-connection system **200** for the tool **26** is shown. The tool-connection system **200** includes a plurality of connections for connecting various elements to the tool **26**, such as fluid feeds, fluid returns, and sensors. Said another way, the tool-connection system **200** can provide various services to the tool **26**, and optionally, to the cavity **72** of the press **64**. In general, the elements provide services and communication with the tool **26**. These elements are generally in communication with the tool **26**, such as being in fluid communication with the tubing **28** of the tool **26**.

[00136] The tool-connection system **200** includes a resistive thermal device (RTD) male connector **202** for temperature monitoring and feedback of the tool **26**. The tool-connection system **200** also includes a first alignment bushing **204**, a thermal fluid intake valve **206** for feeding thermal fluid to the tool **26** from the inlet **30**, a male locking pin **208**, a thermal fluid exhaust valve **210** for returning the thermal fluid from the tool **26** out the outlet **32**, a second alignment bushing **212**, and a vacuum connector **214** and static connector **216** for pressure monitoring of the tool **26**. In addition to or alternate to an RTD, other forms of temperature measurement of the tool **26** can also be utilized, such as thermocouples. These forms include thermocouples, optical pyrometers and other like systems. Certain embodiments may monitor the actual temperature or the rate of change in the temperature.

[00137] Referring to Figure 16, a press-connection system **218** for the press **64** is shown. The press-connection system **218** includes a plurality of connections for connecting various elements to the press **64**, such as fluid feeds, fluid returns, and sensors. These elements are generally in communication with the system **20**, such as being in fluid communication with the piping **38** of the system **20**. The press-connection system **218** includes a RTD female connector **220** for temperature monitoring and feedback of the tool **26**. The press-connection system **218** also includes a thermal fluid exhaust valve **222** for feeding thermal fluid to the tool **26** from the inlet **30**, a thermal fluid intake valve **224** for returning the thermal fluid from the tool **26** out the outlet

32, a first alignment pin **226**, a vacuum connector **228** and a static connector **230** for pressure monitoring of the tool **26**, a female locking ring **230** operated by hydraulic actuators, and a second alignment pin **232**.

5 [00138] Referring to Figure 17, the press **64** is depicted during a press cycle to form a composite article **22**. The press **64** and tool **26** have a pressure and temperature profile which is imparted in part by the press-connection system **218** and the tool-connection system **200** in combination with the system **20**. Typically, connection between the tool **26** and cover **70** of the press **64** is done automatically after the cover **70** closes. Specifically, the tool-connection system **200** and the press-connection system **218** couple and engage with one another after the tool **26**
10 enters the press **64**. Typically, as like shown in Figure 17, the rams **96** are used to push the connection systems **200,218** together. The carrier **86** can later be used to pull the connection systems **200,218** apart. Once coupled, the tool **26** and the press **64** are in fluid (and, typically, electrical communication) with one another as well as in communication with the controller **56**.

[00139] In a specific embodiment, the tool-connection system **200** is operatively connected to
15 the tool **26**, and the press-connection system **218** is in fluid communication with the heater-subsystem **40** and the exchanger-subsystem **49**. As described above, the connection systems **200,218** couple together for feeding and receiving the first thermal fluid to and from the tool **26**. The press-connection system **218** is operatively connected to the tubing **28** of the tool **26** for heating and cooling the mold surface **26** with the first thermal fluid. The press-connection
20 system **218** is operatively connected through the cover **70** and/or the platform **68** of the press **64** into the cavity **72** for coupling with the tool-connection system **200** while the tool **26** is disposed within the cavity **70** of the press **64** for heating and cooling the mold surface **26** with the first thermal fluid.

[00140] Such a “quick-connect/disconnect” configuration provides for manufacturing
25 versatility, such as allowing for multiple tool **26** variations to be utilized with no affiliated change over time. For example, various configurations of tools **26** can be utilized and simply “plugged into” the press **64** via the connection systems **200,218**. This also allows for a fast change out of the tools **26** in the system **20**. Tool **26** changes can occur in a time frame of 5 minutes, as fast as 2 minutes and as long as 10 minutes. As a comparison, typical tool changes in
30 compression molding of fiber reinforced plastic parts can take 4 hours.

[00141] As introduced above, operation of the system **20**, including positioning of the tool **26** and the applied temperature and pressure is generally monitored and controlled by the controller **56**. The controller **56** may be implemented using shared processing devices and/or individual

processing devices. Processing devices may include microprocessors, micro-controllers, digital signal processors, microcomputers, central processing units, field programmable gate arrays, programmable logic devices, state machines, logic circuitry, analog circuitry, digital circuitry, and/or any device that manipulates signals (analog and/or digital) based on operational instructions. The memory may be a single memory device or a plurality of memory devices. Such a memory device may be a read-only memory, random access memory, volatile memory, non-volatile memory, static memory, dynamic memory, flash memory, and/or any device that stores digital information. Note that when the baseband processing module implements one or more of its functions via a state machine, analog circuitry, digital circuitry, and/or logic circuitry, the memory storing the corresponding operational instructions is embedded with the circuitry comprising the state machine, analog circuitry, digital circuitry, and/or logic circuitry.

[00142] Returning to the method, the method further comprises the step of applying vacuum to the vacuum canopy **36** thereby evacuating the envelope to retain the preform **62** adjacent the mold surface **24** of the tool **26**. This is useful for keeping the preform **62** in contact with the mold surface **24** for heating and cooling. Vacuum may be applied by various methods. For example, a vacuum pump (not shown) can be connected to the tool **26** which draws air from the mold surface **24**. Typically, vacuum is tested prior to disposing the tool **26** within the cavity **72** to ensure a proper seal of the vacuum canopy **36** on the tool **26**. As described above, the fasteners **34** and clasps **82** are useful for aligning the vacuum canopy **36** on the tool **26**. The vacuum pump can be in fluid communication with the tool through the cover **70** and/or through the platform **68** of the press **64**. Vacuum can be applied at various pressures, such as from about 10 to about 35, or about 12.5 to about 32.5, or about 15 to about 30, in Hg.

[00143] The method further comprises the step of heating the mold surface **24** of the tool **26** from T_1 to T_2 within Tt_1 . This is useful for thinning the resin of the preform **62**. T_1 , T_2 , and Tt_1 can be as described above. The system **20** can be used for heating the mold surface **24**.

[00144] The method further comprises the step of pressurizing the cavity **72** of the press **64** from P_1 to P_2 within Pt_1 . This is useful for consolidating the preform **62**. P_1 , P_2 , and Pt_1 can be as described above. Typically, the method further comprises the step of providing the pressure tank **66**. The pressure tank **66** is in fluid communication with the cavity **72** of the press **64** to pressurize and/or depressurize the cavity **72** of the press **64**. Such fluid communication can be through the cover **70** and/or through the platform **68** of the press **64**.

[00145] In certain embodiments, the gas is recycled from the cavity **72** after use. In other embodiments, the gas is vented from the cavity **72** after use, rather than being recycled. The

pressure tank **66** can contain various compressed gases. Typically, the pressure tank **66** contains compressed air, such that the cavity **72** of the press **64** is pressurized with air. In certain embodiments, the pressure tank **66** is free of compressed nitrogen gas (N₂). It is to be appreciated that air can include ~78% N₂. While air is typically used to pressurize the cavity **72**, other types of gases may also be used.

[00146] The pressure tank **66** may be a stand alone pressurized tank containing the compressed gas or be part of an air compressor. The pressure tank **66** and/or air compressor may be of various types. The pressure tank **66** and/or air compressor should be capable of handling and delivering the pressures associated with the cavity **72** of the press **64**. For example, the pressure tank **66** should be able to pressurize the cavity **72** of the press **64** to at least 150 psig in no more than 120 seconds. Suitable pressure tanks **66** and air compressors are commercially available from a variety of suppliers. Specific examples of air compressors include those commercially available from Sullair® of Michigan City, IN, including the Sullair® Stationary Air Power Systems, e.g. the Sullair® 2200, the Sullair® 3700, the Sullair® 4500, and the Sullair® 7500.

[00147] The pressure tank **66** can be in fluid communication with a dryer (not shown). The dryer is useful for removing moisture from the compressed gas sent to or returned from the cavity **72** of the press **64**. The dryer may be of various types. Suitable dryers are commercially available from a variety of suppliers. Specific examples of dryers include those commercially available from BEKO Technologies Corp. of Atlanta, GA, including the Drypoint® Series, e.g. the Drypoint® RA.

[00148] Typically, the method further comprises the steps of providing the system **20** and providing the controller **56** for heating and cooling of the mold surface **24** of the tool **26**, as well as for pressurizing and depressurizing the cavity **72**. For example, the controller **56** can be in communication with the pressure tank **66** and the press **64** with the controller **56** controlling the pressure tank **66** and/or the press **64** to pressurize or depressurize the cavity **72**. The controller **56** typically measures pressure of the cavity **72** by feedback from one or more pressure sensors (not shown) disposed within the cavity **72**. The controller **56** is typically programmed to set certain pressures at certain times and/or temperatures.

[00149] The method further comprises the step of maintaining the mold surface **24** of the tool **26** at about T₂ for T_{t2}. This is useful for curing the resin. The method can further comprise the step of maintaining the mold surface **24** of the tool **26** at T₁₋₂ for T_{t<1} prior to heating the mold surface **24** of the tool **26** to T₂.

[00150] The method further comprises the step of maintaining the cavity 72 of the press 64 at about P_2 for Pt_2 . This is useful for further consolidating and curing of the composite article 22. The method further comprises the step of cooling the mold surface 24 of the tool 26 to drop the mold surface 24 from about T_2 to T_3 within Tt_3 . The controller 56, the system 20, and the pressure tank 66 can be used for these steps.

[00151] The method further comprises the step of depressurizing the cavity 72 of the press 64. Typically, the cavity 72 is depressurized back to P_1 over a third period to time (Pt_3). The cavity 72 of the press 64 can be depressurized at various rates. The rate of depressurizing may be linear or curvilinear. For example, the rate of depressurizing can increase at a decreasing rate, increase at an increasing rate, be substantially constant, or combinations thereof. Typically, depressurizing is at a rate of greater than about 0.1, greater than about 0.2, greater than about 0.3, greater than about 0.4, greater than about 0.5, greater than about 0.6, greater than about 0.7, greater than about 0.8, greater than about 0.9, greater than about 1, greater than about 1.1, greater than about 1.2, greater than about 1.3, greater than about 1.4, or greater than about 1.5, psi per second. In certain embodiments, the cavity 72 can be depressurized at a rate upwards of about 100, about 75, about 50, about 25, or about 10, psi per second.

[00152] Pt_3 can be various time periods. Typically, Pt_3 is short relative to previous time periods of pressurizing. However, Pt_3 may also be longer than or equal to one or more previous time periods of pressurizing. Typically, Pt_3 is from about 1 to about 25, from about 1 to about 20, from about 1 to about 15, from about 1 to about 12.5, from about 1 to about 10, from about 1 to about 7.5, from about 1 to about 5, or from about 1 to about 2, minutes. Typically, $(Pt_1 + Pt_2 + Pt_3) \leq (Tt_1 + Tt_2 + Tt_3)$.

[00153] The method can further comprise the step of maintaining the cavity 72 of the press 64 at P_{1-2} for $Pt_{<1}$ prior to pressurizing the cavity 72 of the press 64 to P_2 . The method further comprises the step of separating the cover 70 and the platform 68 of the press 64. Typically, pressure in the cavity 72 is reduced prior to separating the cover 70 and platform 68 to prevent damage to the peripheral seal 74 and/or composite article 22. As alluded to the above, the pressure tank 66 can be used to depressurize the cavity 72. In addition or alternatively, the press 64 can vent the compressed gas to the atmosphere in a rapid or controlled manner. The method can further comprise the step of maintaining vacuum on the vacuum canopy 36. This is typically done while the cavity 72 of the press 64 is pressurized.

[00154] The method further comprises the step of removing the tool 26 from the press 64. The carrier 86 can be used to push or pull the tool 26 from the platform 68 back to the support table

84 or another support table **84**. Referring to Figure 8, another embodiment of the press **64** is shown. One support table **84** can be used for loading and one support table **84** can be used for unloading. In this configuration, different tools **26** can be used to load the press **64** rather than using the previously unloaded tool **26**. This is not to say that a previously unloaded tool **26** cannot be loaded into the press **64** at a later time.

[00155] The method further comprises the step of removing the vacuum canopy **36** from the tool **26**. The vacuum canopy **36** may be removed manually or automatically. The method further comprises the step of removing the composite article **22** from the mold surface **24** of the tool **26**. The composite article **22** may be removed manually or automatically. Typically, the composite article **22** is at a temperature which can be handled by gloved (or bare) hand. The total of $Tt_1 + Tt_2 + Tt_3$ is as described above.

[00156] The present invention also provides a method of forming a preform **62**. The method may be referred to as a layup (or lay-up) method. The preform **62** may be used with the system **20** and/or invention methods described above to form the composite article **22**.

[00157] Referring to Figure 9, the method comprises the step of providing a mandrel **100** having a mandrel surface **102**. Various types of mandrels **100** can be employed. Suitable mandrels **100** are commercially available from a variety of suppliers. Specific examples of mandrels **100** include those commercially available from Models & Tools Inc.

[00158] Typically, the mandrel surface **102** of the mandrel **100** is complimentary to the mold surface **24** of the tool **26**. For example, the surfaces **24,102** may be in a female/male configuration. The mandrel **100** can be similar to the tool **26**. For example, the mandrel can have tubing **104** for conveying a fluid.

[00159] The tubing **104** includes at least one input **106** for communicating fluid to the tubing **104** and at least one outlet **108** for communicating fluid from the tubing **104**. The tubing **104** is proximal or directly in contact with the mandrel surface **102** to expedite heat transfer. The tubing **104** is useful for direct (rather than indirect) heating or cooling of the mandrel surface **102**. The tubing **104** may be formed into the mandrel **100** itself (such as by boring), or attached within the mandrel **100** proximal the mold surface **24**, either to the tool **26** and/or to the mold surface **24**. The tubing **104** can be arranged in various patterns and may be of equal or varying diameters, as like described above for the tool **26**.

[00160] The tubing **104** of the mandrel **100** is connected to piping (not shown) for communicating the fluid to and from the mandrel **100**. The mandrel **100** can be in fluid communication with the system **20** for heating or cooling the mandrel surface **102**.

Alternatively, the mandrel **100** can be in fluid communication with another type of system (not shown), such as a conventional oil- or water-based heating and/or cooling system, typically a water-based system.

5 [00161] The method further comprises the steps of providing pieces of a carbon fiber sheet **110** and providing the resin. The pieces of carbon fiber sheet **110** can be of various types, such as pieces **110** comprising the pre-pregs and/or carbon fiber mats described above. The resin can be of various types, such as the epoxies described above. The resin has a “tack” temperature, which is described further below.

10 [00162] The method further comprises the step of heating the mandrel surface **102** to a first temperature. The first temperature promotes adhesion of the resin to the mandrel surface **102** during preparation of the preform **62**. The first temperature generally corresponds to the tack temperature of the resin, where the resin adheres to both the mandrel surface **102** and to itself, such as adhesion between layers of the pieces **110**.

15 [00163] The tack temperature can be determined via testing or by reference to technical literature of the resin, such as from MSDS or technical data sheets. A typical test for determining tack involves placing a gloved finger or tool on a layer of the resin, and pulling the finger or tool away to determine at which point in temperature the resin adheres to the finger or tool when pulled away. The first temperature is typically of from about 100 to about 175, from about 110 to about 155, or from about 125 to about 140, °F (~38 to ~79, ~43 to ~68, or ~52 to
20 ~60, °C).

[00164] The method typically comprises the step of applying the resin to the mandrel surface **102** of the mandrel **100** to form a resin layer (not shown). The resin may be applied by various methods. For example, the resin may be applied by hand or robotic spraying, brushing, pouring, rolling, etc. Prior to applying the resin, a release liner or coating may be applied to the mandrel
25 surface **102** to prevent sticking of the preform **62**.

[00165] The method further comprises the step of arranging the pieces **110** on the resin layer to form a carbon fiber mat. The pieces **110** may be laid in a uniform layer and/or may overlap one another. Multiple layers of the pieces **110** can be arranged to build up thickness of the carbon fiber mat, and optionally, additional resin can be applied between the layers of the pieces **110**.
30 The method typically comprises the step of applying additional resin on top of the carbon fiber mat.

[00166] The method further comprises the step of disposing a vacuum sheet **112** on the mandrel **100** to define an envelope (not shown) between the vacuum sheet **112** and the mandrel surface

102 of the mandrel **100**. Typically, putty **114** is applied around a periphery of the mandrel **100** for making the envelope airtight. The putty **114** may be applied by various methods, such as by hand, robotic dispenser, etc. A release liner or coating may be applied between the vacuum sheet **112** and the preform **62** to prevent sticking. Rather than using the putty **114**, the vacuum sheet **112** may be configured similar to or the same as the vacuum sheet **36** described above with the tool **26**. In other words, the vacuum sheet **112** may include a peripheral seal (not shown).

[00167] The method further comprises the step of applying vacuum to the vacuum sheet **112** thereby evacuating the envelope to retain the preform **62** adjacent the mandrel surface **102** of the mandrel **100**. This is useful for consolidating the pieces **110** and further form the preform **62**.

This is also useful for keeping the preform **62** in contact with the mandrel surface **102** during heating and cooling. Vacuum can be applied at various pressures, such as from about 10 to about 35, from about 12.5 to about 32.5, or from about 15 to about 30, inches Hg.

[00168] The method further comprises the step of cooling the mandrel surface **102** to a second temperature. The second temperature allows the preform **62** to be released from the mandrel surface **102**. The second temperature is typically cooler than the first temperature, and generally corresponds to either a non-tack or less tacky temperature of the resin. The second temperature is typically from about 35 to about 100, about 40 to about 75, or about 40 to about 50, °F (~1.7 to ~38, ~4 to ~24, or ~4 to ~10, °C). Heating and cooling of the mandrel surface **102** can be controlled manually, or automatically, such as by another controller (not shown). The method further comprises the steps of removing the vacuum sheet **112** from the mandrel **100** and removing the preform **62** from the mandrel surface **102**. These steps can be manual or automatic.

[00169] In certain embodiments, the mandrel **100** can be attached to a manual or robotic arm (not shown), such that the mandrel **100** can be movable from a preparation position to a molding position. For example, in the preparation position, the preform **62** is formed on the mandrel **100**, with the mandrel surface **102** set at the first temperature to hold the preform **62** in place. After the preform **62** is formed, the mandrel **100** can then move to the molding position, where the temperature of the mandrel surface **102** is set to the second temperature, thereby allowing release of the preform **62** from the mandrel surface **102**. The preform **62** can then be disposed on the mold surface **24** of the tool **26** for further processing, such as directly moving or dropping the preform **62** from the mandrel **100** onto the mold surface **24**. Alternatively, the preform **62** can be stored or queued for later use in either the same or a different location.

[00170] Referring to Figure 10, various steps (or processes) may be carried out before and/or after formation of the composite article **22** in the press **64**. These steps can be used in various orders and combinations. These additional steps are merely examples, and are not to be construed as limitations of the present invention.

5 [00171] The pieces **110** for the preform **62** can be provided by a “kit cut” process. For example, a pre-preg sheet can be cut into the pieces **110** using computer driven cutting tables, which use data from a computer aided drafting (CAD) system and/or from digitized patterns and drawings. For precise cutting, the kit cut process may utilize a computer numerically controlled (CNC) work cell, which includes of a series of CNC and machining tools. Patterns and molds can be
10 made on-site, but may also be supplemented by 3rd parties, if needed. Similar to other raw materials, the pieces **110** can be cold stored in a freezer to preserve them in advance of a lay-up process.

[00172] The pieces **110** can be used to form preforms **62** with the mandrel **100** as described above. While automation is possible, the use of hand lay-up generally allows for designing
15 composite articles **22** with different strength requirements throughout the composite article **22** by laying down a kit of the pieces **110** that is unique to each mandrel **100**. In addition, hand lay-up can reduce material cost by eliminating unnecessary extra build-up of the resin.

[00173] After formation of the composite articles **22** via the press **64** and after removal from the tool **24**, they can be provided to a trim process. The composite articles **22** may be
20 mechanically trimmed and/or drilled by a robotic router. The use of the robotic router facilitates consistent accuracy as well as timely turnaround. The composite articles **22** may then be provided to a sub-assembly and bonding process. Composite articles **22** that may require bonding are prepped following the trim process and placed in a bonding cell where they are CNC bonded. The use of a robotic bonding cell provides a consistent adhesive path for bond
25 accuracy as well as quick turnaround.

[00174] The composite articles **22** may then be provided to a finishing process. Here, the composite articles **22** can be robotically or hand sanded. It is believed that while automated technology can streamline the finishing process, use of hand sanding helps to ensure Class A surface quality, if desired. Technicians identify and repair minor surface blemishes of the
30 composite articles **22**, if present. The composite articles **22** may then be provided to a prime process. The composite articles **22** can enter a paint line system for a high volume low pressure (HVLP) primer (or clear coat) application. The composite articles **22** may be washed prior to prevent contamination. Composite articles **22** having exposed carbon fiber weave can be clear

coated and shipped directly to a customer, while composite articles **22** which require color can be primed and may be sent to a 3rd party, e.g. an OEM approved supplier, to be painted before reaching a customer. The composite articles **22** may then be provided to a final inspection process. The composite articles **22** can be gauged and visually inspected to ensure dimensional
5 quality. Clear coated composite articles **22** can be provided to a finesse stage where they are polished to a jewel like finish before a final visual inspection prior to shipment to the customer.

[00175] The composite articles **22** formed from the invention methods have excellent mechanical properties and/or surface properties. For example, the composite articles **22** can have near Class A surfaces, with little to no surface blemishes relative to composite articles formed
10 via conventional autoclaving methods. More specifics of the composite articles **22** are described in the examples immediately below.

[00176] Additional embodiments, aspects, and benefits of the present invention may be appreciated with reference to the disclosures of: U.S. Provisional Patent Application Serial No. 61/410,753, entitled "METHOD OF MAKING COMPOSITE PARTS BY USING
15 MEMBRANE PRESS"; U.S. Provisional Patent Application Serial No. 61/495,661, entitled "RAPID CURE SYSTEM FOR THE MANUFACTURE OF COMPOSITE PARTS"; U.S. Provisional Patent Application Serial No. 61/418,521, entitled "SYSTEMS AND METHODS FOR FORMING COMPOSITE COMPONENTS"; International Application No. PCT/US2011/059434, entitled "THERMAL PROCESSING AND CONSOLIDATION
20 SYSTEM AND METHOD"; and International Application No. PCT/US2011/062836, entitled "METHOD AND SYSTEM FOR FORMING COMPOSITE ARTICLES"; all of which are incorporated herein by reference in their entirety to the extent they do not conflict with the general scope of the present invention.

[00177] The following examples, illustrating the system **20**, methods, and composite articles **22**
25 of the present invention, are intended to illustrate and not to limit the invention.

EXAMPLES

[00178] Comparative examples of composites articles are made by using a conventional autoclave and autoclaving method. Invention examples of composites articles are made by using
30 and the system and method of the present invention. Additional information regarding these examples is provided in Table I below and the subsequent description.

Table I

Example No.:	Comparative Example	Invention Example
Preform		
Carbon Fiber Mat No.:	1	1
Resin No:	1	1
Tool No.:	1	1
Curing Method:	Autoclave	System (20) + Press (64)
Heat Ramp Rate:	~5 °F/min (~2.8°C/min)	~180°F/min (~100°C/min)
Pressurize Ramp Rate:	~0.15 psi/sec (~1 kPa/sec)	~1 psi/sec (~7 kPa/sec)
Depressurize Ramp Rate:	~0.3 psi/sec (~2 kPa/sec)	~1 psi/sec (~7 kPa/sec)
<i>Total Cycle Time:</i>	72 mins	13 mins
<i>Temperature of Tool:</i> (after Total Cycle Time)	~180°F (~82°C)	~120°F (~49°C)
<i>Energy use in "X" units</i>	~2X	X
<i>Operating Costs in "X" units</i>	~5X	X

[00179] The preforms are formed by conventional lay-up methods. The preforms are shaped into car hoods. The carbon fiber mat is an exposed weave pre-preg, and the resin is a "quick cure" epoxy resin, which are both commercially available from Toray Composites (America), Inc. of Tacoma, WA.

[00180] The preforms are loaded into tool and covered with a vacuum sheet. The tools are the same in configuration and material. Vacuum is established and confirmed. The tools are disposed into the autoclave or press, respectively. The autoclave is closed and the started. The press is closed and started. The press is in fluid communication with the invention system.

[00181] Referring to Figure 14, specific parameters including temperature and pressure ramps and dwells for the autoclave can be better appreciated. Each of the TCs in Figure 14 refers to a temperature at a specific point on the mold surface of the tool. As can be appreciated, the autoclave fails to uniformly heat the mold surface at constant temperatures. It is believed that this lack of uniform heat soaking imparts the composite articles formed in the autoclave with various problems, such as surface blemishes. Referring to Figure 11, specific parameters including temperature and pressure ramps and dwells for the press can be better appreciated.

[00182] Figure 12 illustrates a second invention example (not shown in Table I above). Figure 13 illustrates a third invention example (also not shown in Table I above). As can be appreciated with reference to Figures 12 and 13, the invention system is capable of rapidly heating the mold surface in a short period of time. In addition, a dwell is not required to reach a peak temperature.

5 Instead, the peak temperature can be quickly reached within a very short period of initial time based on the rapid heating capability of the invention system.

[00183] Referring to Figure 11, temperature of the mold surface of the tool ramps from T_1 to T_{1-2} using the heater-subsystem and controller. Specifically, the controller directs a portion of the mass of heated fluid from the tank of the heater-subsystem to the tool using the valves until
10 T_{1-2} is reached.

[00184] Once T_{1-2} is reached, the controller stops flow from the tank by using the valves and the heater-subsystem begins to re-circulate to recharge the mass of heated fluid. T_{1-2} is maintained at an acceptable tolerance level by the controller modulating additional flow of the mass of heated fluid to the tool, as needed. During $T_{t<1}$, it is believed that the resin is at or near its lowest
15 viscosity. Having the resin at such a viscosity allows any trapped air or resin byproducts created during cure of the resin (e.g. steam) to evacuate from the composite article.

[00185] While the tool is being heated to temperature T_{1-2} , the cavity of the press is pressurized to P_{1-2} . Specifically, the controller directs the pressure tank to provide compressed air to the cavity. Once P_{1-2} is reached, the controller stops flow from the pressure tank. P_{1-2} is maintained
20 at an acceptable tolerance level by the controller modulating additional flow of compressed air to the cavity, as needed.

[00186] Once $T_{t<1}$ passes, the controller directs another portion (or all of) the mass of heated fluid to the tool until the mold surfaces reaches T_2 . Once T_2 is reached, the controller stops flow from the tank by using the valves and the heater-subsystem begins to re-circulate to recharge the
25 mass of heated fluid. T_2 is maintained at an acceptable tolerance level by the controller modulating additional flow of the mass of heated fluid to the tool, as needed. During T_{t2} , it is believed that the resin is at or near its cure temperature. It is believed that having the resin at such a temperature imparts the composite article with excellent surface and mechanical properties. This temperature can be determined via testing or by reference to technical literature
30 of the resin, such as from MSDS or technical data sheets.

[00187] While the tool is being heated to temperature T_2 , the cavity of the press is pressurized to P_2 . Specifically, the controller directs the pressure tank to provide compressed air to the cavity. Vacuum is maintained while pressure is applied. Once P_2 is reached, the controller stops

flow from the pressure tank. P_2 is maintained at an acceptable tolerance level by the controller modulating additional flow of compressed air to the cavity, as needed. Once P_{t2} passes, the controller directs the press to depressurize. Specifically, the press begins to vent the compressed air to the atmosphere over P_{t3} . The press may do a complete “dump” of the air, i.e., air does not
5 need to be released at a controlled rate.

[00188] In certain examples utilizing systems as depicted in Figure 2, once T_{t2} passes, the controller directs a portion of the mass of cooled fluid from the tank of the chiller-subsystem to the tool using the valves until T_3 is reached. Prior to or while the heater-subsystem was previously being used, the controller directed the chiller-subsystem to form and maintain the
10 mass of cooled fluid using the valves, tank, and chiller. While the chiller-subsystem is being used, the controller directs the heater-subsystem to recharge and maintain the mass of heated fluid using the valves, tank, and heater. As such, the system is ready for a subsequent cycle immediately after a short period of time.

[00189] In other examples utilizing systems as depicted in Figure 18, once T_{t2} passes, the
15 controller directs a portion of the mass of cooled fluid from the tank of the chiller-subsystem to the exchanger-subsystem using the valves until T_3 is reached. Prior to or while the heater-subsystem was previously being used, the controller directed the chiller-subsystem to form and maintain the mass of cooled fluid using the valves, tank, and chiller. While the chiller-subsystem is being used, the controller directs the heater-subsystem to recharge and maintain the mass of
20 heated fluid using the valves, tank, and heater. As such, the system is ready for a subsequent cycle immediately after a short period of time.

[00190] After each of the cycles is complete, the tools are removed from the autoclave and press. Performance of each cycle is evaluated on an appearance basis of the composite articles formed via each method. Specifically, the composite articles are removed from the tools and
25 their surfaces are wiped with white talcum powder to highlight surface blemishes. Pits and/or dry-lines present on the surface of the composite articles are highlighted by the talcum powder. Specifically, such defects are seen as white dots (pits) or white streaks (dry-lines). A pit or dry-line is where the resin has not properly flowed during the cycle thereby leaving a void on the surface.

[00191] The composite articles made by the invention system and method have excellent
30 surface properties relative to those made by the autoclave. Specifically, the composite articles formed via the invention system and method have an ~85 to 90% reduction in the amount of pits and dry-lines relative to those formed in the autoclave. In addition, the composite articles

formed via the invention system and method have an ~85% to 90% reduction in the severity (depth/width) of pits and dry-lines relative to those formed in the autoclave. Such defects have to be repaired (filled and sanded) in order for the surface of the composite article to be considered Class A.

5 [00192] Referring back to Table I above, the invention system and method also has over an ~80% reduction in cycle time relative to the autoclave process (13 mins vs. 72 mins). In addition, the tools are over 30% cooler in temperature after being removed from the press relative to those removed from the autoclave: ~120°F (~49°C) vs. ~180°F (~82°C). As such, the invention system and method allows for a significant reduction in cycle time and overall
10 manufacturing time while providing higher quality composite articles, as compared to those formed using the autoclave.

[00193] It is to be understood that the appended claims are not limited to express and particular compounds, compositions, or methods described in the detailed description, which may vary between particular embodiments which fall within the scope of the appended claims. With
15 respect to any Markush groups relied upon herein for describing particular features or aspects of various embodiments, it is to be appreciated that different, special, and/or unexpected results may be obtained from each member of the respective Markush group independent from all other Markush members. Each member of a Markush group may be relied upon individually and or in combination and provides adequate support for specific embodiments within the scope of the
20 appended claims.

[00194] It is also to be understood that any ranges and subranges relied upon in describing various embodiments of the present invention independently and collectively fall within the scope of the appended claims, and are understood to describe and contemplate all ranges including whole and/or fractional values therein, even if such values are not expressly written
25 herein. One of skill in the art readily recognizes that the enumerated ranges and subranges sufficiently describe and enable various embodiments of the present invention, and such ranges and subranges may be further delineated into relevant halves, thirds, quarters, fifths, and so on. As just one example, a range “of from 0.1 to 0.9” may be further delineated into a lower third, i.e., from 0.1 to 0.3, a middle third, i.e., from 0.4 to 0.6, and an upper third, i.e., from 0.7 to 0.9,
30 which individually and collectively are within the scope of the appended claims, and may be relied upon individually and/or collectively and provide adequate support for specific embodiments within the scope of the appended claims. In addition, with respect to the language which defines or modifies a range, such as “at least,” “greater than,” “less than,” “no more

than,” and the like, it is to be understood that such language includes subranges and/or an upper or lower limit. As another example, a range of “at least 10” inherently includes a subrange of from at least 10 to 35, a subrange of from at least 10 to 25, a subrange of from 25 to 35, and so on, and each subrange may be relied upon individually and/or collectively and provides
5 adequate support for specific embodiments within the scope of the appended claims. Finally, an individual number within a disclosed range may be relied upon and provides adequate support for specific embodiments within the scope of the appended claims. For example, a range “of from 1 to 9” includes various individual integers, such as 3, as well as individual numbers including a decimal point (or fraction), such as 4.1, which may be relied upon and provide
10 adequate support for specific embodiments within the scope of the appended claims.

[00195] The present invention has been described herein in an illustrative manner, and it is to be understood that the terminology which has been used is intended to be in the nature of words of description rather than of limitation. Many modifications and variations of the present invention are possible in light of the above teachings. The present invention may be practiced
15 otherwise than as specifically described within the scope of the appended claims. The subject matter of all combinations of independent and dependent claims, both singly and multiply dependent, is herein expressly contemplated.

CLAIMS

What is claimed is:

1. A thermal system (20) for rapidly heating and cooling a mold surface (24) of a tool (26) used for forming a composite article (20), said thermal system (20) comprising:

I) a heater-subsystem (40) in fluid communication with the tool (26) and comprising;

a heater (42) for heating a first thermal fluid,

a tank (44) in fluid communication with said heater (42) and containing a mass of heated first thermal fluid, and

a three-way valve (46) in fluid communication i) between said tank (44) and said heater (42) for re-circulating the first thermal fluid from said tank (44) to said heater (42) and ii) between said tank (44) and the tool (26) for directing the first thermal fluid from said tank (44) to the tool (26);

II) an exchanger-subsystem (49) in fluid communication with said heater-subsystem (40) and the tool (26) and comprising;

an exchanger (51) for cooling the first thermal fluid returning from the tool (26), and

a three-way valve (53) in fluid communication i) between said exchanger (51) and said heater-subsystem (40) for sending the first thermal fluid from the tool (26) back to the heater-subsystem (40) and ii) between said exchanger (51) and the tool (26) for directing the first thermal fluid from the tool (26) to said exchanger (51); and

III) a chiller-subsystem (48) in fluid communication with said exchanger-subsystem (49) and comprising;

a chiller (50) to cool a second thermal fluid,

a tank (52) in fluid communication with said chiller (50) and containing a mass of cooled second thermal fluid, and

a three-way valve (54) in fluid communication i) between said tank (52) and said chiller (50) for re-circulating the second thermal fluid from said tank (52) to said chiller (50) and ii) between said tank (52) and said exchanger-subsystem (49) for directing the second thermal fluid from said tank (52) to said exchanger (51).

2. The thermal system as set forth in claim 1 further comprising a controller (56) in communication with said subsystems (40,48,49) and the tool (26) for directing the thermal fluids within the thermal system (20) via control of the three-way valves (46,53,54).

3. The thermal system (20) as set forth in claim 2 wherein said controller (56) is programmed to instruct said three-way valve (46) of said heater-subsystem (40) such that the first thermal fluid re-circulates between said heater (42) and said tank (44) and bypasses the tool (26) to maintain the mass of heated first thermal fluid in said heater-subsystem (40).

4. The thermal system (20) as set forth in claim 2 wherein said controller (56) is programmed to instruct said three-way valve (46) of said heater-subsystem (40) such that the first thermal fluid is directed from said heater-subsystem (40) to the tool (26) to heat the mold surface (24) of the tool (26).

5. The thermal system (20) as set forth in any one of claims 2 through 4, wherein said controller (56) is programmed to instruct said three-way valve (54) of said chiller-subsystem (48) such that the second thermal fluid re-circulates between said chiller (50) and said tank (52) and bypasses said exchanger-subsystem (49) to maintain the mass of cooled second thermal fluid in said chiller-subsystem (48).

6. The thermal system (20) as set forth in any one of claims 2 through 4, wherein said controller (56) is programmed to instruct said three-way valve (54) of said chiller-subsystem (48) such that the second thermal fluid is directed from said chiller-subsystem (48) to said exchanger-subsystem (49) to cool the first thermal fluid returning from the tool (26) and entering said exchanger-subsystem (49).

7. The thermal system (20) as set forth in any one of claims 2 through 6, wherein said controller (56) is programmed to instruct said three-way valve (53) of said exchanger-subsystem (49) such that the first thermal fluid returning from the tool (26) is directed to said heater-subsystem (40) and bypasses said exchanger-subsystem (49) to reheat the first thermal fluid within said heater-subsystem (40).

8. The thermal system (20) as set forth in any one of claims 2 through 6, wherein said controller (56) is programmed to instruct said three-way valve (53) of said exchanger-subsystem (49) such that the first thermal fluid returning from the tool (26) is directed to said exchanger-subsystem (49) to cool the first thermal fluid via the second thermal fluid from the chiller-subsystem (48).

9. The thermal system (20) as set forth in any one of claims 1 through 8, further comprising a pump (55) in fluid communication between the tool (26), said heater-subsystem (40), and said exchanger-subsystem (49), for directing the first thermal fluid from said subsystems (40,49) to the tool (26).

10. The thermal system (20) as set forth in any one of claims 1 through 9, further comprising at least one supplemental valve (58) in fluid communication i) between said heater-subsystem (40) and the tool (26) and/or ii) between said exchanger-subsystem (49) and the tool (26) for directing the first thermal fluid to and from the tool (26) and said subsystem(s)(40,49).

11. The thermal system (20) as set forth in any one of claims 1 through 10, wherein; the first thermal fluid is shared between said heater-subsystem (40) and said exchanger-subsystem (49),

the second thermal fluid is shared between said chiller-subsystem (48) and said exchanger-subsystem (49), and

the first thermal fluid is kept separate from the second thermal fluid.

12. The thermal system (20) as set forth in any one of claims 1 through 11, wherein the first thermal fluid is different from the second thermal fluid.

13. The thermal subsystem (20) as set forth in any one of claims 1 through 12, wherein the first thermal fluid comprises thermal oil.

14. The thermal system (20) as set forth in any one of claims 1 through 13, wherein the second thermal fluid comprises water.

15. The thermal system (20) as set forth in any one of claims 1 through 14, wherein; the mold surface (24) of the tool (26) heats at a rate of greater than 60°F (~33°C) per minute via the heater-subsystem (40), and

the mold surface (24) of the tool (26) cools at a rate of greater than 40°F (~22°C) per minute via the exchanger-subsystem (49) and the chiller-subsystem (48).

16. The thermal system (20) as set forth in claim 15, wherein; the mold surface (24) of the tool (26) heats at a rate of greater than 70°F (~39°C) per minute via the heater-subsystem (40), and

the mold surface of the tool (26) cools at a rate of greater than 50°F (~28°C) per minute via the exchanger-subsystem (49) and the chiller-subsystem (48).

17. The thermal system (20) as set forth in any one of claims 1 through 16, further comprising;

a tool-connection system (200) operatively connected to said tool (26), and
a press-connection system (218) in fluid communication with said heater-subsystem (40) and said exchanger-subsystem (49),

wherein said connection systems (200,218) couple together for feeding and receiving the first thermal fluid to and from said tool (26).

18. The thermal system (20) as set forth in claim 17 wherein said tool (26) includes tubing (28) opposite said mold surface (26) and said press-connection system (218) is operatively connected to said tubing (28) for heating and cooling said mold surface (26) with the first thermal fluid.

19. The thermal system (20) as set forth in claim 17 or 18, further comprising a press (64) having a platform (68) and a cover (70) facing said platform (68) with said cover (70) operable to couple with said platform (68) to define a cavity (72) operable to maintain a pressurized and/or temperature controlled environment and wherein said press-connection system (218) is operatively connected through said cover (70) and/or said platform (68) into the cavity (72) for coupling with said tool-connection system (200) while said tool (26) is disposed within the cavity (70) of the press (64) for heating and cooling said mold surface (26) with the first thermal fluid.

20. A composite article (22) formed via the thermal system (20) as set forth in any one of claims 1 through 19.

21. A method of rapidly heating and cooling a mold surface (24) of a tool (26) used for forming a composite article (22), said method comprising the steps of:

providing a heater-subsystem (40) in fluid communication with the tool (26) and comprising;

a heater (42) for heating a first thermal fluid,

a tank (44) in fluid communication with the heater (42) and containing a mass of heated first thermal fluid, and

a three-way valve (46) in fluid communication i) between the tank (44) and the heater (42) for re-circulating the first thermal fluid from the tank (44) to the heater (42) and ii) between the tank (44) and the tool (26) for directing the first thermal fluid from the tank (44) to the tool (26);

providing an exchanger-subsystem (49) in fluid communication with the heater-subsystem (40) and the tool (26) and comprising;

an exchanger (51) for cooling the first thermal fluid returning from the tool (26), and

a three-way valve (53) in fluid communication i) between the exchanger (51) and the heater-subsystem (40) for sending the first thermal fluid from the tool (26) back to the heater-subsystem (40) and ii) between the exchanger (51) and the tool (26) for directing the first thermal fluid from the tool (26) to the exchanger (51); and

providing a chiller-subsystem (48) in fluid communication with the exchanger-subsystem (49) and comprising;

a chiller (50) to cool a second thermal fluid,

a tank (52) in fluid communication with the chiller (50) and containing a mass of cooled second thermal fluid, and

a three-way valve (54) in fluid communication i) between the tank (52) and the chiller (50) for re-circulating the second thermal fluid from the tank (52) to the chiller (50) and ii) between the tank (52) and the exchanger-subsystem (49) for directing the second thermal fluid from the tank (52) to the exchanger (51);

providing a controller (56) in communication with the tool (26) and the subsystems (40,48,49) for instructing the subsystems (40,48,49);

directing the mass of heated first thermal fluid from the tank (44) of the heater-subsystem (40) to the tool (26) via the controller (56) to heat the mold surface (24) of the tool (26) from a first temperature (T_1) to a second temperature (T_2) within a first period of time (T_{t1});

directing the mass of heated first thermal fluid from the tank (44) of the heater-subsystem (40) to the mold surface (24) of the tool (26) via the controller (56) to maintain the mold surface (24) at T_2 for a second period of time (T_{t2}); and

directing the mass of cooled second thermal fluid from the tank (52) of the chiller-subsystem (48) to the exchanger-subsystem (49) via the controller (56) to cool the mold surface (24) of the tool (26) from T_2 to a third temperature (T_3) within a third period of time (T_{t3});

wherein the mold surface (24) of the tool (26) heats at a rate of greater than 60°F (~33°C) per minute and cools at a rate of greater than 40°F (~22°C) per minute; and

wherein $T_{t1} + T_{t2} + T_{t3}$ is no greater than 20 minutes.

22. The method as set forth in claim 21 wherein $T_{t1} + T_{t2} + T_{t3}$ is no greater than 18 minutes.

23. The method as set forth in claim 21 or 22, wherein the controller (56) instructs the three-way valve (46) of the heater-subsystem (40) such that the first thermal fluid re-circulates between the heater (42) and the tank (44) and bypasses the tool (26) to maintain the mass of heated first thermal fluid in the heater-subsystem (40) at a temperature of T_2 or higher.

24. The method as set forth in any one of claims 21 through 23, wherein the controller (56) instructs the three-way valve (46) of the heater-subsystem (40) such that the first thermal fluid is directed from the heater-subsystem (40) to the tool (26) to heat the mold surface (24) of the tool (26) from T_1 to T_2 .

25. The method as set forth in any one of claims 21 through 24, wherein the controller (56) instructs the three-way valve (54) of the chiller-subsystem (48) such that the second thermal fluid re-circulates between the chiller (50) and the tank (52) and bypasses the exchanger-subsystem (49) to maintain the mass of cooled second thermal fluid in the chiller-subsystem (48) at a temperature of T_3 or lower.

26. The method as set forth in any one of claims 21 through 25, wherein the controller (56) instructs the three-way valve (54) of the chiller-subsystem (48) such that the second thermal fluid is directed from the chiller-subsystem (48) to the exchanger-subsystem (49) to cool the first thermal fluid returning from the tool (26) and entering the exchanger-subsystem (49) to a temperature lower than T_2 .

27. The method as set forth in any one of claims 21 through 26, wherein the controller (56) instructs the three-way valve (53) of the exchanger-subsystem (49) such that the first thermal fluid returning from the tool (26) is directed to the heater-subsystem (40) and bypasses the exchanger-subsystem (49) to reheat the first thermal fluid within the heater-subsystem (40) to a temperature of T_2 or higher.

28. The method as set forth in any one of claims 21 through 27, wherein the controller (56) instructs the three-way valve (53) of the exchanger-subsystem (49) such that the first thermal fluid returning from the tool (26) is directed to the exchanger-subsystem (49) to cool the first thermal fluid via the second thermal fluid from the chiller-subsystem (48) to a temperature lower than T_2 .

29. The method as set forth in any one of claims 21 through 28, further comprising the step of maintaining the mold surface (24) of the tool (26) at an intermediate temperature (T_{1-2}) of between T_1 and T_2 via the controller (56) for a portion of Tt_1 ($Tt_{<1}$) prior to heating the mold surface (24) of the tool (26) to T_2 .

30. The method as set forth in claim 29 wherein T_{1-2} is from 100°F (~38°C) to 350°F (~177°C).

31. The method as set forth in claim 29 or 30, wherein $Tt_{<1}$ is from 1 to less than 10 minutes.

32. The method as set forth in any one claims 21 through 31, wherein T_1 is from 50°F (10°C) to 125°F (~52°C).

33. The method as set forth in any one claims 21 through 32, wherein T_2 is from 250°F (~121°C) to 400°F (~204°C).

34. The method as set forth in any one claims 21 through 33, wherein T_3 is from 75°F (~24°C) to 150°F (~66°C).

35. The method as set forth in any one claims 21 through 34, wherein Tt_1 is from 1 to 10 minutes, provided that $Tt_1 + Tt_2 + Tt_3$ is no greater than 20 minutes.

36. The method as set forth in any one claims 21 through 35, wherein Tt_2 is from 1 to 10 minutes, provided that $Tt_1 + Tt_2 + Tt_3$ is no greater than 20 minutes.

37. The method as set forth in any one claims 21 through 36, wherein Tt_3 is from 1 to 10 minutes, provided that $Tt_1 + Tt_2 + Tt_3$ is no greater than 20 minutes.

38. The method as set forth in any one claims 21 through 37, wherein the mass of heated first thermal fluid in the tank (44) of the heater-subsystem (40) is at a temperature of T_2 or higher for heating the mold surface (24) of the tool (26) with the mass of heated fluid.

39. The method as set forth in any one claims 21 through 38, wherein the mass of cooled second thermal fluid in the tank (52) of the chiller-subsystem (48) is at a temperature of T_3 or lower for cooling the mold surface of the tool (26).

40. A composite article (22) formed via the method as set forth in any one of claims 21 through 39.

41. The composite article (22) as set forth in claim 20 or 40, comprising a carbon fiber mat and a resin.




FIG. 1




FIG. 2




FIG. 3

FIG. 4

FIG. 5





FIG. 6






FIG. 7




FIG. 8




FIG. 10




FIG. 9




FIG. 11




FIG. 12




FIG. 13




FIG. 15




FIG. 16




FIG. 17




FIG. 18

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2012/048832

A. CLASSIFICATION OF SUBJECT MATTER
INV. B29C35/00
ADD.
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
Minimum documentation searched (classification system followed by classification symbols)
B29C B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	Akihiko Kitano ET AL: "The CFRP automobile body project in Japan", 20 November 2006 (2006-11-20), XP55041754, Retrieved from the Internet: URL:http://www.sampejapan.gr.jp/graphics/main/reikai/117/NED020061120_abstract.pdf [retrieved on 2012-10-22] pages 1-5,10; figures 1, 3-6	20,40,41
A	JP H01 125609 U (SAUDEN KABUSHIKI KAISHA) 28 August 1989 (1989-08-28) figure 6	1,21
A	EP 2 095 801 A1 (MCNEIL PPC INC [US]) 2 September 2009 (2009-09-02) paragraph [0029]; figure 6	1,21
	----- -/--	

Further documents are listed in the continuation of Box C. See patent family annex.

* Special categories of cited documents :

<p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier application or patent but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p>	<p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&" document member of the same patent family</p>
---	---

Date of the actual completion of the international search 15 November 2012	Date of mailing of the international search report 23/11/2012
--	---

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Gemeinböck, Gerald
--	---

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2012/048832

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 3 860 382 A (SPILLER BASIL HARRY ROYSTON ET AL) 14 January 1975 (1975-01-14) column 1; figure 4 column 5, line 52 - column 7, line 34 -----	1,21
A	Adolf Illig: "Varianten der Kühlkreisläufe" In: "Thermoformen in der Praxis", 1 January 2008 (2008-01-01), Hanser Verlag, 2008, XP55041723, ISBN: 978-3-44-640794-7 pages 289-289, figure 22.1 -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/US2012/048832

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP H01125609	U	28-08-1989	NONE
EP 2095801	A1	02-09-2009	AU 2009200794 A1 17-09-2009
			CA 2656464 A1 29-08-2009
			EP 2095801 A1 02-09-2009
			JP 2009207894 A 17-09-2009
			US 2009218729 A1 03-09-2009
US 3860382	A	14-01-1975	BE 795718 A1 18-06-1973
			CA 1012716 A1 28-06-1977
			CH 573298 A5 15-03-1976
			DE 2308843 A1 30-08-1973
			FR 2173153 A1 05-10-1973
			GB 1408041 A 01-10-1975
			IT 984389 B 20-11-1974
			NL 7302415 A 27-08-1973
			US 3860382 A 14-01-1975