




(86) **Date de dépôt PCT/PCT Filing Date:** 2015/03/26
(87) **Date publication PCT/PCT Publication Date:** 2015/10/01
(45) **Date de délivrance/Issue Date:** 2018/01/02
(85) **Entrée phase nationale/National Entry:** 2016/09/22
(86) **N° demande PCT/PCT Application No.:** JP 2015/059392
(87) **N° publication PCT/PCT Publication No.:** 2015/147170
(30) **Priorité/Priority:** 2014/03/27 (JP2014-066995)

(51) **Cl.Int./Int.Cl.** *F27D 27/00* (2010.01),
F27D 3/14 (2006.01), *B22D 1/00* (2006.01),
B22D 27/02 (2006.01), *B22D 35/00* (2006.01)
(72) **Inventeur/Inventor:**
TAKAHASHI, KENZO, JP
(73) **Propriétaire/Owner:**
TAKAHASHI, KENZO, JP
(74) **Agent:** FETHERSTONHAUGH & CO.

(54) **Titre : APPAREIL DE MELANGE DE METAL FONDU ET DISPOSITIF DE TRANSFERT DE METAL FONDU**
(54) **Title: MOLTEN METAL STIRRING DEVICE AND MOLTEN METAL TRANSFER DEVICE**



(57) **Abrégé/Abstract:**

[Problem] There are provided an efficient molten metal stirring device and an efficient molten metal transfer device. [Solution] There are provided an efficient molten metal stirring device and an efficient molten metal transfer device, which device is adapted to stir or transfer molten metal by a resultant driving force of a first electromagnetic force and a second electromagnetic force according to Fleming's rule. The first electromagnetic force is caused by eddy currents generated in the molten metal using magnetic lines of force generated from a rotating permanent magnet, and the second electromagnetic force according to Fleming's rule is generated by the intersection between the magnetic lines of force and a current that flows between a pair of electrodes provided in advance.

ABSTRACT

[Problem] There are provided an efficient molten metal stirring device and an efficient molten metal transfer device.

- 5 [Solution] There are provided an efficient molten metal stirring device and an efficient molten metal transfer device, which device is adapted to stir or transfer molten metal by a resultant driving force of a first electromagnetic force and a second electromagnetic force according to Fleming's rule. The first electromagnetic force is caused by eddy
10 currents generated in the molten metal using magnetic lines of force generated from a rotating permanent magnet, and the second electromagnetic force according to Fleming's rule is generated by the intersection between the magnetic lines of force and a current that flows between a pair of electrodes provided in advance.

MOLTEN METAL STIRRING DEVICE AND MOLTEN METAL TRANSFER DEVICE

BACKGROUND OF THE INVENTION

5 Field of the Invention

[0001]

The present invention relates to a molten metal stirring device that stirs molten metal formed of metal having conductivity (electrical conductivity), that is, molten metal formed of nonferrous metal (for
10 example, Al, Cu, Zn, Si, an alloy including them as main components, a Mg alloy, or the like), or molten metal formed of metal other than nonferrous metal, and a molten metal transfer device that transfers molten metal formed of these kinds of metal.

15 Background Art

[0002]

Various techniques for stirring molten metal formed of nonferrous metal or molten metal formed of other metal are developed and widely used in industry, but expectations for the development and provision of
20 techniques and devices made in consideration of the future of the earth, such as environmental issues and energy issues, are rapidly increasing. There are many recent stirring devices that employ permanent magnets as a drive principle. For example, there are a device that accelerates molten metal in a flow passage, discharges the molten metal into a main
25 bath, and stirs the molten metal (Prior Art Document 1); a device that stirs molten metal present in a furnace by a rotating-shifting magnetic field generator installed outside the bottom of the furnace (Prior Art Document 2); a device that includes a rotating magnetic field unit installed outside a side wall of a furnace (Prior Art Document 3); and the
30 like. It is evaluated that the stirring effects of all these devices are very excellent.

[0003]

Meanwhile, the advancement of technology in industry is significant, and needs of industry also gradually become high. That is,
35 there is a demand for a molten metal stirring device that has a stirring effect corresponding to purposes, such as a low price, a small size, a

20375-1080

2

small weight, easy maintenance, a simple structure, improved usability, and a large stirring capacity. However, as far as an inventor knows, a molten metal stirring device, which meets this demand, is not yet provided at present. Further, a device having the above-mentioned characteristics is not provided yet as a molten metal transfer device for transferring molten metal, which is formed of these kinds of metal, from one main bath to the other main bath.

Prior Art Document

[0004]

1: Japanese Patent No. 4376771

10 2: Japanese Patent No. 4245673

3: JP 2011-106689 A

SUMMARY OF THE INVENTION

[0005]

15 An aspect of the present disclosure is directed to the provision of a device that meets the above-mentioned needs.

[0006] According to an aspect of the present invention, there is provided a molten metal stirring device comprising:

a furnace main body that includes a storage chamber for storing molten metal formed of conductive metal; and

20 a rotating-shifting magnetic field unit main body that is rotatable to drive and stir the molten metal stored in the furnace main body,

wherein the rotating-shifting magnetic field unit main body includes a permanent magnet, so that input/output magnetic lines of force, which go out of the permanent magnet or enter the permanent magnet, move with the rotation of the rotating-shifting magnetic field unit main body while penetrating the molten metal, in order that a first electromagnetic force for driving the molten metal is generated by

25

20375-1080

3

eddy currents that are generated by the movement of the input/output magnetic lines of force,

the furnace main body includes at least a pair of electrodes that allow current to flow through the molten metal,

5 the pair of electrodes are provided in the storage chamber at positions where the current flowing between the pair of electrodes and the input/output magnetic lines of force intersect each other and generate a second electromagnetic force for driving the molten metal in the same direction as the first electromagnetic force, and

10 the molten metal stored in the storage chamber is driven and stirred by a resultant driving force of the first and second electromagnetic forces.

[0007]

According to another aspect of the present invention, there is provided a molten metal stirring device comprising:

15 a main bath that includes a furnace main body including a storage chamber for storing molten metal formed of conductive metal; and

a stirring unit that drives and stirs the molten metal stored in the furnace main body,

20 wherein the stirring unit includes a passage member that includes a molten metal passage for circulation for allowing the molten metal stored in the furnace main body to flow out and then flow into the furnace main body and a rotating-shifting magnetic field unit main body that is rotatable and generates a first electromagnetic force for driving the molten metal present in the molten metal passage,

25 the rotating-shifting magnetic field unit main body includes a permanent magnet,

20375-1080

4

the furnace main body includes a molten metal outlet and a molten metal inlet that are formed in a side wall,

the molten metal outlet and the molten metal inlet communicate with each other through the passage member so as to allow the circulation of the molten metal that flows out of the furnace main body and flows into the furnace main body through the molten metal passage,

the rotating-shifting magnetic field unit main body is provided outside the passage member and is adapted to be rotatable about a vertical axis extending in a height direction, so that input/output magnetic lines of force, which go out of the permanent magnet or enter the permanent magnet, move with the rotation of the rotating-shifting magnetic field unit main body while penetrating the molten metal present in the molten metal passage, in order that the first electromagnetic force is generated by eddy currents that are generated by the movement of the input/output magnetic lines of force, so that the molten metal is driven toward the molten metal inlet from the molten metal outlet in the molten metal passage by the first electromagnetic force,

at least a pair of electrodes are provided in the molten metal passage of the passage member so that a current flows between the pair of electrodes through the molten metal,

the pair of electrodes are provided in the molten metal passage at positions where the current flowing between the pair of electrodes and the input/output magnetic lines of force intersect each other and generate a second electromagnetic force for driving the molten metal in the same direction as the first electromagnetic force, and

the molten metal present in the molten metal passage is driven toward the molten metal outlet by a resultant driving force of the first and second electromagnetic forces so that the molten metal stored in the storage chamber is driven.

20375-1080

5

[0008]

According to another aspect of the present invention, there is provided a molten metal stirring device comprising:

5 a main bath that includes a furnace main body including a storage chamber for storing molten metal formed of conductive metal; and

a stirring unit including a stirring furnace that includes a stirring chamber for storing molten metal, and a rotating-shifting magnetic field unit main body that is rotatable and drives the molten metal stored in the stirring chamber, the rotating-shifting magnetic field unit main body including a permanent magnet,

10 wherein the storage chamber and the stirring chamber communicate with each other through an opening,

a partition plate stands upright in a vertical direction in the stirring chamber,

15 the opening is divided into a first opening and a second opening by the partition plate,

the stirring chamber is divided into a first chamber communicated to the first opening and a second chamber communicated to the second opening,

20 a gap is formed between a rear end of the partition plate and an inner surface of a side wall of the stirring unit and the first and second chambers communicate with each other through the gap,

the rotating-shifting magnetic field unit main body is provided outside the stirring chamber below or above the stirring chamber so as to be rotatable about a vertical axis extending in the vertical direction, so that input/output magnetic lines of force, which go out of the permanent magnet or enter the permanent magnet, are
25 moved by the rotation of the rotating-shifting magnetic field unit main body while

20375-1080

5a

penetrating the molten metal stored in the stirring unit, in order that a first electromagnetic force is generated by eddy currents that are generated by the movement of the input/output magnetic lines of force, so that the molten metal is driven toward the second chamber from the first chamber through the gap by the first
5 electromagnetic force,

a pair of electrodes are provided in the stirring chamber at positions where a current flowing between the pair of electrodes and the magnetic lines of force generated from the permanent magnet intersect each other and generate a second electromagnetic force for driving the molten metal in the same direction as
10 the first electromagnetic force, and

the molten metal stored in the first chamber is sent toward the second chamber through the gap and is allowed to flow into the storage chamber from the second opening by a resultant driving force of the first and second electromagnetic forces so that the molten metal stored in the storage chamber is driven.

15 [0009]

According to another aspect of the present invention, there is provided a molten metal transfer device that transfers molten metal to a second melting furnace from a first melting furnace, the molten metal transfer device comprising:

a passage member that includes a passage allowing the first and
20 second melting furnaces to communicate with each other,

wherein a rotating-shifting magnetic field unit main body, which is rotatable to drive molten metal present in the passage, is provided outside a middle portion of the passage member,

the rotating-shifting magnetic field unit main body includes a permanent
25 magnet,

20375-1080

5b

input/output magnetic lines of force, which go out of the permanent magnet or enter the permanent magnet, are moved by the rotation of the rotating-shifting magnetic field unit main body while

penetrating the molten metal present in the passage,

a first electromagnetic force for driving the molten metal present in the passage toward the second melting furnace from the first melting furnace is generated by eddy currents that are generated by the movement of the input/output magnetic lines of force,

the passage member includes a pair of electrodes that are provided therein and allow current to flow through the molten metal,

the pair of electrodes are provided at positions where the current flowing between the pair of electrodes and the input/output magnetic lines of force intersect each other and generate a second electromagnetic force for driving the molten metal in the same direction as the first electromagnetic force, and

the molten metal present in the passage is driven toward the second melting furnace from the first melting furnace by a resultant driving force of the first and second electromagnetic forces.

BRIEF DESCRIPTION OF THE DRAWINGS

[0010]

FIG. 1 is a diagram illustrating the principle of the invention.

FIG. 2A is a plan view of a molten metal stirring device according to a first embodiment of the invention.

FIG. 2B is a vertical sectional view taken along line b-b of FIG. 2A.

FIG. 3A is a front view of a rotating-shifting magnetic field unit main body.

FIG. 3B is a side view of the rotating-shifting magnetic field unit main body.

FIG. 3C is a side view of a modification of FIG. 3B.

FIG. 4A is a front view of another rotating-shifting magnetic field unit main body.

FIG. 4B is a side view of another rotating-shifting magnetic field unit main body.

FIG. 4C is a side view of a modification of FIG. 4B.

FIG. 5A is a plan view of a molten metal stirring device according to a second embodiment of the invention.

FIG. 5B is a vertical sectional view taken along line b-b of FIG.

20375-1080

7

5A.

FIG. 6A is a plan view of a molten metal stirring device according to a third embodiment of the invention.

FIG. 6B is a vertical sectional view taken along line b-b of FIG.

5 6A.

FIG. 6C is a vertical sectional view taken along line c-c of FIG.

6A.

FIG. 7A is a front view of another rotating-shifting magnetic field unit main body.

FIG. 7B is a side view of another rotating-shifting magnetic field unit main body.

FIG. 7C is a side view of a modification of FIG. 7B.

FIG. 8A is a plan view of a molten metal stirring device according to a fourth embodiment of the invention.

FIG. 8B is a vertical sectional view taken along line b-b of FIG. 8A.

FIG. 9A is a plan view of a molten metal stirring device according to a fifth embodiment of the invention.

FIG. 9B is a vertical sectional view taken along line b-b of FIG. 9A.

FIG. 10A is a plan view of a molten metal stirring device according to a sixth embodiment of the invention.

FIG. 10B is a vertical sectional view taken along line b-b of FIG. 10A.

FIG. 11A is a plan view of a molten metal transfer device according to an embodiment of the invention.

FIG. 11B is a vertical sectional view taken along line b-b of FIG. 11A.

30 DETAILED DESCRIPTION OF EMBODIMENTS

[0011]

Before the description of embodiments of the invention, the principle of the invention will be described first and a process in which the inventor reaches the invention will then be described so that the embodiments of the invention can be more easily understood.

[0012]

For easy understanding, in the following description of the principle, a conductive nonferrous metal plate, which is long and has a rectangular cross-section, will be used instead of molten metal as an object to be driven by an electromagnetic force.

5 [0013]

A conductive nonferrous metal plate 101, which is long in an X direction, is assumed as illustrated in FIG. 1. A rod-like permanent magnet 102, which is long in a Y direction, is disposed below the nonferrous metal plate 101 so as to be movable in the X direction. A
10 permanent magnet, of which both upper and lower end sides are magnetized to an N pole and an S pole, is used as the permanent magnet 102 in this embodiment. Accordingly, magnetic lines ML of force stand up vertically (in a height direction) from the permanent magnet 102. The magnetic lines ML of force penetrate the nonferrous
15 metal plate 101 to the upper side from the lower side.

[0014]

In addition, a pair of electrodes 2a and 2a are provided on both side surfaces of the nonferrous metal plate 101 so as to face each other. A direct current I flows in the Y direction (a width direction), that is,
20 horizontally between these pair of electrodes 2a and 2a. Accordingly, the horizontal current I and the magnetic lines ML of force, which are generated from the permanent magnet 102 in the height direction, cross each other. The magnetic lines ML of force actually move with the rotation of the permanent magnet as described below. When a certain
25 condition is satisfied, an electromagnetic force (Lorentz force) f according to Fleming's left hand rule is generated at a portion, in which the current I flows, of the nonferrous metal plate 101. That is, a Lorentz force f, which drives the nonferrous metal plate 101 in the X direction and is generated according to Fleming's left hand rule, is applied to the
30 nonferrous metal plate 101.

[0015]

Further, in the above-mentioned structure, the permanent magnet 102 is moved in the direction of an arrow AR (the X direction). Accordingly, the magnetic lines ML of force move while penetrating the
35 nonferrous metal plate 101. Therefore, eddy currents 104 and 104 are generated in the nonferrous metal plate 101 on the front and rear sides

of the magnetic lines ML of force in the X direction. A magnetic field, which is generated by the eddy currents 104 and 104, and a magnetic field, which is generated from the permanent magnet 102, attract and repel each other, and an electromagnetic force f_e , which moves the nonferrous metal plate 101 in the X direction, is generated on the nonferrous metal plate 101. That is, an electromagnetic force f_e , which drives the nonferrous metal plate 1 in the X direction and is generated by the eddy currents, is applied to the nonferrous metal plate 101.

[0016]

10 The above-mentioned two electromagnetic forces f_e and f are applied to the conductive nonferrous metal plate 101 as described above. That is, a large resultant electromagnetic force (resultant driving force) F ($= f + f_e$), which is generated by the combination of the two electromagnetic forces f and f_e , acts on the nonferrous metal plate 101. 15 Accordingly, the nonferrous metal plate 101 can be reliably driven in the X direction by the large resultant driving force F .

[0017]

That is, first, considering a case in which a current I flows between the pair of electrodes 2a and 2a as a first case, the 20 electromagnetic force f according to Fleming's rule is generated. Next, considering a case in which the permanent magnet 102 is moved as a second case, the electromagnetic force f_e caused by the eddy currents is generated. These two electromagnetic forces f and f_e act as the resultant driving force F in the invention where the first and second cases 25 are realized together. It is apparent that the resultant driving force F of the invention is larger without comparing the single electromagnetic force f or f_e with the resultant driving force F ($= f + f_e$) of the invention. Accordingly, the nonferrous metal plate 1 is reliably driven by the large resultant driving force F .

30 [0018]

Here, considering a case in which the nonferrous metal plate 101 is substituted with molten metal M, it is understood that the resultant driving force F acts on the molten metal M and the molten metal M is reliably driven by a large stirring force. This is the principle of the 35 invention.

[0019]

The invention according to the above-mentioned principle is obtained by only the inventor, but a process until the obtainment of the invention will be technically described.

[0020]

5 Like general those skilled in the art, the inventor also intuit that the electromagnetic force f_e caused by eddy currents is generated when the permanent magnet 102 is linearly moved in FIG. 1. However, even though the magnetic field is a magnetic field generated from the rotating permanent magnet 102 (an actually assumed element is a permanent
10 magnet rotating at a certain speed like a rotating-shifting magnetic field unit main body 8 of FIGS. 2A and 2B), those skilled in the art could not assure that the electromagnetic force f according to Fleming's rule can be really obtained as described above. For this reason, the inventor repeated many experiments. Knowledge, which is obtained from these
15 experiments and is unique to the inventor, was obtained. The inventor has made the invention on the basis of the knowledge. That is, the invention is said as an invention that cannot be made by those skilled in the art not performing the following experiments. The invention will be described below.

20 [0021]

 That is, those skilled in the art can be said as persons who obtain two techniques, that is, a first technique for driving molten metal M by the electromagnetic force f according to Fleming's rule (Japanese Patent Application Laid-Open No. 2011-257129) and a second technique for
25 driving molten metal M by the electromagnetic force f_e generated by eddy currents (Japanese Patent No. 4245673, Patent Literature 2). However, those skilled in the art merely obtain the two techniques as techniques that are unrelated to each other. For this reason, even though those skilled in the art have obtained the two techniques, it is said
30 that those skilled in the art cannot make the invention (principle). This is apparent from the following reason. That is, general those skilled in the art intuit that the magnetic lines ML of force stop and are required to stop in the first technique and the magnetic lines ML of force move (rotate) at a certain level of speed and are required to move (rotate) in
35 the second technique. For this reason, even though those skilled in the art obtain the first technique in which the magnetic lines ML of force stop

and the second technique in which the magnetic lines ML of force move (rotate), those skilled in the art do not have an idea of combining the first technique with the second technique. Further, even if those skilled in the art have the idea, those skilled in the art intuit that both techniques do not function well when the first technique and the second technique are combined with each other. Then, the thought of those skilled in the art stops there. In addition, unlike the inventor, general those skilled in the art do not recognize that each of the first and second techniques particularly has inconvenience. For these various reasons, those skilled in the art do not intend to make an improvement in these first and second techniques, do not intend to combine the first technique with the second technique, and also do not have inevitability of the combination of the first and second techniques. That is, general those skilled in the art are not motivated to combine the two techniques.

[0022]

However, for the purpose of meeting the above-mentioned demands of industry, the inventor continues making an effort day and night to develop a device that reliably drives and stirs molten metal M by a large force and is more excellent than a device in the related art. Since the inventor has uniquely thought of the device as described above everyday, the inventor has uniquely thought to simultaneously use the force f of the first technique and the force f_e of the second technique. However, at first, similar to general those skilled in the art, the inventor has also vaguely thought that these two techniques are incompatible with each other. General engineers would give up here. However, since the inventor was eager to provide a new and excellent device, the inventor thought that two techniques are compatible with each other if devising something and could not give up hope of making the two techniques be compatible with each other. That is, the inventor had an object that is unique to the inventor. For this reason, the inventor constantly repeated various experiments that would not be performed by general those skilled in the art. The inventor could obtain knowledge, which is unique to the inventor, on the basis of the results of these experiments and has made the invention on the basis of the knowledge. That is, the inventor obtained the unique knowledge that it is possible to obtain the resultant driving force (the combined driving force) F of the

electromagnetic force f according to Fleming's rule and the electromagnetic force f_e generated by eddy currents by making the first and second techniques be compatible with each other at the same time and to reliably drive and stir molten metal M by the resultant driving force F when various parameters, such as the number of magnetic poles of the rotating-shifting magnetic field unit main body 8 to be described below, the types of the magnetic poles, an interval between the magnetic poles or an angle between the magnetic poles, and a rotational speed, are set to certain values. The inventor has made the invention on the basis of the unique knowledge.

[0023]

As described above, the invention has been made on the basis of the knowledge that is unique to the inventor and is based on the unique experiment results obtained by the inventor. Accordingly, the invention is said as an invention that cannot be made by other those skilled in the art not performing the above-mentioned experiments.

[0024]

Molten metal stirring devices according to embodiments of the invention made on the basis of the knowledge, which is obtained from the unique process described above and is unique to the inventor, will be described below with reference to the drawings.

[0025]

Meanwhile, the scales of the respective drawings to be described below are not the same, and the scale is arbitrarily selected in each drawing. Further, the same components in the respective embodiments will be denoted by the same reference numerals and the detailed description thereof will be omitted.

[0026]

(First embodiment)

FIGS. 2A and 2B illustrate a molten metal stirring device according to a first embodiment of the invention, FIG. 2A is a plan view, and FIG. 2B is a vertical sectional view taken along line b-b of FIG. 2A. As understood from FIGS. 2A and 2B, the first embodiment is an embodiment in which a rotating-shifting magnetic field unit 20 is provided outside a side wall 1a of a furnace main body 1 of a main bath 10.

[0027]

As understood from FIGS. 2A and 2B, the molten metal stirring device includes the main bath 10. Molten metal formed of metal having conductivity (electrical conductivity), that is, molten metal formed of nonferrous metal (for example, Al, Cu, Zn, Si, an alloy including them as main components, a Mg alloy, or the like), or molten metal M formed of metal other than nonferrous metal is stored in a storage chamber 1A of the furnace main body 1 of the main bath 10.

[0028]

As particularly understood from FIG. 2B, a pair of electrodes 2a and 2a are mounted on the side wall 1a of the furnace main body 1 of the main bath 10 so as to face each other in a vertical direction (a height direction). The pair of electrodes 2a and 2a are embedded in the side wall 1a, but do not necessarily need to be embedded and may be provided on the inner surface of the side wall 1a. The same applies to all embodiments to be described below. That is, these electrodes 2a and 2a are exposed from the side wall 1a and are in contact with the stored molten metal M. Accordingly, a current I can flow in a height direction between the electrodes 2a and 2a through the molten metal M. The electrodes 2a and 2a are connected to a power supply device 3 through wires 4a and 4a. A part of the wires 4a and 4a, that is, portions of the wires 4a and 4a close to the electrodes 2a and 2a are provided in the side wall 1a and are not in contact with the molten metal M. The reason why the direct current I is allowed to flow between the electrodes 2a and 2a is to obtain the Lorentz force (a second electromagnetic force) f according to Fleming's left hand rule as described above.

[0029]

The power supply device 3 is adapted to allow a direct current and an alternating current to flow in various modes by control signals that are sent from a control device (not illustrated). In regard to a direct current, the polarities of the pair of electrodes 2a and 2a can be switched to each other. In regard to an alternating current, a period, a waveform, and the like can be selected and adjusted. When the waveform of the current I has, for example, a rectangular shape in the case of an alternating current, the width of a positive pulse and the width of a negative pulse at one period can be arbitrarily set so that a duty ratio is changed. In addition, the power supply device 3 is adapted to be

capable of arbitrarily setting a current value and a voltage value even when any one of a direct current and an alternating current is output.

[0030]

As described above, a current I flows in the vertical direction (a
5 direct current I_{dc} flows to the lower side from the upper side or to the
upper side from the lower side or an alternating current I_{ac} flows)
between the pair of electrodes 2a and 2a. The current I intersects the
magnetic lines ML of force generated from the rotating-shifting magnetic
field unit 20, so that the electromagnetic force (the second
10 electromagnetic force) f according to Fleming's rule for driving the molten
metal M in the direction of an arrow $AR1$ (FIG. 2A) is obtained. As
understood from the following detailed description, in order to obtain a
driving force applied in the direction of the arrow $AR1$, a direct current is
allowed to flow between the pair of electrodes 2a and 2a when the outer
15 periphery of the rotating-shifting magnetic field unit 20 is magnetized to
one pole of an N pole and an S pole, and an alternating current
synchronized with the periods of N poles and S poles (rotation periods) is
allowed to flow between the pair of electrodes when N poles and S poles
are alternately arranged on the outer periphery of the rotating-shifting
20 magnetic field unit. The reason for this is to obtain a driving force f ,
which always drives molten metal M in the same direction, that is, in the
direction of the arrow $AR1$, as an electromagnetic force according to
Fleming's left hand rule. The reason why the current I flowing between
the electrodes 2a and 2a is adapted to be capable of being set to any of
25 a direct current and an alternating current by the power supply device 3
is to apply an electromagnetic force f , which is always applied in the
same rotational direction, to the molten metal M even though any one of
various rotating-shifting magnetic field unit main bodies 8 (see FIGS. 3A,
3B, 3C, 4A, 4B, and 4C) to be described below is used.

30 [0031]

Next, the rotating-shifting magnetic field unit 20 will be described.

[0032]

As understood from FIGS. 2A and 2B, the rotating-shifting
magnetic field unit 20 includes a chassis 7 that is made of a
35 non-magnetic material, a rotating-shifting magnetic field unit main body 8
that is rotatably built in the chassis 7, and a drive unit (not illustrated)

that drives the rotating-shifting magnetic field unit main body 8 clockwise (or counterclockwise). As particularly understood from FIG. 2B, the rotating-shifting magnetic field unit main body 8 is rotatably installed so that input/output magnetic lines ML of force, which go out of the rotating-shifting magnetic field unit main body 8 or enter the rotating-shifting magnetic field unit main body 8, penetrate the molten metal M stored in the furnace main body 2 in a horizontal direction intersecting the vertical direction. Accordingly, the rotating-shifting magnetic field unit main body 8 functions as follows. That is, when a current I is allowed to flow in the vertical direction between the pair of electrodes 2a and 2a particularly in FIG. 2B, horizontal magnetic lines ML of force generated from the rotating-shifting magnetic field unit main body 8 intersect the current I. Accordingly, the Lorentz force (the second electromagnetic force) f, which drives the molten metal M as illustrated by the arrow AR1 of FIG. 2A, is generated.

[0033]

At this time, the rotating-shifting magnetic field unit main body 8 is rotated clockwise as illustrated in, for example, FIG. 2A when viewed from the upper side. Accordingly, the magnetic lines ML of force move while horizontally penetrating the molten metal M. Therefore, eddy currents are generated on the front and rear sides of the moving magnetic lines ML of force and the first electromagnetic force f_e is generated by the eddy currents and the magnetic lines ML of force. Similar to the above-mentioned electromagnetic force f according to Fleming's left hand rule, the electromagnetic force f_e generated by the eddy currents drives the molten metal M in the direction of the arrow AR1.

[0034]

Accordingly, the molten metal M is driven along the arrow AR1 by the resultant driving force F that is generated by the combination of the two electromagnetic forces, that is, the first and second electromagnetic forces f_e and f. Therefore, the molten metal M stored in the furnace main body 1 is horizontally rotated as illustrated by an arrow AR11 of FIG. 2A.

[0035]

Various structures can be employed as the rotating-shifting

magnetic field unit main body 8. FIGS. 3A and 3B illustrate a first example of the rotating-shifting magnetic field unit main body, FIG. 3C illustrates a modification of the first example, FIGS. 4A and 4B illustrate a second example of the rotating-shifting magnetic field unit main body, and FIG. 4C illustrates a modification of the second example.

[0036]

In FIGS. 3A and 3B, the rotating-shifting magnetic field unit main body 8 includes a cylindrical case 8A that is made of a non-magnetic material and a rotating body 8B that is rotatably received in the case 8A.

The rotating body 8B includes a long base 8B1 that is positioned at a rotation center portion thereof. The base 8B1 has a substantially square cross-section, and includes four side surfaces 8B2. A rod-like magnet 8B3, which is formed of a permanent magnet, is mounted on each of the side surfaces 8B2. The inner surface, which is mounted on the side surface 8B2, of each rod-like magnet 8B3 is magnetized to one pole (an S pole) and the outer surface thereof is magnetized to the other pole (an N pole). Accordingly, the same poles (N poles) are arranged on the periphery of the rotating body 8B. On the contrary, it is natural that the outer surface of each rod-like magnet 8B3 may be magnetized to an S pole and the inner surface thereof is magnetized to an N pole so that S poles are arranged on the periphery of the rotating body 8B.

[0037]

FIG. 3C illustrates an example in which a plurality of rod-like magnets 8B3 mounted on the base 8B1 are alternately magnetized to an N pole and an S pole in a circumferential direction.

[0038]

When the same magnetic poles are arranged along the periphery of the rotating body 8B as illustrated in FIGS. 3A and 3B, a current I flowing in the same direction, that is, a direct current may be allowed to flow between the pair of electrodes 2a and 2a. However, when N poles and S poles are alternately arranged along the outer periphery of the rotating body as illustrated in FIG. 3C, an alternating current having a period corresponding to the arrangement of the magnetic poles needs to be allowed to flow between the pair of electrodes 2a and 2a as also briefly described above. Accordingly, the second electromagnetic force f according to Fleming's rule can be obtained as an electromagnetic force

having the same direction (for example, the direction of the arrow AR1 of FIG. 2A) even though the direction of the magnetic lines ML of force is alternately reversed. The control of the direction of the current I between the pair of electrodes 2a and 2a is performed by the control
5 device as described above.

[0039]

The polygonal shape of the cross-section of the base 8B1 may be a polygonal shape of which the number of corners is arbitrary. Further, the number of the rod-like magnets 8B3 mounted on the base 8B1 may
10 also be arbitrary. FIGS. 4A and 4B illustrate an example in which the number of the rod-like magnets 8B3 is set to 2 when the same poles are arranged on the outer periphery of the rotating body. FIG. 4C illustrates an example in which different magnetic poles are alternately arranged.

[0040]

That is, the number of the rod-like magnets 8B3 mounted on the base 8B1 can be appropriately and arbitrarily determined as understood from the above description. Further, the magnetic poles of the rod-like magnets 8B3 arranged in the circumferential direction can be arranged
15 so that the same magnetic poles are arranged in the circumferential direction or different magnetic poles are alternately arranged in the circumferential direction. Furthermore, the cross-sectional shape of the base 8B1 may be an arbitrary polygonal shape according to the number of the provided rod-like magnets 8B3.
20

[0041]

In addition, a permanent magnet, which is formed of a single permanent magnet and is magnetized so that the same magnetic poles or different magnetic poles are arranged therearound, may be used as the rotating body 8B.
25

[0042]

Meanwhile, in the other embodiments to be described below other than the above-mentioned first embodiment, the pair of electrodes 2a and 2a do not necessarily need to be embedded in a furnace wall as illustrated in FIG. 2B and may be provided on the inner surface of a furnace wall 3a. In this case, the wires 4a and 4a may also be
30 embedded in the furnace wall 3a or may be allowed to creep in the storage chamber 1A of the furnace main body 1 without being embedded

so that the wires 4a and 4a are not in contact with the molten metal M.
[0043]

(Second embodiment)

FIGS. 5A and 5B illustrates a molten metal stirring device
5 according to a second embodiment of the invention, FIG. 5A is a plan
view, and FIG. 5B is a vertical sectional view taken along line b-b of FIG.
5A. The rotating-shifting magnetic field unit 20, which is provided
outside the side wall 1a of the furnace main body 1 of the main bath 10,
is provided in an upright state (a standing state) in the first embodiment,
10 but is provided in a horizontal state (a lying state) in the second
embodiment.

[0044]

In addition, the second embodiment is different from the first
embodiment (FIGS. 2A and 2B) in that the pair of electrodes 2a and 2a
15 are also provided on the side wall 1a to horizontally face each other as
particularly understood from FIG. 5A in response to the horizontal
installation of the rotating-shifting magnetic field unit 20 so that a current
I horizontally flows in the second embodiment.

[0045]

20 Moreover, as understood from FIG. 5B, the rotating-shifting
magnetic field unit main body 8 is adapted to be rotated clockwise in FIG.
5B.

[0046]

For this reason, a resultant driving force F, which drives the
25 molten metal M as illustrated by an arrow AR2, (= a first electromagnetic
force f_e generated by eddy currents + a second electromagnetic force f
according to Fleming's left hand rule) is generated. Accordingly, the
molten metal M is reliably driven in the furnace main body 1 so as to
convect as illustrated in FIG. 5B by arrows AR21.

30 [0047]

The first and second embodiments have been described as
separate embodiments in the description of the above-mentioned first
and second embodiments, but may be made as one embodiment. That
is, the rotating-shifting magnetic field unit 20 is adapted to be switched
35 between a vertical position in the vertical direction as in the first
embodiment and a horizontal position in which the rotating-shifting

magnetic field unit lies down as in the second embodiment. Meanwhile, in this case, the furnace main body 1 of the main bath 10 needs to be provided with the pair of electrodes 2a and 2a that are illustrated in FIG. 2B and face each other in the vertical direction and the pair of electrodes 2a and 2a that are illustrated in FIG. 5A and face each other in the horizontal direction, that is, a total of two pairs of electrodes 2a (four electrodes 2a). According to such an embodiment, the rotating-shifting magnetic field unit 20 can be switched between the vertical position and the horizontal position so as to correspond to various conditions, such as an installation site, when used.

[0048]

(Third embodiment)

FIG. 6A is a plan view of a third embodiment of the invention, FIG. 6B is a vertical sectional view taken along line b-b of FIG. 6A, and FIG. 6C is a vertical sectional view taken along line c-c of FIG. 6A.

[0049]

The third embodiment is different from the first and second embodiments in terms of the structure of a rotating-shifting magnetic field unit main body. That is, a rotating-shifting magnetic field unit main body 81B0 illustrated in FIGS. 7A and 7B is used in the third embodiment. That is, a pair of rectangular permanent magnets 81B2 are mounted on the surface of a disc-shaped rotating substrate 81B1 at an arbitrary interval, for example, an interval of 180°. These permanent magnets 81B2 are mounted on the rotating substrate 81B1 so that the inner sides, which are mounted, of these permanent magnets 81B2 correspond to an S pole and the outer sides thereof correspond to an N pole. While the rotating-shifting magnetic field unit main body 81B0 illustrated in FIGS. 7A and 7B is rotated, a direct current is allowed to flow between the pair of electrodes 2a and 2a (FIG. 6B). Accordingly, molten metal M is driven in the direction of an arrow AR3 as illustrated in FIG. 6A by a resultant driving force F of an electromagnetic force f according to Fleming's left hand rule that is generated when a current I flows between the pair of electrodes 2a and 2a and an electromagnetic force fe that is generated by eddy currents generated when the rotating-shifting magnetic field unit main body 81B0 is rotated; and the molten metal M of the furnace main body 1 is driven and rotated as illustrated by arrows

AR31.

[0050]

Further, the plurality of permanent magnets 81B2 can also be mounted on the base 8B1 as illustrated in FIG. 7C so that different poles are arranged in a circumferential direction. In this case, an alternating current needs to be allowed to flow between the pair of electrodes 2a and 2a as described above.

[0051]

When the rotating-shifting magnetic field unit 20 is merely provided later as long as the main bath 10 having been already provided includes a pair of electrodes 2a and 2a, the first to third embodiments having been described above are realized. Alternatively, as long as the pair of electrodes 2a and 2a and the rotating-shifting magnetic field unit 20 are provided later on the main bath 10 having been already provided, the embodiments of the invention can be realized.

[0052]

(Fourth embodiment)

FIG. 8A is a horizontal sectional view of a fourth embodiment of the invention and FIG. 8B is a vertical sectional view taken along line b-b of FIG. 8A. The fourth embodiment is a so-called passage type stirring device that guides molten metal M of a main bath 30 to a so-called molten metal passage 41a, returns the molten metal M to a main bath 30 by applying the resultant driving force F to the molten metal M in the molten metal passage 41a, and stirs the molten metal M stored in the main bath 30.

[0053]

That is, a molten metal stirring device according to the fourth embodiment includes a main bath 30 and a stirring unit 40. The main bath 30 includes a furnace main body 1 that stores molten metal M. The stirring unit 40 includes a passage member 41 that includes a molten metal passage 41a and a rotating-shifting magnetic field unit main body 8.

[0054]

That is, a molten metal outlet 30a1 and a molten metal inlet 30a2 are formed in one side wall 30a of the main bath 30, and communicate with each other through the hollow passage member 41, which has a

20375-1080

21

substantially U-shaped cross-section, of the stirring unit 40. As understood from FIG. 8A, the passage member 41 includes the molten metal passage 41a that is formed therein and has a substantially U-shaped cross-section. That is, one end of the molten metal passage 41a is connected to the molten metal outlet 30a1 so as to communicate with the molten metal outlet 30a1, and the other end of the molten metal passage 41a is connected to the molten metal inlet 30a2 so as to communicate with the molten metal inlet 30a2. Accordingly, the molten metal M of the main bath 30 flows out of the molten metal outlet 30a1 to the molten metal passage 41a, and then is driven in the molten metal passage 41a by the resultant driving force F as described below. After that, the molten metal M returns to the main bath 30 from the molten metal inlet 30b2.

[0055]

In the stirring unit 40, a storage space 40a is divided by the passage member 41 and the side wall 30a. The rotating-shifting magnetic field unit main body 8 is rotatably received in the storage space 40a. Various elements can be used as the rotating-shifting magnetic field unit main body 8, but the rotating-shifting magnetic field unit main bodies illustrated in, for example, FIGS. 3A, 3B, 3C, 4A, 4B, 4C, and the like can be used. For example, when the rotating-shifting magnetic field unit main body illustrated in FIGS. 3A and 3B is used, magnetic lines ML of force horizontally extend and penetrate the molten metal M present in the molten metal passage 41a as particularly illustrated in FIG. 8B.

[0056]

In addition, as particularly illustrated in FIG. 8B, a pair of electrodes 2a and 2a, which face each other in the vertical direction, are provided on the inner wall of the passage member 41 so as to be exposed to the molten metal passage 41a. A current I flows between these electrodes 2a and 2a through the molten metal M in the vertical direction. These electrodes 2a and 2a are connected to a power supply device 3.

[0057]

Accordingly, since the current I, which flows in the vertical direction, intersects the magnetic lines ML of force, which horizontally extend, as particularly understood in FIG. 8B, a second electromagnetic

force f according to Fleming's left hand rule is generated and drives the molten metal M present in the molten metal passage 41a in the direction of arrows AR4 (FIG. 8A).

[0058]

5 Moreover, a first electromagnetic force f_e caused by eddy currents is generated by the rotation of the rotating-shifting magnetic field unit main body 8, and the molten metal M present in the molten metal passage 41a is also driven in the direction of the arrows AR4 by the electromagnetic force f_e .

10 [0059]

 A large resultant driving force F is generated by the combination of the second electromagnetic force f and the first electromagnetic force f_e , acts on the molten metal M present in the molten metal passage 41a, allows the molten metal M to flow into the furnace main body 1 of the
15 main bath 30 from the molten metal inlet 2b1, and allows the molten metal M of the main bath 30 to be sucked into the molten metal passage 41a from the molten metal inlet 2b1. Accordingly, as particularly illustrated in FIG. 8A, the molten metal M stored in the furnace main body 1 of the main bath 30 is reliably stirred and driven along arrows AR41.

20 [0060]

 Meanwhile, the rotating-shifting magnetic field unit main body 8 is installed inside the passage member 41 particularly in FIGS. 8A and 8B, but the rotating-shifting magnetic field unit main body 8 may be installed outside the passage member 41.

25 [0061]

 Further, when the rotating-shifting magnetic field unit main body 8 is installed outside the passage member 41 as described above, the rotating-shifting magnetic field unit main bodies 81B0 illustrated in FIGS. 7A, 7B, and 7C can be used instead of the rotating-shifting magnetic field
30 unit main body 8 so that a rotating shaft extends laterally. The molten metal present in the passage member 41 can also be driven by this structure.

[0062]

 Furthermore, the rotating-shifting magnetic field unit main body 8
35 has been provided inside the so-called U shape of the U-shaped passage member 41, but may be provided outside the U shape of the

passage member 41. In addition, a total of two rotating-shifting magnetic field unit main bodies 8 may be provided inside and outside the U shape so that the passage member 41 (the molten metal passage 41a) is interposed between the two rotating-shifting magnetic field unit main bodies 8.

[0063]

Meanwhile, the magnetic lines ML of force generated from one rotating-shifting magnetic field unit main body 8 are shared in the above-mentioned embodiments so that two forces, that is, the electromagnetic force f_e generated by eddy currents and the electromagnetic force f according to Fleming's rule are obtained. However, it is also technically considered that only the electromagnetic force f_e caused by eddy currents is obtained by the magnetic lines ML of force generated from the rotating-shifting magnetic field unit main body 8, the pair of electrodes 2a and 2a are provided at other positions different from the positions of FIG. 8A and a separate magnetic field unit is provided to obtain the electromagnetic force f according to Fleming's rule, and the electromagnetic force f according to Fleming's rule is obtained by the pair of electrodes 2a and 2a provided at other positions and the separate magnetic field unit. Since two devices for generating so-called magnetic fields are required in this case, it is not possible to avoid not only an increase in cost but also a large installation area for the devices. It is said that the above description is also applied to an embodiment illustrated in FIGS. 11A and 11B to be described below. That is, in FIG. 11A, another magnetic field unit is provided in addition to the rotating-shifting magnetic field unit main body 8 and a pair of electrodes 2a and 2a can be provided at positions where an electromagnetic force f according to Fleming's rule is generated in relationship to the magnetic field unit. Even in this case, it is not possible to avoid an increase in the cost of the device and an increase in the size of the device as described above.

[0064]

(Fifth embodiment)

FIG. 9A is a plan view of a fifth embodiment of the invention and FIG. 9B is a vertical sectional view taken along line b-b of FIG. 11A. The fifth embodiment is different from the fourth embodiment of FIGS. 8A and

8B in terms of the structure of a stirring unit 40A. That is, this embodiment is an embodiment in which a stirring chamber 40A1 communicating with a main bath 30A is made and molten metal M is driven by a resultant driving force F.

5 [0065]

In more detail, a molten metal stirring device according to the fifth embodiment includes the main bath 30A and the stirring unit 40A.

[0066]

10 The main bath 30A includes a furnace main body 1 that stores molten metal M.

[0067]

15 A side wall 1a1, which has a substantially U-shaped cross-section, of the stirring unit 40A is formed so as to be connected to one side wall 1a of the furnace main body 1. The stirring chamber 40A1 of the stirring unit 40A, which communicates with the inside of the furnace main body 1 of the main bath 30A, is formed by the side wall 1a1.

[0068]

20 As particularly understood from FIG. 9A, the inside of the furnace main body 1 and the stirring chamber 40A1 communicate with each other through an opening 50. A partition plate 40A0 stands upright in the direction of the flow of the molten metal in the stirring chamber 40A1. The opening 50 is partitioned into two openings 50A and 50B by the partition plate 40A0, and the stirring chamber 40A1 is partitioned into two upper and lower chambers illustrated in FIG. 9A, that is, a first chamber 25 40A11 and a second chamber 40A12. The partition plate 40A0 is provided so as to be rotatable about a shaft portion 40A10. The width of the opening 50A of the first chamber 40A11 and the width of the opening 50B of the second chamber 40A12 are adjusted by the rotation of the partition plate 40A0, and the flow of the molten metal becomes 30 optimal as described below. A gap G, which allows the flow of the molten metal M, is formed between the shaft portion 40A10 and the inside of the side wall 1a1. Accordingly, the molten metal M can circulate through the opening 50A, the first chamber 40A11, the gap G, the second chamber 40A12, the opening 50B, and the furnace main body 35 1 from the inside of the furnace main body 1 of the main bath 30A as described below.

[0069]

The partition plate 40A1 includes a partition plate main body 40A10 and the shaft portion 40A0. The shaft portion 40A10 (2a) is made of a conductive material, and functions as one of the pair of electrodes 2a and 2a. A plurality of the other electrodes 2a are provided on the inside of the side wall 1a1. Accordingly, a current I horizontally flows between one shaft portion 40A10 (2a) and the plurality of electrodes 2a through the molten metal M. That is, a plurality of paths for the current I are formed horizontally. One electrode 40A10 (2a) and the plurality of the other electrodes 2a are connected to terminals of both poles of the power supply device 3.

[0070]

In addition, as particularly understood from FIG. 9B, a rotating-shifting magnetic field unit 20 is provided below the bottom wall of the stirring chamber 40A1 in the stirring unit 40A. A rotating-shifting magnetic field unit main body 8 is provided in the rotating-shifting magnetic field unit 20 so as to be rotatable about an axis extending in a vertical direction. The rotating-shifting magnetic field unit main body, which is illustrated in FIGS. 7A and 7B or FIG. 7C, or the like can be used as the rotating-shifting magnetic field unit main body 8. For example, when the rotating-shifting magnetic field unit main body illustrated in FIGS. 7A and 7B is used, magnetic lines ML of force stand up as illustrated in FIG. 9B.

[0071]

The second electromagnetic force f according to Fleming's left hand rule is generated by the intersection between the magnetic lines ML of force and the current I that flows between the shaft portion 40A10 (2a) and the electrodes 2a. Further, the first electromagnetic force f_e caused by eddy currents is also generated with the rotation of the rotating-shifting magnetic field unit main body 8. Accordingly, the molten metal M is driven in the direction of arrows AR5 (FIG. 9A) by the resultant driving force F of these two electromagnetic forces f and f_e . Therefore, the molten metal M is rotated and stirred in the furnace main body 1 as illustrated by arrows AR51.

[0072]

(Sixth embodiment)

FIGS. 10A and 10B illustrate a sixth embodiment of the invention, and illustrate a case in which the rotating-shifting magnetic field unit 20 of FIGS. 9A and 9B is installed above the stirring chamber 40A1. Meanwhile, it is natural that the rotating-shifting magnetic field unit main body 8 of FIG. 9B is installed so as to be inverted.

5 [0073]

(Seventh embodiment)

FIG. 11A is a vertical sectional view of a seventh embodiment, and FIG. 11B is a sectional view taken along line b-b.

10 [0074]

The seventh embodiment includes two melting furnaces, that is, main baths 100 and 101. A molten metal furnace system, which includes a molten metal transfer device for transferring molten metal M to a furnace main body 101A of the main bath 101 from a furnace main body 100A of the main bath 100, is illustrated.

15 [0075]

That is, an opening 100b is formed in a bottom wall 100a of one main bath 100, and an opening 101b is formed in a bottom wall 101a of the other main bath 101. These openings 100b and 101b communicate with each other through a hollow passage member 103 that is bent substantially in a U shape. The cross-sectional shape of the passage member 103 is illustrated in FIG. 11B. As understood here, the cross-sectional shape of a communication passage 103a formed in the passage member 103 is a rectangular shape. A pair of electrodes 2a and 2a are provided on the inner surfaces, which face each other in a width direction with the communication passage 103a of the passage member 103 interposed therebetween, of a pair of side walls 103b and 103b. As illustrated in FIG. 11A, the pair of electrodes 2a and 2a are provided above a curved portion 103c of the passage member 103 that is bent in a vertical direction. A rotating-shifting magnetic field unit main body 8 is horizontally provided on the inside (at an upper portion) of the curved portion 103c. The rotating-shifting magnetic field unit main body 8 is illustrated in FIGS. 3A, 3B, 3C, 4A, 4B, and 4C. The electrodes 2a and 2a are connected to a power supply device 3.

20
25
30

35 [0076]

When a current I is allowed to flow between the pair of electrodes

2a and 2a to rotate the rotating-shifting magnetic field unit main body 8 in this device, molten metal M present in the passage member 103 can be transferred to the other main bath 101 from one main bath 100 by a resultant driving force F of a second electromagnetic force f according to
5 Fleming's rule and a first electromagnetic force f_e generated by eddy currents.

[0077]

The inventor has made an experiment to drive molten aluminum according to each of the above-mentioned embodiments, and has
10 confirmed that a driving force (transfer force) can be made larger than each of the electromagnetic force f_e generated by eddy currents and the electromagnetic force f according to Fleming's rule. In the fourth embodiment (FIG. 8) and the seventh embodiment (FIG. 11), the inventor has made an experiment formed of the combination of a case in which
15 the amount of molten metal transferred by only the Lorentz force f is about 1000 Tons/h and a case in which the amount of molten metal transferred by only the electromagnetic force f_e , which is generated by eddy currents, is about 900 Tons/h; and has numerically confirmed that the amount of transferred molten metal can be set in the range of about
20 1800 to 2000 Tons/h.

20375-1080

28

CLAIMS

1. A molten metal stirring device comprising:
a furnace main body that includes a storage chamber for
storing molten metal formed of conductive metal; and
5 a rotating-shifting magnetic field unit main body that is rotatable
to drive and stir the molten metal stored in the furnace main body,
wherein the rotating-shifting magnetic field unit main body
includes a permanent magnet, so that input/output magnetic lines of
force, which go out of the permanent magnet or enter the permanent
10 magnet, move with the rotation of the rotating-shifting magnetic field unit
main body while penetrating the molten metal, in order that a first
electromagnetic force for driving the molten metal is generated by eddy
currents that are generated by the movement of the input/output
magnetic lines of force,
15 the furnace main body includes at least a pair of electrodes that
allow current to flow through the molten metal,
the pair of electrodes are provided in the storage chamber at
positions where the current flowing between the pair of electrodes and
the input/output magnetic lines of force intersect each other and
20 generate a second electromagnetic force for driving the molten metal in
the same direction as the first electromagnetic force, and
the molten metal stored in the storage chamber is driven and
stirred by a resultant driving force of the first and second electromagnetic
forces.
25
2. The molten metal stirring device according to claim 1,
wherein the pair of electrodes are provided at a predetermined
interval in a vertical direction parallel to a height direction, and
the rotating-shifting magnetic field unit main body is provided so
30 as to be rotatable about a vertical axis.
3. The molten metal stirring device according to claim 1,
wherein the pair of electrodes are provided at a predetermined
interval in a horizontal direction intersecting a height direction, and
35 the rotating-shifting magnetic field unit main body is provided so
as to be rotatable about a horizontal axis.

20375-1080

29

4. The molten metal stirring device according to claim 1,
wherein the rotating-shifting magnetic field unit main body
includes one or a plurality of the permanent magnets, and
5 the same magnetic poles are arranged around a vertical axis
extending in a height direction or a horizontal axis intersecting the height
direction.
5. The molten metal stirring device according to claim 1,
10 wherein the rotating-shifting magnetic field unit main body
includes one or a plurality of the permanent magnets, and
different magnetic poles are alternately arranged around a
vertical axis extending in a height direction or a horizontal axis
intersecting the height direction.
- 15 6. The molten metal stirring device according to claim 1, further
comprising:
a plurality of the permanent magnets,
wherein the plurality of permanent magnets are arranged around
20 the vertical axis or the horizontal axis.
7. The molten metal stirring device according to claim 1, further
comprising:
two pairs of the electrodes, that is, a first pair of electrodes and a
25 second pair of electrodes,
wherein the first pair of electrodes are provided at a
predetermined interval in a vertical direction parallel to a height direction,
the second pair of electrodes are provided at a predetermined
interval in a horizontal direction intersecting the height direction, and
30 the rotating-shifting magnetic field unit main body is adapted to
be switched between a first installation position where the
rotating-shifting magnetic field unit main body is provided so as to be
rotatable about a vertical axis and a second installation position where
the rotating-shifting magnetic field unit main body is provided so as to be
35 rotatable about a horizontal axis.

20375-1080

30

8. The molten metal stirring device according to claim 1,
wherein the pair of electrodes are provided at a predetermined
interval in a vertical direction parallel to a height direction, and
the rotating-shifting magnetic field unit main body is provided so
5 as to be rotatable about a horizontal axis intersecting the height
direction.
9. The molten metal stirring device according to claim 8,
wherein the rotating-shifting magnetic field unit main body
10 includes one or a plurality of the permanent magnets, and
the same magnetic poles are arranged around the horizontal
axis.
10. The molten metal stirring device according to claim 8,
15 wherein the rotating-shifting magnetic field unit main body
includes one or a plurality of the permanent magnets, and
different magnetic poles are alternately arranged around the
horizontal axis.
- 20 11. The molten metal stirring device according to claim 4,
wherein a power supply device, which allows a direct current to
flow, is connected between the pair of electrodes.
12. The molten metal stirring device according to claim 5,
25 wherein a power supply device, which allows an alternating
current to flow, is connected between the pair of electrodes, and
the period of the alternating current is controlled in relationship to
the rotation periods of the different magnetic poles of the rotating-shifting
magnetic field unit main body so that the first electromagnetic force
30 drives the molten metal in the same direction.
13. A molten metal stirring device comprising:
a main bath that includes a furnace main body including a
storage chamber for storing molten metal formed of conductive metal; and
35 a stirring unit that drives and stirs the molten metal stored in the
furnace main body,

20375-1080

31

wherein the stirring unit includes a passage member that includes a molten metal passage for circulation for allowing the molten metal stored in the furnace main body to flow out and then flow into the furnace main body and a rotating-shifting magnetic field unit main body that is rotatable and generates a first electromagnetic force for driving the molten metal present in the molten metal passage,

the rotating-shifting magnetic field unit main body includes a permanent magnet,

the furnace main body includes a molten metal outlet and a molten metal inlet that are formed in a side wall,

the molten metal outlet and the molten metal inlet communicate with each other through the passage member so as to allow the circulation of the molten metal that flows out of the furnace main body and flows into the furnace main body through the molten metal passage,

the rotating-shifting magnetic field unit main body is provided outside the passage member and is adapted to be rotatable about a vertical axis extending in a height direction, so that input/output magnetic lines of force, which go out of the permanent magnet or enter the permanent magnet, move with the rotation of the rotating-shifting magnetic field unit main body while penetrating the molten metal present in the molten metal passage, in order that the first electromagnetic force is generated by eddy currents that are generated by the movement of the input/output magnetic lines of force, so that the molten metal is driven toward the molten metal inlet from the molten metal outlet in the molten metal passage by the first electromagnetic force,

at least a pair of electrodes are provided in the molten metal passage of the passage member so that a current flows between the pair of electrodes through the molten metal,

the pair of electrodes are provided in the molten metal passage at positions where the current flowing between the pair of electrodes and the input/output magnetic lines of force intersect each other and generate a second electromagnetic force for driving the molten metal in the same direction as the first electromagnetic force, and

the molten metal present in the molten metal passage is driven toward the molten metal outlet by a resultant driving force of the first and second electromagnetic forces so that the molten metal stored in the

20375-1080

32

storage chamber is driven.

14. The molten metal stirring device according to claim 13,
wherein the rotating-shifting magnetic field unit main body
5 includes one or a plurality of the permanent magnets, and
the same magnetic poles are arranged around the vertical axis
extending in the height direction.

15. The molten metal stirring device according to claim 13,
10 wherein the rotating-shifting magnetic field unit main body
includes one or a plurality of the permanent magnets, and
different magnetic poles are alternately arranged around the
vertical axis extending in the height direction.

15 16. The molten metal stirring device according to claim 14,
wherein a power supply device, which allows a direct current to
flow, is connected between the pair of electrodes.

17. The molten metal stirring device according to claim 15,
20 wherein a power supply device, which allows an alternating
current to flow, is connected between the pair of electrodes, and
the period of the alternating current is controlled in relationship to
the rotation periods of the different magnetic poles of the rotating-shifting
magnetic field unit main body so that the first electromagnetic force
25 drives the molten metal in the same direction even though the different
magnetic poles are rotated.

18. A molten metal stirring device comprising:
a main bath that includes a furnace main body including a
30 storage chamber for storing molten metal formed of conductive metal; and
a stirring unit including a stirring furnace that includes a stirring
chamber for storing molten metal, and a rotating-shifting magnetic field
unit main body that is rotatable and drives the molten metal stored in the
stirring chamber, the rotating-shifting magnetic field unit main body
35 including a permanent magnet,
wherein the storage chamber and the stirring chamber

20375-1080

33

communicate with each other through an opening,

a partition plate stands upright in a vertical direction in the stirring chamber,

5 the opening is divided into a first opening and a second opening by the partition plate,

the stirring chamber is divided into a first chamber communicated to the first opening and a second chamber communicated to the second opening,

10 a gap is formed between a rear end of the partition plate and an inner surface of a side wall of the stirring unit and the first and second chambers communicate with each other through the gap,

the rotating-shifting magnetic field unit main body is provided outside the stirring chamber below or above the stirring chamber so as to be rotatable about a vertical axis extending in the vertical direction, so
15 that input/output magnetic lines of force, which go out of the permanent magnet or enter the permanent magnet, are moved by the rotation of the rotating-shifting magnetic field unit main body while penetrating the molten metal stored in the stirring unit, in order that a first electromagnetic force is generated by eddy currents that are generated
20 by the movement of the input/output magnetic lines of force, so that the molten metal is driven toward the second chamber from the first chamber through the gap by the first electromagnetic force,

a pair of electrodes are provided in the stirring chamber at positions where a current flowing between the pair of electrodes and the
25 magnetic lines of force generated from the permanent magnet intersect each other and generate a second electromagnetic force for driving the molten metal in the same direction as the first electromagnetic force, and

the molten metal stored in the first chamber is sent toward the second chamber through the gap and is allowed to flow into the storage
30 chamber from the second opening by a resultant driving force of the first and second electromagnetic forces so that the molten metal stored in the storage chamber is driven.

19. The molten metal stirring device according to claim 18,
35 wherein one electrode of the pair of electrodes is provided at the rear end of the partition plate and the other electrode thereof is provided

20375-1080

34

on the inside of the stirring chamber of the stirring unit so that the one electrode and the other electrode horizontally face each other.

20. The molten metal stirring device according to claim 19,
5 wherein a plurality of the other electrodes are provided on the inside of the stirring chamber.

21. The molten metal stirring device according to claim 18,
10 wherein a first side wall of the furnace main body and a second side wall of the stirring furnace are connected to each other so as to form the opening.

22. The molten metal stirring device according to claim 18,
15 wherein the partition plate is adapted to be rotatable about the vertical axis passing through the rear end thereof, and is capable of adjusting the sizes of the first and second openings by the rotation of the partition plate.

23. The molten metal stirring device according to claim 18,
20 wherein the rotating-shifting magnetic field unit main body includes one or a plurality of the permanent magnets, and the same magnetic poles are arranged around the vertical axis.

24. The molten metal stirring device according to claim 18,
25 wherein the rotating-shifting magnetic field unit main body includes one or a plurality of the permanent magnets, and different magnetic poles are alternately arranged around the vertical axis.

30 25. The molten metal stirring device according to claim 23, wherein a power supply device, which allows a direct current to flow, is connected between the pair of electrodes.

26. The molten metal stirring device according to claim 24,
35 wherein a power supply device, which allows an alternating current to flow, is connected between the pair of electrodes, and

20375-1080

35

the period of the alternating current is controlled in relationship to the rotation periods of the different magnetic poles of the rotating-shifting magnetic field unit main body so that the first electromagnetic force drives the molten metal in the same direction even though the different
5 magnetic poles are rotated.

27. A molten metal transfer device that transfers molten metal to a second melting furnace from a first melting furnace, the molten metal transfer device comprising:

10 a passage member that includes a passage allowing the first and second melting furnaces to communicate with each other,

wherein a rotating-shifting magnetic field unit main body, which is rotatable to drive molten metal present in the passage, is provided outside a middle portion of the passage member,

15 the rotating-shifting magnetic field unit main body includes a permanent magnet,

input/output magnetic lines of force, which go out of the permanent magnet or enter the permanent magnet, are moved by the rotation of the rotating-shifting magnetic field unit main body while
20 penetrating the molten metal present in the passage,

a first electromagnetic force for driving the molten metal present in the passage toward the second melting furnace from the first melting furnace is generated by eddy currents that are generated by the movement of the input/output magnetic lines of force,

25 the passage member includes a pair of electrodes that are provided therein and allow current to flow through the molten metal,

the pair of electrodes are provided at positions where the current flowing between the pair of electrodes and the input/output magnetic lines of force intersect each other and generate a second
30 electromagnetic force for driving the molten metal in the same direction as the first electromagnetic force, and

the molten metal present in the passage is driven toward the second melting furnace from the first melting furnace by a resultant driving force of the first and second electromagnetic forces.

35

28. The molten metal transfer device according to claim 27,

20375-1080

36

wherein an opening of a bottom wall of the first melting furnace and an opening of a bottom wall of the second melting furnace communicate with each other through the passage member.

5 29. The molten metal transfer device according to claim 27,
wherein the pair of electrodes are provided in the passage of the
passage member at a predetermined interval in a horizontal direction
crossing a height direction.

10 30. The molten metal transfer device according to claim 27,
wherein the rotating-shifting magnetic field unit main body is
adapted to be rotatable about the horizontal axis.

15 31. The molten metal stirring device according to claim 27,
wherein the rotating-shifting magnetic field unit main body
includes one or a plurality of the permanent magnets, and
the same magnetic poles are arranged around a horizontal axis
intersecting a height direction.

20 32. The molten metal stirring device according to claim 27,
wherein the rotating-shifting magnetic field unit main body
includes one or a plurality of the permanent magnets, and
different magnetic poles are alternately arranged around a
horizontal axis intersecting a height direction.


25 33. The molten metal stirring device according to claim 31,
wherein a power supply device, which allows a direct current to
flow, is connected between the pair of electrodes.

30 34. The molten metal stirring device according to claim 32,
wherein a power supply device, which allows an alternating
current to flow, is connected between the pair of electrodes, and
the period of the alternating current is controlled in relationship to
the rotation periods of the different magnetic poles of the rotating-shifting
35 magnetic field unit main body so that the first electromagnetic force
drives the molten metal in the same direction even though the different

20375-1080

37

magnetic poles are rotated.



2/11




FIG. 2A




FIG. 2B

3/11




FIG. 3A




FIG. 3B




FIG. 3C

4/11




FIG. 4A




FIG. 4B




FIG. 4C

5/11




FIG. 5A







FIG. 5B

6/11



7/11




FIG. 7A




FIG. 7B




FIG. 7C

8/11




FIG. 8A




FIG. 8B

9/11




FIG. 9A




FIG. 9B

10/11




FIG. 10A




FIG. 10B

11/11




FIG. 11A




FIG. 11B

