



US008435826B1

(12) **United States Patent**
Lee

(10) **Patent No.:** **US 8,435,826 B1**
(45) **Date of Patent:** ***May 7, 2013**

(54) **BULK SULFIDE SPECIES TREATMENT OF THIN FILM PHOTOVOLTAIC CELL AND MANUFACTURING METHOD**

(75) Inventor: **Howard W. H. Lee**, Saratoga, CA (US)

(73) Assignee: **Stion Corporation**, San Jose, CA (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 722 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **12/567,704**

(22) Filed: **Sep. 25, 2009**

Related U.S. Application Data

(60) Provisional application No. 61/103,549, filed on Oct. 7, 2008, provisional application No. 61/103,239, filed on Oct. 6, 2008.

(51) **Int. Cl.**
H01L 21/38 (2006.01)

(52) **U.S. Cl.**
USPC **438/85**; 257/E21.466; 257/E21.467;
257/E21.483; 257/E21.485; 257/E21.497

(58) **Field of Classification Search** 438/85;
257/E21.466, 467, 483, 485, 497
See application file for complete search history.

(56) References Cited

U.S. PATENT DOCUMENTS

3,520,732	A	7/1970	Nakayama et al.
3,975,211	A	8/1976	Shirland
4,062,038	A	12/1977	Cuomo et al.
4,332,974	A	6/1982	Fraas
4,335,266	A	6/1982	Mickelsen et al.
4,441,113	A	4/1984	Madan
4,442,310	A	4/1984	Carlson et al.
4,461,922	A	7/1984	Gay et al.

(Continued)

FOREIGN PATENT DOCUMENTS

AU	1998/7865198	2/1999
AU	2001/40599 A1	8/2001

(Continued)

OTHER PUBLICATIONS

Baumann, A., et al., Photovoltaic Technology Review, presentation Dec. 6, 2004, 18 pages.

(Continued)


Primary Examiner — Minchul Yang

(74) *Attorney, Agent, or Firm* — Kilpatrick Townsend & Stockton LLP

(57) ABSTRACT

A method for forming a thin film photovoltaic device. The method includes providing a transparent substrate comprising a surface region and forming a first electrode layer overlying the surface region. The method forms a bulk copper indium disulfide material from a multi-layered structure comprising a copper species, an indium species, and a sulfur species overlying the first electrode layer. The bulk copper indium disulfide material comprises one or more portions of a copper poor copper indium disulfide material, a copper poor surface regions, and one or more portions of a sulfur deficient copper indium disulfide material characterized by at least a CuInS_{2-x} species, where $0 < x < 2$. The copper poor surface and one or more portions of the copper poor copper indium disulfide material are subjected to a sodium species derived from a sodium sulfide material to convert the copper poor surface from an n-type characteristic to a p-type characteristic. The method also subjects the one or more portions of the sulfur deficient copper indium disulfide material to a sulfur species derived from the sodium sulfide material to improve a conversion efficiency characteristic of the photovoltaic device. A window layer is formed overlying the copper indium disulfide material.

21 Claims, 11 Drawing Sheets



U.S. PATENT DOCUMENTS					
4,465,575 A	8/1984	Love et al.	6,307,148 B1	10/2001	Takeuchi et al.
4,471,155 A	9/1984	Mohr et al.	6,328,871 B1	12/2001	Ding et al.
4,499,658 A	2/1985	Lewis	RE37,512 E	1/2002	Szlufcik et al.
4,507,181 A	3/1985	Nath et al.	6,361,718 B1	3/2002	Shinmo et al.
4,517,403 A	5/1985	Morel et al.	6,372,538 B1	4/2002	Wendt et al.
4,518,855 A	5/1985	Malak	6,423,565 B1	7/2002	Barth et al.
4,532,372 A	7/1985	Nath et al.	6,632,113 B1	10/2003	Noma et al.
4,542,255 A	9/1985	Tanner et al.	6,635,307 B2	10/2003	Huang et al.
4,581,108 A	4/1986	Kapur et al.	6,653,701 B1	11/2003	Yamazaki et al.
4,589,194 A	5/1986	Roy	6,667,492 B1	12/2003	Kendall
4,598,306 A	7/1986	Nath et al.	6,690,041 B2	2/2004	Armstrong et al.
4,599,154 A	7/1986	Bender et al.	6,784,492 B1	8/2004	Morishita
4,611,091 A	9/1986	Choudary et al.	6,852,920 B2	2/2005	Sager et al.
4,623,601 A	11/1986	Lewis et al.	6,878,871 B2	4/2005	Scher et al.
4,625,070 A	11/1986	Berman et al.	6,974,976 B2	12/2005	Hollars
4,638,111 A	1/1987	Gay	7,122,398 B1	10/2006	Pichler
4,661,370 A	4/1987	Tarrant	7,179,677 B2	2/2007	Ramanathan et al.
4,663,495 A	5/1987	Berman et al.	7,194,197 B1	3/2007	Wendt et al.
4,724,011 A	2/1988	Turner et al.	7,220,321 B2	5/2007	Barth et al.
4,727,047 A	2/1988	Bozler et al.	7,235,736 B1	6/2007	Buller et al.
4,751,149 A	6/1988	Vijayakumar et al.	7,252,923 B2	8/2007	Kobayashi
4,775,425 A	10/1988	Guha et al.	7,265,037 B2	9/2007	Yang et al.
4,798,660 A	1/1989	Ermer et al.	7,319,190 B2	1/2008	Tuttle
4,816,082 A	3/1989	Guha et al.	7,364,808 B2	4/2008	Sato et al.
4,816,420 A	3/1989	Bozler et al.	7,441,413 B2	10/2008	Bae et al.
4,837,182 A	6/1989	Bozler et al.	7,442,413 B2	10/2008	Zwaap et al.
4,873,118 A	10/1989	Elias et al.	7,544,884 B2	6/2009	Hollars
4,915,745 A	4/1990	Pollock et al.	7,736,755 B2	6/2010	Igarashi et al.
4,950,615 A	8/1990	Basol et al.	7,741,560 B2	6/2010	Yonezawa
4,968,354 A	11/1990	Nishiura et al.	7,855,089 B2	12/2010	Farris, III et al.
4,996,108 A	2/1991	Divigalpitiya et al.	7,863,074 B2	1/2011	Wieting
5,008,062 A	4/1991	Anderson et al.	7,910,399 B1	3/2011	Wieting
5,011,565 A	4/1991	Dube et al.	7,955,891 B2	6/2011	Wieting
5,028,274 A	7/1991	Basol et al.	7,960,204 B2	6/2011	Lee
5,039,353 A	8/1991	Schmitt	7,993,954 B2	8/2011	Wieting
5,045,409 A	9/1991	Eberspacher et al.	7,993,955 B2	8/2011	Wieting
5,078,803 A	1/1992	Pier et al.	7,998,762 B1	8/2011	Lee et al.
5,125,984 A	6/1992	Kruehler et al.	8,003,430 B1	8/2011	Lee
5,133,809 A	7/1992	Sichanugrist et al.	8,008,110 B1	8/2011	Lee
5,137,835 A	8/1992	Karg	8,008,111 B1	8/2011	Lee
5,154,777 A	10/1992	Blackmom et al.	8,008,112 B1	8/2011	Lee
5,180,686 A	1/1993	Banerjee et al.	8,026,122 B1	9/2011	Lee
5,211,824 A	5/1993	Knapp	2002/0002992 A1	1/2002	Kariya et al.
5,217,564 A	6/1993	Bozler et al.	2002/0004302 A1	1/2002	Fukumoto et al.
5,231,047 A	7/1993	Ovshinsky et al.	2002/0061361 A1	5/2002	Nakahara et al.
5,248,345 A	9/1993	Sichanugrist et al.	2002/0063065 A1	5/2002	Sonoda et al.
5,261,968 A	11/1993	Jordan	2003/0075717 A1	4/2003	Kondo et al.
5,298,086 A	3/1994	Guha et al.	2003/0089899 A1	5/2003	Lieber et al.
5,336,623 A	8/1994	Sichanugrist et al.	2004/0063320 A1	4/2004	Hollars
5,346,853 A	9/1994	Guha et al.	2004/0084080 A1	5/2004	Sager et al.
5,397,401 A	3/1995	Toma et al.	2004/0095658 A1	5/2004	Buretea et al.
5,445,847 A	8/1995	Wada	2004/0110393 A1	6/2004	Munzer et al.
5,474,939 A	12/1995	Pollock et al.	2004/0187917 A1	9/2004	Pichler
5,501,744 A	3/1996	Albright et al.	2004/0245912 A1	12/2004	Thurk et al.
5,512,107 A	4/1996	Van den Berg	2004/0252488 A1	12/2004	Thurk
5,528,397 A	6/1996	Zavracky et al.	2004/0256001 A1	12/2004	Mitra et al.
5,536,333 A	7/1996	Foote et al.	2005/0074915 A1	4/2005	Tuttle et al.
5,578,103 A	11/1996	Araujo et al.	2005/0098205 A1	5/2005	Roscheisen et al.
5,578,503 A	11/1996	Karg et al.	2005/0109392 A1	5/2005	Hollars
5,622,634 A	4/1997	Noma et al.	2005/0164432 A1	7/2005	Lieber et al.
5,626,688 A	5/1997	Probst et al.	2005/0194036 A1	9/2005	Basol
5,665,175 A	9/1997	Safir	2005/0287717 A1	12/2005	Heald et al.
5,676,766 A	10/1997	Probst et al.	2006/0034065 A1	2/2006	Thurk
5,726,065 A	3/1998	Szlufcik et al.	2006/0040103 A1	2/2006	Whiteford et al.
5,738,731 A	4/1998	Shindo et al.	2006/0051505 A1	3/2006	Kortshagen et al.
5,868,869 A	2/1999	Albright et al.	2006/0096536 A1	5/2006	Tuttle
5,977,476 A	11/1999	Guha et al.	2006/0096537 A1	5/2006	Tuttle
5,981,868 A	11/1999	Kushiya et al.	2006/0096635 A1	5/2006	Tuttle
5,985,691 A	11/1999	Basol et al.	2006/0102230 A1	5/2006	Tuttle
6,040,521 A	3/2000	Kushiya et al.	2006/0130890 A1	6/2006	Hantschel et al.
6,048,442 A	4/2000	Kushiya et al.	2006/0160261 A1	7/2006	Sheats et al.
6,092,669 A	7/2000	Kushiya et al.	2006/0174932 A1	8/2006	Usui et al.
6,107,562 A	8/2000	Hashimoto et al.	2006/0219288 A1	10/2006	Tuttle
6,127,202 A	10/2000	Kapur et al.	2006/0219547 A1	10/2006	Tuttle
6,166,319 A	12/2000	Matsuyama	2006/0220059 A1	10/2006	Satoh et al.
6,172,297 B1	1/2001	Hezel et al.	2006/0249202 A1	11/2006	Yoo et al.
6,258,620 B1	7/2001	Morel et al.	2006/0267054 A1	11/2006	Martin et al.
6,294,274 B1	9/2001	Kawazoe et al.	2007/0006914 A1	1/2007	Lee
			2007/0089782 A1	4/2007	Scheuten et al.

2007/0116892	A1	5/2007	Zwaap
2007/0116893	A1	5/2007	Zwaap
2007/0151596	A1	7/2007	Nasuno et al.
2007/0163643	A1	7/2007	Van Duren et al.
2007/0169810	A1	7/2007	Van Duren et al.
2007/0193623	A1	8/2007	Krasnov
2007/0209700	A1	9/2007	Yonezawa et al.
2007/0264488	A1	11/2007	Lee
2007/0283998	A1	12/2007	Kuriyagawa et al.
2007/0289624	A1	12/2007	Kuriyagawa et al.
2008/0032044	A1	2/2008	Kuriyagawa et al.
2008/0041446	A1	2/2008	Wu et al.
2008/0057616	A1	3/2008	Robinson et al.
2008/0092945	A1	4/2008	Munteanu et al.
2008/0092953	A1	4/2008	Lee
2008/0092954	A1	4/2008	Choi
2008/0105294	A1	5/2008	Kushiya et al.
2008/0110491	A1	5/2008	Buller et al.
2008/0110495	A1	5/2008	Onodera et al.
2008/0121264	A1	5/2008	Chen et al.
2008/0121277	A1	5/2008	Robinson et al.
2008/0210303	A1	9/2008	Lu et al.
2008/0280030	A1	11/2008	Van Duren et al.
2009/0021157	A1	1/2009	Kim et al.
2009/0087940	A1	4/2009	Kushiya
2009/0087942	A1	4/2009	Meyers
2009/0145746	A1	6/2009	Hollars
2009/0217969	A1	9/2009	Matsushima et al.
2009/0234987	A1	9/2009	Lee et al.
2009/0235983	A1	9/2009	Girt et al.
2009/0235987	A1	9/2009	Akhtar et al.
2009/0293945	A1	12/2009	Peter
2010/0081230	A1	4/2010	Lee
2010/0087016	A1	4/2010	Britt et al.
2010/0087026	A1	4/2010	Winkeler et al.
2010/0096007	A1	4/2010	Mattmann et al.
2010/0101648	A1	4/2010	Morooka et al.
2010/0101649	A1	4/2010	Huignard et al.
2010/0122726	A1	5/2010	Lee
2010/0197051	A1	8/2010	Schlezingner et al.
2010/0210064	A1	8/2010	Hakuma et al.
2010/0267190	A1	10/2010	Hakuma et al.
2011/0070682	A1	3/2011	Wieting
2011/0070683	A1	3/2011	Wieting
2011/0070684	A1	3/2011	Wieting
2011/0070685	A1	3/2011	Wieting
2011/0070686	A1	3/2011	Wieting
2011/0070687	A1	3/2011	Wieting
2011/0070688	A1	3/2011	Wieting
2011/0070689	A1	3/2011	Wieting
2011/0070690	A1	3/2011	Wieting
2011/0073181	A1	3/2011	Wieting
2011/0277837	A1	11/2011	Lee
2011/0287575	A1	11/2011	Lee
2011/0287576	A1	11/2011	Lee

FOREIGN PATENT DOCUMENTS

DE	3314197	A1	3/1983
DE	10104726	A1	8/2002
DE	102005062977	B3	9/2007
FR	2646560		11/1990
GB	2124826	A	2/1984
JP	2000/173969		6/2000
JP	2000/219512		8/2000
JP	2002/167695		6/2002
JP	2002/270871		9/2002
JP	2002/299670		10/2002
JP	2004/332043		11/2004
JP	2005/311292		11/2005
WO	WO 01/57932	A1	8/2001
WO	WO 2005/011002		2/2005
WO	WO 2006/126598	A1	11/2006
WO	WO 2007/022221	A2	2/2007
WO	WO 2007/077171	A2	7/2007
WO	WO 2008/025326	A2	3/2008

OTHER PUBLICATIONS

Chopra et al., "Thin-Film Solar Cells: An Overview", 2004, Progress in Photovoltaics: Research and Applications, 2004, vol. 12, pp. 69-92.

Guillen C., "CuInS₂ Thin Films Grown Sequentially from Binary Sulfides as Compared to Layers Evaporated Directly from the Elements", Semiconductor Science and Technology, vol. 21, No. 5, May 2006, pp. 709-712.

Huang et al., "Photoluminescence and Electroluminescence of ZnS:Cu Nanocrystals in Polymeric Networks", Applied Physics Letters, vol. 70, No. 18, May 5, 1997, pp. 2335-2337.

Huang et al., Preparation of ZnxCd_{1-x}S Nanocomposites in Polymer Matrices and their Photophysical Properties, Langmuir, 1998, vol. 14, No. 15, pp. 4342-4344.

International Solar Electric Technology, Inc. (ISET) "Thin Film CIGS", Retrieved from <http://www.isetinc.com/cigs.html> on Oct. 1, 2008, 4 pages.

Kapur et al., "Fabrication of CIGS Solar Cells via Printing of Nanoparticle Precursor Inks", DOE Solar Program Review Meeting 2004, DOE/GO-102005-2067, p. 135-136.

Kapur et al., "Non-Vacuum Processing of CuIn_{1-x}Ga_xSe₂ Solar Cells on Rigid and Flexible Substrates using Nanoparticle Precursor Inks", Thin Solid Films, 2003, vol. 431-432, pp. 53-57.

Kapur et al., "Non-Vacuum Processing of CIGS Solar Cells on Flexible Polymer Substrates", Proceedings of the Third World Conference on Photovoltaic Energy Conversion, Osaka, Japan, 2P-D3-43, 2003.

Kapur et al., "Non-Vacuum Printing Process for CIGS Solar Cells on Rigid and Flexible Substrates", 29th IEEE Photovoltaic Specialists Conference, New Orleans, LA, IEEE, 2002, pp. 688-691.

Kapur et al., "Fabrication of Light Weight Flexible CIGS Solar Cells for Space Power Applications", Materials Research Society, Proceedings vol. 668, (2001) pp. H3.5.1-H3.5.6.

Kapur et al., "Nanoparticle Oxides Precursor Inks for Thin Film Copper Indium Gallium Selenide (CIGS) Solar Cells", Materials Research Society Proceedings, vol. 668, (2001) pp. H2.6.1-H2.6.7.

Metha et al., "A graded diameter and oriented nanorod-thin film structure for solar cell application: a device proposal", Solar Energy Materials & Solar Cells, 2005, vol. 85, pp. 107-113.

Srikant V., et al., "On the Optical Band Gap of Zinc Oxide", Journal of Applied Physics, vol. 83, No. 10, May 15, 1998, pp. 5447-5451.

Yang et al., "Fabrication and Characteristics of ZnS Nanocrystals/Polymer Composite Doped with Tetraphenylbenzidine Single Layer Structure Light-emitting Diode", Applied Physics Letters, vol. 69, No. 3, Jul. 15, 1996, pp. 377-379.

Yang et al., "Preparation, Characterization and Electroluminescence of ZnS Nanocrystals in a Polymer Matrix", Journal Material Chem., 1997, vol. 7, No. 1, pp. 131-133.

Yang et al., "Electroluminescence from ZnS/CdS Nanocrystals/Polymer Composite", Synthetic Metals, 1997, vol. 91, pp. 347-349.

Examination Report for PCT Patent Application No. PCT/US2008/0077965, Apr. 8, 2010, 7 pages. IPER.

International Search Report and Written Opinion for PCT Patent Application No. PCT/US2009/058829 mailed on Mar. 11, 2011, 12 pages.

International Search Report and Written Opinion for PCT Patent Application No. PCT/US2009/065351, mailed on Jan. 26, 2010, 13 pages.

International Search Report and Written Opinion for PCT Patent Application No. PCT/US09/59097, mailed on Dec. 23, 2009, 12 pages.

International Search Report and Written Opinion for PCT Patent Application No. PCT/US09/59095, mailed on Dec. 4, 2009, 12 pages.

International Search Report and Written Opinion for PCT Patent Application No. PCT/US08/77965, mailed on Dec. 9, 2008, 8 pages.

International Search Report and Written Opinion for PCT Patent Application No. PCT/US08/78019 mailed on Dec. 8, 2008, 9 pages.

Non-Final Office Action of Sep. 15, 2011 for U.S. Appl. No. 12/237,377, 18 pages.

Non-Final Office Action of Sep. 7, 2011 for U.S. Appl. No. 12/237,369, 21 pages.

Notice of Allowance of Sep. 2, 2011 for U.S. Appl. No. 12/953,721, 20 pages.
Notice of Allowance of Aug. 26, 2011 for U.S. Appl. No. 12/953,725, 20 pages.
Notice of Allowance of Aug. 25, 2011 for U.S. Appl. No. 12/953,729, 19 pages.
Non-Final Office Action of Aug. 4, 2011 for U.S. Appl. No. 12/479,409, 39 pages.
Notice of Allowance of Aug. 2, 2011 for U.S. Appl. No. 12/953,716, 18 pages.
Notice of Allowance of Aug. 1, 2011 for U.S. Appl. No. 12/577,132, 34 pages.
Notice of Allowance of Aug. 1, 2011 for U.S. Appl. No. 12/953,701, 18 pages.
Notice of Allowance of Aug. 1, 2011 for U.S. Appl. No. 12/953,708, 17 pages.
Final Office Action of May 31, 2011 for U.S. Appl. No. 12/621,489, 13 pages.
Notice of Allowance of May 25, 2011 for U.S. Appl. No. 12/566,651, 8 pages.
Non-Final Office Action of May 2, 2011 for U.S. Appl. No. 12/953,729, 9 pages.
Non-Final Office Action of May 2, 2011 for U.S. Appl. No. 12/953,725, 9 pages.
Non-Final Office Action of May 2, 2011 for U.S. Appl. No. 12/953,721, 9 pages.
Non-Final Office Action of May 2, 2011 for U.S. Appl. No. 12/953,716, 9 pages.
Non-Final Office Action of May 2, 2011 for U.S. Appl. No. 12/953,708, 9 pages.
Non-Final Office Action of May 2, 2011 for U.S. Appl. No. 12/953,701, 9 pages.
Non-Final Office Action of Apr. 28, 2011 for U.S. Appl. No. 12/237,369, 17 pages.
Notice of Allowance of Apr. 27, 2011 for U.S. Appl. No. 12/564,886, 11 pages.
Notice of Allowance of Apr. 26, 2011 for U.S. Appl. No. 12/564,046, 11 pages.
Notice of Allowance of Apr. 25, 2011 for U.S. Appl. No. 12/563,065, 11 pages.
Notice of Allowance of Apr. 19, 2011 for U.S. Appl. No. 12/567,715, 11 pages.
Notice of Allowance of Apr. 8, 2011 for U.S. Appl. No. 12/953,697, 11 pages.

Notice of Allowance of Apr. 5, 2011 for U.S. Appl. No. 12/953,679, 11 pages.
Notice of Allowance of Apr. 5, 2011 for U.S. Appl. No. 12/953,674, 11 pages.
Final Office Action of Dec. 27, 2010 for U.S. Appl. No. 12/479,409, 26 pages.
Non-Final Office Action of Dec. 17, 2010 for U.S. Appl. No. 12/577,132, 11 pages.
Notice of Allowance of Dec. 14, 2010 for U.S. Appl. No. 12/558,117, 8 pages.
Supplemental Notice of Allowability of Dec. 10, 2010 for U.S. Appl. No. 12/568,641, 3 pages.
Notice of Allowance of Nov. 19, 2010 for U.S. Appl. No. 12/568,641, 6 pages.
Notice of Allowance of Oct. 21, 2010 for U.S. Appl. No. 12/565,735, 4 pages.
Restriction Requirement of Oct. 18, 2010 for U.S. Appl. No. 12/568,641, 4 pages.
Non-Final Office Action of Sep. 28, 2010 for U.S. Appl. No. 12/237,371, 15 pages.
Non-Final Office Action of Sep. 22, 2010 for U.S. Appl. No. 12/621,489, 23 pages.
Notice of Allowance of Aug. 27, 2010 for U.S. Appl. No. 12/509,136, 8 pages.
Non-Final Office Action of Aug. 18, 2010 for U.S. Appl. No. 12/237,369, 17 pages.
Non-Final Office Action of Aug. 5, 2010 for U.S. Appl. No. 12/565,735, 14 pages.
Non-Final Office Action of Jul. 22, 2010 for U.S. Appl. No. 12/479,409, 21 pages.
Non-Final Office Action of May 27, 2010 for U.S. Appl. No. 12/568,641, 10 pages.
Ellmer et al., Copper Indium Disulfide Solar Cell Absorbers Prepared in a One-Step Process by Reactive Magnetron Sputtering from Copper and Indium Targets; Elsevier Science B.V; Thin Solid Films 413 (2002) pp. 92-97.
International Search Report & Written Opinion of PCT Application No. PCT/US 09/46161, date of mailing Jul. 27, 2009, 14 pages total.
International Search Report & Written Opinion of PCT Application No. PCT/US 09/46802, mailed on Jul. 31, 2009, 11 pages total.
Onuma et al., Preparation and Characterization of CuInS Thin Films Solar Cells with Large Grain, Elsevier Science B.V; Solar Energy Materials & Solar Cells 69 (2001) pp. 261-269.




Figure 1




Figure 2




Figure 3




Figure 4




Figure 5




Figure 6




Figure 7




Figure 8




Figure 10




Figure 11




Figure 12




Figure 13

1

BULK SULFIDE SPECIES TREATMENT OF THIN FILM PHOTOVOLTAIC CELL AND MANUFACTURING METHOD

CROSS-REFERENCES TO RELATED APPLICATIONS

This application claims priority to U.S. Provisional Patent Application No. 61/103,549 filed Oct. 7, 2008, entitled "BULK SULFIDE SPECIES TREATMENT OF THIN FILM PHOTOVOLTAIC CELL AND MANUFACTURING METHOD" by inventor HOWARD W. H. LEE, commonly assigned and incorporated by reference herein for all purposes. This application is related to U.S. Provisional Patent Application No. 61/103,239 filed Oct. 6, 2008, commonly assigned and incorporated by reference herein for all purposes. This application is also related to U.S. patent application Ser. No. 12/567,715 filed Sep. 25, 2009, now U.S. Pat. No. 8,003,430, commonly assigned and incorporated by reference herein for all purposes.

BACKGROUND OF THE INVENTION

The present invention relates generally to photovoltaic materials and manufacturing method. More particularly, the present invention provides a method and structure for manufacture of high efficiency thin film photovoltaic cells. Merely by way of example, the present method and materials include absorber materials made of copper indium disulfide species, copper tin sulfide, iron disulfide, or others for single junction cells or multi junction cells.

From the beginning of time, mankind has been challenged to find ways of harnessing energy. Energy comes in the forms such as petrochemical, hydroelectric, nuclear, wind, biomass, solar, and more primitive forms such as wood and coal. Over the past century, modern civilization has relied upon petrochemical energy as an important energy source. Petrochemical energy includes gas and oil. Gas includes lighter forms such as butane and propane, commonly used to heat homes and serve as fuel for cooking. Gas also includes gasoline, diesel, and jet fuel, commonly used for transportation purposes. Heavier forms of petrochemicals can also be used to heat homes in some places. Unfortunately, the supply of petrochemical fuel is limited and essentially fixed based upon the amount available on the planet Earth. Additionally, as more people use petroleum products in growing amounts, it is rapidly becoming a scarce resource, which will eventually become depleted over time.

More recently, environmentally clean and renewable sources of energy have been desired. An example of a clean source of energy is hydroelectric power. Hydroelectric power is derived from electric generators driven by the flow of water produced by dams such as the Hoover Dam in Nevada. The electric power generated is used to power a large portion of the city of Los Angeles in California. Clean and renewable sources of energy also include wind, waves, biomass, and the like. That is, windmills convert wind energy into more useful forms of energy such as electricity. Still other types of clean energy include solar energy. Specific details of solar energy can be found throughout the present background and more particularly below.

Solar energy technology generally converts electromagnetic radiation from the sun to other useful forms of energy. These other forms of energy include thermal energy and electrical power. For electrical power applications, solar cells are often used. Although solar energy is environmentally clean and has been successful to a point, many limitations

2

remain to be resolved before it becomes widely used throughout the world. As an example, one type of solar cell uses crystalline materials, which are derived from semiconductor material ingots. These crystalline materials can be used to fabricate optoelectronic devices that include photovoltaic and photodiode devices that convert electromagnetic radiation into electrical power. However, crystalline materials are often costly and difficult to make on a large scale. Additionally, devices made from such crystalline materials often have low energy conversion efficiencies. Other types of solar cells use "thin film" technology to form a thin film of photosensitive material to be used to convert electromagnetic radiation into electrical power. Similar limitations exist with the use of thin film technology in making solar cells. That is, efficiencies are often poor. Additionally, film reliability is often poor and cannot be used for extensive periods of time in conventional environmental applications. Often, thin films are difficult to mechanically integrate with each other. These and other limitations of these conventional technologies can be found throughout the present specification and more particularly below.

From the above, it is seen that improved techniques for manufacturing photovoltaic materials and resulting devices are desired.

BRIEF SUMMARY OF THE INVENTION

According to embodiments of the present invention, a method and a structure for forming thin film semiconductor materials for photovoltaic applications are provided. More particularly, the present invention provides a method and structure for forming semiconductor materials used for the manufacture of high efficiency photovoltaic cells. Merely by way of example, the present method and materials include absorber materials made of copper indium disulfide species, copper tin sulfide, iron disulfide, or others for single junction cells or multi-junction cells.

In a specific embodiment, a method for forming a thin film photovoltaic device is provided. The method includes providing a transparent substrate including a surface region. A first electrode layer is formed overlying the surface region. The method includes forming a copper layer overlying the first electrode layer and forming an indium layer overlying the copper layer to form a multi-layered structure. In a specific embodiment, the method includes subjecting at least the multi-layered structure to a thermal treatment process in an environment containing a sulfur bearing species and forming a bulk copper indium disulfide material from at least the treatment process of the multi-layered structure. In a specific embodiment, the bulk copper indium disulfide material comprises one or more portions of copper indium disulfide material characterized by a copper-to-indium atomic ratio of less than about 0.95:1. The bulk copper indium disulfide material has a surface region characterized by a copper poor surface comprising a copper to indium atomic ratio of less than about 0.95:1. In a specific embodiment, the bulk copper indium disulfide material comprises one or more sulfur deficient region characterized by a CuInS_{2-x} species, where $0 < x < 2$. The method includes subjecting the copper poor surface and one or more portions of the bulk copper indium disulfide material to a sodium species derived from a sodium sulfide material to convert the copper poor surface from an n-type characteristic to a p-type characteristic and to convert any of the one or more portions of the bulk copper indium disulfide material having the copper-to-indium atomic ratio of less than about 0.95:1 from a p-type characteristic to an n-type characteristic. The method further includes subjecting the one or

3

more sulfur efficient regions to a sulfide species to provide for a desirable conversion efficiency characteristic. The sulfide species is derived from the sodium sulfide material in a preferred embodiment. A window layer is formed overlying the copper indium disulfide material. In a specific embodiment, the subjecting of the copper poor surface, the sulfide deficient surface, and the one or more portions of the bulk copper indium disulfide material is performed during at least a thermal treatment process for a time period.

In an alternative embodiment, a method for forming a thin film photovoltaic device is provided. The method includes providing a transparent substrate including a surface region. The method forms a first electrode layer overlying the surface region. A copper indium material is formed overlying the electrode layer by at least sputtering a target comprising an indium copper material. In a specific embodiment, the copper indium material is subjected to a thermal treatment process in an environment containing a sulfur bearing species to form a copper poor copper indium disulfide material from at least the thermal treatment process of the copper poor copper indium material. In a specific embodiment, the copper indium disulfide material comprises an atomic ratio of Cu:In of less than about 0.95:1. In a specific embodiment, the method includes compensating the copper poor copper indium disulfide material using a sodium species to change from an n-type characteristic to a p-type characteristic. The sodium species is derived from a sodium sulfide material in a specific embodiment. In a specific embodiment, the thermal treatment process further forms a sulfur deficient copper indium disulfide material. In a specific embodiment the method includes compensating the sulfur deficient copper indium disulfide material using a sulfide ion derived from the sodium sulfide material. The method further forms a window layer overlying the copper indium disulfide material.

In a yet alternative embodiment, a method for forming a thin film photovoltaic device is provided. The method includes providing a transparent substrate comprising a surface region. A first electrode layer is formed overlying the surface region. A chalcopyrite material is formed overlying the first electrode layer. In a specific embodiment, the chalcopyrite material comprises a copper poor copper indium disulfide region. The copper poor copper indium disulfide region having an atomic ratio of Cu:In of about 0.99 and less. The method includes compensating the copper poor copper indium disulfide region using a sodium sulfide species to cause the chalcopyrite material to change from an n-type characteristic to a p-type characteristic. In a specific embodiment, the chalcopyrite material includes also a sulfur deficient copper indium disulfide region. The method includes compensating the sulfur deficient copper indium disulfide region using a sulfide ion species to provide for a desirable conversion efficiency characteristic for the photovoltaic device in a specific embodiment. The method includes forming a window layer overlying the chalcopyrite material and forming a second electrode layer overlying the window layer.

In yet another embodiment, a thin film photovoltaic device is provided. The thin film photovoltaic device includes a substrate comprising a surface region. The thin film photovoltaic device includes a first electrode layer overlying the surface region. A chalcopyrite material overlying the first electrode layer. In a specific embodiment, the chalcopyrite material includes a copper poor copper indium disulfide bulk region and a surface region. In a specific embodiment, the copper poor copper indium disulfide bulk region has an atomic ratio of Cu:In of about 0.99 and less. A compensating sodium species is provided within one or more portions of the copper poor copper indium disulfide region to change the

4

copper poor copper indium disulfide region from an n-type impurity characteristic to a p-type impurity characteristic. Additionally, a compensating sulfur species is provided with the one or more sulfur deficient copper indium disulfide region to provide for a desirable conversion efficiency characteristic for the thin film photovoltaic device. The thin film photovoltaic device also includes a window layer overlying the chalcopyrite material and a second electrode layer overlying the window layer.

Still further, the present invention provides a method for forming a thin film photovoltaic device. The method includes providing a transparent substrate, which may be soda lime glass or white water glass, comprising a surface region. The method includes forming a first electrode layer overlying the surface region and forming a copper containing layer overlying the first electrode layer. The method also includes forming an indium containing layer overlying the copper containing layer to form a multi-layered structure. The method includes subjecting at least the multi-layered structure to a thermal treatment process in an environment containing a sulfur bearing species according to one or more embodiments. The method includes forming a bulk copper indium disulfide containing material from at least the thermal treatment process of the multi-layered structure. The bulk copper indium disulfide containing material comprises one or more portions of a sulfur deficient copper indium disulfide containing material characterized by at least a CuInS_2 species, where $0 < x < 2$. In a specific embodiment, the method also includes subjecting the one or more portions of the sulfur deficient copper indium disulfide containing material to a sulfur species derived from a sulfur bearing material to improve a device characteristic from a first value to a second value, which is higher than the first value for open circuit voltage, efficiency, and short circuit current. In a specific embodiment, the present method further includes forming a window layer overlying the copper indium disulfide material.

Many benefits are achieved by ways of present invention. For example, the present invention uses starting materials that are commercially available to form a thin film of semiconductor bearing material overlying a suitable substrate member. The thin film of semiconductor bearing material can be further processed to form a semiconductor thin film material of desired characteristics, such as atomic stoichiometry, impurity concentration, carrier concentration, doping, and others. In a specific embodiment, the band gap of the resulting copper indium disulfide material is about 1.55 eV. Additionally, the present method uses environmentally friendly materials that are relatively less toxic than other thin-film photovoltaic materials. In a preferred embodiment, the present method and resulting structure is substantially free from a parasitic junction on an absorber layer based upon a copper poor chalcopyrite material. Also in a preferred embodiment, the open circuit voltage of the chalcopyrite material such as copper indium disulfide ranges from about 0.8 volts and greater and preferably 0.9 volts and greater or 1.0 volts and greater up to 1.2 volts. Depending on the embodiment, one or more of the benefits can be achieved. These and other benefits will be described in more detailed throughout the present specification and particularly below.

Merely by way of example, the present method and materials include absorber materials made of copper indium disulfide species, copper tin sulfide, iron disulfide, or others for single junction cells or multi junction cells.

BRIEF DESCRIPTION OF THE DRAWINGS

FIGS. 1-8 are schematic diagrams illustrating a method and structure for forming a thin film photovoltaic device according to an embodiment of the present invention;

FIGS. 9-11 are simplified diagrams illustrating a method and structure for forming a thin film photovoltaic device including a sodium species treatment and a sulfide species treatment according to an embodiment of the present invention;

FIG. 12 is a simplified diagram of an copper indium disulfide material having one or more copper poor regions and one or more sulfur deficient regions according to an embodiment of the present invention; and

FIG. 13 is an open circuit voltage plot for experiments according to one or more embodiments of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

According to embodiments of the present invention, a method and a structure for forming semiconductor materials for photovoltaic applications are provided. More particularly, the present invention provides a method for manufacturing thin film photovoltaic devices. Merely by way of example, the method has been used to provide a copper indium disulfide thin film material for high efficiency solar cell application. But it would be recognized that the present invention has a much broader range of applicability, for example, embodiments of the present invention may be used to form other semiconducting thin films or multi layers comprising iron sulfide, cadmium sulfide, zinc selenide, and others, and metal oxides such as zinc oxide, iron oxide, copper oxide, and others.

FIGS. 1-8 are simplified schematic diagrams illustrating a method for forming a thin film photovoltaic device according to an embodiment of the present invention. These diagrams are merely examples, which should not unduly limit the claims herein. One skilled in the art would recognize other variations, modifications, and alternatives. As shown in FIG. 1, a substrate 110 is provided. In an embodiment, the substrate 110 includes a surface region 112 and is held in a process stage within a process chamber (not shown). In another embodiment, the substrate 110 is an optically transparent solid material. For example, substrate 110 can use material such as glass, quartz, fused silica, or plastic, or metal, or foil, or semiconductor, or composite materials. Depending upon the embodiment, the substrate can be a single material, multiple materials, which are layered, composites, or stacked, including combinations of these, and the like. Of course there can be other variations, modifications, and alternatives.

As shown in FIG. 2, the present method forms an electrode layer 120 overlying a surface region 112 of substrate 110. The electrode layer can be a suitable metal material, a semiconductor material or a transparent conducting oxide material, or a combination. Electrode layer 120 can be formed using techniques such as sputtering, evaporation (e.g., using electron beam), electro-plating, or a combination of these, and the like, according to a specific embodiment. Preferably, the electrode layer is characterized by a resistivity of about 10 Ohm/cm² to 100 Ohm/cm² and less according to a specific embodiment. In a specific embodiment, the electrode layer can be made of molybdenum or tungsten. The electrode layer can have a thickness ranging from about 100 nm to 2 micron in a specific embodiment, but can also be others depending on the application. Other suitable materials such as copper, chromium, aluminum, nickel, or platinum, and the like may also be used. Of course, there can be other variations, modifications, and alternatives.

As shown in FIG. 3, a copper layer 130 is formed overlying the electrode layer. In particular, copper (Cu) layer 130 is formed overlying the electrode layer 120. For example, the

copper layer can be formed using a sputtering process using a suitable copper target. In one example, a DC magnetron sputtering process can be used to deposit Cu layer 130 onto the electrode layer 120. The sputtering process is performed under a suitable pressure and temperature. In a specific embodiment, the sputtering process can be performed under a deposition pressure of about 6.2 mTorr. In a specific embodiment, the deposition pressure may be controlled using Ar gas. In a specific embodiment, an Ar gas flow rate of about 32 sccm is used to achieve the desired deposition pressure. Deposition can be provided at room temperature without heating the substrate. Of course, minor heating may result due to plasma generated during deposition. Additionally, a DC power supply of about 115 W may be used for the sputtering process. Depending on the embodiment, DC power ranging from 100 W to 150 W may be used depending on the specific materials used. A deposition time for a Cu layer of 330 nm thickness is about 6 minutes or more under the described deposition condition. Of course, the deposition condition can be varied and modified according to a specific embodiment. One skilled in the art would recognize other variations, modifications, and alternatives.

In a preferred embodiment, the method includes forming a barrier layer 125 overlying the electrode layer to form an interface region between the electrode layer and the copper layer. In a specific embodiment, the interface region is maintained substantially free from a metal disulfide layer having a semiconductor characteristic that is different from a copper indium disulfide material formed during later processing steps. Depending upon the embodiment, the barrier layer has suitable conductive characteristics and can be reflective to allow electromagnetic radiation to reflect back into a photovoltaic cell or can also be transparent or the like. In a specific embodiment, the barrier layer is selected from platinum, titanium, chromium, or silver. Of course, there can be other variations, modifications, and alternatives.

Referring now to FIG. 4. The method forms an indium layer 140 overlying copper layer 130. The indium layer is deposited over the copper layer using a sputtering process in a specific embodiment. In a specific embodiment, the indium layer can be deposited using a DC magnetron sputtering process under a similar condition for depositing the Cu layer. The deposition time for the indium layer may be shorter than that for Cu layer. As merely an example, 2 minutes and 45 seconds may be enough for depositing an In layer of about 410 nm in thickness according to a specific embodiment. In another example, the indium layer can be deposited overlying the copper layer using an electro-plating process, or others dependent on specific embodiment.

FIGS. 1 through 4 illustrate a method of forming a multilayered structure 150 comprising copper and indium on a substrate for a thin film photovoltaic device according to an embodiment of the present invention. In a specific embodiment, copper layer 130 and indium layer 140 are provided in a certain stoichiometry to allow for a Cu-rich material with an atomic ratio of Cu:In greater than 1 for the multilayered structure 150. For example, the atomic ratio Cu:In can be in a range from about 1.2:1 to about 2.0:1 or larger depending upon the specific embodiment. In an implementation, the atomic ratio of Cu:In is between 1.35:1 and 1.60:1. In another implementation, the atomic ratio of Cu:In is selected to be about 1.55:1. In a preferred embodiment, the atomic ratio Cu:In is provided such that Cu is limiting, which consumes essentially all of the indium species provided for the resulting structure. In a specific embodiment, indium layer 140 is provided to cause substantially no change in the copper layer 130 formed until further processing. In another embodiment,

indium layer **140** can be first deposited overlying the electrode layer followed by deposition of the copper layer **130** overlying the indium layer. Of course there can be other variations, modifications, and alternatives.

As shown in FIG. 5, multilayered structure **150** is subjected to a thermal treatment process **200**. In a specific embodiment, the thermal treatment process is provided in an environment containing at least a sulfur bearing species **210**. The thermal treatment process is performed at an adequate pressure and temperature. In a specific embodiment, the thermal treatment process is provided at a temperature ranging from about 400 Degrees Celsius to about 600 Degrees Celsius. In certain embodiment, the thermal treatment process can be a rapid thermal process provided at the temperature range for about three to fifteen minutes. In one example, the sulfur bearing species is in a fluid phase. As an example, the sulfur bearing species can be provided in a solution, which has dissolved Na_2S , CS_2 , $(\text{NH}_4)_2\text{S}$, thiosulfate, among others. In another example, the sulfur bearing species **210** is gas phase hydrogen sulfide. In other embodiments, the sulfur bearing species can be provided in a solid phase. As merely an example, elemental sulfur can be heated and allowed to vaporize into a gas phase, e.g., as S_n . In a specific embodiment, the gas phase sulfur is allowed to react to the indium/copper layers. In other embodiments, combinations of sulfur species can be used. Of course, the thermal treatment process **200** includes certain predetermined ramp-up and ramp down time and ramp-up and ramp-down rate. For example, the thermal treatment process is a rapid thermal annealing process. In a specific embodiment, the hydrogen sulfide gas is provided through one or more entry valves with flow rate controls into the process chamber. The hydrogen sulfide gas pressure in the chamber may be controlled by one or more pumping systems or others, depending on the embodiment. Of course, there can be other variations, modifications, and alternatives.

In a specific embodiment, the sulfur bearing species can be provided as a layer material overlying the indium and copper layers or copper and indium layers. In a specific embodiment, the sulfur bearing species is provided as a thin layer or as a patterned layer. Depending upon the embodiment, the sulfur bearing species can be provided as a slurry, a powder, a solid material, a gas, a paste, or other suitable form. Of course, there can be other variations, modifications, and alternatives.

Referring to FIG. 5, the thermal treatment process **200** causes a reaction between copper indium material within the multilayered structure **150** and the sulfur bearing species **210**, thereby forming a layer of copper indium disulfide material (or a copper indium disulfide thin film) **220**. In one example, the copper indium disulfide material or copper indium disulfide thin film **220** is formed by incorporating sulfur ions/atoms stripped or decomposed from the sulfur bearing species into the multilayered structure **150** with indium atoms and copper atoms mutually diffused therein. In an embodiment, the thermal treatment process **200** results in a formation of a cap layer **221** overlying the transformed copper indium disulfide material **220**. The cap layer contains a thickness of substantially copper sulfide material but substantially free of indium atoms. The cap layer includes a surface region **225**. In a specific embodiment, the formation of this cap layer is under a Cu-rich conditions for the Cu—In bearing multilayered structure **150**. Depending on the embodiment, the thickness of the copper sulfide material **221** is on an order of about five to ten nanometers and greater based on original multilayered structure **150** with indium layer **140** overlying copper layer **130**. Of course, there can be other variations, modifications, and alternatives.

FIG. 6 is a schematic diagram illustrating a process of the method for forming a thin film photovoltaic device according to an embodiment of the present invention. The diagram is merely an example, which should not unduly limit the claims herein. One skilled in the art would recognize other variations, modifications, and alternatives. As shown in FIG. 6, a dip process **300** is performed to the copper sulfide material **221** that covers the copper indium disulfide thin film **220**. In particular, the dip process is performed by exposing the surface region **225** to a solution of potassium cyanide **310** in a specific embodiment. In a specific embodiment, the solution of potassium cyanide has a concentration of about 1 weight % to about 10 weight % according to a specific embodiment. The solution of potassium cyanide acts as an etchant that is capable of selectively removing copper sulfide material **221** from the surface region of the copper indium disulfide material. The etching process starts from the exposed surface region **225** and down to the thickness of the copper sulfide material **221** and substantially stopped at the interface between the copper sulfide material **221** and copper indium disulfide material **220**. As a result the copper sulfide cap layer **221** is selectively removed by the etching process to expose surface region **228** of the copper indium disulfide thin film material according to a specific embodiment. In a preferred embodiment, the etch selectivity is about 1:100 or more between copper sulfide and copper indium disulfide material. In other embodiments, other selective etching species can be used. In a specific embodiment, the etching species can be hydrogen peroxide. In other embodiments, other techniques including electro-chemical etching, plasma etching, sputter-etching, or any combination of these may be used. In a specific embodiment, the copper sulfide material can be mechanically removed, chemically removed, electrically removed, or any combination of these, and others. In a specific embodiment, an absorber layer made of copper indium disulfide can have a thickness of about 1 to 10 microns, but can be others. Of course, there can be other variations, modifications, and alternatives.

As shown in FIG. 7, the method further process the copper indium disulfide material to form a p-type copper indium disulfide film **320** in a specific embodiment. In certain embodiments, the as-formed copper indium disulfide material may have a desirable p-type semiconducting characteristic. In a specific embodiment, copper indium disulfide material **220** is subjected to a doping process to adjust p-type impurity concentration therein for the purpose of optimizing I-V characteristic of the high efficiency thin film photovoltaic devices. In an example, aluminum species are allowed to mix into the copper indium disulfide material **220**. In another example, the copper indium disulfide material **220** is mixed with a copper indium aluminum disulfide material. Of course, there can be other variations, modifications, and alternatives.

Subsequently, a window layer **310** is formed overlying the p-type copper indium disulfide material **320**. The window layer can be selected from a group consisting of a cadmium sulfide (CdS), a zinc sulfide (ZnS), zinc selenium (ZnSe), zinc oxide (ZnO), zinc magnesium oxide (ZnMgO), or others. In certain embodiments, these materials may be doped with one or more suitable impurities to form an n^+ type semiconductor material. The window layer and the absorber layer forms a PN-junction associated with a photovoltaic cell. The window layer is heavily doped to form a n' -type semiconductor layer in a preferred embodiment. In one example, indium species are used as the doping material to cause formation of the n^+ -type characteristic associated with the window layer **310**. In another example, the doping process is performed under suitable conditions. In a specific embodiment, the window

layer can use an aluminum doped ZnO material. The aluminum doped ZnO material can range from about 200 nm to about 500 nanometers in a specific embodiment. Of course, there can be other variations, modifications, and alternatives.

Referring to FIG. 8, the method forms a conductive layer 330 overlying a portion of a first surface region of the window layer 310. The conductive layer forms a top electrode layer for the photovoltaic device. In one embodiment, the conductive layer 330 is a transparent conductive oxide (TCO). For example, the TCO can be selected from a group consisting of In_2O_3 :Sn (ITO), ZnO :Al (AZO), SnO_2 :F (TFO), and the like, but can be others. In another embodiment, the TCO layer is provided in a certain predetermined pattern to maximize the fill factor and conversion efficiency of the photovoltaic device. In a specific embodiment, the TCO can also function as a window layer, which essentially eliminates a separate window layer. Of course there can be other variations, modifications, and alternatives.

In a preferred embodiment, the present method maintains an interface region between the electrode layer and the copper indium disulfide material substantially free from a metal disulfide layer having different semiconductor characteristics from the copper indium disulfide material. Depending upon the type of electrode material, the metal disulfide layer is selected from molybdenum disulfide layer or the like. In a specific embodiment, the interface region is characterized by a surface morphology substantially capable of preventing any formation of the metal disulfide layer, which is characterized by a thickness of about 5 nanometers to about 10 nanometers. In a preferred embodiment, the present method includes a thermal process during at least the maintaining process or a portion of the maintaining process of at least 300 Degrees Celsius and greater to prevent any formation of the metal disulfide layer, which can be a molybdenum disulfide or like layer. Of course, there can be other variations, modifications, and alternatives.

In a specific embodiment, the present invention provides a method for forming a thin film photovoltaic device, which is outlined below.

1. Start;
2. Provide a transparent substrate comprising a surface region;
3. Form a first electrode layer overlying the surface region;
4. Form a copper layer overlying the first electrode layer;
5. Form an indium layer overlying the copper layer to form a multi-layered structure (alternatively indium is formed first or a multiple layers are sandwiched together);
6. Subject at least the multi-layered structure to a thermal treatment process in an environment containing a sulfur bearing species;
7. Form a bulk copper indium disulfide material from at least the treatment process of the multi-layered structure, the copper indium disulfide material comprising a copper-to-indium atomic ratio ranging from about 1.2:1 to about 2:1 or 1.35:1 to about 1.60:1 (or preferably and alternatively from about 0.99:1 or 0.95:1 and less), a sulfur deficient region comprising a CuInS_{2-x} species, where $0 < x < 2$, and a thickness of substantially copper sulfide material having a copper sulfide surface region;

8. Remove the thickness of the copper sulfide material to expose a surface region having a copper poor surface comprising a copper to indium atomic ratio of less than about 0.95:1 or 0.99:1;

9. Subject the copper poor surface to a sodium species derived from a sodium sulfide material to convert the copper poor surface from an n-type characteristic to a p-type characteristic;

10. Preferably, subject the bulk copper indium disulfide material having the copper-to-indium atomic ratio of 0.99 or 0.95:1 and less to a sodium ion derived from a sodium sulfide material and subject the sulfur deficient region to a sulfur species derived from the sodium sulfide material to convert the copper poor material from an n-type characteristic to a p-type characteristic and the sulfur deficient region to have a desired conversion efficiency characteristics;

11. Subject the copper poor surface and the bulk copper indium disulfide material including the sulfur deficient region to a treatment process during a time period associated with the subjecting of the copper poor surface with the sodium sulfide material and/or with the subjecting of the bulk copper indium disulfide material;

12. Form a window layer overlying the copper indium disulfide material;

13. Form a second electrode layer; and

14. Perform other steps, as desired.

The above sequence of steps provides a method according to an embodiment of the present invention. In a specific embodiment, the present invention provides a method and resulting photovoltaic structure free from parasitic junction regions in the absorber layer, which impair performance of the resulting device. Other alternatives can also be provided where steps are added, one or more steps are removed, or one or more steps are provided in a different sequence without departing from the scope of the claims herein. Details of the present method and structure can be found throughout the present specification and more particularly below.

FIGS. 9-11 are simplified diagrams illustrating a method and structure for forming a thin film photovoltaic device including sodium sulfide material treatment according to an embodiment of the present invention. These diagrams are merely examples, which should not unduly limit the scope of the claims herein. One of ordinary skill in the art would recognize other variations, modifications, and alternatives. In a specific embodiment, the present method begins with partially completed photovoltaic device 900. As shown, the device includes a transparent substrate 901 comprising a surface region, although other substrates can be used. The device also includes a first electrode layer 903 overlying the surface region. In a specific embodiment, the first electrode layer can be any conductive material including conductive metals, oxides, and semiconductor or combinations of these, as well as any material described herein and outside of the present specification.

In a specific embodiment, the photovoltaic device includes a chalcopyrite material, which acts as an absorber for the photovoltaic device. As shown, the chalcopyrite material can include, among others, copper indium disulfide material, copper indium aluminum disulfide, copper indium gallium disulfide, combinations of these, and others. In a specific embodiment, the chalcopyrite is copper rich, or alternatively copper poor and characterized by one or more portions having a copper to indium atomic ratio of 0.99:1 and less or 0.95:1 and less. In a preferred embodiment, the copper indium disulfide material has one or more copper poor regions, which are preferably compensated using an ionic species. Of course, there can be other variations, modifications, and alternatives. In certain embodiments, the copper indium disulfide material can include one or more sulfur deficient regions characterized by a CuInS_{2-x} species, where $2 > x > 0$. In a preferred embodiment, the one or more sulfur deficient regions can be compensated by a suitable sulfide ion species. In a specific embodiment, the chalcopyrite has a thin layer of copper sulfide 907, which has been previously described, as may remain as a residue or fixed material when the bulk material is copper

rich. In a specific embodiment, a sodium sulfide material may be used to provide for both the compensating sodium species and the compensating sulfide species. Of course, there can be other variations, modifications, and alternatives.

Referring to FIG. 10, the method selectively removes the thin layer of copper sulfide. In a specific embodiment, the thin layer is removed **909** using a solution of potassium cyanide (KCN) or other suitable technique, e.g., dry etching, plasma etching, sputtering. In a specific embodiment, the method may cause formation of a copper poor surface region **1001**. In a specific embodiment, the copper poor surface is characterized by a copper to indium atomic ratio of less than about 0.95:1 or 0.99:1. In a specific embodiment, the copper poor surface region is characterized as an n-type material, which forms a parasitic junction with the p-type copper indium disulfide material, which can be rich in copper. The parasitic junction leads to poor or inefficient device performance. In a specific embodiment, the method can cause formation of a sulfur deficient surface region characterized by a CuInS_{2-x} species, where $2 > x > 0$ and an undesirable conversion efficiency. Of course, there can be other variations, modifications, and alternatives.

In a preferred embodiment, the present method subjects the copper poor surface to an ionic species to convert the copper poor surface from an n-type characteristic to a p-type characteristic **1101**, which behaves like a normal copper indium disulfide surface now, as shown in FIG. 11. In a preferred embodiment, the method subjects at least one or more portions of the bulk copper indium disulfide material to one or more of the ionic species to convert the copper poor region from an n-type characteristic to a p-type characteristic. In a specific embodiment the method subjects at least one or more portions of the bulk copper indium disulfide material to one or more second ionic species to convert the sulfur deficient species to have a desired conversion efficiency characteristics. In a specific embodiment the ionic species can be derived from a sodium ion and the second ionic species can be provided by a sulfide ion. In a preferred embodiment, the sodium ion and the sulfide ion can be derived from a sodium sulfide material. In a specific embodiment, the sulfide ion may also be derived from other sulfides, for example ammonium sulfide in a solution or others. In a specific embodiment, the subjecting the copper poor surface, the subjecting the sulfur deficient surface, and/or bulk material includes a thermal treatment process during a time period associated with the subjecting of at least the copper poor surface with the ionic species and the second ionic species. In a specific embodiment, the thermal treatment process can range in temperature from about 100 Degrees Celsius to about 500 Degrees Celsius, but can be others. Additionally, the thermal treatment process occurs for a time period ranging from a few minutes to about ten minutes to an hour or so. Of course, there can be other variations, modifications, and alternatives.

In a specific embodiment, the ionic species and the second ionic species can be applied using one or more techniques. These techniques include deposition, sputtering, spin coating, spraying, spray pyrolysis, dipping, electro deposition, painting, ink jet coating, sprinkling, any combination of these, and others. In some embodiments, the sodium can be diffused from an overlying material, which can be an electrode layer or molybdenum or other suitable material. Alternatively, sodium can be diffused from a piece of sodium material or the like via a vapor phase. In a specific embodiment, the ionic species such as sodium can be diffused in vapor phase as in the "Siemens" process, but can be others, for short periods of time. In a specific embodiment, the treatment process passivates the surface at the heterojunction or the like,

which facilitates carrier separation and transport. Additionally, the present treatment process can also generate desired conduction band offset, commonly called CBO. Of course, there can be other variations, modifications, and alternatives.

In a specific embodiment, the method includes forming a window layer overlying the copper indium disulfide material. The method also forms an electrode layer overlying the window layer. Depending upon the embodiment, the photovoltaic cell can be coupled to a glass or transparent plate or other suitable member. Alternatively, the photovoltaic cell can be coupled to another cell, e.g., bottom cell, to form a tandem or multi junction cell. Again, there can be other variations, modifications, and alternatives.

FIG. 12 is a simplified diagram of an copper indium disulfide material having one or more copper poor regions and one or more sulfur deficient regions according to an embodiment of the present invention. This diagram is merely an example, which should not unduly limit the scope of the claims herein. One of ordinary skill in the art would recognize other variations, modifications, and alternatives. As shown, the diagram provides a thin film photovoltaic device **1200**. The device has a substrate (e.g., transparent) **1201** comprising a surface region. Depending upon the embodiment, the substrate can be made of any of the materials described herein as well as outside of the present specification. In a specific embodiment, the device has a first electrode layer **1203** overlying the surface region and a chalcopyrite material **1205**, which is an absorber, overlying the surface region. The device also has a copper poor copper indium disulfide bulk region and a surface region. In a specific embodiment, the copper poor copper indium disulfide bulk region having an atomic ratio of Cu:In of about 0.99 and less. In a specific embodiment, the device has compensating sodium species **1204** provided within one or more portions of the copper poor copper indium disulfide region to change the copper poor copper indium disulfide region from an n-type characteristic to a p-type characteristic. In a specific embodiment, the device has a sulfur deficient copper indium disulfide bulk region, characterized by a CuInS_{2-x} species, where $0 < x < 2$. In a specific embodiment, the sulfur deficient copper indium disulfide bulk region is compensated by a sulfide species **1211** to provide for a desirable conversion efficiency characteristic. In a specific embodiment, the compensating sodium species and the compensating sulfur species can be derived from a sodium sulfide material. In other embodiments, the compensating sulfur species can be derived other sulfides such as ammonium sulfide, and others. Also shown is a window layer **1207** overlying the copper indium disulfide region and a second electrode layer **1209** overlying at least a portion of the window layer. Of course, there can be other variations, modifications, and alternatives. Additionally, any of the elements described herein can be made of any of the materials or combination of materials described within the present specification and outside of the specification as well.

FIG. 13 is an open circuit voltage plot of experimental results according to one or more embodiments of the present invention. These diagrams are merely examples, which should not unduly limit the scope of the claims herein. One of ordinary skill in the art would recognize other variations, modifications, and alternatives. Also, these are experimental results and should not unduly limit the scope of the claims herein. The experimental results demonstrate the operation of the present method and resulting devices, which achieved improved results.

In this experiment, a transparent substrate including a surface region was used. The transparent substrate was water white glass or soda lime glass. A first electrode layer made of

13

AZO, which is aluminum doped zinc oxide, is formed overlying the surface region. Next, a copper containing layer is formed using a sputtering process overlying the first electrode layer and an indium layer is formed, also using a sputtering process, overlying the copper layer to form a multi-layered structure. The method subjects at least the multi-layered structure to a thermal treatment process in an environment containing a sulfur bearing species and forming a bulk copper indium disulfide material from at least the treatment process of the multi-layered structure. In a specific embodiment, the bulk copper indium disulfide material comprises one or more portions of copper indium disulfide material characterized by a copper-to-indium atomic ratio of less than about 0.95:1. The bulk copper indium disulfide material has a surface region characterized by a copper poor surface comprising a copper to indium atomic ratio of less than about 0.95:1. The bulk copper indium disulfide material comprises one or more sulfur deficient region characterized by a CuInS_{2-x} species, where $0 < x < 2$. In other experiments, the copper containing layer can include gallium species, formed by co-sputtering with copper or other techniques to form a copper indium gallium disulfide film.

In the experiment, the method subjects the copper poor surface and one or more portions of the bulk copper indium disulfide material to a sodium species derived from a sodium sulfide species to convert the copper poor surface from an n-type characteristic to a p-type characteristic and to convert any of the one or more portions of the bulk copper indium disulfide material having the copper-to-indium atomic ratio of less than about 0.95:1 from an n-type characteristic to a p-type characteristic.

The method further includes subjecting the one or more sulfur deficient regions to a sulfide species to provide for a desirable conversion efficiency characteristic. The sulfide species is derived from $(\text{NH}_4)_2\text{S}$ species in a preferred embodiment. The $(\text{NH}_4)_2\text{S}$ species was dissolved in water to form an aqueous solution, which was about 25% by weight $(\text{NH}_4)_2\text{S}$, but can be others. The aqueous solution is heated to a temperature of about 75 Degrees Celsius, but can be others. The bulk absorber material is subjected to the heated aqueous solution. I believe that the sulfur species compensates and/or passivates the bulk absorber material. In a specific embodiment, a window layer of cadmium sulfide was formed overlying the copper indium disulfide material or the copper indium gallium disulfide material. Details of the experimental results are provided below.

As shown, FIG. 13 illustrates open circuit voltage (V_{oc}) plotted against three runs (1) no bulk treatment using sulfur species; (2) 15 minutes @ 25% by weight sulfur species; and (3) sixty minutes @ 25% by weight sulfur species according to one or more embodiments of the present invention. Each of the runs includes a photovoltaic device used according to the present invention. In the example, however, the experiment used $(\text{NH}_4)_2\text{S}$ species as a source of a sulfur entity that treated the bulk absorber material, and may also treat the surface region of the absorber material. As can be clearly seen, open circuit voltage increased from an average of about 5.7 volts for no sulfur species treatment to about 6.5 volts for sulfur species treatment. The increase in open circuit voltage clearly demonstrates improved device performance according to the present method and structures. Of course, there can be other variations, modifications, and alternatives.

Although the above has been illustrated according to specific embodiments, there can be other modifications, alternatives, and variations. Additionally, although the above has been described in terms of copper indium disulfide, other like materials such as copper indium gallium disulfide, copper

14

indium aluminum disulfide, combinations thereof, and others can be used. Other materials may include CuGaS_2 , CuInSe_2 , Cu(InGa)Se_2 , Cu(InAl)Se_2 , Cu(In,Ga)SSe , combinations of these, and the like. Additionally, as used herein, the term copper indium disulfide is to be interpreted broadly and may include other elements and is not specifically limited to the recited species according to one or more embodiments. Likewise, the other materials and/or compounds are also not limited, but should be interpreted by ordinary meaning according to one or more embodiments. It is understood that the examples and embodiments described herein are for illustrative purposes only and that various modifications or changes in light thereof will be suggested to persons skilled in the art and are to be included within the spirit and purview of this application and scope of the appended claims.

What is claimed is:

1. A method for forming a thin film photovoltaic device, the method comprising:

providing a transparent substrate comprising a surface region;

forming a first electrode layer overlying the surface region;

forming a copper layer overlying the first electrode layer;

forming an indium layer overlying the copper layer to form a multi-layered structure;

subjecting at least the multi-layered structure to a thermal treatment process in an environment containing a sulfur bearing species;

forming a bulk copper indium disulfide material from at least the treatment process of the multi-layered structure, the bulk copper indium disulfide material comprising one or more portions of copper poor copper indium disulfide material characterized by a copper-to-indium atomic ratio of less than about 0.95:1 and the bulk copper indium disulfide material having a surface region characterized by a copper poor surface comprising a copper to indium atomic ratio of less than about 0.95:1, the bulk copper indium disulfide material comprising one or more portions of a sulfur deficient copper indium disulfide material characterized by at least a CuInS_{2-x} species, where $0 < x < 2$, and the bulk copper indium disulfide material having a sulfur deficient surface region characterized by the CuInS_{2-x} species, where $0 < x < 2$, from at least the heat treatment process;

subjecting the copper poor surface, one or more portions of the copper poor copper indium disulfide material to a sodium species derived from a sodium sulfide material to convert the copper poor surface from an n-type characteristic to a p-type characteristic, to convert any of the one or more portions of the copper poor copper indium disulfide material having the copper-to-indium atomic ratio of less than about 0.95:1 from an n-type characteristic to a p-type characteristic;

subjecting the one or more portions of the sulfur deficient copper indium disulfide material and the sulfur deficient surface region to a sulfur species derived from the sodium sulfide material to improve a conversion efficiency characteristic; and

forming a window layer overlying the copper indium disulfide material;

whereupon the subjecting of the copper poor surface, the sulfur deficient surface, the one or more portions of the copper poor copper indium disulfide material, and the sulfur deficient copper indium disulfide material is performed during at least a thermal treatment process for a time period.

15

2. The method of claim 1 wherein the sulfur deficient copper indium disulfide material and the sulfur deficient surface are characterized by a low conversion efficiency.

3. The method of claim 1 wherein the subjecting to the sodium species derived from the sodium sulfide material is provided by at least one process selected from spin coating, spraying, spray pyrolysis, pyrolysis, dipping, deposition, sputtering, or electrolysis.

4. The method of claim 1 wherein the sodium species comprises sodium ions.

5. The method of claim 1 wherein the sulfur species comprises sulfide ions (S_{2-}).

6. The method of claim 1 wherein the sulfur deficient copper indium disulfide material has a interstitial sulfur deficient region.

7. The method of claim 1 wherein the bulk copper indium disulfide comprising a thickness of copper sulfide material, the thickness of copper sulfide material being selectively removed using a solution of potassium cyanide.

8. The method of claim 1 wherein the window layer is selected from a group consisting of a cadmium sulfide, a zinc sulfide, zinc selenium, zinc oxide, or zinc magnesium oxide.

9. The method of claim 1 wherein the thermal treatment process of the copper poor surface and the sulfur deficient surface comprises a temperature ranging from about 100 Degrees Celsius to about 500 Degrees Celsius.

10. The method of claim 1 wherein the forming of the copper layer is provided by a sputtering process or plating process.

11. The method of claim 1 wherein the sodium species derived from the sodium sulfide material compensates for any missing copper in the copper poor surface.

12. The method of claim 1 wherein the sulfide compensated surface and the sulfur.

13. The method of claim 1 wherein the fanning of the indium layer is provided by a sputtering process.

14. The method of claim 1 wherein the forming of the indium layer is provided by a plating, process.

15. The method of claim 1 wherein the bulk copper indium disulfide comprises p-type semiconductor characteristic.

16. The method of claim 1 wherein the window layer comprises an n^+ -type semiconductor characteristic.

17. The method of claim 1 further comprising introducing an indium species in the window layer to cause formation of an n^+ -type semiconductor characteristic.

18. The method of claim 1 wherein the bulk copper indium disulfide is mixed with a copper indium aluminum disulfide or copper indium gallium disulfide.

19. The method of claim 1 wherein the sulfur bearing species comprise hydrogen sulfide in fluid phase.

16

20. A method for forming a thin film photovoltaic device, the method comprising:

providing a transparent substrate comprising a surface region;

forming a first electrode layer overlying the surface region;

forming a chalcopyrite material overlying the electrode layer, the chalcopyrite material comprises a copper poor copper indium disulfide region and a sulfur deficient copper indium disulfide region, the copper poor copper indium disulfide region having an atomic ratio of Cu:In of about 0.99 and less, the sulfur deficient copper indium disulfide region comprising a $CuInS_{2-x}$ species, where $2 > x > 0$;

compensating the copper poor copper indium disulfide region using a sodium species to change in characteristic from an n-type to a p-type

compensating the sulfur deficient copper indium disulfide region using a sulfide species to improve a characteristic of conversion efficiency;

forming a window layer overlying the chalcopyrite material; and

forming a second electrode layer overlying the window layer.

21. A method for forming a thin film photovoltaic device, the method comprising:

providing a transparent substrate comprising a surface region;

forming a first electrode layer overlying the surface region;

forming a copper containing layer overlying the first electrode layer;

forming an indium containing layer overlying the copper containing layer to form a multi-layered structure;

subjecting at least the multi-layered structure to a thermal treatment process in an environment containing a sulfur bearing species;

forming a bulk copper indium disulfide containing material from at least the thermal treatment process of the multi-layered structure, the bulk copper indium disulfide containing material comprising one or more portions of a sulfur deficient copper indium disulfide containing material characterized by at least a $CuInS_{2-x}$ species, where $0 < x < 2$;

subjecting the one or more portions of the sulfur deficient copper indium disulfide containing material to a sulfur species derived from a sulfur bearing material to improve a device characteristic from a first value to a second value; and

forming a window layer overlying the copper indium disulfide material.

* * * * *