

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
25 August 2005 (25.08.2005)

PCT

(10) International Publication Number
WO 2005/078026 A1

(51) International Patent Classification⁷: **C09D 5/10**,
201/10, C23F 11/10, B05D 1/02, 1/18

(21) International Application Number:
PCT/IB2005/000488

(22) International Filing Date: 10 February 2005 (10.02.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0401349 11 February 2004 (11.02.2004) FR

(71) Applicant (for all designated States except US): **DACRAL**
[FR/FR]; 120, rue Galilée, Zaet de Creil St Maximin,
F-60100 Creil (FR).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **ESPINOSA, Antonio,**
Francisco, Iandoli [BR/BR]; Rua Duarte Monis Barreto
61, Jardim dos Estados, CEP-04641-050 Sao Paulo, SP
(BR).

(74) Agents: **MARTIN, Jean-Jacques** et al.; Cabinet Regim-
beau, 20, rue de Chazelles, F-75847 Paris Cedex 17 (FR).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO,
SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN,
GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:

— of inventorship (Rule 4.17(iv)) for US only

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: ANTICORROSION COATING COMPOSITION IN AQUEOUS DISPERSION COMPRISING AN ORGANIC TI-
TANATE AND/OR ZIRCONATE

(57) Abstract: The present invention relates to an anticorrosion coating composition for metallic parts based on particulate metal in aqueous dispersion comprising an organic titanate or zirconate compatible in aqueous phase or in organic phase, optionally a silane-based binder, and water. The present invention likewise relates to an anticorrosion coating of metallic parts obtained from the coating composition according to the invention as well as a metallic substrate provided with this anticorrosion coating. The invention additionally relates to an aqueous composition of C₁-C₈ tetraalkyl titanate, intended for the preparation of a coating composition of a metallic substrate in aqueous dispersion, as well as the process for preparation of such a composition.



WO 2005/078026 A1

- 1 -

**Anticorrosion coating composition in aqueous dispersion
comprising an organic titanate and/or zirconate**

The present invention relates to an anticorrosion coating
5 composition for metal parts, which is based on particulate
metal in aqueous dispersion comprising an organic titanate
or zirconate compatible in aqueous phase or in organic
phase, optionally a silane-based binder, and water.

10 In the sense of the present invention, the expressions
"titanate(s) compatible in organic phase" and "zirconate(s)
compatible in organic phase" are understood as meaning
every organic titanate and zirconate not compatible with
water, that is to say not soluble in an aqueous composition
15 and which in addition is sensitive to moisture and to water
(hydrolysis reaction).


In the sense of the present invention, the expressions
"titanate(s) compatible in aqueous phase" and "zirconate(s)
compatible in aqueous phase" are understood as meaning
20 every organic titanate and zirconate compatible with water,
that is to say soluble or emulsifiable or dispersible in an
aqueous composition. These are generally organic titanates
and organic zirconates which have been stabilized by
chelation. They are likewise named "chelated (organic)
25 titanate(s)" and "chelated (organic) zirconate(s)".

The organic titanates, as well as the organic zirconates,
compatible in organic phase can be used in anhydrous
compositions as catalysts, reticulating agents, surface-
treatment agents, adhesion promoters or anticorrosion
30 agents. However, these organic titanates, as well as the
organic zirconates, have the disadvantage of being very
sensitive to water and to moisture inasmuch as they are
hydrolysed very rapidly. For example, in the case of the


- 2 -

hydrolysis of tetra-n-butyl titanate, the following reactions occur:

1) conversion of the organic titanate to hydrated titanium oxide $\text{Ti}(\text{OH})_4$:



2) then, formation of titanium dioxide TiO_2 :



10 In order to avoid the formation of titanium dioxide, the titanates and zirconates compatible in organic phase must thus be employed under rigorously anhydrous conditions. Consequently, the preparation of anhydrous compositions comprising a titanate or a zirconate compatible in organic phase is accompanied by very constraining handling
15 precautions if it is wished to avoid the hydrolysis of the organic titanate to titanium dioxide on contact with air, moisture or traces of water.

The moisture resistance of titanates or zirconates compatible in organic phase can be improved by substituting
20 two alkoxy groups by chelating agents. These chelating agents contain functional groups containing oxygen or nitrogen atoms which happen to stabilize the organic titanate or zirconate. These organic titanates or zirconates in chelated form can likewise be soluble in
25 water, preferably in the presence of a weak acid of the acetic acid type. For example, the patent US 4 495 156 describes titanates in aqueous chelated form (TYZOR AA which is a titanate compatible in organic phase, TYZOR LA and TYZOR TE which are titanates compatible in aqueous
30 phase) which allow the adhesion to a substrate of a composition comprising them to be improved.

The hydrolysis rate of the organic titanates and zirconates depends on the size and the complexity of the alkyl group

- 3 -

(the more the size of the alkyl group increases, the more the hydrolysis rate decreases). This is the reason why the organic titanates and zirconates in chelated form are less sensitive to hydrolysis than the tetraalkyl titanates or the tetra-alkyl zirconates.

The patent US 4 224 213 describes coating compositions comprising a short-chain alkyl silicate of formula $\text{Si}(\text{OR})_4$, a short-chain alkyl titanate or zirconate and zinc powder. This coating composition is reticulated by reaction of the silicate and the titanate with moisture from the air. The examples of this patent teach that the addition of silicate allows the moisture resistance of organic titanates to be improved. This coating composition is an organic composition which does not contain any water. The silicate, contrary to the silane, does not allow the adhesion of a composition comprising it to a substrate.

The patent EP 0 808 883 describes an aqueous coating composition based on particulate metal, free from chromium, intended to be applied to a substrate. This composition, once applied to the substrate, undergoes hardening in heat in order to provide the said substrate with protection against corrosion. In order to increase the corrosion resistance of this coated substrate, the coated substrate can optionally be coated with a supplementary layer comprising, for example, a silica material.

Surprisingly, the inventors have succeeded in incorporating into an aqueous composition organic titanates and/or organic zirconates, whether they are in chelated or non-chelated form and compatible or not compatible in aqueous phase. They have likewise discovered that the application to a metallic substrate of an aqueous coating composition

- 4 -

based on particulate metal comprising organic titanates and/or organic zirconates allows the resistance to corrosion of the substrate to be improved. The anticorrosion results being sufficient, a substrate coated
5 by such a composition does not need any supplementary layer of anticorrosion coating. In addition, a coating is obtained whose flexibility and resistance to shocks is of very good quality, which is particularly advantageous in the case of anticorrosion coating of screws.

10

The present invention relates to an anticorrosion coating composition of metal parts based on particulate metal in aqueous dispersion comprising, in the following proportions (percentages by mass):

- 15 - an organic titanate and/or zirconate : 0.3 to 24%;
- a particulate metal or a mixture of particulate metals :
10 to 40%;
- a silane-based binder : 1 to 25%;
- water : q.s.p. 100%;

20 with the condition that the sum of the organic titanate and/or the organic zirconate and of the silane-based binder is between 5 and 25%.

The composition advantageously comprises 0.5 to 19% by weight, with respect to the total weight of the
25 composition, of organic titanate and/or zirconate and 1 to 20% by weight, with respect to the total weight of the composition, of silane-based binder, on condition that the sum of organic titanate and/or zirconate and silane-based binder is between 7 and 20% by weight, with respect to the
30 total weight of the composition.


The organic titanates can be chosen from the group constituted by the organic titanates compatible in organic phase and the organic titanates compatible in aqueous

- 5 -

phase.

The titanates compatible in organic phase are advantageously C_1 - C_8 tetraalkyl titanates which can be represented by the following formula (I'):

5




in which R1, R2, R3 and R4 independently represent an optionally substituted C_1 - C_8 alkyl radical. The C_1 - C_8 tetraalkyl titanate is advantageously chosen from the group comprising tetraethyl titanate (TET, $Ti(OC_2H_5)_4$), tetra-n-butyl titanate (T_nBT , $Ti(OC_4H_9)_4$) and octylene glycol titanate (OGT, $Ti(O_2C_8H_{17})_4$).

The organic titanates compatible in organic phase can likewise be organic titanates in chelated form not compatible with water. As examples of organic titanates in chelated form not compatible with water (compatible in organic phase), it is especially possible to cite those marketed by Dupont de Nemours under the name TYZOR® AA (titanium acetylacetonate) or TYZOR® DC (diisopropoxy bisethylacetoacetato titanate).

20

The titanates compatible in aqueous phase are advantageously chelated titanates, which can be represented by the following general formula (II'):



25


- 6 -

in which R and R' independently of one another represent an optionally substituted C₁-C₈ alkyl radical, X and X' independently represent a functional group comprising an oxygen or nitrogen atom, and Y and Y' independently
 5 represent a hydrocarbon chain having 1 to 4 carbon atoms. X and X' advantageously represent an amino or lactate radical.

The organic titanate in chelated form compatible in aqueous
 10 phase is advantageously chosen from the group constituted by the triethanolamine titanates (TYZOR® TE and TEP marketed by Dupont de Nemours). As an example of organic titanates in chelated form compatible in aqueous phase, it is likewise possible to cite those marketed by Dupont de
 15 Nemours under the name TYZOR® TA (alkanolamine titanate in chelated form) and TYZOR® LA (chelate of titanate and lactic acid).

The organic zirconate can be chosen from the group constituted by the zirconates compatible in organic phase
 20 and the zirconates compatible in aqueous phase.

The organic zirconates compatible in organic phase are advantageously C₁-C₁₀ tetraalkyl zirconates, which can be represented by the following formula (I):



25


in which R1, R2, R3 and R4 independently represent an optionally substituted C₁-C₁₀ alkyl radical. The C₁-C₁₀ tetraalkyl zirconate is advantageously chosen from the group constituted by tetra-n-propyl zirconate and tetra-n-

- 7 -

butyl zirconate.

The organic zirconates compatible in organic phase can likewise be organic zirconates in chelated form not compatible with water. As an example of an organic
 5 zirconate in chelated form not compatible with water (compatible in organic phase), it is especially possible to cite those marketed by Dupont de Nemours under the name TYZOR® ZEC (chelated diethyl citrate zirconate).

The organic zirconates compatible in aqueous phase are
 10 advantageously chelated zirconates which can be represented by the following general formula (II):



in which R and R' independently of one another represent an
 15 optionally substituted C₁-C₁₀ alkyl radical, X and X' independently represent a functional group comprising an oxygen or nitrogen atom, and Y and Y' independently represent a hydrocarbon chain having 1 to 4 carbon atoms. X and X' advantageously represent an amino radical.

20 The chelated organic zirconate can advantageously be triethanolamine zirconate (TYZOR® TEAZ marketed by Dupont de Nemours). As an example of an organic zirconate in chelated form compatible in aqueous phase, it is likewise possible to cite that marketed by Dupont de Nemours under
 25 the name TYZOR® LAZ (chelate of zirconate and lactic acid).

The particulate metal of the coating composition can be chosen from the group constituted by the metallic pigments such as aluminium, manganese, nickel, titanium, stainless

- 8 -

steel, zinc, their alloys, as well as their mixtures. The particulate metal is advantageously chosen from zinc and aluminium, as well as their alloys and their mixtures or their alloys with manganese, magnesium, tin or Gallium. The

5 particulate metal present in the composition is advantageously in powder form, different homogeneous or heterogeneous geometric structures, especially spherical, lamellar, lenticular forms or other specific forms. The particulate metal advantageously has a particle size of

10 less than 100 μm , even more advantageously less than 40 μm . When the particulate metal is an alloy or a mixture of zinc and aluminium, the aluminium can optionally be present in very small quantities, for example 1 to 5% by weight of the particulate metal, while at the same time nevertheless

15 providing a coating of shiny appearance. Customarily, the aluminium represents at least 10% by weight of the particulate metal, thus the weight ratio of the aluminium to the zinc is of the order of 1:9. On the other hand, for reasons of economy, the aluminium does not represent more

20 than approximately 50% by weight of the total zinc and aluminium, so that the weight ratio of the aluminium to the zinc can reach 1:1. The content of particulate metal of the coating composition will not exceed approximately 40% by weight of the total weight of the composition in order to

25 maintain the best coating appearance and will customarily represent at least 10% by weight in order to obtain a shiny coating appearance.

The metal can contain in minor quantity one or more solvents, for example dipropylene glycol and/or white

30 spirit, especially when the metal has been prepared in lamellar form. The particulate metals containing solvents are customarily used in the form of pastes, which can be used directly with other ingredients of the composition.

- 9 -

However, the particulate metals can likewise be used in a dry form in the coating composition.

The said silane-based binder advantageously comprises a silane carrying at least one hydrolysable function in hydroxyl function chosen from a C₁-C₄, preferably C₁-C₂, alkoxy radical. The silane advantageously carries three hydrolysable functions in hydroxyl function, preferably identical. The silane can additionally carry an epoxy (oxirane) function, which favours the reticulation and adhesion to the substrate. "Hydrolysable function in hydroxyl function" is understood as meaning any chemical function capable of reacting with water in order to be converted into a hydroxyl function -OH.

The silanes, in the compositions of the present invention, serve as binding agents. They likewise allow the coating bath to be stabilized against a harmful autogenous reaction. The silane seems to bind and passivate the particulate metal, so that the stability of the bath of the coating composition is improved. In addition, it allows the adhesion of the coating and its resistance to corrosion to be improved. The silane advantageously represents 3 to 20% by weight of the total weight of the composition.

The silane is advantageously easily dispersed in the aqueous medium and is, preferably, soluble in such a medium. The silane used is advantageously a silane with an epoxy function chosen from di- or trimethoxysilane with an epoxy function and di- or triethoxysilane with an epoxy function, as well as their mixtures, in particular like beta-(3,4-epoxycyclohexyl)ethyl-trimethoxysilane, 4-(trimethoxysilyl)butane-1,2-epoxide or gamma-glycidoxypropyltrimethoxysilane.

If the organic titanate and/or zirconate used is an organic

- 10 -

titanate and/or zirconate compatible in aqueous phase, the silane is advantageously introduced in quantities such that the proportions by mass, in the final composition, of organic titanate and/or zirconate compatible in aqueous
5 phase:silane are between 95:5 and 5:95.

The anticorrosion composition can be prepared by mixing an organic phase, especially comprising the silane and the particulate metal, with an aqueous phase, especially comprising water and the silane. The organic titanate
10 and/or zirconate compatible in aqueous phase can be introduced either into the aqueous phase or into the organic phase.

When the organic titanate and/or zirconate compatible in aqueous phase is introduced into the organic phase, it is
15 possible to substitute the silane, normally present in the organic phase, by this organic titanate and/or zirconate. The proportions by mass, expressed in dry parts, of organic titanate and/or zirconate and of silane are advantageously between 1:19 and 2:1, more advantageously between 1:16 and
20 1:8.

When the organic titanate and/or zirconate compatible in aqueous phase is introduced into the aqueous phase, it is advantageously first co-hydrolysed with the silane, normally present in the aqueous phase. The mass proportions
25 of organic titanate and/or zirconate and of silane during the co-hydrolysis are advantageously between 0.12 and 0.36, expressed in dry parts. The optimal conditions for the co-hydrolysis are obtained for a ratio by mass of 0.24 titanate and/or zirconate for 1 silane, the ratios being
30 expressed in dry parts.

In order to co-hydrolyse the organic titanate and/or zirconate and the silane, the organic titanate and/or zirconate is introduced into the silane, in an appropriate

- 11 -

ratio, then they are co-hydrolysed by addition of 200 to 500% of water. It would appear that the duration of the co-hydrolysis reaction, that is to say the waiting time which follows the addition of the water, for example 30 or 90 min, does not have any influence on the properties of the co-hydrolysate obtained. If, instead of co-hydrolysing the silane and the organic titanate and/or zirconate compatible in aqueous phase, they are each hydrolysed separately, less satisfactory results are obtained in terms of product stability.

The addition of organic titanate and/or zirconate compatible in aqueous phase in the aqueous phase of the anticorrosion composition improves the anticorrosion properties of this composition more than if this titanate and/or zirconate had been added in the organic phase.

If the organic titanate and/or zirconate used is a titanate and/or zirconate compatible in organic phase, advantageously a C_1 - C_8 tetraalkyl titanate and/or zirconate, the silane is advantageously introduced in quantities such that the proportions by mass, in the final composition, of titanate and/or zirconate compatible in organic phase/silane are between 60/40 and 5/95, advantageously between 50/50 and 10/90.

The liquid medium of the coating composition is virtually always water or a combination of water and organic solvent. Other solvents can optionally be used but, preferably, only in very small quantities. Typically, the composition comprises 28 to 65% by weight of water, with respect to the total weight of the composition.

According to an advantageous embodiment of the invention, the coating composition additionally comprises 1 to 30% by weight of organic solvent or of a mixture of organic

- 12 -

solvents, with respect to the total weight of the composition. The organic solvents are advantageously chosen from the group constituted by the glycolic solvents such as the glycol ethers, in particular diethylene glycol, triethylene glycol and dipropylene glycol, the acetates, propylene glycol, polypropylene glycol, nitropropane, the alcohols, the ketones, propylene glycol methyl ether, 2,2,4-trimethyl-1,3-pentanediol isobutyrate (texanol), white spirit, as well as their mixtures.

10 Dipropylene glycol is particularly advantageous, especially for reasons of economy and of protection of the environment. The quantity of solvents is advantageously lower than 25% by weight, even more advantageously lower than 16% by weight, with respect to the total weight of the composition. When the metallic particles have been prepared
15 in lamellar form in a solvent, the particulate metal resulting can be in the form of paste. It can then form a part of the organic solvent of the composition according to the invention.

20

According to an advantageous embodiment of the invention, the coating composition additionally comprises 0.1 to 7% by weight of molybdenum oxide, with respect to the total weight of the composition. The presence of molybdenum oxide
25 MoO_3 in the anticorrosion coating composition allows control of the sacrificial protection exerted by the particulate metal in suspension in the composition to be improved. The molybdenum oxide MoO_3 is preferably used in an essentially pure orthorhombic crystalline form having a
30 content of molybdenum of greater than approximately 60% by mass. Advantageously, the molybdenum oxide MoO_3 will be used in the anticorrosion compositions in the form of particles of dimensions of between 5 and 200 μm .

- 13 -

According to an advantageous embodiment of the invention, the coating composition additionally comprises 0.5 to 10% by weight of a reinforcing agent of the anticorrosion properties of the composition chosen from the group constituted by yttrium, zirconium, lanthanum, cerium, praseodymium, in the form of oxides or of salts. The said reinforcing agent of the anticorrosion properties of the composition is advantageously yttrium oxide Y_2O_3 or cerium chloride. The said reinforcing agent of the anticorrosion properties of the composition can advantageously be combined with the abovementioned molybdenum oxide, in a mass ratio $0.25 < \text{reinforcing agent of the anticorrosion properties: } MoO_3 < 20$, advantageously $0.5 < \text{reinforcing agent of the anticorrosion properties: } MoO_3 < 16$, even more advantageously $0.5 < \text{reinforcing agent of the anticorrosion properties: } MoO_3 < 14$.

According to an advantageous embodiment, the coating composition additionally comprises a corrosion inhibitor pigment or corrosion inhibitor pigments such as the tri- or polyphosphate of aluminium, the phosphates, the molybdates, the silicates and borates of zinc, strontium, calcium, barium and their mixtures, at levels of the order of 0.2 to 4% by weight, with respect to the total weight of the coating composition.

The coating composition according to the invention can additionally comprise a thickening agent. The thickening agent is advantageously chosen from the group constituted by the cellulosic derivatives such as hydroxymethylcellulose, hydroxyethylcellulose, hydroxypropylcellulose, cellulose acetobutyrate, xanthan gum, the associative thickeners of polyurethane or acrylic type, the silicates such as the optionally treated silicates of magnesium and/or of lithium or the organophilic clays as

- 14 -

well as their mixtures. The content of thickening agent is advantageously lower than 7% by weight with respect to the total weight of the composition, advantageously between 0.005 and 7% by weight with respect to the total weight of the composition.

The coating composition according to the invention can likewise comprise a wetting agent, in a content advantageously lower than 4% by weight, more advantageously between 0.1 and 4% by weight, with respect to the total weight of the composition.

The composition according to the invention can also comprise a pH stabilizer such as boric acid, metaboric acid, tetraboric acid and boron oxide or boron salts. The composition can comprise, with respect to the total weight of the composition, 0.1 to 10% by weight, advantageously 0.2 to 5% by weight and even more advantageously 0.4 to 0.8% by weight, of pH stabilizer.

The composition can likewise comprise a pH modifier, generally chosen from the oxides and the hydroxides of alkali metals, advantageously lithium and sodium, the oxides and the hydroxides of metals belonging to groups IIA and IIB of the Periodic Table, such as the compounds of strontium, calcium, barium, magnesium and zinc. The pH modifier can likewise be a carbonate or a nitrate of the abovementioned metals.

The composition according to the invention can likewise comprise phosphates, substituents containing phosphorus, such as ferrophosphate (pigment), non-organic salts, in quantities lower than 2% by weight with respect to the weight of the composition.

The composition according to the invention is advantageously free from chromium VI. The composition can, however, contain chromium in soluble or non-soluble form

- 15 -

such as, for example, metallic chromium or chromium of oxidation state III.

The composition has good stability on storage, confirming the protective role of the silane towards a harmful
5 reaction of the particulate metal with other ingredients of the composition. The silane likewise allows organic titanate to be stabilized.

The present invention likewise relates to the coating obtained by application of the coating composition
10 according to the invention to a substrate, advantageously by spraying, soaking-draining or soaking-centrifugation, the coating layer then being subjected to a baking operation, preferably at a temperature of between 180°C and 350°C, for approximately 10 to 60 minutes, by supply of
15 thermal energy, such as by convection or infrared, or for approximately 30 seconds to 5 minutes by induction.

According to an advantageous embodiment, the anticorrosion coating will result from an application operation involving, prior to a baking operation, a drying operation
20 of the coated metallic parts, by supply of thermal energy, such as by convection, infra-red or induction, at a temperature of between 30 and 250°C, advantageously of the order of 70°C, in convection or in infrared for 10 to 30 minutes on line or for approximately 30 seconds to 5
25 minutes by induction. Before coating, it is judicious in the majority of cases to eliminate the foreign matter from the surface of the substrate, especially by cleaning and careful degreasing. Under these conditions, the thickness of the dry coating film thus applied is between 3 μm (11
30 g/m^2) and 30 μm (110 g/m^2) and preferably between 4 μm (15 g/m^2) and 12 μm (45 g/m^2), more particularly between 5 μm (18 g/m^2) and 10 μm (40 g/m^2).

The present invention also extends to the metallic

- 16 -

substrate, preferably of steel or steel coated with zinc or with a base layer of zinc deposited by different application methods including mechanical deposition, to cast iron and aluminium, provided with an anticorrosion
5 coating according to the invention applied with the aid of the abovementioned compositions.

The metallic substrate can be previously treated, for example by a treatment with chromate or with phosphate. Thus, the substrate can be pretreated in order to have, for
10 example, a phosphate coating of iron in a quantity of 0.1 to 1 g/m² or a phosphate coating of zinc in a quantity of 1.5 to 4 g/m².

The present invention likewise relates to an aqueous
15 composition of C₁-C₈ tetraalkyl titanate and/or of C₁-C₈ tetraalkyl zirconate, intended for the preparation of a coating composition for a metallic substrate in aqueous dispersion, prepared from a water-soluble organic solvent, a binder containing a silane carrying at least one
20 hydrolysable function in hydroxyl function, a C₁-C₈ tetraalkyl titanate and/or zirconate and water, in the following proportions (percentages by mass):


- water-soluble organic solvent : 0 to 20%
- silane-based binder : 20 to 50%
- 25 - C₁-C₈ tetraalkyl titanate and/or zirconate : 5 to 25%
- water : 40 to 70%

In the context of the present invention, that is to say when the silane is found in the presence of C₁-C₈ tetraalkyl titanate and/or zirconate, it would appear that
30 the silane, in hydrolysed form before condensation, is capable of reacting with the abovementioned hydrated titanium oxide and/or zirconate in order to give a partially stable polymeric chain containing silicon and


- 17 -

titanium and/or zirconate atoms. The silane then appears capable of stabilizing the C₁-C₈ tetraalkyl titanate and/or zirconate. The chemical reactions could be written as follows:


5 (1) Hydrolysis of the silane:



(2) Conversion of the organic titanate or zirconate to hydrated titanium or zirconium oxide:




10 (3) Reaction between the hydrated titanium or zirconium oxide and the hydrolysed silane:



The silane and the organic titanate or zirconate thus associate in order to form the following partial polymeric chain: X(OH)₂·2[R-SiO(OH)₂]

The reaction can continue and lead to the formation of a polymeric chain of the following formula (III):



20

formula (III)

in which X represents Ti or Zr.

The water-soluble organic solvent is advantageously chosen from the group constituted by the glycolic solvents such as the glycol ethers, in particular diethylene glycol, triethylene glycol and dipropylene glycol, the acetates, 25 propylene glycol, the alcohols, the ketones, propylene glycol ether, as well as their mixtures.

The silane carrying at least one hydrolysable function in 30 hydroxyl function contained in the binder is advantageously

- 18 -

chosen from a C₁-C₄, even more advantageously C₁-C₂, alkoxy radical. In addition, this silane advantageously carries an epoxy function. The said silane is preferably chosen from di- or trimethoxysilane with an epoxy function and di- or triethoxysilane with an epoxy function, as well as their mixtures, in particular gamma-glycidoxypropyl-trimethoxysilane or beta-(3,4-epoxycyclohexyl)ethyl-trimethoxysilane.

The C₁-C₈ tetraalkyl titanate is advantageously chosen from the group comprising tetra-ethyl titanate (TET), tetra-n-butyl titanate (T_nBT) and octyleneglycol titanate (OGT) and the C₁-C₈ tetraalkyl zirconate is chosen from the group comprising tetra-n-propyl zirconate and tetra-n-butyl zirconate. In the aqueous composition, the ratio by mass of C₁-C₈ tetraalkyl titanate and/or zirconate with respect to the silane is from 60/40 maximum, advantageously to 50/50 maximum, advantageously to 40/60 maximum.

The aqueous composition of C₁-C₈ tetraalkyl titanate and/or C₁-C₈ tetraalkyl zirconate can be prepared by mixing the silane-based binder, the said titanate or zirconate and, if necessary, the said water-soluble organic solvent, with a small quantity of water and then, by continuous progressive addition, at a low rate, of the remaining quantity of water.

In this stabilized form, the C₁-C₈ tetraalkyl titanate and/or zirconate can, for example, then be introduced into a coating composition for a metallic substrate in aqueous phase, especially an anticorrosion coating composition based on particulate metal in aqueous dispersion, while limiting the formation of titanium dioxide.

The present invention finally relates to the use of the aqueous composition of C₁-C₈ tetraalkyl titanate and/or C₁-

- 19 -

C₈ tetraalkyl zirconate defined above in pretreatment for coatings or adhesives (polyurethane, acrylic, rubber...). This composition can also be used in posttreatment as a sealer based on metallic particles. This composition can
5 likewise be used in passivation treatment for substrates based on steel, zinc, aluminium or steel covered with a zinc-based coating. This composition can finally be used in an additive in order to improve the adhesion of the coatings or adhesives (polyurethane, acrylic, rubber, ...)
10 in aqueous phase.

The examples below show ways in which the present invention can be employed, but do not limit the present invention in any fashion.

15

Preparation of the test panels:

Unless indicated otherwise, the test panels are typically stainless steel panels with a low carbon content, laminated in the cold. They can be prepared first of all by immersion
20 in a cleaning solution. Then, the panels can be wiped with a cleaning pad and then rinsed with water and again immersed in the cleaning solution. After removal of the solution, the panels are rinsed with tap water and dried.

25 Application of the coating to the test panels and weight of the coating:

The clean parts are coated, in a typical fashion, by dipping then into the coating composition, by withdrawing and draining the composition in excess of this, several
30 times with a moderate stirring action, and then by immediate baking or drying at ambient temperature or pre-hardening at a moderate temperature until the coating is dry to the touch and thus baked. The coating weights

- 20 -

(mg/cm²) are determined by comparative weighing before and after coating.

Test of resistance to corrosion (ISO 9227) and estimation:

The resistance to corrosion of coated parts is measured by means of the standard salt projection test (saline mist) for paints and varnishes ISO 9227. In this test, the parts are placed in a chamber maintained at a constant temperature where they are exposed to a fine projection (mist) of a 5% saline solution during specific periods of time, rinsed with water and dried. The extent of corrosion of the parts tested can be expressed in the form of the percentage of red rust.

Example 1: composition based on organic titanate compatible in organic phase

Constituent	Quantity (g/kg)
DPG (dipropylene glycol)	170.60
R40 ⁵	13.00
R95 ⁶	14.00
Dry aluminium ²	25.00
Zinc paste ¹	245.00
Silane A-187 ³	90.00
Dehydran ¹⁰	5.00
Sodium silicate ⁴	8.00
Boric acid	7.50
Molybdenum oxide ⁹	8.00
T _n BT (tetra-n-butyl titanate) ⁸	40.00
Kelzan ⁷	0.65
Water	373.30

Table 1

¹ Zinc in the form of paste to approximately 92% in white spirit

² Alu Chromal VIII powder marketed by Eckart Werke

³ γ-glycidoxypropyltrimethoxysilane (Crompton)

⁴ sodium silicate (Rhodia)

- 21 -

^{5,6} Ethoxylated nonylphenol of R40 or of R95, supplier Oxiteno SA (Brazil)

⁷ Kelzan/Rhodopol 23 from Rhodia

⁸ supplier DuPont de Nemours

5 ⁹ supplier Lavollée

¹⁰ supplier Cognis SA

Example 2: composition based on organic titanate compatible in organic phase

10 a) composition:

<i>Constituent</i>	<i>Quantity (g/kg)</i>
DPG (dipropylene glycol)	175.60
R40	13.00
R95	14.00
Dry aluminium	10.00
Zinc paste	260.00
Silane A-187	115.00
Silicate H300	10.00
Boric acid	9.50
Molybdenum oxide	10.00
T _n BT (tetra-n-butyl titanate)	60.00
Kelzan	0.65
Water	317.25

Table 2

b) Results of tests of resistance to saline mist

15

<i>Duration of bath (days)</i>	<i>Density coating layer (g/m²)</i>	<i>Resistance to saline mist (hours)</i>
5	23.6	2064
10	19.8	1944
15	20.1	1752

Table 3

- 22 -

Example 3: composition based on organic titanate compatible in organic phase

a) composition:

<i>Constituent</i>	<i>Quantity (g/kg)</i>
DPG (dipropylene glycol)	153.50
R40	13.00
R95	14.00
Dry aluminium	10.00
Zinc paste	260.00
Silane A-187	95.00
Silicate H300	10.00
Boric acid	9.50
Molybdenum oxide	10.00
TET (tetraethylene titanate) ¹¹	40.00
Kelzan	0.65
Water	379.35

5

Table 4

¹¹ supplied by DuPont de Nemours

b) Results of tests of resistance to saline mist

<i>Duration of bath (days)</i>	<i>Density coating layer (g/m²)</i>	<i>Resistance to saline mist (hours)</i>
5	20.8	456
10	19.7	360

10

Table 5

Example 4: process for preparation of an aqueous composition of tetrabutyl titanate, organic titanate compatible in organic phase:

15 The following reagents are mixed in order:

- a) 30.00 g of DPG (dipropylene glycol)
- b) 50.00 g of silane A-187

- 23 -

c) 20.00 g of TBT (tetrabutyl titanate)

The solution obtained is allowed to stand for 24 hours. The silane, introduced into the DPG before the T_nBT , reacts
5 with the water optionally present in the DPG. An uncontrolled reaction of the organic titanate with the water optionally present in the DPG is thus avoided.
100.00 g of water (=100.00 ml) are added respecting the following procedure:

- 10 i) add 0.125 ml of water dropwise and then allow the solution to stand for 10 minutes;
ii) repeat step i) 5 times;
iii) add the remaining quantity of water at a rate of
0.25 ml of water/minute/3 pulses, or approximately
15 0.083 ml of water every 20 seconds.

An aqueous composition of colourless organic titanate is obtained. Small crystals can appear; it is assumed that these are silica crystals.

The total duration of the preparation of the aqueous
20 composition of organic titanate is approximately 7 h 30 min.

The aqueous composition of organic titanate is allowed to stand for at least 24 hours before optionally being introduced into a composition of anticorrosion coating.

25

Example 5: process for preparation of an aqueous composition of organic titanate compatible in organic phase:

The process proceeds in the same fashion as in example 4
30 except that the quantity of T_nBT introduced is 30.00 g. An aqueous composition of colourless or sometimes slightly yellow organic titanate is obtained.

- 24 -

Example 6: process for preparation of an aqueous composition of organic titanate compatible in organic phase:

The process proceeds in the same fashion as in example 4 except that the quantity of T_nBT introduced is 40.00 g. An aqueous composition of colourless or sometimes slightly yellow organic titanate is obtained.

Example 7: process for preparation of an aqueous composition of organic titanate compatible in organic phase:

The process proceeds in the same fashion as in example 4 except that the quantity of T_nBT introduced is 40.00 g and the quantity of silane A 187 introduced is 70.00 g. An aqueous composition of colourless or sometimes slightly yellow organic titanate is obtained.

Example 8: corrosion resistance of a coating composition according to the invention based on organic titanate compatible in organic phase

The aqueous composition of organic titanate obtained in example 6 is introduced into an anticorrosion coating composition. Table 6 below indicates the formulation of the composition thus obtained and that of an anticorrosion coating composition of the prior art which do not contains organic titanate.

- 25 -

	<i>Composition according to the invention A (g/kg)</i>	<i>Composition of the prior art B (g/kg)</i>
DPG	160.60	160.60
Silane A 187	90.00	90.00
Water	383.30	421.10
Tetra-n-butyl titanate	40.00	-
Dry aluminium lamellae	25.00	25.00
Zinc paste	245.00	245.00
Molybdenum oxide	8.00	10.00
R40	13.00	13.00
R95	14.00	14.00
Dehydran	5.00	5.00
Sodium silicate	8.00	8.00
Boric acid	7.50	7.50
Kelzan	0.60	0.80

Table 6

The characteristics of composition A are reported in table 7 below:

5

<i>Duration of the bath</i>	<i>adhesion</i>	<i>appearance</i>	<i>pH</i>	<i>density</i>	<i>% of solid</i>	<i>viscosity</i>
72 hours	excellent	very good	7.7	1.35	36.1	54s (23°C)
5 days	excellent	very good	7.9	1.36	37.0	64s (23°C)
10 days	excellent	very good	8.1	1.39	38.3	70s (26°C)
15 days	excellent	very good	7.9	1.40	40.0	83s (26°C)
20 days	excellent	very good	7.8	1.42	41.9	121s (25°C)
25 days	excellent	very good	8.1	1.39	39.4	90s (24°C)

Table 7

- 26 -

The resistance of the two compositions to the saline mist is compared. The resistance values to the saline mist measured are summarized in table 8 below.

<i>Composition according to the invention A</i>		<i>Composition of the prior art B</i>	
Density coating layer (g/m ²)	Resistance to saline mist (hours)	Density coating layer (g/m ²)	Resistance to saline mist (hours)
16	704	16	208
20	880	20	260
24	1056	24	312
28	1232	28	364
32	1408	32	416
36	1584	36	468

5

Table 8

Satisfactory results for resistance to the saline mist are thus observed for the coating composition according to the invention. In fact, for a layer density of 24 g/m², it is possible to attain a duration of resistance to the saline mist of greater than 1000 hours whereas for a composition without organic titanate the duration of resistance to the saline mist is only 312 hours. The addition of organic titanate allows the corrosion resistance of the coating to be at least tripled under these conditions.

Example 9: composition based on organic titanate compatible in organic phase

20

The addition of small quantities of organic titanate (10, 20 or 30 g/kg) allows the quantity of silane and of

- 27 -

molybdenum oxide to be introduced to be decreased, which allows a limitation of the costs, while conserving good anticorrosion results.

In the following examples of compositions (table 9), the quantity of silane is reduced to 44% by weight and the quantity of molybdenum oxide is reduced to 20% by weight, with respect to the quantities conventionally introduced into anticorrosion coating compositions.

	<i>Composition C (g/kg)</i>	<i>Composition D (g/kg)</i>	<i>Composition E (g/kg)</i>
DPG	160.60	160.60	160.60
Silane A 187	50.00	50.00	50.00
Water	453.20	443.20	433.20
Tetra-n-butyl titanate	10.00	20.00	30.00
Dry aluminium lamellae	25.00	25.00	25.00
Zinc paste	245.00	245.00	245.00
Molybdenum oxide	8.00	8.00	8.00
R40	13.00	13.00	13.00
R95	14.00	14.00	14.00
Dehydran	5.00	5.00	5.00
Sodium silicate	8.00	8.00	8.00
Boric acid	7.50	7.50	7.50
Kelzan	0.70	0.70	0.70

Table 9

The values of resistance to the saline mist measured are summarized in table 10 below.

	<i>Composition C</i>	<i>Composition D</i>	<i>Composition E</i>
Weight of layer (g/m ²)	21	22.5	20.5
Red rust (number of hours)	170	310	430

Table 10

Example 10: process of introduction of chelated organic
 5 titanates or zirconates, compatible in aqueous phase, into
 an aqueous phase - co-hydrolysis with the silane:

a) titanates

i) preparation of the aqueous phase:

10 parts by weight of TYZOR® TEP (supplied by DuPont de
 10 Nemours, 60% dry extract) and 25 parts by weight of silane
 A-187 are mixed with magnetic stirring for one hour. 113
 parts by weight of water are then added rapidly and the
 magnetic stirring is maintained for one hour.

This mixture is then introduced into an aqueous composition
 15 constituted of 350 parts by weight of water, 8.8 parts by
 weight of sodium silicate, 8.2 parts by weight of boric
 acid and 9 parts by weight of molybdenum oxide.

ii) composition of the organic phase:

The organic phase contains:

20	- dipropylene glycol	75 parts by weight
	- Remcopal N4 100 ¹²	14 parts by weight
	- Remcopal N9 1001 ¹³	15.5 parts by weight
	- Silane A 187	70 parts by weight
	- Zinc paste	235 parts by weight
25	- Aluminium Stapa ¹⁴	30 parts by weight
	- Schwego foam 8325 ¹⁵	5.5 parts by weight
	- Yttrium oxide ¹⁶	30 parts by weight
	- aerosil 380 ¹⁷	0.4 part by weight

¹² wetting agent of ethoxylated nonylphenol type (CECA)

- 29 -

- ¹³ wetting agent of ethoxylated nonylphenol type (CECA)
¹⁴ 80% Chromal VIII in dipropylene glycol, marketed by Eckart Werke
¹⁵ hydrocarbon-type antifoam (Schwegman)
¹⁶ Y₂O₃ of purity equal to 99.99%
5 ¹⁷ anti-sedimentation agent of silica type (Degussa)

iii) results of the saline mist tests:

- Bath according to the invention: anticorrosion coating composition according to the invention: the
10 organic and aqueous phases obtained (steps ii) and i), respectively) are mixed.

- Reference bath: reference composition:

The aqueous phase of the reference composition contains:

Water	463 parts by weight
15 Sodium silicate 20 N 32	8.8 parts by weight
Boric acid	8.2 parts by weight
Molybdenum oxide	9 parts by weight
Silane A 187	31 parts by weight

The organic phase of the reference composition has the same
20 composition as the organic phase of the bath according to the invention (step ii)).

The saline mist tests are carried out after an ageing of the baths, according to the invention and reference, of the order of 48 hours. The results obtained are given in table
25 11 below:

	Results on screws (5 ^d /4.8 ^e)			Results on steel support	
	Such as	V+CM ^a	2 x G ^b	Sacrificial protection ^c	2xG ^b
Reference bath	672/672	456/840	168/336	624	168
Bath according to the invention	> 1150	840/912	336/576	1150	744

Table 11

- 30 -

^a V + CM: saline mist results after the screws had been subjected to the mechanical shocks of vibrations and falls.

^b 2 x G: saline mist results after the screws or the plates had been subjected twice to chipping, that is to say a
5 spattering of impacts.

^c Sacrificial protection: number of hours of exposure to the saline mist, without red rust after incision of the coating to the metal.

^d notation 5: results corresponding to less than 1% of red
10 rust on surface.

^e notation 4.8: results corresponding to less than 5% of red rust on surface.

Table 11 makes it appear clear that the introduction of chelated organic titanate, compatible in aqueous phase, co-
15 hydrolysed with the silane in the coating compositions increases the good behaviour to saline mist of the samples treated by these compositions.

- 31 -

Claims

1. Anticorrosion coating composition of metallic parts based on particulate metal in aqueous dispersion
5 comprising, in the following proportions (percentages by mass):

- an organic titanate and/or zirconate : 0.3 to 24%;
- a particulate metal or a mixture of particulate metals :
10 to 40%;

- 10 - a silane-based binder : 1 to 25%;
- water : q.s.p. 100%;

with the condition that the sum of the organic titanate and/or zirconate and of the silane-based binder is between 5 and 25%.

15 2. Composition according to Claim 1, characterized in that the organic titanate is chosen from the group constituted by the titanates compatible in organic phase and the titanates compatible in aqueous phase and the organic zirconate is chosen from the group constituted by
20 the zirconates compatible in organic phase and the zirconates compatible in aqueous phase.

3. Composition according to Claim 2, characterized in that the titanates compatible in organic phase are C₁-C₈ tetraalkyl titanates, advantageously chosen from the group
25 comprising tetraethyl titanate, tetra-n-butyl titanate and octylene glycol titanate, and the zirconates compatible in organic phase are C₁-C₈ tetraalkyl zirconates, advantageously chosen from the group comprising tetra-n-propyl zirconate and tetra-n-butyl zirconate.

30 4. Composition according to Claim 2, characterized in that the titanates compatible in aqueous phase are chelated organic titanates, advantageously chosen from the group constituted by triethanolamine titanates, and the

- 32 -

zirconates compatible in aqueous phase are chelated organic zirconates, advantageously the triethanolamine zirconates.

5. Composition according to any one of the preceding claims, characterized in that the particulate metal is
5 chosen from zinc and aluminium, as well as their alloys and their mixtures or their alloys with manganese, magnesium, tin or Galfan.

6. Composition according to any one of the preceding claims, characterized in that the silane-based binder
10 comprises a silane carrying at least one hydrolysable function in hydroxyl function chosen from a C₁-C₄ alkoxy radical.

7. Composition according to any one of the preceding claims, characterized in that the silane additionally
15 carries an epoxy function.

8. Composition according to Claim 7, characterized in that the silane is chosen from di- or trimethoxysilane with an epoxy function or di- or triethoxysilane with an epoxy function, as well as their mixtures, in particular gamma-
20 glycidoxypropyltrimethoxysilane or beta-(3,4-epoxycyclohexyl)ethyltrimethoxysilane.

9. Composition according to any one of the preceding claims, characterized in that it additionally comprises 1 to 30% by weight of organic solvent or of a mixture of
25 organic solvents, with respect to the total weight of the composition.

10. Composition according to Claim 9, characterized in that the organic solvent is chosen from the group constituted by the glycolic solvents such as the glycol
30 ethers, in particular diethylene glycol, triethylene glycol and dipropylene glycol, the acetates, propylene glycol, polypropylene glycol, nitropropane, the alcohols, the ketones, propylene glycol methyl ether, 2,2,4-trimethyl-

- 33 -

1,3-pentanediol isobutyrate (texanol), white spirit, as well as their mixtures.

11. Composition according to any one of the preceding claims, characterized in that it additionally comprises 0.1
5 to 7% by weight of molybdenum oxide, with respect to the total weight of the composition.

12. Composition according to any one of the preceding claims, characterized in that it additionally comprises 0.5 to 10% by weight, with respect to the total weight of the
10 composition, of a reinforcing agent of the anticorrosion properties chosen from the group constituted by yttrium, zirconium, lanthanum, cerium, praseodymium, in the form of oxides or of salts, advantageously yttrium oxide Y_2O_3 , or 0.2 to 4% by weight, with respect to the total weight of
15 the composition, of a corrosion inhibitor pigment such as aluminium triphosphate.

13. Composition according to any one of the preceding claims, characterized in that it additionally comprises a thickening agent, advantageously 0.005 to 7% by weight with
20 respect to the total weight of the composition, and/or a wetting agent, advantageously 0.1 to 4% by weight with respect to the total weight of the composition.

14. Anticorrosion coating of metallic parts, characterized in that it is obtained from a coating composition according
25 to one of claims 1 to 13, by spraying, soaking-draining or soaking-centrifugation, the coating layer then being subjected to a baking operation by supply of thermal energy, such as by convection, infrared or induction, preferably carried out at a temperature of between 180°C
30 and 350°C, for approximately 10 to 60 minutes by convection or infra-red, or for 30 seconds to 5 minutes by induction.

15. Anticorrosion coating of metallic parts according to Claim 14, characterized in that, prior to a baking

- 34 -

operation, the coated metallic parts are subjected to a drying operation by supply of thermal energy, such as by convection, infrared or induction, especially at a temperature of between 30 and 250°C by convection or
5 approximately 10 to 30 minutes on line or by induction for 30 seconds to 5 minutes.

16. Anticorrosion coating of metallic parts according to one of Claims 14 or 15, characterized in that it is applied to the metallic parts to be protected, with a thickness of
10 the dry film of between 3 μm (11 g/m^2) and 30 μm (110 g/m^2) and preferably between 4 μm (15 g/m^2) and 12 μm (45 g/m^2), more particularly between 5 μm (18 g/m^2) and 10 μm (40 g/m^2).

17. Metallic substrate, preferably of steel or of zinc-coated steel or of a base layer of zinc deposited by
15 different methods of application including mechanical deposition, of cast-iron or of aluminium, provided with an anticorrosion coating according to one of Claims 14 to 16.

18. Aqueous composition of $\text{C}_1\text{-C}_8$ tetraalkyl titanate, intended for the preparation of a coating composition for a
20 metallic substrate in aqueous dispersion, prepared from a water-soluble organic solvent, from a binder containing a silane carrying at least one hydrolysable function in hydroxyl function, from a titanate or zirconate compatible
25 in organic phase and from water, in the following proportions (percentages by mass):

- water-soluble organic solvent : 0 to 20%
- silane-based binder : 20 to 50%
- $\text{C}_1\text{-C}_8$ tetraalkyl titanate and/or zirconate : 5 to 25%
- 30 - water : qsp 100%.

19. Composition according to Claim 18, characterized in that the water-soluble organic solvent is chosen from the group constituted by the glycolic solvents such as the

- 35 -

glycol ethers, in particular diethylene glycol, triethylene glycol and dipropylene glycol, the acetates, propylene glycol, propylene glycol methyl ether, the alcohols, the ketones, as well as their mixtures.

5 20. Composition according to either one of Claims 18 and 19, characterized in that the binder comprises a silane carrying at least one hydrolysable function in hydroxyl function chosen from a C₁-C₄ alkoxy radical.

21. Composition according to any one of Claims 18 to 20,
10 characterized in that the silane additionally carries an epoxy function.

22. Composition according to Claim 21, characterized in that the silane is chosen from di- or trimethoxysilane with an epoxy function and di- or triethoxysilane with an epoxy
15 function, as well as their mixtures, in particular gamma-glycidoxy-propyltrimethoxysilane or beta-(3,4-epoxycyclohexyl)-ethyltrimethoxysilane.

23. Composition according to any one of Claims 18 to 22,
20 characterized in that the C₁-C₈ tetraalkyl titanate is advantageously chosen from the group comprising tetraethyl titanate, tetra-n-butyl titanate and octylene glycol titanate, and the C₁-C₈ tetraalkyl zirconate is advantageously chosen from the group comprising tetra-n-propyl zirconate and tetra-n-butyl zirconate.

24. Use of the composition according to any one of Claims
25 18 to 23, in pretreatment for adhesives or coatings, in posttreatment as a sealer based on metallic particles, in passivation treatment for substrates based on steel, zinc, aluminium or steel covered with a zinc-based coating, or in
30 an additive for improving the adhesion of coatings or adhesives in aqueous phase.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/IB2005/000488

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09D5/10 C09D201/10 C23F11/10 B05D1/02 B05D1/18

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09D C23F B05D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 02/088262 A (DOW CORNING CORPORATION; CLERICI, VITTORIO; WILHELMI, ALEXANDRA) 7 November 2002 (2002-11-07) paragraph '0014! - paragraph '0019! abstract	1-24
X	EP 1 233 043 A (METAL COATINGS INTERNATIONAL INC) 21 August 2002 (2002-08-21) paragraph '0017! - paragraph '0019! paragraph '0022! - paragraph '0026! paragraph '0038! - paragraph '0044! paragraph '0050! - paragraph '0056! abstract ----- -/--	1-24

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

31 May 2005

Date of mailing of the international search report

07/06/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Glomm, B

INTERNATIONAL SEARCH REPORT

International Application No

PCT/IB2005/000488

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>US 3 817 905 A (LERNER R,US ET AL) 18 June 1974 (1974-06-18) column 1, line 49 - column 3, line 75 column 4, line 56 - column 5, line 28 abstract; examples 1-6 -----</p>	1-24

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IB2005/000488

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
WO 02088262	A	07-11-2002	AU	6596401 A	20-11-2001
			CA	2408683 A1	15-11-2001
			CN	1429256 A	09-07-2003
			WO	0185854 A1	15-11-2001
			WO	02088262 A1	07-11-2002
			EP	1280863 A1	05-02-2003
			EP	1397443 A1	17-03-2004
			JP	2004501233 T	15-01-2004
			JP	2004527626 T	09-09-2004
			US	2004127625 A1	01-07-2004
			US	2004137238 A1	15-07-2004
EP 1233043	A	21-08-2002	US	2002119337 A1	29-08-2002
			AU	1558202 A	15-08-2002
			BR	0201274 A	12-11-2002
			CA	2369181 A1	14-08-2002
			CN	1385476 A	18-12-2002
			CZ	20020552 A3	16-10-2002
			DE	1233043 T1	20-03-2003
			EP	1233043 A2	21-08-2002
			ES	2181611 T1	01-03-2003
			HU	0200514 A2	28-09-2002
			JP	2002285102 A	03-10-2002
			NO	20020723 A	15-08-2002
			SK	2232002 A3	01-07-2003
			TR	200202479 T3	23-12-2002
			US	2004206266 A1	21-10-2004
			ZA	200201113 A	08-10-2002
US 3817905	A	18-06-1974	AT	331515 B	25-08-1976
			AT	765474 A	15-11-1975
			AT	326794 B	29-12-1975
			AT	1093872 A	15-03-1975
			AU	470586 B2	20-06-1974
			AU	5031672 A	20-06-1974
			BE	793557 A1	29-06-1973
			CA	996292 A1	31-08-1976
			DE	2258010 A1	09-08-1973
			DK	140107 B	18-06-1979
			FR	2166086 A1	10-08-1973
			GB	1380748 A	15-01-1975
			IT	974359 B	20-06-1974
			JP	48078235 A	20-10-1973
			NL	7217205 A	03-07-1973
			NO	140892 B	27-08-1979
			SE	392120 B	14-03-1977