

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
10 April 2003 (10.04.2003)

PCT

(10) International Publication Number
WO 03/029079 A1

- (51) International Patent Classification⁷: **B65B 9/04**, B65D 65/46, C11D 17/04
- (21) International Application Number: PCT/GB02/04311
- (22) International Filing Date:
23 September 2002 (23.09.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
0123684.3 3 October 2001 (03.10.2001) GB
- (71) Applicant (for all designated States except MN, US):
RECKITT BENCKISER N.V. [NL/NL]; Kantoorgebouw De Appelaer, De Fruittuinen 2-12, 2132 NZ Hoofddorp (NL).
- (71) Applicant (for MN only): **RECKITT BENCKISER (UK) LIMITED** [GB/GB]; 103-105 Bath Road, Slough, Berkshire SL1 3UH (GB).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **GUZMANN, Marcus** [DE/DE]; Talstrasse 13, 69181 Leimen (DE). **WIEDEMANN, Ralf** [DE/DE]; Reckitt Benckiser Produktions GmbH, Benckiser Platz 1, 67059 Ludwigshafen (DE).
- (74) Agents: **BOWERS, Craig, M.** et al.; Reckitt Benckiser plc, Group Patents Department, Dansom Lane, Hull HU8 7DS (GB).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Declarations under Rule 4.17:**
- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for all designations
 - of inventorship (Rule 4.17(iv)) for US only
 - of inventorship (Rule 4.17(iv)) for US only
- Published:**
- with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 03/029079 A1

(54) Title: PROCESS FOR PRODUCING A SEALED WATER-SOLUBLE PACKAGE

(57) Abstract: Process for producing a sealed water-soluble package of improved aesthetic appearance by treating at least part of the outer surfaces of the sealed package with a plasticizer composition and applying heat thereto, a package obtainable thereby and a specified use of such package.

PROCESS FOR PRODUCING A SEALED WATER-SOLUBLE PACKAGE

The invention is related to a process for producing a sealed water-soluble package, to a package obtainable thereby and to a specified use of such package.

5 Water-soluble packages are known in different fields of the industry and have recently become popular in the detergent industry for packaging and delivering specific detergent components for automatic dishwashing or laundry washing purposes.

Such water-soluble packages can be produced by either vertical form-fill-seal
10 (VFFS) processes or thermoforming processes.

The thermoforming process generally involves moulding a first sheet of water-soluble film material to create recesses therein to receive a composition, filling the composition into the recesses, covering the recesses filled with the composition with a second sheet of water-soluble film material, and sealing said first and second sheets
15 together at least around said recesses. One disadvantage of such sealed water-soluble packages produced by thermoforming, however, is their aesthetically non-satisfactory, crumbled appearance due to lack of control of shrinkage of the film material.

WO 00/55069 describes conditioning of sealed water-soluble packages of this type
20 by holding them in an environment of raised relative humidity for a period of time. This conditioning is said to improve the impact resistance as well as the sturdiness and resilience of the package. The conditioning is said to take place at about 20°C or below. It is not mentioned that the conditioning would have any impact on the appearance of the sealed packages, i.e. may avoid crumbling and wrinkle formation.

25 It is an object of the present invention to improve the aesthetic appearance of sealed water-soluble packages of above-mentioned type, and in particular to avoid crumbling and formation of wrinkles thereof.

According to the invention, this object is solved by treating at least part of the outer surfaces of the sealed package with a plasticizer composition and applying heat
30 thereto.

2 -

Preferably, the water-soluble film material selected from the group consisting of polymers or polymer mixtures comprising polyvinyl alcohol or polyvinyl alcohol derivatives and mixtures thereof. The water-soluble film material of the first sheet and the second sheet might be the same or different.

- 5 In a preferred embodiment, treatment of the package with the plasticizer composition occurs for a time period of up to 60 seconds.

In a preferred embodiment, heat is applied simultaneously to the treatment with the plasticizer composition, more preferably by treatment with a plasticizer composition of raised temperature. Raised temperature in this context means a temperature higher
10 than the temperature of the sealed package, preferably a temperature higher than the glass transition temperature of the film material of the packaging.

In a most preferred embodiment, treating of the sealed package with the plasticizer composition and applying heat thereto is combined in one step by applying steam or spray, produced from the plasticizer composition, and having a temperature equal or
15 higher than the glass transition temperature (T_g) of the film material on at least part of the outer surfaces of the sealed package.

In a preferred embodiment, the plasticizer composition is selected from the group consisting of water, aqueous solutions, hydrophylic organic compounds or mixtures thereof, preferably having a boiling point of below 250°C, most preferably below
20 120°C, for example an aqueous solution of propylene diglycol or an aqueous solution of glycerol or mixtures thereof. Examples of such plasticizers can be found in US 2,399,401 incorporated as reference herein.

Preferably, the composition contained within the package comprises at least one detergent component, most preferably as a liquid, gel or paste.

25

The preferred process for the creation of the recesses in the first sheet of water-soluble film material is by thermoforming. In this case, the recesses may be formed by heating the film material over a dye having respective cavities, wherein once heated the film material may be drawn into the cavities by vacuum to closely assume
30 the shape of the cavities. The vacuum may be maintained throughout the subsequent

3 -

filling and sealing steps. As a final step, the process may, of course, include the additional steps of separating the formed packages, e.g. by cutting.

In another preferred process, the recesses are formed on an array of cavities where the film is heated to 90-130°C and then, simultaneously to drawing the film into the
5 cavities by means of a vacuum, blown by a stream of compressed air (0,1-5 bar) thereinto from the upside. When the film is released from the vacuum station it remains in the shape determined by the cavities. The film is then progressed to the filling station where the filling material is supplied to the deep drawn areas in the film. Subsequently a second sheet of water-soluble film material is then
10 superimposed onto the first sheet covering the filled recesses and heat-sealed thereto using a heating plate. Therefore, the filled material is deposited in the cavities and raised flanges surrounding each cavity ensure that the films are sealed together along the flanges to form a continuous closed seal. Then the film is transported further to a cutting station separating the individual filled recesses from each other.

15 Moreover, the invention is directed to a package obtainable by the inventive process as well as to the use of such a package in an automatic dishwashing or laundry washing process.

The invention will now be described in more detail by way of the following example.

Example

20 In this example a thermoforming process is described for the production of sealed water-soluble packages according to the invention. The whole processing area was kept at 30-50 % relative humidity (RH) and the temperature was maintained between 20 and 35°C. Both for the water-soluble film material of the first sheet and of the second sheet a polyvinyl alcohol was used which is obtainable under the trade name
25 PT75 from Aicello. However, similar materials such as PT60, also obtainable from Aicello as well as L712D, obtainable from Aquafilm, or any other film from these companies and/or of the companies Chris Craft, Tohallo, Kuraray, Nippon Gohsei, Idroplast or others may be used independently as first and/or second sheet.

A first sheet of PT75 is placed over a plurality of cavities in a forming dye. Each
30 cavity is rectangular shaped having a volume of about 22 ml. The film is delivered to the forming dye in crease free form with minimum tension. In the forming step, the film material is heated to 90 to 130°C for up to 5 seconds, preferably around 0.5 to 1

second. The heated film material is drawn into the cavities by vacuum and/or by additionally applying pressure from the opposite side, forming a plurality of recesses in the sheet, which, once formed, are retained in their thermoformed orientation.

5 Once the recesses are formed, the film is transported to the filling station where the composition, e.g. a detergent material in gel form, is filled into each of the recesses. A second sheet of PT75 film material is then superimposed in the sealing station onto the first sheet covering the filled recesses and heat-sealed thereto using a heating plate. The raised flanges surrounding each cavity ensures that the films are sealed together along the flange to form a continuous closed seal.

10 Once sealed, the packages formed are separated from the web of sheet using cutting means. According to the present invention, the sealed packages are treated with a plasticizer composition and, simultaneously or separately, heat is applied.

15 In this example, a hot water steam of a temperature of 100-120°C is applied onto the surfaces of the ejected packages for a period of 0.5-2 s. In an alternative process, the hot steam or spray may also be applied onto the deep drawn part of packages via the apertures in the dye which has been used to draw the vacuum. In a preferred process the hot steam or spray may be applied while the filled cavities are still part of the web. Then the treated packs are allowed to dry and/or fully absorb the applied material until the film surface has lost its stickiness. Once conditioned, the packages
20 formed are separated from the web of sheet using cutting means.

25 There are a number of different ways for the realization of specific process steps of the present invention. It, however, appears that good results are obtainable as long as the two key issues are met, namely treatment of the film material with a plasticizer composition in steam, mist or spray form and applying heat to the film material, preferably sufficiently to raise the temperature of the film material to or above its glass transition for temperature (T_g).

As a result of those two measures, the film material shrinks back resulting in a sealed package with smooth surfaces, i.e. fitting closely around its content without any substantial wrinkles or crumbling.

30 The features disclosed in the foregoing description and the claims may, both separately and in any combination thereof, be material for realizing the invention in diverse forms thereof.

5 -

Claims

1. Process for producing a sealed water-soluble package containing a composition, the process comprising the steps of
 - (a) moulding a first sheet of water-soluble film material to create recesses therein
5 to receive said composition;
 - (b) filling said composition into said recesses;
 - (c) covering said recesses filled with said composition with a second sheet of water-soluble film material; and
 - (d) sealing said first and second sheets together at least around said recesses,
10 wherein the process additionally comprises treating at least part of the outer surfaces of the sealed package with a plasticizer composition and applying heat thereto.
2. Process according to claim 1, characterized in that the water-soluble film material is selected from the group consisting of polymers or polymer mixtures
15 comprising polyvinyl alcohol or polyvinyl alcohol derivatives and mixtures thereof.
3. Process according to claim 1 or 2, characterized in that treatment of the package with the plasticizer composition occurs for a time period of up to 60 seconds.
4. Process according to any of claims 1 to 3, characterized in that heat is applied
20 simultaneously to the treatment with the plasticizer composition.
5. Process according to claim 4, characterized in that heat is applied by treatment with a plasticizer composition of raised temperature.
6. Process according to claim 5, characterized by applying steam or spray, produced
25 from the plasticizer composition, and having a temperature equal or higher than the glass transition temperature (T_g) of the film material on at least part of the outer surfaces of the sealed package.

6 -

7. Process according to any of the preceding claims, characterized in that the plasticizer composition is selected from the group consisting of water, aqueous solutions, hydrophylic organic compounds or mixtures thereof, preferably having
5 a boiling point of below 250°C, most preferably below 120°C.
8. Process according to claim 7, characterized in that the plasticizer composition is an aqueous solution of propylene diglycol or an aqueous solution of glycerol or a mixture thereof.
9. Process according to any of the preceding claims, characterized in that said
10 composition contained within said package comprises at least one detergent component.
10. Process according to claim 9, characterized in that said composition is a liquid, gel or paste.
11. Process according to any of the preceding claims, characterized in that the
15 recesses are created by thermoforming.
12. Package obtainable by the process of any of claims 1 to 11.
13. Use of a package according to claim 12 in an automatic dishwashing or laundry washing process.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 02/04311

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B65B9/04 B65D65/46 C11D17/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B65B B65D C11D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 716 675 A (ANDERSEN PER JUST ET AL) 10 February 1998 (1998-02-10) column 4, line 44 -column 6, line 10	1
A	WO 00 55069 A (UNILEVER PLC ;LEVER HINDUSTAN LTD (IN); UNILEVER NV (NL)) 21 September 2000 (2000-09-21) cited in the application the whole document	1,12,13
A	US 2 399 401 A (SONNICHSEN HAROLD M ET AL) 30 April 1946 (1946-04-30) cited in the application claim 1	1

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

6 January 2003

Date of mailing of the international search report

15/01/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Grentzius, W

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 02/04311

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5716675	A	10-02-1998	US 5683772 A	04-11-1997
			US 5662731 A	02-09-1997
			US 5783126 A	21-07-1998
			US 5508072 A	16-04-1996
			US 5851634 A	22-12-1998
			US 5580624 A	03-12-1996
			AT 222533 T	15-09-2002
			AT 228920 T	15-12-2002
			AU 703456 B2	25-03-1999
			AU 3511895 A	15-05-1996
			BR 9509423 A	30-09-1997
			CA 2202869 A1	02-05-1996
			DE 29522138 U1	02-03-2000
			DE 29522142 U1	09-03-2000
			DE 69527856 D1	26-09-2002
			EG 20786 A	29-02-2000
			EP 0804331 A1	05-11-1997
			EP 0960711 A2	01-12-1999
			JP 11504950 T	11-05-1999
			NZ 292832 A	28-05-1999
			RU 2160288 C2	10-12-2000
			WO 9612606 A1	02-05-1996
			US 5738921 A	14-04-1998
			US 5705203 A	06-01-1998
			US 5843544 A	01-12-1998
			US 5776388 A	07-07-1998
			US 5709827 A	20-01-1998
			US 5679145 A	21-10-1997
			US 5618341 A	08-04-1997
			AT 226612 T	15-11-2002
			AU 705277 B2	20-05-1999
			AU 2971095 A	07-03-1996
			BR 9508540 A	19-05-1998
			CA 2197059 A1	22-02-1996
			DE 69528656 D1	28-11-2002
			EP 0775173 A1	28-05-1997
			JP 10505369 T	26-05-1998
			NZ 289770 A	28-01-1999
			WO 9605254 A1	22-02-1996
			US 6030673 A	29-02-2000
			US 5660900 A	26-08-1997
			US 5868824 A	09-02-1999
			AT 223297 T	15-09-2002
			AU 706484 B2	17-06-1999
			AU 5280398 A	02-04-1998
			AU 675687 B2	13-02-1997
			AU 5729794 A	22-06-1994
			AU 683249 B2	06-11-1997
			AU 6354494 A	14-09-1994
			AU 699154 B2	26-11-1998
WO 0055069	A	21-09-2000	AU 3960900 A	04-10-2000
			BR 0009047 A	15-01-2002
			CN 1344215 T	10-04-2002
			WO 0055069 A1	21-09-2000
			EP 1161383 A1	12-12-2001
			TR 200102642 T2	22-04-2002
			US 6363693 B1	02-04-2002

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 02/04311

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2399401	A	30-04-1946 GB 577761 A	30-05-1946