

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
27 March 2003 (27.03.2003)

PCT

(10) International Publication Number
WO 03/025074 A1

(51) International Patent Classification⁷: **C09D 5/03**

(21) International Application Number: PCT/US02/27450

(22) International Filing Date: 29 August 2002 (29.08.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/952,699 14 September 2001 (14.09.2001) US

(71) Applicant: **PPG INDUSTRIES OHIO, INC.** [US/US];
3800 West 143rd Street, Cleveland, OH 44111 (US).

(72) Inventors: **BARKAC, Karen, A.**; 322 Oakridge Drive,
Murrysville, PA 15668 (US). **RECHENBERG, Karen, S.**;
188 E. Partridge Road, Gibsonia, PA 15044 (US). **NAKA-**
JIMA, Masayuki; 2604 Glenchester Drive, Wexford, PA
15090 (US).

(74) Agents: **MILES, Jacques, B.** et al.; PPG Industries, Inc.,
One PPG Place, Pittsburgh, PA 15272 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC,
VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK,
TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: IMPROVED MAR RESISTANCE

(57) Abstract: A curable powder coating composition is disclosed comprising a film-forming polymer having reactive functional groups, a curing agent having functional groups reactive with the functional groups of the polymer, the curing agent being present in an amount sufficient to cure the coating composition, and a tricarbamoyl triazine compound. The curable powder coating composition has improved mar resistance properties.



WO 03/025074 A1

IMPROVED MAR RESISTANCE

5 **Field of the Invention**

The present invention relates to powder coating compositions, particularly powder coating compositions with improved mar resistance properties.

10 **Background**

Solid particulate coating formulations referred to in the industry as "powder coatings" can be applied over various substrates. A major benefit of powder coatings is that little, if any, volatile material is given off to the surrounding environment when powder coatings are cured. Due to increasing
15 restrictions on volatile organic content (VOC), powder coatings are preferred for many applications.

One problem with conventional powder coatings is that they exhibit poor mar resistance properties. "Mar resistance" refers to the ability of a coating composition to maintain its appearance when the coating comes in
20 contact with an abrasive material.

To improve mar resistance, microparticulate materials such as silica, metal sulfides, and crosslinked styrene-butadiene are sometimes added to powder coating compositions. Because the addition of microparticulate materials adversely affects the gloss and the distinctness of image (DOI) of a
25 coated surface, this is a less than ideal solution to the problem.

The present invention provides a curable powder coating composition which exhibits improved mar resistance properties.

Summary of the Invention

30 The present invention is a curable powder coating composition comprising a polymer containing reactive functional groups, a curing agent having functional groups reactive with the functional groups of said polymer, the curing agent being present in an amount sufficient to cure said polymer,

- 2 -

and less than 10 percent based on total resin solids of the powder coating composition of a tricarbamoyl triazine compound represented by the following chemical formula: $C_3N_3(NRCOXY)_3$ where Y is an alkyl group or substituted alkyl group having 1 to 12 carbon atoms, X is NR', O, S, PR', and -C-, and R
5 and R' are hydrogen and alkyl or a substituted alkyl having 1 to 12 carbon atoms.

Detailed Description of the Invention

Various numerical ranges are disclosed in this patent application.

10 Because these ranges are continuous, they include every value between the minimum and maximum values. Unless expressly indicated otherwise, the various numerical ranges specified in this application are approximations. It is implied that the minimum and maximum values within the stated ranges are preceded by the word "about". Therefore, slight variations above and below
15 the stated ranges can be used to achieve substantially the same results.

The powder coating composition of the present invention comprises a polymer having reactive functional groups. The polymer having reactive functional groups can be chosen from a variety of materials, including but not limited to, acrylic polymers, polyurethane polymers, and polyester polymers.

20 The reactive functional groups on the polymer are selected from carboxylic acid, epoxy, hydroxyl, amino, carbamate and urea. The polymer is present in the powder coating composition in amounts ranging from about 10 to 90 percent by weight, based on total weight of resin solids in the powder coating composition.

25 In an embodiment of the invention, the polymer having reactive functional groups is an acrylic polymer. Acrylic polymers containing the appropriate functional groups can be formed by reacting polymerizable alpha, beta-ethylenically unsaturated monomers containing the functional groups mentioned above with one or more other polymerizable, unsaturated
30 monomers.

- 3 -

Suitable carboxylic acid group-containing monomers include acrylic acid, methacrylic acid, crotonic acid, itaconic acid, fumaric acid, maleic acid, citraconic acid, and monoalkylesters of unsaturated dicarboxylic acids.

Acrylic acid and methacrylic acid are the preferred carboxylic acids.

5 Suitable epoxy group-containing monomers include glycidyl acrylate and glycidyl methacrylate.

Suitable amino group-containing monomers include aminoethyl methacrylate and aminopropyl methacrylic.

Pendant carbamate functional groups can be incorporated into the
10 acrylic polymer by copolymerizing the acrylic monomers with a carbamate functional vinyl monomer. Examples of suitable carbamate functional monomers include: (a) carbamate functional alkyl esters of methacrylic acid; (b) the reaction product of hydroxyethyl methacrylate, isophorone diisocyanate, and hydroxypropyl carbamate; (c) the reaction product of
15 hydroxypropyl methacrylate, isophorone diisocyanate, and methanol; and (d) the reaction product of isocyanic acid with a hydroxyl functional acrylic or methacrylic monomer like hydroxyethyl acrylate.

Pendant urea groups can be incorporated into the acrylic polymer by copolymerizing the acrylic monomers with urea functional vinyl monomers.
20 Examples of urea functional monomers include: (a) urea functional alkyl esters of acrylic acid or methacrylic acid and (b) the reaction product of hydroxyethyl methacrylate, isophorone diisocyanate, and hydroxyethyl ethylene urea.

The acrylic polymers typically have number average molecular weights
25 of about 1,000 to 10,000 or 1,000 to 5,500 based on gel permeation chromatography using a polystyrene standard. The acrylic polymers have equivalent weights (based on the functional groups mentioned above) of about 200 to 400 or 250 to 355 gram/equivalent. The glass transition temperature (T_g) of the polymer is typically about 30°C to 60°C or 35°C to
30 55°C. The T_g is determined by Differential Scanning Calorimetry (DSC) at a rate of heating equal to 18°F (10°C) per minute.

- 4 -

In another embodiment of the present invention, the polymer having reactive functional groups is a polyurethane polymer containing the functional groups mentioned above for the acrylic polymers. Polyurethane polymers can be prepared by reacting polyols and polyisocyanates. Examples of suitable polyols include low molecular weight aliphatic polyols such as ethylene glycol, propylene glycol, butylene glycol, 1,6-hexylene glycol, neopentyl glycol, cyclohexanedimethanol, trimethylolpropane and the like. Typically, high molecular weight polymeric polyols such as polyether polyols and polyester polyols are used with the lower molecular weight polyols. Examples of polyether polyols are those formed from the oxyalkylation of various polyols like glycols or higher polyols. Suitable glycols include ethylene glycol, 1,6-hexanediol, and Bisphenol A. Suitable higher polyols include trimethylol propane and pentaerythritol. Suitable polyester polyols can be prepared by the polyesterification of organic polycarboxylic acids or anhydrides thereof with organic polyols. Usually, the polycarboxylic acids and polyols are aliphatic or aromatic dibasic acids and diols.

Suitable polyisocyanates include aromatic and aliphatic polyisocyanates. Aliphatic polyisocyanates are preferred because of their exterior durability. Exemplary polyisocyanates include 1,6-hexamethylene diisocyanate, isophorone diisocyanate and 4,4'-methylene-bis-(cyclohexyl isocyanate).

Carboxylic acid functionality can be introduced into the polyurethane by reacting the polyurethane polyol with polycarboxylic acids. Exemplary polycarboxylic acids include succinic acid, adipic acid, azelaic acid, sebacic acid, terephthalic acid, isophthalic acid, tetrahydrophthalic acid, hexahydrophthalic acid, trimellitic acid and anhydrides of such acids. Alternatively, the polyisocyanate can be reacted with a mixture of the polyols mentioned above and a polyol containing carboxylic acid groups such as dimethylol propionic acid.

- 5 -

Hydroxyl functionality can be introduced into the polyurethane by reacting the polyisocyanate with a stoichiometric excess of the polyol component to form a polyurethane polyol.

Epoxy functionality can be incorporated into the polyurethane by including a hydroxy functional epoxy compound like glycidol with the polyol component.

Amino functionality can be introduced into the polyurethane by including a polyamine in the monomer charge. Suitable amines include primary and secondary diamines and polyamines in which the radicals attached to the nitrogen atoms are saturated, aliphatic, alicyclic, aromatic, aromatic-substituted aliphatic, aliphatic-substituted aromatic, or heterocyclic.

Pendant carbamate groups can be incorporated into the polyurethane by forming a hydroxyalkyl carbamate which can be reacted with the polyacids or polyols used to form the polyurethane.

Pendant urea groups can be introduced into the polyurethane by reacting a hydroxyl functional urea such as hydroxyalkyl ethylene urea with the polyacids and polyols used to form the polyurethane. Also, isocyanate terminated polyurethane can be reacted with primary amines, aminoalkyl ethylene urea, or hydroxyalkyl ethylene urea to yield a material with pendant urea groups.

The polyurethane polymers typically have number average molecular weights of about 3,000 to 25,000 or 5,000 to 10,000 based on gel permeation chromatography using a polystyrene standard. The polyurethane polymers have equivalent weights (based on the functional groups mentioned above) of about 280 to 2,805 or 1,122 to 1,870 gram/equivalent. The T(g) of the polymer is typically about 35°C to 85°C or 45°C to 60°C.

In another embodiment of the invention, the polymer having reactive groups is a polyester polymer having the functional groups mentioned above. Polyester polymers are based on a condensation reaction of low molecular weight aliphatic polyols, including cycloaliphatic polyols, with aliphatic and/or aromatic polycarboxylic acids and anhydrides. Examples of suitable aliphatic

- 6 -

polyols include 1,2-ethanediol, 1,3-propanediol, 1,4-butanediol, 1,6-hexanediol, neopentyl glycol, cyclohexane dimethanol, trimethylol propane, and the like. Polymeric polyols such as the polyether polyols mentioned above can be used in combination with the low molecular weight polyols.

- 5 Examples of suitable polycarboxylic acids and anhydrides include succinic acid, adipic acid, azelaic acid, sebacic acid, terephthalic acid, isophthalic acid, tetrahydrophthalic acid, hexahydrophthalic acid, trimellitic acid and anhydrides of such acids.

Carboxylic acid functionality can be introduced into the polyester by
10 reacting a stoichiometric excess of the polycarboxylic acid with the polyol.

Hydroxyl functionality can be incorporated into the polyester by reacting a stoichiometric excess of the polyol component with the polycarboxylic acid.

Epoxy groups can be introduced into the polyester by including an
15 epoxy functional compound such as glycidol with the polyol component.

Amino groups can be introduced into the polyester by including an amino alcohol such as amino ethanol or amino propanol with the polyol component.

Pendant carbamate groups can be introduced into the polyester by
20 forming a hydroxyalkyl carbamate which can be reacted with the polyacids or polyols used to form the polyester.

Pendant urea groups can be introduced into the polyurethane by reacting a hydroxyl functional urea such as hydroxyalkyl ethylene urea with the polyacids and polyols used to form the polyester. Also, polyester
25 prepolymers can be reacted with primary amines, aminoalkyl ethylene urea, or hydroxyalkyl ethylene urea to yield a material with pendant urea groups.

The polyester polymers typically have number average molecular weights of about 3,000 to 35,000 or 5,000 to 10,000 based on gel permeation chromatography using a polystyrene standard. The polyester polymers have
30 equivalent weights (based on the functional groups mentioned above) of

- 7 -

about 280 to 2,805 or 122 to 1,870 gram/equivalent. The T(g) of the polymer is typically about 25°C to 85°C or 50°C to 70°C.

The powder coating composition of the present invention also comprises a curing agent having functional groups that are reactive with the functional groups of the polymer described above. Suitable curing agents include polyepoxides, beta-hydroxyalkylamides, polyacids, aminoplast, and blocked polyisocyanates.

Polyepoxides are suitable curing agents for polymers having carboxylic acid groups and amine. Examples of suitable polyepoxides include those described in U.S. Patent No. 4,681,811 at column 5, lines 33 to 58, incorporated herein by reference.

Beta-hydroxyalkylamides are suitable curing agents for polymers having carboxylic acid groups. Examples of suitable beta-hydroxyalkylamides include those described in U.S. Patent No. 4,801,680 at column 2, line 42 to column 3, line 9, incorporated herein by reference.

Polyacids, particularly polycarboxylic acids, are good curing agents for polymers having epoxy functional groups. Examples of suitable polycarboxylic acids include those described in U.S. Patent No. 5,407,707 at column 3, line 55 to column 4, line 10, incorporated herein by reference.

Aminoplast and phenoplast curing agents are suitable curing agents for polymers having hydroxyl, carboxylic acid, carbamate and urea functional groups. Examples of suitable aminoplast include alkylated methylol melamine and alkylated methylol urea.

Blocked polyisocyanates and polyisocyanurate are suitable curing agents for polymers having hydroxyl and amino groups. Examples of suitable blocked polyisocyanates include benzene triisocyanate, polymethylene isocyanate, 1,4-tetramethylene diisocyanate, 1,6-hexamethylene diisocyanate, 4,4'-diphenylmethane diisocyanate, 1,3-phenylene diisocyanate, 1,4-phenylene diisocyanate, toluene diisocyanate, 1,4-cyclohexyl diisocyanate, isophorone diisocyanate, and 4,4'-methylene-bis(cyclohexyl isocyanate).

- 8 -

The curing agent must be present in an amount sufficient to cure the powder coating composition of the present invention. Typically, the curing agent is present in the powder coating composition in an amount ranging from 10 to 90 weight percent or from 25 to 75 weight percent, said weight
5 percentages based on the total weight of resin solids in the powder coating composition.

The powder coating composition of the present invention also comprises a tricarbamoyl triazine compound represented by the following chemical formula: $C_3N_3(NR'COXY)_3$ where Y is an alkyl group or substituted
10 alkyl group having 1 to 12 carbon atoms, X is NR' , O, S, PR' , or $-C-$, and R and R' are hydrogen and alkyl or a substituted alkyl having 1 to 12 carbon atoms. Examples of suitable substitution groups for the substituted alkyl include ether, ester, amide, acid, epoxy, urethane, urea, hydroxyl (preferred substituent), thiol, silyl (alkoxysilane) group, and cyano group.

15 When X is O, Y is preferably an alkyl group or a substituted alkyl group having 6 to 12, more preferably 6 to 8 carbon atoms.

When X is NR' , Y is preferably an alkyl group or a substituted alkyl group having 1 to 6 more preferably 2 to 4 carbon atoms.

Tricarbamoyl triazine compounds and methods of preparing them are
20 described in U.S. Patent No. 5,084,541, incorporated herein by reference.

It is significant that the present invention is limited to tricarbamoyl triazine compounds having the following chemical formula: $C_3N_3(NR'COXY)_3$ where Y is an alkyl group or substituted alkyl group having 1 to 12 carbon atoms, X is NR' , O, S, PR' , or $-C-$, and R and R' are hydrogen and alkyl or a
25 substituted alkyl having 1 to 12 carbon atoms. Typically, tricarbamoyl triazine compounds are not compatible with powder systems. However, up to 10 percent of the disclosed tricarbamoyl triazine compound based on the total weight of resin solids in the powder coating composition can be loaded into the powder composition without crashing the system. The tricarbamoyl
30 triazine compound is present in the powder coating composition in amounts of up to 10 percent by weight or from about 2 to 8 percent by weight or about 4

- 9 -

to 8 percent by weight, based on total weight of resin solids in the curable composition.

Optimally, the powder coating composition of the present invention can also include the following materials which are all well known in the art:

5 pigments, fillers, light stabilizers, anti-oxidants, flow control agents, anti-popping agents, and catalyst.

The powder coating composition of the present invention is formed by melt blending the above-mentioned components. The melt blending process proceeds as follows. Initially, all of the components are blended in a high
10 shear mixer such as a Henschel Blender. Then, the blended components are melt blended in an extruder at a temperature between 80°C and 130°C. Next, the extrudate is cooled. Lastly, the cooled extrudate is pulverized into a particulate blend and ground to a particle size of 17 to 27 microns using a grinding mill such as an Air Classifying Mill ACM II available from Micron
15 Powder Systems.

The powder coating composition of the present invention can be applied directly to a substrate such as wood, plastic, steel and aluminum. The finished powders can be electrostatically sprayed onto test panels and evaluated for coating properties.

20 The powder coating composition of the present invention exhibits improved mar resistance properties in comparison to conventional powder coatings.

EXAMPLES

25 The present invention is illustrated by the following non-limiting examples. Various powder coating compositions were prepared for purposes of testing. The various powder coating compositions are denoted as Examples A through G. Example A is a conventional powder coating composition. Examples B, D, and F are powder coating compositions
30 according to the present invention. They contain different amounts of the

- 10 -

disclosed tricarbamoyl triazine compound. Examples C, E, and G are comparative examples.

Specific information on the make up of powder coating compositions A through G is contained in Table 1.

5 Table 2 contains information related to mar resistance and gassing.

POWDER COATING COMPOSITIONS

Table 1 below provides a list of the ingredients used to formulate the various powder coating compositions used in the Examples. All of the
10 quantities expressed in Table 1 are in grams.

- 11 -

Table 1

Ingredient	Example A	Example B	Example C (Comparative)	Example D	Example E (Comparative)	Example F	Example G (Comparative)
GMA Functional Acrylic ¹	69.05	65.29	61.53	62.08	59.06	62.68	59.06
DDDA ²	22.68	21.44	20.2	20.58	19.39	20.58	19.39
Acrylic Flow Add ³	1.1	1.1	1.1	1.1	1.1	1.1	1.1
Benzoin	0.2	0.2	0.2	0.2	0.2	0.2	0.2
Microwax C ⁴	0.6	0.6	0.6	0.6	0.6	0.6	0.6
Tinuvin 144 ⁵	2	2	2	2	2	2	2
CGL-1545 ⁶	2	2	2	2	2	2	2
HCA-1 ⁷	2	2	2	2	2	2	2
ARMEEN M2C ⁸	0.37	0.37	0.37	0.37	0.37	0.37	0.37
TACT ⁹	0	5	10	0	0	0	0
TACT modified with hydroxy ethyl carbamate ¹⁰	0	0	0	5	10	0	0
TACT modified ¹¹ with dibutyl amine	0	0	0	0	0	5	10

- 12 -

¹GMA Functional Acrylic is comprised of 50% Glycidal Methacrylate, 10% Butyl Methacrylate, % Styrene, and 35% Methyl Methacrylate, by weight.

²Dodecanedioic Acid

5 ³Acrylic Flow Additive was prepared by solution polymerization in xylene and toluene of the following monomers: 81.2% 2-ethyl hexyl acrylate, 11.8% hydroxyl ethyl acrylate, and 7% N,N-dimethylaminoethyl methacrylate. The polymerization was at reflux temperature in the presence of VAZO 67 (2,2'-Azobis-2-methylbutyronitrile)). The acrylic flow agent was vacuum stripped to 100% solids.

10 ⁴A fatty acid amide (ethylene bis-stearoylamide) that is sold by Hoechst-Celanese Corporation.

15 ⁵TINUVIN 144 (2-tert-butyl-2-(4-hydroxy-3,5-di-tert-butylbenzyl)[bis(methyl-2,2,6,6,-tetramethyl-4-piperidiny)] dipropionate) is an ultraviolet light stabilizer sold by Ciba-Geigy Corp.

20 ⁶CGL-1545 (2-[4((2-Hydroxy-3-(2-ethylhexyloxy) propyl)-oxy]-2-hydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine) is an ultraviolet light stabilizer sold by Ciba-Geigy Corp.

⁷HCA-1 is an anti-yellowing agent sold by Sanko Chemical Corp.

⁸ARMEEN M2C is a methyl dicocoamine sold by Akzo-Nobel Corp.

⁹TACT is a mixture of 2, 4, 6-tris(methyl carbamate)-1, 3, 5-triazine and 2, 4, 6-tris(n-butyl carbamate)-1, 3, 5- triazine which is supplied as an n-butanol solution.

25 ¹⁰TACT modified with hydroxy ethyl carbamate is a product of the reaction between TACT and 2-hydroxyethyl carbamate.

30 ¹¹TACT modified with dibutyl amine is a product of the reaction between TACT and n-butylamine.

COATED SUBSTRATES

Coated substrates were prepared using the powder compositions of Examples A through G. The coated substrates were prepared in the following manner. Panels were coated with ED5000, an electrocoat primer commercially available from PPG Industries, Inc. Then, a layer of Akzo Black Primer commercially available from Akzo Corporation and a layer of BASF Black II Waterborne Basecoat commercially available from BASF Corporation were spray applied on the panel to achieve a film thickness of about 1.1 mils (27.9 microns) and 0.47 mils (12 microns), respectively. Next, the primed panels were cured at a bake schedule of 25 minutes at 311°F (155°C), basecoated and flash baked for 10 minutes at 176°F (80°C). Lastly, the exemplary powder clearcoat compositions were electrostatically applied to the

- 13 -

panels and cured for 30 minutes at 293°F (145°C). The applied film thickness of the powder clearcoat was between 2.7 and 3.5 mils (68.6 to 88.9 microns). The coated substrates were evaluated for mar resistance and gassing.

Table 2 contains data reflecting the gassing and mar resistance properties of the coated panels. The mar resistance value used for analytical purposes is the average of the mar resistance determined using an Atlas Mar Tester with Bon Ami Cleanser and the mar resistance determined using an Atlas Mar Tester with 2 μ 3M Abrasive Paper.

To calculate mar resistance using the Atlas Mar Tester with Bon Ami Cleanser, a light coating of Bon Ami cleanser was applied to each of the test panels. Excess cleanser was shaken off. A set of ten double rubs was then run on each panel using a felt cloth clamped to the acrylic finger on the arm of the instrument. Two more sets of ten double rubs were done for a total of three mar stripes per panel. Next, the panel was washed with cool tap water and dried. Mar Resistance which equals the Marred Gloss divided by the Original Gloss multiplied by 100 was expressed as the percentage of the 20° Gloss retained after the surface is marred by the mar tester.

To calculate mar resistance using the Atlas Mar Tester with 2 μ 3M Abrasive Paper, a 2 inch by 2 inch piece of the 2 μ abrasive paper was placed over the felt cloth and clamped to the acrylic finger on the arm of the instrument. Then, a set of ten double rubs was run on each panel. Two more sets of ten double rubs were done for a total of three mar stripes per panel. Next, the panel was washed with cool tap water and dried. Mar Resistance which equals the Marred Gloss divided by the Original Gloss multiplied by 100 was expressed as the percentage of the 20° Gloss retained after the surface is marred by the mar tester.

Table 2 contains comparative information on the mar resistance of the exemplary coating compositions. Example A was the control.

Gassing refers to holes in the film which result because entrapped air and other volatiles are trying to escape through the clearcoat layer during

- 14 -

cure. Gassing of the panels was rated on a scale of 0 to 3 by visual inspection.

Table 2

5 The following is a description of the numbers and symbols that appear in Table 2 below:

For gassing,

"0" indicates no Gassing;

"1" indicates slight Gassing;

10 "2" indicates moderate Gassing; and

"3" indicates severe Gassing

For mar resistance,

"=" indicates the mar resistance was equal to the control;

15 "+" indicates there was some degree of improvement in mar resistance over the control; and

"++" indicates there was a significant degree of improvement in mar resistance over the control.

	Gassing	20° Gloss	Mar Resistance
Example A	0	84	=
Example B	2	84	+
Example C	3	41	++
Example D	0	82	+
Example E	1	67	++
Example F	0	85	+
Example G	2	84	++

20 Conclusion

As shown in Table 2 above, the powder coating compositions of the present invention demonstrated improved mar resistance properties and

- 15 -

minimal gassing. Because powder coating compositions according to the present invention exhibit minimal gassing, panels coated with the inventive compositions have superior appearance properties.

- 16 -

WHAT IS CLAIMED IS:

1. A curable powder coating composition comprising:
 - a. a polymer containing reactive functional groups;
 - 5 b. a curing agent having functional groups reactive with the functional groups of said polymer, the curing agent being present in an amount sufficient to cure said polymer; and
 - c. less than 10 percent by weight of a tricarbamoyl triazine compound represented by the following chemical formula: $C_3N_3(NRCOXY)_3$
10 where Y is an alkyl group or substituted alkyl group having 1 to 12 carbon atoms, X is NR', O, S, PR', and -C-, and R and R' are hydrogen and alkyl or a substituted alkyl having 1 to 12 carbon atoms, the percentage is based on the total weight of resin solids in the powder coating composition.
- 15 2. A curable powder coating composition according to claim 1 wherein said polymer comprises an acrylic polymer.
3. A curable powder coating composition according to claim 1 wherein said polymer comprises carboxylic acid functional groups.
20
4. A curable powder coating composition according to claim 1 wherein said polymer comprises epoxy functional groups.
5. A curable powder coating composition according to claim 1
25 wherein said polymer comprises hydroxyl functional groups.
6. A curable powder coating composition according to claim 1 wherein said polymer comprises amino functional groups.

- 17 -

7. A curable powder coating composition according to claim 1 wherein said polymer comprises carbamate functional groups.

8. A curable powder coating composition according to claim 1
5 wherein said polymer comprises urea functional groups.

9. A curable powder coating composition according to claim 1 wherein said polymer comprises a polyester.

10 10. A curable powder coating composition according to claim 1 wherein said polymer comprises a polyurethane.

11. A curable powder coating composition according to claim 1 wherein said curing agent comprises a polyepoxide.
15

12. A curable powder coating composition according to claim 1 wherein said curing agent comprises a beta-hydroxyalkylamide.

13. A curable powder coating composition according to claim 1
20 wherein said curing agent comprises a polyacid.

14. A curable powder coating composition according to claim 1 wherein said curing agent comprises an aminoplast

25 15. A curable powder coating composition according to claim 1 wherein said curing agent comprises a polyisocyanate.

- 18 -

16. A curable powder coating composition according to claim 1 wherein said polymer is present in amounts from about 10 to 90 percent by weight, based on the total weight of resin solids in the powder coating composition.

5

17. A curable powder coating composition according to claim 1 wherein said curing agent is present from about 10 to 90 percent by weight, based on the total weight of resin solids in the powder coating composition.

10 18. A curable powder coating composition according to claim 1 wherein said tricarbamoyl triazine compound is present from about 2 to 8 percent by weight, based on the total weight of resin solids in the powder coating composition.

15 19. A curable powder coating composition according to claim 1 wherein X is O and Y is an alkyl or substituted alkyl group having 6 to 8 carbon atoms.

20 20. A curable powder coating composition according to claim 1 wherein X is NR' and Y is an alkyl or substituted alkyl group having 2 to 4 carbon atoms.

21. A curable powder coating composition comprising:
a. a polymer having carboxylic acid functional groups;
b. a beta-hydroxyalkylamide; and
c. less than 10 percent by weight of a tricarbamoyl triazine
25 compound represented by the following chemical formula: $C_3N_3(NRCOXY)_3$
wherein X is NR', Y is an alkyl or substituted alkyl group having 2 to 4 carbon atoms, and R and R' are hydrogen and alkyl or a substituted alkyl having 1 to

- 19 -

12 carbon atoms, the percentage is based on the total weight of resin solids in the powder coating composition .

22. A curable powder coating composition according to claim 21
5 wherein said polymer comprises an acrylic polymer.

23. A curable powder coating composition according to claim 22
wherein the acrylic polymer has a number average molecular weight of about
1,000 to 10,000.

10

24. A curable powder coating composition according to claim 22
wherein the acrylic polymer has an equivalent weight of about 200 to 400.

25. A curable powder coating composition according to claim 22
15 wherein the acrylic polymer has a glass transition temperature from about
30°C to 60°C.

26. A curable powder coating composition according to claim 21
wherein said polymer is present in amounts from about 10 to 90 percent by
20 weight, based on the total weight of resin solids in the powder coating
composition.

27. A curable powder coating composition according to claim 21
wherein said hydroxyalkylamide is present from about 10 to 90 percent by
25 weight, based on the total weight of resin solids in the powder coating
composition.

- 20 -

28. A curable powder coating composition according to claim 21 wherein said tricarbamoyl triazine compound is present from about 2 to 8 percent by weight, based on the total weight of resin solids in the powder coating composition.

5

29. A curable powder coating composition comprising:

a. an acrylic polymer having carboxylic acid functional groups;

b. a beta-hydroxyalkylamide;

10

c. about 5 percent by weight of a tricarbamoyl triazine compound represented by the following chemical formula: $C_3N_3(NR'COXY)_3$ wherein X is NR', Y is an alkyl or substituted alkyl group having 2 to 4 carbon atoms, and R and R' are hydrogen and alkyl or a substituted alkyl having 1 to 12 carbon atoms, the percentage is based on the total weight of resin solids in the powder coating composition.

15

30. A curable powder coating composition according to claim 29 wherein said acrylic polymer is present in an amount from about 10 to 90 percent by weight, based on the total weight of resin solids in the powder coating composition.

20

31. A curable powder coating composition according to claim 29 wherein said hydroxyalkylamide is present from about 10 to 90 percent by weight, based on the total weight of resin solids in the powder coating composition.

25

32. A curable powder coating composition according to claim 29 wherein said acrylic polymer has a number average molecular weight of about 1,000 to 10,000.

30

- 21 -

33. A curable powder coating composition according to claim 29 wherein said acrylic polymer has an equivalent weight of about 500 to 1,500.

34. A curable powder coating composition according to claim 29
5 wherein said acrylic polymer has a glass transition temperature of about 35°C to 120°C.

35. A substrate comprising a cured coating derived from a curable powder coating composition comprising:
10 a. a polymer containing reactive functional groups;
b. a curing agent having functional groups reactive with the functional groups of said polymer which is present in an amount sufficient to cure said polymer; and
c. less than 10 percent of a tricarbamoyl triazine compound
15 represented by the following chemical formula: $C_3N_3(NRCOXY)_3$ where Y is an alkyl group or substituted alkyl group having 1 to 12 carbon atoms, X is NR', O, S, PR', and -C-, and R and R' are hydrogen and alkyl or a substituted alkyl having 1 to 12 carbon atoms, the percentage is based on the total weight of resin solids in the powder coating composition

20

36. A substrate according to claim 35 wherein the polymer comprises an acrylic polymer.

37. A substrate according to claim 35 wherein said polymer
25 comprises carboxylic acid functional groups.

38. A substrate according to claim 36 wherein the acrylic polymer is present in an amount from about 10 to 90 percent by weight, based on the total weight of resin solids in the powder coating composition.

30

- 22 -

39. A substrate according to claim 36 wherein the acrylic polymer has a glass transition temperature of about 35°C to 120°C.

40. A substrate comprising a cured coating derived from a curable powder coating composition comprising:
- a. an acrylic polymer having carboxylic acid functional groups;
 - b. a beta-hydroxyalkylamide;
 - c. about 5 percent of a tricarbamoyl triazine compound
- represented by the following chemical formula: $C_3N_3(NRCOXY)_3$ wherein X is NR', Y is an alkyl or substituted alkyl group having 2 to 4 carbon atoms, and R and R' are hydrogen and alkyl or a substituted alkyl having 1 to 12 carbon atoms, the percentage is based on the total weight of resin solids in the powder coating composition.

15

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/27450

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09D5/03

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 197 44 561 A (BASF COATINGS AG) 1 April 1999 (1999-04-01) the whole document	1,2,4, 13,16, 17,19, 35-39
P,X	DE 100 27 293 A (BASF COATINGS AG) 13 December 2001 (2001-12-13) paragraphs '0028!', '0029!', '0078!'-'0082!', '0084!'-'0087!', '0112!'-'0114!'	1-12, 14-17, 19,35-39
A	DE 199 24 674 A (BASF COATINGS AG) 30 November 2000 (2000-11-30) -/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

12 November 2002

Date of mailing of the international search report

20/11/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Miller, A

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/27450

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 084 541 A (DILEONE ROLAND ET AL) 28 January 1992 (1992-01-28) cited in the application -----	
A	US 4 801 680 A (VICHA SUSAN K ET AL) 31 January 1989 (1989-01-31) cited in the application -----	

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 02/27450

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
DE 19744561	A	01-04-1999	DE 19744561 A1	01-04-1999
			AU 751658 B2	22-08-2002
			AU 9265798 A	12-04-1999
			AU 744669 B2	28-02-2002
			AU 9740198 A	12-04-1999
			BR 9812654 A	22-08-2000
			BR 9812661 A	22-08-2000
			DE 19832106 A1	20-01-2000
			DE 19832107 A1	20-01-2000
			WO 9915598 A1	01-04-1999
			WO 9915593 A1	01-04-1999
			EP 1015519 A1	05-07-2000
			EP 1017750 A1	12-07-2000
			JP 2001517722 T	09-10-2001
			JP 2001517724 T	09-10-2001
			PL 339438 A1	18-12-2000
			PL 339444 A1	18-12-2000
			US 6342274 B1	29-01-2002
			US 6358568 B1	19-03-2002
DE 10027293	A	13-12-2001	DE 10027293 A1	13-12-2001
DE 19924674	A	30-11-2000	DE 19924674 A1	30-11-2000
			BR 0011059 A	05-03-2002
			WO 0073395 A1	07-12-2000
			EP 1190004 A1	27-03-2002
US 5084541	A	28-01-1992	US 4939213 A	03-07-1990
US 4801680	A	31-01-1989	CA 1330682 A1	12-07-1994
			DE 3885258 D1	02-12-1993
			DE 3885258 T2	05-05-1994
			EP 0322834 A2	05-07-1989
			ES 2061620 T3	16-12-1994
			JP 2003458 A	09-01-1990
			JP 2594346 B2	26-03-1997
			KR 9302217 B1	27-03-1993
			MX 164778 B	23-09-1992