



(86) Date de dépôt PCT/PCT Filing Date: 2005/06/21  
 (87) Date publication PCT/PCT Publication Date: 2006/02/23  
 (45) Date de délivrance/Issue Date: 2013/08/06  
 (85) Entrée phase nationale/National Entry: 2007/02/09  
 (86) N° demande PCT/PCT Application No.: EP 2005/052872  
 (87) N° publication PCT/PCT Publication No.: 2006/018341  
 (30) Priorité/Priority: 2004/08/12 (DE10 2004 039 083.5)

(51) Cl.Int./Int.Cl. *C08G 6/02* (2006.01),  
*C08F 283/00* (2006.01), *C08L 61/02* (2006.01),  
*C08L 61/14* (2006.01), *C09D 4/06* (2006.01)

(72) Inventeurs/Inventors:  
 GLOECKNER, PATRICK, DE;  
 WENNING, ANDREAS, DE;  
 DENKINGER, PETER, DE;  
 EWALD, MICHAEL, DE

(73) Propriétaire/Owner:  
 EVONIK DEGUSSA GMBH, DE

(74) Agent: FETHERSTONHAUGH & CO.

(54) Titre : PRODUITS DE REACTION SANS ETAIN, A POINT DE FUSION ELEVE, OBTENUS A PARTIR DE RESINES CETONE-ALDEHYDE A FONCTION CARBONYLE HYDROGENEE, DE RESINES CETONIQUES HYDROGENEES ET DE RESINES CETONE- ALDEHYDE A FONCTION CARBONYLE ET NOYAU HYDROGENES A BASE DE POLYISOCYANATES ET DE CETONES AROMATIQUES

(54) Title: TIN-FREE, HIGH-MELTING REACTION PRODUCTS OF CARBONYL-HYDROGENATED KETONE-ALDEHYDE RESINS, HYDROGENATED KETONE RESINS AND CARBONYL-AND RING-HYDROGENATED KETONE-ALDEHYDE RESINS BASED ON AROMATIC KETONES AND POLYISOCYANATE

(57) **Abrégé/Abstract:**

The invention relates to tin-free reaction products of hydroxyl-containing hydrogenated ketone resins, carbonyl-hydrogenated ketone-aldehyde resins, and carbonyl-hydrogenated and ring-hydrogenated ketone-aldehyde resins based on aromatic ketones and polyisocyanates, to a process for their preparation and to the use thereof, in particular as a main component, base component or additive component in coating materials, adhesives, inks, polishes, glazes, stains, pigment pastes, filling compounds, cosmetics articles, sealants and/or insulants.



O.Z. 6375

20

**Abstract:**

The invention relates to tin-free reaction products of hydroxyl-containing hydrogenated ketone resins, carbonyl-hydrogenated ketone-aldehyde resins, and carbonyl-hydrogenated and ring-  
5 hydrogenated ketone-aldehyde resins based on aromatic ketones and polyisocyanates, to a process for their preparation and to the use thereof, in particular as a main component, base component or additive component in coating materials, adhesives, inks, polishes, glazes, stains, pigment pastes, filling compounds, cosmetics articles, sealants and/or insulants.

O.Z. 6375

1

**Tin-free, high-melting reaction products of carbonyl-hydrogenated ketone-aldehyde resins, hydrogenated ketone resins and carbonyl- and ring-hydrogenated ketone-aldehyde resins based on aromatic ketones and polyisocyanates**

- 5 The invention relates to tin-free reaction products of hydroxyl-containing, carbonyl-hydrogenated ketone and ketone-aldehyde resins and also hydrogenated ketone-aldehyde resins based on aromatic ketones and polyisocyanates, to a process for preparing them and to their use, particularly in coating materials and adhesives.
- 10 Ketone-aldehyde resins are used in coating materials as, for example, a film-forming additive component in order to enhance certain properties such as initial drying rate, gloss, hardness or scratch resistance. Normally ketone-aldehyde resins possess hydroxyl groups and can therefore be crosslinked using, for example, polyisocyanates or amine resins. In physically or oxidatively drying coating or adhesive systems, in contrast, there is no buildup of polymer
- 15 through crosslinking of these resins. Owing to the uncrosslinked and hence relatively low molecular mass fractions, therefore, coatings of this kind often possess a low resistance toward, for example, gasoline, chemicals or solvents.

The abovementioned disadvantages can be mitigated by increasing the molecular weight of

20 the ketone-aldehyde resins. As a result of the increase in molecular weight there is a significant rise in the melting range and/or softening range, which, although beneficial to the initial drying rate and the aforementioned resistance properties of coating materials or adhesives, may impact negatively on the preparation of high-quality products, as for example in respect of the color number of the resins. In addition to this the favorable solubility

25 properties and rheological properties of the resins are adversely affected.

Moreover, as a result of irradiation, for example, the carbonyl groups are subject to classic degradation reactions such as those of Norrish type I or II (Laue, Plagens, Namen- und Schlagwort-Reaktionen der Organischen Chemie [Name and Keyword Reactions] , Teubner

30 Studienbücher, Stuttgart, 1995).

O.Z. 6375

2

The use of non-modified ketone-aldehyde resins or ketone resins is therefore out of the question for high-quality applications in, for example, the exterior sector, where a high level of resistance properties, particularly with respect to weathering and heat, is required. Similarly unsatisfactory weathering properties are possessed by phenolic resins of the novolak type or  
5 natural resins.

The conversion of the carbonyl groups into secondary alcohols by hydrogenation ketone-aldehyde resins has long been practiced (DE 8 70 022, DE 32 41 735, JP 11012338). One typical and known product is Kunstharz SK from Degussa AG. The use of carbonyl- and ring-  
10 hydrogenated ketone-aldehyde resins based on ketones containing aromatic groups is likewise possible. A resin of this kind is described in DE 33 34 631. The OH number of such products, at more than 200 mg KOH/g, is very high.

The reaction between isocyanate groups and hydroxyl groups is normally accelerated using  
15 catalysts. Because of numerous advantages, such as reaction kinetics or catalyst system stability even on prolonged heat exposure, for example, organotin compounds, such as dibutyltin dilaurate, for example, have become established. The industry, however, is being urged to replace these catalysts on environmental and toxicological grounds.

20 WO 03/091307 (EP 1 361 236) describes the preparation and use of polyurethane resins which are the reaction product of at least one diisocyanate and a group of components containing isocyanate-reactive groups, said group being composed of

- a) a 1st group of one or more polyetherpolyols
- b) a 2nd group of one or more polyhydroxylated resins, selected from the group  
25 consisting of hard ketonic resins, polyester resins, acrylic-styrene copolymers, polyacrylates, rosin derivatives and terpene-phenolic resins,
- c) optionally a 3rd group of one or more polyols having a molecular weight  $\leq 800$  g/mol, and
- d) at least one amine and a reaction terminator,

30 the ratio of the equivalent weights of the diisocyanate components and of the components which possess isocyanate-reactive groups being chosen such that substantially all of the

O.Z. 6375

3

isocyanate groups of the diisocyanates are present in the form of reaction product with one of the stated isocyanate-reactive functional groups.

The reaction products on which the present invention is based contain no polyethers, amines  
5 and no chain terminators. The reaction regime as well is different. Accordingly the products obtained there are not comparable with the products of the present invention. Since, obviously, dibutyltin dilaurate is used as catalyst, an environmental and toxicological risk can be assumed as well.

10 EP 1 229 090 describes similar polymers to those of WO 03/091307, and so the same arguments apply. Additionally that publication does not use carbonyl-hydrogenated ketone-aldehyde resin and/or carbonyl-hydrogenated ketone resin and/or carbonyl-hydrogenated and ring-hydrogenated ketone-aldehyde resin based on aromatic ketones.

15 EP 107 097 describes hotmelt adhesives composed of a mixture comprising prepolymeric isocyanate, a thermoplastic polymers and a low molecular weight synthetic resin, characterized in that the mixture comprises the following components:

- a) 20% to 90% by weight of prepolymeric isocyanate
- b) 0% to 75% by weight of a thermoplastic polyurethane
- 20 c) 0% to 50% of a low molecular weight synthetic resin from the group of the ketone resins and/or ketone-aldehyde condensation resins and/or hydrogenation products of acetophenone condensation resins.

In contrast to the products used in EP 107 097 the present invention does not use any  
25 thermoplastic polyurethane. Moreover, it uses hydrogenated resins, especially carbonyl-hydrogenated ketone-aldehyde resins and/or carbonyl-hydrogenated ketone resins and/or carbonyl-hydrogenated and ring-hydrogenated ketone-aldehyde resins based on aromatic ketones. Hydrogenated aldol homocondensates of acetophenone as described in EP 107 097 are explicitly not claimed.

O.Z. 6375

4

DE 34 16 378 describes release coating mixtures using nonhydrogenated ketone-aldehyde resins, especially cyclohexanone-formaldehyde resins, as their main component.

High-melting resins based on hydrogenated ketone-aldehyde resins and diisocyanates and/or polyisocyanates for radiation-curing coating materials are described in DE 102004 020 740. Besides the fact that, therein, radiation-reactive solvents are used, which restrict the scope for use and prohibit use in non-radiation-curing applications, catalysts are used which contain tin, as well.

10 It was an object of the present invention to find tin-free reaction products, stable to hydrolysis, which improve the initial drying rate, hardness, gloss, solvent resistance, chemical resistance, and adhesion of coating systems and adhesives. The products ought to possess good thermal stability and weathering stability. Additionally the preparation ought to be able to be carried out within an optimized time frame from the economics standpoint.

15

Surprisingly it has been possible to achieve this object by using, in coating materials or adhesives, reaction products composed of the products of reaction of hydrogenated ketone resins, carbonyl-hydrogenated ketone-aldehyde resins and/or ring-hydrogenated and carbonyl-hydrogenated ketone-aldehyde resins based on aromatic ketones (aryl alkyl ketones) and diisocyanates or polyisocyanates having a melting range of above 140°C, and being tin-free. Excluded explicitly in this context are homo-aldol-condensation products (ketone resins) of acetophenone.

25 This reaction, which is normally catalyzed with organotin compounds, has surprisingly been catalyzed by the presence of other, tin-free compounds and, especially when bismuth organyls are used, leads to products of equal quality at similar reaction rates.

The tin-free reaction products of the invention are also stable to hydrolysis and resistant to chemicals and possess a high yellowing resistance. In coating materials or adhesives the reaction products generate high gloss, a good initial drying rate, and adhesion to different

30

O.Z. 6375

5

substrates such as metals, for example, and plastics such as polyethylene, polypropylene, or polycarbonate, for example, in conjunction with a high level of hardness.

The invention provides tin-free high-melting reaction products essentially comprising  
5 the product of reaction, with a melting range of above 140°C, of

- A) at least one carbonyl-hydrogenated ketone-aldehyde resin and/or hydrogenated ketone resin and/or carbonyl-hydrogenated and ring-hydrogenated ketone-aldehyde resin based on aromatic ketones  
with  
10 B) at least one aromatic, aliphatic and/or cycloaliphatic diisocyanate or polyisocyanate.

Explicitly excluded are homo-aldol-condensation products (ketone resins) of acetophenone.

Also provided by the invention is a reaction product, where mixtures of additional polymers  
15 C) and of component A) are subjected to polymer-analogous reaction with component B).

The invention further provides for the use of reaction products essentially comprising  
the product of reaction, with a melting range of above 140°C, of

- A) at least one carbonyl-hydrogenated ketone-aldehyde resin and/or hydrogenated ketone  
20 resin and/or carbonyl-hydrogenated and ring-hydrogenated ketone-aldehyde resin based on aromatic ketones  
with  
B) at least one aromatic, aliphatic and/or cycloaliphatic diisocyanate or polyisocyanate  
as a main component, base component or additive component in coating materials, adhesives,  
25 inks, polishes, glazes, stains, pigment pastes, filling compounds, cosmetics articles, sealants  
and/or insulants, particularly for the purpose of enhancing initial drying rate, adhesion  
properties, gloss, solvent resistance, chemical resistance and hardness.

Ketones suitable for preparing the hydrogenated ketone resins and carbonyl-hydrogenated  
30 ketone-aldehyde resins (component A)) include all ketones, especially acetone, acetophenone,  
ring-substituted acetophenone derivatives, such as hydroxy-, methyl-, ethyl-, tert-butyl- and

O.Z. 6375

6

cyclohexyl-acetophenone, 4-tert-butyl methyl ketone, methyl ethyl ketone, heptan-2-one, pentan-3-one, methyl isobutyl ketone, propiophenone, methyl naphthyl ketone, cyclopentanone, cyclododecanone, mixtures of 2,2,4- and 2,4,4-trimethylcyclopentanone, cycloheptanone and cyclooctanone, cyclohexanone and all alkyl-substituted cyclohexanones  
5 having one or more alkyl radicals, which contain in total from 1 to 8 carbon atoms, individually or in a mixture. Examples that may be mentioned of alkyl-substituted cyclohexanones include 4-tert-amylcyclohexanone, 2-sec-butylcyclohexanone, 2-tert-butylcyclohexanone, 4-tert-butylcyclohexanone, 2-methylcyclohexanone and 3,3,5-trimethylcyclohexanone.

10

Generally speaking, however, it is possible to use any of the ketones said in the literature to be suitable for ketone and ketone-aldehyde resins syntheses, generally any C-H-acidic ketones.

Preference is given to hydrogenated ketone resins based on 4-tert-butyl methyl ketone, cyclohexanone, 4-tert-butylcyclohexanone, 3,3,5-trimethylcyclohexanone or heptanone, alone  
15 or in a mixture of these ketones, but not based on acetophenone.

Preference is given to carbonyl-hydrogenated ketone-aldehyde resins based on acetophenone, 4-tert-butyl methyl ketone, cyclohexanone, 4-tert-butylcyclohexanone, 3,3,5-trimethyl-  
20 cyclohexanone or heptanone, alone or in a mixture of these ketones.

As the aldehyde component of the carbonyl-hydrogenated ketone-aldehyde resins (component A)) suitability is possessed in principle by branched or unbranched aldehydes, such as formaldehyde, acetaldehyde, n-butyraldehyde and/or isobutyraldehyde, valeraldehyde and also  
25 dodecanal, for example. Generally speaking it is possible to use any of the aldehydes said in the literature to be suitable for ketone-aldehyde resin syntheses. Preference, however, is given to using formaldehyde, alone or in mixtures.

The required formaldehyde is normally used in the form of an aqueous or alcoholic (e.g.,  
30 methanol or butanol) solution with a strength of from about 20% to 40% by weight. Other use forms of the formaldehyde, including for example the use of para-formaldehyde or trioxane,

O.Z. 6375

7

are likewise possible. Aromatic aldehydes, such as benzaldehyde, may likewise be present as a mixture with formaldehyde.


Starting compounds used with particular preference for the carbonyl-hydrogenated ketone-aldehyde resins of component A) include acetophenone, 4-tert-butyl methyl ketone, cyclohexanone, 4-tert-butylcyclohexanone, 3,3,5-trimethylcyclohexanone and heptanone, alone or in a mixture, and formaldehyde.

To a minor extent it is possible to use nonhydrogenated ketone-aldehyde resins, which then, however, possess lower light fastness properties.

The resins from ketone or from ketone and aldehyde are hydrogenated with hydrogen at pressures of up to 300 bar in the presence of a catalyst. In the course of this reaction the carbonyl group of the ketone resin or ketone-aldehyde resin is converted into a secondary hydroxyl group. Depending on the reaction conditions some of the hydroxyl groups may be eliminated, to give methylene groups. Further moieties, such as any double bonds present, for example, may likewise be hydrogenated in this way.

This is illustrated by the following schema:

20



25

$$n = k + m$$

Ketones suitable for preparing the carbonyl-hydrogenated and ring-hydrogenated ketone-aldehyde resins (component A)) include any ketones which besides C-H-acidic protons possess aromatic groups, especially aryl alkyl ketones such as methyl naphthyl ketone, acetophenone and/or its derivatives, such as, for example, ring-substituted acetophenone derivatives, such as hydroxy-, methyl-, ethyl-, tert-butyl- and cyclohexyl-acetophenone.

O.Z. 6375

8

By appropriate choice of the hydrogenating conditions it is also possible to hydrogenate the hydroxyl groups, so that cycloaliphatic rings are formed. The ring-hydrogenated resins possess OH numbers of from 50 to 450 mg KOH/g, preferably from 100 to 350 mg KOH/g, more preferably from 150 to 300 mg KOH/g. The fraction of aromatic groups is below 50%,  
5 preferably below 30%, more preferably below 10%, by weight in each case. One process is described in DE 33 34 631.

Suitability as component B) is possessed by aromatic, aliphatic and/or cycloaliphatic diisocyanates and/or polyisocyanates.

10

Examples of diisocyanates are cyclohexane diisocyanate, methylcyclohexane diisocyanate, ethylcyclohexane diisocyanate, phenylene diisocyanate, propylcyclohexane diisocyanate, methyldiethylcyclohexane diisocyanate, tolylene diisocyanate, bis(isocyanatophenyl)methane, propane diisocyanate, butane diisocyanate, pentane diisocyanate, hexane diisocyanate, such as  
15 hexamethylene diisocyanate (HDI) or 1,5-diisocyanato-2-methylpentane (MPDI), heptane diisocyanate, octane diisocyanate, nonane diisocyanate, such as 1,6-diisocyanato-2,4,4-trimethylhexane or 1,6-diisocyanato-2,2,4-trimethylhexane (TMDI), nonane triisocyanate, such as 4-isocyanatomethyl-1,8-octane diisocyanate (TIN), decane diisocyanate and triisocyanate, undecane diisocyanate and triisocyanate, dodecane diisocyanates and  
20 triisocyanates, isophorone diisocyanate (IPDI), bis(isocyanatomethylcyclohexyl)methane (H<sub>12</sub>MDI), isocyanatomethyl methylcyclohexyl isocyanate, 2,5(2,6)-bis(isocyanatomethyl)bicyclo[2.2.1]heptane (NBDI), 1,3-bis(isocyanatomethyl)cyclohexane (1,3-H<sub>6</sub>-XDI) or 1,4-bis(isocyanatomethyl)cyclohexane (1,4-H<sub>6</sub>-XDI), alone or in a mixture.

25 Another preferred class of polyisocyanates as component B) are the compounds which have more than two isocyanate groups per molecule and are prepared by dimerization, trimerization, allophanatization, biuretization and/or urethanization of the simple diisocyanates, examples being the reaction products of these simple diisocyanates, such as IPDI, TMDI, HDI and/or H<sub>12</sub>MDI, for example, with polyhydric alcohols (e.g., glycerol,  
30 trimethylolpropane, pentaerythritol) and/or polyfunctional polyamines, or the triisocyanurates,

O.Z. 6375

9

which are obtainable by trimerizing the simple diisocyanates, such as IPDI, HDI and H<sub>12</sub>MDI, for example.

It is also possible to replace some of component A) by other hydroxy-functional polymers C) such as, for example, nonhydrogenated and/or ring-hydrogenated phenyl-aldehyde resins, hydroxy-functional nonhydrogenated ketone-aldehyde resins, hydroxy-functional polyesters and/or polyacrylates. In that case it is possible to subject mixtures of these polymers C) with component A) directly to polymer-analogous reaction with component B). In contradistinction to the "pure" resins of component A) it is possible by this means to adjust certain properties, such as flexibility or hardness, more effectively. The other hydroxy-functional polymers generally possess molecular weights Mn of between 200 and 10 000 g/mol, preferably between 300 and 5000 g/mol.

In order to accelerate the reaction for preparing the resins from A) and B) and optionally C) a tin-free catalyst is used. Suitable tin-free compounds are in principle all those which accelerate an OH/NCO reaction.

Catalysts based on the metals bismuth, zirconium, iron or aluminum are particularly suitable, such as carboxylates, chelates and complexes, for example.

20

The same applies to purely organic catalysts such as tertiary amines, examples being 1,4-diazabicyclo[2.2.2]octane (DABCO), 1,8-diazabicyclo[5.4.0]undec-7-ene (DBU), N,N-dimethylcyclohexylamine (DMCA) or 1,5-diazabicyclo[2.3.0]non-5-ene (DBN).

25 Surprisingly it has been found that catalysts containing bismuth provide very great acceleration of the reaction without altering other properties, such as rheological behavior, for example. After the end of the reaction the catalysts remain in the reaction product and can where appropriate be stabilized in a suitable way. Stabilization by means of monocarboxylic or dicarboxylic acids has proven particularly effective. It is also possible, though, to use any of the compounds said in the literature to be suitable for stabilizing metals.

30

O.Z. 6375

10

The melting range of the product of the tin-free preparation reaction of A) and B) and optionally C) is above 140°C, preferably above 145°C, more preferably above 150°C.

The amounts of A) and B) and, where used, C) are chosen such that 1 mol of the resin  
5 (component A)) or 1 mol of the mixture of A) and C), based on  $M_n$ , and from 0.2 to 15 mol, preferably from 0.25 to 10 mol, in particular from 0.3 to 4 mol of components B) are used.

The preparation of the resins on which the invention is based takes place in the melt or in solution in a suitable organic solvent of component A).

10

For this purpose in one preferred embodiment I

component B) is added in the presence of a suitable catalyst to the solution or melt of component A).

15 The temperature of the reaction is chosen according to the reactivity of component B). Temperatures which have been found appropriate are those between 30 and 150°C, preferably between 50 and 140°C. The reaction also takes place, though less preferably, at room temperature.

20 It has proven advantageous to react 1 mol of component A) - based on  $M_n$  - with from 0.2 to 15 mol, preferably from 0.25 to 10 mol, in particular from 0.3 to 4 mol of the isocyanate component B).

The solvent present where appropriate can, if desired, be separated off after the end of the  
25 reaction, in which case the product of the invention is generally a powder.

In one preferred embodiment II

component B) is added in the presence of a suitable catalyst to the solution or melt of component A) and the hydroxy-functional polymer C), such as nonhydrogenated and/or ring-  
30 hydrogenated phenyl-aldehyde resins, hydroxy-functional, nonhydrogenated ketone-aldehyde resins, hydroxy-functional polyesters and/or polyacrylates, for example.

O.Z. 6375

11

The temperature of the reaction is chosen according to the reactivity of component B). Temperatures which have been found appropriate are those between 30 and 150°C, preferably between 50 and 140°C. The reaction also takes place, though less preferably, at room temperature.

5

It has proven advantageous to react 1 mol of the sum of components A) and C) - based on  $M_n$  - with from 0.2 to 15 mol, preferably from 0.25 to 10 mol, in particular from 0.3 to 4 mol of the isocyanate component B).

- 10 The solvent present where appropriate can, if desired, be separated off after the end of the reaction, in which case the product of the invention is generally a powder.

The examples which follow are intended to illustrate the invention that has been made, though not to restrict it in its scope of application:

15

**Example 1 for the preparation of a reaction product:**

- The synthesis takes place by reacting 400 g of a carbonyl-hydrogenated resin formed from acetophenone and formaldehyde (OHN = 240 mg KOH/g (acetic anhydride method),  $M_n \sim 1000$  g/mol (GPC against polystyrene standard), melting range 114 - 120°C) with 99.3 g  
20 of H<sub>12</sub>MDI (Vestanat EP H<sub>12</sub>MDI, Degussa AG) in the presence of 0.15% of Coscat 83 (based on resin, Caschem Catalysts) in 50% dilution with ethyl acetate in a three-necked flask equipped with stirrer, reflux condenser and temperature sensor under nitrogen at 55°C until an NCO number of less than 0.1 has been reached.

- 25 This gives a pale, clear solution having a dynamic viscosity of 2.6 Pa·s. The Gardner color number of the solution is 0.4. After storage at 60°C for 14 days the Gardner color number is 0.5, which within the bounds of the accuracy of the method can be considered unchanged and suggests high yellowing stability of the resin solution. After the solvent has been separated off a colorless powder is obtained which possesses a melting range of between 163 and 166°C.

O.Z. 6375

12

| Coating material                          | A    | I    |
|---|------|------|
| Nitrocellulose E 510 (65% in isopropanol) | 19.3 | 13.5 |
| Ethyl acetate                             | 23.2 | 19.5 |
| n-Butanol                                 | 5.0  | 5.0  |
| Methoxypropanol                           | 2.5  | 2.5  |
| Vestinol AH                               | 2.5  | 2.5  |
| Resin from example 1                      | -    | 7.5  |
| Total                                     | 52.5 | 50.5 |

Resin solutions A and I were applied using a doctor blade to a glass plate and also to various plastic plates and metal. The wet film thickness was 100  $\mu\text{m}$ . After 14 days under standard conditions (23°C, 50% relative humidity), the gloss and adhesion of the films were measured.

#### Film properties:

| Coating material | FT [ $\mu$ ] | Gloss 60° angle (substrate: pine) |
|------------------|--------------|-----------------------------------|
| A                | 22 – 26      | 69                                |
| I                | 26 – 33      | 92                                |

#### Blade scratch adhesion to various substrates:

| Coating material | Glass | ABS | PE | PVC | PC | Metal |
|------------------|-------|-----|----|-----|----|-------|
| A                | 0     | 0   | 10 | 10  | 10 | 2     |
| I                | 0     | 0   | 8  | 5   | 2  | 0     |

10

0 = very good adhesion; 10 = no adhesion

#### Abbreviations

ABS: Acrylonitrile-butadiene-styrene copolymer

PC : Polycarbonate

O.Z. 6375

13

PE: Polyethylene

PVC: Polyvinyl chloride

FT: Film thickness

23443-955

14

CLAIMS:

1. A tin-free high-melting reaction product essentially comprising the product of reaction, with a melting range of above 140°C, of
- A) at least one carbonyl-hydrogenated ketone-aldehyde resin and/or hydrogenated ketone resin and/or carbonyl-hydrogenated and ring-hydrogenated ketone-aldehyde resin based on aromatic ketones
- with
- B) at least one aromatic, aliphatic and/or cycloaliphatic diisocyanate or polyisocyanate.
- 10 2. A tin-free high-melting reaction product essentially comprising the product of reaction, with a melting range of above 140°C, of
- A) at least one carbonyl-hydrogenated ketone-aldehyde resin and/or hydrogenated ketone resin and/or carbonyl-hydrogenated and ring-hydrogenated ketone-aldehyde resin based on aromatic ketones
- 15 with
- B) at least one aromatic, aliphatic and/or cycloaliphatic diisocyanate or polyisocyanate
- and
- C) at least one further, hydroxy-functionalized polymer.
- 20 3. A reaction product as claimed in claim 1 or 2, wherein C-H-acetic ketones are used in component A).

23443-955

15

4. A reaction product as claimed in any one of claims 1 to 3, wherein in the carbonyl-hydrogenated ketone-aldehyde resins of component A), ketones selected from

acetone, acetophenone, ring-substituted acetophenone derivatives, 4-  
5 tert-butyl methyl ketone, methyl ethyl ketone, heptan-2-one, pentan-3-one, methyl isobutyl ketone, propiophenone, methyl naphthyl ketone, cyclopentanone, cyclododecanone, mixtures of 2,2,4- and 2,4,4-trimethylcyclopentanone, cycloheptanone and cyclooctanone, cyclohexanone and all alkyl-substituted cyclohexanones having one or more alkyl radicals, which contain in total from 1 to 8  
10 carbon atoms, individually or in a mixture, are used.

5. A reaction product as claimed in claim 4, wherein the ring-substituted acetophenone derivative is hydroxy-, methyl-, ethyl-, tert-butyl- or cyclohexyl-acetophenone.

6. A reaction product as claimed in any one of claims 1 to 5, wherein in the  
15 carbonyl-hydrogenated ketone-aldehyde resins of component A), alkyl-substituted cyclohexanones having one or more alkyl radicals containing in total from 1 to 8 carbon atoms, individually or in a mixture, are used as starting compounds.

7. A reaction product as claimed in claim 6, wherein 4-tert-  
20 amylcyclohexanone, 2-sec-butylcyclohexanone, 2-tert-butylcyclohexanone, 4-tert-butylcyclohexanone, 2-methylcyclohexanone and/or 3,3,5-trimethylcyclohexanone are used.

8. A reaction product as claimed in any one of claims 1 to 7, wherein in the aldehyde component of the carbonyl-hydrogenated ketone-aldehyde resins in component A), formaldehyde, acetaldehyde, n-butyraldehyde and/or  
25 isobutyraldehyde, valeraldehyde or dodecanal, alone or in mixtures, are used.

23443-955

16

9. A reaction product as claimed in claim 8, wherein formaldehyde and/or para-formaldehyde and/or trioxane are used.
10. A reaction product as claimed any one of claims 1 to 9, wherein carbonyl hydrogenation products of the resins formed from acetophenone, 4-tert-butyl methyl ketone, cyclohexanone, 4-tert-butylcyclohexanone, 3,3,5-trimethylcyclohexanone or heptanone, alone or in a mixture, and formaldehyde are used as component A).
11. A reaction product as claimed in any one of claims 1 to 10, wherein the hydrogenated ketone resins of component A) comprise ketones selected from acetone, 4-tert-butyl methyl ketone, methyl ethyl ketone, heptan-2-one, pentan-3-one, methyl isobutyl ketone, propiophenone, cyclopentanone, cyclododecanone, mixtures of 2,2,4- and 2,4,4-trimethylcyclopentanone, cycloheptanone and cyclooctanone, cyclohexanone and all alkyl-substituted cyclohexanones having one or more alkyl radicals, which contain in total from 1 to 8 carbon atoms, individually or in a mixture.
12. A reaction product as claimed in claim 11, wherein cyclohexanone, 4-tert-amylcyclohexanone, 2-sec-butylcyclohexanone, 2-tert-butylcyclohexanone, 4-tert-butylcyclohexanone, 2-methylcyclohexanone and/or 3,3,5-trimethylcyclohexanone are used.
13. A reaction product as claimed in any one of claims 1 to 12, wherein aryl alkyl ketones are used in the carbonyl-hydrogenated and ring-hydrogenated ketone-aldehyde resins of component A).
14. A reaction product as claimed in any one of claims 1 to 13, wherein the carbonyl-hydrogenated and ring-hydrogenated ketone-aldehyde resins of component A) comprise ketones selected from acetophenone, ring-substituted acetophenone derivatives, and methyl naphthyl ketone.

23443-955

17

15. A reaction product as claimed in claim 14, wherein the ring-substituted acetophenone derivative is hydroxy-, methyl-, ethyl-, tert-butyl- or cyclohexyl-acetophenone.

16. A reaction product as claimed in any one of claims 1 to 15, wherein  
5 formaldehyde, acetaldehyde, n-butyraldehyde and/or isobutyraldehyde, valeraldehyde or dodecanal, alone or in mixtures, are used in the aldehyde component of the carbonyl-hydrogenated and ring-hydrogenated ketone-aldehyde resins of component A).

17. A reaction product as claimed in any one of claims 1 to 16, wherein in  
10 component B), diisocyanates selected from cyclohexane diisocyanate, methylcyclohexane diisocyanate, ethylcyclohexane diisocyanate, phenylene diisocyanate, propylcyclohexane diisocyanate, methyldiethylcyclohexane diisocyanate, tolylene diisocyanate, bis(isocyanatophenyl)methane, propane diisocyanate, butane diisocyanate, pentane diisocyanate, hexane diisocyanate,  
15 heptane diisocyanate, octane diisocyanate, nonane diisocyanate, nonane triisocyanate, decane diisocyanate and triisocyanate, undecane diisocyanate and triisocyanate, dodecane diisocyanates and triisocyanates, isophorone diisocyanate (IPDI), bis(isocyanatomethylcyclohexyl)methane (H<sub>12</sub>MDI), isocyanatomethyl methylcyclohexyl isocyanate, 2,5(2,6)-bis(isocyanatomethyl)bicyclo[2.2.1]heptane (NBDI),  
20 1,3-bis(isocyanatomethyl)cyclohexane (1,3-H<sub>6</sub>-XDI) or 1,4-bis(isocyanatomethyl)cyclohexane (1,4-H<sub>6</sub>-XDI), alone or in mixtures, are used.

18. A reaction product as claimed in claim 17, wherein the hexane diisocyanate is hexamethylene diisocyanate (HDI) or 1,5-diisocyanato-2-methylpentane (MPDI).

25 19. A reaction product as claimed in claim 17, wherein the nonane diisocyanate is 1,6-diisocyanato-2,4,4-trimethylhexane or 1,6-diisocyanato-2,2,4-trimethylhexane (TMDI).

23443-955

18

20. A reaction product as claimed in claim 17, wherein the nonane triisocyanate is 4-isocyanatomethyl-1,8-octane diisocyanate (TIN).
21. A reaction product as claimed in any one of claims 1 to 20, wherein polyisocyanates prepared by dimerization, trimerization, allophanatization, biuretization and/or urethanization of simple diisocyanates are used as component B).
22. A reaction product as claimed in any one of claims 1 to 21, wherein isocyanates based on IPDI, TMDI, H<sub>12</sub>MDI and/or HDI are used as component B).
23. A reaction product as claimed in any one of claims 1 to 22, wherein 1 mol of component A), based on M<sub>n</sub>, and from 0.2 to 15 mol of component B) are used.
24. A reaction product as claimed in claim 23, wherein 0.25 to 10 mol of component B) are used.
25. A reaction product as claimed in claim 23, wherein 0.3 to 4 mol of component B) are used.
26. A reaction product as claimed in any one of claims 1 to 25, wherein the melting range of the reaction product of A) and B) is above 140°C.
27. A reaction product as claimed in any one of claims 1 to 25, wherein the melting range of the reaction product of A) and B) is above 145°C.
28. A reaction product as claimed in any one of claims 1 to 25, wherein the melting range of the reaction product of A) and B) is above 150°C.
29. A reaction product as claimed in any one of claims 1 to 28, wherein polyesters, polyacrylates, nonhydrogenated ketone-aldehyde resins and/or

23443-955

19

nonhydrogenated and/or ring-hydrogenated phenyl-aldehyde resins are used as hydroxy-functionalized polymers C).

30. The reaction product as claimed in any one of claims 1 to 29, where mixtures of the polymers C) and component A) are subjected to polymer-analogous  
5 reaction with component B).

31. A process for preparing a reaction product essentially comprising the product of reaction, with a melting range of above 140°C, of

A) at least one carbonyl-hydrogenated ketone-aldehyde resin and/or hydrogenated ketone resin and/or carbonyl-hydrogenated and ring-hydrogenated  
10 ketone-aldehyde resin based on aromatic ketones

with

B) at least one aromatic, aliphatic and/or cycloaliphatic diisocyanate or polyisocyanate

and if desired,

15 C) at least one further, hydroxy-functionalized polymer by reacting A) and B) and, where used, C) at temperatures from 20 to 150°C in the presence of a catalyst which contains no tin.

32. A process as claimed in claim 31, wherein compounds of claims 2 to 21 are used.

20 33. A process as claimed in claim 32, wherein compounds comprising zirconium, iron, bismuth and/or aluminum are used as catalyst.

34. A process as claimed in claim 33, wherein compounds comprising bismuth are used as catalyst.

23443-955

20

35. A process as claimed in any one of claims 31 to 34, wherein the catalyst is stabilized.
36. A process as claimed in claim 35, wherein the catalyst is stabilized with monocarboxylic and/or dicarboxylic acids.
- 5 37. A process as claimed in claim 31, wherein organic compounds are used as catalyst.
38. A process as claimed in claim 37, wherein tertiary amines are used as catalyst.
39. A process as claimed in claim 38, wherein 1,4-diazabicyclo [2.2.2]  
10 octane (DABCO), 1,8-diazabicyclo[5.4.0]undec-7-ene (DBU),  
N,N-dimethylcyclohexylamine (DMCA) and/or 1,5-diazabicyclo[2.3.0]non-5-ene  
(DBN) are used.
40. A process as claimed in any one of claims 31 to 39, wherein component  
15 B is added in the presence of the tin-free catalyst to the solution or melt of component  
A).
41. A process as claimed in any one of claims 31 to 40, wherein component  
B is added in the presence of the tin-free catalyst to the solution or melt of component  
A) and the hydroxy-functional polymer C).
42. A process as claimed in any one of claims 31 to 41, wherein reaction is  
20 carried out at temperatures between 30 and 150°C.
43. A process as claimed in any one of claims 31 to 41, wherein reaction is  
carried out at temperatures between 50 and 140°C.
44. The use of a reaction product as claimed in any one of claims 1 to 30 as  
a main component, base component or additive component in a coating material,

23443-955

21

adhesive, ink, polish, glaze, stain, pigment paste, filling compound, cosmetics article, sealant and/or insulant.

45.           The use of a reaction product as claimed in any one of claims 1 to 30 as a main component, base component or additive component in a coating material,  
5 adhesive, ink, polish, glaze, stain, pigment paste, filling compound, cosmetics article, sealant and/or insulant for the purpose of improving the adhesion properties and hardness.