

(12) PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. AU 199864437 B2
(10) Patent No. 731843

(54) Title
Treated horticultural substrates

(51)⁷ International Patent Classification(s)
A01N 059/06

(21) Application No: **199864437** (22) Application Date: **1998.03.02**

(87) WIPO No: **WO98/38866**

(30) Priority Data

(31) Number	(32) Date	(33) Country
08/812301	1997.03.05	US
08/972648	1997.11.18	US

(43) Publication Date : **1998.09.22**

(43) Publication Journal Date : **1998.11.26**

(44) Accepted Journal Date : **2001.04.05**

(71) Applicant(s)
Engelhard Corporation; The United States of America, as represented by The Secretary of Agriculture

(72) Inventor(s)
Dennis G. Sekutowski; Gary J. Puterka; D. Michael Glenn

(74) Agent/Attorney
GRIFFITH HACK,GPO Box 1285K,MELBOURNE VIC 3001

(56) Related Art
US 5414954
US 5122518
JP 60-149508



(51) International Patent Classification⁶ : A01N 59/06 // (A01N 59/06, 55:00, 25:04)		A1	(11) International Publication Number: WO 98/38866 (43) International Publication Date: 11 September 1998 (11.09.98)
(21) International Application Number: PCT/US98/03965			(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).
(22) International Filing Date: 2 March 1998 (02.03.98)			
(30) Priority Data: 08/812,301 5 March 1997 (05.03.97) US 08/972,648 18 November 1997 (18.11.97) US			
(71) Applicants: ENGELHARD CORPORATION [US/US]; 101 Wood Avenue, P.O. Box 770, Iselin, NJ 08830-0770 (US). THE UNITED STATES OF AMERICA, as represented by THE SECRETARY OF AGRICULTURE [US/US]; U.S. Dept. of Agriculture, Washington, DC 20250 (US).			Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(72) Inventors: SEKUTOWSKI, Dennis, G.; 1 Edna Horn Drive, Stockton, NJ 08559 (US). PUTERKA, Gary, J.; Route 1, Box 279, Billmyer Road, Shepherdstown, WV 25443 (US). GLENN, D., Michael; P.O. Box 1408, Shepherdstown, WV 25443 (US).			
(74) Agents: MILLER, Stephen, I. et al.; Engelhard Corporation, 101 Wood Avenue, P.O. Box 770, Iselin, NJ 08830-0770 (US).			

(54) Title: TREATED HORTICULTURAL SUBSTRATES

(57) Abstract

Disclosed are horticultural substrates coated with a particulate membrane and a method for controlling pests and providing enhanced horticultural effect by applying a particulate membrane to the surface of the horticultural substrate.

TREATED HORTICULTURAL SUBSTRATESCross-reference to Related Applications

This application is a continuation-in-part of U.S. Patent Application No. 08/812301, filed March 5, 1997, 5 which is incorporated herein by reference for its teachings related to the invention disclosed herein.

Field of the Invention

The present invention is directed to horticultural substrates treated with a particulate membrane and 10 methods for controlling pests associated with such substrates and for providing enhanced horticultural effects.

Background of the Invention

The prior art has discussed the use of certain inert 15 particulate solids as insecticides, see for example; Driggers, B.F., "Experiments with Talc and Other Dusts Used Against Recently Hatched Larvae of the Oriental and Codling Moths," *J. Econ. Ent.*, 22 327-334 (1929); Hunt, C.R., "Toxicity of Insecticide Dust Diluents and Carriers 20 to Larvae of the Mexican Bean Beetle," *J. Econ. Ent.*, 40 215-219 (1947); P. Alexander, J. A. Kitchener and H. V. A. Briscoe, "Inert Dust Insecticides," Parts I, II, and III, *Ann. Appl. Biol.*, 31 143-159, (1944); and US patents 3,159,536 (1964) and 5,122,518 (1992), each of which is 25 incorporated herein by reference with regard to its teachings relating to particulate materials.

Plant diseases are caused by various pathogens, e.g., fungi, bacteria and virus, and these diseases have generally been controlled commercially by the use of 30 chemical pesticides. For example, commercial fungicides

generally belong to the following types of chemical compounds: inorganic (copper or sulfur based), organic (anilines, anilides, dithiocarbamates, halogen compounds and heterocyclic nitrogen compounds), antibiotics and 5 biologicals. Chemically toxic fungicides and bactericides are often formulated with inert particulates. Inert particulates, however, have been shown to be ineffective toward these plant pests when applied by themselves (see W. O. Cline and R. D. Milholland, "Root Dip Treatments 10 for Controlling Blueberry Stem Blight Caused by *Botryosphaeria dothidea* in Container-Grown Nursery Plants," *Plant Disease* 76 136-138 (1992)). Furthermore, not only have inert particulates been shown to be ineffective in plant disease control, but it has been 15 reported by S. K. Bhattacharyya and M. K. Basu, "Kaolin Powder as a Fungal Carrier," *Appl. Envir. Microbio.* 44 751-753 (1982) that kaolin powder may be used to carry and preserve an *Aspergillus* sp. for at least 90 days. In another report, S. M. Lipson and G. Stotzky, "Effect of 20 Kaolinite on the Specific Infectivity of Reovirus," *FEMS Micr. Let.* 37 83-88 (1986), it was reported that the infectivity of enteric viruses (e.g., poliovirus, rotavirus and reovirus) is prolonged when these viruses are adsorbed on naturally occurring particulates 25 (sediments, clay materials) in terrestrial and aquatic environments.

O. Ziv and R.A. Frederiksen, "The Effect of Film-forming Anti-transpirants on Leaf Rust and Powdery Mildew Incidence on Wheat," *Plant Path.* 36 242-245 (1987); M. 30 Kamp, "Control of *Erysiphe cichoracearum* on *Zinnia elegans*, with a Polymer-based Antitranspirant," *Hort. Sci.* 20 879-881 (1985); and J. Zekaria-Oren and Z. Eyal, "Effect of Film-forming Compounds on the Development of Leaf Rust on Wheat Seedlings," *Plant Dis.* 75 231-234

(1991)) discuss the use of anti-transpirant polymer films to control disease. Of course, the use of anti-transpirants is undesirable because they reduce the exchange of necessary gases on the surface of living 5 plants.

For prior art regarding horticultural effects see, for example, Byers, R.E., K.S. Yoder, and G. E. Mattus, "Reduction in Russetting of 'Golden Delicious' Apples with 2,4,5-TP and Other Compounds," *HortScience* 18:63-10 65); Byers, R.E., D.H. Carbaugh, and C.N. Presley, "'Stayman' Fruit Cracking as Affected by Surfactants, Plant Growth Regulators, and Other Chemicals," *J. Amer. Soc. Hort. Sci.* 115:405-411 (1990); Durner, E.F., and T.J. Gianfagna, "Peach Pistil Growth Inhibition and 15 Subsequent Bloom Delay by Midwinter Bud Whitewashing," *HortScience* 25:1222-1224 (1990); and M.N. Westwood, Temperate-zone Pomology, page 313 W.H. Freeman and Co. (1978).

Therefore, there is still a need for cost effective 20 inert, nontoxic improved agents for pest control and for enhanced horticultural effects and methods for their use.

Summary of the Invention

This invention relates to horticultural substrates where the surface of said substrates is coated with a 25 particulate membrane and to methods for pest control and enhanced horticultural effects by forming said membrane on the surface of the horticultural substrate.

In one embodiment, this invention relates to coated substrates comprising a horticultural substrate wherein 30 the surface of said substrate is coated with a membrane comprising one or more particulate layers, said layers comprising one or more particulate materials, said particulate materials being finely divided, and wherein

said membrane allows for the exchange of gases on the surface of said substrate.

In another embodiment, this invention relates to a method for pest control on horticultural substrates which 5 comprises forming on the surface of said substrate a membrane comprising one or more particulate layers, said layers comprising one or more particulate materials, said particulate materials being finely divided, and wherein said membrane allows for the exchange of gases on the 10 surface of said substrate.

In still another embodiment, this invention relates to a method for providing enhanced horticultural effects which comprises forming on the surface of a horticultural substrate a membrane comprising one or more particulate 15 layers, said layers comprising one or more particulate materials, said particulate materials being finely divided, and wherein said membrane allows for the exchange of gases on the surface of said substrate.

Brief Description of the Drawings

20 Figure 1 is a scanning electron micrograph of an untreated petunia petal.

Figure 2 is a scanning electron micrograph of a petunia petal coated with a membrane of octylsilane treated calcined kaolin particles.

25 Figure 3 is a scanning electron micrograph of a petunia petal coated with a membrane of vinyl silane treated calcined kaolin particles.

Figure 4 is a scanning electron micrograph of a petunia petal coated with a membrane of 30 methylethoxysiloxane treated calcined kaolin particles.

Figure 5 is a scanning electron micrograph of a petunia petal coated with a membrane of a calcined kaolin treated with a siloxane material.

Figure 6 is a scanning electron micrograph of a

petunia petal coated with a membrane of a calcined kaolin.

Detailed Description of the Invention

The horticultural substrates to which this invention relates are agricultural and ornamental crops, including those selected from the group consisting of fruits, vegetables, trees, flowers, grasses, seeds, roots, and landscape and ornamental plants.

The membranes of this invention comprise one or more particulate layers, said layers comprising one or more particulate materials, said particulate materials being finely divided.

The finely divided particulate materials which make up the particulate membrane of this invention may be hydrophilic or hydrophobic materials and the hydrophobic materials may be hydrophobic in and of themselves, e.g., mineral talc, graphite, and Teflon® or may be hydrophilic materials that are rendered hydrophobic by application of an outer coating of a suitable hydrophobic wetting agent (e.g., the particulate material has a hydrophilic core and a hydrophobic outer surface).

Typical particulate hydrophilic materials useful for the purposes of this invention include: minerals, such as calcium carbonate, talc, kaolin (both hydrous and calcined kaolins, with calcined kaolins being preferred), bentonites, clays, attapulgite, pyrophyllite, wollastonite, silica, feldspar, sand, quartz, chalk, limestone, precipitated calcium carbonate, diatomaceous earth and barytes; functional fillers such as microspheres (ceramic, glass and organic), aluminum trihydrate, pyrogenic silica, ceramic fibers and glass fibers; and pigments such as colorants or titanium dioxide.

The surfaces of such materials can be made

hydrophobic by addition of hydrophobic wetting agents. Many industrial mineral applications, especially in organic systems such as plastic composites, films, organic coatings or rubbers, are dependent upon just such 5 surface treatments to render the mineral surface hydrophobic; see, for example, Jesse Edenbaum, Plastics Additives and Modifiers Handbook, Van Nostrand Reinhold, New York, 1992, pages 497-500 which is incorporated herein by reference for teachings of such surface 10 treatment materials and their application. So-called coupling agents such as fatty acids and silanes are commonly used to surface treat solid particles as fillers or additives targeted to these industries. Such hydrophobic agents are well known in the art and common 15 examples include: chrome complexes such as Volvan® and Quilon® obtained from DuPont; organic titanates such as Tilcom® obtained from Tioxide Chemicals; organic zirconate or aluminate coupling agents obtained from Kenrich Petrochemical, Inc.; organofunctional silanes 20 such as Silquest® products obtained from Witco or Prosil® products obtained from PCR; modified silicone fluids such as the DM-Fluids obtained from Shin Etsu; and fatty acids such as Hystrene® or Industrene® products obtained from Witco Corporation or Emersol® products obtained from 25 Henkel Corporation (stearic acid and stearate salts are particularly effective fatty acids and salts thereof for rendering a particle surface hydrophobic).

Examples of preferred particulate materials suitable for the purposes of this invention that are commercially 30 available from Engelhard Corporation, Iselin, NJ are the siloxane treated calcined kaolins sold under the trademark Translink®, and stearic acid treated ground calcium carbonates commercially available from English China Clay under the trademarks Supercoat® and Kotamite®.

35 The term "finely divided" when utilized herein means

that the particulate materials have a median individual particle size below about 10 microns and preferably below about 3 microns and more preferably the median particle size is about one micron or less. Particle size and 5 particle size distribution as used herein are measured with a Micromeritics Sedigraph 5100 Particle Size Analyzer. Measurements were recorded in deionized water for hydrophilic particles. Dispersions were prepared by weighing 4 grams of dry sample into a plastic beaker 10 adding dispersant and diluting to the 80 ml mark with deionized water. The slurries were then stirred and set in an ultrasonic bath for 290 seconds. Typically, for kaolin 0.5% tetrasodium pyrophosphate is used as a dispersant; with calcium carbonate 1.0% Calgon T is used. 15 Typical densities for the various powders are programmed into the sedigraph, e.g., 2.58 g/ml for kaolin. The sample cells are filled with the sample slurries and the X-rays are recorded and converted to particle size distribution curves by the Stokes equation. The median 20 particle size is determined at the 50% level.

Preferably, the particulate material has a particle size distribution wherein up to 90% by weight of the particles have a particle size of under about 10 microns, preferably below about 3 microns and more preferably 25 about one micron or less.

The particulate materials particularly suitable for use in this invention are inert, nontoxic and hydrophobic.


As used herein "inert" particulate materials are 30 particles that are not physiological poisons, that is, the particulate materials of this invention do not, as their primary function, kill pests. While not being bound by theory, it is believed that the pest control of this invention is achieved primarily by prophylactic means 35 rather than primarily through the destruction of the

unwanted pests.

The particulate materials are preferably nontoxic meaning that in the limited quantities needed for effective pest control or enhanced horticultural effect 5 such materials are not considered harmful to horticultural substrate, animals, the environment, the applicator and the ultimate consumer.

The preferred particulate materials of the instant invention are hydrophobic. Hydrophobicity refers to the 10 physical property of a surface to dislike or repel water. Most mineral particle surfaces are hydrophilic, i.e., water liking. The terms hydrophobic and hydrophilic are not always accurately used in the literature and both are often confused with similar terms such as, lipophilic or 15 lipophobic, oleophilic or oleophobic, lyophilic or lyophobic, and polar or nonpolar. Hydrophobicity can be described in more quantitative terms by using contact angle measurements. The contact angle is defined by the equilibrium forces that occur when a liquid sessile drop 20 is placed on a smooth surface. The tangent to the surface of the convex liquid drop at the point of contact among the three phases, solid (S), liquid (L) and vapor (V) is the contact angle θ as illustrated in the following 25 figure.

25



The relationship between the surface tension of the solid-vapor (γ_{sv}), liquid-vapor (γ_{lv}) and solid-liquid (γ_{sl}) can be defined by the following Young's equation:

$$F = \gamma p \cos \theta$$

30 where F = wetting force; γ = liquid surface tension; and

p = wetting perimeter.

If the water droplet spreads out on the surface the contact angle is less than 90 degrees and the surface is hydrophilic. If the surface is hydrophobic then the 5 contact angle is greater than 90 degrees. Thus, 180 degrees is the maximum hydrophobicity that a surface can have.

Many surfaces change their surface energy upon contact with water (see J. Domingue, Amer. Lab, Oct 10 1990). Dynamic contact angle measurements provide both an advancing and receding contact angle. The advancing contact angle is a measurement of the surface hydrophobicity upon initial contact with a liquid, while the receding contact angle measures the hydrophobicity 15 after the surface has been wetted with a liquid. Thus, for the purposes of this invention, "hydrophobic" or "hydrophobicity," when used in reference to the particulate materials useful for the purposes of this invention, such particles may have either an advancing 20 and/or receding contact angle of greater than 90°. Preferred materials have receding contact angles of greater than 90°.

The dynamic contact angles referred to herein are based on a gravimetric principle of the Wilhelmy plate 25 technique and are determined by measurement on the Dynamic Contact Angle Instrument which can measure both advancing and receding contact angles of powdered samples. A dynamic contact angle analysis system (model DCA 315) from ATI Cahn Instruments Inc. was used for all 30 contact angle measurements referred to and reported herein. The surface tension (γ) of deionized water was determined with a standard platinum calibration plate. Powder samples were deposited on dual sided adhesive tape. The perimeter (p) of the tape was determined with a

-10-

caliper. The impregnated tape was placed in the DCA 315 and lowered and raised in the deionized water at a rate of 159 microns/second for two immersion cycles. The contact angles were determined from the advancing and 5 receding wetting hysteresis curves of the first immersion cycle. Most samples were prepared and run in duplicate and the results averaged. The data analysis was made with a WinDCA software for Windows diagnostic package from the manufacturer, ATI Cahn Instruments Inc.

10 Representative contact angle values for a variety of inert particulate materials are given in Table I. Although many of the powders listed are hydrophilic and have advancing and receding contact angles less than 90°, some hydrophobic particles as measured by the advancing 15 contact angle, for example talc, become hydrophilic upon wetting.

-11-

Table I

Contact Angle Values of Powders			
	Advancing Contact Angle (°)	Receding Contact Angle (°)	
5	Calcium Carbonate ¹	28.4	32.5
	Calcium Carbonate ²	37.8	38.1
10	Calcium Carbonate ³ (ST)	180	171.1
	Barytes ⁴	32.2	30.3
15	Mica ⁵	42.3	39.9
	Mica ⁶	31.5	25.0
20	Silica ⁷	38.5	38.2
	Diatomite ⁸	39.4	35.3
25	ATH ⁹	38.7	0
	Wollastonite ¹⁰	23.1	27.5
30	Wollastonite ¹¹	9.4	14.1
	Talc ¹²	180	12.8
35	Talc ¹³	159.2	11.5
	Feldspar ¹⁴	35.9	39.2
40	Nepheline	19.4	25.4
	Syenite ¹⁵		
45	Kaolin hydrous ¹⁶	29	30.1
	Kaolin calcined ¹⁷	26	20.5

30 ST= Surface Treated

1. Atomite[®] (ECC Int.) 2. GS 6532 (Georgia Marble) 3. Kotamite[®] (ECC Int.) 4. Bartex[®] 65 (Hitox) 5. WG 325 (KMG Minerals) 6. C-3000 (KMG Minerals) 7. Novacite[®] L-207A (Malvern Min Co.) 8. Diafil[®] 340 (CR Mineral Corp.) 9. Alcan[®] SF (Alcan Chemicals) 10. NYAD[®] 1250 (NYCO) 11. Wollastokup[®] (NYAD) 12. Vantalc[®] 6H (RT Vanderbilt) 13. Vertal[®] 710 (Luzenac Amer Inc.) 14. Minspar[®] 4 (K-T Feldspar Corp) 15. Minex[®] 10 (Unimin) 16. ASP[®] 900 (Engelhard Corp) 17. Satintone[®] W (Engelhard Corp)

Hydrophilic surfaces can be made hydrophobic by

40 addition of hydrophobic wetting agents as shown in Table II for hydrous and calcined kaolin. However, not all hydrophobic surface treatments render hydrophobicity to a particle as shown in Table II.

Table II

		Surface Treated Kaolin Particles			
		Hydrous Kaolin Advancing Angle (°)	Hydrous Kaolin Receding Angle (°)	Calcined Kaolin Advancing Angle (°)	Calcined Kaolin Receding Angle (°)
5	Surface Treatment (1%)				
	no treatment	31	30	26	21
	Stearic acid ¹	155.5	0	166	102
	Octyltriethoxysilane ²	158	0	180	180
	Vinyltriethoxysilane ³	120	22	164	140
10	polydimethylsiloxane ⁴ linear	27	26	24	26
	methylethoxysiloxane polymer ⁵	89	24	180	154
15	polydimethyl siloxane cyclic ⁶	112	45	155	154

1. Industrene 7018 (Witco) 2. A-137 (Witco) 3. A-151 (Witco) 4. L-45 (Witco) 5. A-272 (Witco) 6. CG-4491 (HULS America Inc.)

The preferred hydrophilic core particles are those, which when treated with a hydrophobic wetting agent and 20 are applied to the surface of a horticultural substrate, form a membrane on the substrate. Examples of such particles are calcium carbonate and kaolin. Calcined kaolin is preferred to hydrous kaolin.

As previously discussed, this invention relates to 25 horticultural substrates wherein the surface of said substrate is coated with a membrane comprising one or more particulate layers. This membrane allows for the exchange of gases on the surface of said substrate. The gases which pass through the membrane are those which are 30 typically exchanged through the surface skin of living plants. Such gases typically include water vapor, carbon dioxide, oxygen, nitrogen and volatile organics.

The portion of a substrate to be covered with said membrane is within the skill of the ordinary artesian. 35 Optimally, the substrate is fully covered with said membrane, and although diminished disease control and/or

horticultural effects may result, less than full substrate coverage is within the scope of this invention; preferably, however, the substrate is substantially covered. Reference is made to U.S. Serial No. 08/972,659 5 filed concurrently herewith on November 18, 1997, entitled "Method for Providing Enhanced Photosynthesis" and to U.S. Serial No. 08/972,653 filed concurrently herewith on November 18, 1997, entitled "Method for Protecting Surfaces from Arthropod Infestation" which are 10 incorporated herein by reference for their teachings regarding methods for insect control and improved photosynthesis. Preferably, the membranes of this invention are sufficiently continuous so as to provide effective control of disease. The membrane may have 15 imperfections such as gaps or voids, but such imperfections should not be so large as to materially affect the disease control of such membrane. Such gaps or voids typically will not exceed about 5 μ , and are preferably less than about 1 μ . In another preferred 20 embodiment, the membrane is water repellent. The membrane may be formed by applying one or more layers of finely divided particulate material until a membrane is formed of sufficient thickness and continuity to be an effective disease control barrier, i.e., the particles on the 25 surface of the substrate are so closely associated that pathogens are unable to penetrate the particulate coating and infect the underlying horticultural substrate. For example, this can typically be accomplished by applying in a uniform manner from about 25 up to about 3000 30 micrograms of particulate material/cm² of substrate for particles having specific density of around 2-3 g/cm³. In addition, environmental conditions such as wind and rain may reduce coverage of the membrane and, therefore, it is within the scope of this invention to apply the particles 35 one or more times during the growing season of said

horticultural crop so as to maintain the desired effect of invention.

This particulate membrane may be prepared by applying a slurry of finely divided particles in a volatile liquid such as water, a low boiling organic solvent or low boiling organic solvent/water mixture. One or more layers of this slurry can be sprayed or otherwise applied to the substrate. The volatile liquid is preferably allowed to evaporate between coatings.

Surfactants or dispersants may be useful in preparing an aqueous slurry of the particulate materials of this invention. The membrane of this invention may be hydrophilic or hydrophobic, but is preferably hydrophobic. Normal dusting of particles, aside from not being commercially practical on a large scale due to drift and inhalation hazards, is not effective at forming a membrane on a horticultural substrate suitable for disease control. The membrane of this invention may be formed, however, by carefully applying the finely divided particles to the substrate, e.g., with a paint brush. While not being bound by theory, it is believed that the one or more layers of finely divided particulate material form a membrane due to particle to particle cohesion of evenly distributed, closely associated particles.

The low boiling organic liquids useful in the present invention are preferably water-miscible and contain from 1 to 6 carbon atoms. The term "low boiling" as used herein shall mean organic liquids which have a boiling point generally no more than 100°C. These liquids enable the particulate solids to remain in finely divided form without significant agglomeration. Such low boiling organic liquids are exemplified by: alcohols such as methanol, ethanol, propanol, i-propanol, i-butanol, and the like, ketones such as acetone, methyl ethyl ketone and the like, and cyclic ethers such as

ethylene oxide, propylene oxide and tetrahydrofuran. Combinations of the above-mentioned liquids can also be employed. Methanol is the preferred low boiling organic liquid.

5 Low boiling organic liquids may be employed in applying the particles to form the membranes of this invention. Typically, the liquids are used in an amount sufficient to form a dispersion of the particulate material. The amount of liquid is typically up to about 10 30 volume percent of the dispersion, preferably from about 3 up to about 5 volume percent, and most preferably from about 3.5 to about 4.5 volume percent. The particulate material is preferably added to a low boiling organic liquid to form a slurry and then this slurry is 15 diluted with water to form an aqueous dispersion. The resulting slurry retains the particles in finely divided form wherein most of the particles are dispersed to a particle size of less than about 10 microns.

 This invention also provides methods for pest 20 control and enhanced horticultural effects by forming said membrane on the surface of the horticultural substrate. The foregoing discussions regarding i) said membrane being comprised of one or more layers of particulate material, ii) said particulate material being 25 finely divided, iii) said membrane allowing for the transpiration of water vapor from said substrate through said membrane, and iv) application techniques for applying said layers to the horticultural substrate, as well as the specific embodiments discussed herein, also 30 apply to these methods.

 The pests controlled by this invention refer to arthropods including insects, mites, spiders and related animals and diseases of various pathogens such as fungi, bacteria and virus. Diseases can be transmitted in a 35 number of ways such as wind currents, water splash and/or

arthropod transmission. Examples of diseases commonly caused by wind currents and water splash include: Fire blight (bacteria--*Erwinia amylovora*), apple scab (fungus--*Venturia inaequalis*), Potato Blight (fungus--

5 *Phytophthora infestans*), Soft rots (fungus--*Botrytis cinerea*), Leaf blight and leaf spot (bacteria--*Xanthomonas* sp.), and bacterial leaf spot and leaf blight (bacteria--*Pseudomonas* sp.). Examples of diseases commonly caused by arthropod transmission are the fungus

10 disease, Dutch Elm disease, of American Elm by the European elm beetle; the bacterial disease, Fire blight, of apples and pears by flies, beetles and other insects; the virus disease, Curly Top, of sugar beets by the beet leaf hopper. Disease control also applies to those

15 secondary infections of wound sites on a plant that results from arthropod feeding such as brown rot infection of stone fruits that results when the disease organism enters the plant through plum curculio feeding sites.

20 This invention can also provide the benefit of enhanced horticultural effects including improved color, smoother fruit surface, increased soluble solids, e.g., sugars, acidity, etc., reduced bark and fruit cracking, reduced plant temperature and reduced russetting.

25 The following examples are illustrative of embodiments of the invention and are not intended to limit the invention as encompassed by the claims forming part of the application.

EXAMPLE 1

30 This example demonstrates that coating a plant substrate with a membrane of finely divided particles greatly reduces the degree of infection as compared to a substrate not coated with a particulate membrane. Efficacy of various particulate membranes toward disease

control was demonstrated by screening evaluations of *Botrytis cinerea* on strawberry petals (*Fragaria x ananassa* Pucheene). All preparations in Tables III and IV were made by applying suspensions of the particles listed 5 in the table prepared by first dispersing 5 grams of the identified particle in 10 ml methanol which is then brought to 100 ml with deionized water. Petals were then sprayed with this suspension using a Paasche air brush to run off. The petals were allowed to air dry and then 10 10 μ l of *Botrytis* inoculum (3.6×10^7 spores/ml) was added over the petals. The petals were then incubated in a 100% humidity chamber for 24 hours.

Table III

Fungus Efficacy of surface treated and untreated particles			
Particle	% Infection after 24 hrs	Advancing Contact Angle (°)	Receding Contact Angle (°)
Control - no particles	88.9	-	-
Methanol	76.5	-	-
Kaolin hydrous [ST] ¹	73.0	155.5	0
Kaolin calcined ²	68.0	19.4	20.5
Kaolin hydrous ³	63.8	29	30.1
Kaolin calcined [ST] ⁴	62.0	166	102
Calcium Carbonates ⁵	57.0	28.4	32.5
Talc ⁶	49.3	180	12.8
Calcined Kaolin [ST] ⁷	44.7	146	128
Calcium Carbonate [ST] ⁸	36.8	180	171
Translink® 77	23.6	153	120

1. ASP® 900 (Engelhard Corporation) treated with stearate 2. Satintone® W (Engelhard Corporation) 3. ASP® 900 (Engelhard Corporation) 4. Satintone® W (Engelhard Corporation) treated with stearate 5. Atomite® (ECC Int.) 6. Vantalc® 6H (RT Vanderbilt) 7. Translink® 37 (Engelhard Corporation) 8. Kotamite® (ECC Int.) Data are the mean of 3 independent replications, each containing 10

strawberry petals.

5 Infection was measured by the presence of a necrotic lesion characteristic of a *Botrytis* infection. The data was analyzed by the Duncan's multiple range test ($P=0.05$) on the arcsine transformed percentages and are presented as untransformed mean for convenience).

EXAMPLE 2

10 Performing the same evaluations and comparing surface treated particles to untreated particles of calcined kaolin gave the results in Table IV.

Table IV

Fungus Efficacy of surface treated calcined kaolin					
	Particles	% Infection after 24 hrs	Advancing Contact Angle (°)	Receding Contact Angle (°)	Character of particle coating
15	Control - no particles	88	-	-	Figure 1
20	octylsilane treated ¹ Satintone [®] W	25	180	180	Figure 2
25	vinylsilane treated ² Satintone [®] W	29	164	140	Figure 3
	methylethoxysil oxane treated ³ Satintone [®] W	25	180	154	Figure 4
	Translink [®] 77	0	153	120	Figure 5
	Satintone [®] W	-	-	-	Figure 6

1. 1% A-137 (Witco) 2. 1% A-151 (Witco) 3. 1% A-272 (Witco)

30 Scanning electron micrographs shown in Figures 1-6 were collected with a Philips XL 30 FEG scanning electron microscope (SEM) at 1 Kv accelerating voltage and 1 x

10 (-5) mbar vacuum. Samples of petunia petals were coated with particle membranes as described in Example 1 and placed in the instrument without any additional sample preparation. The vacuum caused a collapse of the surface 5 irregularities of the petal substrate, but did not affect the particle membranes as illustrated in Figures 2 - 6. All images are presented at 400X magnification.

Figure 1 illustrates the uneven surface of an uncoated petunia petal. Under an ordinary optical 10 microscope one observes a surface containing many peaks and valleys. These peaks are collapsed under the conditions necessary to collect the SEM image. Ordinary optical images, however, often do not show the membrane surface because the membranes are very thin and 15 transparent to visible light. SEM techniques, however, can capture an image of the surface of such membranes.

Figures 2 - 4 illustrate the membrane surface prepared from calcined kaolin particles (1.2 micron median particle size) treated with the various 20 hydrophobic wetting agents listed in Table IV.

Figure 5 illustrates the surface of the membrane prepared from Translink® 77 which has fewer and smaller voids than those voids appearing in Figures 2 - 4.

Figure 6 illustrates the surface of the membrane 25 prepared from the same calcined kaolin particles (0.8 micron medium particle size) used in the manufacture of Translink® 77. The image clearly shows regularly spaced large voids on the order of 20 microns diameter.

Example 3

30 "Seckel" pear trees received the following treatments: 1) conventional pesticide applications applied according to the presence of economic levels of pests using the Virginia, West Virginia and Maryland Cooperative Extension 1997 Spray Bulletin for Commercial tree Fruit

-20-

Growers publication 456-419, 2) no treatment, 3) weekly application of Translink® 77 beginning in April 29, 1997, 4) weekly application of calcined kaolin (Satintone® 5HP) beginning in April 29, 1997, 5) weekly application of 5 treated calcium carbonate (SuperCoat® - commercially available from English China Clay) beginning in April 29, 1997. 6) weekly application of Translink 37® beginning in April 29, 1997. Treatments (3), (5) and (6) applied 25 pounds material suspended in 4 gal methanol and added 10 to 100 gal water. Treatment (4) applied 25 pounds material suspended in 100 gal water with the addition of 27oz Ninex® MT-603 and 2 pints Toximul. These treatments were applied at the rate of 125 gal/acre using an orchard sprayer. This mixture was applied at the rate of 125 15 gal/acre using an orchard sprayer. Treatments ended September 15, 1997. The treatments were arranged in a randomized complete block design with 2 replications and 4 trees/plot. A freeze of 25 °F occurred on October 23, 1997 and freeze damage of foliage was evaluated on 20 October 28, 1997. Freeze damage was evaluated by collecting 40 leaves/plot (10 from each tree). Leaves with necrosis on the leaf margin to the midvein that extended to the abaxial side of the leaf exhibited freeze damage. Undamaged leaves lacked this necrosis. Each 25 leaf was categorized as damaged or undamaged and percentage undamaged from each plot calculated. Data were analyzed using Analysis of variance using a randomized complete block design.

Table V

30

Treatment	Undamaged leaves (%)
Conventional	2.5
Control	2.5
Translink 77	81.5
Satintone 5HP	11.5

Supercoat	67.0
Translink 37	69.0

These data demonstrate that freeze damage was extensive when no particles were applied (conventional and control, 5 2.5% each). Freeze damage was extensive when a hydrophilic particle was applied to the tree (Satintone 5HP, 11.5 %). Freeze damage was moderated when hydrophobic particles were applied to the trees (Translink 77, Supercoat, and Translink 37, 81.5%, 67%, 10 and 69%, respectively). These data demonstrate that the presence of a hydrophobic particle membrane will moderate freeze damage.

Example 4

"Red Delicious" apple trees received the following 15 treatments: 1) Conventional pesticide applications applied according to the presence of economic levels of pests using the Virginia, West Virginia and Maryland Cooperative Extension 1997 Spray Bulletin for Commercial tree Fruit Growers publication 456-419, 2) no treatment, 20 3) weekly application of Translink® 77 beginning in March 11, 1997, 4) weekly application of calcined kaolin (Satintone® 5HP) beginning in April 29, 1997, and 5) weekly application of treated calcium carbonate (SuperCoat® - commercially available from English China 25 Clay) beginning in April 29, 1997. Treatments (3), and (5) applied 25 pounds material suspended in 4 gal methanol and added to 100 gal water. Treatment (4) applied 25 pounds material suspended in 100 gal water with the addition of 27oz Ninex® MT-603 and 2 pints 30 Toximul. These treatments were applied at the rate of 125 gal/acre using an orchard sprayer. This mixture was applied at the rate of 125 gal/acre using an orchard sprayer. The treatments were arranged in a randomized

complete block design with 4 replications and 3 trees/plot. Treatments were not irrigated and received 21.58 cm of precipitation from 1 May to 30 August 1997. Fruit were harvested at maturity; fruit number were 5 measured at harvest. Data were analyzed using Analysis of variance using a randomized complete block design.

Table VI

Treatment	Fruit number/tree
Conventional	322
Control	246
Translink 77 applied 3/11/97	382
Satintone 5HB applied 4/29/97	302
Supercoat applied 4/29/97	301

The weekly application of Translink® 77 before bud break and the occurrence of a severe frost on April 9, 1997 with a minimum temperature of 20 °F, moderated the frost 20 damage as demonstrated by a larger number of fruit (382) reaching maturity compared to Satintone® HB (302) or Supercoat® (301). The weekly application of Translink® 77 before bud break also moderated the frost damage to fruit compared to the conventional treatment and the 25 untreated control (322 and 246 respectively), neither of which received any pesticide applications prior to the frost. The application after the frost of Supercoat®, a hydrophobic particle, or Satintone® 5HB, a hydrophilic particle, did not increase the number of fruit/tree.

30

Example 5

"Golden Delicious" apples received 3 treatments: 1) commercial pesticide application applied according to the presence of economic levels of pests using the Virginia, West Virginia and Maryland Cooperative Extension 1997

Spray Bulletin for Commercial tree Fruit Growers publication 456-419, 2) full rate of Translink® 77, and 3) half rate of Translink® 77. Treatments (2) and (3) applied 25 and 12.5 pounds material, respectively, 5 suspended in 4 and 2 gal methanol, respectively, and added to 100 gal water. This mixture was applied at the rate of 200 gal/acre using an orchard sprayer. The treated area was approximately 1 acre plots with 2 replications of each treatment in a randomized block 10 design. At harvest the plots were commercially harvested and processed by a commercial grading line. At the time of grading, 100 fruit from each plot were randomly chosen to determine surface defects. The data are reported in Table VII.

15

Table VII

Treatment	Russetting downgrade (%)
Translink® 77 full rate	3.3
Translink® 77 half rate	3.9
Conventional	13.8

20 Application of Translink® 77 at the full and half rate reduced russetting on the apple surface compared to the conventional treatment.

Example 6

"Stayman" apples received 2 treatments: 1) commercial 25 pesticide application applied according to the presence of economic levels of pests using the Virginia, West Virginia and Maryland Cooperative Extension 1997 Spray Bulletin for Commercial tree Fruit Growers publication 456-419, 2) Translink® 77 treatment applied 25 pounds 30 material suspended in 4 gal methanol and added to 96 gal water. This mixture was applied at the rate of 200 gal/acre using an orchard sprayer. Each treatment was applied to 1 acre blocks with no randomization. Apples

were harvested commercially and processed on a commercial grading line. Data presented represent percent packout from the commercial grading line. At time of grading 100 fruit each treatment were randomly chosen to evaluate for surface defects. Cracking percentage was the percentage of fruit with visible cracks in the fruit. The date is reported in table VIII.

10

Table VIII

Treatment	Fruit Cracking (%)
Translink® 77	2
Conventional	22

The application of Translink® 77 decreased the cracking of apple fruit compared to the conventional treatment.

15 Throughout the specification and claims, the words "comprise", "comprises" and "comprising" are used in a non-exclusive sense.



THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:

1. A coated substrate comprising a horticultural substrate selected from the group consisting of fruits, vegetables, trees, flowers, grasses, roots, and landscape and ornamental plants wherein the surface of said substrate is coated with a membrane formed from a slurry comprising water and one or more particulate materials, the membrane comprised of one or more particulate layers, 10 said layers comprising calcined kaolin particulate materials, said particulate materials being finely divided, and wherein said membrane allows for the exchange of gases on the surface of said substrate.
- 15 2. The coated substrate of claim 1, wherein said particulate materials are hydrophobic.
3. The coated substrate of claim 1, wherein said particulate material has a Receding Contact Angle of 20 greater than 90°.
4. The coated substrate of claim 1, wherein the particulate material has a particle size distribution wherein up to 90% of the particles have a particle size of 25 under about 10 microns.
5. The coated substrate of claim 1, wherein the particulate material comprises a hydrophilic core and a hydrophobic outer surface.
- 30 6. The coated substrate of claim 5, wherein said hydrophobic outer surface materials are selected from the group consisting of chrome complexes, organic titanates, organic zirconate or aluminate coupling agents, 35 organofunctional silanes, modified silicone fluids and fatty acids and salts thereof.



7. The method of claim 1, wherein the substrate is selected from the group consisting of agricultural and ornamental crops.

5 8. The method of claim 1, wherein the substrate is selected from the group consisting of fruits, vegetables, trees, flowers, and landscape and ornamental plants.

10 9. The coated substrate of claim 1, wherein the finely divided particulate materials have a median individual particle size below about 3 microns.

15 10. The coated substrate of claim 5, wherein the hydrophilic core particulate materials are selected from the group consisting of calcium carbonate, calcined kaolin and mixtures thereof.

20 11. A coated substrate comprising a horticultural substrate selected from the group consisting of fruits, vegetables, trees, flowers, grasses, roots, and landscape and ornamental plants wherein the surface of said substrate is coated with a membrane formed from a slurry comprising water and one or more particulate materials, the membrane comprised of one or more particulate layers, 25 said layers comprising one or more hydrophobic particulate materials, said hydrophobic particulate materials comprising i) a hydrophilic core selected from the group consisting of calcium carbonate, calcined kaolin and mixtures thereof and ii) a hydrophobic outer surface, said particulate materials have a median individual particle 30 size of about one micron or less, and wherein said membrane allows for the exchange of gases on the surface of said substrate.

35 12. A method for pest control on horticultural substrates selected from the group consisting of fruits, vegetables, trees, flowers, grasses, roots, and landscape



and ornamental plants which comprises applying a slurry comprising water and calcined kaolin particulate materials to the surface of said substrate to form a membrane comprised of one or more particulate layers, said layers comprising one or more particulate materials, said particulate materials being finely divided, and wherein said membrane allows for the exchange of gases on the surface of said substrate.

5 13. The method of claim 12, wherein said particulate materials are hydrophobic.

10 14. The method of claim 12, wherein said particulate material has a Recording Contact Angle of greater than 90°.

15 15. The method of claim 12, wherein the particulate material has a particle size distribution wherein up to 90% of the particles have a particle size of under about 10 microns.

20 16. The method of claim 12, wherein the particulate material comprises a hydrophilic outer core and a hydrophobic outer surface.

25 17. The method of claim 16, wherein said hydrophilic core materials are selected from the group consisting of calcium carbonate, mica, kaolin, bentonite, attapulgite, pyrophyllite, wollastonite, silica, feldspar, sand, quartz, chalk, limestone, diatomaceous earth, baryte, 30 ceramic, glass and organic microspheres, aluminum trihydrate, ceramic fibers, glass fibers, colorants and titanium dioxide.

35 18. The method of claim 16, wherein said hydrophobic outer surface materials are selected from the group consisting of chrome complexes, organic titanates, organic zirconate or aluminate coupling agents, organofunctional



silanes, modified silicone fluids and fatty acids and salts thereof.

19. The coated substrate of claim 12, wherein the 5 substrate is selected from the group consisting of agricultural and ornamental crops.

20. The method of claim 12, wherein the substrate is selected from the group consisting of fruits, vegetables, 10 trees, flowers, roots, and landscape and ornamental plants.

21. The method of claim 12, wherein the finely divided particulate materials have a median individual 15 particle size below about 3 microns.

22. The method of claim 16, wherein the hydrophilic core particulate materials are selected from the group consisting of calcium carbonate, calcined kaolin and 20 mixtures thereof.

23. A method for pest control on horticultural substrates selected from the group consisting of fruits, vegetables, trees, flowers, grasses, roots, and landscape 25 and ornamental plants, which comprises applying a slurry comprising water and one or more particulate materials to the surface of said substrate to form a membrane comprised of one or more particulate layers, said layers comprising one or more hydrophobic particulate materials, said 30 hydrophobic particulate materials comprising i) a hydrophilic core selected from the group consisting of calcium carbonate, calcined kaolin and mixtures thereof, and ii) a hydrophobic outer surface, said particulate materials have a median individual particle size of about 35 one micron or less, and wherein said membrane allows for the exchange of gases on the surface of said substrate.



24. A method for enhancing the horticultural effect of horticultural substrates selected from the group consisting of fruits vegetables, trees, flowers, grasses, roots, and landscape and ornamental plants which comprises
5 applying a slurry comprising water and calcined kaolin particulate materials to the surface of said substrate to form a membrane comprised of one or more particulate layers, said layers comprising one or more particulate materials, said particulate materials being finely
10 divided, and wherein said membrane allows for the exchange of gases on the surface of said substrate.

25. The method of claim 24, wherein said particulate materials are hydrophobic.

15 26. The method of claim 24, wherein said particulate material has a Receding Contact Angle of greater than 90°.

20 27. The method of claim 24, wherein the particulate material has a particle size distribution wherein up to 90% of the particles have a particle size of under about 10 microns.

25 28. The method of claim 24, wherein the particulate material comprises a hydrophilic core and a hydrophobic outer surface.

30 29. The method of claim 28, wherein said hydrophilic core materials are selected from the group consisting of calcium carbonate, mica, kaolin, bentonite, attapulgite, pyrophyllite, wollastonite, silica, feldspar, sand, quartz, chalk, limestone, diatomaceous earth, baryte, ceramic, glass and organic microspheres, aluminum trihydrate, ceramic fibers, glass fibers, colorants and
35 titanium dioxide.

30. The method of claim 28, wherein said hydrophobic



outer surface materials are selected from the group consisting of chrome complexes, organic titanates, organic zirconate or aluminate coupling agents, organofunctional silanes, modified silicone fluids and fatty acids and 5 salts thereof.

31. The coated substrate of claim 24, wherein the substrate is selected from the group consisting of agricultural and ornamental crops.

10

32. The method of claim 24, wherein the finely divided particulate materials have a median individual particle size below about 3 microns.

15

33. The method of claim 28, wherein the hydrophilic core particulate materials are selected from the group consisting of calcium carbonate, calcined kaolin and mixtures thereof.

20

34. A method for enhancing the horticultural effect of horticultural substrates selected from the group consisting of fruits, vegetables, trees, flowers, grasses, roots, and landscape and ornamental plants, which comprises applying a slurry comprising water and one or 25 more particulate materials to the surface of said substrate to form a membrane comprised of one or more particulate layers, said layers comprising one or more hydrophobic particulate materials, said hydrophobic particulate materials comprising i) a hydrophilic core 30 selected from the group consisting of calcium carbonate, calcined kaolin and mixtures thereof, and ii) a hydrophobic outer surface, said particulate materials have



a median individual particle size of about one micron or less, and wherein said membrane allows for the exchange of gases on the surface of said substrate.

5

Dated this 1st day of February 2000

ENGELHARD CORPORATION and UNITED STATES OF AMERICA

REPRESENTED BY THE SECRETARY OF AGRICULTURE


By their Patent Attorneys

10 GRIFFITH HACK

Fellows Institute of Patent and

Trade Mark Attorneys of Australia

6
3
5
1
2
3
4
5
6
7
8
9
0



1 / 3




FIG. 1




FIG. 2

2 / 3




FIG. 3




FIG. 4

3 / 3




FIG. 5




FIG. 6