



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification⁵ : C08F 220/18, C09J 133/06, 7/02, A61L 15/58</p>	<p>A1</p>	<p>(11) International Publication Number: WO 94/24177</p> <p>(43) International Publication Date: 27 October 1994 (27.10.94)</p>
<p>(21) International Application Number: PCT/US94/03881</p> <p>(22) International Filing Date: 8 April 1994 (08.04.94)</p> <p>(30) Priority Data: 08/047,637 14 April 1993 (14.04.93) US</p> <p>(71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133 (US).</p> <p>(72) Inventors: LUCAST, Donald, H.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). MOORE, Cheryl, L.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). JAMES, Ruth, A.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US).</p> <p>(74) Agents: HOFFMAN, Amy, J. et al.; Office of Intellectual Property Counsel, Minnesota Mining and Manufacturing Company, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).</p>	<p>(81) Designated States: CA, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>	
<p>(54) Title: CROSSLINKED ABSORBENT PRESSURE SENSITIVE ADHESIVE AND WOUND DRESSING</p>		
<p>(57) Abstract</p> <p>Crosslinked, absorbent pressure sensitive adhesive compositions are disclosed comprising an acrylate or methacrylate ester of an alcohol, a hydrophilic alkylene oxide acrylate, a hydrophilic N-vinyl lactam, and an effective amount of a crosslinking agent. The compositions have an enhanced skin adhesion profile and are moderately absorbent. Also disclosed are precursor adhesive compositions and low-profile wound dressings.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgystan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

5

CROSSLINKED ABSORBENT PRESSURE SENSITIVE ADHESIVE AND WOUND DRESSING

Field of the Invention

10 The invention broadly relates to pressure sensitive adhesive compositions, precursor compositions for such adhesives, and wound dressings using such adhesive compositions. More specifically, the invention relates to biologically compatible, absorbent, pressure sensitive adhesive compositions, precursor compositions for such
15 adhesives, and wound dressings using such adhesive compositions.

Background of the Invention

20 Pressure sensitive adhesives have long been used in the manufacture of medical tapes and dressings intended for attachment to the skin.

Pressure sensitive adhesives intended for use in attaching tapes and/or dressings to the skin must possess a number of physical, chemical and biological characteristics including (i) biological compatibility with skin over
25 extended periods of continuous contact, (ii) biological compatibility with surgical incisions and lesions, and (iii) a bonding strength sufficient to prevent premature peeling of the tape/dressing from the skin but low enough
30 to prevent skin irritation upon removal of the tape/dressing.

Acrylate-Based Pressure Sensitive Adhesives

35 Acrylate-based pressure sensitive adhesive tapes have been used for many years in medical and surgical applications. Acrylate-based pressure sensitive adhesive tapes are generally biologically compatible and provide
40 acceptable adhesion to the skin. One such acrylate-based pressure sensitive adhesive tape having acceptable skin

adhesion performance is disclosed in United States Patent No. 3,121,021 issued to Copeland.

Acrylate-based pressure sensitive adhesive tapes are known to suffer from adhesion buildup after extended
5 contact with the skin. Excessive adhesion buildup causes the tape to strip skin from the body upon removal from the skin to the point of producing moderate pain and prolonged skin irritation. United States Patent No. 3,321,451 issued to Gander discloses that the inclusion of certain amine
10 salts into an acrylate-based pressure sensitive adhesive facilitates the removal of pressure sensitive adhesive tape from the skin by permitting the bonding strength of the tape to be reduced by soaking the tape with water. United States Patent No. 3,475,363, also issued to Gander,
15 attempts to overcome the objectionable adhesion buildup associated with acrylate-based pressure sensitive adhesives by including the crosslinking agent dimethylaminoethyl methacrylate into the adhesive.

United States Patent No. 3,532,652 issued to Zang
20 discloses that the adhesion buildup observed with acrylate-based pressure sensitive adhesives is caused by the migration of body fluids, such as skin oils, into the adhesive. Zang discloses that partially crosslinking an acrylate-based pressure sensitive interpolymer adhesive
25 with polyisocyanate overcomes the adhesion buildup problem.

United States Patent No. 4,140,115 issued to Schonefeld discloses that the skin-stripping irritation associated with the removal of acrylate-based pressure sensitive adhesive tapes can be alleviated by blending an
30 unreacted polyol having a fatty acid ester pendant moiety into the acrylate-based pressure sensitive adhesive. We observe that such an adhesive would tend to leave objectionable residue on the skin after removal of the
35 tape.

Crosslinking of
Pressure Sensitive Adhesives

5 The crosslinking of acrylate-containing polymers using
a photosensitive crosslinking agent, such as a
benzophenone, is taught by United States Patent No.
4,181,752 issued to **Martens et al.**

10 United States Patent No. 4,165,266 issued to **Stueben
et al.** discloses a pressure sensitive adhesive composition
synthesized from a poly(vinyl alkyl ether), a monoacrylate
monomer and a photoinitiator, such as benzophenone.

15 A solvent and heat resistant pressure sensitive
adhesive is disclosed in a Japanese language review article
authored by Toshio Okada entitled Radiation Curing of
Pressure Sensitive Adhesives, Volume 20, No. 611984. The
pressure-sensitive adhesive is a copolymer of benzoin
acrylate and an acrylate monomer, such as 2-
ethylhexylacrylate, cured by exposure to ultraviolet
radiation. We believe that the degree of crosslinking in
20 such a composition would result in an adhesive having
unacceptably low adhesion strength for use in securing a
tape or dressing to the skin.

25 While the varied adhesives disclosed above provide a
wide range of beneficial properties, a substantial need
still exists for a low-cost, absorbent, biologically
compatible, pressure sensitive adhesive useful in the
manufacture of a low-profile wound dressing having a
moderate capacity for absorbing wound exudate.

30 Summary of the Invention

Pressure-Sensitive
Adhesive

35 The invention is a moderately absorbent, biologically
compatible, pressure sensitive adhesive useful in the
manufacture of a low-profile wound dressing with an
acceptable adhesion to skin and a moderate capacity for
absorbing wound exudate without objectionable adhesion
buildup after extended contact with the skin. The adhesive
40 may be formulated to provide a substantially transparent

dressing so that the wound may be inspected and monitored without removing the dressing.

A first aspect of the invention is an absorbent, biologically compatible, pressure sensitive adhesive comprising a crosslinked copolymer of (a) an acrylate monomer selected from the group consisting of (i) an acrylate or methacrylate ester of a non-tertiary C₄₋₁₂ alcohol, and (ii) an acrylate or methacrylate ester of a mixture of non-tertiary C₁₋₁₄ alcohols with a resultant average of between about 4-12 carbon atoms per alcohol molecule; (b) a hydrophilic alkylene oxide acrylate monomer having an average of about 3 to 40 alkylene oxide units; (c) a hydrophilic N-vinyl lactam monomer; and (d) a crosslinking agent effective for crosslinking the copolymer.

The pressure sensitive adhesive can be chemically tailored, within physically defined parameters, to produce a skin compatible adhesive having a unique combination of properties. The properties of the novel pressure sensitive adhesive include (i) biological compatibility with human skin over extended periods of continuous contact, (ii) biological compatibility with surgical incisions and lesions, (iii) a bonding strength sufficient to preventing premature peeling of the tape/dressing from the skin but low enough to prevent skin irritation upon removal of the tape/dressing, (iv) a moderate absorbency sufficient to permit use of an otherwise low-absorbent tape/dressing over a surgical incision or lesion producing a moderate amount of fluid exudate, (v) a conformability sufficient to permit a tape/dressing to follow to the contours of the body, and (vi) a cohesive strength effective for maintaining the adhesive in position between the skin and the backing of the tape/dressing during application and use.

Precursor Composition for Manufacture of a Pressure-Sensitive Adhesive

A second aspect of the invention is a precursor composition useful for making an absorbent, biologically

compatible, pressure sensitive adhesive. The precursor composition comprises an uncrosslinked copolymer of (a) an acrylate monomer selected from the group consisting of (i) an acrylate or methacrylate ester of a non-tertiary C₄₋₁₂ alcohol, and (ii) an acrylate or methacrylate ester of a mixture of non-tertiary C₁₋₁₄ alcohols with a resultant average of between about 4-12 carbon atoms per alcohol molecule; (b) a hydrophilic alkylene oxide acrylate monomer having an average of about 3 to 40 alkylene oxide units; (c) a hydrophilic N-vinyl lactam monomer; and (d) a crosslinking agent effective for crosslinking the copolymer.

Wound Dressing

A third aspect of the invention is a wound dressing comprising (i) a substrate (ii) an absorbent pressure sensitive adhesive coated upon a major surface of the substrate, and (iii) a release liner protectively sandwiching the adhesive between the substrate and the liner. The pressure sensitive adhesive comprising a crosslinked copolymer of (a) an acrylate monomer selected from the group consisting of (i) an acrylate or methacrylate ester of a non-tertiary C₄₋₁₂ alcohol, and (ii) an acrylate or methacrylate ester of a mixture of non-tertiary C₁₋₁₄ alcohols with a resultant average of between about 4-12 carbon atoms per alcohol molecule; (b) a hydrophilic alkylene oxide acrylate monomer having an average of about 3 to 40 alkylene oxide units; (c) a hydrophilic N-vinyl lactam; and (d) a crosslinking agent effective for crosslinking the copolymer.

Copolymerizing of a crosslinking agent into the backbone of the pressure sensitive adhesive copolymer greatly increases crosslinking efficiency and permits the copolymer to be crosslinked after formation of the copolymer. The increased crosslinking efficiency permits very minor amounts of crosslinking agent to achieve useful degrees of crosslinking.

Use of the preferred photosensitive crosslinking agent in the copolymer of this invention allows the use of solventless coating techniques because the copolymer need not be crosslinked until after it is coated upon a support member.

These and various other advantages and features of novelty which characterize the invention are pointed out with particularity in the claims annexed hereto and forming a part hereof. However, for a better understanding of the invention, its advantages, and objects obtained by its use, reference should be had to the accompanying descriptive matter, in which there is illustrated and described preferred embodiments of the invention.

Detailed Description of
Embodiments of the Invention

The first aspect of the invention is a biologically compatible, moderately absorbent, pressure sensitive adhesive composition which is a crosslinked copolymer of (a) a hydrophobic acrylate monomer (monomer A), (b) a hydrophilic alkylene oxide acrylate monomer (monomer B), (c) a hydrophilic N-vinyl lactam (monomer C), and (d) a mono-ethylenically unsaturated crosslinking agent (monomer PX). The PX monomer is preferably a photosensitive crosslinking agent effective for crosslinking the copolymer upon exposure to ultraviolet radiation.

A second aspect of the invention is a precursor composition useful for manufacturing the pressure sensitive adhesive composition described above. The precursor composition comprises the copolymer of A, B, C and PX described above prior to crosslinking of the copolymer.

A third aspect of the invention is a wound dressing for use over surgical incisions or lesions exuding a moderate amount of fluids. The dressing comprises a substrate coated on a major surface with the absorbent pressure sensitive adhesive composition described above, and a release liner protectively sandwiching the adhesive between the substrate and the liner.

The properties and characteristics of the adhesive compositions of this invention are based upon a synergistic interaction of the various individual components. Consequently, efforts to describe the attributes contributed and/or influenced by each of the individual components is not necessarily indicative of the attributes possessed by the final adhesive composition. Such descriptions should therefore be used only as an indication of general trends and as a guide to those attributes which should be carefully considered when selecting the other components of the composition. For example, monomer B impacts absorbency such that incorporation of a minor proportion of monomer B in the adhesive would tend to produce an adhesive having reduced absorbency. However, the overall absorbency of the adhesive may be returned to an acceptable level by selecting a highly absorbent monomer C, increasing the amount of monomer C in the adhesive, etc.

The Monomers

Monomer A

Monomer A is a hydrophobic acrylate monomer which contributes to the visco-elastic properties of the copolymer. The monomer is selected from the group consisting of (i) an acrylate or methacrylate ester of a non-tertiary C₄₋₁₂ alcohol, and (ii) an acrylate or methacrylate ester of a mixture of non-tertiary C₁₋₁₄ alcohols with an average of between about 4-12 carbon atoms per alcohol molecule. Useful acrylate and methacrylate alcohol esters include specifically, but not exclusively, the acrylic acid and methacrylic acid esters of 1-butanol, 1-pentanol, 3-pentanol, 2-methyl-1-butanol, 1-methyl-1-butanol, 1-methyl-1-pentanol, 2-methyl-1-pentanol, 3-methyl-1-pentanol, 2-ethyl-1-butanol, 2-ethyl-1-hexanol, 3,5,5-trimethyl-1-hexanol, 3-heptanol, 2-octanol, 1-decanol, and 1-dodecanol. Mixtures of these alcohols are available from Exxon under the Exxal family mark. A

preferred alcohol mixture for use in synthesizing monomer A is Exxal-8.

5 The copolymer includes about 30 to 70 wt%, preferably about 40 to 50 wt% monomer A based upon the total weight of all monomers in the copolymer. Inclusion of less than about 30 wt% monomer A tends to produce an adhesive which is excessively hydrophilic to the point of losing cohesive strength when exposed to more than modest amounts of fluid. Inclusion of greater than about 70 wt% monomer A tends to
10 produce an adhesive with insufficient absorbency.

Monomer B

Monomer B is a hydrophilic alkylene oxide acrylate. The synthesis of monomer B employs commercially available
15 starting materials and widely known and accepted conventional techniques. For example, monomer B may be prepared by reacting an α , β -unsaturated carboxylic acid, such as acrylic acid or methacrylic acid, with an equimolar amount of a monoalcohol of a poly(lower alkylene oxide).
20 The esterification reaction is generally conducted under anhydrous conditions in an organic solvent, such as toluene, which preferably forms an azeotropic mixture with the water which is generated by the esterification reaction. Typically, the alcohol is combined with the
25 organic solvent and the unsaturated carboxylic acid is then added.

The reaction is conducted in the presence of an acid catalyst, such as para-toluenesulfonic acid, and a free-radical inhibitor, such as copper powder. The reaction
30 mixture is refluxed for several hours under a nitrogen atmosphere and the resultant water removed by azeotropic distillation.

Suitable polyalkylene oxides which may be used to prepare the preferred B monomers using the above-described
35 procedure include the methoxy-poly(ethylene oxide) ethanols of about 350 MW, 550 MW, 750 MW, 2000 MW and 5000 MW, respectively, which are commercially available from Union Carbide Corp. The polyalkylene oxide of choice is

polyethylene oxide having an average of from 3 to 40 polyethylene (EO) units, preferably 5 to 20 EO units, per molecule.

5 The copolymer includes about 15 to 40 wt%, preferably about 20 to 30 wt% monomer B based upon the total weight of all monomers in the copolymer. Inclusion of less than about 15 wt% monomer tends to produce an adhesive having reduced absorbency and reduced transparency. Inclusion of greater than about 40 wt% monomer B tends to produce an
10 adhesive having reduced tack.

Monomer C

Monomer C is a hydrophilic N-vinyl lactam which is copolymerizable with monomers A, B and PX. The monomer
15 reinforces the adhesive and contributes modest absorbency and improved cohesiveness to the adhesive composition.

Monomer C is an N-vinyl lactam. Preferred N-vinyl lactams are N-vinylpyrrolidone and N-vinyl-2-caprolactam.

The copolymer includes about 15 to 50 wt%, preferably
20 about 20 to 30 wt% monomer C based upon the total weight of all monomers in the copolymer. Inclusion of less than about 15 wt% monomer C tends to produce an adhesive having a reduced cohesiveness observed as an unsatisfactory "skin adhesion profile". Inclusion of greater than about 50 wt%
25 monomer C tends to produce an adhesive with reduced tack and reduced conformability.

Crosslinking Monomer PX


Crosslinking monomer PX is a copolymerizable,
30 monoethylenically unsaturated crosslinkable monomer. The ethylenically unsaturated group is copolymerizable with the A, B and C monomers to form the backbone of the polymer chain. The PX monomer is preferably one which may be crosslinked after coating of the adhesive composition upon
35 a support such as by exposure to ultraviolet radiation.

A preferred PX monomer is a monoethylenically unsaturated aromatic ketone. Such PX monomers are known to absorb ultraviolet radiation and form a triplet excited

state through intersystem crossing. The excited-state molecules abstract hydrogen radicals from the polymer chain leaving free radical sites which combine to form crosslinks. The semi-pinacol radical on the aromatic ketone can also produce crosslinking.

A hydroxyl group positioned ortho to the carbonyl group on the aromatic ring is known to inhibit the ability of aromatic ketones to effect crosslinking. Accordingly, the aromatic ketone monomer must be free of ortho-aromatic hydroxyl groups to be effective as a photosensitive crosslinking agent.

Suitable PX monomers are represented by the general formula:



wherein:

R: is a lower alkyl or phenyl which may be substituted with one or more halogen atoms, alkoxy groups or hydroxyl groups except that when R is a hydroxy substituted phenyl the hydroxyl group(s) must be positioned meta or para to the aromatic carbonyl;

X: is halogen, alkoxy or hydroxyl provided that when X is a hydroxyl group it is positioned meta or para to the aromatic carbonyl;

Y: is a divalent linking group which is preferably a covalent bond, an oxygen atom(-O-), an amino group (-NR¹- wherein R¹ is hydrogen or lower alkyl), an oxyalkyleneoxy group (-O-R²-O-wherein R² is an alkylene group), a carbamoylalkyleneoxy group (-O-R²-O-(O)-N-(R¹)-R³- wherein R³ is a covalent bond or an alkyleneoxy group such as -R²-O-);

Z: is alkenyl or ethylenically unsaturated acyl group; and

n: is an integer from 0 to 4.

Particularly preferred PX monomers are the acryloxybenzophenones such as 4-acryloxybenzophenone.

The copolymer includes about 0.01 to 2 wt%, preferably about 0.025 to about 0.5 wt% PX monomer based upon the total weight of all monomers in the copolymer. A PX content of less than about 0.025 wt% tends to produce an adhesive with reduced cohesive strength while a PX content of greater than about 2 wt% tends to produce an adhesive with reduced tack.

It will be understood that other forms of radiation can be used to cross-link the pressure sensitive adhesive of the present invention. For example, electron beam radiation can be used to cross-link the adhesives of the present invention. In such an instance, the PX monomer would become an optional component in the pressure sensitive adhesive composition.

Properties and Characteristics

Inherent Viscosity

Inherent viscosity (IV) is recognized as a relative measure of polymer molecular weight. In order to achieve the desired creep compliance and skin adhesion profile the inherent viscosity of the uncrosslinked copolymer of this invention should be between about 0.5 to 1.4 dl/g when measured in tetrahydrofuran (THF). More preferably, the inherent viscosity is between about 0.5 to 1.1 dl/g, most preferably between about 0.6 to 0.95 dl/g when measured in THF.

Creep Compliance

The fundamentals of creep compliance (J_3) as they relate to polymeric materials and, in particular, to viscoelastic polymers is covered in "Viscoelastic Properties of Polymers", John D. Ferry, 3rd Edition, John Wiley and Sons, 1980, Chapter 1; "Treatise on Adhesion and Adhesives", R. L. Patrick - Editor, Volume 2, Marcel Dekker Inc., 1969, Section entitled "Materials"/ "Pressure

Sensitive Adhesives"; Properties and Structure of Polymers, Tobolsky, John Wiley and Sons, 1960, Chapter II, Section 6; and "Handbook of Pressure Sensitive Adhesive Technology", C. A. Dahlquist, Donatas Satas - Editor, Van Norstrand
5 Reinhold Company, 1982, Chapter 5.

The creep compliance of the adhesive composition of this invention is dependent upon several factors including the specific type and relative amounts of monomers A, B, C and PX in the copolymer and the degree to which the
10 copolymer is polymerized. Generally, an increase in the amount of PX monomer will result in an increase in the degree of crosslinking within the copolymer and thereby decrease the creep compliance of the copolymer. Similarly,
15 an increase in the degree to which the copolymer is polymerized will increase the length of the polymer chains and thereby decrease the creep compliance of the copolymer. These two factors may be adjusted as necessary to produce an adhesive having the desired creep compliance.

20 Moisture Vapor Transmission Rate

Adhesives preferred for use as a pressure sensitive adhesive in wound dressings are those which permit passage
25 of moisture vapor such as perspiration. Accordingly, the preferred materials are those with a twenty four hour moisture vapor transmission rate ($MVTR T_{24}$) of at least about 500 g/m², most preferably at least about 1000 g/m², when measured in accordance with ASTM E 96-80 at 40°C with
30 a humidity differential of 80%.

Skin Adhesion

The adhesive of this invention exhibits an initial skin adhesion (T_0) of between about 8 to 80 g/cm width,
35 preferably between about 12 to 60 g/cm width; and a twenty four hour skin adhesion (T_{24}) of between about 8 to 160 g/cm width, preferably between about 12 to 80 g/cm width. Adhesives with an adhesion of less than about 8 g/cm width at any time during normal periods of use will result in

premature peeling from the skin while adhesives with an adhesion of greater than about 160 g/cm width at the time of removal will produce significant skin irritation upon removal.

5 In addition, the adhesive exhibits a (T_{WET}) of at least about 8 g/cm width, preferably at least about 12 g/cm width.

Adhesive Lift

10 An adhesive which prematurely peels or delaminates from the skin is commercially unacceptable for use as a skin adhesive. Generally, an adhesive must exhibit an average adhesive lift rating (Lift) of less than about 2.5 to be useful as a skin adhesive.

15 The adhesive of this invention can be reproducibly synthesized with an acceptable adhesive Lift rating of less than about 2.5, typically below about 2, without interfering with the ability of the adhesive to meet the other characteristics required for consideration of the
20 adhesive as an acceptable skin adhesive.

Adhesive Residue

 An adhesive which leaves excessive residue behind is commercially unacceptable for use as a skin adhesive.
25 Generally, an adhesive must exhibit an average adhesive residue rating (Residue) of less than about 2.5 to be useful as a skin adhesive.

 The adhesive of this invention can be reproducibly synthesized with an acceptable Residue rating of less than
30 about 2.5, typically below about 2, without interfering with the ability of the adhesive to meet the other characteristics required for consideration of the adhesive as an acceptable skin adhesive.

Skin Adhesion Profile

35 The "Skin Adhesion Profile" of an adhesive is a combination of the Skin Adhesion, Adhesive Lift and Adhesive Residue characteristics of the adhesive. A

satisfactory "Skin Adhesion Profile" is a combination of Skin Adhesion, Adhesive Lift and Adhesive Residue which is subjectively acceptable to consumers. For example, an adhesive having superior skin adhesion but modest adhesive lift and adhesive residue may possess an unsatisfactory Skin Adhesion Profile while an adhesive having fair skin adhesion but superior adhesive lift and adhesive residue may possess a satisfactory Skin Adhesion Profile.

10 Immersion Absorption

The adhesive of the present invention possesses a twenty-four hour immersed absorption capacity ($Imrs_{24}$) of at least about 200%, preferably about 300% to 450%. This level of absorption capacity makes the adhesive well adapted for use in wound dressings intended to cover surgical incisions and lesions expected to exude moderate amounts of body fluids. For example, a ten centimeter square wound dressing having a 1 mil (0.025 cm) thick film of the adhesive of this invention rated at ($Imrs_{24}$) of 300% can be expected to absorb and retain about 7.5 ml of fluid in the adhesive.

Demand Absorption

The adhesive of the present invention possesses a demand absorption ($Dmnd_{15}$) (measured as the slope of the line through the point of the curve at 15 minutes and through the origin) of at least about 1.5 g/hr, preferably about 2.0 g/hr. This rate of absorption demand makes the adhesive well adapted for use in wound dressings intended to cover surgical incisions and lesions expected to exude moderate amounts of body fluids within a relatively short time span.

Polymerization Process

35 Monomers A, B, C and PX are free radical polymerized to form the precursor composition of this invention which may then be crosslinked to form the adhesive.

Solvent

The A, B, C and PX monomers may be dissolved in a suitable inert organic solvent for polymerization. The solvent must be effective for dissolving monomers A, B, C and PX as well as the resultant uncrosslinked copolymer. Suitable solvents include specifically, but not exclusively, single solvent systems, such as ethyl acetate; and cosolvent systems, such as mixtures of ethyl acetate/toluene and ethyl acetate/toluene/isopropyl alcohol. Other solvent systems are also believed to be useful.

The amount of solvent used must be sufficient to achieve intimate contact between the polymerization reactants including monomers A, B, C, and PX as well as the polymerization initiator and initiated polymer chains. Typically, use of about 30-80 wt% solvent, based on the total weight of reactants and solvent, is sufficient to achieve substantially complete polymerization within a reasonable time period.

In addition to the solvent-based technique, copolymerization of the monomers may be completed by other well known techniques such as suspension polymerization, emulsion polymerization, and bulk polymerization.

Polymerization Initiator

Polymerization of the solvent dissolved monomers is effected by standard free radical polymerization utilizing a suitable free radical initiator. Numerous free radical initiators are well known in the industry. Exemplary of those free radical initiators suitable for use in the present invention are those described in United States Reissue Patent No. 24,906 issued to Ulrich, the disclosure of which is herein incorporated by reference. Suitable thermally activated initiators include specifically, but not exclusively, azo compounds such as 2,2'-azo-bis(isobutyronitrile), tert-butyl hydroperoxide, benzoyl peroxide, and cyclohexanone peroxide. Generally, about 0.01 to 1 wt%, preferably about 0.01 to 0.5 wt%,

initiator, based upon the total weight of all monomers in the copolymer, is effective for initiating polymerization.

Coating onto Substrate

5 The adhesive precursor may be coated onto a substrate to form various articles intended for adhesion to skin including tapes, patches, strips, wound dressings, monitoring or neuro-stimulating electrodes, drapes, etc. Without intending to be unduly limited thereby, the
10 remainder of the discussion will be presented with respect to the manufacture of a wound dressing.

Wound Dressing Backings

15 Substrates suitable for use in the manufacture of a wound dressing intended for attachment to the skin include woven, nonwoven and knit fabrics and conformable synthetic films such as polypropylene, polyethylene, polyvinyl
20 chloride, polyurethane, polyester, and ethyl cellulose.

 Suitable woven and nonwoven fabrics include those formed from threads of synthetic or natural materials including cotton, nylon, rayon, polyester, and the like. Synthetic films suitable for use are those having a tensile
25 modulus of less than about 400,000 psi (2758.8 MPa), preferably less than about 300,000 psi (2069.1 MPa), measured in accordance with ASTM D-638.

 The fabric should be sufficiently continuous to prevent the passage of pathogens, such as bacteria from
30 entering the wound.

 The preferred substrates are those which permit visual inspection of the wound without removal of the dressing and permit passage of body fluids such as perspiration and wound exudate. Accordingly, preferred materials are those
35 which are transparent and possess a twenty four hour moisture vapor transmission rate ($MVTR T_{24}$) of at least about 500 g/m², most preferably at least about 1000 g/m² when measured in accordance with ASTM E 96-80 at 40°C with a humidity differential of 80%.

A continuous polyurethane film sold by B. F. Goodrich and a continuous polyester film sold by E. I. Dupont DeNemours each have an $MVTR T_{24}$ value of about 1000 to 1500 g/m². Woven substrates, such as that sold by Minnesota Mining and Manufacturing Company and used in surgical tape possess even higher $MVTR T_{24}$ values.

Coating Techniques

The copolymer precursor can be coated onto the substrate by any of a variety of conventional techniques such as roll coating, spray coating, extrusion coating, coextrusion, hot-melt coating and the like. The process of choice depends upon the nature of the substrate employed. For example, a preferred method for coating the adhesive upon a nonwoven fabric is to dissolve the adhesive copolymer in an organic solvent, spread the copolymer solvent onto a release liner, and then laminate the adhesive coating onto the nonwoven fabric before the adhesive is completely dry.

As mentioned previously, use of the preferred photosensitive crosslinking agent in the copolymer of this invention allows the use of solventless coating techniques because the copolymer need not be crosslinked until after it is coated upon a support member. For example, the adhesive may be coated without the aid of a solvent by (i) stripping solvent remaining from polymerization by any of the well known conventional techniques, (ii) coating the dried, uncrosslinked polymer onto a suitable substrate by any of the well known conventional "hot melt" techniques such as an extrusion or roto gravure process, and then (iii) crosslinking the coated polymer to form an absorbent pressure sensitive adhesive film.

Crosslinking

The coated adhesive precursor is then crosslinked by contacting or exposing the precursor to the appropriate crosslinking initiator such as ultraviolet radiation at an

intensity and for a duration sufficient to crosslink the copolymer by means of the PX monomer.

5 The extent to which the copolymer is crosslinked depends upon both the amount of PX monomer in the copolymer and the intensity of the treatment. For purposes of quality control, the degree to which the copolymer is crosslinked is preferably controlled by treating the copolymer so as to effect substantially complete crosslinking of the PX monomer and adjusting the amount of
10 PX monomer as necessary.

When a photosensitive PX monomer is employed, ultraviolet radiation treatment is conveniently effected using medium-pressure mercury lamps providing an output of about 80 watts per cm (200 watts per inch) and having a
15 spectral output over a range of about 180 to 430 nanometers.

Sterilization

20 When the adhesive is intended for use in a wound dressing, the adhesive must be sterilized. A widely accepted method of sterilizing wound dressings is to subject the dressing to about 2.5 to 5 megarads of gamma radiation.

25

Testing Protocols

Inherent Viscosity (IV) (Degree of Polymerization)

5 The inherent viscosity of a polymer is measured in accordance with the protocol described by Fred W. Billmeyer, Jr. at pages 84-85 of the textbook entitled Textbook of Polymer Science, Second Edition, published by Wiley-Interscience, (1971). Briefly, solution viscosity is
10 measured by comparing the efflux time (t) required for a specified volume of polymer solution to flow through a capillary tube with the corresponding efflux time (t_0) for the solvent. The measured variables t , t_0 , and solute concentration (c) are then used to calculate inherent
15 viscosity (also known as Logarithmic Viscosity) using the equation:

$$\eta = (\ln t/t_0)/c$$

20 Creep Compliance

The adhesive to be tested is knife-coated onto a smooth film of polytetrafluoroethylene to a thickness of 150 micrometers. The adhesive coating is dried to constant weight in an air-circulating oven (at least five minutes at
25 110°C). The dried adhesive is stripped from the polytetrafluoroethylene support to form a dried adhesive film.

Two identical test specimens are die-cut from the dried adhesive film and positioned on a Parallel Plate Creep Compliance Rheometer. One of the specimens is
30 laminated to each side of a rigid metal center plate and then sandwiched between rigid metal outer plates to form a plate/adhesive/plate/adhesive/plate laminate. Screws connecting the outer plates are tightened to compress the
35 interposed test specimens approximately 10%.

The specimen-containing plates are positioned horizontally within the rheometer with one end of the center plate electronically connected to a chart recorder and the other end attached to a flexible wire. The

flexible wire is extended horizontally from the center plate, directed downward around a pulley, and connected to a 500 gram weight. The outer plates are held in a fixed position.

5 The size of the weight is selected to measurably deform the test specimen a distance no greater than its thickness.

 A strip chart recorder is started and the variables of time (t), displacement (*Strain*) and applied force (*Stress*) are recorded. The creep compliance of the tested adhesive is then calculable in cm^2/dyne using the equation:

$$J_{(t)} = (2AX)/(hf)$$

where:

- 15 (t) is the time at which the measurement is taken (hrs),
 (A) is the area of one major surface of the adhesive sample (cm^2),
 (h) is the thickness of the adhesive sample after
20 compression (cm),
 (X) is the displacement at time t (where X is less than h) (cm), and
 (f) is the force exerted on the center plate by the weight attached to the end of the flexible wire
25 (dynes).

Moisture Vapor Transmission Rate

(Upright)

30 The Moisture Vapor Transmission Rate ($MVTR_{up}$) is measured in accordance with ASTM E 96-80 as modified below.

 Thirty five millimeter diameter samples of a 0.025 cm thick film of the adhesive is laminated to a 0.0275 cm thick polyurethane web having a $MVTR_{up} T_{24}$ of 2,000 to 2,400
35 g/m^2 measured at 40°C and a relative humidity differential of 80%.

 The laminated samples are sandwiched between the adhesive surfaces of two axially aligned foil adhesive rings having 2.54 cm diameter holes. Each sample is pulled

to ensure a flat, wrinkle-free and void-free foil/sample/foil laminate.

5 A four-ounce (0.14 kg) glass jar is filled half-full with distilled water. The jar is fitted with a screw-on cap having a 3.8 cm diameter hole concentrically aligned with a rubber washer having a 4.445 cm outside-diameter and a 2.84 cm inside-diameter.

10 The foil/sample/foil laminate is concentrically positioned on the rubber washer and the sample-containing sub-assembly screwed loosely onto the jar.

The assembly is placed into a chamber maintained at a temperature of 40°C and 20% relative humidity. The assembly is removed from the chamber after four hours, weighed to the nearest 0.01 gram (W_1), and immediately returned to the chamber. The cap is now screwed tightly onto the jar without bulging of the sample. The assembly is again removed from the chamber after an additional eighteen hours and weighed to the nearest 0.01 gram (W_2).

20 The $MVTR_{up} T_{24}$ of the adhesive (measured in grams of water transmitted per square meter of sample area over a twenty four hour period) may then be calculated according the formula set forth below:

$$MVTR_{up} T_{24} = (W_1 - W_2) (4.74 \cdot 10^4) / t$$

25 where:

- (W_1) is the initial weight of the assembly (grams)
- (W_2) is the final weight of the assembly (grams), and
- (t) is the time period between W_1 and W_2 (hrs).

30 Three samples of each adhesive were run and the average of the three samples reported.

Moisture Vapor Transmission Rate (Inverted)

35 The protocol for measuring $MVTR_{inv}$ is the same as the "Upright" protocol except that the assembly is inverted inside the chamber once the cap is tightly screwed onto the jar so that the water within the jar directly contacts the

foil/sample/foil laminate while the assembly is within the chamber.

Skin Adhesion

5 Evaluation of the adhesiveness of a composition to human skin is an inherently temperamental determination. Human skin possesses wide variations in composition, topography, and the presence/absence of various body fluids. However, controlled and comparative values of
10 adhesion are attainable by employing a select panel of individuals trained to recognize the normal skin variations encountered in medical practice.

Initial skin adhesion (T_0), skin adhesion after 24 hours of continuous contact with the skin (T_{24}), and skin
15 adhesion to wet skin (T_{WET}) is measured in accordance with the widely accepted PSTC-1 Peel Adhesion Test for single coated adhesive tape conducted at a removal angle of 180° . The PSTC-1 Peel Adhesion Test is a testing protocol
20 established by the Specifications and Technical Committee of the Pressure Sensitive Tape Council located at 5700 Old Orchard Road, Skokie, Illinois. The test is modified for our purposes by applying the tape to the skin of a living human.

The adhesive is tested as a 0.025 cm film coated onto
25 a 0.0275 cm thick polyurethane web having a $MVTR_{up}$ T_{24} of 2,000 to 2,400 g/m² measured at 40°C and a relative humidity differential of 80%. Three samples measuring 2.5 cm wide by 7.6 cm long are applied to the back of each of six human subjects (three men and three women). The subjects are
30 placed in a prone positioned with arms at their sides and heads turned to one side. Samples are applied to both sides of the spinal column with the length of each sample positioned at a right angle to the spinal column. The samples are applied without tension or pulling of the skin.

35 Those samples tested for wet skin adhesion are applied to skin which had been moistened with a water saturated cloth, leaving visually observable drops of standing water, immediately before application of the sample.

The samples are pressed into place with a 2 kg roller moved at a rate of approximately 2.5 cm/sec with a single forward and reverse pass. No manual pressure should be applied to the roller during application.

5 The samples are then removed either immediately after application (T_0) or after 24 hours of continuous contact with the skin (T_{24}), at a removal angle of 180° and removal rate of 15 cm per minute, using a conventional adhesion tester equipped with 25 lb (11.4 kg) test line attached to
10 a 2.5 cm clip. The clip is attached to the edge of the sample furthest from the spinal column by manually lifting about 1 cm of the sample from the skin and attaching the clip to the raised edge. The adhesion tester is a strain-gauge mounted on a motor-driven carriage.

15 The measured force required to effect removal is reported in grams per cm.

Adhesive Lift

20 Evaluation of the adhesive tenacity of a composition to human skin is an inherently temperamental determination for the same reasons established above in connection with evaluation of the adhesiveness of a composition to human skin.

25 However, the observational values as to adhesive tenacity (*Lift*) are generally reproducible and in accord with subjective assessments of similar properties which are widely accepted in the art as meaningful, reliable and reproducible.

30 The Adhesive Lift Test is a subjective assessment of the extent to which adhesive tape prematurely separates from the body after application of a sample in accordance with the Skin Adhesion Test. The applied samples are visually inspected just prior to testing for Skin Adhesion (i.e. twenty four hours after application) to determine the
35 extent to which the edges of the sample have separated from the skin. Each sample is assigned a numerical rating from 0 to 5 based on the following observation:

	Rating	Definition
	0	No visible separation.
	1	Separation at edges of tape only.
	2	Separation of 1% to 25% of tape area.
5	3	Separation of 26% to 50% of tape area.
	4	Separation of 51% to 75% of tape area.
	5	Separation of 76% to 100% of tape area.

Each sample is assigned a single whole number from the list established above by each panel member. The assigned values from the panel members are then averaged and reported to the tenths position. Due to the subjective nature of the test, differences of less than 0.5 in averaged residue values should be considered substantially the same.

Adhesive Residue

As with the rating of Adhesive Lift, an assessment of the Adhesive Residue Rating (*Residue*) of a composition to human skin is an inherently temperamental but reproducible determination.

The Adhesive Residue Test is a subjective assessment of the amount of adhesive left upon the skin after removal of an adhesive sample in accordance with the Skin Adhesion Test. The skin directly underlying each sample was visually inspected to determine the extent to which the area contacted by the adhesive contains residual adhesive. Each sample was then assigned a numerical rating from 0 to 5 based on the following observation:

	Rating	Definition
	0	No visible residue.
	1	Residue at edges of tape only.
	2	Residue covering 1% to 25% of tested area.
35	3	Residue covering 26% to 50% of tested area.
	4	Residue covering 51% to 75% of tested area.
	5	Residue covering 76% to 100% of tested area.

Each sample was assigned a single whole number from the list established above by each panel member. The assigned values from the panel members were then averaged and reported to the tenth position. Due to the subjective nature of the test, differences of less than 0.5 in averaged residue values should be considered substantially the same.

Preferred skin adhesives will generally exhibit an average residue rating below about 2.5.

Absorption (Immersion)

The water absorptive capacity of an adhesive is measured by immersing the adhesive into buffered water and measuring the weight of water absorbed.

Round test samples having a 5 cm² surface area are preweighed (W_i) and placed into a 180 ml bottle containing 30 ml of phosphate buffered saline solution having a pH of 7.2 purchased from Sigma Chemical Company. The bottles are capped and allowed to stand without agitation. The samples are removed 24 hours after initial immersion in the bottle and weighed (W_f). The Absorbency Value is calculable using the following formula:

$$Imrs_{24} = [(W_f - W_i) / W_i] \times 100$$

Absorption (Demand)

The initial rate at which an adhesive is able to absorb water is measured by contacting a sample of the adhesive with buffered water, periodically measuring the weight of water absorbed, plotting the weight of water absorbed verses time, and measuring the slope of a line through the origin of the plot and the data point at 15 minutes.

Equipment

Feeding Plate

A water feeding plate is constructed from (i) a 5/8 inch thick six inch diameter plexiglass base plate, (ii) a
5 ½ inch thick six inch diameter plexiglass top plate, (iii) a sixty mm diameter Corning 60C™ fritted glass disc, (iv) two, two-way valves, and (iv) one 3½ inch and one 4 inch diameter O-ring.

The base plate is machined to provide (a) a ½ inch
10 deep, three inch diameter, central cylindrical reservoir, (ii) a pair of radially opposed passages extending completely through the sides of the plate into communication with the reservoir, and (c) concentric 3½ inch diameter and 4 inch diameter grooves. The two-way
15 valves are sealing fitted into the bores and the O-rings positioned within the grooves.

The top plate is machined to provide a sixty mm central hole into which the glass frit is sealed with
20 silicone adhesive. The top surface of the glass frit is positioned flush with the top surface of the plate.

The top plate is secured over the base plate using four machine screws spaced along the periphery of the
plates which pass through orifices drilled in the top plate and extend into axially aligned bores within the bottom
25 plate.

Supply Tank

A 19 cm diameter supply tank of phosphate buffered saline solution is connected with rubber tubing to a first
30 of the valves attached to the Feeding Plate. The tank is covered to prevent evaporation of the saline solution but is NOT sealed. The tank is placed upon a standard Lab Jack so that the vertical position of the tank may be raised and lowered as necessary to generate zero head pressure at the
35 surface of the glass frit in the feeding plate.

Balance

The feeding plate is placed upon the pan of a standard electronic balance to permit changes in the weight of the feeding plate to be measured and recorded.

5

Procedure

The reservoir is filled with saline solution from the supply tank and bubbles removed by opening the second of the two-way valves connected to the feeding plate. The tank is then vertically positioned to provide zero head pressure within the reservoir.

10

A six centimeter diameter disc of Whatmann No. 1 filter paper is positioned on the glass frit to prevent the adhesive from bonding to the frit.

15

An oversized sample of the adhesive to be tested (one which more than covers the glass frit) is centered over the glass frit. The balance is tared to zero and the cumulative weight of saline solution absorbed by the adhesive sample weighed over time.

20

The height of the supply tank is NOT readjusted during the experiment unless more than 20 grams of saline solution is removed from the tank due to absorption or evaporation. Should more than twenty grams of saline be removed from the tank the vertical height of the tank is repositioned once immediately after the twenty grams have been removed to compensate for the decrease in head pressure generated by the saline solution within the tank.

25

The increased weight is plotted against time and a "Demand Absorption Value" ($Dmnd_{15}$) determined by measuring the slope of a line through the origin of the plot and the curve at fifteen minutes.

30

The invention will be further illustrated by reference to the following non-limiting Examples. All parts and percentages are expressed as parts by weight unless otherwise indicated.

35

Examples 1-51

Into a 0.95 liter amber bottle was placed the respective amounts of (i) isooctyl acrylate (*Monomer A*) prepared by Fischer esterification of acrylic acid with Exxal-8 obtained from Exxon Corporation except for Examples 14-16, where butyl acrylate (BA), available from Union Carbide, was employed, (ii) N-vinyl pyrrolidone (*Monomer B*) obtained from General Aniline & Film Corporation, (iii) a 46 solids wt% toluene solution of polyethylene oxide acrylate (n=16, except for Examples 17-51 where n=9) (*Monomer C*) prepared by Fischer esterification of methoxypoly (ethylene oxide) ethanol (M.W. 750) with acrylic acid (calculated upon dry monomer) for n=16 or purchased as 100% solids from Shin Nakamura for n=9, (iv) a 26 wt% ethyl acetate solution of acryloxybenzophenone (*Monomer PX*) (calculated upon dry monomer), (v) an analytical reagent grade ethyl acetate, and (vi) an analytical reagent grade isopropyl alcohol. The specific amount of each of these components (in grams) used to form the pressure sensitive adhesives of Examples 1-51 is given in TABLE 1.

For each of the Example compositions, the solution was deoxygenated by purging the bottle with nitrogen at a rate of one liter per minute for three minutes. The deoxygenated bottle was sealed and placed in a rotating water bath maintained at 55°C for twenty four hours to effect substantially complete polymerization of monomers A, B, C and PX.

The Inherent Viscosity (*IV*), Creep Compliance (J_3), the twenty four hour Moisture Vapor Transmission Rate (Upright) ($MVTR_{up} T_{24}$), the twenty four hour Moisture Vapor Transmission Rate (Inverted) ($MVTR_{inv} T_{24}$), Skin Adhesion (Initial) (T_0), Skin Adhesion (Twenty Four Hours) (T_{24}), Skin Adhesion (Wet) (T_{WET}), Adhesive Lift (*Lift*), Adhesive Residue (*Res*), Absorption (Immersion) ($Imrs_{24}$), and Absorption (Demand) ($Dmnd_{15}$) of the samples were then measured in accordance with the testing protocols set forth herein. The results of such testing are set forth in TABLE

2 below. The extent to which the polymers were crosslinked by exposure to ultraviolet radiation prior to testing is also set forth in TABLE 2.

5

TABLE 1

Amount of each component in grams used to form the pressure sensitive adhesives of Examples 1-51.

10

Ex. Nos.	IOA	NVP	EOA	ABP	EtOAc	IPA
1-3	75.0	100.0	75.0	0.96	129.5	35.0
4-7	133.1	79.2	81.5	0.96	180.9	25.0
8-10	174.8	37.5	81.5	0.96	188.5	17.5
11-13	143.5	37.5	149.5	0.96	146.8	22.5
14-16	109.9	69.9	152.1	0.96	92.6	40.0
17-23	79.9	40.4	80.0	0.2	167.8	32.3
24-30	94.8	40.0	65.0	0.2	171.4	28.6
31-39	79.8	70.0	50.0	0.2	161.4	38.6
40-46	81.8	54.0	64.0	0.2	163.6	36.4
47-51	79.8	70.0	39.7	0.2	153.9	37.8

15

20

25

30

IOA = Isooctyl acrylate
 NVP = N-vinylpyrrolidone
 EOA = Ethylene oxide acrylate
 ABP = 4-acryloxybenzophenone
 EtOAc = ethyl acetate
 IPA = isopropyl alcohol

TABLE 2

Ex. No.	Ratio (IOA/NVP/EOA'/ABP)	IV	UVmj	MRad	J _s	MVTR up	MVTR invf	I _s	I ₂₄	Lift	Res	I _{wet}	Imrs ₂₄	Dmnd _s
1	30 / 40 / 29.9 / 0.1	0.84	100		0.41									
2			200		0.44	2148	2997	33	160	2.0	0.9	26	177	2.0
3			300		0.43									
4	53.2 / 31.7 / 15 / 0.1	0.91	100		1.42			135	510	0.9	1.7			
5			200		1.39	1180	1060	76	407	1.4	1.3	30	65	0.4
6			200					67	474	1.1	1.6			
7			300		1.36			53	317	1.2	0.9			
8	69.9 / 15 / 15 / 0.1	0.87	100		X									
9			200		X	1250	1412	124	118	1.7	3.7	39	32	
10			300		8.12									
11	57.4 / 15 / 27.5 / 0.1	0.96	100		X									
12			200		X	1792	6504	87	67	1.7	4.1	41	145	1.6
13			300		8.96									

IOA = Isooctyl acrylate
 NVP = N-vinylpyrrolidone
 EOA⁹ = Ethylene oxide acrylate with an average of 9 EO units per molecule.
 EOA¹⁶ = Ethylene oxide acrylate with an average of 16 EO units per molecule.
 ABP = 4-acryloxybenzophenone
 Ba = butyl acrylate

Ex. No.	Ratio (IOA/NVP/EOA'/ABP)	IV	UVmi	MRad	I _s	MVTR up	MVTR invl	T _s	T _w	Res	T _{wet}	Imrs ₂₄	Dmnd _{is}	
14	43.9 / 28 / 28 / 0.1	1.05	100		6.27	1998	8322	54	89	2.6	0.0	26	47	2.3
15			200		6.28									
16			300		5.01									
17	39.9 / 20 / 40 / 0.1	0.76	0	0	No Test									
18			0	2.71		1936	9493	134	160	1.8	2.5	21		
19			0	3.16				155	193	1.8	0.7			
20			100					123	156	2.8	1.0	54		
21			200	0	6.43	2002	6952	31	24	3.2	0.0	15		
22			200	2.94	5.51			15	0	5.0		360		2.6
23			300											

IOA = Isooctyl acrylate
 NVP = N-vinylpyrrolidone
 EOA⁹ = Ethylene oxide acrylate with an average of 9 EO units per molecule.
 EOA¹⁶ = Ethylene oxide acrylate with an average of 16 EO units per molecule.
 ABP = 4-acryloxybenzophenone
 Ba = EOA¹⁶ butyl acrylate

Ex. No.	Ratio (IOA/NVP/EOA'/ABP)	IV	UVmj	MRad	J _s	MVTR up	MVTR invl	T ₁	T ₂	Lift	Res	T _{wet}	Imrs ₂₄	Dmnd ₁₅
24	47.4 / 20 / 32.5 / 0.1	0.81	0	0	No Test	1738	7953	135	240	1.3	2.7	22		
25		0	0	2.71				164	268	1.0	0.7			
26		0	0	3.16				108	232	1.5	0.5	31		
27		100	100	0	3.08	1724	5458	33	72	1.7	0.0	14		
28		200	200	2.94	1.40			24	44	2.2	0.0		304	1.6
29		200	200											
30		300	300											
31	39.9 / 35 / 25 / 0.1	0.88	0	0	5.51	1909	9052	37	161	2.0	0.8	24		
32		0	0	2.71				83	209	1.7	0.0			
33		0	0	3.16										
34		50	50	3.21	1.12			25	104	2.1	0.1			
35		50	50		2.39			31	124	3.3	0.0	19		
36		100	100		1.87			10	13	4.2	0.0		655	2.4
37		200	200	2.94	0.70			16	39	2.3	0.0	15		
38		200	200	0	1.16	1882	5622							
39		300	300											

IOA = Isooctyl acrylate
 NVP = N-vinylpyrrolidone
 EOA' = Ethylene oxide acrylate with an average of 9 EO units per molecule.
 EOA¹⁶ = Ethylene oxide acrylate with an average of 16 EO units per molecule.
 ABP = 4-acryloxybenzophenone
 O = EOA¹⁶
 'Ba = butyl acrylate

Ex. No.	Ratio (IOA/NVP/EOA'/ABP)	IV	UV _{mi}	MRad	I _s	MVTR up	MVTR inv _t	T _o	T ₂₄	Lift	Res	T _{wet}	Imrs ₂₄	Dimnd _{is}
40	40.9 / 27 / 32 / 0.1	0.79	0	0	10.23			142	225	1.8	0.3			
41			0	3.16				85	202	2.0	2.0	34		
42			0	2.71		1962	8835	88	173	2.8	0.0	34		
43			100					25	40	3.3	0.0	14		
44			200	0	2.02	1882	5918	13	7	4.5	0.0		437	2.2
45			200	2.94	1.02									
46			300											
47			50					109	173	1.3	0.2			
48	42 / 36.8 / 20.90 ^o / 0.3	0.74	57		2.68								674	
49			108		2.18									
50			200					54	150	1.8	0.2			
51			208					11	68	1.9	0.2			442

IOA = Isooctyl acrylate
 NVP = N-vinylpyrrolidone
 EOA' = Ethylene oxide acrylate with an average of 9 EO units per molecule.
 EOA¹⁶ = Ethylene oxide acrylate with an average of 16 EO units per molecule.
 ABP = 4-acryloxybenzophenone
 o = EOA¹⁶
 'Ba = butyl acrylate

LEGEND

	Symbol	Meaning (units)
	$Imrs_{24}$	Absorption measured by the Immersion Technique (% of sample weight)
5	$Dmnd_{15}$	Absorption measured by the Demand Technique expressed as the slope of the line through the origin and at a point 15 minutes on the demand curve (g/hr)
10	IV	Inherent Viscosity (dl/g)
	J_3	Creep Compliance Measured After Three Minutes ($cm^2/dyne \cdot 10^{-5}$)
15	Lift	Lift (Extent of Premature Peeling)
	MRad	Sterilizing Gamma Radiation (megarads)
20	Res	Adhesive Residue (Extent to which residual adhesive remains on skin)
	UVmj	Ultra Violet Radiation (millijoules/cm ²)
25	$MVTR_{Up}$	Moisture Vapor Transmission Rate Measured with Upright Cup (g/m ² for 24 hrs)
	$MVTR_{Inv}$	Moisture Vapor Transmission Rate Measured w/ an Inverted Cup (g/m ² for 24 hrs)
30	T_0	Skin Adhesion at time (t) = 0 hrs (grams/2.54 cm width)
	T_{24}	Skin Adhesion at time (t) = 24 hrs (grams/2.54 cm width)
35	T_{WET}	Skin Adhesion to Wet Skin at time (t) = 0 hrs (grams/2.54 cm width)

While in accordance with the patent statutes,
description of the preferred weight fractions, and
processing conditions have been provided, the scope of the
5 invention is not to be limited thereto or thereby. Various
modifications and alterations of the present invention will
be apparent to those skilled in the art without departing
from the scope and spirit of the present invention.

10 Consequently, for an understanding of the scope of the
present invention, reference is made to the following
claims.

Claims:

1. An absorbent pressure-sensitive adhesive comprising a crosslinked copolymer of A, B, C and PX wherein:
- 5
- (a) A is an acrylate monomer selected from the group consisting of (i) an acrylate or methacrylate ester of a non-tertiary C₄₋₁₂ alcohol, and (ii) an acrylate or methacrylate ester of a mixture of
- 10 non-tertiary C₁₋₁₄ alcohols with a resultant average of between about 4-12 carbon atoms per alcohol molecule;
- (b) B is a hydrophilic alkylene oxide acrylate
- 15 monomer having an average of about 3 to 40 alkylene oxide units;
- (c) C is a hydrophilic N-vinyl lactam monomer; and
- 20 (d) PX is a crosslinking monomer effective for crosslinking the copolymer upon exposure to ultraviolet radiation.
2. The pressure-sensitive adhesive of claim 1 wherein
- 25 monomer B is an ethylene oxide acrylate.
3. The pressure-sensitive adhesive of claim 1 wherein monomer C is selected from the group consisting of N-vinyl pyrrolidone, N-vinyl-2-caprolactam, and combinations
- 30 thereof.
4. The pressure-sensitive adhesive of claim 1 wherein the adhesive comprises about 30 to 70 wt% monomer A, about 15 to 40 wt% monomer B, about 15 to 50 wt% monomer C, and
- 35 about 0.01 to 2 wt% crosslinking monomer PX.

5. The pressure-sensitive adhesive of claim 4 wherein the adhesive has (i) an $MVTR_{up, T_{24}}$ of at least 1000 g/m^2 , (ii) an $Imrs_{24}$ of at least about 300%, and (iii) an $Dmnd_{15}$ of at least 1.5 g/hr.

5

6. A precursor composition useful for making the absorbent pressure-sensitive adhesive of claim 1; the precursor composition comprising an uncrosslinked copolymer of A, B, C and PX wherein:

10

(a) A is a monomer selected from the group consisting of (i) an acrylate or methacrylate ester of a non-tertiary C_{4-12} alcohol, and (ii) an acrylate or methacrylate ester of a mixture of non-tertiary C_{1-14} alcohols averaging between about 4-12 carbon atoms per alcohol molecule;

15

(b) B is a hydrophilic alkylene oxide acrylate monomer having an average of about 3 to 40 alkylene oxide units;

20

(c) C is a hydrophilic N-vinyl lactam monomer; and

(d) PX is a crosslinking monomer effective for crosslinking the copolymer.

25

7. A wound dressing comprising a substrate coated with the absorbent pressure-sensitive adhesive of claim 1 on a major surface thereof, and a release liner protectively sandwiching the adhesive between the substrate and the liner.

30

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 94/03881

A. CLASSIFICATION OF SUBJECT MATTER

IPC 5 C08F220/18 C09J133/06 C09J7/02 A61L15/58

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 C08F C09J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 130 080 (JOHNSON & JOHNSON PROD. INC.) 2 January 1985 ---	
A	CHEMICAL ABSTRACTS, vol. 83, no. 24, 15 December 1975, Columbus, Ohio, US; abstract no. 194465, 'PRESSURE-SENSITIVE ADHESIVE COMPOSITIONS' page 57 ;column 1 ; see abstract & JP,A,7 565 535 (SAIDEN CHEMICAL CO.) -----	

 Further documents are listed in the continuation of box C. Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

2 August 1994

Date of mailing of the international search report

30.08.94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+ 31-70) 340-3016

Authorized officer

Cauwenberg, C

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 94/03881

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0130080	02-01-85	AU-B- 566553	22-10-87
		AU-A- 2990484	03-01-85
		CA-A- 1252244	04-04-89
		DE-A- 3471317	23-06-88
		JP-A- 60015478	26-01-85

JP-A-7565535		NONE	
