



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2079768 C 2002/11/19

(11)(21) **2 079 768**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(22) **Date de dépôt/Filing Date:** 1992/10/02

(41) **Mise à la disp. pub./Open to Public Insp.:** 1993/04/05

(45) **Date de délivrance/Issue Date:** 2002/11/19

(30) **Priorités/Priorities:** 1991/10/04 (3-283,847) JP;
1991/11/07 (3-319,899) JP

(51) **Cl.Int.⁵/Int.Cl.⁵** C08L 3/02, C08L 67/00

(72) **Inventeurs/Inventors:**

Tokiwa, Yutaka, JP;
Takagi, Sigeyuki, JP;
Koyama, Masatoshi, JP

(73) **Propriétaires/Owners:**

Director-General of Agency of Industrial Science and
Technology, JP;
Research Institute of Innovative Technology for the
Earth, JP;
Chuo Kagaku Co., Ltd., JP

(74) **Agent:** SIM & MCBURNEY

(54) **Titre :** PLASTIQUE BIODEGRADABLE QUI CONTIENT DE L'AMIDON, ET METHODE DE PRODUCTION

(54) **Title:** STARCH-CONTAINING BIODEGRADABLE PLASTIC AND METHOD OF PRODUCING SAME

(57) **Abrégé/Abstract:**

A biodegradable plastic composition, which may be in the form of a molded body, includes gelatinized starch and a biodegradable, aliphatic polyester resin having a melting point of 45-130 °C. The plastic is produced by kneading a blend containing a starchy substance selected from non-gelatinized, granular starch and gelatinized starch and the aliphatic polyester resin at a temperature higher than the melting point of the aliphatic polyester in the presence of water in an amount of 1-45 % based on the weight of the starchy substance.



STARCH-CONTAINING BIODEGRADABLE PLASTIC AND
METHOD OF PRODUCING SAME

Abstract

5 A biodegradable plastic composition, which may be in
the form of a molded body, includes gelatinized starch and a
biodegradable, aliphatic polyester resin having a melting point
of 45-130 °C. The plastic is produced by kneading a blend
containing a starchy substance selected from non-gelatinized,
granular starch and gelatinized starch and the aliphatic
10 polyester resin at a temperature higher than the melting point
of the aliphatic polyester in the presence of water in an amount
of 1-45 % based on the weight of the starchy substance.

STARCH-CONTAINING BIODEGRADABLE PLASTIC AND
METHOD OF PRODUCING SAME

This invention relates to a biodegradable plastic
5 material and a method of preparing same.

There is an increasing demand for a plastic material
which is decomposed by the action of microorganisms (bacteria,
yeast, fungi, etc.) or enzymes, thereby to lose the original
shape.

10 One well know biodegradable plastic material includes a
mixture of starch with a synthetic polymer such as a
polyethylene (Maddever and Chapman, "Modified Starch Based
Biodegradable Plastics", ANTEC '89, Soc. Plastics Eng.
Conference Proceedings pp. 1351-1355 (May 1-4, 1989)), an
15 ethylene/acrylic acid copolymer (US-A-4,138,784 and 4,337,181)
or an ethylene/vinyl alcohol copolymer (JP-A-Hei-3-31333).

In the above polyethylene-containing plastic material,
the starch is present as a filler within a matrix of the
polyethylene which is not biodegradable. Thus, the
20 biodegradability of this material is not satisfactory. While
the plastic material containing the ethylene/acrylic acid
copolymer has superior water resistance and mechanical
properties as compared with the polyethylene-containing
plastic material, the biodegradability is less satisfactory.
25 Regarding the ethylene/vinyl alcohol copolymer-containing
plastic material, the composition of the copolymer is not
disclosed so that it is not clear whether or not the copolymer
is biodegradable. This material has a problem that pin holes
are apt to be formed in films obtained therefrom because
30 bubbles are unavoidably formed by vaporization of water during
kneading of the raw materials.

The present invention has been made with the foregoing
problems of the conventional plastic materials in view.

- 2 -

Other aspects of this invention are as follows:

A biodegradable plastic material comprising a mixture of gelatinized starch with a biodegradable, aliphatic polyester resin having a melting point of 45°-130°C.

5 A method of producing a biodegradable plastic material comprising the steps of:

providing a blend containing gelatinized starch and a biodegradable, aliphatic polyester resin having a melting point of 45°-130°C; and

10 kneading said blend at a temperature higher than the melting point of said aliphatic polyester but lower than the decomposition temperature of said gelatinized starch in the presence of water in an amount of 1-45% based on the weight of said gelatinized starch.

A biodegradable plastic material comprising a matrix of a biodegradable, aliphatic polyester resin having a melting point of 45°-130°C; 15 and gelatinized starch dispersed in said matrix, wherein said gelatinized starch is present in an amount of 30-90% based on the total weight of said aliphatic polyester resin and said gelatinized starch.

A process for producing a biodegradable plastic molding, comprising the steps of:

20 providing a molten mixture containing a biodegradable, aliphatic polyester resin having a melting point of 45°-130°C, and gelatinized starch, wherein the weight ratio of said polyester resin to said gelatinized starch is 10:90 to 70:30; and

25 extruding said mixture through a die under the conditions satisfying the following expressions:

$$100 > n_s / n_e \geq 0.8$$

$$n_e \geq 600$$

30 wherein n_e and n_s stand for the viscosity, in terms of poise, of the aliphatic polyester resin and the gelatinized starch, respectively, at the extrusion temperature.

- 2a -

A method of producing a biodegradable plastic material comprising the steps of:

5 providing a blend containing a non-gelatinized, granular starch and a biodegradable, aliphatic polyester resin having a melting point of 45°-130°C; and

10 kneading said blend at a temperature higher than the melting point of said aliphatic polyester but lower than the decomposition temperature of said starch in the presence of water in an amount of 1-45% based on the weight of said starch to gelatinize said starch.

The present invention will now be described in detail below.

15 The term "starch" as used herein is intended to refer to any type of non-modified and modified starches and includes starches or starch-containing materials of natural, vegetable origin composed mainly of amylose and/or amylopectin, and modified starch products. Illustrative of suitable starches and

starch-containing materials are potato starch, corn starch, wheat starch, tapioca starch, rice starch, sweet potato starch, sago starch, waxy corns, high amylose corns, wheat flour and rice flour. Polysaccharides such as guar gum, chitin and chitosan may also be usable. Examples of modified starch products include starches onto which a monomer such as an acrylate, a methacrylate, an olefin or styrene is grafted; products obtained by reaction of starches with a fatty acid; and starches modified by dextrinization, oxidation, acidification, alphanization, etherification, esterification and cross-linking. In addition, destructured starches obtained by heat-treating water-containing starch at a temperature of 105-190 °C (EP-A-0327505) are included within the scope of the modified starches.

The term "gelatinized starches" as used herein is intended to refer to products obtained by treating the above starches by any known gelatinization method such as by heating in the presence of water at a temperature of about 40 °C or more. Gelatinization may also be effected by kneading starch granules in the presence of 1-45 % by weight of water for a period of time sufficient to disrupt the granules.

The term "plastic material" as used herein is intended to refer both to a plastic composition to be used as raw material for the production of shaped or molded articles and to a plastic molding or shaped body obtained from the composition.

The aliphatic polyester resin used in the present invention should be biodegradable. Illustrative of suitable biodegradable polyester resin are polyethylene adipate, polyethylene suberate, polyethylene azelate, polyethylene decamethylate, polytetramethylene succinate, polytetramethylene adipate, polypropiolactone, polycaprolactone and block copolymers of the above esters with polyamide. The use of polycaprolactone is especially preferred. It is also important that the aliphatic polyester resin have a melting point of 45-130 °C, preferably 50-120 °C. When the melting point is lower than 45 °C, the resulting molded product tends to thermally deform at room temperature. Too high a melting point in excess

of 130 °C is disadvantageous because vaporization of water considerably occurs to cause the formation of bubbles in the molded product.

5 The biodegradable plastic material according to the present invention comprises a mixture of the above gelatinized starch with the above biodegradable, aliphatic polyester. The amount of the gelatinized starch is generally 2-98 %, preferably 10-95 %, more preferably 30-90 %, most preferably 40-85 %, based on the total weight of the gelatinized starch and the aliphatic
10 polyester.

In addition to the above mixture, the plastic material of this invention may contain various additives such as a biodegradable plasticizer, a weatherability improving agent (e.g. UV stabilizer), a germicide, a herbicide, a fertilizer, an
15 anti-oxidation agent, a surfactant, a filler, a starch stabilizer and a pigment. Illustrative of suitable plasticizers are ethylene glycol, propylene glycol, polyethylene glycol and polypropylene glycol with a number average molecular weight of 200-4000, glycerin and sorbitol. The plasticizer is used in an
20 amount of 0.5-100 % based on the weight of the gelatinized starch.

The plastic material may be prepared by kneading a blend of ungelatinized or gelatinized starch, an aliphatic polyester resin and an additive (optional) in the presence of
25 water at a temperature higher than the melting point of the aliphatic polyester resin but lower than the decomposition point of the starch. When polycaprolactone is used as the aliphatic polyester resin, the kneading is generally performed at a temperature of 70-130 °C, preferably 80-110 °C. Ungelatinized
30 starch is gelatinized as a result of the kneading. The amount of the water is generally 1-45 %, preferably 12-45 %, based on the weight of the starch on dry basis. The water to be present in the kneading system may be derived from that contained in the raw material starch and/or that added at the start of the
35 kneading operation. The kneaded mixture is then shaped into any desired shape such as a pellet, sheet, film, plate, rod, pipe or

receptacle. In one preferred embodiment according to the present invention, gelatinization of starch, kneading and molding are simultaneously performed using an extruder.

5 The plastic material according to the present invention preferably has a structure in which the aliphatic polyester resin, which exhibits good resistance to water, forms a matrix and the gelatinized starch, which is poor in water resistance, is dispersed in the matrix. Such a plastic material exhibits satisfactory resistance to water since the gelatinized starch
10 which is poor in water resistance is covered with the matrix of the aliphatic polyester resin which has good resistance to water.

The plastic material in which the polyester resin forms a matrix may be suitably obtained extruding a molten mixture of
15 an aliphatic polyester and gelatinized starch through a die under the conditions satisfying the following expressions:

$$100 > n_s/n_e \geq 0.8, \text{ preferably } 50 > n_s/n_e \geq 0.8, \text{ and} \\ n_e \geq 600, \text{ preferably } n_e \geq 900$$

wherein n_e and n_s stand for the viscosities, in terms of poise,
20 of the aliphatic polyester resin and the gelatinized starch, respectively, at the extrusion temperature. The above conditions can be achieved by suitably selecting the kind and/or the molecular weight of the aliphatic polyester resin and/or by suitably selecting the water content of the gelatinized starch.
25 As described previously, ungelatinized starch may be fed as such to an extruder since gelatinization thereof occurs before extrusion through the die.

The plastic material of this invention is capable of being consumed by microorganisms in an environment suitable for
30 the growth of the microorganisms to cause reduction of the weight and volume of the plastic material with time. Thus, the plastic material may be used as daily necessities such as disposable packages in the form of a case, a bottle or the like receptacle, as agricultural materials such as a green house
35 construction film, a soil cover sheet, a nursery pot, a fertilizer bag or a pesticidal carrier, as a leisure goods such

as a bag, a packing material for fishing equipments and as a material for drug delivery systems.

The following examples will further illustrate the present invention. Percentages are by weight.

5

Preparation of Plastic Materials:

Example 1

Granular cornstarch (9217 g) having a water content of 13.2 % was placed into a kneader, over which were sprayed 783 g of water. The total water content is 25 % based on the weight of the starch on dry basis. After the contents in the kneader had been kneaded for about 1 hour, 2000 g of polycaprolactone (PCL) were added and the mixture was kneaded for about 30 minutes. The resulting mixture was charged into a hopper of a biaxial extruder and extruded through a T-die at a feed rate of 10 kg/hour, a screw revolution speed of 100 rpm and a barrel temperature gradient of 30-80-95 °C to obtain a uniform film free of air bubbles. The n_e and n_s values measured at 95 °C with a flow tester (orifice diameter: 1 mm) are found to be 113,000 poises and 1,600,000 poises, respectively, so that n_s/n_e is 14.2.

Examples 2-4

Example 1 was repeated in the same manner as described except that the amount of water sprayed was changed to 1183 g (total water content: 30 %), 1983 g (total water content: 40 %) and 0 g (total water content: 15.2 %). The films thus obtained were uniform and free of air bubbles.

Example 5

Granular cornstarch having a water content of 13.2 % was placed into an oven and maintained at 110 °C until the water content of 6 % was reached. The resulting cornstarch (8511 g) was kneaded together with 2000 g of PCL for about 1 hour. The resulting mixture was then extruded in the same manner as that in example 1 to give a uniform film free of air bubbles.

Comparative Example 1

Example 1 was repeated in the same manner as described except that no PCL was used.

5 Examples 6-9

Example 1 was repeated in the same manner as described except that the amount of PCL was changed to 889 g (Example 6), 3429 g (Example 7), 8000 g (Example 8) and 18667 g (Example 9).

10 Water Resistance:

Example 10

Each of the films (0.1 g) obtained in Examples 1-9 and Comparative Example 1 was sliced to a thickness of about 100 μm . The sliced sample was placed into a flask containing 20 ml of
15 water at 30 °C and shaken for 16 hours while maintaining at that temperature. The mixture was then filtered and the filtrate was measured for its total organic carbon concentration (TOC). The results are summarized in Table 1 below.

20 Biodegradability:

Example 11

Each of the films (0.1 g) obtained in Examples 1-9 and Comparative Example 1 was sliced to a thickness of about 100 μm . The sliced sample was placed into a flask containing 20 ml of
25 water containing alpha-amylase and lipase and shaken for 16 hours while maintaining at 30 °C. The mixture was then filtered and the filtrate was measured for its total organic carbon concentration (TOC). The results are summarized in Table 1 below.

30 In Table 1, the term "total water content" refers to percentage of water based on the weight of starch on dry basis and the term "content of gelatinized starch" refers to percentage of the weight of the starch on dry basis based on the total weight of the starch and PCL.

Table 1

	Example No.	Total Water Content (%)	Content of Gelatinized Starch (%)	n_s/n_e	Water Resistance TOC (ppm)	Biodegradability TOC (ppm)
5	1	25	80	14.2	24	1747
	2	30	80	3.2	28	1877
	3	40	80	0.9	34	1970
10	4	15.2	80	43.5	4	1624
	5	6	80	93.7	4	1451
	6	25	90	14.2	30	1710
	7	25	70	14.2	22	1045
	8	25	50	14.2	10	650
15	9	25	30	14.2	6	443
	Comp.1	25	100	-	700	1510

From the results shown in Table 1, it will be appreciated that the TOC values in the water resistance test of the films of Examples 1-9 are much lower than that of Comparative Example 1. This indicates that the dissolution of starch in water was reduced in the case of the films of this invention. Especially, the films of Examples 4, 5, 8 and 9 in which PCL forms a matrix exhibit excellent water resistance. The results of the biodegradability test summarized in Table 1 show that the films of this invention have satisfactory biodegradability. The TOC value of a film formed only of PCL is found to be 350 ppm.

30 Preparation of Plastic Materials:

Example 12

Acid-treated starch (9281 g) having a water content of 13.8 % was placed into a kneader, over which was sprayed a mixed liquid consisting of 719 g of water and 800 g of glycerin. The total water content is 25 % based on the weight of the starch on dry basis. The glycerin content is 10 % based on the weight of

the starch on dry basis. After the contents in the kneader had been kneaded for about 1 hour, 2000 g of polypropiolactone were added and the mixture was kneaded for about 30 minutes. The resulting mixture was charged into a hopper of a biaxial extruder and extruded through a T-die at a feed rate of 15 kg/hour, a screw revolution speed of 60 rpm and a barrel temperature gradient of 30-85-105 °C to obtain a uniform, flexible film free of air bubbles. The n_s/n_e value was found to be 14.2. The film was tested for water resistance and biodegradability in the same manner as above to reveal that the TOC values in water resistance test and biodegradability test are 81 ppm and 2211 ppm, respectively.

Example 13

Example 12 was repeated in the same manner as described except that white dextrin and polyethylene adipate were substituted for the acid treated starch and the polypropiolactone, respectively. The n_s/n_e value was found to be 81.3. The film obtained was tested for water resistance and biodegradability in the same manner as above to reveal that the TOC values in water resistance test and biodegradability test are 70 ppm and 1300 ppm, respectively.

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A biodegradable plastic material comprising a mixture of gelatinized starch with a biodegradable, aliphatic polyester resin having a melting point of 45°-130°C.
2. A biodegradable plastic material as claimed in Claim 1, wherein the amount of said gelatinized starch is 2-98% based on the total weight of said aliphatic polyester resin and said gelatinized starch.
3. A biodegradable plastic material as claimed in Claim 1, wherein said aliphatic polyester resin is a polycaprolactone.
4. A method of producing a biodegradable plastic material comprising the steps of:
 - providing a blend containing gelatinized starch and a biodegradable, aliphatic polyester resin having a melting point of 45°-130°C; and
 - kneading said blend at a temperature higher than the melting point of said aliphatic polyester but lower than the decomposition temperature of said gelatinized starch in the presence of water in an amount of 1-45% based on the weight of said gelatinized starch.
5. A method as claimed in Claim 4, further comprising molding said kneaded blend into a desired shape.
6. A biodegradable plastic material comprising a matrix of a biodegradable, aliphatic polyester resin having a melting point of 45°-130°C; and gelatinized starch dispersed in said matrix, wherein said gelatinized starch is present in an amount of 30-90% based on the total weight of said aliphatic polyester resin and said gelatinized starch.
7. A biodegradable plastic material as claimed in Claim 6, wherein said aliphatic polyester resin is a polycaprolactone.

8. A process for producing a biodegradable plastic molding, comprising the steps of:

providing a molten mixture containing a biodegradable, aliphatic polyester resin having a melting point of 45°-130°C, and gelatinized starch, wherein the weight ratio of said polyester resin to said gelatinized starch is 10:90 to 70:30; and

extruding said mixture through a die under the conditions satisfying the following expressions:

$$100 > n_s / n_e \geq 0.8$$
$$n_e \geq 600$$

wherein n_e and n_s stand for the viscosity, in terms of poise, of the aliphatic polyester resin and the gelatinized starch, respectively, at the extrusion temperature.

9. A process as claimed in Claim 8, wherein said molten mixture further contains water in an amount of 1-45% based on the weight of said gelatinized starch.

10. A method of producing a biodegradable plastic material comprising the steps of:

providing a blend containing a non-gelatinized, granular starch and a biodegradable, aliphatic polyester resin having a melting point of 45°-130°C; and

kneading said blend at a temperature higher than the melting point of said aliphatic polyester but lower than the decomposition temperature of said starch in the presence of water in an amount of 1-45% based on the weight of said starch to gelatinize said starch.

11. A method as claimed in Claim 10, further comprising molding said kneaded blend into a desired shape.

