



US011925066B2

(12) **United States Patent**  
**Lim et al.**

(10) **Patent No.:** **US 11,925,066 B2**  
(45) **Date of Patent:** **Mar. 5, 2024**

(54) **DISPLAY DEVICE**

(71) Applicant: **LG Display Co., Ltd.**, Seoul (KR)

(72) Inventors: **Kyoung-Nam Lim**, Gyeongsangbuk-do (KR); **Yu-Ho Jung**, Paju-si (KR); **Dong-Young Kim**, Paju-si (KR)

(73) Assignee: **LG Display Co., Ltd.**, Seoul (KR)

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **17/964,805**

(22) Filed: **Oct. 12, 2022**

(65) **Prior Publication Data**

US 2023/0035377 A1 Feb. 2, 2023

**Related U.S. Application Data**

(63) Continuation of application No. 17/125,912, filed on Dec. 17, 2020, now Pat. No. 11,502,149, which is a (Continued)

(30) **Foreign Application Priority Data**

Dec. 19, 2017 (KR) ..... 10-2017-0175083

(51) **Int. Cl.**

**H10K 59/121** (2023.01)

**H01L 27/12** (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC ..... **H10K 59/1213** (2023.02); **H01L 27/1244** (2013.01); **H10K 59/1216** (2023.02);

(Continued)

(58) **Field of Classification Search**

CPC ..... H01K 59/1213; H01K 59/123; H01K 59/124; H10K 59/1213; H10K 59/1216;

(Continued)

(56) **References Cited**

**U.S. PATENT DOCUMENTS**

9,082,667 B2 7/2015 Youn et al.

9,293,485 B2 3/2016 Youn et al.

(Continued)

**FOREIGN PATENT DOCUMENTS**

CN 104183600 A 12/2014

CN 104752485 A 7/2015

(Continued)

**OTHER PUBLICATIONS**

European Patent Office, Extended European Search Report and Opinion, EP Patent Application No. 18212522.9, dated Apr. 30, 2019, seven pages.

(Continued)



*Primary Examiner* — Antonio B Crite

(74) *Attorney, Agent, or Firm* — Fenwick & West LLP

(57) **ABSTRACT**

Disclosed is a display device that with low power consumption. The display device includes a first thin film transistor having a polycrystalline semiconductor layer in an active area and a second thin film transistor having an oxide semiconductor layer in the active area, wherein at least one opening disposed in a bending area has the same depth as one of a plurality of contact holes disposed in the active area, whereby the opening and the contact holes are formed through the same process, and the process is therefore simplified, and wherein a high-potential supply line and a low-potential supply line are disposed so as to be spaced apart from each other in the horizontal direction, whereas a reference line and the low-potential supply line are disposed so as to overlap each other, thereby preventing signal lines from being shorted.

**20 Claims, 22 Drawing Sheets**



**Related U.S. Application Data**

continuation of application No. 16/805,286, filed on Feb. 28, 2020, now Pat. No. 10,903,296, which is a continuation of application No. 16/210,815, filed on Dec. 5, 2018, now Pat. No. 10,615,236.

(51) **Int. Cl.**

**H01L 29/786** (2006.01)  
**H10K 59/123** (2023.01)  
**H10K 59/124** (2023.01)  
**H10K 59/126** (2023.01)  
**H10K 59/131** (2023.01)  
**H10K 77/10** (2023.01)  
**H10K 59/12** (2023.01)  
**H10K 59/35** (2023.01)  
**H10K 102/00** (2023.01)

(52) **U.S. Cl.**

CPC ..... **H10K 59/123** (2023.02); **H10K 59/124** (2023.02); **H10K 59/126** (2023.02); **H10K 59/131** (2023.02); **H10K 77/111** (2023.02); **H01L 27/1225** (2013.01); **H01L 27/1251** (2013.01); **H01L 27/1255** (2013.01); **H01L 27/1274** (2013.01); **H01L 27/1288** (2013.01); **H01L 29/78633** (2013.01); **H01L 29/78675** (2013.01); **H01L 29/7869** (2013.01); **H10K 59/1201** (2023.02); **H10K 59/353** (2023.02); **H10K 2102/311** (2023.02); **H10K 2102/341** (2023.02)

(58) **Field of Classification Search**

CPC .. H10K 59/124; H10K 59/126; H10K 59/123; H10K 27/1251; H10K 77/111  
 See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

9,318,427 B2 4/2016 Youn et al.  
 9,647,052 B2 5/2017 Youn et al.  
 9,786,229 B2 10/2017 Lee et al.  
 9,954,043 B2 4/2018 Park et al.  
 10,109,704 B2 10/2018 Shin et al.  
 10,224,344 B2 3/2019 Lee et al.  
 10,475,868 B2 11/2019 Park et al.  
 10,573,704 B2 2/2020 Cai  
 10,679,567 B2 6/2020 Lee et al.  
 10,692,442 B2 6/2020 Lee et al.  
 2014/0217373 A1 8/2014 Youn et al.  
 2014/0306941 A1 10/2014 Kim et al.  
 2014/0353670 A1 12/2014 Youn et al.  
 2014/0368228 A1 12/2014 Kim  
 2015/0187279 A1 7/2015 Lee et al.  
 2015/0243722 A1 8/2015 Kwon et al.

2015/0287750 A1 10/2015 Youn et al.  
 2016/0064421 A1 3/2016 Oh et al.  
 2016/0079336 A1 3/2016 Youn et al.  
 2016/0093644 A1 3/2016 Ki et al.  
 2016/0218305 A1 7/2016 Kim et al.  
 2017/0069701 A1 3/2017 Cai  
 2017/0170206 A1 6/2017 Lee et al.  
 2017/0194404 A1 7/2017 Park et al.  
 2017/0222184 A1 8/2017 Park  
 2017/0262109 A1 9/2017 Choi et al.  
 2017/0288007 A1 10/2017 Shin et al.  
 2018/0012551 A1 1/2018 Lee et al.  
 2018/0068621 A1 3/2018 Lee et al.  
 2018/0090699 A1 3/2018 Shin et al.  
 2018/0204896 A1 7/2018 Park et al.  
 2019/0157312 A1 5/2019 Lee et al.  
 2019/0181198 A1\* 6/2019 Son ..... H10K 71/00  
 2020/0243022 A1 7/2020 Lee et al.

FOREIGN PATENT DOCUMENTS

CN 104795403 A 7/2015  
 CN 106887447 A 6/2017  
 CN 106935628 A 7/2017  
 EP 2814074 A1 12/2014  
 EP 2889866 A2 7/2015  
 EP 3174097 A1 5/2017  
 EP 3188269 A1 7/2017  
 JP 2007-318106 A 12/2007  
 JP 2011-209405 A 10/2011  
 JP 2012-238005 A 12/2012  
 JP 2016-224118 A 12/2016  
 JP 2017-173505 A 9/2017  
 KR 10-2014-0099164 A 8/2014  
 KR 10-2015-0101409 A 9/2015  
 KR 10-2015-0101418 A 9/2015  
 KR 10-2016-0018048 A 2/2016  
 KR 10-2016-0027907 A 3/2016  
 KR 10-2016-0093202 A 8/2016  
 KR 10-2017-0106621 A 9/2017  
 KR 10-2017-0114029 A 10/2017  
 KR 10-2017-0136484 A 12/2017  
 KR 10-2018-0137640 A 12/2018  
 WO WO 2016/203340 A1 12/2016

OTHER PUBLICATIONS

Japan Patent Office, Notice of Reasons for Refusal, JP Patent Application No. 2018-228385, dated Nov. 26, 2019, five pages.  
 Korean Intellectual Property Office, Office Action, KR Patent Application No. 10-2017-0175083, dated May 20, 2019, 11 pages (with concise explanation of relevance).  
 China National Intellectual Property Administration, First Notification of Office Action, CN Patent Application No. 201811512305.5, dated Oct. 12, 2020, 17 pages.  
 United States Office Action, U.S. Appl. No. 16/805,286, filed Apr. 30, 2020, nine pages.

\* cited by examiner

FIG. 1




FIG.2




FIG.3A




FIG.3B




FIG.4A




FIG.4B




FIG.5




FIG. 6






FIG.8




FIG.9A




FIG.9B




FIG.9C





FIG.9D





FIG.9E




FIG.9F




FIG.9G




FIG.9H




FIG.9I




FIG.9J




FIG.9K





FIG.9L





# 1

## DISPLAY DEVICE

### CROSS-REFERENCE TO RELATED APPLICATIONS

This application is a continuation of U.S. patent application Ser. No. 17/125,912 filed on Dec. 17, 2020 which is a continuation of U.S. patent application Ser. No. 16/805,286 filed on Feb. 28, 2020 which is a continuation of U.S. patent application Ser. No. 16/210,815 filed on Dec. 5, 2018 which claims the benefit of Republic of Korea Patent Application No. 10-2017-0175083, filed on Dec. 19, 2017, each of which is hereby incorporated by reference in its entirety.

### BACKGROUND

#### Field of Technology

The present disclosure relates to a display device, and more particularly to a display device that is capable of realizing low power consumption.

#### Discussion of the Related Art

Image display devices, which are a core technology in the information and communication age and serve to display various kinds of information on a screen, have been developed such that the image display devices are thinner, lighter, and portable and exhibit high performance. As a result, flat panel display devices that have lower weight and volume than cathode ray tubes (CRT) have received a great deal of attention.

Representative examples of such flat panel display devices may include a liquid crystal display (LCD) device, a plasma display panel (PDP) device, an organic light-emitting display (OLED) device, and an electrophoretic display (ED) device.

With the active development of personal electronic devices, portable and/or wearable flat panel display devices have been developed. A display device capable of realizing low power consumption is required in order to be applied to portable and/or wearable devices. However, display devices developed to date have difficulty in realizing low power consumption.

### SUMMARY

Accordingly, the present disclosure is directed to a display device that substantially obviates one or more problems due to limitations and disadvantages of the related art.

An object of the present disclosure is to provide a display device that is capable of realizing low power consumption.

Additional advantages, objects, and features of the invention will be set forth in part in the description which follows and in part will become apparent to those having ordinary skill in the art upon examination of the following, or may be learned from practice of the invention. The objectives and other advantages of the invention may be realized and attained by the structure particularly pointed out in the written description and claims hereof as well as the appended drawings.

To achieve these objects and other advantages and in accordance with the purpose of the disclosure, as embodied and broadly described herein, a display device includes a first thin film transistor having a polycrystalline semiconductor layer in an active area and a second thin film transistor having an oxide semiconductor layer in the active

# 2

area, thereby realizing low power consumption, wherein at least one opening disposed in a bending area has the same depth as one of a plurality of contact holes disposed in the active area, whereby the opening and the contact holes are formed through the same process, and the process is therefore simplified, and wherein a high-potential supply line and a low-potential supply line, the voltage difference between which is large, are disposed so as to be spaced apart from each other in the horizontal direction, whereas a reference line and the low-potential supply line, the voltage difference between which is small, are disposed so as to overlap each other, thereby preventing signal lines from being shorted.

It is to be understood that both the foregoing general description and the following detailed description of the present invention are exemplary and explanatory and are intended to provide further explanation of the invention as claimed.

### BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are included to provide a further understanding of the disclosure and are incorporated in and constitute a part of this application, illustrate embodiment(s) of the disclosure and together with the description serve to explain the principle of the invention. In the drawings:

FIG. 1 is a plan view showing a display device according to the present disclosure;

FIG. 2 is a sectional view showing the display device taken along line I-I' of FIG. 1 according to present disclosure;

FIGS. 3A and 3B are plan views showing subpixels disposed in an active area shown in FIG. 1 according to present disclosure;

FIGS. 4A and 4B are plan views showing embodiments of a signal link disposed in a bending area shown in FIG. 1 according to present disclosure;

FIG. 5 is a circuit diagram illustrating each subpixel of the display device shown in FIG. 1 according to present disclosure;

FIG. 6 is a plan view showing the subpixel shown in FIG. 5 according to present disclosure;

FIG. 7A is a sectional view showing an organic light-emitting display device taken along lines II-II' and III-III' of FIG. 6, and FIG. 7B is a sectional view showing an organic light-emitting display device taken along lines IV-IV', and V-V' of FIG. 6 according to the present disclosure;

FIG. 8 is a sectional view showing another embodiment of a bending area shown in FIG. 7 according to the present disclosure; and

FIGS. 9A to 9M are sectional views illustrating a method of manufacturing the organic light-emitting display device shown in FIG. 7.

### DETAILED DESCRIPTION OF THE INVENTION

Reference will now be made in detail to the embodiments of the present disclosure, examples of which are illustrated in the accompanying drawings.

FIG. 1 is a plan view showing a display device according to the present invention, and FIG. 2 is a sectional view showing the display device according to the present disclosure.

The display device shown in FIGS. 1 and 2 includes a display panel **200**, a scan driver **202**, and a data driver **204**.

The display panel **200** is divided into an active area **AA** provided on a substrate **101** and a non-active area **NA** disposed around the active area **AA**. The substrate **101** is made of a plastic material that exhibits high flexibility, by which the substrate **101** is bendable. For example, the substrate **101** may be made of polyimide (PI), polyethylene terephthalate (PET), polyethylene naphthalate (PEN), polycarbonate (PC), polyether sulfone (PES), polyacrylate (PAR), polysulfone (PSF), or cyclic olefin copolymer (COC).

The active area **AA** displays an image through unit pixels arranged in a matrix form. Each unit pixel may include red (R), green (G), and blue (B) subpixels. Alternatively, each unit pixel may include red (R), green (G), blue (B), and white (W) subpixels. For example, as shown in FIG. 3A, the red (R), green (G), and blue (B) subpixels may be arranged along the same imaginary horizontal line. Alternatively, as shown in FIG. 3B, the red (R), green (G), and blue (B) subpixels may be spaced apart from each other so as to form an imaginary triangular structure.

Each subpixel includes at least one of a thin film transistor having an oxide semiconductor layer or a thin film transistor having a polycrystalline semiconductor layer. A thin film transistor having an oxide semiconductor layer and a thin film transistor having a polycrystalline semiconductor layer exhibit higher electron mobility than a thin film transistor having an amorphous semiconductor layer. Consequently, it is possible to realize high resolution and low power consumption.

At least one of the data driver **204** or the scan driver **202** may be disposed in the non-active area **NA**.

The scan driver **202** drives scan lines of the display panel **200**. The scan driver **202** is configured using at least one of a thin film transistor having an oxide semiconductor layer or a thin film transistor having a polycrystalline semiconductor layer. The thin film transistor of the scan driver **202** is simultaneously formed in the same process as that for forming at least one thin film transistor disposed at each subpixel in the active area **AA**.

The data driver **204** drives data lines of the display panel **200**. The data driver **204** is mounted on the substrate **101** in the form of a chip, or is mounted on a signal transport film **206** in the form of a chip. The data driver **204** is attached to the non-active area **NA** of the display panel **200**. As shown in FIGS. 4A and 4B, a plurality of signal pads **PAD** are disposed in the non-active area **NA** so as to be electrically connected to the signal transport film **206**. Drive signals generated from the data driver **204**, the scan driver **202**, a power supply unit (not shown), and a timing controller (not shown) are supplied to signal lines disposed in the active area **AA** via the signal pads **PAD**.

The non-active area **NA** includes a bending area **BA** that enables the display panel **200** to be bent or folded. The bending area **BA** is an area that is bent in order to locate non-display areas, such as the signal pads **PAD**, the scan driver **202**, and the data driver **204**, on the rear surface of the active area **AA**. As shown in FIG. 1, the bending area **BA** is disposed in the upper part of the non-active area **NA**, which is located between the active area **AA** and the data driver **204**. Alternatively, the bending area **BA** may be disposed in at least one of the upper, lower, left, or right part of the non-active area **NA**. Consequently, the area ratio of the active area **AA** to the entire screen of the display device is maximized, and the area ratio of the non-active area **NA** to the entire screen of the display device is minimized.

A signal link **LK** disposed in the bending area **BA** connects the signal pads **PAD** with the signal lines disposed

in the active area **AA**. In the case in which the signal link **LK** is formed in a straight line in the bending direction **BD**, the greatest bending stress may be applied to the signal link **LK**, whereby the signal link **LK** may be cracked or cut. According to the present disclosure, therefore, the signal link **LK** is configured to have a wide area in the direction that intersects the bending direction **BD** in order to minimize the bending stress applied to the signal link **LK**. To this end, as shown in FIG. 4A, the signal link **LK** may be formed in a zigzag shape or in the shape of a sine wave. Alternatively, as shown in FIG. 4B, the signal link **LK** may be formed in a shape in which a plurality of hollow diamonds is connected in a line.

In addition, as shown in FIG. 2, at least one opening **212** is disposed in the bending area **BA** such that the bending area **BA** can be easily bent. The opening **212** is formed by removing a plurality of inorganic dielectric layers **210**, which are disposed in the bending area **BA** and form cracks in the bending area **BA**. Specifically, when the substrate **101** is bent, bending stress is continuously applied to the inorganic dielectric layers **210** disposed in the bending area **BA**. Since the inorganic dielectric layers **210** exhibit lower elasticity than an organic dielectric material, cracks may be easily formed in the inorganic dielectric layers **210**. The cracks formed in the inorganic dielectric layers **210** spread to the active area **AA** along the inorganic dielectric layers **210**, which leads to line defects and device-driving deterioration. Consequently, at least one planarization layer **208**, made of an organic dielectric material that exhibits higher elasticity than the inorganic dielectric layers **210**, is disposed in the bending area **BA**. The planarization layer **208** may reduce bending stress generated when the substrate **101** is bent, whereby the formation of cracks may be prevented. The opening **212** in the bending area **BA** is formed through the same mask process as that for forming at least one of a plurality of contact holes disposed in the active area **AA**, whereby the structure and process may be simplified.

A display device having a simplified structure and process may be applied to a display device that requires a thin film transistor, such as a liquid crystal display device or an organic light-emitting display device. Hereinafter, an embodiment of the present disclosure in which a display device having a simplified structure and process is applied to an organic light-emitting display device will be described.

As shown in FIG. 5, each subpixel **SP** of the organic light-emitting display device includes a pixel-driving circuit and a light-emitting device **130** connected to the pixel-driving circuit.

As shown in FIG. 5, the pixel-driving circuit may be configured to have a 4T1C structure having four thin film transistors **ST1**, **ST2**, **ST3**, and **DT** and a storage capacitor **Cst**. Here, the structure of the pixel-driving circuit is not limited to the structures shown in FIG. 5. Various kinds of pixel-driving circuits may be used.

The storage capacitor **Cst** of the pixel-driving circuit shown in FIG. 5 is connected between a gate node **Ng** and a source node **Ns** in order to maintain voltage between the gate node **Ng** and the source node **Ns** uniform during a light emission period. The drive transistor **DT** includes a gate electrode connected to the gate node **Ng**, a drain electrode connected to a drain node **Nd**, and a source electrode connected to the light-emitting device **130**. A drive transistor **DT** controls the magnitude of drive current based on voltage between the gate node **Ng** and the source node **Ns**. The light-emitting device **130** is connected between the source node **Ns**, which is connected to the source electrode of the drive transistor **DT**, and a low-potential supply line **162** in order to emit light based on drive current.

The first switching transistor ST1 shown in FIGS. 5 and 6 includes a gate electrode 152 connected to a first scan line SL1, a drain electrode 158 connected to a source node Ns, a source electrode 156 connected to a data line DL, and a semiconductor layer 154 that forms a channel between the source and drain electrodes 156 and 158. The first switching transistor ST1 is turned on in response to a scan control signal SC1 from the first scan line SL1 in order to supply data voltage Vdata from the data line DL to the source node Ns.

The second switching transistor ST2 includes a gate electrode GE connected to a second scan line SL2, a drain electrode DE connected to a reference line RL, a source electrode SE connected to a gate node Ng, and a semiconductor layer ACT that forms a channel between the source and drain electrodes SE and DE. The second switching transistor ST2 is turned on in response to a scan control signal SC2 from the second scan line SL2 in order to supply a reference voltage Vref from the reference line RL to the gate node Ng.

The third switching transistor ST3 includes a gate electrode GE connected to an emission control line EL, a drain electrode DE connected to the drain node Nd, a source electrode SE connected to the high-potential supply line 172, and a semiconductor layer ACT that forms a channel between the source and drain electrodes SE and DE. The third switching transistor ST3 is turned on in response to an emission control signal EM from the emission control line EL in order to supply high-potential voltage VDD from the high-potential supply line 172 to the drain node Nd.

Each of the high-potential supply line 172 and the low-potential supply line 162, which are included in the pixel-driving circuit, is formed in a mesh shape so as to be shared by at least two subpixels. To this end, the high-potential supply line 172 includes first and second high-potential supply lines 172a and 172b, and the low-potential supply line 162 includes first and second low-potential supply lines 162a and 162b.

Each of the second high-potential supply line 172b and the second low-potential supply line 162b is disposed parallel to the data line DL, and is provided for at least two subpixels.

The first high-potential supply line 172a is electrically connected to the second high-potential supply line 172b, and is arranged parallel to the scan line SL. The first high-potential supply line 172a diverges from the second high-potential supply line 172b so as to intersect the second high-potential supply line 172b. Consequently, the first high-potential supply line 172a compensates for the resistance of the second high-potential supply line 172b in order to minimize the voltage drop (IR drop) of the high-potential supply line 172.

The first low-potential supply line 162a is electrically connected to the second low-potential supply line 162b, and is arranged parallel to the scan line SL. The first low-potential supply line 162a diverges from the second low-potential supply line 162b so as to intersect the second low-potential supply line 162b. Consequently, the first low-potential supply line 162a compensates for the resistance of the second low-potential supply line 162b in order to minimize the voltage drop (IR drop) of the low-potential supply line 162.

Since each of the high-potential supply line 172 and the low-potential supply line 162 is formed in a mesh shape, the number of second high-potential supply lines 172b and second low-potential supply lines 162b that are disposed in the vertical direction may be reduced. Since a larger number

of subpixels may be disposed in proportion to the reduced number of second high-potential supply lines 172b and second low-potential supply lines 162b, an aperture ratio and resolution are improved.

One of the transistors included in the pixel-driving circuit includes a polycrystalline semiconductor layer, and each of the other transistors includes an oxide semiconductor layer. For example, each of the first and third switching transistors ST1 and ST3 of the pixel-driving circuit shown in FIGS. 5 and 6 is constituted by a first thin film transistor 150 having a polycrystalline semiconductor layer 154, and each of the second switching transistor ST2 and the drive transistor DT is constituted by a second thin film transistor 100 having an oxide semiconductor layer 104. According to the present disclosure, as described above, a second thin film transistor 100 having an oxide semiconductor layer 104 is applied to the drive transistor DT of each subpixel, and a first thin film transistor 150 having a polycrystalline semiconductor layer 154 is applied to the switching transistor ST of each subpixel, whereby power consumption may be reduced.

The first thin film transistor 150 shown in FIGS. 6 and 7 includes a polycrystalline semiconductor layer 154, a first gate electrode 152, a first source electrode 156, and a first drain electrode 158.

The polycrystalline semiconductor layer 154 is formed on a lower buffer layer 112. The polycrystalline semiconductor layer 154 includes a channel area, a source area, and a drain area. The channel area overlaps the first gate electrode 152 in the state in which a lower gate dielectric film 114 is interposed there between so as to be formed between the first source and first drain electrodes 156 and 158. The source area is electrically connected to the first source electrode 156 via a first source contact hole 160S. The drain area is electrically connected to the first drain electrode 158 via a first drain contact hole 160D. Since the polycrystalline semiconductor layer 154 exhibits higher mobility than the amorphous semiconductor layer, thereby exhibiting low consumption and high reliability, the polycrystalline semiconductor layer 154 is suitable for being applied to the switching transistor ST of each subpixel and the scan driver 202 that drives the scan line SL. A multi buffer layer 140 and a lower buffer layer 112 are disposed between the polycrystalline semiconductor layer 154 and the substrate 101. The multi buffer layer 140 delays the diffusion of moisture and/or oxygen permeating the substrate 101. The multi buffer layer 140 is formed by alternately stacking silicon nitride (SiNx) and silicon oxide (SiOx) at least once. The lower buffer layer 112 protects the polycrystalline semiconductor layer 154 and blocks the introduction of various kinds of defects from the substrate 101. The lower buffer layer 112 may be made of a-Si, silicon nitride (SiNx), or silicon oxide (SiOx).

The first gate electrode 152 is formed on the lower gate dielectric film 114. The first gate electrode 152 overlaps the channel area of the polycrystalline semiconductor layer 154 in the state in which the lower gate dielectric film 114 is disposed therebetween. The first gate electrode 152 may be made of the same material as a storage lower electrode 182, such as one of molybdenum (Mo), aluminum (Al), chrome (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd), and copper (Cu) or an alloy thereof, and may have a single-layered structure or a multi-layered structure. However, the present disclosure is not limited thereto.

First and second lower interlayer dielectric films 116 and 118 located on the polycrystalline semiconductor layer 154 are made of an inorganic film having higher hydrogen particle content than an upper interlayer dielectric film 124. For example, the first and second lower interlayer dielectric

films **116** and **118** are made of silicon nitride (SiN<sub>x</sub>) formed by deposition using NH<sub>3</sub> gas, and the upper interlayer dielectric film **124** is made of silicon oxide (SiO<sub>x</sub>). During a hydrogenation process, the hydrogen particles contained in the first and second lower interlayer dielectric films **116** and **118** are diffused to the polycrystalline semiconductor layer **154**, whereby apertures in the polycrystalline semiconductor layer **154** are filled with hydrogen. Consequently, the polycrystalline semiconductor layer **154** becomes stabilized, thereby preventing a reduction in the properties of the first thin film transistor **150**.

The first source electrode **156** is connected to the source area of the polycrystalline semiconductor layer **154** via the first source contact hole **160S**, which is formed through the lower gate dielectric film **114**, the first and second lower interlayer dielectric films **116** and **118**, an upper buffer layer **122**, and the upper interlayer dielectric film **124**. The first drain electrode **158** faces the first source electrode **156**, and is connected to the drain area of the polycrystalline semiconductor layer **154** via the first drain contact hole **160D**, which is formed through the lower gate dielectric film **114**, the first and second lower interlayer dielectric films **116** and **118**, the upper buffer layer **122**, and the upper interlayer dielectric film **124**. Since the first source and first drain electrodes **156** and **158** are made of the same material as a storage supply line **186** and are formed in the same plane as the storage supply line **186**, the first source and first drain electrodes **156** and **158** may be simultaneously formed through the same mask process as that for forming the storage supply line **186**.

After activation and hydrogenation of the polycrystalline semiconductor layer **154** of the first thin film transistor **150**, the oxide semiconductor layer **104** of the second thin film transistor **100** is formed. That is, the oxide semiconductor layer **104** is located on the polycrystalline semiconductor layer **154**. As a result, the oxide semiconductor layer **104** is not exposed to a high-temperature atmosphere during the activation and hydrogenation of the polycrystalline semiconductor layer **154**. Consequently, damage to the oxide semiconductor layer **104** is prevented, whereby the reliability of the oxide semiconductor layer **104** is improved.

The second thin film transistor **100** is disposed on the upper buffer layer **122** so as to be spaced apart from the first thin film transistor **150**. The second thin film transistor **100** includes a second gate electrode **102**, an oxide semiconductor layer **104**, a second source electrode **106**, and a second drain electrode **108**.

The second gate electrode **102** overlaps the oxide semiconductor layer **104** in the state in which an upper gate dielectric pattern **146** is disposed there between. The second gate electrode **102** is formed in the same plane as the first high-potential supply line **172a**, i.e. on the upper gate dielectric pattern **146**, and is made of the same material as the first high-potential supply line **172a**. Consequently, the second gate electrode **102** and the first high-potential supply line **172a** may be formed through the same mask process, whereby the number of mask processes may be reduced.

The oxide semiconductor layer **104** is formed on the upper buffer layer **122** so as to overlap the second gate electrode **102** such that a channel is formed between the second source electrode **106** and the second drain electrode **108**. The oxide semiconductor layer **104** is made of an oxide including at least one of Zn, Cd, Ga, In, Sn, Hf, or Zr. Since the second thin film transistor **100** including the oxide semiconductor layer **104** exhibits higher charge mobility and lower leakage of current than the first thin film transistor **150** including the polycrystalline semiconductor layer **154**, the

second thin film transistor **100** may be applied to the switching and drive thin film transistors ST and DT, each of which has a short on time and a long off time.

The upper interlayer dielectric film **124** and the upper buffer layer **122**, which are adjacent to the upper part and the lower part of the oxide semiconductor layer **104**, respectively, are made of an inorganic film that has lower hydrogen particle content than the lower interlayer dielectric films **116** and **118**. For example, the upper interlayer dielectric film **124** and the upper buffer layer **122** may be made of silicon oxide (SiO<sub>x</sub>), and the lower interlayer dielectric films **116** and **118** may be made of silicon nitride (SiN<sub>x</sub>). During heat treatment of the oxide semiconductor layer **104**, therefore, hydrogen in the lower interlayer dielectric films **116** and **118** and hydrogen in the polycrystalline semiconductor layer **154** may be prevented from spreading to the oxide semiconductor layer **104**.

The second source and second drain electrodes **106** and **108** may be formed on the upper interlayer dielectric film **124**, may be made of one of molybdenum (Mo), aluminum (Al), chrome (Cr), gold (Au), titanium (Ti), nickel (Ni), neodymium (Nd), and copper (Cu) or an alloy thereof, and may have a single-layered structure or a multi-layered structure. However, the present disclosure is not limited thereto.

The second source electrode **106** is connected to a source area of the oxide semiconductor layer **104** via a second source contact hole **110S**, which is formed through the upper interlayer dielectric film **124**. The second drain electrode **108** is connected to a drain area of the oxide semiconductor layer **104** via a second drain contact hole **110D**, which is formed through the upper interlayer dielectric film **124**. The second source and second drain electrodes **106** and **108** are formed so as to face each other in the state in which a channel area of the oxide semiconductor layer **104** is disposed there between.

As shown in FIG. 7, a storage lower electrode **182** and a storage upper electrode **184** overlap each other in the state in which the first lower interlayer dielectric film **116** is disposed therebetween in order to form a storage capacitor Cst (**180**).

The storage lower electrode **182** is connected to one of the second gate electrode **102** and the second source electrode **106** of the drive transistor DT. The storage upper electrode **184** is located on the lower gate dielectric film **114**, is formed in the same layer as the first gate electrode **152**, and is made of the same material as the first gate electrode **152**.

The storage upper electrode **184** is connected to the other of the second gate electrode **102** and the second source electrode **106** of the drive transistor DT via the storage supply line **186**. The storage upper electrode **184** is located on the first lower interlayer dielectric film **116**. The storage upper electrode **184** is formed in the same layer as a light-blocking layer **178** and the first low-potential supply line **162a**, and is made of the same material as the light-blocking layer **178** and the first low-potential supply line **162a**. The storage upper electrode **184** is exposed through a storage contact hole **188**, which is formed through the second lower interlayer dielectric film **118**, the upper buffer layer **122**, and the upper interlayer dielectric film **124**, so as to be connected to the storage supply line **186**. Meanwhile, the storage upper electrode **184** may be integrally connected to the light-blocking layer **178**, although the storage upper electrode **184** is shown in FIG. 7 as being spaced apart from the light-blocking layer **178**.

The first lower interlayer dielectric film **116**, which is disposed between the storage lower electrode **182** and the

storage upper electrode **184**, is made of an inorganic dielectric material, such as SiOx or SiNx. In one embodiment, the first lower interlayer dielectric film **116** is made of SiNx, which exhibits higher permittivity than SiOx. Consequently, the storage lower electrode **182** and the storage upper electrode **184** overlap each other in the state in which the first lower interlayer dielectric film **116**, which is made of SiNx exhibiting high permittivity, is disposed there between, whereby the capacitance value of the storage capacitor Cst, which is proportional to permittivity, is increased.

The light-emitting device **130** includes an anode **132** connected to the second source electrode **106** of the second thin film transistor **100**, at least one light-emitting stack **134** formed on the anode **132**, and a cathode **136** on the light-emitting stack **134**.

The anode **132** is connected to a pixel connection electrode **142**, which is exposed through a second pixel contact hole **144**, which is formed through a second planarization layer **128**. Here, the pixel connection electrode **142** is connected to the second source electrode **106**, which is exposed through a first pixel contact hole **120**, which is formed through a first planarization layer **126**.

The anode **132** is formed to have a multi-layered structure including a transparent conductive film and an opaque conductive film, which exhibits high reflectance. The transparent conductive film is made of a material that has a relatively large work function value, such as indium-tin-oxide (ITO) or indium-zinc-oxide (IZO). The opaque conductive film is made of Al, Ag, Cu, Pb, Mo, Ti, or an alloy thereof, and has a single-layered or multi-layered structure. For example, the anode **132** is formed to have a structure in which a transparent conductive film, an opaque conductive film, and a transparent conductive film are sequentially stacked, or a structure in which a transparent conductive film and an opaque conductive film are sequentially stacked. The anode **132** is disposed on the second planarization layer **128** so as to overlap a circuit area in which the first and second thin film transistors **150** and **100** and the storage capacitor (Cst) **180** are disposed, as well as a light-emitting area defined by a bank **13**, whereby the light emission size is increased.

The light-emitting stack **134** is formed by a hole-related layer, an organic light-emitting layer, and an electron-related layer on the anode **132** in the forward sequence or in the reverse sequence. In addition, the light-emitting stack **134** may include first and second light-emitting stacks, which are opposite to each other in the state in which a charge generation layer is disposed there between. In this case, the organic light-emitting layer of one of the first and second light-emitting stacks generates blue light, and the organic light-emitting layer of the other of the first and second light-emitting stacks generates yellow-green light, whereby white light is generated through the first and second light-emitting stacks. The white light generated by the light-emitting stack **134** is incident on a color filter (not shown), which is located on the light-emitting stack **134**, whereby a color image may be realized. Alternatively, each light-emitting stack **134** may generate colored light corresponding to each subpixel without using a separate color filter in order to realize a color image. That is, a light-emitting stack **134** of a red (R) subpixel may generate red light, a light-emitting stack **134** of a green (G) subpixel may generate green light, and a light-emitting stack **134** of a blue (B) subpixel may generate blue light.

The bank **138** is formed so as to expose the anode **132**. The bank **138** may be made of an opaque material (e.g. black) in order to prevent optical interference between

neighboring subpixels. In this case, the bank **138** includes a light-blocking material made of at least one of color pigment, organic black, or carbon.

The cathode **136** is formed on the upper surface and the side surface of the light-emitting stack **134** so as to be opposite to the anode **132** in the state in which the light-emitting stack **134** is disposed there between. In the case in which the display device according to the present disclosure is applied to a front emission type organic light-emitting display device, the cathode **136** is made of a transparent conductive film, such as indium-tin-oxide (ITO) or indium-zinc-oxide (IZO).

The cathode **136** is electrically connected to the low-potential supply line **162**. As shown in FIGS. **5B** and **6**, the low-potential supply line **162** includes first and second low-potential supply lines **162a** and **162b**, which intersect each other. As shown in FIG. **7**, the first low-potential supply line **162a** is formed on the upper gate dielectric pattern **146**, which is the same layer as the second gate electrode **102**, and is made of the same material as the second gate electrode **102**. The second low-potential supply line **162b** is formed on the first planarization layer **126**, which is the same layer as the pixel connection electrode **142**, and is made of the same material as the pixel connection electrode **142**. The second low-potential supply line **162b** is electrically connected to the first low-potential supply line **162a**, which is exposed through a first line contact hole **164**, which is formed through the upper interlayer dielectric film **124**, and the first planarization layer **126**.

As shown in FIGS. **5** and **6**, the high-potential supply line **172**, which supplies high-potential voltage VDD, which is higher than the low-potential voltage VSS supplied through the low-potential supply line **162**, includes first and second high-potential supply lines **172a** and **172b**, which intersect each other. As shown in FIG. **7**, the first high-potential supply line **172a** is formed on the upper gate dielectric pattern **146**, which is the same layer as the second gate electrode **102**, and is made of the same material as the second gate electrode **102**. The second high-potential supply line **172b** is formed on the upper interlayer dielectric film **124**, which is the same layer as the second source and second drain electrodes **106** and **108**, and is made of the same material as the second source and second drain electrodes **106** and **108**. The second high-potential supply line **172b** is electrically connected to the first high-potential supply line **172a**, which is exposed through a second line contact hole **174**, which is formed through the upper interlayer dielectric film **124**.

Since each of the high-potential supply line **172** and the low-potential supply line **162** is formed in a mesh shape, the first high-potential supply line **172a** and the first low-potential supply line **162a**, which are arranged in the horizontal direction, are disposed parallel to the scan line SL.

The second high-potential supply line **172b** and the second low-potential supply line **162b**, which are arranged in the vertical direction, are disposed at opposite sides of each subpixel. For example, as shown in FIG. **6**, the second low-potential supply line **162b** is disposed at the right side of each subpixel, and the second high-potential supply line **172b** is disposed at the left side of each subpixel. The difference between the high-potential voltage VDD supplied through the second high-potential supply line **172b** and the low-potential voltage VSS supplied through the second low-potential supply line **162b** is great. In the case in which the second high-potential supply line **172b** and the second low-potential supply line **162b** are disposed vertically in the state in which the first planarization layer **126** is disposed

there between, dielectric breakdown occurs in the first planarization layer 126, whereby the second high-potential supply line 172b and the second low-potential supply line 162b are shorted. According to the present invention, the second high-potential supply line 172b and the second low-potential supply line 162b are disposed so as to be spaced apart from each other in the leftward-rightward direction, whereby it is possible to prevent the second high-potential supply line 172b and the second low-potential supply line 162b from being shorted.

The second low-potential supply line 162b overlaps the reference line RL in the state in which the first planarization layer 126 is disposed therebetween. The reference voltage Vref supplied through the reference line RL and the low-potential voltage VSS supplied through the second low-potential supply line 162b are similar or equal. Consequently, there is no or little voltage difference between the second low-potential supply line 162b and the reference line RL. In particular, the difference between the reference voltage Vref supplied through the reference line RL and the low-potential voltage VSS supplied through the second low-potential supply line 162b is less than the difference between the high-potential voltage VDD supplied through the second high-potential supply line 172b and the low-potential voltage VSS supplied through the second low-potential supply line 162b. Consequently, no dielectric breakdown occurs in the first planarization layer 126 disposed between the second low-potential supply line 162b and the reference line RL, whereby it is possible to prevent the second low-potential supply line 162b and the reference line RL from being shorted and thus to prevent a product from catching a fire.

As shown in FIGS. 7A and 7B, a signal link 176, which is connected to at least one of the low-potential supply line 162, the high-potential supply line 172, the data line DL, the scan line SL, or the emission control line EL, is formed so as to cross the bending area BA, in which first and second openings 192 and 194 are formed. The first opening 192 exposes the side surface of the upper interlayer dielectric film 124 and the upper surface of the upper buffer layer 122. The first opening 192 is formed so as to have the same depth d1 as at least one of the second source contact hole 110S or the second drain contact hole 110D. The second opening 194 is formed so as to expose the side surfaces of the multi buffer layer 140, the lower buffer layer 112, the lower gate dielectric film 114, the first and second lower interlayer dielectric films 116 and 118, and the upper buffer layer 122. The second opening 194 is formed so as to have a greater depth d2 than at least one of the first source contact hole 160S or the first drain contact hole 160D or to have the same depth d2 as at least one of the first source contact hole 160S or the first drain contact hole 160D. As shown in FIGS. 7A and 7B, the sum of the thicknesses of the multi buffer layer 140 and the lower buffer layer 112 has the same thickness as the upper interlayer dielectric film 124 or has a larger thickness than the upper interlayer dielectric film 124. As shown in FIG. 8, the lower buffer layer 112 has the same thickness as the upper interlayer dielectric film 124 or has a larger thickness than the upper interlayer dielectric film 124. Consequently, the multi buffer layer 140, the lower buffer layer 112, the lower gate dielectric film 114, the first and second lower interlayer dielectric films 116 and 118, the upper buffer layer 122, and the upper interlayer dielectric film 124 are removed from the bending area BA by the first and second openings 192 and 194. That is, the inorganic dielectric layers 140, 112, 114, 116, 118, 122, and 124, which form cracks in the bending area BA, are removed

from the bending area BA, whereby the substrate 101 may be easily bent without forming cracks.

As shown in FIG. 7, the signal link 176 may be formed together with the pixel connection electrode 142 through the same mask process as that for forming the pixel connection electrode 142. In this case, the signal link 176 is made of the same material as the pixel connection electrode 142, and is formed in the same plane as the pixel connection electrode 142, i.e. on the first planarization layer 126. In order to cover the signal link 176 formed on the first planarization layer 126, the second planarization layer 128 is disposed on the signal link 176, or an encapsulation film or an inorganic encapsulation layer constituted by an encapsulation stack including a combination of inorganic or organic encapsulation layers is disposed on the signal link 176, without the second planarization layer 128.

In addition, as shown in FIG. 8, the signal link 176 may be formed together with the source and drain electrodes 106, 156, 108, and 158 through the same mask process as that for forming the source and drain electrodes 106, 156, 108, and 158. In this case, the signal link 176 is made of the same material as the source and drain electrodes 106, 156, 108, and 158, and is formed in the same plane as the source and drain electrodes 106, 156, 108, and 158, i.e. on the upper interlayer dielectric film 124. In addition, the signal link 176 is formed on the substrate 101 so as to contact the substrate 101. Consequently, the signal link 176 is formed on the side surface of the upper interlayer dielectric film 124 and the upper surface of the upper buffer layer 122, which are exposed through the first opening 192, and is formed on the side surfaces of the multi buffer layer 140, the lower buffer layer 112, the lower gate dielectric film 114, the first and second lower interlayer dielectric films 116 and 118, and the upper buffer layer 122, which are exposed through the second opening 194. As a result, the signal link 176 is formed in the shape of stairs. In order to cover the signal link 176 formed in the shape of stairs, at least one of the first or second planarization layer 126 or 128 is disposed on the signal link 176, or an encapsulation film or an inorganic encapsulation layer constituted by an encapsulation stack including a combination of inorganic or organic encapsulation layers is disposed on the signal link 176 without the first and second planarization layers 126 and 128.

In addition, as shown in FIG. 8, the signal link 176 may be formed on the multi buffer layer 140. In this case, the multi buffer layer 140 disposed between signal links 176 is removed such that the substrate can be easily bent without forming cracks in the substrate, whereby a trench 196, through which the substrate 101 is exposed, is formed between the signal links 176.

Meanwhile, at least one moisture-blocking hole (not shown) formed through the first and second planarization layers 126 and 128 may be disposed in the bending area BA. The moisture-blocking hole is formed in at least one of a space between the signal links 176 or the upper parts of the signal links 176. The moisture-blocking hole prevents external moisture from permeating into the active area AA through at least one of the first or second planarization layer 126 or 128 disposed on the signal link 176. In addition, an inspection line (not shown) that is used during an inspection process is formed so as to have the same structure as one of the signal links 176 shown in FIGS. 7 to 8.

As described above, the multi buffer layer 140, the lower buffer layer 112, the lower gate dielectric film 114, the first and second lower interlayer dielectric films 116 and 118, the upper buffer layer 122, and the upper interlayer dielectric film 124 are removed from the bending area BA by the first

and second openings **192** and **194**. That is, the inorganic dielectric layers **140**, **112**, **114**, **116**, **118**, **122**, and **124**, which form cracks in the bending area BA, are removed from the bending area BA, whereby the substrate **101** may be easily bent without forming cracks.

FIGS. **9A** to **9M** are sectional views illustrating a method of manufacturing the organic light-emitting display device shown in FIG. **7**.

Referring to FIG. **9A**, a multi buffer layer **140**, a lower buffer layer **112**, and a polycrystalline semiconductor layer **154** are sequentially formed on a substrate **101**.

Specifically, SiOx and SiNx are alternately stacked at least once on the substrate **101** in order to form a multi buffer layer **140**. Subsequently, SiOx or SiNx is deposited on the entire surface of the multi buffer layer **140** in order to form a lower buffer layer **112**. Subsequently, an amorphous silicon thin film is formed on the substrate **101**, on which the lower buffer layer **112** is formed, by low-pressure chemical vapor deposition (LPCVD) or plasma-enhanced chemical vapor deposition (PECVD). Subsequently, the amorphous silicon thin film is crystallized into a polycrystalline silicon thin film. The polycrystalline silicon thin film is patterned through a photolithography and etching process using a first mask in order to form a polycrystalline semiconductor layer **154**.

Referring to FIG. **9B**, a lower gate dielectric film **114** is formed on the substrate **101**, on which the polycrystalline semiconductor layer **154** is formed, and a first gate electrode **152** and a storage lower electrode **182** are formed on the lower gate dielectric film **114**.

Specifically, an inorganic dielectric material, such as SiNx or SiOx, is deposited on the entire surface of the substrate **101**, on which the polycrystalline semiconductor layer **154** is formed, in order to form a lower gate dielectric film **114**. Subsequently, a first conductive layer is deposited on the entire surface of the lower gate dielectric film **114**, and is patterned through a photolithography and etching process using a second mask in order to form a first gate electrode **152** and a storage lower electrode **182**. Subsequently, the polycrystalline semiconductor layer **154** is doped with a dopant through a doping process using the first gate electrode **152** as a mask in order to form source and drain areas, which do not overlap the first gate electrode **152**, and a channel area, which overlaps the first gate electrode **152**.

Referring to FIG. **9C**, at least one layer of first lower interlayer dielectric film **116** is formed on the substrate **101**, on which the first gate electrode **152** and the storage lower electrode **182** are formed, and a storage upper electrode **184** and a light-blocking layer **178** are formed on the first lower interlayer dielectric film **116**.

Specifically, an inorganic dielectric material, such as SiNx or SiOx, is deposited on the entire surface of the substrate **101**, on which the first gate electrode **152** and the storage lower electrode **182** are formed, in order to form a first lower interlayer dielectric film **116**. Subsequently, a second conductive layer is deposited on the entire surface of the first lower interlayer dielectric film **116**, and is patterned through a photolithography and etching process using a third mask in order to form a storage upper electrode **184** and a light-blocking layer **178**.

Referring to FIG. **9D**, at least one layer of second lower interlayer dielectric film **118** and an upper buffer layer **122** are sequentially formed on the substrate **101**, on which the storage upper electrode **184** and the light-blocking layer **178** are formed, and an oxide semiconductor layer **104** is formed on the upper buffer layer **122**.

Specifically, an inorganic dielectric material, such as SiNx or SiOx, is deposited on the entire surface of the substrate **101**, on which the storage upper electrode **184** and the light-blocking layer **178** are formed, in order to form a second lower interlayer dielectric film **118**. Subsequently, an inorganic dielectric material, such as SiNx or SiOx, is deposited on the entire surface of the second lower interlayer dielectric film **118** in order to form an upper buffer layer **122**. Subsequently, an oxide semiconductor layer **104** is deposited on the entire surface of the upper buffer layer **122**, and is patterned through a photolithography and etching process using a fourth mask in order to form an oxide semiconductor layer **104**, which overlaps the light-blocking layer **178**.

Referring to FIG. **9E**, an upper gate dielectric pattern **146**, a second gate electrode **102**, a first low-potential supply line **162a**, and a first high-potential supply line **172a** are formed on the substrate **101**, on which the oxide semiconductor layer **104** is formed.

Specifically, an upper gate dielectric film is formed on the substrate **101**, on which the oxide semiconductor layer **104** is formed, and a third conductive layer is formed thereon by deposition, such as sputtering. The upper gate dielectric film is made of an inorganic dielectric material, such as SiOx or SiNx. The third conductive layer is made of Mo, Ti, Cu, AlNd, Al, Cr, or an alloy thereof, and has a single-layered or multi-layered structure. Subsequently, the third conductive layer and the upper gate dielectric film are simultaneously patterned through a photolithography and etching process using a fifth mask in order to form a second gate electrode **102**, a first low-potential supply line **162a**, and a first high-potential supply line **172a** and to form an upper gate dielectric pattern **146** thereunder so as to have the same pattern. At this time, during dry etching of the upper gate dielectric film, the portion of the oxide semiconductor layer **104** that does not overlap the second gate electrode **102** is exposed to plasma, and oxygen in the oxide semiconductor layer **104** exposed to plasma is removed as the result of reacting with plasma. Consequently, the portion of the oxide semiconductor layer **104** that does not overlap the second gate electrode **102** becomes a conductor to constitute source and drain areas.

Referring to FIG. **9F**, an upper interlayer dielectric film **124**, having therein a first opening **192**, first and second source contact holes **160S** and **110S**, first and second drain contact holes **160D** and **110D**, a first storage contact hole **188**, and first and second line contact holes **164** and **174**, is formed on the substrate **101**, on which the upper gate dielectric pattern **146**, the second gate electrode **102**, the first low-potential supply line **162a**, and the first high-potential supply line **172a** are formed.

Specifically, an inorganic dielectric material, such as SiNx or SiOx, is deposited on the entire surface of the substrate **101**, on which the upper gate dielectric pattern **146**, the second gate electrode **102**, the first low-potential supply line **162a**, and the first high-potential supply line **172a** are formed, in order to form an upper interlayer dielectric film **124**. Subsequently, the upper interlayer dielectric film **124** is patterned through a photolithography and etching process using a sixth mask in order to form first and second source contact holes **160S** and **110S**, first and second drain contact holes **160D** and **110D**, a first storage contact hole **188**, and first and second line contact holes **164** and **174**. In addition, the portion of the upper interlayer dielectric film **124** in a bending area BA is removed to form a first opening **192**. At this time, the first and second source contact holes **160S** and **110S**, the first and second drain contact holes **160D** and **110D**, the first storage contact hole **188**, the first and second

line contact holes **164** and **174**, and the first opening **192** are formed through the upper interlayer dielectric film **124** so as to have the same depth.

Referring to FIG. 9G, a second opening **194** is formed in the bending area BA on the substrate **101**, on which the upper interlayer dielectric film **124** is formed, and the lower gate dielectric film **114**, the first and second lower interlayer dielectric films **116** and **118**, and the upper buffer layer **122** in the first source contact hole **160S**, the first drain contact hole **160D**, and the first storage contact hole **188** are selectively removed.

Specifically, the lower gate dielectric film **114**, the first and second lower interlayer dielectric films **116** and **118**, and the upper buffer layer **122** in the first source contact hole **160S**, the first drain contact hole **160D**, and the first storage contact hole **188** are selectively removed from the substrate **101**, on which the upper interlayer dielectric film **124** is formed, through a photolithography and etching process using a seventh mask. At the same time, the multi buffer layer **140**, the lower buffer layer **112**, the lower gate dielectric film **114**, the first and second lower interlayer dielectric films **116** and **118**, and the upper buffer layer **122** in the bending area are removed in order to form a second opening **194**. Meanwhile, a portion of the substrate **101** may also be removed at the time of forming the second opening **194**.

Referring to FIG. 9H, first and second source electrodes **156** and **106**, first and second drain electrodes **158** and **108**, a storage supply line **186**, a reference line RL, and a second high-potential supply line **172b** are formed on the substrate **101**, on which the second opening **194** is formed.

Specifically, a fourth conductive layer, made of Mo, Ti, Cu, AlNd, Al, Cr, or an alloy thereof, is deposited on the entire surface of the substrate **101**, on which the second opening **194** is formed. Subsequently, the fourth conductive layer is patterned through a photolithography and etching process using an eighth mask in order to form first and second source electrodes **156** and **106**, first and second drain electrodes **158** and **108**, a storage supply line **186**, a reference line RL, and a second high-potential supply line **172b**.

Referring to FIG. 9I, a first planarization layer **126** having a first pixel contact hole **120** is formed on the substrate **101**, on which the first and second source electrodes **156** and **106**, the first and second drain electrodes **158** and **108**, the storage supply line **186**, the reference line RL, and the second high-potential supply line **172b** are formed.

Specifically, an organic dielectric material, such as an acrylic resin, is applied to the entire surface of the substrate **101**, on which the first and second source electrodes **156** and **106**, the first and second drain electrodes **158** and **108**, the storage supply line **186**, the reference line RL, and the second high-potential supply line **172b** are formed, in order to form a first planarization layer **126**. Subsequently, the first planarization layer **126** is patterned through a photolithography process using a ninth mask in order to form a first pixel contact hole **120**, which extends through the first planarization layer **126**. At the same time, the first line contact hole **164** is formed through the first planarization layer **126**.

Referring to FIG. 9J, a pixel connection electrode **142**, a second low-potential supply line **162b**, and a signal link **176** are formed on the substrate **101**, on which the first planarization layer **126** is formed.

Specifically, a fifth conductive layer, made of Mo, Ti, Cu, AlNd, Al, Cr, or an alloy thereof, is deposited on the entire surface of the substrate **101**, on which the first planarization layer **126** having the first pixel contact hole **120** is formed. Subsequently, the fifth conductive layer is patterned through

a photolithography and etching process using a tenth mask in order to form a pixel connection electrode **142**, a second low-potential supply line **162b**, and a signal link **176**.

Referring to FIG. 9K, a second planarization layer **128** having a second pixel contact hole **144** is formed on the substrate **101**, on which the pixel connection electrode **142**, the second low-potential supply line **162b**, and the signal link **176** are formed.

Specifically, an organic dielectric material, such as an acrylic resin, is deposited on the entire surface of the substrate **101**, on which the pixel connection electrode **142**, the second low-potential supply line **162b**, and the signal link **176** are formed, in order to form a second planarization layer **128**. Subsequently, the second planarization layer **128** is patterned through a photolithography process using an eleventh mask in order to form a second pixel contact hole **144**.

Referring to FIG. 9L, an anode **132** is formed on the substrate **101**, on which the second planarization layer **128** having therein the second pixel contact hole **144** is formed.

Specifically, a fifth conductive layer is deposited on the entire surface of the substrate **101**, on which the second planarization layer **128** having therein the second pixel contact hole **144** is formed. A transparent conductive film or an opaque conductive film is used as the fifth conductive layer. Subsequently, the fifth conductive layer is patterned through a photolithography and etching process using a twelfth mask in order to form an anode **132**.

Referring to FIG. 9M, a bank **138**, an organic light-emitting stack **134**, and a cathode **136** are sequentially formed on the substrate **101**, on which the anode **132** is formed.

Specifically, a photosensitive film for banks is applied to the entire surface of the substrate **101**, on which the anode **132** is formed, and the photosensitive film for banks is patterned through a photolithography process using a thirteenth mask in order to form a bank **138**. Subsequently, an organic light-emitting stack **134** and a cathode **136** are sequentially formed in an active area (AA), excluding a non-active area (NA), through a deposition process using a shadow mask.

According to the present disclosure, as described above, the first opening **192** in the bending area BA and the second source and drain contact holes **110S** and **110D** are formed through the same mask process, the second opening **194** in the bending area BA and the first source and drain contact holes **160S** and **160D** are formed through the same mask process, the first source and first drain electrodes **156** and **158** and the second source and second drain electrodes **106** and **108** are formed through the same mask process, and the storage contact hole **188** and the first source and drain contact holes **160S** and **160D** are formed through the same mask process, whereby the number of mask processes may be reduced by at least four compared to the conventional art. In the organic light-emitting display device according to the present disclosure, therefore, it is possible to eliminate at least four mask processes that are normally performed in the conventional art, whereby it is possible to simplify the structure and manufacturing process of the display device and thus to improve productivity.

As is apparent from the above description, according to the present disclosure, a second thin film transistor having an oxide semiconductor layer is applied to a drive transistor of each subpixel, and a first thin film transistor having a polycrystalline semiconductor layer is applied to a switching transistor of each subpixel, whereby it is possible to reduce power consumption. In addition, according to the present

disclosure, openings disposed in a bending area and a plurality of contact holes disposed in an active area are formed through the same mask process, whereby the openings and the contact holes have the same depth. Consequently, it is possible to simplify the structure and manufacturing process of the display device according to the present disclosure and thus to improve productivity. Furthermore, according to the present invention, a high-potential supply line and a low-potential supply line, the voltage difference between which is relatively large, are disposed so as to be spaced apart from each other in the horizontal direction, whereas a reference line and the low-potential supply line, the voltage difference between which is relatively small, are disposed so as to overlap each other, thereby preventing signal lines from being shorted.

It will be apparent to those skilled in the art that various modifications and variations can be made in the present invention without departing from the spirit or scope of the invention. Thus, it is intended that the present invention covers the modifications and variations of this invention provided they come within the scope of the appended claims and their equivalents.

What is claimed is:

**1.** A display device comprising:

a substrate including an active area and a bending area; a first thin film transistor on the active area of the substrate, the first thin film transistor including a first semiconductor layer;

a second thin film transistor spaced away from the first thin film transistor in the active area of the substrate, the second thin film transistor including a second semiconductor layer;

an upper interlayer dielectric film on the first semiconductor layer and the second semiconductor layer;

a first planarization layer on the upper interlayer dielectric film, the first planarization layer extending to the bending area of the substrate;

a pixel connection electrode on the first planarization layer in active area, the pixel connection electrode electrically connected to the second thin film transistor;

a second planarization layer on the first planarization layer, the second planarization layer covering the pixel connection electrode;

an organic light-emitting device including an anode electrode connected to the pixel connection electrode, a light-emitting stack on the anode electrode, and a cathode electrode on the light-emitting stack; and

a signal link between the first planarization layer and the second planarization layer in the bending area, the signal link including a same material as the pixel connection electrode,

wherein a distance between the substrate and the signal link in the bending area is smaller than a distance between the substrate and the pixel connection electrode on the active area.

**2.** The display device according to claim 1, wherein the first planarization layer contacts an upper surface of the substrate in the bending area.

**3.** The display device according to claim 1, wherein at least one of the first semiconductor layer and the second semiconductor layer includes an oxide semiconductor.

**4.** The display device according to claim 1, wherein the signal link is disposed on a same plane as the pixel connection electrode.

**5.** The display device according to claim 1, wherein the second semiconductor layer is on a different layer from the first semiconductor layer.

**6.** The display device according to claim 5, further comprising:

a lower interlayer dielectric film between the first semiconductor layer and the second semiconductor layer; and

an opening penetrating the lower interlayer dielectric film and the upper interlayer dielectric film in the bending area,

wherein the substrate includes a recessed region overlapping with the opening in the bending area, and

wherein the signal link includes a portion disposed within the opening.

**7.** The display device according to claim 6, wherein the opening exposes a side surface of the lower interlayer dielectric film, a side surface of the upper interlayer dielectric film and a side wall of the recessed region, and

wherein the side wall of the recessed region is continuously with the side surface of the lower interlayer dielectric film exposed by the opening.

**8.** The display device according to claim 7, wherein the opening includes a first opening exposing the side surface of the upper interlayer dielectric film, and a second opening exposing the side surface of the lower interlayer dielectric film and the side wall of the recessed region, and wherein a depth of the second opening is greater than a depth of the first opening.

**9.** A display device comprising:

a substrate including an active area and a bending area; a first thin film transistor on the active area of the substrate, the first thin film transistor including a first semiconductor layer;

a second thin film transistor spaced away from the first thin film transistor in the active area of the substrate, the second thin film transistor including a second semiconductor layer;

an upper interlayer dielectric film on the first semiconductor layer and the second semiconductor layer;

a first planarization layer on the upper interlayer dielectric film, the first planarization layer extending to the bending area of the substrate;

a pixel connection electrode on the first planarization layer in active area, the pixel connection electrode electrically connected to the second thin film transistor;

a second planarization layer on the first planarization layer, the second planarization layer covering the pixel connection electrode;

an organic light-emitting device including an anode electrode connected to the pixel connection electrode, a light-emitting stack on the anode electrode, and a cathode electrode on the light-emitting stack; and

a signal link between the first planarization layer and the second planarization layer in the bending area, the signal link including a same material as the pixel connection electrode,

wherein the first thin film transistor further includes a first source electrode and a first drain electrode that are between the upper interlayer dielectric film and the first planarization layer,

wherein the second thin film transistor further includes a second source electrode and a second drain electrode that are between the upper interlayer dielectric film and the first planarization layer,

wherein the upper interlayer dielectric film includes a first source contact hole between the first semiconductor layer and the first source electrode, a first drain contact hole between the first semiconductor layer and the first drain electrode, a second source contact hole between

19

the second semiconductor layer and the second source electrode, and a second drain contact hole between the second semiconductor layer and the second drain electrode, and

wherein the second source electrode and the second drain electrode are disposed on a same layer as the first source electrode and the first drain electrode.

10. The display device according to claim 9, wherein the first source electrode, the first drain electrode, the second source electrode, and the second drain electrode include the same material as the pixel connection electrode and the signal link.

11. The display device according to claim 9, wherein a depth of the second source contact hole is different from a depth of the first source contact hole, and a depth of the second drain contact hole is different from a depth of the first drain contact hole.

12. The display device according to claim 9, further comprising a plurality of insulating layers between the active area of the substrate and the second semiconductor layer,

wherein the first source contact hole and the first drain contact hole extend through the plurality of insulating layers.

13. The display device according to claim 12, wherein at least one of the plurality of insulating layers includes an inorganic insulating material, and the first planarization layer includes an organic insulating material.

14. The display device according to claim 12, wherein a thickness of a portion of the substrate overlapping with the plurality of insulating layers is greater than a thickness of a portion of the substrate that is outside the plurality of insulating layers.

15. The display device according to claim 12, wherein the first thin film transistor further includes a first gate electrode, and

wherein the plurality of insulating layers comprises:  
 a lower gate dielectric film between the first semiconductor layer and the first gate electrode of the first thin film transistor;

20

an upper buffer layer between the first gate electrode of the first thin film transistor and the second semiconductor layer of the second thin film transistor; and  
 a lower interlayer dielectric film between the first gate electrode of the first thin film transistor and the upper buffer layer.

16. The display device according to claim 15, further comprising an upper gate dielectric pattern between the second semiconductor layer and the upper interlayer dielectric film,

wherein the second thin film transistor further includes a second gate electrode between the upper gate dielectric pattern and the upper interlayer dielectric film.

17. The display device according to claim 12, wherein the first planarization layer includes a first portion in the active area and a second portion outside the first portion,

wherein the first portion of the first planarization layer covers the first thin film transistor and the second thin film transistor, and

wherein the second portion of the first planarization layer covers side surfaces of the plurality of insulating layers.

18. The display device according to claim 17, wherein the signal link is on the second portion of the first planarization layer.

19. The display device according to claim 17, wherein the plurality of insulating layers further comprises:

a multi buffer layer on the substrate and the first semiconductor layer;

a lower buffer layer on the multi buffer layer and the first semiconductor layer.

20. The display device according to claim 17, wherein the second portion of the first planarization layer covers a side surface of the upper interlayer dielectric film, and

wherein the side surfaces of the plurality of insulating layers are closer to the signal link than the side surface of the upper interlayer dielectric film.

\* \* \* \* \*