



(22) Date de dépôt/Filing Date: 2009/02/19

(41) Mise à la disp. pub./Open to Public Insp.: 2009/08/27

(45) Date de délivrance/Issue Date: 2021/12/07

(62) Demande originale/Original Application: 2 715 878

(30) Priorité/Priority: 2008/02/21 (US61/030,544)

(51) Cl.Int./Int.Cl. *C12N 11/082* (2020.01),
C12M 3/00 (2006.01), *C12M 3/04* (2006.01),
C12N 11/02 (2006.01), *C12N 11/08* (2020.01),
C12N 5/071 (2010.01)

(72) Inventeurs/Inventors:
FRYER, BENJAMIN, US;
NELSON, SHELLEY, US;
NIELSEN, VILLY, US;
BREVIG, THOMAS, US;
MARWOOD, TINA KRISTENSEN, US

(73) Propriétaires/Owners:
JANSSEN BIOTECH, INC., US;
NUNC A/S, DK


(74) Agent: NORTON ROSE FULBRIGHT CANADA

(54) Titre : PROCEDES, PLAQUES A SURFACE MODIFIEE ET COMPOSITIONS PERMETTANT LA FIXATION, LA CULTURE ET LE DETACHEMENT DE CELLULES


(54) Title: METHODS, SURFACE MODIFIED PLATES AND COMPOSITIONS FOR CELL ATTACHMENT, CULTIVATION AND DETACHMENT




H1p50 on 1:30 MATRIGEL



H1p50 on untreated NUNC LON DELTA



H1p51 on Surface Modified Plate 2



H1p51 on Surface Modified Plate 3



H1p51 on Surface Modified Plate 4

(57) **Abrégé/Abstract:**

The present invention relates to the field of mammalian cell culture, and provides methods and compositions for cell attachment to, cultivation on and detachment from a solid substrate surface containing from at least about 0.5% N, a sum of O and N of greater than or equal to 17.2% and a contact angle of at least about 13.9 degrees, lacking a feeder cell layer and lacking an adlayer. In one embodiment of the present invention, the cell's are treated with a compound capable of inhibiting Rho kinase activity. In another embodiment, the cells are treated with a compound capable of inhibiting Rho activity.

(74) **Agent(suite/continued):** LLP/S.E.N.C.R.L., S.R.L.

ABSTRACT

The present invention relates to the field of mammalian cell culture, and provides methods and compositions for cell attachment to, cultivation on and detachment from a solid substrate surface containing from at least about 0.5% N, a sum of O and N of greater than or equal to 17.2% and a contact angle of at least about 13.9 degrees, lacking a feeder cell layer and lacking an adlayer. In one embodiment of the present invention, the cells are treated with a compound capable of inhibiting Rho kinase activity. In another embodiment, the cells are treated with a compound capable of inhibiting Rho activity.

METHODS, SURFACE MODIFIED PLATES AND COMPOSITIONS FOR CELL ATTACHMENT, CULTIVATION AND DETACHMENT

This application is a divisional of Canadian Patent Application No. 2,715,878, filed on February 19, 2009.

FIELD OF THE INVENTION

- [0001]** This application claims priority to provisional application serial number 61/030,544, filed February 21st 2008.
- [0002]** The present invention relates to the field of mammalian cell culture, and provides methods and compositions for cell attachment to, cultivation on, and detachment from a solid substrate surface containing from at least about 0.5% N, a sum of O and N of greater than or equal to 17.2% and a contact angle of at least about 13.9 degrees, lacking a feeder cell layer and lacking an adlayer. In one embodiment of the present invention, the cells are treated with a compound capable of inhibiting Rho kinase activity. In another embodiment, the cells are treated with a compound capable of inhibiting Rho activity.

BACKGROUND

- [0003]** Cultivation of mammalian cells is one of many processes in the life and health sciences. Vessels for mammalian cell culture and analysis involving anchorage-dependent cells are often made of glass or a polymer, such as, for example, polystyrene, that frequently requires additional surface treatment to allow the cells to attach to the surface of the vessel. Such treatments may include applying an adlayer on the surface, for example, by adsorption, grafting or plasma polymerization techniques. Alternatively, the surface treatment may be via chemical modification of the vessel surface itself, which can be achieved by, for example, atmospheric corona, radio frequency vacuum plasma, DC glow discharge, and microwave plasma treatments. These surface treatments change the composition of elements and chemical groups in the surface. The particular chemistry

that results depends on the surface treatment method, energy, and time, as well as the composition of the gasses used.

- [0004] For example, US5449383 discloses a substrate comprising a bulk polymeric material; and a thin polymeric layer which is suitable for supporting cell growth, comprising a reorientation resistant polymer comprising plasma-polymerized amide monomers presenting amide groups for the attachment of cells, wherein said amide monomers are selected from the group of dimethyl formamide and amides having the formula $R^1\text{-CO-N(R}^2\text{)R}^3$ wherein R^1 is an aliphatic, alicyclic, or aromatic group, each of which may be optionally substituted by halogen atoms or hydroxyl groups, and R^2 and R^3 are each independently hydrogen or an alkyl group, and wherein said thin polymer layer promotes attachment and proliferation of said cells.
- [0005] In another example, EP0348969A1 discloses a method for endothelialization of a polymeric surface comprising contacting a polymeric surface with a plasma generated from a gaseous material comprising nitrogen whereby said polymeric surface is modified to contain surface amino groups, and applying to said modified surface sufficient endothelial cells to form a confluent layer of cells on said amino group-containing surface without a requirement for cell proliferation.
- [0006] In another example, EP0092302A2 discloses a method for influencing the growth of cell culture in a growth media on a substrate, characterized in that the surface chemistry of the substrate is modified by subjecting the surface of the substrate to a plasma, which is produced from carbon, hydrogen, oxygen, nitrogen, sulphur, phosphorus, a halogen, or a compound of any one of these elements.
- [0007] In another example, US 6,617,152B2 discloses an apparatus for treating a polymeric substrate surface comprising: (a) a gas inlet, a microwave energy source and a plasma mixing chamber, the plasma mixing chamber in fluid communication with both the gas inlet and the microwave energy source; (b) a dual chambered treatment area having an inner treatment chamber contained within an outer treatment chamber, said inner treatment chamber having an opening in fluid communication with said outer chamber;

(c) said plasma mixing chamber in fluid communication with said outer treatment chamber by means of an aperture; (d) a vacuum outlet line attached to said outer chamber; and (e) whereby said opening in said inner treatment chamber is aligned with said aperture, said opening being spaced from said aperture at predetermined distance.

[0008] In one example, US2003/0180903A1 discloses a polymeric substrate having a working surface upon which cells can be cultured wherein the surface oxygen content is at least 25 percent as measured by electron microscopy for chemical analysis at depth about 50 Angstroms.

[0009] In one example, WO2006114098 discloses a micro-structured biocompatible material for surgical implants and cell guiding tissue culture surfaces. The microstructure of the biomaterial surface is selected to promote growth of undifferentiated ES cells; promote neuronal differentiation of ES cells; or promote differentiation of ES cells.

[0010] In another example, Bigdeli *et al.* (J. Biotechnol. 133:146-153, 2008) describes a method of adaptation and/or selection of human ES cells to be cultivated without differentiation under feeder-cell free conditions and without prior treatment of the solid substrate surface with extracellular matrix protein, involving (i) changing media from medium conditioned by human diploid embryonic lung fibroblasts to medium conditioned by neonatal chondrocytes; (ii) then passaging the cells enzymatically from the mouse embryonic feeder cell layer to MatrigelTM-treated plates, then to CostarTM plates, and, finally, to PrimariaTM plates; and (iii) changing back to the first used medium again. Very few of the human ES cells subjected to this method gave rise to established cell lines, suggesting that this method involves selection of human ES cells to the culture conditions.

[0011] Surface treatments that change the composition of elements and chemical groups in the surface itself have successfully been used for preparing polymer solid substrates for the culture of many types of mammalian cells. However, there are significant limitations in terms of poor attachment and/or cultivation using certain types of mammalian cells, for example, pluripotent stem cells and human embryonic kidney (HEK) 293 cells.

- [0012] Graham *et al.*, (J. Gen. Virol. 36:59-72, 1977) disclose the generation of the cell line HEK293.
- [0013] HEK293 cell attachment may be enhanced by making an adlayer on the solid substrate surface, using, for example, extracellular matrix proteins, polylysine, polyornithine, or polyethyleneimine, before adding the HEK293 cells to the culture vessel. Preparing the adlayer is, however, time-consuming, and typically results in a non-sterile solid substrate with a shorter shelf life than the bare solid substrate. Therefore, there is a significant need for methods and materials for enhancing the attachment of HEK293 cells to solid substrates lacking an adlayer.
- [0014] Current methods of culturing pluripotent stem cells, in particular, embryonic stem (ES) cells require complex culture conditions, such as, for example, culturing the embryonic stem cells on a solid substrate surface with a feeder cell layer, or on a solid substrate surface with an adlayer of extracellular matrix protein. Culture systems that employ these methods often use feeder cells or extracellular matrix proteins obtained from a different species than that of the stem cells being cultivated (xenogeneic material). Media obtained by exposure to feeder cells, that is, media conditioned by cells other than undifferentiated ES cells, may be used to culture the ES cells, and media may be supplemented with animal serum.
- [0015] For example, Reubinoff *et al.* (Nature Biotechnol. 18:399-404, 2000) and Thompson *et al.* (Science 282:1145-1147, 1998) disclose the culture of ES cell lines from human blastocysts using a mouse embryonic fibroblast feeder cell layer.
- [0016] In another example, Xu *et al.* (Nature Biotechnology 19:971-974, 2001) discloses the use of MatrigelTM and laminin for treating solid substrate surfaces before feeder-cell free cultivation of human ES cells without differentiation.
- [0017] In another example, Vallier *et al.* (J. Cell Sci. 118:4495-4509, 2005) discloses the use of fetal bovine serum for treating solid substrate surfaces before feeder-cell free cultivation of human ES cells without differentiation.

- [0018]** In another example, WO2005014799 discloses conditioned medium for the maintenance, proliferation and differentiation of mammalian cells. WO2005014799 state: “The culture medium produced in accordance with the present invention is conditioned by the cell secretion activity of murine cells, in particular, those differentiated and immortalized transgenic hepatocytes, named MMH (Met Murine Hepatocyte).”
- [0019]** In another example, Wanatabe *et al.* (Nature Biotechnol. 35:681-686, 2007) state “a ROCK inhibitor permits survival of dissociated human embryonic stem cells”, and demonstrate reduced dissociation-induced apoptosis, increases cloning efficiency (from approximately 1% to approximately 27%) and facilitation of subcloning after gene transfer, using mouse embryonic fibroblasts as feeder cells, collagen and MatrigelTM as extracellular matrix protein, and Y-27632 or Fasudil for inhibition of ROCK. Furthermore, dissociated human ES cells treated with Y-27632 were protected from apoptosis in serum-free suspension culture.
- [0020]** In another example, Peerani *et al.* (EMBO Journal 26:4744-4755, 2007) state “Complexity in the spatial organization of human embryonic stem cell (hESC) cultures creates heterogeneous microenvironments (niches) that influence hESC fate. This study demonstrates that the rate and trajectory of hESC differentiation can be controlled by engineering hESC niche properties. Niche size and composition regulate the balance between differentiation-inducing and –inhibiting factors. Mechanistically, a niche size-dependent spatial gradient of Smad1 signaling is generated as a result of antagonistic interactions between hESCs and hESC-derived extra-embryonic endoderm (ExE). These interactions are mediated by the localized secretion of bone morphogenetic protein-2 (BMP2) by ExE and its antagonist, growth differentiation factor-3 (GDF3) by hESCs. Micropatterning of hESCs treated with small interfering (si) RNA against GDF3, BMP2 and Smad1, as well treatments with a Rho-associated kinase (ROCK) inhibitor demonstrate that independent control of Smad1 activation can rescue the colony size-dependent differentiation of hESCs. Our results illustrate, for the first time, a role for Smad1 in the integration of spatial information and in the niche-size dependent control of hESC self-renewal and differentiation.”

- [0021] In another example, Koyanagi, M *et al* (J Neurosci Res. 2007 Sep 7 [Epub ahead of print]) state “Rho-GTPase has been implicated in the apoptosis of many cell types, including neurons, but the mechanism by which it acts is not fully understood. Here, we investigate the roles of Rho and ROCK in apoptosis during transplantation of embryonic stem cell-derived neural precursor cells. We find that dissociation of neural precursors activates Rho and induces apoptosis. Treatment with the Rho inhibitor C3 exoenzyme and/or the ROCK inhibitor Y-27632 decreases the amount of dissociation-induced apoptosis (anoikis) by 20-30%. Membrane blebbing, which is an early morphological sign of apoptosis; cleavage of caspase-3; and release of cytochrome c from the mitochondria are also reduced by ROCK inhibition. These results suggest that dissociation of neural precursor cells elicits an intrinsic pathway of cell death that is at least partially mediated through the Rho/ROCK pathway. Moreover, in an animal transplantation model, inhibition of Rho and/or ROCK suppresses acute apoptosis of grafted cells. After transplantation, tumor necrosis factor-alpha and pro-nerve growth factor are strongly expressed around the graft. ROCK inhibition also suppresses apoptosis enhanced by these inflammatory cytokines. Taken together, these results indicate that inhibition of Rho/ROCK signaling may improve survival of grafted cells in cell replacement therapy.).
- [0022] In another example, Yoneda *et al* (J. Cell Biol. 170: 443-453, August 3, 2005) states “the homologous mammalian rho kinases (ROCK I and II) are assumed to be functionally redundant, based largely on kinase construct overexpression. As downstream effectors of Rho GTPases, their major substrates are myosin light chain and myosin phosphatase. Both kinases are implicated in microfilament bundle assembly and smooth muscle contractility. Here, analysis of fibroblast adhesion to fibronectin revealed that although ROCK II was more abundant, its activity was always lower than ROCK I. Specific reduction of ROCK I by siRNA resulted in loss of stress fibers and focal adhesions, despite persistent ROCK II and guanine triphosphate-bound RhoA. In contrast, the microfilament cytoskeleton was enhanced by ROCK II down-regulation. Phagocytic uptake of fibronectin-coated beads was strongly down-regulated in ROCK II-depleted cells but not those lacking ROCK I. These effects originated in part from distinct lipid-

binding preferences of ROCK pleckstrin homology domains. ROCK II bound phosphatidylinositol 3,4,5P₃ and was sensitive to its levels, properties not shared by ROCK I. Therefore, endogenous ROCKs are distinctly regulated and in turn are involved with different myosin compartments.”

- [0023] In another example, Harb *et al* (PloS ONE 3(8): e3001. oi:10.1371/journal.pone.0003001, August 2008) discloses an essential role of the Rho-Rock-Myosin signaling axis for the regulation of basic cell-cell communications in both mouse and human ES cells, and would contribute to advance [sic] in medically compatible xeno-free environments for human pluripotent stem cells.
- [0024] The use of xenogeneic material may be unsuitable for certain applications utilizing pluripotent stem cells. Alternative materials may be used. For example, Stojkovic *et al.* (Stem Cells 23:895-902, 2005) discloses the use of human serum for treating solid substrate surfaces before feeder-cell free cultivation of human ES cells without differentiation.
- [0025] An alternative culture system employs serum-free medium supplemented with growth factors capable of promoting the proliferation of ES cells.
- [0026] For example, Cheon *et al.* (BioReprod DOI:10.1095/biolreprod.105.046870; 19 Oct 2005) disclose a feeder-cell free, serum-free culture system in which ES cells are maintained in unconditioned serum replacement medium supplemented with different growth factors capable of triggering ES cell self-renewal.
- [0027] In another example, Levenstein *et al.* (Stem Cells 24:568-574, 2006) disclose methods for the long-term culture of human ES cells in the absence of fibroblasts or conditioned medium, using media supplemented with basic fibroblast growth factor (FGF).
- [0028] In another example, US20050148070 discloses a method of culturing human ES cells in defined media without serum and without fibroblast feeder cells, the method comprising: culturing the stem cells in a culture medium containing albumin, amino acids, vitamins, minerals, at least one transferrin or transferrin substitute, at least one insulin or insulin

substitute, the culture medium essentially free of mammalian fetal serum and containing at least about 100 ng/ml of a FGF capable of activating a FGF signaling receptor, wherein the growth factor is supplied from a source other than just a fibroblast feeder layer, the medium supported the proliferation of stem cells in an undifferentiated state without feeder cells or conditioned medium.

[0029] In another example, US20050233446 discloses a defined media useful in culturing stem cells, including undifferentiated primate primordial stem cells. In solution, the media is substantially isotonic as compared to the stem cells being cultured. In a given culture, the particular medium comprises a base medium and an amount of each of basic FGF, insulin, and ascorbic acid necessary to support substantially undifferentiated growth of the primordial stem cells.

[0030] In another example, US6800480 states “In one embodiment, a cell culture medium for growing primate-derived primordial stem cells in a substantially undifferentiated state is provided which includes a low osmotic pressure, low endotoxin basic medium that is effective to support the growth of primate-derived primordial stem cells. The basic medium is combined with a nutrient serum effective to support the growth of primate-derived primordial stem cells and a substrate selected from the group consisting of feeder cells and an extracellular matrix component derived from feeder cells. The medium further includes nonessential amino acids, an anti-oxidant, and a first growth factor selected from the group consisting of nucleosides and a pyruvate salt.”

[0031] In another example, US20050244962 states: “In one aspect the invention provides a method of culturing primate embryonic stem cells. One cultures the stem cells in a culture essentially free of mammalian fetal serum (preferably also essentially free of any animal serum) and in the presence of fibroblast growth factor that is supplied from a source other than just a fibroblast feeder layer. In a preferred form, the fibroblast feeder layer, previously required to sustain a stem cell culture, is rendered unnecessary by the addition of sufficient fibroblast growth factor.”

- [0032] In another example, WO2005065354 discloses a defined, isotonic culture medium that is essentially feeder-free and serum-free, comprising: a. a basal medium; b. an amount of basic fibroblast growth factor sufficient to support growth of substantially undifferentiated mammalian stem cells; c. an amount of insulin sufficient to support growth of substantially undifferentiated mammalian stem cells; and d. an amount of ascorbic acid sufficient to support growth of substantially undifferentiated mammalian stem cells.
- [0033] In another example, WO2005086845 discloses a method for maintenance of an undifferentiated stem cell, said method comprising exposing a stem cell to a member of the transforming growth factor-beta (TGF β) family of proteins, a member of the fibroblast growth factor (FGF) family of proteins, or nicotinamide (NIC) in an amount sufficient to maintain the cell in an undifferentiated state for a sufficient amount of time to achieve a desired result.
- [0034] Pluripotent stem cells provide a potential resource for research and drug screening. At present, large-scale culturing of human ES cell lines is problematic and provides substantial challenges. A possible solution to these challenges is to passage and culture the human ES cells as single cells. Single cells are more amenable to standard tissue culture techniques, such as, for example, counting, transfection, and the like.
- [0035] For example, Nicolas *et al.* provide a method for producing and expanding human ES cell lines from single cells that have been isolated by fluorescence-activated cell sorting following genetic modification by lentivirus vectors (Stem Cells Dev. 16:109-118, 2007).
- [0036] In another example, US patent application US2005158852 discloses a method “for improving growth and survival of single human embryonic stem cells. The method includes the step of obtaining a single undifferentiated hES cell; mixing the single undifferentiated cell with an extracellular matrix to encompass the cell; and inoculating the mixture onto feeder cells with a nutrient medium in a growth environment”.

- [0037] In another example, Sidhu et al. (Stem Cells Dev. 15:61-69, 2006) describe the first report of three human ES cell clones, hES 3.1, 3.2 and 3.3, derived from the parent line hES3 by sorting of single-cell preparations by flow cytometry.
- [0038] However, passage and culture of human ES cells as single cells leads to genetic abnormalities and the loss of pluripotency. Culture conditions are important in the maintenance of pluripotency and genetic stability. Generally, passage of human ES cell lines is conducted manually or with enzymatic agents such as collagenase, liberase™ or dispase™.
- [0039] For example, Draper et al. note the presence of “karyotypic changes involving the gain of chromosome 17q in three independent human embryonic stem cell lines on five independent occasions.” (Nature Biotechnol. 22:53-54, 2004).
- [0040] In another example, Buzzard et al. state, “we have only ever detected one karyotype change event...the culture methods used may have had some bearing on our results, given that our methods are distinctly different from those used by most other groups. Typically we passage human ES cells after 7 days by first dissecting the colony with the edge of a broken pipette...No enzymatic or chemical methods of cell dissociation are incorporated into this method. We speculate that this may explain the relative cytogenetic resilience of hES (human ES) cells in our hands.” (Nature Biotechnol. 22:381-382, 2004).
- [0041] In another example, Mitalipova et al. state “bulk passage methods... can perpetuate aneuploid cell populations after extended passage in culture, but may be used for shorter periods (up to at least 15 passages) without compromising the karyotypes...it may be possible to maintain a normal karyotype in hES cells under long-term manual propagation conditions followed by limited bulk passaging in experiments requiring greater quantities of hES cells than manual passage methods, alone, can provide”. (Nature Biotechnol. 23:19-20, 2005).
- [0042] In another example, Heng et al. state “the results demonstrated that the second protocol (trypsinization with gentle pipetting) is much less detrimental to cellular viability than is

the first protocol (collagenase treatment with scratching). This in turn translated to higher freeze-thaw survival rates.” (Biotechnology and Applied Biochemistry 47:33-37, 2007).

[0043] In another example, Hasegawa *et al.* state, “we have established hESC sublines tolerant of complete dissociation. These cells exhibit high replating efficiency and also high cloning efficiency and they maintain their ability to differentiate into the three germ layers.” (Stem Cells 24:2649-2660, 2006).

[0044] Therefore, there is a significant need for methods and compositions for the cultivation of mammalian cells, including cultivation of pluripotent stem cells in the absence of feeder cells and an adlayer, while maintaining the pluripotency of the cells.

SUMMARY

[0045] In one embodiment, the disclosure provides methods and compositions for the attachment, cultivation and detachment of cells to a solid substrate surface containing from at least about 0.5% N, a sum of O and N of greater than or equal to 17.2% and a contact angle of at least about 13.9 degrees, and lacking a feeder cell layer.

[0046] In one embodiment, the disclosure provides a method to enhance the attachment of cells to a surface containing at least 0.5% N, a sum of O and N of greater than or equal to 17.2% and a contact angle of at least 13.9 degrees, lacking a feeder cell layer and lacking an adlayer comprising:

- a. treating a suspension of cells with at least one compound selected from the group consisting of: a compound capable of inhibiting Rho kinase activity, and a compound capable of inhibiting Rho activity, and
- b. adding the suspension of cells to the surface and allowing the cells to attach, wherein the surface comprises corona plasma treated polystyrene, microwave plasma treated polystyrene, corona plasma treated cyclic olefin copolymer or a corona plasma treated blend of polystyrene and polycarbonate.

[0047] In one embodiment, the cells are maintained in culture after the cells attach to the surface. In an alternate embodiment the at least one compound is removed.

- [0048]** In one embodiment, the cells are detached from the surface by removing the at least one compound.
- [0049]** In one embodiment the suspension of cells is a suspension of clusters of cells. In an alternate embodiment, the suspension of cells is a suspension of single cells.
- [0050]** In one embodiment, the cells are pluripotent stem cells. In an alternate embodiment, the cells are stem cells.
- [0051]** Also disclosed is a method to enhance the attachment of cells to a surface containing from at least about 0.9% N, a sum of O and N of greater than or equal to 22.3% and a contact angle of at least about 13.9 degrees, lacking a feeder cell layer and lacking an adlayer, comprising the steps of:
- a. Obtaining a suspension of cells, and
 - b. Adding the suspension of cells to the surface and allowing the cells to attach.
- [0052]** In another aspect, there is provided a composition comprising:
- a. A surface that is part of a vessel or matrix for use in cell culture or analysis, containing from at least 0.5% N, a sum of O and N of greater than or equal to 17.2% and a contact angle of at least 13.9 degrees, lacking a feeder cell layer and lacking an adlayer, and
 - b. At least one compound selected from the group consisting of: a compound capable of inhibiting Rho kinase activity, and a compound capable of inhibiting Rho activity, wherein the surface comprises corona plasma treated polystyrene, microwave plasma treated polystyrene, corona plasma treated cyclic olefin copolymer or a corona plasma treated blend of polystyrene and polycarbonate.
- [0052a]** In another aspect, there is provided a method to attach pluripotent stem cells to a corona-plasma treated polystyrene surface containing at least 1.6% N, a sum of O and N of greater than or equal to 26.5% and having a contact angle of at least 14.3 degrees, lacking a feeder cell layer and lacking an adlayer, comprising the steps of:

- a. obtaining a suspension of the pluripotent stem cells, and
- b. adding the suspension of pluripotent stem cells to the surface and allowing the pluripotent stem cells to attach.

[0052b] In another aspect, there is provided a corona plasma treated polystyrene surface that is part of a vessel or matrix when used in cell culture or analysis, lacking a feeder cell layer and lacking an adlayer, wherein the surface allows the attachment and cultivation of pluripotent stem cells, and wherein the surface contains at least 1.6% N, has a sum of O and N of greater than or equal to 26.5% and has a contact angle of at least 14.3 degrees.

BRIEF DESCRIPTION OF THE DRAWINGS

- [0053] Figure 1 shows phase contrast micrographs (4x) of cells of the human ES cell line H1 that were passaged twice as clusters with LIBERASE on surface modified plates 2, 3 or 4. Images of cells of the human ES cell line H1, cultured on plates treated with a 1:30 dilution of MatrigelTM, Nunclon DeltaTM plates are also shown.
- [0054] Figure 2 shows the effect of 10 μ M Y-27632 on the attachment of human ES cells to surface modified plates. The figure shows phase contrast micrographs (4x) of cells of the human ES cell line H1 that were passaged twice as clusters on surface modified plates 3 and 4. Cells were then passaged onto surface modified plates 2, 3 or 4, in MEF conditioned medium containing 10 μ M Y-27632. Cells were cultured for four days prior to taking the photographs. Cells cultured in the absence of Y-27632 were included as controls.
- [0055] Figure 3 shows a schematic of the time-course of treatment of compounds on human ES cells cultured on the surface modified plates of the present invention. Cells of the human ES cell line H1 were passaged four times as clusters with LIBERASE treatment on surface modified plates 3, or 4, and cultured in MEF conditioned medium. Cells were treated for the first two days after passage with either 10 μ M of the Rho Kinase inhibitor, Y-27632, or with 0.5 ng/ml of the Rho inhibitor, a cell permeable form of exoenzyme C3 transferase. Cells that were treated with the Rho Kinase inhibitor, Y-27632 and were thereafter treated for the first two days after each passage with Y-27632 on surface modified plate 3 are referred to as “7s”. Cells that were treated with the Rho Kinase inhibitor, Y-27632 and were thereafter treated for the first two days after each passage with Y-27632 on surface modified plate 4 are referred to as “3s”. Cells that were treated with the Rho inhibitor for two days and were then treated with the Rho Kinase inhibitor, Y-27632 for two days after each passage and thereafter treated for the first two days after passage with Y-27632 on surface modified plate 3 are referred to as “5s”. Cells that were treated with the Rho inhibitor for two days and were then treated with the Rho kinase inhibitor, Y-27632 for two days after each passage and thereafter treated for the first two days after passage with Y-27632 on surface modified plate 4 are referred to as “1s”.

- [0056] Figure 4 shows the expression of markers associated with pluripotency and differentiation in human ES cells treated according to the protocol outlined in Figure 6 as determined by qRT-PCR.
- [0057] Figure 5 shows the expression of pluripotency markers in cells of the human ES cell line H1 as determined by flow cytometry at passage 4 (p4), passage 9 (p9), and again at passage 10, 11, or 12 (p10, p11, or p12).
- [0058] Figure 6 shows immuno-fluorescent images of cells of the human ES cell line H1 were passaged serially as clusters with LIBERASE treatment on surface modified plate 4, and cultured in MEF conditioned medium. Expression of proteins associated with markers of pluripotency was detected in cells cultured for 11 passages on surface modified plate 4. Cells were treated with 10 μ M Y-27632 for two days after each passage.
- [0059] Figure 7 shows the ability for human ES cells to form definitive endoderm after culture on surface modified plates. Cells of the human ES cell line H1 were passaged 11 times as clusters with LIBERASE treatment on surface modified plates 3, or 4 and cultured in MEF conditioned medium. At passage 8 (p8) and again at passage 10 or 11 (p10-11) cells were treated with DMEM:F12 media containing 0.5% FBS, 100 ng/ml Activin A, and 20ng/ml Wnt3a for two days and then treated with DMEM:F12 media containing 2% FBS and 100 ng/ml Activin A for three more days. The y-axis on the graph shows the percent positive CXCR4 cells obtained by flow cytometry. See also Table 5.
- [0060] Figure 8 shows the ability for human ES cells to form pancreatic endoderm after culture on surface modified plates. Cells of the human ES cell line H1 were passaged eight times as clusters with LIBERASE treatment on surface modified plates 3, or 4 and cultured in MEF conditioned medium. At passage 8 (p8) cells were subjected to differentiation to definitive endoderm by treatment with DMEM:F12 media containing 0.5% FBS, 100 ng/ml Activin A, and 20 ng/ml Wnt3a for two days and then treated with DMEM:F12 media containing 2% FBS and 100 ng/ml Activin A for three more days. The cells were then further differentiated to embryonic foregut with four days of treatment with DMEM:F12 media containing 2% FBS, 100 ng/ml FGF-10, and 1 μ M cyclopamine-

KAAD. The cells were then differentiated to pancreatic endodenn with four days of treatment with DMEM:F12 media containing 1% B-27, 100 ng/ml FGF-10, 1 μ M cyclopamine-KAAD and 2 μ M retinoic acid. Cells were stained by immunofluorescence for PDX-1 and E-cadherin and total cell number was identified by Hoechst dye.

- [0061] Figure 9 shows the ability of human ES cells cultured on surface modified plates to form embryoid bodies.
- [0062] Figure 10 shows the karyotype of human ES cells cultured on surface modified plate 4.
- [0063] Figure 11 shows the effect of treatment with Rho kinase inhibitors (Y-27632 from EMD biosciences, Y-27632 from Sigma, Fasudil, and Hydroxyfasudil) on the attachment of human ES cells to surface modified plates. Cells were cultured in medium containing the indicated compounds, at the concentrations listed, for three days. Cells were stained with crystal violet and images taken.
- [0064] Figure 12 shows the dose-response of Y-27632 on the attachment of human ES cells to surface modified plates. Various concentrations of the Rho kinase inhibitor, Y-27632, was added to the cultures at a specified concentration (0, 1, 2, 4, or 10 μ M Y-27632) for the first day. The cells were then maintained from day 2 onward in media containing 10 μ M Y-27632 with daily media changes for five days. Media was removed from the plates on day five and the cells were stained with 0.5% crystal violet, and images taken.
- [0065] Figure 13 shows the formation of human ES cell colonies four days after passage onto surface modified plates 2, 3, or 4 with or without 10 of μ M Y-27632.
- [0066] Figure 14 shows the formation of human ES cell colonies four days after passage onto Matrigel™ treated plates with or without 10 μ M Y-27632.
- [0067] Figure 15 shows the difference between continual and intermittent treatment of human ES cells with Y-27632, on attachment of cells to surface modified plates.

- [0068] Figure 16 depicts images of cells from the human ES cell line H9, that were passaged as single cells, seeded on to surface modified plate 3 in MEF conditioned media containing (B) or with out (A) 10 μ M Y-27632. The images were taken 24 hours after seeding.
- [0069] Figure 17 depicts the expression of markers associated with pluripotency in cells from the human ES cell line H9, that were passaged as single cells for 5 passages, using TrypLE™ Express, and plated onto surface modified plates 3 and 4, with or with out 10 μ M of Y-27632 (Y). The pluripotency markers are listed on the x-axis and the percentage of positive cells is shown on the y-axis.
- [0070] Figure 18 depicts the total cell number of cells from the human ES cell line H9, that were passaged as single cells, plated onto surface modified plates 3 and 4. The effect of 10 μ M of Y-27632 (Y) on cell number was examined on cells passaged on Matrigel™ (naïve, N), and cells passaged 10 times on the surface modified plates (acclimated, A). The different cell conditions are listed on the x-axis and the number of cells divided by 10^4 is shown in the y-axis.
- [0071] Figure 19 depicts the rate of growth of cells from the human ES cell line H9, that were passaged as single cells on Matrigel™ treated plates prior to the study. Cells were seeded at $10^4/\text{cm}^2$ and cultured in MEF conditioned media with or with out 10 μ M of Y-27632 on surface modified plates 3 and 4. The y-axis shows the number of cells collected 2, 3 or 4 days after seeding (divided by 10^4).
- [0072] Figure 20 depicts the rate of growth of cells from the human ES cell line H9, that were passaged as single cells for 10 passages on surface modified plates prior to the study. Cells were seeded at $10^4/\text{cm}^2$ and cultured in MEF conditioned media with or with out 10 μ M of Y-27632 on surface modified plates 3 and 4. The y-axis shows the number of cells collected 2, 3 or 4 days after seeding (divided by 10^4).
- [0073] Figure 21 depicts images of cells from the human ES cell line H9, that were passaged as single cells, seeded on to surface modified plates 2-4 and 13 in a 96-well format. The MEF conditioned media contained 10 μ M of Y-27632. Images were taken 48 hours after seeding.

- [0074]** Figure 22 shows the ability of cells from the human ES cell line H9, that were passaged as single cells, seeded on to surface modified plates 3 and 4 to differentiate into definitive endoderm. The extent of formation of definitive endoderm was determined by measuring CXCR expression by flow cytometry. The effect of 10 μ M Y-27632 on the formation of definitive endoderm was investigated. Cells were treated with Y-27632 during expansion. Cells expanded and differentiated on MatrigelTM were included as a control. The y-axis shows percent positive CXCR4 cells obtained by flow cytometry.
- [0075]** Figure 23 shows the ability of cells from the human ES cell line H9, that were passaged as single cells, seeded on to surface modified plates 3 and 4 to differentiate into pancreatic endoderm. Cells were plated onto the surface modified plates and cultured in MEF conditioned medium containing 10 μ M Y-27632, and passaged 8 times on the surface modified plates prior to differentiation. The y-axis shows the fold increase of pancreatic differentiation marker expression (Ngn3, Pdx1, Insulin) by q-PCR at the posterior foregut stage (PF) and the hormone expressing endocrine cell stage (EN).
- [0076]** Figure 24 shows the attachment of human ES cells to surface modified plates. Passage 50 H9 human ES cells were plated at a 1:2 dilution on Surfaces 3 and 4, CellBINDTM, and PrimariaTM. Media was removed from the plates 24 hours after plating and the cells were stained with 0.5% crystal violet, and images taken. Arrows indicate colonies.
- [0077]** Figure 25 shows the attachment of human ES cells to surface modified plates. Passage 50 H9 human ES cells were plated at a 1:2 dilution on Surfaces 3 and 4, CellBINDTM, and PrimariaTM in the presence of various concentrations of Y-27632 (0, 1, 2, 4, 10 and 20 micromolar). Media was removed from the plates 24 hours after plating and the cells were stained with 0.5% crystal violet, and images taken. Colonies are dark spots on the well. Arrows are used to highlight colonies on the untreated wells.
- [0078]** Figure 26 shows the attachment of human ES cells to surface modified plates. Passage 53 H9 human ES cells were plated at a 1:3 dilution on Surfaces 2-4 and 13, CellBINDTM, and PrimariaTM in the absence or presence of Y-27632 (0 or 20 micromolar). Media was removed from the plates 48 hours after plating and the cells were stained with 0.5%

crystal violet, and images taken. Colonies are dark spots on the well. Arrows are used to highlight colonies on the untreated wells.

- [0079]** Figure 27 shows the first attempt (October) and second attempt (December) to attach human H9 ES cells to surface modified plates 14 and 15 and an attempt to attach human H1 ES cells to surface modified plates 14 and 15. Passage 42 and passage 53 H9 human ES, and passage 57 H1 human ES cells were plated at a 1:2 or 1:3 dilution to the modified surfaces in the presence of 20 micromolar Y-27632. Media was removed from the plates 24-48 hours after plating and the cells were stained with 0.5% crystal violet, and images taken. Colonies are dark spots on the well. Arrows are used to highlight colonies on the plates.
- [0080]** Figure 28 shows the attachment of human ES cells to a surface modified plate 4 in defined media, mTeSR™. Passage 50 H9 human ES cells were plated at a 1:2 dilution to the modified surfaces in the absence or presence of Y-27632 (0 or 20 micromolar) in wells that were untreated or treated with proteins (0.1% gelatin, 2% BSA, 0.34mg/ml rat Collagen I, 1:1000 diluted Matrigel™, or 1:5000 diluted Matrigel™). Media was removed from the plates 48 hours after plating and the cells were stained with 0.5% crystal violet, and images taken. Colonies are dark spots on the well.
- [0081]** Figure 29 shows the water contact angles of surface modified plates measured over 11 weeks using the static sessile drop method. The first measurement was done one week after surface treatment and sterilization. Each data point represents the mean contact angle (one measurement on each of 7 drops). The contact angles on Nuclon Delta™ and CellBIND™ plates were measured under the same experimental conditions as Surfaces 1-4 and 13, but the surface treatment and sterilization was done more than 12 weeks before the first measurement (Nuclon Delta™ * was sterilized one week before the first measurement).
- [0082]** Figure 30 shows the density of negative charges on surface modified plates measured as reactivity of surfaces with positively charged crystal violet. Three samples of each surface were tested, and absorbance measurements on desorbed crystal violet from each

sample were performed in triplicate. Mean and standard deviation of nine measurements are given.

[0083] Figure 31 shows the effect of solid substrate surfaces and Y-27632 on attachment and growth of HEK293 cells in chemically defined, serum-free Pro293a-CDMTM medium (A) or EMEM medium supplemented with 10% fetal bovine serum (B). HEK293 cells were seeded in 96-well plates with CellBINDTM surface, Nunclon DeltaTM surface or Surface 4. The number of HEK293 cells attached to these surfaces is shown as a function of culture conditions and concentration of Y-27632. Cells received either: (i) 96 hours of constant treatment in culture with Y-27632 (Y-27632 96h on); or (ii) 48 hours of constant treatment in culture with Y-27632 followed by a change of medium and then 48 hours in culture without Y-27632 (Y-27632 48h on/48h off). HEK293 cells cultured without Y-27632 in the medium (No Y-27632) were handled the same way as cells cultured with Y-27632, that is, for either 96-hours without a change of medium, or with a change of medium after 48 hours. Y-27632 enhanced attachment of HEK293 cells on Surface 4 and the CellBINDTM surface when applied at concentrations of 2.0 and 5.0 μ M. Removing Y-27632 after 48 hours of incubation resulted in detachment of a significant number of cells from Surface 4 and the CellBINDTM surface. Mean and standard deviation of three measurements are shown.

[0084] Figure 32 shows the effect of solid substrate surfaces and Rho kinase inhibitors Y-27632 and H-1152 on growth of HEK293 cells in EMEM medium supplemented with 10% fetal bovine serum. HEK293 cells were seeded in Multidish 24-well plates with either Surface 4 (A) or a non-treated (but gamma irradiated; 25 kGy) polystyrene surface (B).

[0085] Figure 33 shows the effect of H-1152 and Surface 4 on HEK293-cell attachment and morphology. HEK293 cells were seeded in Multidish 12-well plates in EMEM medium supplemented with 10% fetal bovine serum and H-1152, and incubated for 67 hours in an automated, in-incubator microscope. Growth curves in A and photomicrographs in B show the general effect of H-1152 on HEK293-cell attachment and growth on surface 4, and the effect of a change of medium on HEK293-cell attachment and morphology on surface 4 in the presence or absence of H-1152.

- [0086] Figure 34 shows growth curves over 3 passages for HEK293 cells grown on surface 4 and Nunclon Delta™ surface in the absence or presence of 2.5 μ M Y-27632. HEK293 cells in EMEM medium supplemented with 10% fetal bovine serum were passaged 3 times by trypsinization.
- [0087] Figure 35 shows the effect of Rho kinase inhibition on the attachment of cells of the human embryonic stem cell line H1 to surface modified plates 4, 18 and 19, and Primaria™. Wells A&B were control wells on all surfaces. Wells C&D contained 10 μ M Y-27632. Wells E&F contained 3 μ M H1152-glycyl. Wells G&H contained 10 μ M H1152-glycyl.
- [0088] Figure 36 shows the effect of Rho kinase inhibition on the attachment of cells of the human embryonic stem cell line H1 to surface modified plate 30. (--) = no treatment. (RI) = 3 μ M H1152-glycyl. (MG) = adlayer of 1:30 dilution of MATRIGEL. (MG+RI) = adlayer of 1:30 dilution of MATRIGEL + 3 μ M H1152-glycyl.
- [0089] Figure 37 shows the effect of Rho kinase inhibition on the attachment of cells of the human embryonic stem cell line H1 to surface modified plate 31. (--) = no treatment. (RI) = 3 μ M H1152-glycyl. (MG) = adlayer of 1:30 dilution of MATRIGEL. (MG+RI) = adlayer of 1:30 dilution of MATRIGEL + 3 μ M H1152-glycyl.
- [0090] Figure 38 shows the effect of Rho kinase inhibition on the attachment of cells of the human embryonic stem cell line H1 to surface modified plate 32. (--) = no treatment. (RI) = 3 μ M H1152-glycyl. (MG) = adlayer of 1:30 dilution of MATRIGEL. (MG+RI) = adlayer of 1:30 dilution of MATRIGEL + 3 μ M H1152-glycyl.
- [0091] Figure 39 shows the effect of Rho kinase inhibition on the attachment of cells of the human embryonic stem cell line H1 to surface modified plate 33. (--) = no treatment. (RI) = 3 μ M H1152-glycyl. (MG) = adlayer of 1:30 dilution of MATRIGEL. (MG+RI) = adlayer of 1:30 dilution of MATRIGEL + 3 μ M H1152-glycyl.

- [0092] Figure 40 shows the effect of Rho kinase inhibition on the attachment of cells of the human embryonic stem cell line H1 to surface modified plate 34. (--) = no treatment. (RI) = 3 μ M H1152-glycyl. (MG) = adlayer of 1:30 dilution of MATRIGEL. (MG+RI) = adlayer of 1:30 dilution of MATRIGEL + 3 μ M H1152-glycyl.
- [0093] Figure 41 shows the water contact angles of surface modified plates measured over 40 weeks using the static sessile drop method.
- [0094] Figure 42 shows the water contact angles of surface modified plates using the static sessile drop method.
- [0095] Figure 43 shows the density of negative charges on surface modified plates measured as reactivity of surfaces with positively charged crystal violet.
- [0096] Figure 44 shows the density of negative charges on surface modified plates 4, 22-24 and 29 measured as reactivity of surfaces with positively charged crystal violet. Three samples of each surface were tested, and absorbance measurements on desorbed crystal violet from each sample were performed in triplicate. The negative charge density for surfaces 4, 22-24 and 29 was normalized to the negative charge density of the Nunclon DeltaTM surface. Mean and standard deviation of nine measurements are given.

DETAILED DESCRIPTION

- [0097] For clarity of disclosure, and not by way of limitation, the detailed description of the invention is divided into the following subsections that describe or illustrate certain features, embodiments or applications of the present invention.

Definitions

- [0098] “Adlayer” as used herein refers to a layer that is formed on a surface of a solid substrate, by attaching molecules to the surface by either covalent (also known as grafting) or non-covalent (also known as adsorption) bonds. Molecules used in making an adlayer can, for example, be proteinaceous molecules, which may include, for example, extracellular

matrix proteins, amino acids and the like, and non-biological molecules, such as, for example, polyethyleneimine.

- [0099] "β-cell lineage" refers to cells with positive gene expression for the transcription factor PDX-1 and at least one of the following transcription factors: NGN-3, Nkx2.2, Nkx6.1, NeuroD, Isl-1, HNF-3 beta, MAFA, Pax4, and Pax6. Cells expressing markers characteristic of the β cell lineage include β cells.
- [00100] "Cells expressing markers characteristic of the definitive endoderm lineage" as used herein refers to cells expressing at least one of the following markers: SOX-17, GATA-4, HNF-3 beta, GSC, Cer1, Nodal, FGF-8, Brachyury, Mix-like homeobox protein, FGF-4 CD48, comesodermin (EOMES), DKK4, FGF-17, GATA-6, CXCR4, C-Kit, CD99, or OTX2. Cells expressing markers characteristic of the definitive endoderm lineage include primitive streak precursor cells, primitive streak cells, mesendoderm cells and definitive endoderm cells.
- [00101] "Cells expressing markers characteristic of the pancreatic endoderm lineage" as used herein refers to cells expressing at least one of the following markers: PDX-1, HNF-1beta, PTF-1 alpha, HNF-6, or HB9. Cells expressing markers characteristic of the pancreatic endoderm lineage include pancreatic endoderm cells.
- [00102] "Cells expressing markers characteristic of the pancreatic endocrine lineage" as used herein refers to cells expressing at least one of the following markers: NGN-3, NeuroD, Islet-1, PDX-1, NKX6.1, Pax-4, Ngn-3, or PTF-1 alpha. Cells expressing markers characteristic of the pancreatic endocrine lineage include pancreatic endocrine cells, pancreatic hormone expressing cells, and pancreatic hormone secreting cells, and cells of the β-cell lineage.
- [00103] "Definitive endoderm" as used herein refers to cells which bear the characteristics of cells arising from the epiblast during gastrulation and which form the gastrointestinal tract and its derivatives. Definitive endoderm cells express the following markers: CXCR4, HNF-3 beta, GATA-4, SOX-17, Cerberus, OTX2, goosecoid, c-Kit, CD99, and Mix11.

- [00104] “Extracellular matrix proteins” refers to proteinaceous molecules normally found between cells in the body or in the placenta. Extracellular matrix proteins can be derived from tissue, body fluids, such as, for example, blood, or media conditioned by non-recombinant cells or recombinant cells or bacteria.
- [00105] “Extraembryonic endoderm” as used herein refers to a population of cells expressing at least one of the following markers: SOX-7, AFP, and SPARC.
- [00106] “HEK293 cells” refers to a cell line generated by transformation of a culture of normal human embryonic kidney cells as described by Graham *et al.* (J. Gen. Virol. 36:59-72, 1977), and any cells derived from this parent cell line.
- [00107] “Markers” as used herein, are nucleic acid or polypeptide molecules that are differentially expressed in a cell of interest. In this context, differential expression means an increased level for a positive marker and a decreased level for a negative marker. The detectable level of the marker nucleic acid or polypeptide is sufficiently higher or lower in the cells of interest compared to other cells, such that the cell of interest can be identified and distinguished from other cells using any of a variety of methods known in the art.
- [00108] “Matrix” as used herein refers to a 3-dimensional support to which cells may attach.
- [00109] “Mesendoderm cell” as used herein refers to a cell expressing at least one of the following markers: CD48, comesodermin (EOMES), SOX-17, DKK4, HNF-3 beta, GSC, FGF-17, GATA-6.
- [00110] “Pancreatic endocrine cell” or “pancreatic hormone expressing cell” as used herein refers to a cell capable of expressing at least one of the following hormones: insulin, glucagon, somatostatin, and pancreatic polypeptide.
- [00111] “Pancreatic hormone secreting cell” as used herein refers to a cell capable of secreting at least one of the following hormones: insulin, glucagon, somatostatin, and pancreatic polypeptide.

- [00112] “Pre-primitive streak cell” as used herein refers to a cell expressing at least one of the following markers: Nodal, or FGF-8.
- [00113] “Primitive streak cell” as used herein refers to a cell expressing at least one of the following markers: Brachyury, Mix-like homeobox protein, or FGF-4.
- [00114] “Surface” as used herein refers to the outermost layer of molecules of a solid substrate vessel or matrix intended for use in cell culture or analysis. The elemental composition, the roughness, and the wettability of the surface can be analyzed by X-Ray Photoelectron Spectroscopy (XPS), Atomic Force Microscopy (AFM), and contact angle measurement, respectively.
- [00115] “Surface modified plate” refers to a vessel containing any one of surfaces 1-34, described in Examples 16, 17 and 26, or plates containing surfaces that are sold under the trade names Nunclon Delta™, Costar™, Falcon™, CellBIND™, and Primaria™. The vessel can, for example, be made of a polymer, such as polystyrene (PS), cyclic olefin copolymer (COC), polycarbonate (PC), polymethyl methacrylate (PMMA), or styrene acrylonitrile copolymer (SAN).
- [00116] Stem cells are undifferentiated cells defined by their ability at the single cell level to both self-renew and differentiate to produce progeny cells, including self-renewing progenitors, non-renewing progenitors, and terminally differentiated cells. Stem cells are also characterized by their ability to differentiate *in vitro* into functional cells of various cell lineages from multiple germ layers (endoderm, mesoderm and ectoderm), as well as to give rise to tissues of multiple germ layers following transplantation and to contribute substantially to most, if not all, tissues following injection into blastocysts.
- [00117] Stem cells are classified by their developmental potential as: (i) totipotent, meaning able to give rise to all embryonic and extraembryonic cell types; (ii) pluripotent, meaning able to give rise to all embryonic cell types; (iii) multipotent, meaning able to give rise to a subset of cell lineages, but all within a particular tissue, organ, or physiological system (for example, hematopoietic stem cells (HSC) can produce progeny that include HSC (self-renewal), blood cell restricted oligopotent progenitors and all cell types and elements (e.g.,

platelets) that are normal components of the blood); (iv) oligopotential, meaning able to give rise to a more restricted subset of cell lineages than multipotent stem cells; and (v) unipotent, meaning able to give rise to a single cell lineage (e.g., spermatogenic stem cells).

[00118] Differentiation is the process by which an unspecialized ("uncommitted") or less specialized cell acquires the features of a specialized cell such as, for example, a nerve cell or a muscle cell. A differentiated or differentiation-induced cell is one that has taken on a more specialized ("committed") position within the lineage of a cell. The term "committed", when applied to the process of differentiation, refers to a cell that has proceeded in the differentiation pathway to a point where, under normal circumstances, it will continue to differentiate into a specific cell type or subset of cell types, and cannot, under normal circumstances, differentiate into a different cell type or revert to a less differentiated cell type. Dedifferentiation refers to the process by which a cell reverts to a less specialized (or committed) position within the lineage of a cell. As used herein, the lineage of a cell defines the heredity of the cell, that is, which cells it came from and what cells it can give rise to. The lineage of a cell places the cell within a hereditary scheme of development and differentiation. A lineage-specific marker refers to a characteristic specifically associated with the phenotype of cells of a lineage of interest and can be used to assess the differentiation of an uncommitted cell to the lineage of interest.

[00119] Various terms are used to describe cells in culture. "Maintenance" refers generally to cells placed in a growth medium under conditions that facilitate cell growth and/or division that may or may not result in a larger population of the cells. "Passaging" refers to the process of removing the cells from one culture vessel and placing them in a second culture vessel under conditions that facilitate cell growth and/or division.

[00120] A specific population of cells, or a cell line, is sometimes referred to or characterized by the number of times it has been passaged. For example, a cultured cell population that has been passaged ten times may be referred to as a P10 culture. The primary culture, that is, the first culture following the isolation of cells from tissue, is designated P0. Following the first subculture, the cells are described as a secondary culture (P1 or passage 1). After the second subculture, the cells become a tertiary culture (P2 or passage 2), and so on. It will be

understood by those of skill in the art that there may be many population doublings during the period of passaging; therefore the number of population doublings of a culture is greater than the passage number. The expansion of cells (that is, the number of population doublings) during the period between passaging depends on many factors, including but not limited to the seeding density, substrate, medium, growth conditions, and time between passaging.

[00121] In one embodiment, the present invention provides a method to enhance the attachment of cells to a surface containing from at least about 0.9% N, a sum of O and N of greater than or equal to 22.3% and a contact angle of at least about 13.9 degrees, lacking a feeder cell layer and lacking an adlayer, comprising the steps of:

- a. Obtaining a suspension of cells, and
- b. Adding the suspension of cells to the surface and allowing the cells to attach.

[00122] In one embodiment, the present invention provides a method to enhance the attachment of cells to a surface containing from at least about 0.5% N, a sum of O and N of greater than or equal to 17.2% and a contact angle of at least about 13.9 degrees, lacking a feeder cell layer and lacking an adlayer, comprising the steps of:

- a. Obtaining a suspension of cells,
- b. Treating the suspension of cells with at least one compound selected from the group consisting of: a compound capable of inhibiting Rho kinase activity, and a compound capable of inhibiting Rho activity, and
- c. Adding the suspension of cells to the surface and allowing the cells to attach.

[00123] In one embodiment the suspension of cells is a suspension of clusters of cells. In an alternate embodiment, the suspension of cells is a suspension of single cells.

[00124] In one embodiment, the cells are pluripotent stem cells. In an alternate embodiment, the cells are stem cells.

- [00125]** In one embodiment, the surface has an adlayer. In one embodiment, the adlayer is an extracellular matrix component, such as, for example, those derived from basement membrane or that may form part of adhesion molecule receptor-ligand couplings. In one embodiment, the adlayer is made from MATRIGEL (Becton Dickenson). MATRIGEL is a soluble preparation from Engelbreth-Holm Swarm tumor cells that gels at room temperature to form a reconstituted basement membrane. The proteinaceous adlayer may also be formed from laminin, fibronectin, proteoglycan, entactin, heparan sulfate, and the like, alone or in various combinations.
- [00126]** In one embodiment, the cells are maintained in culture after the cells attach to the surface. In an alternate embodiment the at least one compound is removed after the cells attach to the surface. In one embodiment, the cells are detached from the surface by removing the at least one compound.
- [00127]** In one embodiment, the suspension of cells is treated with at least one compound capable of inhibiting Rho kinase activity. In an alternate embodiment, the suspension of cells is treated with at least one compound capable of inhibiting Rho activity. In an alternate embodiment, the suspension of cells is treated with at least one compound capable of inhibiting Rho kinase activity and at least one compound capable of inhibiting Rho activity.
- [00128]** The at least one compound capable of inhibiting Rho kinase activity is selected from the group consisting of: Y-27632, Fasudil, and Hydroxyfasudil.
- [00129]** In one embodiment, the at least compound capable of inhibiting Rho kinase activity is Y-27632.
- [00130]** The at least one compound capable of inhibiting Rho kinase activity may be used at a concentration from about 0.1 μM to about 100 μM . In one embodiment, the at least one compound capable of inhibiting Rho kinase activity is used at a concentration of about 10 μM .
- [00131]** In one embodiment, the at least one compound capable of inhibiting Rho activity is a Rho GTPase inhibitor.

- [00132] In one embodiment, the at least one compound capable of inhibiting Rho activity is exoenzyme C3 Transferase.
- [00133] The at least one compound capable of inhibiting Rho activity may be used at a concentration from about 0.01µg/ml to about 5µg/ml. In one embodiment, the at least one compound capable of inhibiting Rho activity is used at a concentration of about 0.5µg/ml.

Surface Modified Plates

- [00134] Surface modified plates suitable for use in the present invention may be vessels whose surfaces have been modified to contain from at least about 0.5% N, a sum of O and N of greater than or equal to 17.2% and a contact angle of at least about 13.9 degrees. Alternatively, the surface may be a 3-dimensional matrix, such as, for example, a porous scaffold, to which cells can attach.
- [00135] In one embodiment, the surface modified plate comprises a plate whose surface contains from at least about 0.5% N, a sum of O and N of greater than or equal to 17.2% and a contact angle of at least about 13.9 degrees. In an alternate embodiment, the surface modified plate comprises a plate whose surface contains from at least about 0.5% N, a sum of O and N of greater than or equal to 19.5% and a contact angle of at least about 13.9 degrees.
- [00136] In one embodiment, the surface modified plate comprises a plate whose surface contains from at least about 1.3% N, a sum of O and N of at least about 24.9% and a contact angle of at least about 20.7 degrees, which is referred herein as surface modified plate 1.
- [00137] In one embodiment, the surface modified plate comprises a plate whose surface contains from at least about 1.7% N, a sum of O and N of at least about 29.6% and a contact angle of at least about 14.3 degrees, which is referred herein as surface modified plate 2.
- [00138] In one embodiment, the surface modified plate comprises a plate whose surface contains from at least about 2.0% N, a sum of O and N of at least about 30.7% and a contact angle of at least about 18.4 degrees, which is referred herein as surface modified plate 3.

- [00139]** In one embodiment, the surface modified plate comprises a plate whose surface contains from at least about 2.1% N, a sum of O and N of at least about 30.2% and a contact angle of at least about 17.4 degrees, which is referred herein as surface modified plate 4.
- [00140]** In one embodiment, the surface modified plate comprises a plate whose surface contains from at least about 1.8% N, a sum of O and N of at least about 28.2% and a contact angle of at least about 18.8 degrees, which is referred herein as surface modified plate 13.
- [00141]** In one embodiment, the surface modified plate comprises a plate whose surface contains from at least about 1.0% N, a sum of O and N of at least about 27.8% and a contact angle of at least about 44.3 degrees, which is sold under the trade name CELLBIND.
- [00142]** In one embodiment, the surface modified plate comprises a plate whose surface contains from at least about 10.2% N, a sum of O and N of at least about 23.0% and a contact angle of at least about 39.5 degrees, which is sold under the trade name PRIMARIA.

Characterization of the Surface Modified Plates

- [00143]** In one embodiment, the elemental composition of the surface of the surface modified plates may be analyzed by X-Ray Photoelectron Spectroscopy (XPS). XPS, also known as Electron Spectroscopy for Chemical Analysis (ESCA), is used as a method to determine what elements or atoms are present in the surface of a solid substrate (all elements in concentrations less than 0.1 atomic percent can be detected, except hydrogen and helium), and to determine the bonding environment of such elements or atoms. As an example, an XPS analysis of a polystyrene (contains only carbon and hydrogen) solid sample would typically give greater than 97% carbon, less than 3% oxygen, and 0% nitrogen (hydrogen is not detected; different levels of oxygen may be detected due to oxidation of the polystyrene chains at the surface, for example, as a result of sterilization by irradiation) (Brevig *et al.*, Biomaterials 26:3039-3053, 2005; Shen and Horbett, J. Biomed. Mater. Res. 57:336-345, 2001).

- [00144] In one embodiment, the roughness of the surface of the surface modified plates may be analyzed by Atomic Force Microscopy (AFM). Surface atoms or molecules with a lateral resolution down to 1Å and a vertical resolution down to 0.1Å can be imaged by AFM.
- [00145] In one embodiment, the wettability of the surface of the surface modified plates may be analyzed by measuring the contact angle. For example, contact angle measurement by the static sessile drop method provides information on the interaction between the surface of a solid substrate and a liquid. The contact angle describes the shape of a liquid drop resting on the surface of the solid substrate, and is the angle of contact of the liquid on the surface of the solid substrate, measured within the liquid at the contact line where liquid, solid, and gas meet. A surface with a water contact angle larger than 90° is termed hydrophobic, and a surface with water contact angle less than 90° is termed hydrophilic. On extremely hydrophilic surfaces, that is, surfaces that have a high affinity for water, a water droplet will completely spread (an effective contact angle of 0°).
- [00146] In one embodiment, the negative charge density of the surface of the surface modified plates may be analyzed by measuring the reactivity of the surface with crystal violet. Crystal violet carries a positive charge, which enables it to bind to negatively charged molecules and parts of molecules, for example, negatively charged functional groups present on a polymer surface. A surface with a high crystal violet reactivity has a higher density of negative charges than a surface with a low crystal violet reactivity, given that the surfaces have the same roughness and thus area.

Pluripotent Stem Cells

Characterization of Pluripotent Stem Cells

- [00147] Pluripotent stem cells may express one or more of the stage-specific embryonic antigens (SSEA) 3 and 4, and markers detectable using antibodies designated Tra-1-60 and Tra-1-81 (Thomson *et al.*, Science 282:1145 1998). Differentiation of pluripotent stem cells *in vitro* results in the loss of SSEA-4, Tra-1-60, and Tra-1-81 expression (if present) and increased expression of SSEA-1. Undifferentiated pluripotent stem cells typically have alkaline phosphatase activity, which can be detected by fixing the cells with 4%

paraformaldehyde and then developing with Vector Red as a substrate, as described by the manufacturer (Vector Laboratories, Burlingame Calif.). Undifferentiated pluripotent stem cells also typically express Oct-4 and TERT, as detected by RT-PCR.

[00148] Another desirable phenotype of propagated pluripotent stem cells is a potential to differentiate into cells of all three germinal layers: endoderm, mesoderm, and ectoderm tissues. Pluripotency of stem cells can be confirmed, for example, by injecting cells into severe combined immunodeficient (SCID) mice, fixing the teratomas that form using 4% paraformaldehyde, and then examining them histologically for evidence of cell types from the three germ layers. Alternatively, pluripotency may be determined by the creation of embryoid bodies and assessing the embryoid bodies for the presence of markers associated with the three germinal layers.

[00149] Propagated pluripotent stem cell lines may be karyotyped using a standard G-banding technique and compared to published karyotypes of the corresponding primate species. It is desirable to obtain cells that have a "normal karyotype," which means that the cells are euploid, wherein all human chromosomes are present and not noticeably altered.

Sources of Pluripotent Stem Cells

[00150] The types of pluripotent stem cells that may be used include established lines of pluripotent cells derived from tissue formed after gestation, including pre-embryonic tissue (such as, for example, a blastocyst), embryonic tissue, or fetal tissue taken any time during gestation, typically but not necessarily before approximately 10-12 weeks gestation. Non-limiting examples are established lines of human ES cells or human embryonic germ cells, such as, for example the human ES cell lines H1, H7, and H9 (WiCell). Also contemplated is use of the compositions of this disclosure during the initial establishment or stabilization of such cells, in which case the source cells would be primary pluripotent cells taken directly from the source tissues. Also suitable are cells taken from a pluripotent stem cell population already cultured in the absence of feeder cells, as well as a pluripotent stem cell population already cultured in the presence of feeder cells. Also suitable are mutant human ES cell lines, such as, for example, BG01v

(BresaGen, Athens, GA). Also suitable are cells derived from adult human somatic cells, such as, for examples, cells disclosed in Takahashi *et al*, Cell 131: 1-12 (2007).

- [00151]** In one embodiment, human ES cells are prepared as described by Thomson *et al*. (U.S. Pat. No. 5,843,780; Science 282:1145, 1998; Curr. Top. Dev. Biol. 38:133 ff., 1998; Proc. Natl. Acad. Sci. U.S.A. 92:7844, 1995).

Culture of Pluripotent Stem Cells

- [00152]** In one embodiment, pluripotent stem cells are cultured on a layer of feeder cells or extracellular matrix protein that support the pluripotent stem cells in various ways, prior to culturing according to the methods of the present invention. For example, pluripotent stem cells are cultured on a feeder cell layer that supports proliferation of pluripotent stem cells without undergoing substantial differentiation. The growth of pluripotent stem cells on a feeder cell layer without differentiation is supported using (i) Obtaining a culture vessel containing a feeder cell layer; and (ii) a medium conditioned by culturing previously with another cell type, or a non-conditioned medium, for example, free of serum or even chemically defined.
- [00153]** In another example, pluripotent stem cells are cultured in a culture system that is essentially free of feeder cells, but nonetheless supports proliferation of pluripotent stem cells without undergoing substantial differentiation. The growth of pluripotent stem cells in feeder-cell free culture without differentiation is supported using (i) an adlayer on a solid substrate surface with one or more extracellular matrix proteins; and (ii) a medium conditioned by culturing previously with another cell type, or a non-conditioned medium, for example, free of serum or even chemically defined.
- [00154]** In an alternate embodiment, pluripotent stem cells are cultured on a surface modified plate containing from at least about 0.5% N, a sum of O and N of greater than or equal to 17.2% and a contact angle of at least about 13.9 degrees in a medium conditioned by culturing previously with another cell type, or a non-conditioned medium, for example, free of serum or even chemically defined.

[00155] *Culture medium*: An example of cell culture medium suitable for use in the present invention may be found in US20020072117. Another example of cell culture medium suitable for use in the present invention may be found in US6642048. Another example of cell culture medium suitable for use in the present invention may be found in WO2005014799. Another example of cell culture medium suitable for use in the present invention may be found in Xu *et al* (Stem Cells 22: 972-980, 2004). Another example of cell culture medium suitable for use in the present invention may be found in US20070010011. Another example of cell culture medium suitable for use in the present invention may be found in Cheon *et al*. (BioReprod DOI:10.1095/biolreprod.105.046870; 19 Oct 2005). Another example of cell culture medium suitable for use in the present invention may be found in Levenstein *et al*. (Stem Cells 24: 568-574, 2006). Another example of cell culture medium suitable for use in the present invention may be found in US20050148070. Another example of cell culture medium suitable for use in the present invention may be found in US20050233446. Another example of cell culture medium suitable for use in the present invention may be found in US6800480. Another example of cell culture medium suitable for use in the present invention may be found in US20050244962. Another example of cell culture medium suitable for use in the present invention may be found in WO2005065354. Another example of cell culture medium suitable for use in the present invention may be found in WO2005086845.

[00156] Suitable culture media may also be made from the following components, such as, for example, Dulbecco's modified Eagle's medium (DMEM), Gibco # 11965-092; Knockout Dulbecco's modified Eagle's medium (KO DMEM), Gibco # 10829-018; Ham's F12/50% DMEM basal medium; 200 mM L-glutamine, Gibco # 15039-027; non-essential amino acid solution, Gibco 11140-050; β -mercaptoethanol, Sigma # M7522; human recombinant basic fibroblast growth factor (bFGF), Gibco # 13256-029.

Differentiation of Pluripotent Stem Cells

[00157] In one embodiment of the present invention, pluripotent stem cells are propagated in culture, while maintaining their pluripotency. Changes in pluripotency of the cells with time can be determined by detecting changes in the levels of expression of markers

associated with pluripotency. Alternatively, changes in pluripotency can be monitored by detecting changes in the levels of expression of markers associated with differentiation or markers associated with another cell type.

- [00158]** In an alternate embodiment, pluripotent stem cells are propagated in culture and then treated in a manner that promotes their differentiation into another cell type. The other cell type may be a cell expressing markers characteristic of the definitive endoderm lineage. Alternatively, the cell type may be a cell expressing markers characteristic of the pancreatic endoderm lineage. Alternatively, the cell type may be a cell expressing markers characteristic of the pancreatic endocrine lineage. Alternatively, the cell type may be a cell expressing markers characteristic of the β -cell lineage.
- [00159]** Pluripotent stem cells treated in accordance with the methods of the present invention may be differentiated into a variety of other cell types by any suitable method in the art.
- [00160]** For example, pluripotent stem cells treated in accordance with the methods of the present invention may be differentiated into neural cells, cardiac cells, hepatocytes, and the like.
- [00161]** For example, pluripotent stem cells treated in accordance with the methods of the present invention may be differentiated into neural progenitors and cardiomyocytes according to the methods disclosed in WO2007030870.
- [00162]** In another example, pluripotent stem cells treated in accordance with the methods of the present invention may be differentiated into hepatocytes according to the methods disclosed in US patent 6,458,589.
- [00163]** For example, pluripotent stem cells may be differentiated into cells expressing markers characteristic of the definitive endoderm lineage according to the methods disclosed in D'Amour *et al.*, Nature Biotechnol. 23:1534-1541, 2005.
- [00164]** For example, pluripotent stem cells may be differentiated into cells expressing markers characteristic of the definitive endoderm lineage according to the methods disclosed in Shinozaki *et al.*, Development 131:1651-1662, 2004.

- [00165]** For example, pluripotent stem cells may be differentiated into cells expressing markers characteristic of the definitive endoderm lineage according to the methods disclosed in McLean *et al.*, Stem Cells 25:29-38, 2007.
- [00166]** For example, pluripotent stem cells may be differentiated into cells expressing markers characteristic of the definitive endoderm lineage according to the methods disclosed in D'Amour *et al.*, Nature Biotechnol. 24:1392-1401, 2006.
- [00167]** Markers characteristic of the definitive endoderm lineage are selected from the group consisting of SOX17, GATA4, Hnf-3beta, GSC, Cer1, Nodal, FGF-8, Brachyury, Mix-like homeobox protein, FGF-4 CD48, eomesodermin (EOMES), DKK4, FGF-17, GATA6, CXCR4, C-Kit, CD99, and OTX2. Suitable for use in the present invention is a cell that expresses at least one of the markers characteristic of the definitive endoderm lineage. In one aspect of the present invention, a cell expressing markers characteristic of the definitive endoderm lineage is a primitive streak precursor cell. In an alternate aspect, a cell expressing markers characteristic of the definitive endoderm lineage is a mesendoderm cell. In an alternate aspect, a cell expressing markers characteristic of the definitive endoderm lineage is a definitive endoderm cell.
- [00168]** For example, pluripotent stem cells may be differentiated into cells expressing markers characteristic of the pancreatic endoderm lineage according to the methods disclosed in D'Amour *et al.*, Nature Biotechnol. 24:1392-1401, 2006.
- [00169]** Markers characteristic of the pancreatic endoderm lineage are selected from the group consisting of Pdx1, HNF-1beta, PTF1a, HNF-6, HB9 and PROX1. Suitable for use in the present invention is a cell that expresses at least one of the markers characteristic of the pancreatic endoderm lineage. In one aspect of the present invention, a cell expressing markers characteristic of the pancreatic endoderm lineage is a pancreatic endoderm cell.
- [00170]** Pluripotent stem cells may be differentiated into cells expressing markers characteristic of the pancreatic endocrine lineage by any method in the art.

- [00171] For example, pluripotent stem cells may be differentiated into cells expressing markers characteristic of the pancreatic endocrine lineage according to the methods disclosed in D'Amour *et al.*, Nature Biotechnol. 24:1392-1401, 2006.
- [00172] For example, pluripotent stem cells may be differentiated into cells expressing markers characteristic of the pancreatic endocrine lineage, by the methods disclosed in D'Amour *et al.*, Nature Biotechnol. 24:1392-1401, 2006.
- [00173] Markers characteristic of the pancreatic endocrine lineage are selected from the group consisting of NGN-3, NeuroD, Islet-1, Pdx-1, NKX6.1, Pax-4, and PTF-1 alpha. In one embodiment, a pancreatic endocrine cell is capable of expressing at least one of the following hormones: insulin, glucagon, somatostatin, and pancreatic polypeptide. Suitable for use in the present invention is a cell that expresses at least one of the markers characteristic of the pancreatic endocrine lineage. In one aspect of the present invention, a cell expressing markers characteristic of the pancreatic endocrine lineage is a pancreatic endocrine cell. The pancreatic endocrine cell may be a pancreatic hormone-expressing cell. Alternatively, the pancreatic endocrine cell may be a pancreatic hormone-secreting cell.
- [00174] In one aspect of the present invention, the pancreatic endocrine cell is a cell expressing markers characteristic of the β cell lineage. A cell expressing markers characteristic of the β cell lineage expresses Pdx1 and at least one of the following transcription factors: NGN-3, Nkx2.2, Nkx6.1, NeuroD, Isl-1, HNF-3 beta, MAFA, Pax4, and Pax6. In one aspect of the present invention, a cell expressing markers characteristic of the β cell lineage is a β cell.
- [00175] The present invention is further illustrated, but not limited by, the following examples.

EXAMPLES

Example 1

Passage and Maintenance of Human Embryonic Stem Cells as Cell Clusters

- [00176]** The human ES cell lines H1 and H9 were initially maintained on mitomycin C inactivated primary mouse embryonic fibroblasts (MEF). The human ES cells were switched from MEF feeders to Matrigel™ (Becton-Dickinson, Bedford, MA) over repeated passages.
- [00177]** Treatment of surfaces with Matrigel™: Growth Factor Reduced Matrigel™ was thawed at 4°C and then diluted 1:30 in cold DMEM/F12 (Invitrogen, Carlsbad, CA). Volumes sufficient to cover the surface were added to each 6-cm dish (2 ml) or each well of a 6-well plate (1 ml), and incubated 1 hr at room temp. Treated surfaces were used within a few hours or stored at 4°C up to two weeks.
- [00178]** Human ES cell culture: Undifferentiated human ES cell colonies (from either the H9 or H1 lines) were harvested from feeder layers by incubation in 1 mg/ml collagenase IV (Sigma-Aldrich, St. Louis, MO) in DMEM/F12 for 10 minutes, followed by scraping with a pipette. Cell clumps were pelleted by centrifugation at 600 x g for four minutes and the pellet dispersed gently with a 2-ml pipette to break colonies into small clusters of cells. These cell clusters were seeded onto Matrigel™-treated dishes in media conditioned with mouse embryonic fibroblasts (MEF-CM), further supplemented with bFGF (8 ng/ml; R&D Systems, Minneapolis, MN), at 50-150 colonies per 6-cm dish in 5 ml growth medium. Medium was changed daily. Colonies on Matrigel™ in MEF-CM became large and were passed when they occupied 70-80% of the surface area, approximately every 3-4 days. The human ES cells in the colonies had a high nucleus to cytoplasm ratio and had prominent nucleoli, similar to human ES cells maintained on feeders (Figure 1). Differentiated cells represented less than 5% of total cells in culture.
- [00179]** For routine passage of cells in MEF-CM on Matrigel™, cells were incubated in 1 mg/ml collagenase IV in DMEM/F12 for up to 60 minutes and removed from the dishes by forceful streams of DMEM/F12 with scraping. Cells were pelleted, dispersed, and seeded at a 1:3 or 1:4 ratio.

Example 2

Passage of Human Embryonic Stem Cells as Single Cells

- [00180]** Human ES cells of the cell line H9 were grown as single cells according to the methods disclosed in US Patent Application LFS5163USPSP, assigned to LifeScan Inc. Cells were passaged by treatment with TrypLE™ Express for five minutes at 37°C, and seeded at 10,000 cells/cm² substrate surface.

Example 3

Attachment, Cultivation and Maintenance of Pluripotency of Human Embryonic Stem Cells Using Surface Modified Plates Lacking Extracellular Matrix Protein/Components and Feeder Cells

- [00181]** Human ES cells of the line H1, at passage 49 were maintained in MEF conditioned media on Nunclon Delta™ plates treated with a 1:30 dilution of growth factor reduced Matrigel™, prior to study. Cells were dissociated from the surface for passage by 1mg/ml collagenase dissociation or by manual scraping.
- [00182]** These cells were then seeded onto two untreated wells of the surface modified plates (6-well format). Additionally, one well of each plate was treated with 0.1% xeno-free human gelatin as a control. Cells were also plated directly onto untreated and gelatin-treated wells of Costar™ (cat. no. 3516; Corning, Corning, NY), Falcon™ (cat. no. 351146; Becton Dickinson, Franklin Lakes, NJ) and Nunclon Delta™ (cat. no. 140675; Thermo Fisher Scientific, Roskilde, Denmark) 6-well plates for negative controls, and plated onto wells treated with 1:30 dilution of growth factor reduced Matrigel™ to provide as positive controls. In all treatments cells were maintained in MEF conditioned media.
- [00183]** After two passages, surface modified plates 2, 3, and 4 had attached ES cell colonies, which re-attached to the plates and grew following enzymatic dissociation. There was no apparent difference in rate of attachment or growth in gelatin or untreated wells from surface modified plates 2, 3, or 4.
- [00184]** Cells mechanically dissociated from plates treated with 1:30 dilution of growth factor reduced Matrigel™ were poorly attached to surface modified plates 2, 3, and 4, while

cells enzymatically dissociated with 1 mg/ml collagenase were well attached in gelatin or untreated wells from surface modified plates 2, 3, or 4.

- [00185]** H1p49 ES cells added to surface modified plates 1 and 5-12 and to untreated or gelatin treated Nunclon Delta™ plates, Falcon™ plates, and Costar™ plates did not attach. The same cells did attach to plates treated with 1:30 dilution of growth factor reduced Matrigel™, indicating that the cells were competent to attach to a substrate surface.
- [00186]** Normal passage time for ES cells of the H1 line plated on 1:30 dilution of growth factor reduced Matrigel™ was 3-4 days, however cells plated on surface modified plates 2, 3 and 4 took 7 days of culturing before they were ready for passage. This was probably due to the reduced rate of attachment on the treated surfaces, since more starting colonies were apparent on Matrigel™-treated surfaces immediately after plating than on Surfaces 2, 3 and 4.
- [00187]** The passage (p) 50 Cells were split at a 1 to 2 ratio and half of the sample was collected for RNA purification and tested for expression of pluripotency markers (Table 1). The other half of each sample was replated to surface modified plates. Colonies that formed at this passage (p51) also required 7 days of culturing before they were ready to be passaged, and the small colonies that developed after only 4 days of culturing are shown in Figure 1. These colonies maintained classical ES cell colony morphology.
- [00188]** Cultures were stopped at passage 4 on surface modified plates 2, 3 and 4 and samples were assayed for pluripotency markers by qRT-PCR (Table 2) and differentiated to a definitive endoderm fate (DE). Cells at passage 4 maintained expression of the classical pluripotency markers: Oct4, Nanog, Sox2, and TERT. Furthermore, the cells were able to differentiate to a definitive endoderm fate upon exposure to a media containing DMEM/F12, 100ng/ml Activin A, 20 ng/ml Wnt3a, and 0.5-2.0% FBS (Table 3) indicating that pluripotency was maintained in the cells through passage 4.

Example 4

**Attachment, Cultivation and Maintenance of Pluripotency of Human Embryonic
Stem Cells on Surface Modified Plates Lacking Extracellular Matrix
Protein/Components and Feeder Cells: Effects of Rho Inhibition and Rho Kinase
Inhibition**

- [00189]** Human ES cells of the line H1, at passage 49 were maintained in MEF conditioned media on Nunclon DeltaTM plates treated with a 1:30 dilution of growth factor reduced MatrigelTM, prior to study. Cells were dissociated from the surface for passage by 1mg/ml collagenase dissociation.
- [00190]** These cells were then seeded onto untreated wells of surface modified plates (6-well format). Cells were also plated directly onto untreated and gelatin-treated wells of CostarTM, FalconTM, and Nunclon DeltaTM 6-well plates for negative controls and plated onto wells treated with 1:30 dilution of growth factor reduced MatrigelTM to provide as positive controls. In all treatments cells were maintained in MEF conditioned media.
- [00191]** Human ES cells of the line H1, at passage 49 added to surface modified plates 1 and 5-12 and to untreated or gelatin treated Nunclon DeltaTM plates and CostarTM plates did not attach, however, they did attach to surface modified plates 2, 3, and 4. The same cells did attach to plates treated with 1:30 dilution of growth factor reduced MatrigelTM, indicating that the cells were competent to attach to a substrate surface.
- [00192]** Normal passage time for H1 ES cells plated on 1:30 dilution of growth factor reduced MatrigelTM was 3-4 days, however cells plated on surface modified plates 2, 3 and 4 took 7 days of culturing before they were ready for passage. This was probably due to the reduced rate of attachment on the surface modified plates, since more starting colonies were apparent on MatrigelTM-treated surfaces immediately after plating than on surface modified plates 2, 3 and 4.
- [00193]** The passage (p) 50 Cells were split at a 1 to 2 ratio and half of the sample was collected for RNA purification and tested for expression of pluripotency markers (Table 1). The other half of each sample was replated to surface modified plates. Colonies that formed at this passage (p51) also required 7 days of culturing before they were ready to be

passed, and the small colonies that developed after only 4 days of culturing are shown in Figure 1. These colonies maintained classical ES cell colony morphology.

- [00194] Due to the delay in passage, the cells were split at a 1 to 2 ratio and half of the passage 4 samples were plated in MEF conditioned media or MEF conditioned media supplemented with the Rho kinase (ROCK) inhibitor, Y-27632, at a 10 μ M concentration in an attempt to improve cell growth kinetics. Cells were kept in the plating media for 48 hours after passage at which time the media was changed to fresh unsupplemented MEF conditioned media.
- [00195] The addition of Y-27632 at a 10 μ M concentration significantly increased plating efficiency of the cells (p52) and the improvement in colony growth was apparent after 4 days post-plating (Figure 2). Alternatively, prior to collagenase dissociation, human ES cells of the line H1 were also treated with 0.5 ng/ml of a cell permeable form of the Rho inhibitor, C3 exotransferase, which also increased the plating efficiency of the cells.
- [00196] While cells plated in 10 μ M Y-27632 could be passaged 4 days after plating, cells plated without the ROCK inhibitor were not ready to be split 4 days after plating. Cells treated with Rho inhibitor, C3 exotransferase were also not ready for passage 4 days after plating and cells exhibited increased differentiation to a fibroblast-like morphology. Consequently, cells treated with Rho inhibitor at passage 4 were treated with Y-27632 at all subsequent passages (Figure 3).
- [00197] Cells were further passaged to at least 10 passages on surface modified plates 3 and 4 and were tested for the presence of markers associated with pluripotency: genes by qRT-PCR; cell surface marker expression by flow cytometry; and immunofluorescence of cell surface and nuclear proteins (Figures 4-6). Cellular pluripotency was also confirmed by testing their capacity to differentiate to definitive endoderm, pancreatic endoderm, and form embryoid bodies composed of the three germ layers (Figures 7-9). Cells were also tested for karyotypic stability, and we observed that cells could maintain a normal karyotype (Figure 10).

Example 5

Attachment and Detachment of Human Embryonic Stem Cells Through Rho Kinase Inhibition

- [00198]** Human ES cells of the line H9, at passage 40 were maintained in MEF conditioned media on Nunclon Delta™ plates treated with a 1:30 dilution of growth factor reduced Matrigel™, prior to study. Cells were dissociated from the surface for passage by 1 mg/ml collagenase dissociation or by manual scraping.
- [00199]** These cells were then seeded onto surface modified plates 2, 3, 4 and 13 (12-well format) in the presence of increasing amounts one of the following Rho Kinase inhibitors: Y-27632 (from Sigma, St. Louis, MO or EMD, San Diego, CA), Fasudil (Sigma), or Hydroxyfasudil (Sigma), and maintained for 3 days, each day replacing the media and compound. At the end of day three, media was removed and the plates were stained with Crystal Violet (0.5% in water) to visualize colonies.
- [00200]** By day three, surface modified plates 2, 3, 4 and 13 had attached ES cell colonies in the presence of increasing amounts of Rho kinase inhibitor. Best results were obtained through the use of Y-27632 (10 μ M), although some colonies could be observed to attach and grow with the Rho kinase inhibitors, Fasudil and Hydroxyfasudil (Figure 11).
- [00201]** It was attempted to determine the optimal dose of Y-27632 to promote cell binding, by treating cells with a range of plating concentrations of Y-27632 for the first day of culture. After the first day in culture cells were treated on subsequent days with a 10 μ M concentration of Y-27632. It was observed that the maximal concentration to stimulate attachment and growth of ES cells was 10 μ M (Figure 12) and that this occurred on surface modified plates 2, 3, 4, 13 and CellBIND™ (Corning, Corning, NY).
- [00202]** The effect of treating the cells continuously with a single dose of Y-27632 on attachment and growth was also tested. The cells were dosed with 0, 1, 4, or 10 μ M Y-27632 for 4 days. Some binding was observed on surface modified plates without treatment (0 μ M), however the optimal concentration to stimulate attachment and growth of ES cells was 10 μ M Y-27632 (Table 4) on surface modified plates 2, 3, 4, 13.

[00203] Since the addition of ROCK inhibitor significantly enhances the plating and growth kinetics on surface modified plates 2, 3, and 4 versus untreated cells (Figure 13), we wished to determine if this was due to maintenance of proper cell attachment or due to increased cell proliferation. It was observed that Rho Kinase inhibition does not increase cell proliferation, because cells treated with Y-27632 grow at a similar density as untreated cells (Figure 14). Instead, Y-27632 treatment maintains the attachment of cells to the surface and allows them to grow with normal proliferation kinetics (Figure 15). Removal of a Rho Kinase inhibitor from the growth media of ES cells plated in the presence of Rho kinase inhibitor results in detachment of the cells from the surface. The formation of embryoid bodies with differentiation to the 3 germ lineages is accomplished by culturing ES cells in a suspension. Consequently, although later reapplication of a Rho kinase inhibitor restored attachment of cells (Figure 15), as expected, substantial differentiation of the ES cell culture was observed in samples where Rho kinase inhibitor was withdrawn for 24 hours of culture and cells were allowed to detach, grow in suspension for 24 hours and Rho kinase inhibitor was then reapplied.

Example 6

H9 human ES cells passaged with TrypLE™ Express on Surface Modified Plates Show Improved Adhesion with Y-27632

[00204] Initial passaging of H9 human ES cells onto surface modified plates. Adhesion is improved with continuous 10 μ M of Y-27632. This is true for the four surface modified plates tested: 2, 3, 4 and 13. Images of H9 cells 24 hours after seeding on Surface 3 are shown in Figure 16.

Example 7

H9 single Human Embryonic Stem Cells Passaged with TrypLE™ Express on Surface Modified Plates Remain Pluripotent

[00205] Human ES cells are pluripotent and have the ability to differentiate into all cell lineages. The pluripotent state of the cells must be maintained by the surface on which they grow.

To determine if the surface modified plates can maintain human ES cell pluripotency, the human ES cells were passaged 38 times with collagenase and 38 times with TrypLE™ Express followed by 5 passages on surface modified plate 3 (Surface 3), surface modified plate 4 (Surface 4) or Matrigel™ at 1:30 dilution. 10 μ M of Y-27632 was added to the media of indicated samples. The expression, of pluripotency markers Tra-1-60, Tra-1-81, SSEA-3 and SSEA-4, was evaluated by flow cytometry. Results are shown in Figure 17. The percentage of positive cells is indicated on the y-axis. Single human ES cells grown on surface modified plates 3 and 4 can maintain their pluripotency.

Example 8

Rho Kinase Inhibition Promotes Adhesion and growth of Cells from the Human Embryonic Stem Cell line H9, Grown as Single Cells on Surface Modified Plates upon Transfer from Matrigel™

[00206] The role of Y-27632 in human ES cell adhesion and cell growth was studied in relation to the surface modified plates. H9 human ES cells were passaged 38 times with collagenase and 50 times with TrypLE™ Express followed by seeding onto Surfaces modified plates 3 or 4 (naïve cells). Alternatively H9 human ES cells passaged 38 times with collagenase and 38 times with Triple Express followed by 9 passages on surface modified plate 3 (Surface 3, acclimated cells), or surface modified plate 4 (Surface 4, acclimated cells). Cells were seeded at a density of $10^4/\text{cm}^2$ in MEF conditioned media and grown for two days with or without the presence of 10 μ M of Y-27632. Results are shown in Figure 18. Y-27632 improves attachment of naïve cells to surface modified plates 3 and 4. Y-27632 did not improve attachment of acclimated cells to surface modified plates 3 or 4. surface modified plate 3 improved attachment and/or growth of naïve cells. Surface modified plate 4 improved attachment and/or growth of acclimated human ES cells. The cells were followed for a total of 4 days (Figures 19 and 20). The naïve single cells exhibited an increase growth rate when cultured with 10 μ M Y-27632 with surface modified plate 3 showing a slight advantage (Figure 19). The acclimated single cells exhibited improved growth rates with out the 10 μ M of Y-27632 (Figure 20).

Example 9

Surface Modified Plates can be used to Screen Compounds

[00207] Surface modified plates in 96-well configuration and in the Society for Biomolecular Screening (SBS) standard format can be used for growing single human ES cells in the presence of 10 μ M Y-27632. Images of H9 single cells plated in 96-well plate wells are shown in Figure 21. This would allow for the screening of compounds directly in 96-well plates with no interfering cells or adlayers, such as mouse embryonic fibroblasts or Matrigel™, respectively.

Example 10

Single Embryonic Stem Cells Cultured on Surface Modified Plates are able to Differentiate into Definitive Endoderm

[00208] One goal is to differentiate human ES cells into different cell lineages. To determine if surface modified plates can support differentiation, human ES cells were passaged 38 times with collagenase and 38 times with TrypLE™ Express followed by 9 passages on surface modified plate 3 (Surface 3), or surface modified plate 4 (Surface 4). As a positive control, human ES cells were grown on Matrigel™ at 1:30 dilution. 10 μ M of Y-27632 was added to the media during expansion of indicated cell samples. After cell expansion, the ability of the cultured cells to form definitive endoderm was evaluated. Briefly, 70% confluent cultures were treated with 100 ng/ml Activin A, 10 ng/ml Wnt3a and 0.5% FBS in DMEM-F12 media for two days. The treatment was followed by 3 days with 100 ng/ml Activin A and 2% FBS in DMEM/F12. Cells differentiated into definitive endoderm are identified by CXCR4 protein expression, via flow cytometry (Figure 22). The percentage of positive cells is indicated on the y-axis. Human ES cells cultured as single cells can differentiate into definitive endoderm in the presence or absence of Y-27632 on surface modified plates 3 and 4.

Example 11

Single Embryonic Stem Cells Cultured on Surface Modified Plates are able to Differentiate into Pancreatic Endoderm

[00209] After completion of the definitive endoderm protocol, the cells were incubated for 3 days with FGF-7 (50 ng/ml; R&D Systems), the sonic hedgehog inhibitor, KAAD cyclopamine (2.5 μ M; Sigma-Aldrich) and 2% FBS in DMEM-F12 medium. At this point, cells not treated with Y-27632 during expansion detached from the surface modified plates 3 and 4. The cells treated with Y-27632 during expansion, were incubated an additional four days with FGF-7 (50 ng/ml), KAAD cyclopamine (2.5 μ M), Retinoic Acid (1 μ M; Sigma-Aldrich) and 1% B27 (Invitrogen) in DMEM-F12 (posterior foregut stage, PF). After this time, cells were incubated an additional four days in Exendin 4 (50 ng/ml; Sigma-Aldrich), DAPT (1 μ M; Calbiochem), and 1% B27 in DMEM-F12. Differentiation was continued to the pancreatic endoderm stage (EN). This entailed a three-day treatment with CMRL medium (Invitrogen) containing 50ng/ml, HGF, IGF (R&D Systems), and Exendin 4 (50ng/ml), and 1% B27. RNA samples were taken at stages PF and EN from one well of the surface modified plates 3 and 4. These samples were then analyzed by real-time PCR at this step for pancreatic markers Pdx1, Nkx6.1, Nkx2.2, Pax4, NeuroD, HNF3b, Ptf1a, Insulin and AFP. Evaluation of the same pancreatic endoderm markers was repeated at this stage. RNA samples from untreated human ES cells of the same line were subjected to real-time PCR in parallel to treated samples. Treated samples were normalized to untreated controls set to a fold change of 1. Pdx1 and insulin expression was monitored and compared between surface modified plates.

[00210] Induction of pancreatic endoderm markers was observed from cells treated on surface modified plates 3 and 4, although expression was higher with cells treated on surface modified plate 3 (Figure 23). Both surface modified plates in the presence of Y-27632 during expansion can support the differentiation of single human ES cells to posterior foregut and pancreatic endoderm whereas single cells not treated with Y-27632 during expansion detached prior to posterior foregut differentiation.

Example 12

H1 and H9 Human ES Cells Adhere to Surface Modified Plates and Adherence is Enhanced by Treating Cells with Y-27632

- [00211]** Passage 49 H9 human ES cells previously plated to 1:30 Matrigel™ treated plasticware and grown in MEF conditioned media supplemented with 8ng/ml of bFGF were LIBERASE treated and plated to surface modified plates in MEF conditioned media supplemented with 8ng/ml of bFGF and not otherwise treated or supplemented with increasing concentrations of Y-27632. 24 and 48 hours after plating H9 human ES cells to surface modified plates small colonies could be observed on Surfaces 2-4 and 13, and CellBIND™, and Primaria™ (cat. no. 353846, Becton Dickinson, Franklin Lakes, NJ) with crystal violet stain (Figures 24-26). Furthermore, the adherence of H9 human ES cell colonies was improved by the addition of Y-27632 and the effect was dose responsive (Figure 25). Low concentrations of Y-27632 (1 to 2 micromolar) showed a minimal improvement in human ES cell attachment versus untreated human ES cells (Figure 25) while higher concentrations of Y-27632 (4 to 20 micromolar) promoted adherence of human ES cells to surface modified plates as measured by crystal violet stain (Figure 25 and 26).
- [00212]** In addition to the dynamic regulation of human ES cell attachment by addition of Y-27632 to the cell culture media, different rates of adhesion of human ES cells to various surface modified plastics in the presence of Y-27632 were observed. For example, cells were less adherent to CellBIND™ plates and were more likely, over time, to detach from CellBIND™ plates even in the presence of sustained Y-27632 treatment while cells were more adherent and less likely to detach from surface modified plates, 3, 4, or 13 or Primaria™ when treated with the Rho kinase inhibitor, Y-27632 (Figure 25 and 26).

Example 13

Cells from the Human Embryonic Stem Cell Lines H1 and H9 Attach and Form Colonies at Different Rates on Surface Modified Plates in the Presence of Y-27632

- [00213]** H1 and H9 human ES cells previously plated to 1:30 Matrigel™-treated plasticware and grown in MEF conditioned media supplemented with 8 ng/ml of bFGF were LIBERASE

treated and plated to surface modified plates in MEF conditioned media supplemented with 8 ng/ml of bFGF and not otherwise treated or supplemented with 20 micromolar Y-27632. Forty-eight hours after plating H9 human ES cells to surface modified plates 14 and 15, small colonies were observed when the media was supplemented with 20 micromolar Y-27632 (attachment and colony formation was variable from experiment to experiment) (Figure 27). H1 human ES cells also attached to and formed colonies on both Surface 14 and 15 in media supplemented with 20 micromolar Y-27632, and this was more prevalent than the binding observed with H9 human ES cells. These data indicate that there is human ES cell line-to-line variability in attachment to and colony formation on solid substrate surfaces.

Example 14

Human ES Cell Attachment to Surface Modified Plates Using Defined Media

[00214] Passage 49 H9 human ES cells were passaged twice in the defined media, mTeSR™, on Matrigel™-treated plasticware. The cells were then LIBERASE treated and plated onto the surface modified plate Nunc4 in mTeSR™ media. Cells were either plated in media with or without 20 micromolar Y-27632. Wells were also treated with various proteins for 30 minutes prior to seeding cells (no treatment, 0.1% gelatin, 2% BSA, .34mg/ml rat Collagen I, 1:1000 Matrigel™, or 1:5000 Matrigel™) to determine if these proteins could promote human ES cell adhesion in defined media with or without Y-27632 (Figure 28). In the absence of Y-27632, human ES cells plated onto a surface modified plate in defined media did not attach- even in the presence of extracellular matrix proteins such as Collagen I or 1:1000 Matrigel™. However, when 20 micromolar Y-27632 was added to defined mTeSR™ media, human ES cells adhered to surface Nunc4. Furthermore, this adherence was equivalent in untreated wells and wells treated with 0.1% gelatin, 2% BSA, and 0.34 mg/ml rat Collagen I. There was a modest increase in human ES cell attachment in wells with low concentrations of Matrigel™ (1:1000 and 1:5000 dilutions), however these concentrations of Matrigel™ were insufficient to promote adhesion in the absence of Y-27632. These results demonstrate that in the presence of the ROCK Inhibitor, Y-27632, human ES cells can be cultured on modified plastic substrates in

defined media and that low concentrations of MatrigelTM of about 1:1000 or 1:5000 can improve this adhesion.

Example 15

Surface Modified Plates in a Flask Format can Promote Human ES Cell Attachment and Differentiation to Definitive Endoderm and Pancreatic Endoderm

[00215] H1 and H9 human ES cells previously plated to 1:30 MatrigelTM-treated plasticware and grown in MEF conditioned media supplemented with 8ng/ml of bFGF were LIBERASE treated and plated to T25, T75, T150, and T175 flasks at a 1:2 or 1:3 seeding density onto various size flasks with modified surfaces. The cells were seeded in MEF conditioned media supplemented with 8ng/ml of bFGF and 20 micromolar Y-27632. Human ES cell colonies were then allowed to grow, with daily media changes of MEF conditioned media supplemented with 8ng/ml of bFGF and 20 micromolar Y-27632, until the plates were approximately 50% confluent. At this time the media was changed to DMEM/F12 media containing 2% BSA, 100ng/ml Activin A, 20ng/ml Wnt3a, and 20 micromolar Y-27632 and the cells were maintained in this media for 2 days with daily media changes. On day 3 and 4 the media was changed to DMEM/F12 media containing 2% BSA, 100ng/ml Activin A, and 20 micromolar Y-27632. Cells were then released from the surface with TrypLE and assays by flow cytometry for expression of the definitive endoderm (DE) surface marker, CXCR4. It was observed that under these conditions, human ES cells differentiated to a highly CXCR4 positive population, that was as high as almost 90% CXCR4+, indicating that the cells were mostly differentiated to definitive endoderm (Table 5). Furthermore, the attachment of the cells to the culture surface during growth or during differentiation was dependent on maintaining ROCK inhibition, since withdrawal of Y-27632 from the culture media resulted in cell detachment from the plastic.

[00216] To determine if pancreatic endoderm could be formed from the definitive endoderm derived on surface modified plates in flask format, the cells were incubated for an additional four days with Y-27632 (20 micromolar), FGF-7 (50 ng/ml), KAAD

cyclopamine (2.5 micromolar), and 1% B27 (Invitrogen) in DMEM-F12 and then an additional four days in this media supplemented with Retinoic Acid (1 micromolar; Sigma-Aldrich) to differentiate the cells to a pancreatic endoderm stage. RNA samples were then taken and analyzed by real-time PCR for the pancreatic marker Pdx1. Treated samples were normalized to untreated controls set to a fold change of 1. It was observed that samples had increased levels of PDX1 versus undifferentiated human ES cells, with mRNA levels at least 256 fold higher in the differentiated cells than that observed in undifferentiated human ES cells.

Example 16

Surface Treatment and Surface Modified Plates

- [00217]** Surface modified plates were prepared by treating injection molded items using a corona plasma treatment or a microwave plasma treatment (Table 6). The polymer materials used in injection molding were polystyrene, polycarbonate, a blend of polycarbonate and polystyrene, and cyclic olefin copolymer. The surface modified plates were individually packed in plastic bags, then sterilized by gamma irradiation (25 kGy), and finally stored at room temperature until used in cell culture or surface characterization experiments. Surface modified plates 18, 30 and 31-32 were molded using the same polymer materials as surface modified plates 19, 33 and 34, respectively, but were not plasma treated. Surfaces 14 and 31 were not gamma irradiated.
- [00218]** Corona plasma treatment was carried out in a metal vacuum chamber with only one electrode inside the chamber and electrically isolated from the inside of chamber (C-Lab Plasma; Vetaphone A/S, Denmark). The metal walls served as counter electrode (ground). A self-tuning corona generator generated the electrical field giving sufficient energy to generate plasma in the entire chamber. An item to be treated was placed at the bottom of the chamber. The chamber was closed and evacuated to a pressure of 10^{-2} mbar. At this pressure the valve to the vacuum pump was closed and the corona generator engaged. The generator was set to generate an output of 2000 W. The plasma was

energized for 5 to 60 seconds. The gas inlet valve (air) was then opened, and the pressure in the chamber returned to atmospheric level.

- [00219] The microwave plasma treatment was carried out in a quartz vacuum chambers (Model 300-E for surface modified plates 5-12 and Model 440 for surface modified plates 14 and 15; both from Technics Plasma GmbH, Germany). The energy to generate the plasma was supplied by a 2.43 GHz microwave generator outside the chamber. An item to be treated was placed on a glass plate inside the chamber. The chamber was closed and evacuated to a pressure between 0.3 and 0.5 mbar. The valve to the vacuum pump was kept open, and the pressure was maintained at the desired value by adjusting gas (air or oxygen) flow with the gas inlet valve. The microwave generator was then engaged. The generator was set to generate an output of 500 or 600 W. The pump valve was then closed, and the air inlet valve was opened, in order to bring the pressure in the chamber to atmospheric level.
- [00220] Table 6 shows power, time, pressure, and gasses used in preparing surface modified plates by corona plasma or microwave plasma.

Example 17

Surface Characterization of the Surface Modified Plates of the Present Invention

Water Contact Angles

- [00221] Surface modified plates 1-4 and 13 were individually packed in plastic bags, sterilized, and stored at room temperature throughout the test period. Contact angles were first measured one week after surface treatment and sterilization, and then again at the time points given in Figure 29. All contact angle measurements were done using the static sessile drop method and a PG-X measuring Head from FIBRO Systems AB, Sweden [goniometer consisting of video camera and computer software (v. 3.1)]. The tangent leaning method was used for calculation of the contact angles. Drops of 4.0 μ L MilliQ water was applied using automatic drop application in static mode, according to the manufactures instructions. The contact angle of each drop was measured once (7 drops

were applied to each sample per time point). For each time point, a new sample was used in order to avoid any influence from earlier measurements. Measurements on Nunclon Delta™ and CellBIND™ surfaces was performed under the same experimental conditions as measurements on Surface 1-4 and 13, but the surface treatment and sterilization was done more than 12 weeks before the first measurement (Nunclon Delta™* was sterilized one week before the first measurement). Figure 29 shows that surface modified plates 1-4 and 13 were of similar hydrophilicity and more hydrophilic (lower water contact angles) than Nunclon Delta™ and CellBIND™ surfaces. The hydrophilicity of surface modified plates 1-4 and 13 was stable for at least 12 weeks after surface treatment and sterilization.

[00222] CellBIND™ has previously been described as having a contact angle of 13.4 degrees (standard deviation of 4 degrees) [Corning Technical Report (2005), Corning® CellBIND® Surface: An Improved Surface for Enhanced Cell Attachment (CLS-AN-057 REV1) on http://catalog2.corning.com/Lifesciences/media/pdf/t_CellBIND_Improved_Surface_CLS_AN_057.pdf].

Negative Charge Density

[00223] The density of negative charges on surface modified plates 1-4 and 13, Nunclon Delta™ surface, CellBIND™ surface, Primaria™ surface, Falcon™ surface, and a non-treated (but sterilized) polystyrene surface (all in 3-cm dish format) was determined. Three ml of aqueous crystal violet solution (0.015% w/v) was dispensed in each dish, and dishes were incubated for 60 minutes at room temperature under gentle shaking (50 rpm). In order to remove crystal violet not bound to the surfaces, the dishes were washed three times with 3 ml MilliQ water, and then dried over night at 60°C. The crystal violet bound to the surface was desorbed by addition of 1.5 ml of 0.1 M HCl in EtOH solution (99%) and incubating the dishes for 2 minutes at room temperature under gentle shaking (50 rpm). Absorbance of the HCl:EtOH solution with desorbed crystal violet was measured at 590 nm using an EnVision 2100 microplate reader (Perkin Elmer; Waltham, MA, USA). Absorbance values were corrected for background absorbance of HCl:EtOH

solution. The negative charge density was measured on three dishes per surface, and absorbance measurement was performed in triplicate for each dish.

- [00224]** The negative charge density for surface modified plates is shown in Figure 30. The negative charge densities of Surfaces 1-4 and 13 were similar, but longer surface treatment time in the interval of 5-60 seconds tended to result in a lower surface negative charge density. Surfaces 1-4 and 13 had significantly lower negative charge densities than CellBIND™ surface and a Nunclon Delta™ surface treated in 2007. Surfaces 1-4 and 13 had negative charge densities at the same level as a Nunclon Delta™ surface treated in 2005, and significantly higher negative charge densities than Primaria™ surface, Falcon™ surface, and a non-treated (but sterilized) polystyrene surface. The lower negative charge density of Nunclon Delta™ surface treated in 2005 than of Nunclon Delta™ surface treated in 2007, suggest that surface-treated polystyrene becomes slightly less negatively charged over time. The high level of negative charge density of CellBIND™ is not because of higher surface roughness and thus surface area (See AFM analysis in this Example).

X-Ray Photoelectron Spectroscopy (XPS)

- [00225]** Surface modified plates 1-4 and 13-15, and plates with Nunclon Delta™, Costar™, Falcon™, CellBIND™ and Primaria™ surfaces were analyzed using XPS. Sample was presented to the x-ray source by cutting sections from the plates and mounting them with spring clips onto a stainless steel sample holder. Samples were irradiated with Al K α radiation (1486 eV). The analysis was performed with an angle of 45° between the sample and analyzer. The spectra were curve fit using the software package provided by the instrument's vendor, Physical Electronics. The software utilized commercial Matlab™ routines for data processing. The instrument used for the analysis was a Physical Electronics Model 5400 X-Ray Photoelectron Spectrometer. The outermost two to five nanometers in depth in a region of about one millimeter in diameter from the surface treated part of the plates was analyzed in each of two plates per surface.

- [00226]** Surface elemental composition in units of atomic percent is shown in Table 7. All surface modified plates contained carbon, oxygen and nitrogen (hydrogen is not detected in XPS) in the surface. Surfaces 1-4, Surface 13 and CellBIND™ surface contained more oxygen than the other surfaces analyzed. Surfaces 1-4 and Surfaces 13-15 contained less nitrogen than Primaria™, but more nitrogen than the surfaces of Nunclon Delta™, Costar™, Falcon™, and CellBIND™ plates. Oxygen and nitrogen levels correlated positively with longer surface treatment time (Surfaces 1-4 and 13), and the highest levels of both of these elements were obtained using 30 or 60 seconds of corona plasma treatment (Surface 3 and Surface 4, respectively). Surfaces 3 and 4 were similar in elemental composition. Surfaces 2 and 13 were similar in elemental composition, and more like Surfaces 3 and 4 than Surface 1 in elemental composition.
- [00227]** C1s spectra peaks were curve fit (best chi-squared fit), in order to identify and quantify the bonding environments for carbon in the surfaces, by using peak widths and energy locations for species as found in the literature (Table 8). The concentrations are reported in units of atomic percent, which were obtained by multiplying the area percent by the atomic concentration. Surfaces 2-4 and 13 were similar in terms of the carbon bonding environments. The proportion of carbon in C*-C-O-C-C* bonding environment was lower in Surfaces 2-4 and 13 than in the other surfaces analyzed. The proportion of carbon in O-[C=O]-O bonding environment was higher in Surfaces 2-4 and 13 than in the other surfaces analyzed. Similarities between Surfaces 2-4 and 13 and Surface 1, CellBIND™ surface, and/or Primaria™ surface were also identified. The proportion of carbon in C-O-C or C-NH3⁺ bonding environment (same energy location in spectra) was higher in Surfaces 1-4 and 13 than in the other surfaces analyzed. The proportion of carbon in C-O-C*=O bonding environment was higher in Surfaces 2-4, Surface 13, and Primaria™ surface than in the other surfaces analyzed. The proportion of carbon in CO₃ - bonding environment was higher in Surfaces 2-4, Surface 13, and CellBIND™ surface than in the other surfaces analyzed. The proportion of carbon in C=O bonding environment was higher in Surfaces 1-4, Surface 13, and CellBIND™ surface than in the other surfaces analyzed. The proportion of carbon in C-[O]-C bonding environment was higher in Surfaces 1-4, Surface 13, CellBIND™ surface, and Primaria™ surface than in

the other surfaces analyzed. The energy loss peak resulted from an aromatic $\Pi \rightarrow \Pi^*$ transition, and is an indicator of surface aromaticity.

- [00228]** The O1s spectra peaks were almost Gaussian and could not be curve fit. N1s spectra peaks were curve fit (best chi-squared fit), in order to identify and quantify the bonding environments for nitrogen in the surfaces, by using peak widths and energy locations for species as found in the literature (Table 9). The concentrations are reported in units of atomic percent, which were obtained by multiplying the area percent by the atomic concentration. The N1s signals from Nunclon DeltaTM, CellBINDTM, CostarTM, and FalconTM surfaces were weak, and it was, therefore, not possible to do identification of the bonding environments for nitrogen in these surfaces. N1s spectra were indistinguishable for surface modified plates 1-4 and 13, and data resulting from curve fitting of two representative N1s spectra is shown. The proportion of nitrogen in $-\text{NH}_3^+$ bonding environment was higher in Surfaces 1-4 and 13 than in Surfaces 14 and 15 and PrimariaTM surface. Nitrogen in $-\text{NH}_2$ bonding environment was detected only in Surfaces 14 and 15 and PrimariaTM surface. Nitrogen in $-\text{NO}_2$ bonding environment was detected only in Surfaces 1-4 and 13, and in a single sample of Surface 15. Nitrogen in $-\text{NO}_3$ bonding environment was detected only in Surface 15 and PrimariaTM surface.
- [00229]** CellBINDTM has previously been described as having an elemental composition of 70.4% carbon, 29.0% oxygen, 0.6% nitrogen, and <0.01% other elements, and a relatively high concentration of C-[O]-C, C=O, and COOH/R groups, as analyzed by ESCA [Corning Technical Report (2005), Corning® CellBIND® Surface: An Improved Surface for Enhanced Cell Attachment (CLS-AN-057 REV1) on http://catalog2.corning.com/Lifesciences/media/pdf/t_CellBIND_Improved_Surface_CLS_AN_057.pdf].
- [00230]** PrimariaTM has previously been described as having an elemental composition of 74.6% carbon, 14.1% oxygen, 11.1% nitrogen, and 0.2% other elements, with mainly nitrile ($\text{C}\equiv\text{N}$) and urea [$\text{HN}(\text{C}=\text{O})\text{NH}$] carbon-to-nitrogen bonding environments, as analyzed by ESCA.

Atomic Force Microscopy (AFM)

[00231] Surface modified plates 1-4 and 13, and plates with Nunclon Delta™ and CellBIND™ surfaces were analyzed using AFM. Samples were analyzed using a Digital Instruments Multimode Atomic Force Microscope in tapping mode. The tip used was a tapping mode tip, type TESP7. Samples were attached to the sample disks with double sticky tape. Regions of 10 µm x 10 µm and 500 nm x 500 nm of the surface-treated part of the plates were analyzed. Surface mean roughness (Ra) and maximum height (Rmax) in units of nanometers are shown in Table 10. Like the plates with Nunclon Delta™ and CellBIND™ surfaces, surface modified plates 1-4 and 13 were relatively smooth, and Ra and Rmax did not correlate with surface treatment time in either of the two scans. Analysis of non-treated polystyrene and oxidized polystyrene surfaces intended for cell culture, and Primaria™ surface has been described by Shen and Horbett (J. Biomed. Mater. Res. 57:336-345, 2001): surface roughness approximately 4 nm for all three surfaces.

Example 18

Surface Elemental Composition and Contact Angle in Relation to Human ES Cell Attachment and Colony Formation

- [00232]** A summary of the results of the XPS analysis of surface elemental composition, the surface contact angle measurements, and human ES cell attachment and colony formation experiments is given in Table 11.
- [00233]** Human ES cell attachment to and colony formation (at least 15 colonies per 10 cm² surface) on a solid substrate surface in the absence of a compound capable of inhibiting Rho or Rho kinase was observed on only surface modified plates 2-4 and 13, CellBIND™ plates, and Primaria™ plates (cells were presented to the surfaces as a suspension of clusters of cells). Surface modified plates 2-4 and 13 supported cell attachment, colony formation and passaging. After about three passages, the growth rate of human ES cells on surface modified plates 2-4 and 13 declined spontaneously (only in the absence of Rho inhibition and Rho kinase inhibition), although cell morphology

indicated that the cells were not differentiating. Furthermore, pluripotency marker expression was maintained in cells passaged four times on Surface 3. CellBIND™ plates supported human ES cell attachment and colony formation, but differentiation of the cells was observed prior to the first passage. Based upon cell morphology observations, Primaria™ plates supported human ES cell attachment and colony formation, without signs of differentiation (passaging was not tested). Both oxygen (for example, Surface 2 versus Surface 14) and nitrogen (for example, Primaria™ versus Costar™, and Surfaces 2 and 13 versus CellBIND™) content of surfaces had an effect on the ability of the surfaces to support human ES cell attachment and colony formation in the absence of Rho inhibition and Rho kinase inhibition. Surfaces with a nitrogen content of at least about 0.9%, a sum of nitrogen and oxygen content of at least about 22.3%, and a water contact angle of at least about 13.9 degrees supported human ES cell attachment and colony formation in the absence of Rho inhibition or Rho kinase inhibition.

[00234] Human ES cell attachment and colony formation (at least 15 colonies per 10 cm² surface) on a solid substrate surface in the presence of a compound capable of inhibiting Rho or Rho kinase was observed on surface modified plates 1-15, surface modified plate 19, surface modified plate 33, surface modified plate 34, CellBIND™, and Primaria™ (cells were presented to the surfaces as a suspension of clusters of cells). We noted that surfaces 2-4 and 13 and Primaria™ were better than surfaces 1, 19, 33 and 34 and CellBIND™, which again were better than surfaces 5-12, 14 and 15, at promoting human ES cell attachment and colony formation. On surface modified plates 3 and 4, and in the presence of a Rho kinase inhibitor, human ES cells attached and formed colonies that expanded and could be passaged at least 10 times, giving rise to pluripotent cells with normal karyotype (karyotype tested only in cells grown on Surface 4). Both oxygen (for example, CellBIND™ versus Nunclon Delta™) and nitrogen (for example, Primaria™ versus Costar™; and Surfaces 2 and 13 versus CellBIND™) content of surfaces had an effect on the ability of the surfaces to support human ES cell attachment and colony formation in the presence of Rho kinase inhibition. Surfaces with a nitrogen content of at least about 0.5%, a sum of nitrogen and oxygen content of at least about 17.2%, and a water contact angle of at least about 13.9 degrees supported human ES cell attachment

and colony formation in the presence of Rho kinase inhibition. Surfaces with a nitrogen content of at least about 0.5%, a sum of nitrogen and oxygen content of at least about 17.3% but less than 19.9%, and a water contact angle of at least about 9.4 degrees supported human ES cell attachment and colony formation in the presence of Rho kinase inhibition in some cases (surface 14), but not in others (surfaces 22-24).

- [00235] We noted that removal of Rho kinase inhibitor from human ES cell cultures cultured on surface modified plate 4 resulted in detachment of the human ES cells from the surface of the solid substrate. The cells could then be reattached to the surface by re-treatment with a Rho kinase inhibitor. Given that enzymatic passage of human ES cells is a potential stressor and may cause karyotypic instability, using temporary removal of Rho kinase inhibitor to passage human ES cells could eliminate the stresses of enzymatic passage.
- [00236] Human ES cell attachment and colony formation was also demonstrated using animal-component-free medium, Rho kinase inhibition and surface modified plate 4. Pre-treatment of surface modified plate 4 with extracellular matrix proteins resulted in more colonies, but only in the presence of Rho kinase inhibition.
- [00237] In addition to passaging human ES cells with enzymatic methods that maintain colony style culture conditions by passaging cells as clusters, human ES cells could also be passaged as single cells using enzymes like TrypLE™ or Accutase™. In the presence or in the absence of Rho kinase inhibitor, human ES cell colonies dissociated into a suspension of single cells using TrypLE™ attached to surface modified plates 3 and 4, and formed colonies that could be passaged at least five times and give rise to cells with pluripotency markers.
- [00238] Removal of Rho kinase inhibitor from the human ES cell cultures prepared by passaging the cells as a suspension of single cells did not result in detachment of the human ES cells from the surface of the solid substrate, but resulted in colonies that grew faster than if the Rho kinase inhibitor was not removed.

Example 19

Treatment with Y-27632 Enhance HEK293 Cell Attachment to Surface Modified Plates

- [00239]** Human embryonic kidney cells 293 (HEK293, ECACC no. 85120602) were maintained in Eagle's Minimum Essential Medium (EMEM; Lonza, Verviers, Belgium) containing 10% fetal bovine serum (FBS; Lonza). The cells were adapted to Pro293a-CDM medium (Lonza), a chemically defined, serum-free medium optimized for cultivation of adherent HEK293, by gradually and over several passages using the sequential ratios of 3:1, 1:1, 1:3, 1:7, and finally 0:1 of serum-supplemented EMEM and Pro293a-CDM medium. For maintenance and adaptation, HEK293 cells were seeded at 2.0×10^4 cells/cm² in 75-cm² flasks with Nunclon Delta™ surface (Thermo Fisher Scientific, Roskilde, Denmark) and passaged at 70-80% confluence using Trypsin/EDTA for dissociation.
- [00240]** Pro293a-CDM medium (100 µl) supplemented with Y-27632 (Sigma Chemical Co., St. Louis, MO) in concentrations of 1.0, 4.0 or 10 µM was dispensed in flat-bottomed, 96-well plates with Surface 4, Nunclon Delta™ surface, or CellBIND™ surface. Another 100 µl of Pro293a-CDM medium with HEK293 cells was added to the wells (4.0×10^4 cells/cm²). The cultures were then incubated at 37°C in a humidified atmosphere of 5% CO₂ in air for: (i) 96 hours; or (ii) 48 hours, followed by washing cultures once with 200 µl Dulbecco's Phosphate Buffered Saline (DPBS; Lonza), then adding 200 µl of Pro293a-CDM medium without Y-27632, and finally incubating cultures for another 48 hours.
- [00241]** The number of viable cells in the wells was then determined using a lactate dehydrogenase (LDH) activity kit from Roche, Switzerland. Briefly, wells were washed with Pro293a-CDM medium, and adherent cells were lysed in 100 µl DPBS with 2% (v/v) Triton™ X-100 (Sigma Chemical Co.) during a 30-min incubation at 37°C. Lysate and 100-µl catalyst and dye reagent mixture were mixed and incubated in the dark at 25°C for 30 min. The reaction was stopped by adding 50 µl of 1.0 M HCl, and the absorbance at 490 nm was measured in a microplate reader (Genios Pro; Tecan, Austria). The number of cells was calculated using the A490 values from these samples and from standards containing LDH from a known number of cells.

- [00242]** The effect of the solid substrate surfaces and Y-27632 on attachment and growth of HEK293 cells in Pro293a-CDM medium is shown in Figure 31a, where the 96-hour continuous exposure to Y-27632 is labeled “Y-27632 96h on” and the 48-hour continuous exposure to Y-27632 followed by a change of medium and 48 hours of incubation in the absence of Y-27632 is labeled “Y-27632 48h on/48h off”. In the absence of Y-27632, HEK293 cells attached to all three surfaces. A change of medium after 48 hours of incubation resulted in significantly fewer cells in the cultures, measured after 96 hours of incubation. Y-27632 enhanced attachment of HEK293 cells on Surface 4 and CellBIND™ surface when applied at concentrations of 2.0 and 5.0 μ M. Removing Y-27632 after 48 hours of incubation resulted in significant detachment of cells from all three surfaces.
- [00243]** A similar experiment, but using 2.0×10^4 non-adapted HEK293 cells per cm^2 and EMEM supplemented with 10% FBS throughout, was performed. The effect of the solid substrate surfaces and Y-27632 on attachment and growth of HEK293 cells in EMEM supplemented with 10% FBS is shown in Figure 31b, where the 96-hour continuous exposure to Y-27632 is labeled “Y-27632 96h on” and the 48-hour continuous exposure to Y-27632 followed by a change of medium and 48 hours of incubation in the absence of Y-27632 is labeled “Y-27632 48h on/48h off”. In the absence of Y-27632, HEK293 cells attached to all three surfaces. A change of medium after 48 hours of incubation resulted in significantly fewer cells in the cultures, measured after 96 hours of incubation. Y-27632 enhanced attachment of HEK293 cells on Surface 4 and CellBIND™ surface when applied at concentrations of 2.0 and 5.0 μ M. Removing Y-27632 after 48 hours of incubation resulted in significant detachment of cells from Surface 4 and CellBIND™.

Example 20

Treatment with Y-27632 and H-1152 Enhance HEK293 Cell Growth on Surface Modified Plates

- [00244]** HEK293 cells were maintained in EMEM (Lonza) containing 10% FBS (Lonza). Cells were passaged at 70-80% confluence using Trypsin/EDTA for dissociation, and seeded at

c 2.0×10^4 cells/cm² in 75-cm² flasks with Nunclon Delta™ surface (Thermo Fisher Scientific, Roskilde, Denmark).

[00245] EMEM (500 µl) supplemented with 10 % FBS containing 1.0, 5.0, 10, 15 or 20 µM Y-27632 (Sigma Chemical Co.), or 0.4, 1.2, 1.6, 2.4 or 2.8 µM H-1152 (Calbiochem, EMD Chemicals Inc., Darmstadt, Germany) was dispensed in Multidish 24-well plates with either Surface 4 or a non-treated (but gamma irradiated; 25 kGy) polystyrene surface. Another 500 µl of EMEM supplemented with 10% FBS and containing HEK293 cells were added to the wells (2.0×10^4 cells/cm²). The cultures were placed in an IncuCyte™ Plus (Essen Instruments, Michigan, USA) and incubated at 37°C in a humidified atmosphere of 5% CO₂ in air. The IncuCyte™ Plus is an automated imaging platform, configured to fit inside a CO₂ incubator, and designed to provide kinetic, non-invasive live cell imaging by acquiring phase contrast images of the cells at user-defined times and locations within the cultures. The primary metric of the instrument is culture confluence, that is, the fraction of the surface that is covered by cells. The HEK293 cells were incubated for 72 hours without manipulations, and images were collected every two hours at 9 positions in triplicate cultures. Culture confluence was determined using the IncuCyte™ Plus software (v. 3.4.1.25966).

[00246] Increasing concentration of Y-27632 and H-1152 enhances attachment and growth of HEK293 cells on Surface 4 (Figure 32a). The effect of a non-treated cell culture surface and Y-27632 or H-1152 on attachment and growth of HEK293 is shown in (Figure 32b). Growth and attachment of HEK293 cells was slightly enhanced in the presence of 10 µM Y-27632 and 0.6 - 1.2 µM H-1152. However, the enhancement of growth and attachment of HEK293 cells on a non-treated cell culture surface is insignificant in comparison to Surface 4.

Example 21

Treatment with H-1152 Enhances HEK293 Cell Growth and Attachment to Surface Modified Plates

- [00247]** HEK293 cells were maintained in EMEM (Lonza) containing 10% FBS (Lonza). Cells were passaged at 70-80% confluence using Trypsin/EDTA for dissociation, and seeded at $c 2.0 \times 10^4$ cells/cm² in 75-cm² flasks with Nunclon DeltaTM surface (Thermo Fisher Scientific, Roskilde, Denmark).
- [00248]** EMEM (1.0 ml) supplemented with 10 % FBS containing 0.4, 0.8, 1.2, 1.6, 2.0, 2.4 or 2.8 μ M H-1152 was dispensed in Multidish 12-well plates with Surface 4. Another 1.0 ml of EMEM supplemented with 10% FBS and containing HEK293 cells were added to the wells (4.0×10^4 cells/cm²). The cultures were placed in an IncuCyteTM Plus, and incubated at 37°C in a humidified atmosphere of 5% CO₂ in air for 42 hours (images were collected every 6 hours). One ml of culture medium was then removed by pipetting, and 1.0 ml EMEM supplemented with 10% FBS containing 0.2, 0.4, 0.6, 0.8, 1.0, 1.2 and 1.4 μ M H-1152 was added. The cultures were placed in the IncuCyteTM Plus again, and images were collected every hour over the following 25 hours. Images were collected at 9 positions in triplicate cultures, and culture confluence was determined using the IncuCyteTM Plus software. Images from the IncuCyteTM Plus collected at specific positions in HEK293 cell cultures grown in the absence or presence of H-1152 (0.6 μ M) was retrieved and presented as phase-contrast micrographs for the comparison of HEK293 culture morphology at the following time points: start of incubation (0 hours), just before medium change (42 hours), 1 hour after the medium change (43 hours), and, finally, after 52 hours of incubation.
- [00249]** In the absence of H-1152 and in the presence of 0.2 μ M or 0.4 μ M H-1152, the change of 50% of the medium after 42 hours of incubation resulted in a significant reduction in culture confluence (Figure 33a). In the presence of 0.6 μ M, 0.8 μ M or 1.4 μ M H-1152, the effect of changing the medium was minimal. HEK293 cells grown on Surface 4 in the presence of H-1152 covered the solid substrate surfaces more evenly than HEK293 cells grown on Surface 4 in the absence of H-1152 (Figure 33b). In the absence of H-1152, HEK293 cells formed large clusters, whereas, HEK293 cells in the presence of H-1152 formed smaller clusters with lower cell density.

Example 22

Treatment with Y-27632 Enhances HEK293 Cell Growth Over Three Passages on Surface Modified Plates

[00250] EMEM (500 μ l) supplemented with 10 % FBS containing 5.0 μ M Y-27632 was dispensed in wells of Multidish 24-well plates with Surface 4 or Nunclon Delta™ surface. Another 500 μ l of EMEM supplemented with 10% FBS and containing HEK293 cells was added to the wells (2.0×10^4 cells/cm²), and the cultures were incubated at 37°C in a humidified atmosphere of 5% CO₂ in air for 3 days. Cells were passaged by treatment with Trypsin/EDTA (Lonza, Verviers, Belgium) for two minutes at 37°C, and the total cell number was determined using a NucleoCount Cell Counter (Chemometec A/S, Allerød, Denmark). For successive passages, HEK293 cells were seeded at 2.0×10^4 cells/cm². The growth of HEK293 cells on Surface 4 and Nunclon Delta™ surface was enhanced by the presence of 2.5 μ M Y-27632 (Figure 34).

Example 23

Attachment, Cultivation and Maintenance of Human Embryonic Stem Cells Using Surface Modified Plates 4, 18, and 19 that lack Extracellular Matrix Protein/Components and Feeder Cells

[00251] Passage 42 H1 hES cells maintained on 1:30 MATRIGEL coated plasticware in MEF conditioned media supplemented with 8ng/ml of bFGF were lifted by LIBERASE™ enzymatic treatment and plated to surface modified 96 well format plates at a 1 to 2 dilution in MEF conditioned media supplemented with 8ng/ml of bFGF. The cells were plated to modified surfaces 4, 18, or 19, or Primaria™. In order to determine the effect of Rho Kinase inhibition on binding to the modified surface we treated the cells with either 10 μ M of the Rho Kinase inhibitor Y-27632, or 3 or 10 μ M of the Rho Kinase inhibitor H-1152glycyl. Untreated cells served as controls. After 24 hours in culture the wells were aspirated, the cells were dried, and the wells were stained with Crystal violet.

[00252] We observed that after 24 hours in culture, ES cell colonies had attached and spread when treated with Rho Kinase inhibitors on surface modified plates 4 and 19 and the

Primaria™ plate, however the same effect was not observed on surface modified plate 18 (Figure 35).

Example 24

Attachment, Cultivation and Maintenance of Human Embryonic Stem Cells Using Surface Modified Plates 30, 31, 32, 33, and 34 that lack Extracellular Matrix Protein/Components and Feeder Cells

- [00253]** Passage 47 H1 hES cells maintained on 1:30 MATRIGEL coated plasticware in MEF conditioned media supplemented with 8ng/ml of bFGF were lifted by TrypLE™ enzymatic treatment and plated to surface modified 96 well format plates at a 1 to 3 dilution in MEF conditioned media supplemented with 8ng/ml of bFGF. The cells were plated to modified surfaces 30, 31, 32, 33, or 34. In order to determine the effect of Rho Kinase inhibition on binding to the modified surface we treated the cells with 3μM of the Rho Kinase inhibitor H-1152glycyl. Untreated cells served as controls. Additionally, cells were seeded to wells in the surface modified plate that were pre-treated with Matrigel™. 24 hours after plating the media was changed with fresh MEF conditioned media supplemented with 8ng/ml of bFGF, and for cells seeded in the presence of the Rho Kinase inhibitor the media was supplemented with 3μM H-1152glycyl. After 48 hours in culture the wells were aspirated, the cells were dried, and the wells stained with Crystal violet.
- [00254]** We observed that after 48 hours in culture, ES cell colonies had attached and spread when treated with Rho Kinase inhibitors on surface modified plates 33 and 34 (Figure 39 and 40 respectively), however the same effect was not observed on surface modified plates 30, 31 or 32 (Figures 36-40 respectively).

Example 25

Attachment, Cultivation and Maintenance of Human Embryonic Stem Cells Using Surface Modified Plates 22, 23, 24 or 29 that lack Extracellular Matrix Protein/Components and Feeder Cells

[00255] Passage 46 H1 hES cells maintained on 1:30 MATRIGEL coated plasticware in MEF conditioned media supplemented with 8ng/ml of bFGF were lifted by LiberaseTM enzymatic treatment and plated to surface modified 60mm dishes at a 1 to 3 dilution in MEF conditioned media supplemented with 8ng/ml of bFGF. The cells were plated to surface modified plates 3, 4, 22, 23, 24 and 29. In order to determine the effect of Rho Kinase inhibition on binding to the modified surface we treated the cells with 3 μ M of the Rho Kinase inhibitor H-1152glycyl to plate the cells. The media was changed with fresh MEF conditioned media supplemented with 8ng/ml of bFGF and 1 μ M of the Rho Kinase inhibitor H-1152glycyl 24 hours after plating the cells. Cells seeded to modified surface 3, 4 or matrigelTM coated plastic served as controls. The plates were observed by phase microscopy 24 and 48 hours after plating. We observed that after 48 hours in culture, ES cell colonies had not attached to surface modified plates 22, 23, 24 or 29 plated with or without Rho Kinase inhibitor, while cells plated to surface modified plate 3 or 4 in the presence of Rho Kinase inhibitor did attach and spread.

Example 26

Further Surface Characterization of the Surface Modified Plates of the Present Invention

Water Contact Angles

[00256] Surface modified plates 1-4 and 13 were individually packed in plastic bags, sterilized, and stored at room temperature throughout a 40-week test period. Contact angles were first measured one week after surface treatment and sterilization, and then again at the time points given in Figure 41. All contact angle measurements were done as described in Example 17. Measurements on Nunclon DeltaTM and CellBINDTM surfaces was performed under the same experimental conditions as measurements on Surface 1-4 and 13, but the surface treatment and sterilization was done more than 12 weeks before the first measurement (Nunclon Delta^{TM*} was sterilized one week before the first measurement). Figure 41 shows that surface modified plates 1-4 and 13 were of similar hydrophilicity and more hydrophilic (lower water contact angles) than Nunclon DeltaTM

and CellBIND™ surfaces. The hydrophilicity of surface modified plates 1-4 and 13 was stable for at least 41 weeks after surface treatment and sterilization.

[00257] Contact angles were also measured on surface modified plates 5-12, 22-24, 29, 30 and 33, which were packed in plastic bags, sterilized as described in Example 16, and stored at room temperature for 9 weeks (except for surface modified plate 29 which was stored for 28 weeks). Surface modified plates 18, 19, 32 and 34 were in single-microwell format and could, therefore, not be used for measurements of contact angles. Surface modified plates 30 and 33 were in a microwell plate format, and contact angle measurements were performed on the backside of the plate and not inside wells. Contact angles were measured as described in Example 17 (for the highly hydrophilic surface modified plate 29, a smaller drop of 2.5 µl MilliQ water was applied), but triplicate samples were analysed, with 7 drops being applied per sample. Measurements on plates with Costar™, Falcon™, Primaria™ and Nunclon Delta™ surfaces was performed under the same experimental conditions, but the surface treatment and sterilization was done more than 12 weeks before the first measurement. Figure 42 shows that surface modified plates 5-12 were more hydrophilic (lower water contact angles) than Nunclon Delta™, Costar™ and Falcon™ surfaces. The hydrophilicity of surfaces 5-12 was comparable to the hydrophilicity of the Primaria™ surface, and higher than the hydrophilicity of surfaces 1-4 and 13 (shown in Figure 41). The hydrophilicity of surface modified plates 22-24 and 33 was comparable to the hydrophilicity of surfaces 1-4 and 13 (shown in Figure 41), whereas the hydrophilicity of surface 30 was comparable to the hydrophilicity of Nunclon Delta™, Costar™ and Falcon™ surfaces. Surface modified plate 29 was significantly more hydrophilic than the other surfaces analysed.

Negative Charge Density

[00258] The density of negative charges on surface modified plates 5-12 (all 5-cm dish format), 18, 19, 30, 32, 33 and 34 (all microwell format), surface modified plates 22-24 and 29 (all 6-cm dish format), and CellBIND™ surface (3-cm dish format), Primaria™ surface (multidish-6 format) and Nunclon Delta™ surface (3-cm dish format) was determined. Aqueous crystal violet solution (0.015% w/v) in excess was added to each format (0.34

ml/cm² for dish format and 0.13 ml/cm² for microwell format), and was incubated for 60 minutes at room temperature under gentle shaking (50 rpm). In order to remove crystal violet not bound to the surfaces, the dishes were washed three times with 3 ml MilliQ water for the dish formats and three times with 350 μ l MilliQ water for microwell formats, and then dried over night at 60°C. The crystal violet bound to the surface was desorbed by addition of 0.17 ml/cm² of 0.1 M HCl in EtOH solution (99%) and incubating the dishes for 2 minutes at room temperature under gentle shaking (50 rpm). Absorbance of the HCl:EtOH solution with desorbed crystal violet was measured at 590 nm using an EnVision 2100 microplate reader (Perkin Elmer; Waltham, MA, USA). Absorbance values were corrected for background absorbance of HCl:EtOH solution. The negative charge density was measured on three dishes with surface modified plates 5-12, 22-24, 29, CellBIND™, Primaria™ and Nunclon Delta™, and absorbance measurements were performed in triplicate for each dish. For surface modified plates 18, 19, 30, 32, 33 and 34, one sample was tested with triplicate measurements.

- [00259]** The negative charge densities of surface modified plates 5-12 were similar, and these surfaces had significantly lower negative charge densities than CellBIND™ surface and Nunclon Delta™ surface, but significantly higher negative charge densities than the Primaria™ surface (Figure 43). The negative charge densities of surface modified plates 19, 33 and 34 were significantly higher than the negative charge densities of surface modified plates 18, 30 and 32, the latter being the respective non-treated surfaces in the same polymer material. The negative charge densities of surface modified plates 22-24 and 29 were normalized to the negative charge density of the Nunclon Delta™ surface, and Figure 44 shows that surface modified plates 22-24 had higher negative charge densities than the Nunclon Delta™ surface, whereas the negative charge density for surface modified plate 29 was significantly lower than the negative charge density of the Nunclon Delta™ surface (and surface 4).

X-Ray Photoelectron Spectroscopy (XPS)

- [00260]** Surface modified plates 5-12, 18, 19, 22-24, 29, 30, 31-34 were analyzed using XPS as described in Example 17. Surface elemental composition in units of atomic percent is

shown in Table 12. All surfaces contained carbon, oxygen and nitrogen (hydrogen is not detected in XPS), except surface modified plates 31 and 32 (not plasma treated), which did not contain nitrogen. Surface modified plates 5-12 contained less oxygen than surface modified plates 1-4 and 13, but significantly more oxygen than CostarTM, FalconTM and Nunclon DeltaTM surfaces (shown in Table 7). Surface modified plates 5-12, were prepared by microwave plasma treatment while surface modified plates 1-4 and 13 were produced by corona plasma treatment. Surface modified plates 19, 33 and 34, which were prepared by Corona plasma treatment, but injection molded from other polymers than polystyrene (which was used in the preparation of surface modified plates 1-4 and 13), contained oxygen levels comparable to those of surface modified plates 1-4 and 13. Surface modified plates 22-24 contained less oxygen than surface modified plates 1-4 and 13. Surface modified plate 29 contained oxygen at a level comparable to surface modified plates 1-4 and 13. Surface modified plates 5-12, 19, 33 and 34 contained less nitrogen than surface modified plates 1-4 and 13, but more nitrogen than CostarTM, FalconTM and Nunclon DeltaTM surfaces (shown in Table 7). Surface modified plate 29 contained significantly more nitrogen than the other surfaces analysed, including the PrimariaTM surface.

[00261] C1s spectra peaks were curve fit (best chi-squared fit), in order to identify and quantify the bonding environments for carbon in the surface modified plates, by using peak widths and energy locations for species as found in the literature (Table 13). The concentrations are reported in units of atomic percent, which were obtained by multiplying the area percent by the atomic concentration. All plasma-treated surfaces, except surfaces 10, 22-24 and 29, were similar in terms of the carbon bonding environments. The proportion of carbon in C-[O]-C was significantly higher in Surfaces 19, 33 and 34 than in surfaces 5-12, 18, 30 and 32 and surfaces 1-4 and 13 (shown in Table 8). The proportion of carbon in O-[C=O]-O bonding environment was lower in surfaces 5-12, 19, 33 and 34 than in surfaces 1-4 and 13. The proportion of carbon in C*-C-O-C-C* was significantly higher in surfaces 5-9, 11, 12, 19, 33 and 34 than in surfaces 1-4 and 13, but comparable to Nunclon DeltaTM and CellBINDTM surfaces. The proportion of carbon in C-O-C or C-NH₃⁺ bonding environment (same energy location in spectra) was lower in surfaces 5-

12, 19, 33 and 34 than in surfaces 1-4 and 13, but was higher than in Costar™, Falcon™, CellBIND™ and Primaria™ surfaces. The proportion of carbon in C–O–C*=O bonding environment was higher in surfaces 19, 33 and 34 than in surfaces 5-12, and comparable to the level in surfaces 1-4 and 13. The proportion of carbon in C=O bonding environment was higher in surfaces 5-12 than in surfaces 19, 33 and 34, but lower than in surfaces 1-4 and 13. The proportion of carbon in CO₃⁻ bonding environment was higher in surfaces 5-12 than in surfaces 19, 33 and 34, and comparable to the level in surfaces 1-4 and 13. Surfaces 22-24 were similar in terms of carbon bonding environments. The proportion of carbon in C–[O]–C, O–[C=O]–O, C–O–C or C–NH₃⁺, C–O–C*=O and C=O for surfaces 22-24 was significantly lower than for surfaces 1-4 and 13. The proportion of carbon in CO₃⁻ and C*–C–O–C–C* bonding environments was higher for surfaces 22-24 than for surfaces 1-4 and 13. The carbon bonding environment of surface 29 was different from the carbon bonding environment of all other plasma-treated surfaces. The proportion of carbon in C–[O]–C was comparable to surfaces 1-4 and 13. The proportions of carbon in O–[C=O]–O, CO₃⁻ and C*–C–O–C–C* bonding environments were lower for surface 29 than for surfaces 1-4 and 13. The proportions of carbon in C–O–C or C–NH₃⁺, C–O–C*=O and C=O bonding environments were higher for surface 29 than for surfaces 1-4 and 13. The energy loss peak resulted from an aromatic $\Pi \rightarrow \Pi^*$ transition, and is an indicator of surface aromaticity.

[00262] The O1s spectra peaks were almost Gaussian and could not be curve fit. N1s spectra peaks were curve fit (best chi-squared fit), in order to identify and quantify the bonding environments for nitrogen in the surfaces, by using peak widths and energy locations for species as found in the literature (Table 14). The concentrations are reported in units of atomic percent, which were obtained by multiplying the area percent by the atomic concentration. The proportion of nitrogen in –NH₃⁺ bonding environment in all surfaces, except surface 9, was lower than in surfaces 1-4 and 13. Nitrogen in –NH₂ bonding environment in surfaces 5-12, 19, 33 and 34 varied, but was higher than in surfaces 1-4 and 13. Nitrogen in –NO₂ bonding environment in surfaces 5-12, 19, 33 and 34 varied, but was lower than in surfaces 1-4 and 13. Nitrogen in –NO₃ bonding environment in surfaces 5-12, 19, 33 and 34 varied, but was higher than in surfaces 1-4 and 13. The

nitrogen bonding environments of surfaces 22-24 and 29 were different from the other plasma-treated surfaces. The proportion of nitrogen in -NH₂ bonding environment in surfaces 22-24 and 29 varied, but was significantly higher than in surfaces 1-4 and 13. The proportion of nitrogen in -NO₂ bonding environment was lower in surfaces 22-24 and 29 than in surfaces 1-4 and 13. The proportion of nitrogen in O=C-N-C=O bonding environment was comparable in surfaces 22-24 and 29 and surfaces 1-4 and 13.

[00263] Although the various aspects of the invention have been illustrated above by reference to examples and preferred embodiments, it will be appreciated that the scope of the invention is defined not by the foregoing description but by the following claims properly construed under principles of patent law.

TABLES

Table 1: Expression of Pluripotency Markers in Cells of the Human Embryonic Stem Cell Line H1 at Passage 50, Cultured on the Surface Modified Plates of the Present Invention

Culture Condition	Marker									
	CFC1	GATA2	GJA7	NANOG	OCT4	SOX2	SOX7	TERT	TUBB3	ZIC1
Costar	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
1:30 MATRIGEL										
Surface Modified Plate 2	0.3	0.5	0.8	0.8	0.4	0.8	2.1	0.6	3.2	1.5
Gelatin										
Surface Modified Plate 2	1.0	0.4	0.9	0.9	0.7	1.1	1.9	0.7	2.8	1.5
No Coating										
Surface Modified Plate 2	0.3	0.5	0.7	0.7	0.3	0.6	0.8	1.0	3.1	
No Coating										
Surface Modified Plate 3	0.5	0.6	0.7	0.8	0.5	0.8	1.4	0.9	3.0	3.0
Gelatin										
Surface	0.3	0.5	0.7	0.8	0.5	0.6	1.9	1.0	3.9	0.9

Modified Plate 3 No Coating										
Surface Modified Plate 3 No Coating	0.3	0.7	0.8	1.3	0.5	0.8	1.4	1.2		1.0
Surface Modified Plate 4 Gelatin	0.4	0.4	0.7	1.0	0.5	0.9	1.2	1.0	3.2	2.9
Surface Modified Plate 4 No Coating	0.5	0.6	1.1	1.2	0.9	1.4	2.3	1.3	4.1	1.5
Surface Modified Plate 4 No Coating	1.0	0.3	1.8	1.0	0.8	1.3	0.8	0.9	2.1	1.7

Table 2: Expression of Pluripotency Markers in Cells of the Human Embryonic Stem Cell Line H1 at Passage 53 Cultured on the Surface Modified Plates of the Present Invention

Culture Condition	MARKER									
	CFC1	GATA2	GJA7	MIXL1	NANOG	OCT4	SOX2	SOX7	TERT	TUBI
Costar	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
1:30 MATRIGEL										
Surface Modified Plate 2	6.22	33.25	1.42	3.98	0.13	0.46	0.42	2.81	0.50	3.6
Surface Modified Plate 3	15.80	16.78	1.11	20.64	0.75	1.90	1.25	1.89	1.83	1.3
Surface Modified Plate 4	11.41	17.58	8.61	14.06	4.46	20.22	6.39	1.91	14.42	31.5

Table 3: Expression of Markers Characteristic of the Definitive Endoderm Lineage in Cells of the Human Embryonic Stem Cell Line H1 at Passage 51 (p2) and Passage 53 (p4) Cultured on the Surface Modified Plates of the Present Invention, Treated with Activin A

% Expression of the surface marker CXCR4 following differentiation of H1 human ES cells to definitive endoderm

	p2	p4
Surface #4	45.5	74.8

Table 4: Percent confluence (acquisition area occupied by objects) and total human H9 embryonic stem cell colonies greater than 50K sq. microns in the acquisition area after one passage on the Surface Modified Plates of the Present Invention

NUNC MODIFIED SURFACE	RI EXPOSURE	PERCENT ACQUISITION AREA OCCUPIED BY OBJECTS [%]	ACQUISITION AREA OCCUPIED BY OBJECTS [sq. microns]	TOTAL OBJECTS IN ACQUISITION AREA	PERCENT ACQUISITION AREA OCCUPIED BY hES COLONIES > 50K sq. microns [%]	ACQUISITION AREA OCCUPIED BY hES COLONIES >50K sq. microns [sq. microns]	TOTAL hES COLONIES > 50K sq. microns IN ACQUISITION AREA	ACQUISITION AREA [sq. micron]	10X FIELD AREA [sq micron]
2	0	4.4	6.83E+06	942	3.6	5.61E+06	22	1.56E+08	6.02E+05
2	1	0.4	6.89E+05	348	0.0	5.33E+04	1	1.56E+08	6.02E+05
2	4	9.9	1.55E+07	2,433	8.1	1.26E+07	47	1.56E+08	6.02E+05
2	10	79.4	1.24E+08	1,146	79.2	1.24E+08	262	1.56E+08	6.02E+05
3	0	2.2	3.39E+06	1,601	1.2	1.82E+06	10	1.56E+08	6.02E+05
3	1	4.1	6.45E+06	1,347	3.0	4.74E+06	21	1.56E+08	6.02E+05
3	4	37.5	5.85E+07	3,230	33.9	5.29E+07	151	1.56E+08	6.02E+05
3	10	69.4	1.08E+08	1,587	67.8	1.06E+08	270	1.56E+08	6.02E+05
4	0	15.8	2.47E+07	1,131	26.0	4.05E+07	96	1.56E+08	6.02E+05
4	1	6.9	1.07E+07	1,507	5.7	8.96E+06	29	1.56E+08	6.02E+05
4	4	39.1	6.10E+07	2,180	36.8	5.74E+07	149	1.56E+08	6.02E+05
4	10	92.1	1.44E+08	449	91.8	1.43E+08	264	1.56E+08	6.02E+05
13	0	1.4	2.11E+06	254	0.9	1.45E+06	5	1.56E+08	6.02E+05
13	1	0.2	2.97E+05	301	0.0	0.00E+00	0	1.56E+08	6.02E+05
13	4	10.5	1.64E+07	6,200	5.2	8.17E+06	30	1.56E+08	6.02E+05
13	10	69.4	1.08E+08	1,587	67.8	1.06E+08	270	1.56E+08	6.02E+05

μM concentration of Y-27632 for 96 hour
RI exposure: culture

Table 5: Expression of Markers Characteristic of the Definitive Endoderm Lineage in Cells of the Human Embryonic Stem Cell Line H1 at Passage 51 Cultured on the Surface Modified Plates of the Present Invention, Treated with Activin A

% Expression of the surface marker CXCR4 following differentiation of H1 human ES cells to definitive endoderm

	p8	p10-11
Surface #4 (1s)	62.7	55.5
Surface #4 (3s)	68.4	41.4
Surface #3 (5s)	N/A	55.6
Surface #3 (7s)	62.5	52

Table 6: Preparation of the Surface Modified Plates of the Present Invention

Preparation of Surface Modified Plates					
Surface	Polymer	Power (W)	Time (s)	P (mbar)	Gas
Corona Plasma					
1	Polystyrene	2000	5	1E-02	Air
13	Polystyrene	2000	10	1E-02	Air
2	Polystyrene	2000	15	1E-02	Air
3	Polystyrene	2000	30	1E-02	Air
4	Polystyrene	2000	60	1E-02	Air
19	Cyclic olefin copolymer	2000	60	1E-02	Air
33	Polycarbonate/polystyrene	2000	60	1E-02	Air
34	Polycarbonate	2000	60	1E-02	Air
Microwave Plasma					
5	Polystyrene	600	6	0.3-0.4	Air
6	Polystyrene	600	12	0.3-0.4	Air
7	Polystyrene	600	18	0.3-0.4	Air
8	Polystyrene	600	24	0.3-0.4	Air
9	Polystyrene	600	6	0.3-0.4	Oxygen
10	Polystyrene	600	12	0.3-0.4	Oxygen
11	Polystyrene	600	18	0.3-0.4	Oxygen
12	Polystyrene	600	24	0.3-0.4	Oxygen
14*	Polystyrene	500	60	0.4-0.5	Air
15	Polystyrene	500	60	0.4-0.5	Air

* Not sterilized by gamma irradiation

Table 7: Surface Elemental Composition of Surface Modified Plates as Determined by XPS

Surface Elemental Composition of Surface Modified Plates as Determined by XPS Measurements on two samples and mean $\pm$ standard deviation (SD) is given in units of atomic percent									
Surface	% Carbon			% Oxygen			% Nitrogen		
	1	2	Mean $\pm$ SD	1	2	Mean $\pm$ SD	1	2	Mean $\pm$ SD
Surface 1	74.2	76.1	75.1 $\pm$ 0.3	24.6	22.6	23.6 $\pm$ 1.4	1.3	1.3	1.3 $\pm$ 0.0
Surface 2	69.0	72.0	70.5 $\pm$ 2.1	29.3	26.5	27.9 $\pm$ 2.0	1.8	1.6	1.7 $\pm$ 0.1
Surface 3	68.5	70.2	69.4 $\pm$ 1.2	29.3	28.0	28.7 $\pm$ 0.9	2.2	1.8	2.0 $\pm$ 0.3
Surface 4	69.2	70.5	69.9 $\pm$ 0.9	28.8	27.5	28.2 $\pm$ 0.9	2.1	2.0	2.1 $\pm$ 0.1
Surface 13 *	69.9	73.5	71.7 $\pm$ 2.5	27.9	24.9	26.4 $\pm$ 2.1	1.9	1.6	1.8 $\pm$ 0.2
Surface 14	82.8	82.5	82.7 $\pm$ 0.2	15.6	15.6	15.6 $\pm$ 0.0	1.6	1.8	1.7 $\pm$ 0.1
Surface 15	78.6	78.7	78.7 $\pm$ 0.1	20.0	20.0	20.0 $\pm$ 0.0	1.4	1.3	1.4 $\pm$ 0.1
Nuncclon Delta TM	84.8	84.6	84.7 $\pm$ 0.1	14.7	14.7	14.7 $\pm$ 0.0	0.5	0.6	0.6 $\pm$ 0.1
CellBIND TM	72.3	72.2	72.2 $\pm$ 0.1	26.7	26.9	26.8 $\pm$ 0.1	1.0	0.9	1.0 $\pm$ 0.1
Falcon TM	95.2	94.7	94.9 $\pm$ 0.4	4.7	5.1	4.9 $\pm$ 0.3	0.1	0.3	0.2 $\pm$ 0.1
Costar TM	85.8	85.4	85.6 $\pm$ 0.3	13.8	14.4	14.1 $\pm$ 0.4	0.4	0.2	0.3 $\pm$ 0.1
Primaria TM	77.7	76.5	77.0 $\pm$ 0.8	12.7	12.9	12.8 $\pm$ 0.1	9.7	10.6	10.2 $\pm$ 0.6

* Other elements were detected at a concentration of 0.4%

Table 8: Carbon Bonding Environment by C1s Spectra Curve Fitting

Carbon Bonding Environment by C1s Spectra Curve Fitting Atomic percent of each functional group is given as mean $\pm$ standard deviation (n = 2)									
Surface	Functional groups and C1s binding energies in eV								
	C-C (284.6 eV)	C*-C- O-C- C* (285.2 eV)	C-O- C, C- NH ₃ ⁺ (286.1 eV)	C- [O]-C (287.0 eV)	C=O (287.9 eV)	C-O- C*=O (288.9 eV)	CO ₃ ⁻ (289.8 eV)	O- [C=O]- O (291.0 eV)	Energy loss peak (292 eV)
Surface 1	34.5 $\pm$ 0.6	11.4 $\pm$ 0.7	14.1 $\pm$ 0.7	4.2 $\pm$ 0.5	4.5 $\pm$ 0.1	1.7 $\pm$ 0.1	1.7 $\pm$ 0.1	1.9 $\pm$ 0.1	0.55 $\pm$ 0.1
Surface 2	31.7 $\pm$ 1.3	7.9 $\pm$ 1.5	13.4 $\pm$ 0.8	5.4 $\pm$ 0.3	4.3 $\pm$ 0.6	2.2 $\pm$ 0.1	2.7 $\pm$ 0.4	2.5 $\pm$ 0.4	0.45 $\pm$ 0.1
Surface 3	31.5 $\pm$ 1.5	7.4 $\pm$ 2.0	12.7 $\pm$ 2.1	4.8 $\pm$ 0.1	4.8 $\pm$ 0.1	2.0 $\pm$ 0.1	2.8 $\pm$ 0.2	2.7 $\pm$ 0.0	0.35 $\pm$ 0.2
Surface 4	31.6 $\pm$ 0.5	6.5 $\pm$ 2.7	14.1 $\pm$ 1.3	4.1 $\pm$ 0.0	4.7 $\pm$ 0.5	3.0 $\pm$ 0.5	2.6 $\pm$ 0.1	2.8 $\pm$ 0.3	0.40 $\pm$ 0.3
Surface 13	33.6 $\pm$ 0.6	6.7 $\pm$ 3.2	13.2 $\pm$ 0.5	4.9 $\pm$ 0.4	4.9 $\pm$ 0.3	2.2 $\pm$ 0.2	3.0 $\pm$ 0.1	2.7 $\pm$ 0.4	0.45 $\pm$ 0.2
Surface 14	49.7 $\pm$ 2.6	17.2 $\pm$ 3.5	8.1 $\pm$ 1.7	3.2 $\pm$ 0.3	2.2 $\pm$ 0.6	1.0 $\pm$ 0.1	0.8 $\pm$ 0.1	0.2 $\pm$ 0.0	0.15 $\pm$ 0.1
Surface 15	46.7 $\pm$ 0.1	20.0 $\pm$ 0.0	11.2 $\pm$ 4.0	4.0 $\pm$ 0.9	2.9*	1.9 $\pm$ 0.7	1.5 $\pm$ 1.0	0.3*	0.10*
Nunclon Delta™	36.2 $\pm$ 1.3	28.2 $\pm$ 1.3	7.9 $\pm$ 0.5	3.9 $\pm$ 0.6	3.5 $\pm$ 0.1	0.8 $\pm$ 0.0	1.0 $\pm$ 0.0	1.9 $\pm$ 0.1	1.1 $\pm$ 0.1
CellBIND™	27.6 $\pm$ 1.1	19.2 $\pm$ 0.6	5.7 $\pm$ 0.0	6.5 $\pm$ 2.0	5.7 $\pm$ 0.0	1.3 $\pm$ 1.0	3.0 $\pm$ 0.1	1.6 $\pm$ 2.0	0.60 $\pm$ 0.0
Falcon™	76.2 $\pm$ 3.2	12.0 $\pm$ 3.5	5.7 $\pm$ 1.0	0.1 $\pm$ 0.2	0.0 $\pm$ 0.0	0.0 $\pm$ 0.0	0.0 $\pm$ 0.1	0.6 $\pm$ 0.1	0.30 $\pm$ 0.4
Costar™	60.8 $\pm$ 6.0	12.5 $\pm$ 5.4	7.0 $\pm$ 2.0	2.1 $\pm$ 0.4	0.5 $\pm$ 0.3	0.2 $\pm$ 0.0	1.0 $\pm$ 0.2	0.8 $\pm$ 0.0	0.60 $\pm$ 0.1
Primaria™	50.1 $\pm$ 1.8	11.1 $\pm$ 0.2	1.9 $\pm$ 2.3	4.8 $\pm$ 0.2	3.1 $\pm$ 0.1	3.0 $\pm$ 0.1	0.5 $\pm$ 0.1	0.5 $\pm$ 0.0	0.30 $\pm$ 0.0

* The functional group was identified in only one sample.

Table 9: Nitrogen Bonding Environment by N1s Spectra Curve Fitting

Nitrogen Bonding Environment by N1s Spectra Curve Fitting Atomic percent of each functional group is given as mean $\pm$ standard deviation (n = 2)					
Surface	Functional groups and N1s binding energies in eV				
	-NH ₂ (398.8 eV)	O=C-N- C=O (400.8 eV)	-NH ₃ ⁺ (401.8 eV)	-NO ₂ (406.5 eV)	-NO ₃ (407.0 eV)
Surface 1-4 and 13 *	0.0	46.9 $\pm$ 2.2	43.0 $\pm$ 0.4	10.2 $\pm$ 1.8	0.0
Surface 14	4.0 $\pm$ 1.4	75.0 $\pm$ 1.4	21.0 $\pm$ 2.8	0.0	0.0
Surface 15	6.0 $\pm$ 1.4	76.5 $\pm$ 3.5	14.0 $\pm$ 7.1	3.0**	2.0 $\pm$ 0.0
Primaria TM	11.0 $\pm$ 0.0	81.0 $\pm$ 0.0	4.0 $\pm$ 0.0	0.0	4.0 $\pm$ 0.0

* N1s spectra were indistinguishable for Surface modified plates 1-4 and 13, and data resulting from curve fit of two representative N1s spectra is given.

** The functional group was identified in only one sample.

Table 10: Surface Roughness of the Surface Modified Plates of the Present Invention as Determined by AFM

Surface Roughness of the Surface Modified Plates of the Present Invention as Determined by AFM				
Surface	10 μm x 10 μm scan		500 nm x 500 nm scan	
	R_a (nm)	R_{max} (nm)	R_a (nm)	R_{max} (nm)
Surface modified plate 1	2.40	20.97	0.13	2.35
Surface modified plate 2	2.27	17.38	0.42	4.40
Surface modified plate 3	2.49	22.44	0.17	2.00
Surface modified plate 4	1.77	13.83	0.32	5.20
Surface modified plate 13	2.14	17.99	0.18	2.30
Nunclon Delta TM	1.75	15.22	0.17	1.67
Cellbind TM	1.63	13.04	0.17	2.10

Table 11: Summary of the Results of the XPS Analysis of Surface Elemental Composition and Human Embryonic Stem Cell Attachment and Colony Formation Experiments on the Surface Modified Plates of the Present Invention

		Polymer Material	Surface Treatment	hESC Attachment and Colony Formation (visual inspection)			hESC Attachment and Colony Formation (automated microscopy, % confluence)		% Nitrogen		% Oxygen		Sum of % Nitrogen and % Oxygen	Water contact angle (degrees)	
				No RI	Y-27632	H-1152	Y-27632	H-1152	Mean	SD	Mean	SD		Mean	SD
Surface	1	PS	CP	-	++	ND	31.4	ND	1.3	0.0	23.6	1.4	24.9	20.7	0.3
	13	PS	CP	+	+++	+++	82.7	ND	1.8	0.2	26.4	2.1	28.2	18.8	0.5
	2	PS	CP	+	+++	+++	48.6	ND	1.7	0.1	27.9	2.0	29.6	14.3	0.4
	3	PS	CP	+	+++	+++	67.5	ND	2.0	0.3	28.7	0.9	30.7	18.4	0.8
	4	PS	CP	+	+++	+++	75.3	ND	2.1	0.1	28.2	0.9	30.2	17.4	2.0
	5	PS	MP	-	+	ND	2.9	ND	1.3	0.2	19.6	0.2	20.9	38.7	1.1
	6	PS	MP	-	+	ND	6.6	ND	1.3	0.2	19.1	0.5	20.4	39.4	1.5
	7	PS	MP	-	+	ND	4.3	ND	1.3	0.1	20.1	1.9	21.4	38.1	1.3
	8	PS	MP	-	+	ND	5.7	ND	1.5	0.1	20.0	1.0	21.5	39.0	1.5
	9	PS	MP	-	+	ND	18.3	ND	1.0	0.1	19.3	0.8	20.3	42.0	0.8
	10	PS	MP	-	+	ND	11.5	ND	0.8	0.2	19.1	0.2	19.9	41.0	1.1
	11	PS	MP	-	+	ND	10.7	ND	0.9	0.1	20.3	0.1	21.2	40.0	0.7
	12	PS	MP	-	+	ND	19.3	ND	0.9	0.1	21.2	0.7	22.1	40.0	0.6
	14	PS	MP	-	+	ND	ND	ND	1.7	0.1	15.6	0.0	17.3	ND	
	15	PS	MP	-	+	ND	ND	ND	1.4	0.1	20.0	0.0	21.4	ND	
	18	COC	None	-	-	-	ND	ND	0.0	0.0	2.3	0.1	2.3	ND	
	19	COC	CP	-	++	++	ND	ND	1.3	0.1	25.4	1.0	26.7	ND	
	22	PS		-	ND	-	ND	ND	1.6	****	15.9	****	17.5	21.4	0.7
	23	PS		-	ND	-	ND	ND	1.1	0.1	17.1	1.2	18.2	30.0	2.1
	24	PS		-	ND	-	ND	ND	1.3	0.4	16.7	2.7	18.0	27.7	3.3
	29	PS		-	ND	-	ND	ND	17.9	2.1	28.7	0.8	46.6	7.9	0.6
	30	PS/PC	None	-	ND	-	ND	ND	0.2	0.1	3.9	0.6	4.1	70.2	0.5
	33	PS/PC	CP	-	ND	++	ND	ND	1.0	0.1	25.0	0.2	26.0	21.8	0.5
	31	PC	None	-	ND	-	ND	ND	0.0	0.0	16.7	0.4	16.7	ND	
	32	PC	None	-	ND	-	ND	ND	0.0	0.0	17.0	0.4	17.0	ND	
	34	PC	CP	-	ND	++	ND	ND	1.1	0.1	23.9	0.6	25.0	ND	
	CellBIND™	PS		+++	++	++	ND	ND	1.0	0.1	26.8	0.1	27.8	44.3	1.3
	Nunclon Delta™	PS		-	-	-	ND	ND	0.6	0.1	14.7	0.0	15.3	63.1	2.0
	Falcon™	PS		-	-	-	ND	ND	0.2	0.1	4.9	0.3	5.1	75.1	2.9
	Costar™	PS		-	-	-	ND	ND	0.3	0.1	14.1	0.4	14.4	61.4	2.4
	Primaria™	PS		****	+++	+++	ND	ND	10.2	0.6	12.8	0.1	23.0	39.5	2.0

"-" means formation of less than 15 colonies per 10 cm²

"+", "++", and "+++" means some (15 or more colonies per 10 cm²), more, and most human ES cell attachment and colony formation, respectively

"RI" means Rho kinase inhibitor; "ND" means experiment not done

"PS" means polystyrene; "PC" means polycarbonate; "PS/PC" means blend of polystyrene and polycarbonate; "COC" means cyclic olefin copolymer; "CP" means corona plasma; "MP" means microwave plasma

* Human ES cells attach and grow into colonies that can be passaged about 3 times (then growth rate declines spontaneously)

** Human ES cells attach and grow into colonies that spontaneously differentiate before the first passaging

*** Human ES cells attach and grow into colonies (passaging not tested)

**** Only one sample available for analysis

Table 12: Surface Elemental Composition as Determined by XPS

Surface Elemental Composition as Determined by XPS Measurements on two samples (except Surface 22) and mean $\pm$ standard deviation (SD) is given in units of atomic percent									
Surface	% Carbon			% Oxygen			% Nitrogen		
	1	2	Mean $\pm$ SD	1	2	Mean $\pm$ SD	1	2	Mean $\pm$ SD
Surface 5	79.1	79.1	79.1 $\pm$ 0.0	19.5	19.8	19.6 $\pm$ 0.2	1.4	1.1	1.3 $\pm$ 0.2
Surface 6	79.4	79.2	79.3 $\pm$ 0.1	19.5	18.8	19.1 $\pm$ 0.5	1.1	1.4	1.3 $\pm$ 0.2
Surface 7	76.2	80.0	78.1 $\pm$ 2.7	21.5	18.8	20.1 $\pm$ 1.9	1.3	1.2	1.3 $\pm$ 0.1
Surface 8	77.8	78.7	78.2 $\pm$ 0.6	20.8	19.3	20.0 $\pm$ 1.0	1.4	1.5	1.5 $\pm$ 0.1
Surface 9	79.2	80.3	79.7 $\pm$ 0.8	19.9	18.7	19.3 $\pm$ 0.8	0.9	1.0	1.0 $\pm$ 0.1
Surface 10	80.4	79.2	79.8 $\pm$ 0.8	19.0	19.3	19.1 $\pm$ 0.2	0.6	0.9	0.8 $\pm$ 0.2
Surface 11	78.7	78.6	78.6 $\pm$ 0.1	20.4	20.3	20.3 $\pm$ 0.1	0.9	0.8	0.9 $\pm$ 0.1
Surface 12	77.2	78.5	77.8 $\pm$ 0.9	21.8	20.7	21.2 $\pm$ 0.7	1.0	0.8	0.9 $\pm$ 0.1
Surface 18*	97.6	97.8	97.7 $\pm$ 0.1	2.4	2.2	2.3 $\pm$ 0.1	0.0	0.0	0.0 $\pm$ 0.0
Surface 19	74.1	72.5	73.3 $\pm$ 1.1	24.7	26.2	25.4 $\pm$ 1.0	1.2	1.3	1.3 $\pm$ 0.1
Surface 22	82.5			15.9			1.6		
Surface 23**	82.2	79.1	80.7 $\pm$ 2.2	16.2	17.9	17.1 $\pm$ 1.2	1.0	1.1	1.1 $\pm$ 0.1
Surface 24**	84.0	79.6	81.8 $\pm$ 3.1	14.8	18.6	16.7 $\pm$ 2.7	1.0	1.6	1.3 $\pm$ 0.4
Surface 29	52.5	54.5	53.5 $\pm$ 1.4	28.1	29.2	28.7 $\pm$ 0.8	19.4	16.4	17.9 $\pm$ 2.1
Surface 30*	96.3	95.5	95.9 $\pm$ 0.6	3.5	4.4	3.9 $\pm$ 0.6	0.2	0.1	0.2 $\pm$ 0.1
Surface 31***	83.0	81.3	82.2 $\pm$ 1.2	16.4	17.0	16.7 $\pm$ 0.4	0.0	0.0	0.0 $\pm$ 0.0
Surface 32*	83.3	82.7	83.0 $\pm$ 0.4	16.7	17.3	17.0 $\pm$ 0.4	0.0	0.0	0.0 $\pm$ 0.0
Surface 33	74.2	73.7	73.9 $\pm$ 0.3	24.9	25.2	25.0 $\pm$ 0.2	0.9	1.0	1.0 $\pm$ 0.1
Surface 34	74.7	75.5	75.1 $\pm$ 0.6	24.3	23.5	23.9 $\pm$ 0.6	1.1	1.0	1.1 $\pm$ 0.1

* Not plasma treated.

** Other elements were detected at a concentration of 0.2-2.0%.

Table 13: Carbon Bonding Environment by C1s Spectra Curve Fitting

Carbon Bonding Environment by C1s Spectra Curve Fitting Atomic percent of each functional group is given based on one measurement on Surfaces 5-12 and 22, and as mean $\pm$ standard deviation for the other surfaces (n = 2)									
Surface	Functional groups and C1s binding energies (eV)								
	C-C (284.6 eV)	C*-C- O-C- C* (285.2 eV)	C-O-C, C- NH ₃ ⁺ (286.1 eV)	C-[O]- C (287.0 eV)	C=O (287.9 eV)	C-O- C*=O (288.9 eV)	CO ₃ ⁻ (289.8 eV)	O- [C=O]- O (291.0 eV)	Energy loss peak (292 eV)
Surface 5	38.0	22.1	8.2	4.6	0.6	1.4	2.8	0.8	0.0
Surface 6	34.3	26.0	10.6	5.2	1.1	1.3	1.0	0.1	0.0
Surface 7	31.2	23.7	9.6	5.7	0.8	1.4	2.7	0.5	0.5
Surface 8	31.7	25.2	9.6	5.0	0.7	1.6	2.8	0.7	0.5
Surface 9	37.3	22.6	8.4	4.5	0.6	1.2	3.2	0.8	0.6
Surface 10	51.5	9.6	11.3	4.0	0.0	0.8	1.6	0.0	1.6
Surface 11	34.7	23.0	8.5	4.7	2.3	0.4	1.1	0.6	0.6
Surface 12	36.3	21.0	8.1	4.8	1.2	1.2	3.4	0.7	0.5
Surface 18*	86.4 $\pm$ 1.9	0.0	9.8 $\pm$ 1.4	0.0	0.0	1.5 $\pm$ 0.7	0.0	0.0	0.0
Surface 19	31.5 $\pm$ 1.5	18.7 $\pm$ 0.3	11 $\pm$ 0.8	10.3 $\pm$ 0.1	0.0	1.8 $\pm$ 0.5	0.0	0.0	0.0
Surface 22	61.5	10.4	4.9	0.0	1.2	0.9	2.3	1.5	0.0
Surface 23	62.5 $\pm$ 4.1	9.0 $\pm$ 0.7	4.2 $\pm$ 0.3	0.0	1.5 $\pm$ 0.6	0.8 $\pm$ 0.1	1.9 $\pm$ 0.0	0.9 $\pm$ 0.5	0.0
Surface 24	66.2 $\pm$ 6.1	8.8 $\pm$ 0.4	2.4 $\pm$ 0.9	0.0	1.0 $\pm$ 0.6	1.2 $\pm$ 0.6	1.3 $\pm$ 0.6	1.1 $\pm$ 0.1	0.0
Surface 29	17.8 $\pm$ 4.9	0.0	18.9 $\pm$ 1.3	5.4 $\pm$ 0.9	7.4 $\pm$ 5.0	4.2 $\pm$ 0.6	0.0	0.0	0.0
Surface 30*	84.3 $\pm$ 0.5	0.0	5.7 $\pm$ 0.1	1.9 $\pm$ 0.0	0.0	0.0	0.0	0.0	3.9 $\pm$ 0.1
Surface 31*	55.3 $\pm$ 0.6	9.3 $\pm$ 0.3	9.0 $\pm$ 0.1	3.5 $\pm$ 0.2	0.0	0.0	0.0	0.0	2.4 $\pm$ 0.1
Surface 32*	51.5 $\pm$ 8.5	11.2 $\pm$ 2.8	10.7 $\pm$ 3.5	3.3 $\pm$ 1.1	0.0	0.0	0.0	3.3 $\pm$ 0.0	2.9 $\pm$ 0.6
Surface 33	27.7 $\pm$ 1.7	19.9 $\pm$ 0.9	11.1 $\pm$ 0.0	11.1 $\pm$ 0.0	0.0	4.1 $\pm$ 0.4	0.0	0.0	0.0
Surface 34	29.2 $\pm$ 0.2	21.0 $\pm$ 0.1	10.9 $\pm$ 0.6	10.1 $\pm$ 0.5	0.0	3.7 $\pm$ 0.1	0.0	0.0	0.0

* Not plasma treated.

Table 14: Nitrogen Bonding Environment by N1s Spectra Curve Fitting

Nitrogen Bonding Environment by N1s Spectra Curve Fitting					
Atomic percent of each functional group is given based on one measurement on Surfaces 5-12 and 22, and as mean $\pm$ standard deviation for the other surfaces (n = 2)					
Surface	Functional groups and N1s binding energies in eV				
	-NH ₂ (398.8 eV)	O=C-N-C=O (400.8 eV)	-NH ₃ ⁺ (401.8 eV)	-NO ₂ (406.5 eV)	-NO ₃ (407.0 eV)
Surface 5	3.0	50.0	36.0	2.0	9.0
Surface 6	46.0	26.0	11.0	5.0	12.0
Surface 7	25.0	47.0	22.0	2.0	4.0
Surface 8	13.0	56.0	26.0	1.0	4.0
Surface 9	2.0	44.0	45.0	4.0	5.0
Surface 10	8.0	71.0	17.0	2.0	2.0
Surface 11	13.0	37.0	35.0	4.0	11.0
Surface 12	6.0	52.0	31.0	2.0	9.0
Surface 18*	ND**	ND	ND	ND	ND
Surface 19	19.0 $\pm$ 8.4	51.5 $\pm$ 6.3	24.0 $\pm$ 2.8	1.5 $\pm$ 0.7	4.0 $\pm$ 0.0
Surface 22	22.0	24.0	54.0	0.0	0.0
Surface 23	26.0 $\pm$ 1.4	51.0 $\pm$ 4.2	23.0 $\pm$ 5.7	0.0	0.0
Surface 24	23.0 $\pm$ 17.0	47.0 $\pm$ 5.7	30.0 $\pm$ 11.3	0.0	0.0
Surface 29	52.0 $\pm$ 9.9	35.0 $\pm$ 15.6	6.0 $\pm$ 2.8	3.5 $\pm$ 2.1	3.0 $\pm$ 1.4
Surface 30*	ND	ND	ND	ND	ND
Surface 31*	ND	ND	ND	ND	ND
Surface 32*	ND	ND	ND	ND	ND
Surface 33	7.5 $\pm$ 0.7	53.5 $\pm$ 2.1	29.5 $\pm$ 0.7	5.0 $\pm$ 0.0	4.5 $\pm$ 2.1
Surface 34	11.5 $\pm$ 2.1	55.5 $\pm$ 6.4	28.0 $\pm$ 7.1	4.0 $\pm$ 1.4	1.0 $\pm$ 0.0

* Not plasma treated.

** ND: analyzed, but not detected.

[00264] Further embodiments include:

1. A method to enhance the attachment of cells to a surface containing from at least about 0.5% N, a sum of O and N of greater than or equal to 17.2% and a contact angle of at least about 13.9 degrees, lacking a feeder cell layer and lacking an adlayer, comprising the steps of:

- a. Obtaining a suspension of the cells,
 - b. Treating the suspension of cells with at least one compound selected from the group consisting of: a compound capable of inhibiting Rho kinase activity, and a compound capable of inhibiting Rho activity, and
 - c. Adding the suspension of cells to the surface and allowing the cells to attach.
2. The method of embodiment 1, wherein the sum of O and N is greater than or equal to 19.5%.
3. The method of embodiment 1, wherein the surface has an adlayer.
4. The method of embodiment 1, wherein the cells are maintained in culture after the cells attach to the surface.
5. The method of embodiment 4, wherein at least one compound is removed after the cells attach to the surface.
6. The method of embodiment 1, wherein the cells are detached from the surface by removing at least one compound.
7. The method of embodiment 1, wherein the suspension of cells is a suspension of clusters of cells.
8. The method of embodiment 1, wherein the suspension of cells is a suspension of single cells.
9. The method of embodiment 1, wherein the surface is part of a vessel or matrix.
10. A method to enhance the attachment of cells to a surface containing from at least about 0.9% N, a sum of O and N of greater than or equal to 22.3% and a contact angle of at least about 13.9 degrees, lacking a feeder cell layer and lacking an adlayer, comprising the steps of:

- a. Obtaining a suspension of the cells, and
 - b. Adding the suspension of cells to the surface and allowing the cells to attach.
- 11. The method of embodiment 10, wherein the surface has an adlayer.
 - 12. The method of embodiment 10, wherein the cells are maintained in culture after the cells attach to the surface.
 - 13. The method of embodiment 10, wherein the suspension of cells is a suspension of clusters of cells.
 - 14. The method of embodiment 10, wherein the suspension of cells is a suspension of single cells.
 - 15. The method of embodiment 10, wherein the surface is part of a vessel or matrix.
 - 16. A surface that is part of a vessel or matrix intended for use in cell culture or analysis, containing from at least about 0.9% N, a sum of O and N of greater than or equal to 22.3% and a contact angle of at least about 13.9 degrees, lacking a feeder cell layer and lacking an adlayer, wherein the surface allows the attachment and cultivation of cells.
 - 17. The method of embodiment 16, wherein the surface has an adlayer.
 - 18. The surface of embodiment 16, wherein the cells are maintained in culture after the cells attach to the surface.
 - 19. A composition comprising:
 - a. A surface that is part of a vessel or matrix intended for use in cell culture or analysis, containing from at least about 0.5% N, a sum of O and N of greater than or equal to 17.2% and a contact angle of at least about 13.9 degrees, lacking a feeder cell layer and lacking an adlayer, and

- b. At least one compound selected from the group consisting of: a compound capable of inhibiting Rho kinase activity, and a compound capable of inhibiting Rho activity.
- 20. The composition of embodiment 19, wherein the sum of O and N is greater than or equal to 19.5%.
- 21. The method of embodiment 19, wherein the surface has an adlayer.

WHAT IS CLAIMED IS:

1. A method to attach pluripotent stem cells to a corona plasma treated polystyrene surface containing at least 1.6% N, a sum of O and N of greater than or equal to 26.5% and having a contact angle of at least 14.3 degrees, lacking a feeder cell layer and lacking an adlayer, comprising the steps of:
 - a. obtaining a suspension of the pluripotent stem cells, and
 - b. adding the suspension of pluripotent stem cells to the surface and allowing the pluripotent stem cells to attach.
2. The method of claim 1, wherein the surface has one of the following features:
 - i. contains at least 1.7% N, has a sum of O and N of at least 29.6% and has a contact angle of at least 14.3 degrees;
 - ii. contains at least 2.0% N, has a sum of O and N of at least 30.7% and has a contact angle of at least 18.4 degrees;
 - iii. contains at least 2.1% N, has a sum of O and N of at least 30.2% and has a contact angle of at least 17.4 degrees;
 - iv. contains at least 1.8% N, has a sum of O and N of at least 28.2% and has a contact angle of at least 18.8 degrees;
 - v. contains from 1.6% N to 1.8% N, has a sum of O and N of at least 29.6% and has a contact angle of at least 14.3 degrees;
 - vi. contains from 1.8% to 2.2% N, has a sum of O and N of at least 30.7% and has a contact angle of at least 18.4 degrees;
 - vii. contains from 2.0% to 2.1% N, has a sum of O and N of at least 30.2% and has a contact angle of at least 17.4 degrees; or
 - viii. contains from 1.6% to 1.8% N, has a sum of O and N of at least 28.2% and has a contact angle of at least 18.8 degrees.

3. The method of claim 1 or claim 2, wherein the corona plasma treated polystyrene surface contains at least 1.7% N, has a sum of O and N of at least 29.6% and has a contact angle of at least 14.3 degrees.
4. The method of claim 1 or claim 2, wherein the corona plasma treated polystyrene surface contains at least 2.0% N, has a sum of O and N of at least 30.7% and has a contact angle of at least 18.4 degrees.
5. The method of claim 1 or claim 2, wherein the corona plasma treated polystyrene surface contains at least 2.1% N, has a sum of O and N of at least 30.2% and has a contact angle of at least 17.4 degrees.
6. The method of claim 1 or claim 2, wherein the corona plasma treated polystyrene surface contains at least 1.8% N, has a sum of O and N of at least 28.2% and has a contact angle of at least 18.8 degrees.
7. The method of claim 1 or claim 2, wherein the corona plasma treated polystyrene surface contains from 1.6% N to 1.8% N, has a sum of O and N of at least 29.6% and has a contact angle of at least 14.3 degrees.
8. The method of claim 1 or claim 2, wherein the corona plasma treated polystyrene surface contains from 1.8% to 2.2% N, has a sum of O and N of at least 30.7% and has a contact angle of at least 18.4 degrees.
9. The method of claim 1 or claim 2, wherein the corona plasma treated polystyrene surface contains from 2.0% to 2.1% N, has a sum of O and N of at least 30.2% and has a contact angle of at least 17.4 degrees.
10. The method of claim 1 or claim 2, wherein the corona plasma treated polystyrene surface contains from 1.6% to 1.8% N, has a sum of O and N of at least 28.2% and has a contact angle of at least 18.8 degrees.
11. The method of any one of claims 1 to 10, wherein the cells are maintained in culture after the cells attach to the surface.


12. The method of any one of claims 1 to 11, wherein the suspension of pluripotent stem cells is a suspension of clusters of pluripotent stem cells.
13. The method of any one of claims 1 to 11, wherein the suspension of pluripotent stem cells is a suspension of single pluripotent stem cells.
14. The method of any one of claims 1 to 13, wherein the pluripotent stem cells are human pluripotent stem cells.
15. The method of any one of claims 1 to 13, wherein the pluripotent stem cells are human embryonic stem cells.
16. The method of any one of claims 1 to 15, further comprising treating the suspension with a compound capable of inhibiting Rho kinase activity prior to adding the suspension of cells to the surface.
17. The method of claim 16, wherein the compound capable of inhibiting Rho kinase activity is selected from the group consisting of: Y-27632, Fasudil, and Hydroxyfasudil.
18. The method of any one of claims 1 to 16, further comprising treating the suspension of cells with a compound capable of inhibiting Rho activity prior to adding the suspension of cells to the surface.
19. The method of claim 18, wherein the compound capable of inhibiting Rho activity is a Rho GTPase inhibitor or exoenzyme C3 Transferase.
20. The method of any one of claims 1 to 10, wherein the surface is part of a vessel or matrix.
21. A corona plasma treated polystyrene surface that is part of a vessel or matrix when used in cell culture or analysis, lacking a feeder cell layer and lacking an adlayer, wherein the surface allows the attachment and cultivation of pluripotent stem cells, and wherein the surface contains at least 1.6% N, has a sum of O and N of greater than or equal to 26.5% and has a contact angle of at least 14.3 degrees.
22. The surface of claim 21, wherein the surface has one of the following features:

- a. contains at least 1.7% N, has a sum of O and N of at least 29.6% and has a contact angle of at least 14.3 degrees;
 - b. contains at least 2.0% N, has a sum of O and N of at least 30.7% and has a contact angle of at least 18.4 degrees;
 - c. contains at least 2.1% N, has a sum of O and N of at least 30.2% and has a contact angle of at least 17.4 degrees;
 - d. contains at least 1.8% N, has a sum of O and N of at least 28.2% and has a contact angle of at least 18.8 degrees;
 - e. contains from 1.6% N to 1.8% N, has a sum of O and N of at least 29.6% and has a contact angle of at 14.3 degrees;
 - f. contains from 1.8% to 2.2% N, has a sum of O and N of at least 30.7% and has a contact angle of at least 18.4 degrees;
 - g. contains from 2.0% to 2.1% N, has a sum of O and N of at least 30.2% and has a contact angle of at least 17.4 degrees; or
 - h. contains from 1.6% to 1.8% N, has a sum of O and N of at least 28.2% and has a contact angle of at least 18.8 degrees.
23. The surface of claim 21 or claim 22, wherein the pluripotent stem cells are human pluripotent stem cells.
24. The surface of any one of claims 21 to 23, wherein the surface contains at least 1.7% N, has a sum of O and N of at least 29.6% and has a contact angle of at least 14.3 degrees.
25. The surface of any one of claims 21 to 23, wherein the surface contains at least 2.0% N, has a sum of O and N of at least 30.7% and has a contact angle of at least 18.4 degrees.
26. The surface of any one of claims 21 to 23, wherein the surface contains at least 2.1% N, has a sum of O and N of at least 30.2% and has a contact angle of at least 17.4 degrees.
27. The surface of any one of claims 21 to 23, wherein the surface contains at least 1.8% N, has a sum of O and N of at least 28.2% and has a contact angle of at least 18.8 degrees.


28. The surface of any one of claims 21 to 23, wherein the surface contains from 1.6% N to 1.8% N, has a sum of O and N of at least 29.6% and has a contact angle of at least 14.3 degrees.
29. The surface of any one of claims 21 to 23, wherein the surface contains from 1.8% to 2.2% N, has a sum of O and N of at least 30.7% and has a contact angle of at least 18.4 degrees.
30. The surface of any one of claims 21 to 23, wherein the surface contains from 2.0% to 2.1% N, has a sum of O and N of at least 30.2% and has a contact angle of at least 17.4 degrees.
31. The surface of any one of claims 21 to 23, wherein the surface contains from 1.6% to 1.8% N, has a sum of O and N of at least 28.2% and has a contact angle of at least 18.8 degrees.

Figure 1


Replacement Sheet 1/46




H1p50 on 1:30 MATRIGEL




H1p50 on untreated NUNC LON DELTA



H1p51 on Surface Modified Plate 2



H1p51 on Surface Modified Plate 3



H1p51 on Surface Modified Plate 4

Figure 2

Replacement Sheet 2/46




Figure 3 Replacement Sheet 3/46




Figure 4

Replacement Sheet 4/46





Figure 5

Replacement Sheet 5/46









Figure
6

Figure 7

Replacement Sheet 7/46






**Figure
8**


Figure 9

Replacement Sheet 9/46

P10 on Surface #4 (1s)



P11 on Surface #3 (7s)



10 days culture
DMEM:F12 w/ 10% FBS
Low Binding Plate



10/46

Banding Technique: GTL Band Resolution: Good
Metaphases Counted: 20 Analyzed: 5 Karyotyped: 3

RESULTS: 46,XY[20] Apparently NORMAL Male Human Karyotype

NORMAL FISH Signal Pattern for Chromosomes 12 and 17

Non-clonal Aberrations: none



H1p59 p10 on Surface #4 (1s)

Figure
10

Figure 11

Replacement Sheet 11/46




Figure 12

Replacement Sheet 12/46




Figure 13

Replacement Sheet 13/46






Figure 14

Replacement Sheet 14/46






- Continual Treatment Y-27632 96 hours
- 48 hour Treatment Y-27632
- 24 hour removal
- 24 hour Y-27632

H1 passage 1:3 ratio
10uM Y-27632

	48 hrs/ 24hrs/ 24hrs (on/off/ on)		48 hrs/ 24hrs/ 24hrs (on/off/ on)
96 hrs 10uM Y27632	Y27632	96 hrs 10uM Y27632	Y27632



Crystal violet stain

**Figure
15**

Figure 16

Replacement Sheet 16/46




Figure 17

Replacement Sheet 17/46




Figure 18




Figure 19

Replacement Sheet 19/46




Figure 20

Replacement Sheet 20/46







Figure 21 Surface #2 Replacement Sheet 21/46



Surface #4



Surface #3



Surface #13




Figure 22

Replacement Sheet 22/46




Figure 23

Replacement Sheet 23/46




Figure 24

Replacement Sheet 24/46






Figure 25

Replacement Sheet 25/46

Corning "Cellbind"

BD "Primaria"




Surface #3

Surface #4

p0 H9p50 passaged 1:2 ratio from Matrigel, 24hr in culture

Figure 26

Replacement Sheet 26/46




H9 p53 passaged from 1:30Matrigel to surface
48hours in culture, 1:3 seeding density

Figure 27

Replacement Sheet 27/46

No Colony binding observed on
Surface #14 or #15 without Y27632

48 hr culture
H9 p42 Oct 19




14 15
20uM
Y27632

48 hr culture
H9 p53 Dec 7



14 15
20uM
Y27632

24 hr culture
H1 p57 Dec 13



No
Y27632



20uM
Y27632

Figure 28

Replacement Sheet 28/46

No Y27632

20uM Y27632



H9 p50, p2 in TeSR, p0 on Surface #4
1:2 split, 48 hours in culture

Figure 29

Replacement Sheet 29/46




Figure 30

Replacement Sheet 30/46




Figure 31a

Replacement Sheet 31/46




Figure 31b

Replacement Sheet 32/46




Figure 32a

Y-27632

Replacement Sheet 33/46

H-1152





Figure 32b

Replacement Sheet 34/46






Figure 33

Replacement Sheet 35/46

a)



b)

Incubation time	No H-1152	0.6 μM H-1152
0 hours		
42 hours		
43 hours		
52 hours		

Figure 34






Figure 35 Replacement Sheet 37/46



Surface modified Plate 4



Primaria



Surface modified Plate 18



Surface modified Plate 19

Figure 36

Replacement Sheet 38/46




Figure 37

Replacement Sheet 39/46




Figure 38


Replacement Sheet 40/46
MG

Figure 39

Replacement Sheet 41/46




Figure 40

Replacement Sheet 42/46

MG

+




Figure 41

Replacement Sheet 43/46




Figure 42

Replacement Sheet 44/46




Figure 43

Replacement Sheet 45/46







Figure 44

Replacement Sheet 46/46







H1p50 on 1:30 MATRIGEL




H1p50 on untreated NUNCLON DELTA



H1p51 on Surface Modified Plate 2



H1p51 on Surface Modified Plate 3



H1p51 on Surface Modified Plate 4