




(86) Date de dépôt PCT/PCT Filing Date: 2001/09/27
(87) Date publication PCT/PCT Publication Date: 2002/05/02
(45) Date de délivrance/Issue Date: 2007/07/03
(85) Entrée phase nationale/National Entry: 2003/04/07
(86) N° demande PCT/PCT Application No.: US 2001/030203
(87) N° publication PCT/PCT Publication No.: 2002/035002
(30) Priorité/Priority: 2000/10/26 (US09/697,693)

(51) Cl.Int./Int.Cl. *D21G 3/00* (2006.01)
(72) Inventeur/Inventor:
MEHMOOD, BILAL, US
(73) Propriétaire/Owner:
KADANT WEB SYSTEMS INC., US
(74) Agent: FETHERSTONHAUGH & CO.

(54) Titre : RACLE COMPOSITE ET PROCEDE DE FABRICATION CORRESPONDANT
(54) Title: COMPOSITE DOCTOR BLADE AND ITS METHOD OF MANUFACTURE



(57) Abrégé/Abstract:

A composite doctor blade comprises a steel support band configured with (W_a) a width and thickness (T_a) suitable for mounting in a blade holder, with tensile and yield strengths suitable for a selected doctoring application. A wear resistant strip of high speed steel is integrally joined to an edge of the support band. The wear resistant strip has tensile and yield strengths higher than those of the support band, and has a hardness of between about 55 to about 65 Rc.

ABSTRACT OF THE DISCLOSURE

A composite doctor blade comprises a steel support band configured with (Wa) a width and thickness (Ta) suitable for mounting in a blade holder, with tensile and yield strengths
5 suitable for a selected doctoring application. A wear resistant strip of high speed steel is integrally joined to an edge of the support band. The wear resistant strip has tensile and yield strengths higher than those of the support band, and has a hardness of between about 55 to about 65 Rc.

COMPOSITE DOCTOR BLADE AND ITS METHOD OF MANUFACTURE

BACKGROUND OF THE INVENTION

5 1. Field of the Invention

This invention relates to doctor blades used in various applications, including cleaning, creping and coating in paper making, tissue making, web converting, and similar operations.

2. Description of the Prior Art

10 Doctor blades contact the surfaces of rolls in paper making, tissue making and web converting machines for the purpose of cleaning, applying coatings to sheets, or sheet removal. Conventional doctor blade materials include metals, homogeneous plastics, and composite laminates made of synthetic and natural fibers.

Conventional doctor blades typically have a monolithic edge to edge structure.

15 Selection of blade material therefore entails striking a compromise between materials which provide adequate resistance to edge wear, and materials having the tensile and yield strengths necessary to operate effectively in the intended doctoring mode. Often, this necessity to compromise results in the selection of a blade material with less than optimum resistance to edge wear.

20 There are numerous doctoring processes where blade edge wear can be particularly problematic. For example, in creping and coating, the quality of the resulting paper product is directly affected by the geometry of the blade edge. As the blade wears and the geometry changes, product characteristics such as bulk, tensile strength, softness or crepe count are adversely affected.

25 In cleaning operation, blade loading is directly related to the contact area of the blade edge. As the blade wears, its contact area increases with a concomitant reduction in contact pressure. Lower contact pressures can reduce cleaning effectiveness, which in turn can produce holes in the sheet, sheet breaks and/or sheet wraps.

30 In the past, those skilled in the art have sought to avoid or at least minimize the above problems by resorting to more frequent blade changes. However, this too is disadvantageous in that it reduces the overall efficiency of the paper making process.

Other attempts at extending blade life have included hardening blade surfaces by means of an ion nitriding process, as described in U.S. Patent No. 5,753,076 (King et al.), or employing ceramic wear strips as disclosed in U.S. Patent No. 5,863,329 (Yamanouchi). A number of drawbacks are associated with ion nitriding processes, including inter alia, high capital investments for costly vacuum chambers, batch processing of individual blades as opposed to the more economical processing of long lengths of coiled blade stock, and the uncontrolled application of the process to all blade surfaces rather than to only the edge regions which are susceptible to wear, which further increases costs.

Although ceramic wear strips beneficially extend blade life, their extreme hardness can produce excessive wear of certain roll surfaces, in particular the cast iron surfaces of yankee rolls. This in turn necessitates frequent and costly roll regrinding. Ceramic tipped blades penetrate much deeper into roll coatings, making it necessary to reduce blade loading pressures by as much as 30%. In creping operations, this reduced loading can have a detrimental effect on tissue properties. Ceramic materials are also expensive and as such, add significantly and disadvantageously to high blade costs.

SUMMARY OF THE INVENTION

It is desirable to provide an improved doctor blade which has greater resistance to edge wear, thus providing a more consistent blade geometry, which in turn improves the quality and consistency of the paper products being produced. Greater resistance to blade wear also increases the overall efficiency of the paper making process by reducing the frequency of blade changing.

A doctor blade in accordance with an aspect of the present invention has a steel support band configured with a width and thickness suitable for mounting in a blade holder, with tensile and yield strengths suitable for a selected doctoring application. A wear resistant strip of high-speed steel is integrally joined to an edge of the support band, preferably by electron beam welding. The wear resistant strip has tensile and yield strengths higher than those of the support band. The wear resistant strip may have a hardness of between about 55 to about 65 Rc.

According to another aspect of the present invention, there is provided a method of manufacturing the composite doctor blade described in the above paragraph. The method includes the steps of: electron beam welding the wear resistant strip to the support band to provide a composite structure; heating the composite structure to a first temperature to
5 anneal and straighten the composite structure; reheating the composite structure to a second temperature followed by quenching to partially harden the wear resistant strip; and reheating the composite structure to a third temperature to temper and reduce the hardness of the wear resistant strip to between about 55 to about 65 Rc.

These and other features and advantages of the present invention will now be
10 described in greater detail with reference to the accompanying drawings, wherein:

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a perspective view of one embodiment of a doctor blade in accordance
15 with the present invention;

Figures 2 and 3 are perspective views similar to Figure 1 showing other embodiments of doctor blades in accordance with the present invention; and

Figure 4 is a block diagram depicting the method of manufacturing doctor blades in accordance with the present invention.

20

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

With reference initially to Figure 1, a composite doctor blade in accordance with the present invention is generally depicted at 10 as comprising a steel support band 12 having a
25 width W_a and thickness T_a suitable for mounting in a conventional blade holder (not shown). The support band 12 has tensile and yield strengths suitable for the intended doctoring application, and may for example be selected from the group consisting of D6A, 6150, 6135, 1095, 1075, 304SS and 420SS.

A wear resistant strip 14 of high-speed steel ("HSS") is integrally joined as at 16 to
30 an edge of the support band 12. The strip 14 has tensile and yield strengths higher than those of the support band 12, with a hardness of between about 55 to about 65 Rc. Such

materials advantageously resist plastic deformation and wear under the elevated temperature conditions frequently encountered in doctoring applications.

Preferably, the support band 12 and wear resistant strip 14 are joined by electron welding. The wear resistant strip 14 has a width W_b of between about 0.025 to about 0.33 of the total blade width measured as $W_a + W_b$.

The wear resistant strip 14 and the support band 12 may have the same thickness T_a , as shown in Figure 1. Alternatively, as shown in Figures 2 and 3, the wear resistant strip 14 may have a thickness T_b greater than the thickness T_a of the support band. In Figure 2, the thicker wear resistant strip is offset with respect to the support band to provide a flat continuous surface on one side, and a stepped configuration in the opposite side. In Figure 3, the wear resistant strip is centrally located, thus providing stepped configurations on both sides of the blade.

The material of the wear resistant strip is preferably selected from the group consisting of molybdenum high-speed steels, tungsten high speed steels and intermediate high-speed steels, all as specified in ASM Metals Handbook: Properties and Selection: Irons, Steels, and High Performance Alloys. Vol. 1 Tenth Edition. Copyright MARCH 1990 ASM INTERNATIONAL. The wear resistant strip 14 is preferably substantially free from carbide segregation, and with well dispersed spheroidal carbides having a size ranging from about 3 to about 6, and preferably from about 5 to about 6 units of measurement based on ASTM sizing charts.

With reference to Figure 4, a preferred method of manufacturing doctor blades in accordance with the present invention is shown as comprising the following steps, in sequence:


- a) in block 18, electron beam welding the wear resistant strip 14 to the support band 12 to provide the composite blade structure;
- b) in block 20, heating the composite blade structure 10 to a first temperature of preferably between about 1300 to about 1450°F, to anneal and straighten the welded components;
- c) in block 22, reheating the composite structure to a second temperature of between about 1500 to about 2200°F to partially harden the wear resistant strip 14;
- d) in block 24, quenching the composite structure; and

4a

e) in block 26, reheating the composite structure to a third temperature of about 850 to about 1200°F to temper and reduce the hardness of the wear resistant strip to a level within the range of between about 55 to about 65 Rc.

In contrast to the usage of fully hardened high speed steels in other

5



industrial applications, partial hardening in accordance with the present invention achieves lower hardness levels which are more compatible with roll surfaces, while still providing marked improvement in wear resistance, making it possible in most instances to at least double useful blade life. By varying the thickness of the wear
5 resistant strip while allowing the thickness of the support band to remain constant, fine tuning of paper properties can be achieved without the necessity of having to change blade holders. The composite blade stock of the present invention may be produced continuously and economically in long coiled lengths, thus providing significant cost savings as compared to prior art batch processes.

10 I claim:

1. A composite doctor blade comprising:

a steel support band configured with a width and thickness for mounting in a blade holder, and having tensile and yield strengths for a selected doctoring application; and

a wear resistant strip of high speed steel integrally joined to an edge of said support band, said wear resistant strip having tensile and yield strengths higher than said tensile and yield strengths, respectively, of said support band.
2. The doctor blade of claim 1 wherein said wear resistant strip is joined to said support band by electron beam welding.
3. The doctor blade of claim 1 wherein said wear resistant strip has a width of between about 0.025 to about 0.33 of the total blade width.
4. The doctor blade of claim 1 wherein the thickness of said wear resistant strip is greater than the thickness of said support band.
5. The doctor blade of claim 4 wherein the thickness of said wear resistant strip is not more than twice the thickness of said support band.
6. The doctor blade as claimed in claim 1 wherein the material of said wear resistant strip is selected from the group consisting molybdenum high-speed steels, tungsten high-speed steels and intermediate high-speed steels.
7. The doctor blade of claim 1 wherein said wear resistant strip is substantially free from carbide segregation and has well dispersed spheroidal carbides.
8. The doctor blade of claim 7 wherein said wear resistant strip has well dispersed spheroidal carbides having a size ranging from about 3 to about 6 microns.
9. The doctor blade of claim 8 wherein said spheroidal carbides have a size ranging from about 5 to about 6 microns.
10. A method of manufacturing the composite doctor blade of claim 1, comprising:

- a) electron beam welding said wear resistant strip to said support band to provide a composite structure;
- b) heating said composite structure to a first temperature to anneal and straighten said composite structure;
- c) reheating said composite structure to a second temperature followed by quenching to partially harden said wear resistant strip; and
- d) reheating said composite structure to a third temperature to temper and reduce the hardness of said wear resistant strip to between about 55 to about 65 Rc.

11. The method of claim 10 wherein said first temperature in step (b) is between about 1300 to about 1450°F.

12. The method of claim 10 wherein said second temperature in step (c) is between about 1500 to about 2200°F.

13. The method of claim 10 wherein said third temperature in step (d) is between about 850 to about 1200°F.

14. The doctor blade of any one of claims 2, 3, 4, 6 and 7 wherein said wear resistant strip has a hardness of between about 55 to about 65 Rc.

1/2

FIG. 1




FIG. 2





FIG. 3



2/2




FIG. 4

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/30203

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 D21G3/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D21G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched


Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 3 688 336 A (COSTELLO, JR. ET AL.) 5 September 1972 (1972-09-05) ---	
A	WO 99 54520 A (VALMET CORPORATION) 28 October 1999 (1999-10-28) ---	
A	GB 978 988 A (LODDING ENGINEERING CORP.) 1 January 1965 (1965-01-01) -----	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

3 April 2002

Date of mailing of the international search report

09/04/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

De Rijck, F

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 01/30203

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 3688336	A	05-09-1972	NONE	
WO 9954520	A	28-10-1999	FI 980884 A	23-10-1999
			AU 3424199 A	08-11-1999
			WO 9954520 A1	28-10-1999
GB 978988	A	01-01-1965	NONE	

