

[54] ACRYLATED EPOXIDIZED SOYBEAN OIL
URETHANE DERIVATIVES

[75] Inventors: **George W. Borden**, Niantic, Conn.;
Oliver W. Smith, South Charleston,
W. Va.; **David J. Trecker**, Old Lyme,
Conn.

[73] Assignee: **Union Carbide Corporation**, New
York, N.Y.

[22] Filed: **Nov. 6, 1974**

[21] Appl. No.: **521,510**

Related U.S. Application Data

[62] Division of Ser. No. 343,694, March 22, 1973, which
is a division of Ser. No. 103,912, Jan. 4, 1971,
abandoned.

[52] U.S. Cl. **260/23 EP; 260/23 TN**

[51] Int. Cl.² **C08G 18/04; C08G 18/06**

[58] Field of Search **260/23 EP, 23 TN**

[56] **References Cited**
UNITED STATES PATENTS

2,882,249	4/1959	Posnansky	260/23 TN
3,125,592	3/1964	Nevin	260/405
3,224,989	12/1965	Nevin	260/23 EP
3,256,225	6/1966	Nevin	260/23 EP
3,450,613	6/1969	Steinberg	204/159.15
3,457,324	7/1969	Sekmakas	260/22 EP
3,505,250	4/1970	Saunders	260/22 TN
3,509,234	4/1970	Burlant et al.	260/22 TN
3,551,517	12/1970	Dowbenko et al.	260/22 EP
3,673,140	6/1972	Ackerman et al.	260/22 TN
3,713,864	1/1973	Ackerman et al.	260/22 TN

Primary Examiner—**Ronald W. Griffin**
Attorney, Agent, or Firm—**Francis M. Fazio**


[57] **ABSTRACT**

The urethane derivatives of acrylated epoxidized soybean oil, which is the reaction product of epoxidized soybean oil with acrylic acid or methacrylic acid, are produced by the reaction of acrylated epoxidized soybean oil with an organic isocyanate. The derivatives are useful alone, or in conjunction with a photosensitizer, and/or a pigment as inks and coatings. The ink and coating compositions can be cured by radiation.

6 Claims, No Drawings

group is involved since this group reacts readily and rapidly with water. Any one of the conventional catalysts known to promote the reaction of an isocyanato group with a reactive hydrogen atom of the hydroxyl group, can be used. The number of such catalysts is large, and illustrative thereof one can mention triethylamine, N,N,N',N'-tetramethylbutane-1,3-diamine, dibutyltin dilaurate, stannous octoate, stannous laurate, dioctyltin diacetate, lead octoate, bis[2-(N,N-dimethylamino)ethyl]ether, 1,4-diazabicyclo[2.2.2]octane, and the like.


In the reaction of the acrylated epoxidized soybean oil compound with an amine compound, the amine compound is preferably a secondary amine of the formula $R_2'NH$, wherein Each R' can be substituted or unsubstituted alkyl having from 1 to about 15 carbon atoms, or an aryl group having up to 15 carbons, or the R_2' unit together with the nitrogen atom of the NH group forms a ring structure having 5 or 6 ring atoms. Illustrative thereof one can mention dimethylamine, diethylamine, dibutylamine, dioctylamine, di-2-ethylhexylamine, diphenylamine, N-methyl-N-phenylamine, morpholine, piperidine, pyrrolidine, and the like. In this reaction the amine compound adds across the double bond of the acrylyl unit of the acrylated epoxidized soybean oil compound to produce a compound containing the group



The reaction between the secondary amine and the acrylated epoxidized soybean oil can be carried out by mixing the two compounds together and stirring at a temperature of from about 10° C. to about 100° C.; ambient temperatures are preferred, thus eliminating any need for temperature control facilities. The amount of amine added can be an amount sufficient to react with from about 5 to 40 percent of the acrylyl groups present. If desired, an inert solvent, such as those heretofore mentioned, can also be present.

The urethane derivatives of the acrylated epoxidized soybean oil and the amine derivatives of the acrylated epoxidized soybean oil can be used per se as coating compositions, either alone or in admixture with conventional solvents, pigments, fillers and other additives. They can be applied by conventional means and cured by exposure to heat, light, electron radiation, X-ray radiation, and other known means for curing and crosslinking a polymer, either alone or in the presence of a crosslinker.

The acrylated epoxidized soybean oil compounds, the urethane derivatives thereof and the amine derivatives thereof can also be used to produce coating compositions known as 100 percent reactive coating compositions by mixing them with a reactive solvent. These reactive solvents are well known to those skilled in the art and include olefinic monomers such as styrene, alpha-methylstyrene, p-methylstyrene, p-chlorostyrene, and acrylyl compounds such as the acrylate esters, the methacrylate esters, the acrylamides and the methacrylamides. These acrylyl compounds can be represented by the formula:



wherein Z is hydrogen or methyl; t is an integer having a value of 1 to 3; and R''' is alkoxy having from 1 to about 18 carbon atoms (e.g., methoxy, ethoxy, propoxy, isopropoxy, 2-methylhexoxy, 2-ethylhexoxy, decoxy, octadecyloxy); hydroxyalkoxy having up to about 15 carbon atoms (e.g., hydroxymethoxy, hydroxyethoxy, hydroxypropoxy, hydroxydecoxy); alkoxyalkoxy having up to a total of about 15 carbon atoms (e.g., methoxymethoxy, methoxyethoxy, ethoxybutoxy, methoxypropoxy, decoxypentoxo); cyano; cyanoalkoxy having up to about 15 carbon atoms (e.g., cyanomethoxy, cyanobutoxy, cyanodecoxy); aryloxy (e.g., phenoxy, toloxy, xyloxy, phenoxyethoxy, naphthoxy, benzyloxy); or an $-(OC_nH_{2n})_zNR''''_2$ group wherein n is an integer having a value of 1 to 10, z has a value of 0 or 1 and R'''' is alkyl having 1 to 10 carbon atoms when t is one or polyvalent alkylene or oxyalkylene having 2 to 8 carbon atoms in the alkylene moiety thereof when t is other than one.

Illustrative of suitable acrylyl compounds, many more of which are well known in the art, one can mention methyl acrylate, ethyl acrylate, 2-ethylhexyl acrylate, methoxyethyl acrylate, butoxyethyl acrylate, butyl acrylate, methoxybutyl acrylate, cyano acrylate, cyanoethyl acrylate, phenyl acrylate, methyl methacrylate, propyl methacrylate, methoxyethyl methacrylate, ethoxymethyl methacrylate, phenyl methacrylate, ethyl methacrylate, lauryl methacrylate, N,N-dimethyl acrylamide, N,N-diisopropyl acrylamide, N,N-didecyl acrylamide, N,N-dimethyl methacrylamide, N,N-diethyl methacrylamide, (N,N-dimethylamino)methyl acrylate, 2-(N,N-dimethylamino)ethyl acrylate, 2-(N,N-dipentylamino)ethyl acrylate, (N,N-dimethylamino)-methyl methacrylate, 2-(N,N-diethylamino)propyl acrylate, ethylene glycol diacrylate, propylene glycol diacrylate, neopentyl glycol diacrylate, 1,6-hexanediol diacrylate, diethylene glycol diacrylate, triethylene glycol diacrylate, dipropylene glycol diacrylate, ethylene glycol diacrylate, ethylene glycol dimethacrylate, propylene glycol dimethacrylate, diethylene glycol dimethacrylate, tripropylene glycol diacrylate, trimethylolpropane triacrylate, pentaerythritol triacrylate, and the like.

The concentration of reactive solvent in the 100 percent reactive coating composition can be from zero to about 90 weight percent, with from 5 to 60 weight percent preferred, and from 10 to 50 weight percent most preferred.

When the coating compositions are to be cured by light means they can contain from about 0.1 to about 10 weight percent of an activator such as any of the known photosensitizers or photoinitiators, preferably at a concentration of from about one to about 5 weight percent. These can be added singly or in mixtures and include, for example, benzophenone, p-methoxybenzophenone, acetophenone, m-chloroacetophenone, propiophenone, xanthone, benzoin, benzil, benzaldehyde, naphthoquinone, anthraquinone, benzoin butyl ether, and the like.

If desired, an amine can also be present to further accelerate curing by light radiation when the photoinitiator is an aryl ketone. Amines that shown this synergistic rate-enhancing effect include triethanolamine, triisopropanolamine, methyldiethanolamine, tributylamine, triethylamine and the like.

The photoinitiators or photosensitizers are usually present at a concentration of from about 0.1 to about 10 weight percent, preferably from about 1 to about 5 weight percent, based on the weight of the composition. The amine accelerator, when present, is preferably present at a concentration of from about 1 to about 10 weight percent, and can be as high as 25 weight percent of the composition.

The coating compositions are produced by conventional methods by mixing the selected components together. To facilitate preparation one can apply a small amount of heat. The coatings can be applied by conventional means, including spray, curtain, dip, pad, roll-coating and brushing procedures. They may, if desired, be dried under ambient or oven conditions. The coatings can be applied to any acceptable substrate such as wood, metal, glass, fabric, paper, fiber, plastic that is in any form, e.g., sheet, coil, molded, film, panel, tube, etc.

The coating compositions containing the urethane derivatives of acrylated epoxidized soybean oil or the amine derivatives of epoxidized soybean oil can be cured by exposure to heat or radiation, either before or after the coating has dried. The radiation can be ionizing radiation, either particulate or non-particulate, or non-ionizing radiation. As a suitable source of particulate radiation, one can use any source which emits electrons or charged nuclei. Particulate radiation can be generated from electron accelerators such as the Van de Graaff accelerator, resonance transformers, linear accelerators, insulating core transformers, radioactive elements such as cobalt-60, strontium-90, etc. As a suitable source of non-particulate ionizing radiation, one can use any source which emits light radiation in the range of from about 10^{-3} Angstroms, to about 2000 Angstroms, preferably from about 5×10^{-3} Angstroms to about 1 Angstrom. Suitable sources are vacuum ultraviolet lamps, such as xenon or krypton arcs, and radioactive elements such as cesium-137, strontium-90 and cobalt-60. The nuclear reactors are also known to be a useful source of such radiation. As a suitable source of non-ionizing radiation, one can use any source which emits radiation of from about 2000 Angstroms to about 4000 Angstroms, such as mercury arcs, carbon arcs, tungsten filament lamps, xenon arcs, krypton arcs, sunlamps, lasers, and the like. All of these devices and sources are well known in the art and those skilled in radiation technology are fully aware of the manner in which the radiation is generated and the precautions to be exercised in its use.

The use of low to high pressure mercury lamps to generate ultraviolet light is known. The largest such mercury lamp of commercial utility is generally about 5 feet long, having a diameter of about 1 to 2 inches and an electrical input of about 20 kilowatts. Mercury lamps generate a typical ultraviolet light line structure.

The ionizing radiation dosage necessary to effect curing or crosslinking of the coating composition will vary depending upon the composition of the particular coating that is undergoing radiation, the extent of crosslinking desired, the number of crosslinkable sites available and the molecular weight of the starting polymer in the coating composition. The total dosage will generally be from about 10^3 rads to 10^8 rads, preferably from 5×10^5 rads to 10^7 rads. A rad is 100 ergs of ionizing energy absorbed per gram of material being irradiated.

Recently a source of light radiation emitting high intensity predominantly continuum light radiation containing ultraviolet, visible and infrared radiation was discovered that can be used to polymerize monomers and to crosslink polymer compositions, namely the swirl-flow plasma arc radiation source. By means of proper light filters on this source one can selective screen out a portion of the light radiation emitted, permitting only that wavelength portion desired to reach the material being treated.

The term "high intensity predominantly continuum light radiation" means continuum radiation with a source intensity of at least 350 watts per square centimeter steradian (about 1000 kilowatts per square foot of source projected area) having only a minor part of the energy in peaks of bandwidths less than 100 Angstrom units, with less than about 30 percent of the light radiated having wavelengths shorter than 4,000 Angstrom units and at least about 70 percent of the light energy radiated having wavelengths longer than 4,000 Angstrom units.

This form of high intensity continuum light radiation is derived from an artificial source that generates high intensity predominantly continuum light radiation with a source intensity of at least about 350 watts per square centimeter steradian, as abbreviated by the term: watts $\text{cm}^{-2} \text{sr}^{-1}$. Said high intensity predominantly continuum artificial light radiation generally has about 70 percent of the light radiated at a wavelength longer than 4,000 Angstroms and less than about 30 percent of the light radiated having a wavelength shorter than 4,000 Angstroms, usually, however, about 80 percent of the light radiated has a wavelength longer than 4,000 Angstroms and less than about 20 percent of the light radiated has a wavelength shorter than 4,000 Angstroms, and the source intensity can vary from about 350 watts (about 1000 kilowatts per square foot of source projected area) to about 5,000 watts (about 15,000 kilowatts per square foot of source projected area) or more per square centimeter steradian. A convenient source of high intensity predominantly continuum light radiation is a swirl-flow plasma arc light radiation apparatus. The equipment for generating high intensity predominantly continuum light radiation by this means is known and available; many different forms thereof are described in the literature. A highly efficient apparatus for obtaining high intensity predominantly continuum light radiation is the swirl-flow plasma arc radiation source described in U.S. Pat. No. 3,364,387. The apparatus or equipment necessary for generating the light radiation is not the subject of this invention and any source or apparatus capable of generating high intensity predominantly continuum light radiation can be used.

While any artificial source of generating high intensity predominantly continuum light radiation can be used, as previously indicated the swirl-flow plasma arc radiation apparatus is most convenient. Any apparatus that operates according to the known principles of the swirl-flow plasma arc radiation source can be used to produce the high intensity predominantly continuum light radiation useful in the curing or crosslinking process or this invention. These apparatuses are often known by other terms but those skilled in this art recognize that they emit high intensity predominantly continuum light radiation. The source of radiation in a 50 kilowatt swirl-flow plasma arc radiation source is an arc only about four inches long enclosed in a quartz envelope about 1.5 inches in diameter. This lamp can be

readily removed and refurbished and has an acceptable long lifetime. Further, a swirl-flow plasma arc radiation apparatus having a 250 kilowatt rating would be only about two or three times as large as a 50-kilowatt source. Another advantage is the absence of a need for expensive radiation shielding. Precautions required for the artificial light sources include those needed to protect one's eyes from the intense visible light and from the ultraviolet light present to prevent inadvertent sunburn effect on the body.

It is to be noted that in the spectra of high intensity predominantly continuum light radiation there is a continuum of radiation throughout the entire spectral range. This type of continuum radiation in the ultraviolet range has not heretofore been obtainable from the conventional commercial mercury arcs of lamps generally available for generating ultraviolet light. The previously known means for generating ultraviolet light produced light that shows a line or peak spectrum in the ultraviolet range, it is not a continuum spectrum in the ultraviolet range. In a line spectrum the major portion of useable ultraviolet light is that portion at which the line or band in the spectrum forms a peak; in order for such energy to be useful the material or composition that is to be treated with ultraviolet radiation must be capable of absorbing at that particular wavelength range at which the peak appears. In the event the material or composition does not have the ability to absorb at that particular wavelength range there is little or no absorption or reaction. Thus, in the event the material or composition to be treated absorbs at a particular wavelength range in one of the valleys of the spectral curve there will be little or no reaction since there is little or no ultraviolet energy to adequately excite the system. With a high intensity predominantly continuum radiation, there is a high intensity continuum radiation of ultraviolet energy across the entire ultraviolet wavelength range of the spectrum and there is generally sufficient ultraviolet energy generated at all useful ultraviolet wavelengths to enable one to carry out reactions responsive to ultraviolet radiation without the problem of selecting compound that will absorb at the peak wavelength bands only. With the high intensity continuum radiation now discovered one does not have the problem of being unable to react materials or compositions that absorb in the valley areas only since for all intents and purposes such valleys do not exist in high intensity continuum radiation, the high intensity radiated light energy is essentially a continuum, it is not in peak bands.

High intensity predominantly continuum light radiation is to be distinguished from ultraviolet radiation generated by commercially available low, medium and high pressure mercury arc ultraviolet lamps. These mercury arc lamps produce light emission which is primarily line or peak rather than continuum light, wherein a major part of the light appears in bands narrower than 100 Angstrom units, and much less than 70 percent is above 4,000 Angstrom units.

As is known, high intensity predominantly continuum light radiation from a swirl-flow plasma arc radiation source is emitted from an arc generated between a pair of electrodes that are lined up axially and encased in a quartz cylinder. In an embodiment a pair of concentric quartz cylinders between which cooling water or gas flows is used. A rare gas, such as argon, krypton, neon or xenon, introduced into the inner cylinder tangentially through inlets located at one end of the inner

cylinder creates a swirling flow or vortex which restricts the arc to a small diameter. An electrical potential applied across the electrodes causes a high density current to flow through the gas to generate a plasma composed of electrons, positively charged ions and neutral atoms. A plasma generated in the above gases produces high intensity predominantly continuum light radiation with diffuse maxima in the region of from about 3,000 to about 6,000 Angstroms. The radiation source can also be used with reflectors or refractive optical systems to direct the high intensity predominantly continuum light radiation emanating from the arc to a particular point or direction or geometrical area.

The coating compositions of this invention are readily cured by exposure to the radiation for a shorter period of time. The exposure can vary from a period as short as a fraction of a second to a period that may be as long as ten minutes or longer. In most instances a period of from about 0.1 second to about two minutes is adequate. The distance of the composition from the radiation source will vary depending upon the particular energy source being employed. It can vary from a fraction of an inch up to 10 feet or more; preferably the distance is from about 1 foot to about 4 feet. Exposure can be under normal atmospheric conditions or under an inert gas blanket, for example under nitrogen; the preferred process includes the use of an inert gas atmosphere.

Alternatively, one can add a peroxidic compound, a perester, peracid, peroxide, hydroperoxide, or a persulfate or azo compound to the composition and then cure or crosslink by heating at from about 50° C. to about 250° C. The amount of such compound added can vary from about 0.1 to about 10 weight percent, preferably 0.5 to about 2.5 weight percent, of the composition. Any of these compounds known to be useful in the curing of polymer compositions can be used, such as, di-t-butyl peroxide, dicumyl peroxide, t-butyl hydroperoxide, alpha-tetralin hydroperoxide, t-butyl peracetate, peracetic acid, perbenzoic acid, benzoyl peroxide, dichlorobenzoyl peroxide, ammonium persulfate, azobis(isobutyronitrile), dimethyl azobis(isobutyrate), and the like.

ILLUSTRATIVE EXAMPLES

PREPARATION OF ACRYLATED EPOXIDIZED SOYBEAN OIL COMPOUNDS

Example 1

A mixture was prepared containing 300 parts by weight of a commercially available epoxidized soybean oil and 47.5 parts by weight of acrylic acid. The epoxidized soybean oil had an average molecular weight of about 1,000, an oxirane content of about 7 percent by weight and it was the epoxide of the triester of glycerol with soybean oil. The mixture was heated at 40° C. for 70 hours and then cooled. The reaction product contained 38.6 parts of unreacted acrylic acid with the balance of the reaction product being acrylated epoxidized soybean oil having an oxirane content of 5.2 percent and an acrylyl content of 0.354 milliequivalents per gram.

Example 2

A mixture was prepared using 250 parts of the same epoxidized soybean oil used in Example 1 and 216 parts of acrylic acid; and it was then stirred at 125° C.

for one hour in an open reaction vessel. After cooling to room temperature it was diluted with diethyl ether. The mixture was washed several times with one percent aqueous sodium acid phosphate and then with one percent aqueous sodium chloride solutions. The diethyl ether was removed in vacuo and the product dried. The reaction product contained 49 parts of unreacted acrylic acid and the balance, 417 parts, was acrylated epoxidized soybean oil having an oxirane content of 0.2 percent, an acrylyl content of 2.2 milliequivalents per gram and a viscosity of 1,500 centistokes at 25° C. by the Gardner method.

Example 3

A mixture was prepared using 100 grams of the same epoxidized soybean oil used in Example 1, 400 grams of ethylbenzene and 0.2 gram of tridecylphosphite; it was stirred at 90° C. under a nitrogen purge for one hour. Five hundred grams of acrylic acid, 0.006 gram of phenothiazine, 0.056 gram of hydroquinone and 0.025 gram of alloocimene were added to the above mixture and stirring was continued for another 3 hours at 90° C. to 100° C. while purging with oxygen. The unreacted acrylic acid and the solvent were removed by flash distillation under vacuum at 120° C. The acrylated epoxidized soybean oil had an oxirane content of 0.93 percent, an acrylyl content of 2.1 milliequivalents per gram and a viscosity of 1,850 centistokes at 100° F. by the Gardner method; the distilled product also contained 0.54 percent unreacted acrylic acid.


Example 4

Two liters of the epoxidized soybean oil used in Example 1, 8 liters of acrylic acid, 8 grams of hydroquinone, 2 grams of p-methoxyphenol and 0.5 gram and phenothiazine were charged to a reaction flask and reacted at 100° C. to 110° C. for 5 hours while continuously purging dry air through the mixture. The unreacted acrylic acid was distilled under vacuum on a rotary film evaporator and the residual product was diluted with diethyl ether. The solution was passed through a column of amine containing ion exchange resin sold commercially as A-21 (Rohm & Haas) and then distilled to remove the diethyl ether. The acrylated epoxidized soybean oil was a straw yellow color and was free of unreacted acrylic acid.

PREPARATION OF URETHANE DERIVATIVES OF ACRYLATED EPOXIDIZED SOYBEAN OIL COMPOUNDS

Example 5


One hundred parts by weight of acrylated epoxidized soybean oil, produced as described in Example 4, were mixed with 10 parts of methyl isocyanate, 30 parts of anhydrous tetrahydrofuran and 0.05 part of dibutyltin dilaurate in an amber glass bottle and the bottle was sealed. The mixture was agitated at room temperature for 12 hours. The urethane of the acrylated epoxidized soybean oil contained units of the following formula in the molecule:



This structure was confirmed by infrared analysis. The amber-colored urethane had a viscosity of 1,000 poises.


Example 6

Two hundred parts by weight of acrylated epoxidized soybean oil, produced as described in Example 4, were dissolved in 100 parts of diethyl ether and then 6 parts of an 80/20 mixture of the 2,4- and 2,6-tolylenediisocyanate isomers and 0.05 part of dibutyltin dilaurate were added. After agitating in a closed vessel at room temperature for 12 hours the diethyl ether was distilled under vacuum. The amber-colored urethane had a viscosity of 110 poises. The structure of the urethane of the acrylated epoxidized soybean oil was confirmed by infrared spectrum; it contained units of the following formula in the molecule:



Example 7

Ninety five parts by weight of acrylated epoxidized soybean oil, produced as described in Example 4, were mixed with 5 parts of methylenebis-4,4'-phenyl isocyanate and 0.05 part of dibutyltin dilaurate and agitated at 50° C. in a closed reactor for 16 hours. The yellow urethane of the acrylated epoxidized soybean oil had a Brookfield viscosity of 3,300 centipoises at 25° C. and contained units of the following formula:



PREPARATION OF AMINE DERIVATIVES OF ACRYLATED EPOXIDIZED SOYBEAN OIL COMPOUNDS


Example 8

Ninety seven parts by weight of acrylated epoxidized soybean oil, produced as described in Example 4, were reacted with three parts of diethanolamine in a closed vessel for one hour. The aminated acrylated epoxidized soybean oil was light yellow and it had a Brookfield viscosity of 17,900 centipoises at 25° C. Analysis indicated that about 14 percent of the double bonds of the acrylyl group had reacted with the diethanolamine; the compound contained units of the formula:



Example 9

In a manner similar to that described in Example 8, 97 parts of the acrylated epoxidized soybean oil and 3 parts of morpholine were reacted at 25° C. for 1 hour. The morpholine adduct of the acrylated epoxidized soybean oil was amber in color and it had a Brookfield viscosity of 19,000 centipoises at 25° C. Analysis indicated that about 14 percent of the double bonds of the acrylated epoxidized soybean oil had reacted with the morpholine; the compound contained units of the formula:



PREPARATION OF COATING COMPOSITIONS

Example 10

The urethane of acrylated epoxidized soybean oil, produced as described in Example 6 by the reaction of acrylated soybean oil with two weight percent of an 80/20 mixture of 2,4- and 2,6- tolylenediisocyanate, was coated on steel panels. The panels were placed in a flat box covered with polyethylene film, purged with nitrogen and irradiated with electrons from a 300 kilovolt electron accelerator to impart a dose of 0.5 megarad to the coating. The coating cured to hard, tough surfaces having the following properties.

Run	A	B
Sward hardness (glass = 100)	8	20
Reverse impact (inch-lbs)	>165	25
Acetone resistance (rub cycles)	16	50
Boiling water resistance, (30 min. immersion)	good	excellent

Example 11

Coating compositions were produced by the addition of varying amounts of 2-hydroxyethyl acrylate (HEA) to the same urethane derivative of acrylated epoxidized soybean oil used in Example 10. The coatings were applied to steel panels and were then irradiated with five megarads of high energy electrons in the same manner described in Example 10; Runs A to C. In addition, coating compositions were produced from the

unmodified acrylated epoxidized soybean oil and 2-hydroxyethyl acrylate and similarly irradiated; Runs D to G. As is evident from the results, the addition of the 2-hydroxyethyl acrylate lowers the viscosity making the coating solution easier to apply, while at the same time the properties of the coatings improved with the increased concentration thereof used.

Run	HEA wt%	Viscosity cps at 25° C.	Sward hardness glass = 100	Reverse impact in-lbs.
A	0	25,000	20	25
B	20	1,840	20	100
C	30	750	28	165
D	0	6,800	12	50
E	20	1,200	14	100
F	30	390	14	>165
G	40	210	14	>165

Example 12

To the acrylated epoxidized soybean oil compound of Example 7 there was added 5 weight percent of benzophenone as photosensitizer. The composition was coated on to steel panels and irradiated for sixty seconds under two side-by-side 550 watt medium pressure mercury arcs. The compositions cured to smooth, hard, clear coatings which resisted 200 acetone rub-cycles.

Example 13

A composition was prepared containing 70 parts by weight of the acrylated epoxidized soybean oil compound prepared as described in Example 4 and 30 parts of 2-hydroxyethyl acrylate; it had a viscosity of 390 centipoises at 25° C. The composition was coated on steel panels which were irradiated as described in Example 10 with varying amounts of high energy electrons to determine the effect of varying the electron dosage on the properties of the cured film. It was found that a dose of two megarads was sufficient, a higher dose showed little further improvement. The results are tabulated below; all coatings had a reverse impact of greater than 165 in-lbs.

Megarads	Sward hardness glass = 100	Acetone resistance, rub-cycles	Boiling water resistance 30 min.
0.25	2	11	fair
0.5	8	15	good
1.0	8	30	good
2.0	14	46	good
5.0	14	50	good

Example 14

A composition was prepared containing 80 parts of acrylated epoxidized soybean oil produced as described in Example 4 and 20 parts of 2-butoxyethyl acrylate. This composition was used to produce coating compositions containing varying amounts of tricyclo[5.2.1.0^{2,6}]dec-3-en-8(-9)-yl acrylate (DCPA), which were coated on steel panels and cured in the manner described in Example 10. A dosage of 2.5 megarads was applied to each panel. The coatings cured to smooth, clear films. All of the films had an acetone resistance of 50 rub-cycles and after 30 minutes immersion in boiling water had a boiling water resistance rating of excellent. The data is recorded below:

DCPA wt. %	Sward hardness glass = 100	Reverse impact, in-lbs
0	12	5
12.5	16	25
25.0	22	>165
37.5	34	>165

Example 15

A composition was produced containing 95 parts by weight of the diethanolamine adduct of Example 8 and 5 parts by weight of benzophenone. The solutions were coated on steel panels and irradiated for 10 seconds as described in Example 12 to produce a clear, smooth, tack-free coating.

A composition containing 75 parts by weight of the adduct of Example 8, 20 parts by weight of neopentyl glycol diacrylate and 5 parts by weight of benzoin butyl ether cures to a clear, hard coating when it is irradiated in a similar manner.

Example 16


A coating composition was produced by mixing 95 parts by weight of the morpholine adduct of Example 9 and 5 parts by weight of benzophenone. The solution was coated on steel panels and irradiated with two side-by-side 2.2-kilowatt medium-pressure mercury arcs housed in directional reflectors placed 18 inches over and parallel to a conveyor line moving at 76 feet per minute. A single pass of the coated panel under the mercury arcs cured the composition to a clear, tack-free coating.

Example 17

Ninety-five parts by weight of an acrylated epoxidized soybean oil produced as described in Example 4 and five parts by weight of benzophenone were mixed to form a uniform solution. This was coated on steel panels and irradiated as described in Example 16; three passes under the mercury arcs were required to cure the composition to a tack-free state. A comparison with Example 16 indicates that the amine adducts cure more rapidly.

What is claimed is:

1. Acrylated epoxidized soybean oil urethane compounds having in the molecule the group:



wherein X is hydrogen or methyl, said compounds being the reaction product of:

A. epoxidized soybean oil reacted with acrylic acid or methacrylic acid and

B. an organic isocyanate.

2. A compound as claimed in claim 1 wherein (A) is the reaction product of epoxidized soybean oil with methacrylic acid.

3. A compound as claimed in claim 1 wherein (A) is the reaction product of epoxidized soybean oil with acrylic acid.

4. A compound as claimed in claim 3 wherein (B) is methyl isocyanate.

5. A compound as claimed in claim 3 wherein (B) is tolylene diisocyanate.

6. A compound as claimed in claim 3 wherein (B) is methylenebis-4,4'-phenyl diisocyanate.

* * * * *