



(43) International Publication Date
23 March 2017 (23.03.2017)

- (51) International Patent Classification:
B01J 21/18 (2006.01) *B01J 31/16* (2006.01)
B01J 31/06 (2006.01)
- (21) International Application Number:
PCT/US2016/051646
- (22) International Filing Date:
14 September 2016 (14.09.2016)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
62/218,003 14 September 2015 (14.09.2015) US
62/306,028 9 March 2016 (09.03.2016) US
- (71) Applicant: MASSACHUSETTS INSTITUTE OF
TECHNOLOGY [US/US]; 77 Massachusetts Avenue,
Cambridge, MA 02139 (US).
- (72) Inventors: METZGER, Eric, D.; 399 Marlborough
Street, Boston, MA 02115 (US). DINCA, Mircea; 61
Cherry Street Unit 1, Somerville, MA 02144 (US).
BROZEK, Carl, K.; 715 10th Avenue East Apt. 4,
Seattle, WA 98102 (US).
- (74) Agent: GABERT, Andrea, J.; Wolf, Greenfield & Sacks,
P.C., 600 Atlantic Avenue, Boston, MA 02210-2206 (US).
- (81) Designated States (*unless otherwise indicated, for every
kind of national protection available*): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,
HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,
KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME,
MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ,
OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,
SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM,
ZW.
- (84) Designated States (*unless otherwise indicated, for every
kind of regional protection available*): ARIPO (BW, GH,

[Continued on next page]

(54) Title: COMPOSITIONS AND METHODS FOR SELECTIVE OLIGOMERIZATION COMPRISING METAL ORGANIC FRAMEWORKS




FIG. 1A

(57) Abstract: Compositions and methods for selective olefin (e.g., ethylene) oligomerization comprising metal organic frameworks (MOFs) are generally provided. In some embodiments, a MOF comprises a plurality of metal ions, each coordinated with at least one ligand comprising at least two unsaturated N-heterocyclic aromatic groups arranged about an organic core.



WO 2017/048787 A1



GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ,
TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU,
TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE,
DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT,
LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE,

SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— *with international search report (Art. 21(3))*

COMPOSITIONS AND METHODS FOR SELECTIVE OLEFIN OLIGOMERIZATION COMPRISING METAL ORGANIC FRAMEWORKS

Related Applications

5 This application claims priority to U.S. Provisional Patent Application Serial No. 62/218,003, filed September 14, 2015, and entitled “Compositions and Methods for Selective Olefin Oligomerization Comprising Metal Organic Frameworks” and U.S. Provisional Patent Application Serial No. 62/306,028, filed March 9, 2016, and entitled “Compositions and Methods for Selective Olefin Oligomerization Comprising Metal
10 Organic Frameworks”, each of which are incorporated herein by reference in their entirety for all purposes.

Field

 Compositions and methods for selective olefin oligomerization comprising metal
15 organic frameworks (MOFs) are generally provided. In some embodiments, a MOF comprises a plurality of metal ions, each metal ion coordinated with at least one ligand comprising at least two N-heterocyclic aromatic groups arranged about an organic core.

Background

20 Ethylene is a cornerstone of the petrochemical industry. For example, the dimerization of ethylene to 1-butene plays a key role in the production of alkylate gasoline and of linear low-density polyethylene. Overall, ethylene oligomerization is one of the largest industrial transformations enabled by homogeneous catalysts, exceeded in volume only by hydroformylation, hydrocyanation, and methanol carbonylation. The
25 prominence of ethylene dimerization in the overall industrial production of 1-butene is projected to rise further with the increasing reliance on natural gas feedstocks. Despite substantial academic and industrial efforts, the development of heterogeneous catalysts for ethylene dimerization has suffered from either a lack of activity or poor selectivity. Addressing the selectivity challenge is particularly difficult because, for example, small
30 changes in the ligand sphere or electronic structure of the metal can change the relative rates of ethylene insertion versus beta-hydride elimination, which together relate to product distribution. Such degree of fine tuning in ligand design is the realm of homogeneous catalysis and has not traditionally been available to heterogeneous

systems.

Accordingly, improved compositions and methods are needed.

Summary

5 In some embodiments, a method for forming butene (e.g., 1-butene) from ethylene are provided, the method comprising exposing ethylene to a metal organic framework (MOF) catalyst to produce butene, wherein the MOF catalyst comprises a plurality of metal ions, each metal ion coordinated with at least one ligand, and wherein each ligand comprises at least two N-heterocyclic aromatic groups arranged about an
10 organic core, wherein the N-heterocyclic aromatic groups are selected from the group consisting of imidazolate, triazolate, and tetrazolate.

In some embodiments, a method for forming butene (e.g., 1-butene) from ethylene is provided, the method comprising exposing ethylene to a metal organic framework (MOF) catalyst to produce butene, wherein the MOF comprises a plurality of
15 metal ions, each metal ion coordinated with at least one ligand, and wherein butene is formed with a selectivity of at least about 95% and at a turnover frequency of at least about 20,000 per hour.

In some embodiments, the MOF comprising a plurality of metal ions (e.g., Ni^{+2} and/or Zn^{+2}) and a plurality of ligands comprising one, two, three, or four N-heterocyclic
20 aromatic groups (e.g., imidazolate, triazolate, and/or tetrazolate).

Brief Description of the Drawings

FIG. 1A - FIG. 1D show simulated structures of a non-limiting MOF, according to some embodiments;

25 FIG. 2 shows PXRD patterns of a non-limiting MOF, after ethylene oligomerization reactions, according to some embodiments;

FIG. 3 and FIG. 4 show exemplary chromatograms after ethylene dimerization with a non-limiting MOF, according to some embodiments;

FIG. 5 shows another exemplary chromatogram after ethylene dimerization with
30 a non-limiting MOF, according to some embodiments;

FIG. 6 shows an exemplary chromatogram for ethylene dimerization with a comparative MOF, according to some embodiments; and

FIG. 7 shows a scanning electron microscope image of non-limiting MOF

particles, according to some embodiments; and

FIG. 8A - FIG. 8C show simulated structure of a non-limiting example of an MOF.

Other aspects, embodiments, and features of the invention will become apparent
5 from the following detailed description when considered in conjunction with the
accompanying drawings. The accompanying figures are schematic and are not intended
to be drawn to scale. For purposes of clarity, not every component is labeled in every
figure, nor is every component of each embodiment of the invention shown where
illustration is not necessary to allow those of ordinary skill in the art to understand the
10 invention. All patent applications and patents incorporated herein by reference are
incorporated by reference in their entirety. In case of conflict, the present specification,
including definitions, will control.

Detailed Description

15 Compositions and methods comprising metal organic frameworks (MOFs) and
related uses are generally provided. In some embodiments, a MOF comprises a plurality
of metal ions, each coordinated with at least one ligand, wherein each ligand comprises
at least two unsaturated N-heterocyclic aromatic groups.

The term "metal-organic framework" is given its ordinary meaning in the art and
20 refers to a one-, two-, or three-dimensional coordination polymer including metal ions
and ligands which function as organic structural units, wherein a portion of the metal
ions are each chemically bonded to at least one bi-, tri- or poly-dentate organic structural
unit. The metal ions, in addition to being coordinated with at least one ligand, may also
be bound to one or more auxiliary ligands, as described in more detail herein.

25 The MOFs described herein may be utilized in a wide variety of applications. In
some embodiments, the MOFs may be utilized as a catalyst. For example, in some
embodiments, the MOFs may be utilized as a catalyst for olefin oligomerization or olefin
dimerization. In a particular embodiment, the MOF may be utilized as a catalyst for
ethylene dimerization (e.g., to form 1-butene).

30 In some embodiments, the catalyst is a heterogeneous catalyst. The term
"heterogeneous catalyst" will be understood by those of ordinary skill in the art and
generally refers to a catalyst in solid state catalyzing a reaction which is fully or partly
run in another phase, such as a solvent phase or gaseous phase. In some embodiments,

the MOFs described herein are utilized in a solid state, for example, as a solid dispersed in a solution. One non-limiting advantage to heterogeneous catalysts is the catalyst may generally be easily separated from a reaction mixture. In some embodiments, the catalyst (e.g., the heterogeneous catalyst) is a single site catalyst. The term “single site catalyst” will be understood by those of ordinary skill in the art and generally refers to a catalyst that has only a single type of kinetically active site. For example, for the MOFs described herein, a single type of metal ion for each MOF may act as the catalytic site(s).

The MOFs described herein are particularly advantageous as catalysts for the oligomerization (e.g., dimerization) of olefins such as ethylene. In some embodiments, the MOFs described herein have high turnover frequencies (e.g., greater than about 12,400 moles of ethylene per mole of active metal ion at room temperature under 30 bar of ethylene, greater than about 21,600 moles of ethylene per mole of active metal ion at room temperature under 30 bar of ethylene), high selectivity (e.g., greater than about 95% for butenes), and/or long catalyst lifetimes as compared to traditional olefin catalysts. In some embodiments, the TOF is about 27,000 with a selectivity of 96% for 1-butene at 50 bar of ethylene. In some embodiments, the TOF is about 41,500 with a selectivity of 96% for 1-butene at 50 bar of ethylene. The MOF catalysts described herein may generally be used in any reactor suitable for the oligomerization of olefins. While much of the description herein relates to the dimerization of ethylene, those skilled in the art would understand, based upon the teachings of this specification, that other olefins such as propylene, 1-butene, or 1-pentene may also be oligomerized by catalysis with such MOFs.

Those of ordinary skill in the art will be aware of suitable systems and methods for utilizing a MOF described herein for catalysis. For example, the MOF may be loaded into a reactor for use as an olefin oligomerization catalyst. Olefins (e.g., ethylene, propylene, or the like) may be introduced into the reactor, wherein the olefin oligomerizes upon exposure to the catalyst. Optionally, the reactor may contain one or more solvents (e.g., an organic solvent) and/or one or more additives (e.g., alkylaluminum). The reactor may be operated at any suitable temperature and/or pressure. In some embodiments, the reactor may be operated until a high fraction (e.g., greater than about 80%, greater than about 90%, greater than about 95%, or more) of the desired oligomer (e.g., butene) is produced. In some embodiments, the reactor is

operated at or near atmospheric pressure. In other embodiments, the reactor is operated at elevated pressures (e.g., under an atmosphere of ethylene).

In some embodiments, oligomerization of an olefin is conducted (e.g., the formation of butene from ethylene) in the presence of the MOF and an additive. The presence of the additive, in some cases, may increase the turnover frequency and/or the selectivity of the oligomerization carried out in the presence of the MOF (e.g., for butene) as compared to the turnover frequency and/or the selectivity in the absence of the additive. In some embodiments, the additive is an alkylaluminum compound. Non-limiting examples of alkylaluminum compounds include aluminoxanes (e.g., methylaluminoxane, modified methylaluminoxane) ethylaluminum dichloride, diethylaluminum chloride, triethylaluminum, and trimethylaluminum. In an exemplary embodiment, the additive is methylaluminoxane. In some embodiments, the additive is an alkyl magnesium halide (e.g., ethyl magnesium bromide). In some embodiments, the additive is an alkyllithium compound (e.g., methyllithium). The additive may be provided in any suitable amount. In some embodiments, the ratio of moles of additive to moles of active metal center (e.g., Ni^{+2}) is between 1 and 1000, or between 1 and 500, or between 1 and 250, or between 1 and 100, or between 50 and 500, or between 50 and 400, or between 50 and 300, or between 50 and 200, or between 50 and 150, or about 1, about 2, about 5, about 10, about 25, about 50, or about 100.

The oligomerization may be conducted at any suitable temperature or pressure. For example, in some cases, oligomerization in the presence of the MOF may be conducted at a temperature of at least about 0 °C, at least about 25 °C, at least about 50 °C, or at least about 100 °C. In certain embodiments, oligomerization in the presence of the MOF may be conducted at a temperature of less than or equal to about 150 °C, less than or equal to about 100 °C, less than or equal to about 50 °C, or less than or equal to about 25 °C. Combinations of the above-referenced ranges are also possible (e.g., between about 0 °C and about 150 °C). Other ranges are also possible.

In some embodiments, oligomerization in the presence of the MOF is conducted at a pressure of at least about 15 bar, at least about 30 bar, or at least about 50 bar. In certain embodiments, oligomerization in the presence of the MOF is conducted at a pressure of less than or equal to about 75 bar, less than or equal to about 50 bar, or less than or equal to about 30 bar. Combinations of the above-referenced ranges are also possible (e.g., between about 15 bar and about 75 bar). Other ranges are also possible.

Those skilled in the art would be capable of selecting suitable combinations of temperatures and pressures for the oligomerization of olefins based upon the teachings of the specification.

In some embodiments, the MOFs described herein may catalyze the formation of butene from ethylene with high selectivity. For example, in some embodiments, butene is formed in the presence of a MOF with a selectivity of at least about 80%, at least about 85%, at least about 90%, at least about 95%, at least about 97%, at least about 98%, at least about 99%, at least about 99.5%, at least about 99.8%, or at least about 99.9% for butene. In certain embodiments, butene is formed in the presence of a MOF with a selectivity of 100% for butene.

In certain embodiments, butene is formed with a high weight percentage of 1-butene versus the total amount of butenes. That is to say, the MOFs described herein may also catalyze the formation of 1-butene from ethylene with a high selectivity. In some embodiments, at least about 80 wt%, at least about 85 wt%, at least about 90 wt%, at least about 95 wt%, at least about 97 wt%, at least about 98 wt%, at least about 99 wt%, at least about 99.5 wt%, at least about 99.8 wt, or at least about 99.9 wt% of amount of butene formed from ethylene in the presence of the MOFs described herein is 1-butene.

Those of ordinary skill in the art will be aware of methods and techniques for determining selectivity. The selectivity of a reaction for 1-butene may be determined by determining the percent by weight of 1-butene based on total amount of products (e.g., butenes, hexenes, octenes, etc.) produced. For example, gas chromatography may be used to determining the weight percentage of butene versus the total amount of product produced and/or the total weight percentage of 1-butene versus the total amount of butenes produced.

In certain embodiments, the MOF may catalyze the formation of butene with a high turnover frequency. Turnover frequency, as used herein, refers to the number of moles of ethylene consumed per moles of active metal centers in the MOF. For example, in some embodiments, wherein the active metal center is a nickel ion, the TOF refers to the number of moles of ethylene consumed per mole of nickel. In some embodiments, butenes (and 1-butene) is formed in the presence of the MOF at a turnover frequency of at least about 12,000, at least about 12,500, at least about 14,000, at least about 15,000, at least about 16,000, at least about 17,500, at least about 18,000, at least about 20,000, at least about 21,000, at least about 22,000, at least about 25,000, at least about 27,000,

or at least about 30,000, at least about 35,000, or at least about 41,500 per hour per moles of active metal centers (e.g., nickel). In certain embodiments, butene (and 1-butene) is formed in the presence of the MOF at a turnover frequency of less than or equal to about 40,000, less than or equal to about 30,000, less than or equal to about 25,000, less than or equal to about 20,000, less than or equal to about 18,000, less than or equal to about 16,000, less than or equal to about 15,000, or less than or equal to about 14,000 per hour per moles of active metal centers (e.g., nickel). Combinations of the above referenced ranges are also possible (e.g., between about 12,000 and about 40,000 per hour per moles of active metal centers (e.g., nickel)).

In some embodiments, the TOF is determined per hour at 25 °C and 50 bar. The number of moles of ethylene converted can be determined, for example, using gas chromatography after an hour of reacting the ethylene with the metal ion-containing MOF at 25°C. Those of ordinary skill in the art will be aware of methods and systems for determining the number of moles of active metal centers. For example, in embodiments wherein the active metal center is nickel and the MOF also comprises zinc, number of moles of nickel may be determined based at least in part on the ratio of nickel to zinc (e.g., based on the structure of the MOF) and the weight of the MOF used.

In some embodiments, the MOF may catalyze the formation of butene or 1-butene with a selectivity of at least about 50%, or 60%, or 70%, or 75%, or 80%, or 85%, or 90%, or 95% and a turnover frequency of at least about 12,500 per hour per moles of active metal centers (e.g., nickel). In some embodiments, the MOF may catalyze the formation of butene or 1-butene with a selectivity of at least about 50%, or 60%, or 70%, or about 75%, or 80%, or 85%, or 90%, or 95% and a turnover frequency of at least about 15,000 per hour per moles of active metal centers (e.g., nickel). In some embodiments, the MOF may catalyze the formation of butene or 1-butene with a selectivity of at least about 50%, or 60%, or 70%, or about 75%, or 80%, or 85%, or 90%, or 95% and a turnover frequency of at least about 17,500 per hour per moles of active metal centers (e.g., nickel). In some embodiments, the MOF may catalyze the formation of butene or 1-butene with a selectivity of at least about 50%, or 60%, or 70%, or about 75%, or 80%, or 85%, or 90%, or 95% and a turnover frequency of at least about 20,000 per hour per moles of active metal centers (e.g., nickel). In some embodiments, the MOF may catalyze the formation of butene or 1-butene with a selectivity of at least about 50%, or 60%, or 70%, or about 75%, or 80%, or 85%, or

90%, or 95% and a turnover frequency of at least about 22,500 per hour per moles of active metal centers (e.g., nickel). In some embodiments, the MOF may catalyze the formation of butene or 1-butene with a selectivity of at least about 50%, or 60%, or 70%, or about 75%, or 80%, or 85%, or 90%, or 95% and a turnover frequency of at least
5 about 25,000 per hour per moles of active metal centers (e.g., nickel). In some embodiments, the MOF may catalyze the formation of butene or 1-butene with a selectivity of at least about 50%, or 60%, or 70%, or about 75%, or 80%, or 85%, or 90%, or 95% and a turnover frequency of at least about 27,000 per hour per moles of active metal centers (e.g., nickel). In some embodiments, the MOF may catalyze the
10 formation of butene or 1-butene with a selectivity of at least about 50%, or 60%, or 70%, or about 75%, or 80%, or 85%, or 90%, or 95% and a turnover frequency of at least about 30,000 per hour per moles of active metal centers (e.g., nickel). In some embodiments, the MOF may catalyze the formation of butene or 1-butene with a selectivity of at least about 50%, or 60%, or 70%, or about 75%, or 80%, or 85%, or
15 90%, or 95% and a turnover frequency of at least about 35,000 per hour per moles of active metal centers (e.g., nickel). In some embodiments, the MOF may catalyze the formation of butene or 1-butene with a selectivity of at least about 50%, or 60%, or 70%, or about 75%, or 80%, or 85%, or 90%, or 95% and a turnover frequency of at least about 41,500 per hour per moles of active metal centers (e.g., nickel).

20 In some embodiments, a MOF comprises a plurality of metal ions, each coordinated with at least one ligand comprising at least two unsaturated N-heterocyclic aromatic groups. In some embodiments, at least some of the metal ions are associated with two, three, or four ligands, and each of those ligands are individually associated with one, two, three, or four metal ions. In some embodiments, at least some of the metal
25 ions are associated with two ligands, and each of those ligand is individually associated with two metal ions. In some embodiments, at least some of the metal ions are associated with three ligands, and each of those ligand is individually associated with three metal ions. In some embodiments, at least some of the metal ions are associated with four ligands, and each of those ligand is individually associated with two metal ions. In some
30 embodiments, a ligand is charged. In some embodiments, a ligand has a charge of (-1), or (-2), or (-3), or (-4). In some embodiments, a ligand has a charge of (-2).

In some cases, each metal ion is coordinated with at least two ligands, at least three ligands, or at least four ligands. For example, in some embodiments, the MOF

comprises a plurality of metal ions associated with at least two triazoles, at least three triazoles, or at least four triazoles. Other non-limiting examples of suitable ligands are described in detail herein. In some embodiments, the plurality of metal ions may be selected from the group consisting of Ni^{2+} , Ti^{3+} , Ti^{4+} , Cr^{2+} , Cr^{3+} , Mn^{2+} , Fe^{3+} , Fe^{2+} , Co^{2+} , Cu^{2+} , and Zn^{2+} , or combinations thereof.

Any suitable metal ion may be employed. Each metal ion may be monovalent, divalent, trivalent, or tetravalent. In some embodiments, a least one type of metal ion is a monovalent metal ion. In some embodiments, each metal ion is a monovalent metal ion. Non-limiting examples of monovalent metal ions are Ag^+ , Cu^+ , and Au^+ . In some embodiments, at least one type of metal ion is a divalent metal ion. In some embodiments, the metal ion is a divalent metal ion. Non-limiting examples of monovalent metal ions are Mg^{2+} , Mn^{2+} , Fe^{2+} , Co^{2+} , Ni^{2+} , Cu^{2+} , Pd^{2+} , Pt^{2+} , Ru^{2+} , Cd^{2+} , Zn^{2+} , Pb^{2+} , Hg^{2+} , V^{2+} , and Cr^{2+} . In some cases, the metal ion is Ni^{+2} . In some embodiments, at least one type of metal ion is a divalent metal ion. In some embodiments, the metal ion is a trivalent metal ion. Non-limiting examples of trivalent metal ions are Fe^{3+} , V^{3+} , Ti^{3+} , Sc^{3+} , Al^{3+} , In^{3+} , Ga^{3+} , Mn^{3+} , Co^{3+} , and Cr^{3+} . In some embodiments, at least one type of metal ion is a tetravalent metal ion. In some embodiments, the metal ion is a tetravalent metal ion. A non-limiting examples of tetravalent metal ion is Ti^{4+} .

In some embodiments, the MOF comprises a plurality of a first type of metal ion and a plurality of a second type of metal ion. In some cases, the first type of metal is Ni^{2+} . In some embodiments, the second type of metal ion is Zn^{2+} . In some embodiments, each MOF comprises a single metal ion of the first type. In some embodiments, each MOF comprises more than one of the first type of metal ion. In some embodiments, one or more of the first type of metal ion are the active metal centers for catalysis. In some embodiments, only a single first type of metal ion is an active metal center for catalysis.


In an exemplary embodiment, the MOF catalyst comprises a plurality of metal ions which are each Ni^{2+} . In some embodiments, the MOF comprises a plurality of Ni^{+2} ions and a plurality of a second type of metal ion. In such embodiments, the Ni^{+2} metal centers are the active metal centers for catalysis. In another exemplary embodiment, the MOF catalyst comprises a plurality of metal ions selected from Ni^{2+} and Zn^{2+} . For example, in some embodiments, the MOF catalyst comprises a first metal ion comprising

Ni^{2+} and a second metal ion comprising Zn^{2+} , where the first metal ion and the second metal ion are each coordinated with at least one ligand comprising a triazolate.

In some embodiments, more than one type of metal ion may be employed, for example, a first type of metal ion and a second type of metal ion. In some cases, the first type of metal ion and the second type of metal ion may have the same valency. For example, the first type of metal ion may be a first type of divalent metal ion and the second type of metal ion may be a second different type of divalent metal ion. The two or more types of metal ions may be provided in any suitable ratio.


In some embodiments, a metal ion may be associated with one or more one auxiliary ligands. In some cases, the one or more auxiliary ligand may be found above and/or below the metal ion (e.g., as apical ligands). An auxiliary ligand may or might not be charged. Non-limiting examples of auxiliary ligands include halides (e.g., chlorine, fluorine, bromine, iodine), other salts (e.g., alkyl (e.g., $-\text{CH}_3$), allyl, nitrite, sulfite, chloride, fluoride, bromide, iodide, triflate, BF_4 , PF_6 , NO_3^- , SO_4^{2-} , ClO_4^- , nitrate, carbonate, sulfonate, etc.), and coordinating solvents (e.g., water, pyridine, tetrahydrofuran, diethyl ether, tetrahydrofuran, ammonia, toluene, benzene, etc.).

In an exemplary embodiment, the MOF comprises Ni (e.g., as Ni^{+2}), a plurality of second type of metal ions (e.g., Zn^{+2}), wherein the Ni metal center is associated with three unsaturated N-heterocyclic aromatic groups and optionally an anion. For example, the MOF or a portion of the MOF may comprise the structure:




wherein each heteroaromatic ring is a portion of a ligand (as indicated by the dashed lines), each Y is independently N or C, E is an ion (e.g., a second type of metal ion, optionally bound to one or more additional ligands and indicated by the hatched lines), and X is an anion. In some embodiments, E is a second type of metal ion. The second type of metal ion may or might not be nickel. In some cases, the second type of metal ion is zinc. In some embodiments structure, E is coordinated with three unsaturated N-heterocyclic

aromatic groups. In some embodiments, the MOF or a portion of the MOF comprises the structure:




wherein E and X are as described above.

- 5 In some embodiments, X may be absent in all of or a portion of the MOF. For example, in a non-limiting example, a portion of the MOF may comprise the structure:



- wherein each heteroaromatic ring is a portion of a ligand, each Y is independently N or C, M is a metal ion selected from the group consisting of Ni^{2+} , Ti^{3+} , Cr^{2+} , Cr^{3+} , Mn^{2+} , Fe^{2+} , Co^{2+} , Cu^{2+} , Zn^{2+} , and X is a suitable anion.

In some embodiments, E may be absent in a portion of or all of the MOF. For example, in a non-limiting example, a portion of the MOF may comprise the structure:




- wherein each heteroaromatic ring is a portion of a ligand, each Y is independently N or C, and X is a suitable anion.


It should be understood that while the ligands depicted above contain 5-membered rings, a heterocycle of any ring size may be substituted in the place of any or

all of the ligands coordinated to the metal ion. Furthermore, the MOF may comprise one or more of the above structures. For example, in some embodiments, a significant portion of the MOF comprises both E and X and at least a portion of the MOF does not comprise the E and/or X.

- 5 In some embodiments, M^2 is bound to additional ligands comprising N-heterocyclic aromatic groups. In some embodiments, M^2 is bound by six ligands comprising N-heterocyclic aromatic groups. In some embodiments, the ligand comprising the N-heterocyclic aromatic group has a structure as in Formula (I):




- 10 wherein each R^1 is the same or different and is selected from the group consisting of hydrogen, -alkyl, $-NO_2$, $-R'$, $-F$, $-Cl$, $-Br$, $-I$, $-CN$, $-NC$, $-SO_3R'$, $-SO_3H$, $-OR'$, $-OH$, $-SR'$, $-SH$, $-PO_3R'$, $-PO_3H$, $-CF_3$, $-NR'_2$, $-NHR'$, and $-NH_2$, and each R' is the same or different and is optionally substituted alkyl or optionally substituted aryl. In some embodiments, M^2 is bound to six unsaturated N-heterocyclic aromatic groups having a
- 15 structures as in Formula (I). In some embodiments, each R^1 is hydrogen. In some embodiments, the ligand comprising the N-heterocyclic aromatic group



- wherein each R^1 is the same or different and is selected from the group consisting of hydrogen, -alkyl, $-NO_2$, $-R'$, $-F$, $-Cl$, $-Br$, $-I$, $-CN$, $-NC$, $-SO_3R'$, $-SO_3H$, $-OR'$, $-OH$,
- 20 $-SR'$, $-SH$, $-PO_3R'$, $-PO_3H$, $-CF_3$, $-NR'_2$, $-NHR'$, and $-NH_2$, wherein each R' is the same or different and is optionally substituted alkyl or optionally substituted aryl, wherein each Y is independently alkylene, heteroalkylene, arylene, heteroarylene, $-O-$, $-C(=O)-$, $-S-$, and r is 0, 1, 2, or 3. In some embodiments, r is 0 (e.g., so that the two aryl

rings are directly bound via a bond). In some embodiments, each R^1 is hydrogen. In some embodiments, r is 0 and each R^1 is hydrogen. In some embodiments, the ligand has the structure:



also referred to herein as “bibta”. In some embodiments, E is Ti^{3+} , Cr^{2+} , Cr^{3+} , Mn^{2+} , Fe^{2+} , Co^{2+} , Cu^{2+} , and Zn^{2+} , and each X is any suitable anion or optionally absent. Non-limiting examples of suitable anions include alkyl (e.g., $-CH_3$), allyl, nitrite, sulfite, chloride, fluoride, bromide, iodide, triflate, BF_4 , PF_6 , NO_3^- , SO_4^{2-} , and ClO_4^- .

As described above, generally, the MOF comprises at least one ligand comprising at least two unsaturated N-heterocyclic aromatic groups. In some embodiments, at least one ligand comprises two unsaturated N-heterocyclic aromatic groups. In some embodiments, at least one ligand comprises three unsaturated N-heterocyclic aromatic groups. In some embodiments, each ligand comprises two unsaturated N-heterocyclic aromatic groups. In some embodiments, each ligand comprises three unsaturated N-heterocyclic aromatic groups. In some embodiments, each ligand comprises four unsaturated N-heterocyclic aromatic groups.

The unsaturated N-heterocyclic aromatic group may be selected from any suitable group. Non-limiting examples include pyrrolate, pyrazolate, triazolate, imidazolate, oxazolate, tetrazolate, and pyridinate. Other non-limiting examples include thiazolate, oxadiazolate, purinate, quinolonate, and indolate.


In some embodiments, the unsaturated N-heterocyclic aromatic groups are selected from the group consisting of pyrazolate, triazolate, imidazolate, and tetrazolate. In some embodiments, the unsaturated N-heterocyclic aromatic groups are selected from the group consisting of pyrazolate, pyridinate, imidazolate, triazolate, and tetrazolate. In some embodiments, the unsaturated N-heterocyclic aromatic groups are selected from the group consisting of imidazolate, imidazolate, triazolate, and tetrazolate. In some embodiments, the unsaturated N-heterocyclic aromatic groups are pyrazolates. In certain embodiments, the unsaturated N-heterocyclic aromatic groups are triazolates. Non-limiting examples of triazolate include 1,2,4-triazolate and 1,2,3-triazolate.

For example, in some embodiments, the at least one ligand comprises two or more triazolate, three or more triazolate, or four or more triazolate. In some embodiments, the at least one ligand comprises two triazolates. In some embodiments, the ligand comprises three triazolate. Other N-heterocyclic aromatic groups described
5 herein, and/or combinations of two or more N-heterocyclic aromatic groups described herein, are also possible. For example, in some embodiments, the at least one ligand comprises at least one triazolate and at least one tetrazolate (e.g., one triazolate and one tetrazolate, two triazolates and one tetrazolate, two triazolates and two tetrazolates, etc.). Other combinations are possible.

10 In some embodiments, the at least one ligand comprises at least two unsaturated N-heterocyclic aromatic groups arranged about an organic core. The organic core of the ligand comprising at least two unsaturated N-heterocyclic aromatic groups may be any suitable core. In some embodiments, the core is aromatic. Generally, the core comprises a rigid structure formed from fused aryl and/or heteroaryl rings. In some embodiments,
15 the organic core comprises a plurality of fused aryl and/or heteroaryl rings. In some cases, the organic core comprises a plurality of fused aryl rings. In some cases, the organic core comprises one or more of benzyl, thiophenyl, carbazolyl, pyrrolyl, indolyl, and furanyl.

In some embodiments, the at least one ligand comprises a structure as in:


- 15 -



wherein B is an aromatic or heterocyclic core (e.g., comprising one or more aromatic rings, e.g. B can be biphenyl), wherein each R^1 is the same or different and is selected


5 from the group consisting of hydrogen ($-H$), -alkyl (e.g., $-CH_3$), $-NO_2$, $-R'$, $-F$, $-Cl$, $-Br$, $-I$, $-CN$, $-NC$, $-SO_3R'$, $-SO_3H$, $-OR'$, $-OH$, $-SR'$, $-SH$, $-PO_3R'$, $-PO_3H$, $-CF_3$, $-NR'_2$, $-NHR'$, and $-NH_2$, wherein each R' is the same or different and is optionally substituted alkyl or optionally substituted aryl. In some embodiments, each R^1 is the same and is hydrogen. Non-limiting examples of such ligands include:

- 16 -



wherein each R^1 is the same or different and is selected from the group consisting of
 5 hydrogen, -alkyl, $-\text{NO}_2$, $-\text{R}'$, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, $-\text{CN}$, $-\text{NC}$, $-\text{SO}_3\text{R}'$, $-\text{SO}_3\text{H}$, $-\text{OR}'$, $-\text{OH}$,
 $-\text{SR}'$, $-\text{SH}$, $-\text{PO}_3\text{R}'$, $-\text{PO}_3\text{H}$, $-\text{CF}_3$, $-\text{NR}'_2$, $-\text{NHR}'$, and $-\text{NH}_2$, wherein each R' is the
 same or different and is optionally substituted alkyl or optionally substituted aryl. In
 some embodiments, each R^1 is the same and hydrogen.

In certain embodiments, the ligand comprises the structure as in:




10


wherein each R^1 is the same or different and is selected from the group consisting of
 hydrogen, -alkyl, $-\text{NO}_2$, $-\text{R}'$, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, $-\text{CN}$, $-\text{NC}$, $-\text{SO}_3\text{R}'$, $-\text{SO}_3\text{H}$, $-\text{OR}'$, $-\text{OH}$,

$-\text{SR}'$, $-\text{SH}$, $-\text{PO}_3\text{R}'$, $-\text{PO}_3\text{H}$, $-\text{CF}_3$, $-\text{NR}'_2$, $-\text{NHR}'$, and $-\text{NH}_2$, wherein each R' is the same or different and is optionally substituted alkyl or optionally substituted aryl.

In some embodiments, the ligand comprises the structure:



- 5 wherein each R^1 is the same or different and is selected from the group consisting of hydrogen, $-\text{alkyl}$, $-\text{NO}_2$, $-\text{R}'$, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, $-\text{CN}$, $-\text{NC}$, $-\text{SO}_3\text{R}'$, $-\text{SO}_3\text{H}$, $-\text{OR}'$, $-\text{OH}$, $-\text{SR}'$, $-\text{SH}$, $-\text{PO}_3\text{R}'$, $-\text{PO}_3\text{H}$, $-\text{CF}_3$, $-\text{NR}'_2$, $-\text{NHR}'$, and $-\text{NH}_2$, wherein each R' is the same or different and is optionally substituted alkyl or optionally substituted aryl, wherein each Y is independently alkylene, heteroalkylene, arylene, heteroarylene, $-\text{O}-$, $-\text{C}(=\text{O})$, $-\text{S}-$, and r is 0, 1, 2, or 3. In some embodiments, r is 0. In some embodiments, each R^1 is hydrogen. In some embodiments, the ligand has the structure:
- 10



In some embodiments, r is 0. In some embodiments, each R^1 is H . In some embodiments, r is 0 and each R^1 is hydrogen. In some embodiments, when r is zero and

- 15 In some embodiments, more than one type of ligand comprising at least two unsaturated N-heterocyclic aromatic groups may be employed, for example, a first type of ligand and a second type of ligand. The two or more types of ligands may be provided in any suitable ratio. As described herein, the ligand may comprise any combination of unsaturated N-heterocyclic aromatic groups (e.g., at least one triazolate; a combination of triazolates and tetrazolates; at least one tetrazolate, etc.) In some embodiments, following synthetic modification of a MOF or a precursor ligand which is to be utilized to form a MOF, a mixture of types of ligands (or precursor ligands) may be present. For example, the ligands within the MOF or a plurality of precursor ligands that will be used to form a MOF may be synthetically modified (e.g., oxidized) and only a portion of the
- 20

substituents of the ligands or precursor ligands may be altered. Thus, the ligands within the MOF or the precursor ligands used to form the MOF may comprise a number of different substitution patterns. As a non-limiting example, if the ligand (or precursor ligand) comprises two substituents that are targeted to be modified, upon modification of a plurality of the ligands, for each ligand within the plurality, both substituents may be modified, or only one substituent may be modified, or neither substituent may be modified. Thus, the plurality of ligands may comprise some ligands with both substituents modified, some ligands with only one substituent modified, and some ligands with neither substituent modified. The MOFs may be synthesized using methods known in the art (e.g., see *Chem. Eur. J.* **2011**, *17*, 1837-1848; *Chem. Eur. J.* **2015**, *21*, 8188-8199). For example, in some cases, a method of synthesizing a MOF comprises exposing a plurality of metal ions to a plurality of precursor ligands to form a MOF comprising a portion of the plurality of metal ions each coordinated with at least one ligand, wherein the at least one ligand comprises at least two unsaturated N-heterocyclic aromatic groups arranged about an organic core. Non-limiting examples of ligands comprises at least unsaturated N-heterocyclic aromatic groups arranged about an organic core are described herein. In some embodiments, the metal ion is provided as a salt, and the at least one precursor ligand comprises at least two N-heterocyclic aromatic groups which, during the course of the reaction are deprotonated to form the corresponding ligand (e.g., comprising unsaturated N-heterocyclic aromatic groups). For example, the precursor ligand may be deprotonated to have a charge of (-1), or (-2), or (-3), or (-4). Exemplary precursor ligands are described herein.

In some embodiments, an MOF comprising at least a first type of metal ion and a second type of metal ion may be prepared by metal exchange of a substantially similar MOF comprising only a single type of metal ion. In some embodiments, the metal exchange may be carried out by adding the first type of metal ion to solution comprising the MOF comprising only the second type of metal ion. For example, an MOF comprising zinc ions may be exposed to a plurality of a first type of metal ions (e.g., in solution) and at least one zinc ion may be exchanged by a first type of metal ion (e.g., Ni²⁺). In some embodiments, only one of the second type of metal ions is exchanged with the first type of metal ion. In some embodiments, one or less of the second type of metal ions is exchanged with the first type of metal ion. In other embodiments, more than one of the second type of metal ions is replaced with the first type of metal ion.

In some embodiments, following synthesis of the MOF, the MOF may be modified. For example, the ligands of the MOF may be modified to include one or more functional groups and/or the one or more of the functional groups of the ligand may be modified. The ability to modify in the MOF following synthesis of the MOF is beneficial as the properties of the MOFs may be more readily tuned. In some embodiments, the MOF is modified to include hydrophilic groups. The MOF may be modified using any suitable technique. In some embodiments, the MOF is exposed to oxidative conditions to associate new functional groups and/or modify currently present functional groups that are present on the ligand of the MOF. As a non-limiting example, a ligand of the MOF may comprise one or more alkyl sulfide groups, and the MOF may be exposed to oxidizing conditions (e.g., dimethyldioxirane) to modify the alkyl sulfide groups into alkyl sulfoxides or alkyl ethyl sulfones groups.


In some embodiments, following synthesis of the MOF, one or more of the metal ions may be exchanged. For example, an MOF comprising zinc ions may be exposed to a plurality of nickel ions, and at least one zinc ion may be replaced by a nickel ion.

In some embodiments, the MOFs formed may comprise little or no excess metal ions. That is, the MOF comprises essentially no metal ions which are not coordinated with a ligand comprising at least two unsaturated N-heterocyclic aromatic groups (i.e., “free metal ions”). In some embodiments, the MOF comprises less than about 0.5 wt%, or less than about 0.4 wt%, or less than about 0.3 wt%, or less than about 0.2 wt%, or less than about 0.1 wt%, or less than about 0.05 wt%, or less than about 0.03 wt%, or less than about 0.02 wt%, or less than about 0.01 wt%, or less than about 0.005 wt%, or less than about 0.001 wt% of free metal ions. Those of ordinary skill in the art will be aware of methods for determining the amount of free metal ions, for example, using XPS.

In some embodiments, each precursor ligand comprises two N-heterocyclic aromatic groups. In some embodiments, each precursor ligand comprises three N-heterocyclic aromatic groups. In some embodiments, each precursor ligand comprises four N-heterocyclic aromatic groups. The N-heterocyclic aromatic group for the precursor ligand may be selected from any suitable group. Non-limiting examples are pyrrole, pyrazole, triazole, imidazole, and tetrazole. In some embodiments, the N-heterocyclic aromatic groups are selected from the group consisting of pyrazole, triazole, imidazole, and tetrazole. In some embodiments, the N-heterocyclic aromatic groups are


selected from the group consisting of pyrazole, imidazole, and tetrazole. In some embodiments, the N-heterocyclic aromatic groups are pyrazoles. The organic core of the precursor ligand comprising at least two N-heterocyclic aromatic groups may be as described here.

5 In some embodiments, each precursor ligand has the structure:




wherein B is an aromatic or heterocyclic core, wherein each R^1 is the same or different and is selected from the group consisting of hydrogen, -alkyl, -NO₂, -R', -F, -Cl, -Br, -I, -CN, -NC, -SO₃R', -SO₃H, -OR', -OH, -SR', -SH, -PO₃R', -PO₃H, -CF₃, -NR'₂, -NHR', and -NH₂, wherein each R' is the same or different and is optionally substituted alkyl or optionally substituted aryl. In some embodiments, each R^1 is the same and is hydrogen. Non-limiting examples of such ligands include:

10



wherein each R^1 is the same or different and is selected from the group consisting of hydrogen, $-\text{NO}_2$, $-\text{R}'$, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, $-\text{CN}$, $-\text{NC}$, $-\text{SO}_3\text{R}'$, $-\text{SO}_3\text{H}$, $-\text{OR}'$, $-\text{OH}$, $-\text{SR}'$,
 5 $-\text{SH}$, $-\text{PO}_3\text{R}'$, $-\text{PO}_3\text{H}$, $-\text{CF}_3$, $-\text{NR}'_2$, $-\text{NHR}'$, and $-\text{NH}_2$, wherein each R' is the same or different and is optionally substituted alkyl or optionally substituted aryl. In some embodiments, each R^1 is the same and hydrogen.

In some embodiments, each precursor ligand has a structure as in:



wherein each R^1 is the same or different and is selected from the group consisting of hydrogen, $-\text{NO}_2$, $-\text{R}'$, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, $-\text{CN}$, $-\text{NC}$, $-\text{SO}_3\text{R}'$, $-\text{SO}_3\text{H}$, $-\text{OR}'$, $-\text{OH}$, $-\text{SR}'$,
 10 $-\text{SH}$, $-\text{PO}_3\text{R}'$, $-\text{PO}_3\text{H}$, $-\text{CF}_3$, $-\text{NR}'_2$, $-\text{NHR}'$, and $-\text{NH}_2$, wherein each R' is the same or different and is optionally substituted alkyl or optionally substituted aryl. In a particular embodiment, each R^1 is the same and hydrogen.

15 The metal ion and the ligand may be provided in any suitable amounts. In some embodiments, the mole ratio of the metal ion to the ligand may be based upon the coordination of the metal ion to the ligand. For example, in embodiments, where the ligand is coordinated with three metal ions, and each metal ion is associated with two ligands, the mole ratio of the metal ion to the ligand may be at least 3:2. As another
 20 example, in embodiments, where the ligand is coordinated with two metal ions, and each metal ion is associated with one ligand, the mole ratio of the metal ion to the precursor

ligand may about 2:1. In some embodiments, the ligand is providing in slight mole excess.

In some embodiments, the metal ions are provided as a salt. Non-limiting examples of salts chloride, fluoride, bromide, iodide, triflate, BF_4 , PF_6 , NO_3^- , SO_4^{2-} , and
5 ClO_4^- salts. In some cases, the salt is SO_4^{2-} .

Any suitable solvent may be utilized in the synthetic methods of forming the MOFs described herein. Non-limiting examples of solvents include water, methanol, ethanol, propanol, benzene, *p*-cresol, toluene, xylene, diethyl ether, glycol, diethyl ether, petroleum ether, hexane, cyclohexane, pentane, methylene chloride, chloroform, carbon
10 tetrachloride, dioxane, tetrahydrofuran (THF), dimethyl sulfoxide (DMSO), dimethylformamide, hexamethyl-phosphoric triamide, ethyl acetate, pyridine, triethylamine, picoline, mixtures thereof, or the like.

The MOFs may be synthesized at any suitable temperature. In some cases, the reaction is carried out at about room temperature (e.g., about 25 °C, about 20 °C, between
15 about 20 °C and about 25 °C, or the like). In some cases, however, the reaction is carried out at temperatures below or above room temperature. In some embodiments, the reaction is carried at a temperature between about 25 °C and about 200 °C, about 25 °C and about 150 °C, or between about 50 °C and about 200 °C, or between about 50 °C and about 150 °C, or between about 100 °C and about 150 °C.

In some embodiments, the MOFs may be synthesized in the presence of a base
20 (e.g., to aid in deprotonation of the ligand). Non-limiting examples of bases include NR''_3 wherein each R'' is the same or different and is hydrogen, optionally substituted alkyl, or optionally substituted aryl, and QOH , wherein Q is a cation (e.g., a metal cation, a semi-metal cation, NH_4).

In some embodiments, the MOFs may be synthesized in an inert atmosphere. For
25 example, the reactions may be carried out in or under an inert nitrogen or argon atmosphere (e.g., using standard Schlenk techniques and/or in an inert-atmosphere glovebox).

MOFs synthesized using the methods described herein may be purified using
30 techniques known to those of ordinary skill in the art. In some embodiments, a synthesized MOF may be washed, sometimes involving a Soxhlet extractor, boiled, and/or sonicated (e.g., to remove excess starting materials).

Definitions

For convenience, certain terms employed in the specification, examples, and appended claims are listed here.

5 As used herein, the term “reacting” refers to the forming of a bond between two or more components to produce a stable, isolable compound. For example, a first component and a second component may react to form one reaction product comprising the first component and the second component joined by a covalent bond. That is, the term “reacting” does not refer to the interaction of solvents, catalysts, bases, ligands, or
10 other materials which may serve to promote the occurrence of the reaction with the component(s).

Definitions of specific functional groups and chemical terms are described in more detail below. For purposes of this invention, the chemical elements are identified in accordance with the Periodic Table of the Elements, CAS version, *Handbook of*
15 *Chemistry and Physics*, 75th Ed., inside cover, and specific functional groups are generally defined as described therein. Additionally, general principles of organic chemistry, as well as specific functional moieties and reactivity, are described in *Organic Chemistry*, Thomas Sorrell, University Science Books, Sausalito: 1999, the entire contents of which are incorporated herein by reference.

20 The term “aliphatic,” as used herein, includes both saturated and unsaturated, nonaromatic, straight chain (i.e., unbranched), branched, acyclic, and cyclic (i.e., carbocyclic) hydrocarbons, which are optionally substituted with one or more functional groups. As will be appreciated by one of ordinary skill in the art, “aliphatic” is intended herein to include, but is not limited to, alkyl, alkenyl, alkynyl, cycloalkyl, cycloalkenyl,
25 and cycloalkynyl moieties. Thus, as used herein, the term “alkyl” includes straight, branched and cyclic alkyl groups. An analogous convention applies to other generic terms such as “alkenyl”, “alkynyl”, and the like. Furthermore, as used herein, the terms “alkyl”, “alkenyl”, “alkynyl”, and the like encompass both substituted and unsubstituted groups. In certain embodiments, as used herein, “aliphatic” is used to indicate those
30 aliphatic groups (cyclic, acyclic, substituted, unsubstituted, branched or unbranched) having 1–20 carbon atoms. Aliphatic group substituents include, but are not limited to, any of the substituents described herein, that result in the formation of a stable moiety (e.g., aliphatic, alkyl, alkenyl, alkynyl, heteroaliphatic, heterocyclic, aryl, heteroaryl,

acyl, oxo, imino, thiooxo, cyano, isocyano, amino, azido, nitro, hydroxyl, thiol, halo, aliphaticamino, heteroaliphaticamino, alkylamino, heteroalkylamino, arylamino, heteroarylamino, alkylaryl, arylalkyl, aliphaticoxy, heteroaliphaticoxy, alkyloxy, heteroalkyloxy, aryloxy, heteroaryloxy, aliphaticthioxy, heteroaliphaticthioxy, alkylthioxy, heteroalkylthioxy, arylthioxy, heteroarylthioxy, acyloxy, and the like, each of which may or may not be further substituted).

As used herein, the term "alkyl" is given its ordinary meaning in the art and refers to the radical of saturated aliphatic groups, including straight-chain alkyl groups, branched-chain alkyl groups, cycloalkyl (alicyclic) groups, alkyl substituted cycloalkyl groups, and cycloalkyl substituted alkyl groups. In some cases, the alkyl group may be a lower alkyl group, *i.e.*, an alkyl group having 1 to 10 carbon atoms (*e.g.*, methyl, ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, nonyl, or decyl). In some embodiments, a straight chain or branched chain alkyl may have 30 or fewer carbon atoms in its backbone, and, in some cases, 20 or fewer. In some embodiments, a straight chain or branched chain alkyl may have 12 or fewer carbon atoms in its backbone (*e.g.*, C₁-C₁₂ for straight chain, C₃-C₁₂ for branched chain), 6 or fewer, or 4 or fewer. Likewise, cycloalkyls may have from 3-10 carbon atoms in their ring structure, or 5, 6 or 7 carbons in the ring structure. Examples of alkyl groups include, but are not limited to, methyl, ethyl, propyl, isopropyl, cyclopropyl, butyl, isobutyl, *t*-butyl, cyclobutyl, hexyl, and cyclohexyl.

The term "alkylene" as used herein refers to a bivalent alkyl group. An "alkylene" group is a polymethylene group, *i.e.*, -(CH₂)_z-, wherein *z* is a positive integer, *e.g.*, from 1 to 20, from 1 to 10, from 1 to 6, from 1 to 4, from 1 to 3, from 1 to 2, or from 2 to 3. A substituted alkylene chain is a polymethylene group in which one or more methylene hydrogen atoms are replaced with a substituent. Suitable substituents include those described herein for a substituted aliphatic group.

Generally, the suffix "-ene" is used to describe a bivalent group. Thus, any of the terms defined herein can be modified with the suffix "-ene" to describe a bivalent version of that moiety. For example, a bivalent carbocycle is "carbocyclylene", a bivalent aryl ring is "arylene", a bivalent benzene ring is "phenylene", a bivalent heterocycle is "heterocyclylene", a bivalent heteroaryl ring is "heteroarylene", a bivalent alkyl chain is "alkylene", a bivalent alkenyl chain is "alkenylene", a bivalent alkynyl chain is "alkynylene", a bivalent heteroalkyl chain is "heteroalkylene", a bivalent heteroalkenyl

chain is "heteroalkenylene", a bivalent heteroalkynyl chain is "heteroalkynylene", and so forth.

The terms "alkenyl" and "alkynyl" are given their ordinary meaning in the art and refer to unsaturated aliphatic groups analogous in length and possible substitution to the alkyls described above, but that contain at least one double or triple bond respectively.

In certain embodiments, the alkyl, alkenyl and alkynyl groups employed in the invention contain 1-20 aliphatic carbon atoms. In certain other embodiments, the alkyl, alkenyl, and alkynyl groups employed in the invention contain 1-10 aliphatic carbon atoms. In yet other embodiments, the alkyl, alkenyl, and alkynyl groups employed in the invention contain 1-8 aliphatic carbon atoms. In still other embodiments, the alkyl, alkenyl, and alkynyl groups employed in the invention contain 1-6 aliphatic carbon atoms. In yet other embodiments, the alkyl, alkenyl, and alkynyl groups employed in the invention contain 1-4 carbon atoms. Illustrative aliphatic groups thus include, but are not limited to, for example, methyl, ethyl, *n*-propyl, isopropyl, allyl, *n*-butyl, sec-butyl, isobutyl, *t*-butyl, *n*-pentyl, sec-pentyl, isopentyl, *t*-pentyl, *n*-hexyl, sec-hexyl, moieties and the like, which again, may bear one or more substituents. Alkenyl groups include, but are not limited to, for example, ethenyl, propenyl, butenyl, 1-methyl-2-buten-1-yl, and the like. Representative alkynyl groups include, but are not limited to, ethynyl, 2-propynyl (propargyl), 1-propynyl and the like.

The term "cycloalkyl," as used herein, refers specifically to groups having three to ten, preferably three to seven carbon atoms. Suitable cycloalkyls include, but are not limited to cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cycloheptyl and the like, which, as in the case of other aliphatic, heteroaliphatic, or heterocyclic moieties, may optionally be substituted with substituents including, but not limited to aliphatic; heteroaliphatic; aryl; heteroaryl; arylalkyl; heteroarylalkyl; alkoxy; aryloxy; heteroalkoxy; heteroaryloxy; alkylthio; arylthio; heteroalkylthio; heteroarylthio; -F; -Cl; -Br; -I; -OH; -NO₂; -CN; -CF₃; -CH₂CF₃; -CHCl₂; -CH₂OH; -CH₂CH₂OH; -CH₂NH₂; -CH₂SO₂CH₃; -C(O)R_x; -CO₂(R_x); -CON(R_x)₂; -OC(O)R_x; -OCO₂R_x; -OCON(R_x)₂; -N(R_x)₂; -S(O)₂R_x; -NR_x(CO)R_x, wherein each occurrence of R_x independently includes, but is not limited to, aliphatic, heteroaliphatic, aryl, heteroaryl, arylalkyl, or heteroarylalkyl, wherein any of the aliphatic, heteroaliphatic, arylalkyl, or heteroarylalkyl substituents described above and herein may be substituted or unsubstituted, branched or unbranched, cyclic or acyclic, and wherein any of the aryl or heteroaryl substituents

described above and herein may be substituted or unsubstituted. Additional examples of generally applicable substituents are illustrated by the specific embodiments shown in the Examples that are described herein.

The term “heteroaliphatic,” as used herein, refers to an aliphatic moiety, as
5 defined herein, which includes both saturated and unsaturated, nonaromatic, straight chain (i.e., unbranched), branched, acyclic, cyclic (i.e., heterocyclic), or polycyclic hydrocarbons, which are optionally substituted with one or more functional groups, and that contain one or more oxygen, sulfur, nitrogen, phosphorus, or silicon atoms, *e.g.*, in place of carbon atoms. In certain embodiments, heteroaliphatic moieties are substituted
10 by independent replacement of one or more of the hydrogen atoms thereon with one or more substituents. As will be appreciated by one of ordinary skill in the art, “heteroaliphatic” is intended herein to include, but is not limited to, heteroalkyl, heteroalkenyl, heteroalkynyl, heterocycloalkyl, heterocycloalkenyl, and heterocycloalkynyl moieties. Thus, the term “heteroaliphatic” includes the terms
15 “heteroalkyl,” “heteroalkenyl,” “heteroalkynyl,” and the like. Furthermore, as used herein, the terms “heteroalkyl,” “heteroalkenyl,” “heteroalkynyl,” and the like encompass both substituted and unsubstituted groups. In certain embodiments, as used herein, “heteroaliphatic” is used to indicate those heteroaliphatic groups (cyclic, acyclic, substituted, unsubstituted, branched or unbranched) having 1–20 carbon atoms.
20 Heteroaliphatic group substituents include, but are not limited to, any of the substituents described herein, that result in the formation of a stable moiety (*e.g.*, aliphatic, alkyl, alkenyl, alkynyl, heteroaliphatic, heterocyclic, aryl, heteroaryl, acyl, sulfinyl, sulfonyl, oxo, imino, thiooxo, cyano, isocyano, amino, azido, nitro, hydroxyl, thiol, halo, aliphaticamino, heteroaliphaticamino, alkylamino, heteroalkylamino, arylamino,
25 heteroarylamino, alkylaryl, arylalkyl, aliphaticoxy, heteroaliphaticoxy, alkyloxy, heteroalkyloxy, aryloxy, heteroaryloxy, aliphaticthioxy, heteroaliphaticthioxy, alkylthioxy, heteroalkylthioxy, arylthioxy, heteroarylthioxy, acyloxy, and the like, each of which may or may not be further substituted).

The term “heteroalkyl” is given its ordinary meaning in the art and refers to an
30 alkyl group as described herein in which one or more carbon atoms is replaced by a heteroatom. Suitable heteroatoms include oxygen, sulfur, nitrogen, phosphorus, and the like. Examples of heteroalkyl groups include, but are not limited to, alkoxy, alkoxyalkyl, amino, thioester, poly(ethylene glycol), and alkyl-substituted amino.

The terms “heteroalkenyl” and “heteroalkynyl” are given their ordinary meaning in the art and refer to unsaturated aliphatic groups analogous in length and possible substitution to the heteroalkyls described above, but that contain at least one double or triple bond respectively.

5 Some examples of substituents of the above-described aliphatic (and other) moieties of compounds of the invention include, but are not limited to aliphatic; heteroaliphatic; aryl; heteroaryl; alkylaryl; alkylheteroaryl; alkoxy; aryloxy; heteroalkoxy; heteroaryloxy; alkylthio; arylthio; heteroalkylthio; heteroarylthio; F; Cl; Br; I; -OH; -NO₂; -CN; -CF₃; -CHF₂; -CH₂F; -CH₂CF₃; -CHCl₂; -CH₂OH; -CH₂CH₂OH; 10 -CH₂NH₂; -CH₂SO₂CH₃; -C(O)R_x; -CO₂(R_x); -CON(R_x)₂; -OC(O)R_x; -OCO₂R_x; -OCON(R_x)₂; -N(R_x)₂; -S(O)₂R_x; -NR_x(CO)R_x wherein each occurrence of R_x independently includes, but is not limited to, aliphatic, alicyclic, heteroaliphatic, heterocyclic, aryl, heteroaryl, alkylaryl, or alkylheteroaryl, wherein any of the aliphatic, heteroaliphatic, alkylaryl, or alkylheteroaryl substituents described above and herein may 15 be substituted or unsubstituted, branched or unbranched, cyclic or acyclic, and wherein any of the aryl or heteroaryl substituents described above and herein may be substituted or unsubstituted. Additional examples of generally applicable substituents are illustrated by the specific embodiments shown in the Examples that are described herein.

 The term “aryl” is given its ordinary meaning in the art and refers to aromatic 20 carbocyclic groups, optionally substituted, having a single ring (*e.g.*, phenyl), multiple rings (*e.g.*, biphenyl), or multiple fused rings in which at least one is aromatic (*e.g.*, 1,2,3,4-tetrahydronaphthyl, naphthyl, anthryl, or phenanthryl). That is, at least one ring may have a conjugated pi electron system, while other, adjoining rings can be cycloalkyls, cycloalkenyls, cycloalkynyls, aryls and/or heterocyclyls. The aryl group 25 may be optionally substituted, as described herein. Substituents include, but are not limited to, any of the previously mentioned substituents, *i.e.*, the substituents recited for aliphatic moieties, or for other moieties as disclosed herein, resulting in the formation of a stable compound. In some cases, an aryl group is a stable mono- or polycyclic unsaturated moiety having preferably 3-14 carbon atoms, each of which may be 30 substituted or unsubstituted. “Carbocyclic aryl groups” refer to aryl groups wherein the ring atoms on the aromatic ring are carbon atoms. Carbocyclic aryl groups include monocyclic carbocyclic aryl groups and polycyclic or fused compounds (*e.g.*, two or more adjacent ring atoms are common to two adjoining rings) such as naphthyl groups.

The terms “heteroaryl” is given its ordinary meaning in the art and refers to aryl groups comprising at least one heteroatom as a ring atom. A “heteroaryl” is a stable heterocyclic or polyheterocyclic unsaturated moiety having preferably 3-14 carbon atoms, each of which may be substituted or unsubstituted. Substituents include, but are not limited to, any of the previously mentioned substituents, *i.e.*, the substitutes recited for aliphatic moieties, or for other moieties as disclosed herein, resulting in the formation of a stable compound. In some cases, a heteroaryl is a cyclic aromatic radical having from five to ten ring atoms of which one ring atom is selected from S, O, and N; zero, one, or two ring atoms are additional heteroatoms independently selected from S, O, and N; and the remaining ring atoms are carbon, the radical being joined to the rest of the molecule via any of the ring atoms, such as, for example, pyridyl, pyrazinyl, pyrimidinyl, pyrrolyl, pyrazolyl, imidazolyl, thiazolyl, oxazolyl, isooxazolyl, thiadiazolyl, oxadiazolyl, thiophenyl, furanyl, quinoliny, isoquinoliny, and the like.

It will also be appreciated that aryl and heteroaryl moieties, as defined herein may be attached via an alkyl or heteroalkyl moiety and thus also include -(alkyl)aryl, -(heteroalkyl)aryl, -(heteroalkyl)heteroaryl, and -(heteroalkyl)heteroaryl moieties. Thus, as used herein, the phrases “aryl or heteroaryl moieties” and “aryl, heteroaryl, -(alkyl)aryl, -(heteroalkyl)aryl, -(heteroalkyl)heteroaryl, and -(heteroalkyl)heteroaryl” are interchangeable. Substituents include, but are not limited to, any of the previously mentioned substituents, *i.e.*, the substituents recited for aliphatic moieties, or for other moieties as disclosed herein, resulting in the formation of a stable compound.

It will be appreciated that aryl and heteroaryl groups (including bicyclic aryl groups) can be unsubstituted or substituted, wherein substitution includes replacement of one or more of the hydrogen atoms thereon independently with any one or more of the following moieties including, but not limited to: aliphatic; alicyclic; heteroaliphatic; heterocyclic; aromatic; heteroaromatic; aryl; heteroaryl; alkylaryl; heteroalkylaryl; alkylheteroaryl; heteroalkylheteroaryl; alkoxy; aryloxy; heteroalkoxy; heteroaryloxy; alkylthio; arylthio; heteroalkylthio; heteroarylthio; F; Cl; Br; I; -OH; -NO₂; -CN; -CF₃; -CH₂F; -CHF₂; -CH₂CF₃; -CHCl₂; -CH₂OH; -CH₂CH₂OH; -CH₂NH₂; -CH₂SO₂CH₃; -C(O)R_x; -CO₂(R_x); -CON(R_x)₂; -OC(O)R_x; -OCO₂R_x; -OCON(R_x)₂; -N(R_x)₂; -S(O)R_x; -S(O)₂R_x; -NR_x(CO)R_x wherein each occurrence of R_x independently includes, but is not limited to, aliphatic, alicyclic, heteroaliphatic, heterocyclic, aromatic, heteroaromatic, aryl, heteroaryl, alkylaryl, alkylheteroaryl, heteroalkylaryl or heteroalkylheteroaryl,

wherein any of the aliphatic, alicyclic, heteroaliphatic, heterocyclic, alkylaryl, or alkylheteroaryl substituents described above and herein may be substituted or unsubstituted, branched or unbranched, saturated or unsaturated, and wherein any of the aromatic, heteroaromatic, aryl, heteroaryl, -(alkyl)aryl or -(alkyl)heteroaryl substituents described above and herein may be substituted or unsubstituted. Additionally, it will be appreciated, that any two adjacent groups taken together may represent a 4, 5, 6, or 7-membered substituted or unsubstituted alicyclic or heterocyclic moiety. Additional examples of generally applicable substituents are illustrated by the specific embodiments described herein.

The terms “halo” and “halogen” as used herein refer to an atom selected from the group consisting of fluorine, chlorine, bromine, and iodine.

It will be appreciated that the above groups and/or compounds, as described herein, may be optionally substituted with any number of substituents or functional moieties. That is, any of the above groups may be optionally substituted. As used herein, the term “substituted” is contemplated to include all permissible substituents of organic compounds, “permissible” being in the context of the chemical rules of valence known to those of ordinary skill in the art. In general, the term “substituted” whether preceded by the term “optionally” or not, and substituents contained in formulas of this invention, refer to the replacement of hydrogen radicals in a given structure with the radical of a specified substituent. When more than one position in any given structure may be substituted with more than one substituent selected from a specified group, the substituent may be either the same or different at every position. It will be understood that “substituted” also includes that the substitution results in a stable compound, *e.g.*, which does not spontaneously undergo transformation such as by rearrangement, cyclization, elimination, *etc.* In some cases, “substituted” may generally refer to replacement of a hydrogen with a substituent as described herein. However, “substituted,” as used herein, does not encompass replacement and/or alteration of a key functional group by which a molecule is identified, *e.g.*, such that the “substituted” functional group becomes, through substitution, a different functional group. For example, a “substituted phenyl group” must still comprise the phenyl moiety and cannot be modified by substitution, in this definition, to become, *e.g.*, a pyridine ring. In a broad aspect, the permissible substituents include acyclic and cyclic, branched and unbranched, carbocyclic and heterocyclic, aromatic and nonaromatic substituents of organic

compounds. Illustrative substituents include, for example, those described herein. The permissible substituents can be one or more and the same or different for appropriate organic compounds. For purposes of this invention, the heteroatoms such as nitrogen may have hydrogen substituents and/or any permissible substituents of organic

5 compounds described herein which satisfy the valencies of the heteroatoms.

Furthermore, this invention is not intended to be limited in any manner by the permissible substituents of organic compounds. The term "stable," as used herein, preferably refers to compounds which possess stability sufficient to allow manufacture and which maintain the integrity of the compound for a sufficient period of time to be
10 detected and preferably for a sufficient period of time to be useful for the purposes detailed herein.

Examples of substituents include, but are not limited to, halogen, azide, alkyl, aralkyl, alkenyl, alkynyl, cycloalkyl, hydroxyl, alkoxyl, amino, nitro, sulfhydryl, imino, amido, phosphonate, phosphinate, carbonyl, carboxyl, silyl, ether, alkylthio, sulfonyl,
15 sulfonamido, ketone, aldehyde, ester, heterocyclyl, aromatic or heteroaromatic moieties, -CF₃, -CN, aryl, aryloxy, perhaloalkoxy, aralkoxy, heteroaryl, heteroaryloxy, heteroarylalkyl, heteroaralkoxy, azido, amino, halide, alkylthio, oxo, acylalkyl, carboxy esters, -carboxamido, acyloxy, aminoalkyl, alkylaminoaryl, alkylaryl, alkylaminoalkyl, alkoxyaryl, arylamino, aralkylamino,
20 alkylsulfonyl, -carboxamidoalkylaryl, -carboxamidoaryl, hydroxyalkyl, haloalkyl, alkylaminoalkylcarboxy-, aminocarboxamidoalkyl-, cyano, alkoxyalkyl, perhaloalkyl, arylalkyloxyalkyl, and the like.

The following examples are intended to illustrate certain embodiments of the present invention, but do not exemplify the full scope of the invention.

25

EXAMPLES

Example 1

The following example demonstrates the synthesis and structure of an exemplary MOF for use as a catalyst in ethylene dimerization.

30 Four of the five Zn²⁺ ions in Zn₅Cl₄(BTDD)₃ (MFU-4l) are coordinated to contain a central Zn atom that is octahedrally coordinated by six nitrogen atoms, and four pore-exposed tetrahedral Zn²⁺ ions coordinated by three nitrogen atoms and a chloride (FIGs. 1A-1D). BTDD=bis(1H-1,2,3-triazolo[4,5-b],[4',5'-i])dibenzo[1,4]dioxin. The

bond angles and lengths surrounding these Zn^{2+} ions suggest that nickel-substituted MFU-4l could serve as a very proficient heterogeneous catalyst for ethylene dimerization. Soaking the parent zinc framework in a *N,N*-dimethylformamide (DMF) solution of $\text{Ni}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ for one month produced a nickel-substituted material, $\text{Ni}_{0.46}\text{Zn}_{4.54}\text{Cl}_{2.38}(\text{NO}_3)_{1.62}(\text{BTDD})_3$ (Ni-MFU-4l), where approximately one Zn^{2+} ion in every two SBUs was replaced by Ni^{2+} , as revealed by inductively-coupled plasma atomic emission spectroscopy (ICP-AES). To remove excess metal ions physisorbed in the pores of the framework, Ni-MFU-4l was successively soaked in fresh DMF and methanol. The structural integrity of the material was maintained during these manipulations, as evidenced by the powder X-ray diffraction (PXRD) analysis (FIG. 2). N_2 adsorption isotherms for activated Ni-MFU-4l revealed an uptake of $622 \text{ cm}^3/\text{g}$ at 77 K and 760 torr, and a BET surface area of $2711 \text{ m}^2/\text{g}$, in line with the values reported for the parent Zn material.

Example 2

This example demonstrates the use of the MOF described in Example 1 as a catalyst in ethylene dimerization.

Ni-MFU-4l displays excellent activity for ethylene dimerization (see Table 1A and 1B) and compared to alternative catalysts. A typical catalytic run consisted of the addition of methylaluminoxane (MAO) to a rapidly stirred suspension of Ni-MFU-4l in toluene, with subsequent pressurization with ethylene gas. Upon completion, the reactor was rapidly cooled with a dry ice/acetone bath to condense the oligomerized products, the reaction was quenched with cooled water, and 1-pentene was added as an external standard before the organic layer was analyzed by gas chromatography (see FIG. 3, FIG. 4, and FIG. 5). After 60 minutes at 25 °C, 30 bar of ethylene, and in the presence of 100 equivalents of MAO, Ni-MFU-4l showed a turnover frequency of 21,800 moles of ethylene consumed per mole of Ni per hour. The reaction products contained 94.4 wt% butenes, of which 1-butene accounted for 86.0 wt%, and 5.6 wt% hexenes. The reaction temperature had a dramatic effect on the catalytic performance of Ni-MFU-4l. For a given ethylene pressure, the dimerization activity was comparable at 0 °C and 25 °C, but showed a marked drop-off when the temperature was increased to 50 °C. Increasing the temperature also decreased the selectivity for 1-butene in favor of the isomerized, less desirable product 2-butene. Thus, at 50 °C, 30 bar of ethylene, and 100 equivalents of

MAO, the activity dropped to 1,600 hr⁻¹, and 1-butene represented only 83.1% of all butenes.

The reaction pressure also played a role in the catalytic performance, showing a positive correlation with the activity. At 0 °C and 100 equivalents of MAO, increasing the pressure from 15 bar to 30 bar elevated the turnover frequency from 6,300 hr⁻¹ to 22,600 hr⁻¹. The selectivity for 1-butene relative to 2-butene also generally increased with increasing pressure, with the only exception to this trend coming from the less active reactions at 50 °C. This suggests that higher ethylene pressure enhanced the rate of chain transfer relative to chain isomerization, leading to the enrichment of alpha-olefins within the product distribution.

MAO additive generally improved catalytic activity in Ni-MFU-4l. When treated with an equivalent amount of Et₂AlCl, the turnover frequency of Ni-MFU-4l was 4,700 hr⁻¹, and polymeric residues were observed. The amount of MAO, and other additives, generally correlated with the observed catalytic activity. The most substantial increase was observed when the quantity of MAO was doubled from 50 to 100 equivalents.

In a first non-limiting embodiment, a turnover frequency of 27,100 moles of ethylene consumed per mole of nickel per hour was reached in the presence of 500 equivalents of MAO at 50 bar and 25 °C. Under these conditions, the catalyst showed a selectivity of 96.9% for butenes, with 1-butene accounting for 92.9% of C₄ products. In a second non-limiting embodiment, a turnover frequency of 41,500 moles of ethylene consumed per mole of nickel per hour was reached in the presence of 500 equivalents of MAO at 50 bar and 25 °C when the nickel loading level was decreased to 1 percent of the total metal content of the MOF. Under these conditions, the catalyst showed a selectivity of 97.4% for butenes, with 1-butene accounting for 94.5% of C₄ products. The selectivity for 1-butene increased when catalysis was run with 100 equivalents of MAO at 50 bar and 0 °C. These conditions lead to a turnover frequency of 22,600 moles of ethylene consumed per mole of nickel per hour and an optimized selectivity of 98.4% for butenes, with 1-butene making up 97.8% of the C₄ fraction. Indeed, the optimized overall selectivity for 1-butene was thus 96.2%.

Under these conditions, Ni-MFU-4l produced C₆ olefins as the sole byproducts. In an industrial setting these oligomers will not typically foul the reactor, can readily be separated using technology currently employed in the Alphabutol process, and are

valuable themselves as copolymerization monomers. The high activity suggests that all of the nickel sites are active, not just those exposed on the surface.

Without wishing to be bound by theory, shape selectivity induced by the pores of the MOF may explain the preference for butenes relative to hexenes, although this does not account for the higher 1-butene selectivity observed with the heterogeneous catalyst. An alternative explanation is that the less sterically encumbered active site in the MOF enhances the rate of chain transfer relative to chain propagation or chain isomerization. The Ni environment within Ni-MFU-4l provides an ideal balance between active site accessibility and pore-induced shape selectivity, which lead to unprecedented selectivity for 1-butene.

To determine whether the nickel sites in Ni-MFU-4l were responsible for the catalytic activity, standard dimerization reactions with unsubstituted, all-zinc MFU-4l were conducted. No product formation was observed, indicating that the nickel sites are necessary for dimerization activity. Furthermore, leaching tests showed that the reaction no longer proceeded if the MOF was filtered and removed from the reactor, confirming that the catalytic activity was not attributable to trace homogeneous decomposition products of the MOF (FIG. 6). Finally, PXRD analysis ensured that Ni-MFU-4l remained crystalline after catalysis (FIG. 2).

Example 3

The following example demonstrates the lifetime of the MOF catalyst described in Example 1.

One of the major attractions in heterogenizing homogeneous catalysts stems from the possibility of extending the catalyst lifetime by eliminating bimolecular decomposition pathways. To study the lifetime of Ni-MFU-4l and the potential for catalyst recycling, a two-reactor system that allowed distillation of the reaction products without exposing the Ni-MFU-4l/MAO slurry to the atmosphere was constructed. This experimental setup allowed the removal of products by distillation and repressurization of the reactor for evaluating the catalyst in consecutive runs. The reactor was thus cycled continuously over 72 hours (8 cycles), with only a minor decrease in catalyst activity (See Table 2). Over the course of these 8 cycles, over 92,000 moles of ethylene were dimerized per mole of nickel, highlighting the robustness of Ni-MFU-4l for catalytic ethylene dimerization.

Table 1A. Results of ethylene oligomerization with Ni-MFU-4l.

Entry	Pressure (bar)	T (°C)	MAO equivs	TOF (hr ⁻¹) ^a	Selectivity (wt %)		
					C4	C6	α -C4
1	50	25 °C	500	27000	96.53	3.47	92.31
2	50	25 °C	250	26700	97.36	2.64	93.70
3	50	25 °C	100	23300	97.14	2.86	93.59
4	50	25 °C	50	5900	95.77	4.23	84.72
5	50	0 °C	100	22600	98.35	1.65	97.81
6	50	25 °C	100	23300	97.14	2.86	93.59
7	50	50 °C	100	1700	87.51	12.49	80.52
8	30	0 °C	100	21600	97.43	2.57	95.50
9	30	25 °C	100	21800	94.41	5.59	85.98
10	30	50 °C	100	1600	89.34	10.66	83.14
11	15	0 °C	100	6300	94.17	5.83	93.54
12	15	25 °C	100	11100	94.75	5.25	80.73
13	15	50 °C	100	600	85.19	14.81	79.30

^aMoles of ethylene converted per mole of nickel per hour, determined by GC analysis.

Table 1B. Ethylene dimerization with Ni-MFU-4l.

Entry	Pressure (bar)	T (°C)	MAO equivs	TOF (h ⁻¹) ^e	Selectivity (wt %)			
					C ₄ ^f	C ₆ ^g	α -C ₄ ^h	Overall 1-butene ⁱ
1 ^a	50	25	500	27000	96.5	3.5	92.3	89.1
2 ^a	50	25	250	26700	97.4	2.6	93.7	91.3
3 ^a	50	25	100	21000	97.2	2.8	94.6	92.0
4 ^a	50	25	50	5900	95.8	4.2	84.7	81.1
5 ^a	50	0	100	22600	98.4	1.6	97.8	96.2
6 ^a	50	25	100	21000	97.2	2.8	94.6	92.0
7 ^a	50	50	100	1700	87.5	12.5	80.5	70.4
8 ^a	30	0	100	21600	97.4	2.6	95.5	93.0
9 ^a	30	25	100	21000	95.2	4.8	86.9	82.7
10 ^a	30	50	100	1600	89.3	10.7	83.1	74.2
11 ^a	15	0	100	6300	94.2	5.8	93.5	88.1
12 ^a	15	25	100	11100	94.8	5.2	80.7	76.5
13 ^a	15	50	100	600	85.2	14.8	79.3	67.6
14 ^a	5	25	100	3600	92.9	7.1	72.8	67.6
15 ^a	10	25	100	7000	94.4	5.6	80.8	76.3
16 ^a	15	25	100	11100	94.8	5.2	80.7	76.5
17 ^a	20	25	100	16400	94.9	5.1	81.9	77.7
18 ^a	25	25	100	19800	95.7	4.3	86.8	83.1
19 ^a	30	25	100	21000	95.2	4.8	86.9	82.7
20 ^a	40	25	100	20000	96.6	3.4	94.3	91.1
21 ^a	50	25	100	21000	97.2	2.8	94.6	92.0
22 ^b	50	25	500	9100	97.3	2.7	93.0	90.5
23 ^a	50	25	500	27000	96.5	3.5	92.3	89.1
24 ^c	50	25	500	39600	97.3	2.7	94.7	92.1
25 ^d	50	25	500	41500	97.4	2.6	94.5	92.0

Results of ethylene dimerization with Ni-MFU-4l, as determined by GC analysis.

^aCatalyst is Ni(10%)-MFU-4l ^bCatalyst is Ni(30%)-MFU-4l ^cCatalyst is Ni(3%)-MFU-4l

5 ^dCatalyst is Ni(1%)-MFU-4l. ^eMoles of ethylene converted per mole of nickel per hour, determined by GC analysis. ^fPercent oligomeric products that are C₄ olefins. ^gPercent oligomeric products that are C₆ olefins. ^hPercent 1-butene relative to all C₄ products. ⁱThe overall selectivity for 1-butene among all products.

Table 2. Results of the lifetime experiments with Ni-MFU-4l where the products are distilled off into a second reactor. ^aTurnovers defined as the moles of ethylene converted per nickel site. Each cycle lasts for 1 hour.

Cycle	Turnovers ^a	Selectivity (wt %)			
		C4	C6	C8	α -C4
1	13600	99.35	0.65	-	93.88
2	12100	99.18	0.82	-	88.78
3	10200	99.02	0.98	-	84.73
4	11000	98.65	1.35	-	82.82
5	12000	98.22	1.78	-	84.00
6	12000	98.15	1.85	-	85.54
7	11000	98.29	1.71	-	85.35
8	11200	98.86	1.14	-	84.74

5

Example 4

The following example demonstrates the synthesis and structure of an exemplary MOF for use as a catalyst in ethylene dimerization.

Four of the five Zn^{2+} ions in $\text{Zn}_5\text{Cl}_4(\text{bibta})_3$ (CFA-1) are coordinated to contain a central Zn atom that is octahedrally coordinated by six nitrogen atoms, and four pore-exposed tetrahedral Zn^{2+} ions coordinated by three nitrogen atoms and a chloride (FIG. 8A-FIG. 8C). bibta=1*H*,1'*H*-5,5'-bibenzo[*d*]triazole. The bond angles and lengths surrounding these Zn^{2+} ions suggest that nickel-substituted CFA-1 may be a very proficient heterogeneous catalyst for ethylene dimerization. Soaking the parent zinc framework in a *N,N*-dimethylformamide (DMF) solution of $\text{Ni}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ for one month produced a nickel-substituted material, $\text{Ni}_{0.34}\text{Zn}_{4.66}\text{Cl}_4(\text{bibta})_3$ (Ni-CFA-1), where approximately one Zn^{2+} ion in every three SBUs was replaced by Ni^{2+} , as revealed by inductively-coupled plasma atomic emission spectroscopy (ICP-AES). To remove excess metal ions physisorbed in the pores of the framework, Ni-CFA-1 was successively soaked in fresh DMF and methanol. The structural integrity of the material was maintained during these manipulations, as evidenced by the powder X-ray diffraction.

20

Example 5

This example demonstrates the use of the MOF described in Example 4 as a catalyst in ethylene dimerization.

Ni-CFA-1 displays excellent activity for ethylene dimerization compared to
5 alternative catalysts. A typical catalytic run involved the addition of modified methylaluminoxane (MMAO-12) to a rapidly stirred suspension of Ni-CFA-1 in toluene, with subsequent pressurization with ethylene gas. Upon completion, the reactor was rapidly cooled with a dry ice/acetone bath to condense the oligomerized products, the reaction was quenched with cooled water, and 1-pentene was added as an external
10 standard before the organic layer was analyzed by gas chromatography. At 25 °C and 1000 equivalents of MMAO-12 the turnover frequency is 36,400 with a selectivity of 96% for butenes and a selectivity of 90% for 1-butene relative to all C₄ products. The selectivity for 1-butene relative to 2-butene also generally increased with increasing pressure. This suggests that higher ethylene pressure enhanced the rate of chain transfer
15 relative to chain isomerization, leading to the enrichment of alpha-olefins within the product distribution.

Example 6

This example outlines the methods used in Examples 1-5.

20 Powder X-ray diffraction (PXRD) patterns were recorded on a Bruker Advance II diffractometer equipped with $\theta/2\theta$ Bragg-Brentano geometry and Ni-filtered Cu-K α radiation ($K\alpha_1 = 1.5406 \text{ \AA}$). The tube voltage and current were 40 kV and 40 mA, respectively.

A Micromeritics ASAP 2020 Surface Area and Porosity Analyzer was used to
25 measure nitrogen adsorption isotherms. An oven-dried sample tube equipped with a S3 TranSeal™ (Micromeritics) was evacuated and tared. The sample was transferred to the sample tube, heated to 200 °C for 12 h, and held at that temperature until the outgas rate was less than 2 mtorr/minute. The evacuated sample tube was weighed again and the sample mass was determined by subtracting the mass of the previously tared tube. An N₂
30 isotherm was measured using liquid nitrogen baths (77 K). UHP grade (99.999% purity) N₂ and He, oil-free valves and gas regulators were used for all free space corrections and measurements.

The ethylene dimerization reaction mixtures were analyzed with an Agilent 7890B gas chromatograph (30 meter PoraBOND Q PT capillary column) equipped with a 5977A mass spectrometer and a flame ionization detector.

5 **Synthesis of H₂BTDD, Linker for MFU-4l.** A solution of NaNO₂ (2.86 g, 41.4 mmol) and water (10 mL) was added over ten minutes into a stirring, ice-cooled suspension of dibenzo[1,4]dioxine-2,3,7,8-tetramine tetrakis hydrochloride (7.35 g, 18.8 mmol), acetic acid (70 mL), and water (10 mL). After the transfer was complete, the resulting suspension was allowed to stir an additional 30 minutes. The title compound was
10 obtained by filtration, rinsing with water (50 mL) and methanol (50 mL), as a tan powder (4.31 g, 16.2 mmol, 86% yield). ¹H NMR (500 MHz, trifluoroacetic acid-D₁) δ 7.65 (4 H). ¹³C NMR (125 MHz, trifluoroacetic acid-D₁) δ 145.25, 131.72, 100.40.

Synthesis of Zn₅Cl₄(BTDD)₃. H₂BTDD (1.00 g, 3.76 mmol) was heated with stirring in
15 DMF (1.0 L) at 140 °C until a homogeneous solution was obtained. The solution was then cooled down to room temperature before the addition of ZnCl₂. The mixture was heated to 140 °C with stirring overnight. The resulting powder was obtained by filtration and rinsed with DMF. The powder was soaked in DMF for 12 hours before isolation via centrifugation. This soaking process was repeated four times with DMF, and then two
20 additional times with methanol. The sample was then filtered, rinsed with dichloromethane, and then dried under high vacuum overnight at 180 °C.

Synthesis of Ni_{0.46}Zn_{4.54}Cl_{2.38}(NO₃)_{1.62}(BTDD)₃. Ni(NO₃)₂•6H₂O (5.5 g, 19 mmol) was dissolved in 100 mL of DMF. MFU-4l was suspended in an additional 50 mL of DMF
25 and added to the Ni(NO₃)₂•6H₂O solution. The resulting suspension was allowed to sit at room temperature for one month. The solution was decanted, and the remaining powder was soaked in 100 mL fresh DMF. This process was repeated once daily for three days. The powder was subsequently suspended in 100 mL of fresh methanol. The methanol was replaced once daily for three days. The resulting powder was collected via gravity
30 filtration and was transferred into activation glassware. The material was activated at 150 °C under high vacuum.

General Procedure for Ethylene Oligomerization. In the typical catalytic run, a magnetic stir bar and 5 mg of thermally desolvated Ni-MFU-4l were introduced into a 50 mL stainless steel Parr reactor in a nitrogen filled glovebox. 5 mL of toluene were added to the reactor, followed by the addition of the specified number of equivalents of methylaluminumoxane (10% w/w in toluene, Aldrich). The reactor was fully sealed, transferred out of the glovebox, and brought to the reaction temperature specified with a temperature controller and internal temperature probe. Thirty minutes after the addition of methylaluminumoxane, the reactor was pressurized with ethylene through a dip tube and magnetic stirring was turned on. After one hour, the reactor was rapidly cooled in a dry ice/acetone bath. When the internal temperature reaches -20 °C, the reactor was slowly vented to atmospheric pressure. The reactor was opened and the reaction solution was treated with precooled deionized water. 1-pentene was added to the solution to serve as an external standard before the organic layer was filtered through a precooled 0.2 µm syringe filter. A small sample of the organic layer was quickly analyzed via gas chromatography. Control experiments with the unsubstituted MFU-4l or with alternative aluminum activators were carried out in the same manner as described above.

Leaching Experiment with Ni-MFU-4l. To verify that leached nickel species were not responsible for the observed catalytic activity, a magnetic stir bar and 5 mg of thermally desolvated Ni-MFU-4l were introduced into a 50 mL stainless steel Parr reactor in a nitrogen filled glovebox. 5 mL of toluene was added to the reactor, followed by the addition of 100 equivalents of methylaluminumoxane (10% w/w in toluene, Aldrich). The reactor was fully sealed, transferred out of the glovebox, and brought to the reaction temperature specified with a temperature controller and internal temperature probe. Thirty minutes after the addition of methylaluminumoxane, magnetic stirring was turned on and the reactor was pressurized with ethylene through a dip tube. After one hour, the reactor was transferred into a nitrogen glove bag and slowly vented to atmospheric pressure. The reactor was opened and the reaction solution was sparged with dry nitrogen for 15 minutes to remove any residual butenes in solution. The solution was subsequently filtered through three 0.2 µm syringe filters and transferred into a new 50 mL stainless steel Parr reactor. This new reactor was fully closed, transferred out of the glove bag, and pressurized with ethylene through a dip tube. Internal stirring was maintained throughout the reaction, and after one hour the reactor was rapidly cooled to -

20 °C with a dry ice/acetone bath. Once the internal temperature reached -20 °C the reactor was slowly vented to atmospheric pressure. The reactor was opened and the reaction solution was treated with precooled deionized water. 1-pentene was added to the solution to serve as an external standard before the organic layer was filtered through a
5 precooled 0.2 µm syringe filter. A small sample of the organic layer was quickly analyzed via gas chromatography.

Lifetime Experiment with Ni-MFU-4l. A two-reactor system that allowed the distillation the reaction product without exposing the Ni-MFU-4l/MAO slurry to air was
10 constructed in order to study the lifetime of Ni-MFU-4l and the potential for catalyst recycling. As with typical oligomerization experiments, a magnetic stir bar and 5 mg of thermally desolvated Ni-MFU-4l were introduced into a 25 mL stainless steel Parr reactor, referred to as reactor 1, in a nitrogen filled glovebox. 5 mL of toluene was added to the reactor, followed by the addition of 100 equivalents of methylaluminoxane (10%
15 w/w in toluene, Aldrich). The reactor was fully sealed, transferred out of the glovebox, and the temperature of the reactor was monitored with an internal temperature probe. A 50 mL stainless steel Parr reactor, referred to as reactor 2, was connected to reactor 1 with three feet of 1/8" copper tubing, although the valve connecting reactor 1 to reactor 2 was left closed. Reactor 2 was evacuated to remove ambient water and oxygen inside the
20 vessel. After evacuation, reactor 2 was cooled below -20 °C with a dry ice/acetone bath, as monitored with an internal temperature probe. Thirty minutes after the addition of methylaluminoxane to Ni-MFU-4l, reactor 1 was pressurized to 50 bar with ethylene through a dip tube and magnetic stirring was turned on. After one hour, reactor 1 was placed in a lukewarm water bath and the connection between reactor 1 and reactor 2 was
25 opened, allowing the product butenes to condense in the second reactor. After 30 minutes to allow the system to equilibrate, the connection between reactor 1 and reactor 2 was closed. Reactor 2 was opened, and 10 mL of precooled toluene and 0.1 mL of 1-pentene were added to the vessel. This organic mixture was analyzed via gas chromatography. Reactor 1 was repressurized with ethylene and allowed to react for one hour, while
30 reactor 2 was cleaned and evacuated. This process was continued for 10 cycles before reactor 1 was opened and the organic products were analyzed via GC/MS.

While several embodiments of the present invention have been described and illustrated herein, those of ordinary skill in the art will readily envision a variety of other means and/or structures for performing the functions and/or obtaining the results and/or one or more of the advantages described herein, and each of such variations and/or
5 modifications is deemed to be within the scope of the present invention. More generally, those skilled in the art will readily appreciate that all parameters, dimensions, materials, and configurations described herein are meant to be exemplary and that the actual parameters, dimensions, materials, and/or configurations will depend upon the specific application or applications for which the teachings of the present invention is/are used.
10 Those skilled in the art will recognize, or be able to ascertain using no more than routine experimentation, many equivalents to the specific embodiments of the invention described herein. It is, therefore, to be understood that the foregoing embodiments are presented by way of example only and that, within the scope of the appended claims and equivalents thereto, the invention may be practiced otherwise than as specifically
15 described and claimed. The present invention is directed to each individual feature, system, article, material, kit, and/or method described herein. In addition, any combination of two or more such features, systems, articles, materials, kits, and/or methods, if such features, systems, articles, materials, kits, and/or methods are not mutually inconsistent, is included within the scope of the present invention.

20 The indefinite articles “a” and “an,” as used herein in the specification and in the claims, unless clearly indicated to the contrary, should be understood to mean “at least one.”

The phrase “and/or,” as used herein in the specification and in the claims, should be understood to mean “either or both” of the elements so conjoined, i.e., elements that
25 are conjunctively present in some cases and disjunctively present in other cases. Other elements may optionally be present other than the elements specifically identified by the “and/or” clause, whether related or unrelated to those elements specifically identified unless clearly indicated to the contrary. Thus, as a non-limiting example, a reference to
30 “A and/or B,” when used in conjunction with open-ended language such as “comprising” can refer, in one embodiment, to A without B (optionally including elements other than B); in another embodiment, to B without A (optionally including elements other than A); in yet another embodiment, to both A and B (optionally including other elements); etc.

As used herein in the specification and in the claims, “or” should be understood to have the same meaning as “and/or” as defined above. For example, when separating items in a list, “or” or “and/or” shall be interpreted as being inclusive, i.e., the inclusion of at least one, but also including more than one, of a number or list of elements, and, optionally, additional unlisted items. Only terms clearly indicated to the contrary, such as “only one of” or “exactly one of,” or, when used in the claims, “consisting of,” will refer to the inclusion of exactly one element of a number or list of elements. In general, the term “or” as used herein shall only be interpreted as indicating exclusive alternatives (i.e. “one or the other but not both”) when preceded by terms of exclusivity, such as “either,” “one of,” “only one of,” or “exactly one of.” “Consisting essentially of,” when used in the claims, shall have its ordinary meaning as used in the field of patent law.

As used herein in the specification and in the claims, the phrase “at least one,” in reference to a list of one or more elements, should be understood to mean at least one element selected from any one or more of the elements in the list of elements, but not necessarily including at least one of each and every element specifically listed within the list of elements and not excluding any combinations of elements in the list of elements. This definition also allows that elements may optionally be present other than the elements specifically identified within the list of elements to which the phrase “at least one” refers, whether related or unrelated to those elements specifically identified. Thus, as a non-limiting example, “at least one of A and B” (or, equivalently, “at least one of A or B,” or, equivalently “at least one of A and/or B”) can refer, in one embodiment, to at least one, optionally including more than one, A, with no B present (and optionally including elements other than B); in another embodiment, to at least one, optionally including more than one, B, with no A present (and optionally including elements other than A); in yet another embodiment, to at least one, optionally including more than one, A, and at least one, optionally including more than one, B (and optionally including other elements); etc.

In the claims, as well as in the specification above, all transitional phrases such as “comprising,” “including,” “carrying,” “having,” “containing,” “involving,” “holding,” and the like are to be understood to be open-ended, i.e., to mean including but not limited to. Only the transitional phrases “consisting of” and “consisting essentially of” shall be closed or semi-closed transitional phrases, respectively, as set forth in the United States Patent Office Manual of Patent Examining Procedures, Section 2111.03.

Claims

What is claimed is:

- 5 1. A method for forming butene from ethylene, the method comprising:
exposing ethylene to a metal organic framework (MOF) catalyst to produce
butene,
wherein the MOF catalyst comprises a plurality of metal ions, each metal ion
coordinated with at least one ligand, and at least one metal ion being Ni^{2+} , and
10 wherein the at least one ligand comprises at least two N-heterocyclic aromatic
groups arranged about an organic core, wherein the N-heterocyclic aromatic groups are
selected from the group consisting of imidazolate, triazolate, and tetrazolate.
2. The method of claim 1, wherein butene is formed with a selectivity of at least
15 about 75% and at a turnover frequency of at least about 12,500 per hour.
3. A method for forming butene from ethylene, the method comprising:
exposing ethylene to a metal organic framework (MOF) catalyst to produce
butene,
20 wherein the MOF comprises a plurality of metal ions, each metal ion coordinated
with at least one ligand, and at least one metal ion being Ni^{2+} , and
wherein butene is formed with a selectivity of at least about 95% and at a
turnover frequency of at least about 20,000 per hour.
- 25 4. The method as in claim 3, wherein each ligand comprises at least two N-
heterocyclic aromatic groups arranged about an organic core, wherein the N-heterocyclic
aromatic groups are selected from the group consisting of pyrazolate, pyridinate,
imidazolate, triazolate, and tetrazolate.
- 30 5. The method as in any preceding claim, wherein an additive is present during the
exposing step.

6. The method as in claim 5, wherein the additive is selected from the group consisting of an aluminoxane, methylaluminoxane, ethylaluminum dichloride, diethylaluminum chloride, triethylaluminum, an alkyl magnesium halide an alkyllithium, and trimethylaluminum.

5

7. The method as in claim 5, wherein the additive is methylaluminoxane.

8. The method as in any preceding claim, wherein at least one metal ion is selected from the group consisting of Ni^{2+} , Ti^{3+} , Cr^{2+} , Cr^{3+} , Mn^{2+} , Fe^{2+} , Co^{2+} , Cu^{2+} , and Zn^{2+} .

10

9. The method as in any preceding claim, wherein at least one metal ion is Zn^{2+} .

10. The method as in any preceding claim, wherein the N-heterocyclic aromatic group is triazolate.

15

11. The method as in any preceding claim, wherein butene is formed with a selectivity of at least about 80%, or at least about 85%, or at least about 90%, or at least about 95%, or about 96%, or about 97%, or about 98%, or about 99%, or about 99.5%, or about 100%.

20

12. The method as in any preceding claim, wherein 1-butene is formed with a selectivity of at least about 80%, or at least about 85%, or at least about 90%, or at least about 95%, or about 96%, or about 97%, or about 98%, or about 99%, or about 99.5%, or about 100%.

25


13. The method as in any preceding claim, wherein butene is formed with a selectivity of at least about 80%, or at least about 85%, or at least about 90%, or at least about 95%, or about 96%, or about 97%, or about 98%, or about 99%, or about 99.5%, or about 100% at a turnover frequency of at least about 12,500, or at least about 15,000, or at least about 17,500, or at least about 20,000, or at least about 25,000, or at least about 30,000, or at least about 35,000, or at least about 41,500 per hour per active metal center.

30

14. The method as in any preceding claim, wherein 1-butene is formed with a selectivity of at least about 80%, or at least about 85%, or at least about 90%, or at least about 95%, or about 96%, or about 97%, or about 98%, or about 99%, or about 99.5%, or about 100% at a turnover frequency of at least about 12,500, or at least about 15,000,
 5 or at least about 17,500, or at least about 20,000, or at least about 25,000, or at least about 30,000, or at least about 35,000, or at least about 41,500 per hour per active metal center.

15. The method as in any preceding claim, wherein the MOF comprises at least two
 10 ligands comprising triazolate.


16. The method as in any preceding claim, wherein the at least one ligand comprising the N-heterocyclic aromatic group has a structure as in Formula (I):



15 wherein each R¹ is the same or different and is selected from the group consisting of hydrogen, -alkyl, -NO₂, -R', -F, -Cl, -Br, -I, -CN, -NC, -SO₃R', -SO₃H, -OR', -OH, -SR', -SH, -PO₃R', -PO₃H, -CF₃, -NR'₂, -NHR', and -NH₂, and each R' is the same or different and is optionally substituted alkyl or optionally substituted aryl.


20 17. The method as in claim 16, wherein each R¹ is hydrogen.

18. The method as in any preceding claim, wherein the at least one ligand comprising the N-heterocyclic aromatic group comprises the structure:



- wherein each R^1 is the same or different and is selected from the group consisting of hydrogen, -alkyl, -NO₂, -R', -F, -Cl, -Br, -I, -CN, -NC, -SO₃R', -SO₃H, -OR', -OH, -SR', -SH, -PO₃R', -PO₃H, -CF₃, -NR'₂, -NHR', and -NH₂, wherein each R' is the same or different and is optionally substituted alkyl or optionally substituted aryl,
- 5 wherein each Y is independently alkylene, heteroalkylene, arylene, heteroarylene, -O-, -C(=O), -S-, and wherein r is 0, 1, 2, or 3.

19. The method as in claim 18, wherein the ligand has the structure:



10

20. The method as in claim 18 or 19, wherein each R^1 is H.
21. The method as in claim 18, 19, or 20, wherein r is 0.

15

1/13




FIG. 1A

2/13




FIG. 1B

3/13




FIG. 1C

4/13




FIG. 1D




FIG. 2

6/13




FIG. 3

7/13




FIG. 4

8/13




FIG. 5

9/13




FIG. 6

10/13




FIG. 7

11/13




FIG. 8A

12/13




FIG. 8B

13/13




FIG. 8C

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 16/51646

Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☒ Claims Nos.: 8-21
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying additional fees, this Authority did not invite payment of additional fees.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- ☐ The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- ☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 16/51646

A. CLASSIFICATION OF SUBJECT MATTER IPC(8) - B01J 21/18, B01J 31/06, B01J 31/16 (2016.01) CPC - B01J 2231/20, Y02P 20/52, C07C 2531/22, C07C 2529/83 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC(8) - B01J 21/18, B01J 31/06, B01J 31/16 (2016.01) CPC - B01J 2231/20, Y02P 20/52, C07C 2531/22, C07C 2529/83 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Patents and non-patent literature (classification, keyword; search terms below) Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) PatBase, Google Scholar (non-patent literature), Google Patents; search terms: butene, ethylene, metal organic framework, MOF, catalyst, N-heterocyclic aromatic, dimerization, nickel, methylaluminoxane, MAO, cocatalyst, activating agent		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	Canivet et al. "MOF-Supported Selective Ethylene Dimerization Single-Site Catalysts through One-Pot Postsynthetic Modification," Journal of the American Chemical Society, 7 March 2013 (07.03.2013), Vol 135, pg 1195-1198, entire document	1-7
Y	US 2014/0326007 A1 (Dinca et al.) 6 November 2014 (06.11.2014), entire document, especially abstract, para [0006], [0007], [0027]	1-7
Y	US 2013/0066128 A1 (BREUIL et al.) 14 March 2013 (14.03.2013), entire document, especially abstract, para [0019], [0020]	7
A	US 2012/0077667 A1 (Liu et al.) 29 March 2012 (29.03.2012), entire document	1-7
☐ Further documents are listed in the continuation of Box C. ☐		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier application or patent but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search 26 October 2016		Date of mailing of the international search report 02 DEC 2016
Name and mailing address of the ISA/US Mail Stop PCT, Attn: ISA/US, Commissioner for Patents P.O. Box 1450, Alexandria, Virginia 22313-1450 Facsimile No. 571-273-8300		Authorized officer: Lee W. Young PCT Helpdesk: 571-272-4300 PCT OSP: 571-272-7774