




US 20080319537A1

(19) **United States**(12) **Patent Application Publication**
ADDONIZIO et al.(10) **Pub. No.: US 2008/0319537 A1**(43) **Pub. Date: Dec. 25, 2008**(54) **STENT HAVING HELICAL ELEMENTS**(30) **Foreign Application Priority Data**(75) Inventors: **Scott J. ADDONIZIO**, Fort
Lauderdale, FL (US); **David L.**
CAMP, JR., Hillsboro Beach, FL
(US); **Gary J. BECKER**, Miami,
FL (US); **John D. PAZIENZA**,
Pompano Beach, FL (US)Jun. 13, 1997 (EP) 97201799
May 6, 1998 (EP) 98201446**Publication Classification**(51) **Int. Cl.**
A61F 2/06 (2006.01)(52) **U.S. Cl.** **623/1.22**

Correspondence Address:

CHRISTOPHER & WEISBERG, P.A.
200 EAST LAS OLAS BOULEVARD, SUITE 2040
FORT LAUDERDALE, FL 33301 (US)(73) Assignee: **ORBUSNEICH MEDICAL, INC.**,
Fort Lauderdale, FL (US)(21) Appl. No.: **12/196,761**(22) Filed: **Aug. 22, 2008****Related U.S. Application Data**(63) Continuation of application No. 12/027,382, filed on
Feb. 7, 2008, which is a continuation of application
No. 10/014,705, filed on Dec. 11, 2001, now Pat. No.
7,329,277, which is a continuation-in-part of applica-
tion No. 09/511,481, filed on Feb. 23, 2000, now Pat.
No. 7,108,714, which is a continuation of application
No. 09/094,402, filed on Jun. 10, 1998, now Pat. No.
6,117,165.(57) **ABSTRACT**

An expandable stent comprised of a plurality of helical seg-
ments is disclosed. In one embodiment, the stent is generally
cylindrical in shape having a cylindrical axis, and comprises
a first and second set of helical segments. The helical seg-
ments in the first set are substantially parallel and have a first
pitch forming a first helical angle with respect to the cylin-
drical axis. The helical segments in the second set are also
generally parallel to each other and form a second pitch that
differs from the first pitch, thereby forming a second helical
angle with respect to the cylindrical axis. In an alternative
embodiment, the stent comprises one set of helical segments
and a plurality of circumferential elements that are joined
together by the helical segments to form a plurality of cylin-
drical elements which are joined together to form a stent
body. The stent may also have endzones.






FIG. 1




FIG. 2




FIG. 3




FIG. 5




FIG. 4




FIG. 6




FIG. 7




FIG. 8




FIG. 9





FIG. 10






FIG. 12




FIG. 13




FIG. 14




FIG. 15

STENT HAVING HELICAL ELEMENTS

CROSS-REFERENCE TO RELATED APPLICATION

[0001] This application is a continuation of U.S. patent application Ser. No. 12/027,382, filed on Feb. 7, 2008, which application is a continuation of U.S. patent application Ser. No. 10/014,705, filed on Dec. 11, 2001, now issued U.S. Pat. No. 7,329,277, which application claims the benefit of U.S. Provisional Application No. 60/254,688, filed on Dec. 11, 2000, all of which are hereby incorporated in their entirety by reference. U.S. patent application Ser. No. 10/014,705 is also continuation-in-part of U.S. patent application Ser. No. 09/511,481, filed on Feb. 23, 2000, now U.S. Pat. No. 7,108,714, which is a continuation of U.S. patent application Ser. No. 09/094,402, filed Jun. 10, 1998, now U.S. Pat. No. 6,117,165, all of which are hereby incorporated in their entirety by reference.

FIELD OF THE INVENTION

[0002] The present invention relates to prosthetic stents. In particular, the present invention relates to stents having helical elements and to methods for manufacturing the stents of the present invention.

BACKGROUND OF THE INVENTION

[0003] Stents are prosthetic devices that are implanted in the lumen of a vessel inside the body to provide support for the vessel's wall. Structural support from stents is particularly important in angioplasty procedures. Typically, stents are implanted within a vessel system to reinforce vessels that are partially occluded, collapsing, weakened, or abnormally dilated. More generally, stents can be used inside any physiological conduit or duct including, for example, arteries, veins, bile ducts, the urinary tract, alimentary tracts, the tracheobronchial tree, a cerebral aqueduct or the genitourinary system. Stents may be used in both humans and animals.

[0004] There are typically two types of stents: self expanding stents and balloon expandable stents. Self expanding stents automatically expand once they are released and assume a deployed, expanded state. A balloon expandable stent is expanded using an inflatable balloon catheter. The balloon is inflated to plastically deform the stent. Balloon expandable stents may be implanted by mounting the stent in an unexpanded or crimped state on a balloon segment of a catheter. The catheter, after having the crimped stent placed thereon, is inserted through a puncture in a vessel wall and moved through the vessel until it is positioned in the portion of the vessel that is in need of repair. The stent is then expanded by inflating the balloon catheter against the inside wall of the vessel. Specifically, the stent is plastically deformed by inflating the balloon so that the diameter of the stent is increased and remains at an increased state. In some situations, the vessel in which the stent is implanted may be dilated by the stent itself when the stent is expanded.

[0005] The Palmaz-Schatz® stent, which is disclosed in the Handbook of Coronary Stents by Patrick W. Serruys et al. (Martin Dunitz, LTD 1998), is an example of a balloon expandable stent that had been implanted in hundreds of thousands of patients. The Palmaz-Schatz® stent, like other known stents, has certain limitations. These include, but are not limited to: (i) low stent-to-vessel ratio uniformity, (ii) comparative rigidity of the stent in a crimped as well as

deployed state, and (iii) limited flexibility making delivery and placement in narrow vessels difficult. Stent-to-vessel ratio generally refers to the degree that the vessel wall is supported by the stent in its expanded state and preferably should be uniform throughout the length of the stent. Furthermore because the Palmaz-Schatz® stent consists of one or more bridges that connect a number of consecutively slotted tubes, there are a number of bare areas in the vessel after the expansion of the stent. These shortfalls are common to many stents.

SUMMARY OF THE INVENTION

[0006] The present invention is directed to expandable stents that have relatively uniform stent-to-vessel ratios when expanded and other desirable properties, as well as methods for making these stents. The stents of the present invention comprise a generally cylindrically shaped main body having a plurality of expandable helical segments. The main body is comprised of a plurality of cylindrical main body elements that are joined together by the helical segments. The cylindrical elements have cylindrical axes that are collinear with the cylindrical axis of the main body. The cylindrical elements are formed from a plurality of circumferential elements that are joined together by the expandable helical segments. In some embodiments, the stent may comprise endzones that straddle the main body.

[0007] In one embodiment of the present invention, the stent may comprise a first non-helical endzone and a second non-helical endzone that straddle the main body. The main body is generally cylindrically shaped and has a cylindrical axis. A plurality of adjacent main body cylindrical elements are connected together to form the main body of the stent. Each main body cylindrical element may be comprised of a plurality of expandable first and second circumferential elements. In some embodiments, the second circumferential elements have a circumferential dimension less than the circumferential dimension of the first circumferential elements. In yet other embodiments, the first and second circumferential elements have the same circumferential dimensions and are substantially identical except that, with respect to the cylindrical axis of the stent, they are oriented differently. Each second circumferential segment in each main body cylindrical element is connected to two first circumferential segments. In addition, each second circumferential segment in each main body cylindrical element is connected to a second circumferential segment in an adjoining main body cylindrical element thereby forming a plurality of helices in the main body of the stent.

[0008] In one embodiment, the main body may be comprised of a plurality of first helical segments each having a substantially identical first pitch and a plurality of second helical segments, each having a substantially identical second pitch. The first and second pitches are generally different. In at least one embodiment, the second pitch is twice that of the first, and at least one first helical segment crosses one of the second helical segments.

[0009] The stents of the present invention may be manufactured from a tubular member by removing material from the tube to form a first endzone region, a second endzone region, and a middle region. By removing material from the middle region a plurality of parallel helical segments will remain and a plurality of circumferential segments will remain connecting the helical segments. Alternatively, the stent may be

formed from a tube by removing material such that at least two sets of helical segments remain with each set having a different pitch.

BRIEF DESCRIPTION OF THE DRAWINGS

[0010] FIG. 1 is a three dimensional view of one embodiment of a stent according to the present invention in its unexpanded state.

[0011] FIG. 2 is planar view of a flattened portion of the circumference of the stent in FIG. 1.

[0012] FIG. 3 is an enlarged portion of FIG. 2.

[0013] FIG. 4 is another planar view of a flattened portion of the circumference of a stent according to the present invention in its unexpanded state.

[0014] FIG. 5 is an enlarged view of a portion of FIG. 4 showing a first circumferential element of the stent.

[0015] FIG. 6 is an enlarged view of a portion of FIG. 4 showing a second circumferential element of the stent.

[0016] FIG. 7 is a planar view of a flattened portion of the stent in FIG. 1 showing a plurality of sets of helical segments propagating through the stent's body.

[0017] FIG. 8 is a planar view of a flattened endzone that may be employed in a stent of the present invention.

[0018] FIG. 9 is a planar view of a flattened portion of part of the endzone shown in FIG. 8.

[0019] FIG. 10 is a planar view of a flattened portion of an expandable stent according to the present invention, after the stent has been deployed in a lumen.

[0020] FIG. 11 is three dimensional view of an alternative embodiment of the present invention.

[0021] FIG. 12 is a three dimensional view of another stent according to the present invention.

[0022] FIG. 13 is a planar view of the stent shown in 12.

[0023] FIG. 14 is a detailed view of a portion of FIG. 13.

[0024] FIG. 15 is a detailed view of another portion of FIG. 13.

DETAILED DESCRIPTION OF THE INVENTION

[0025] The present invention is directed to an expandable stent, as well as a method of manufacturing the stent. In one embodiment, as is shown in FIGS. 1 and 2, the stent comprises a generally cylindrical shaped main body section 11 having a cylindrical axis 5 and a wall thickness 103. The wall thickness 103 may optionally be uniform throughout the stent. The main body section 11 is comprised of a plurality of helical segments 30 and 40 and a plurality of main body cylindrical elements 100, each having cylindrical axes (not shown) that are collinear with the main body cylindrical axis 5. The main body cylindrical elements 100 are each comprised of circumferential elements 50 that are joined together by the helical segments 30 and 40 to form individual cylinders 100.

[0026] The stent may also have a first endzone 10 and a second endzone 20 that straddle the body section 11. In some embodiments, such as the one shown in FIG. 1, the endzones 10 and 20 may advantageously provide the stent with square outer edges 8. The stent may be manufactured from stainless steel, or other suitable materials. In most embodiments, it is desirable that the material, or a portion of the material, be radiopaque and that the various segments that form the stent be contiguous. Although, in some embodiments, the various segments that make up the stent can be distinct elements that are joined together.

[0027] The main body 11, shown in FIGS. 1 and 2, may be formed in numerous ways. For example, the body 11 may contain two or more first helical segment 30 and 40 that are generally parallel to each other. In some embodiments they may be opposite each other by 180.degree. In general, the first helical segments 30 and 40 will be spaced equidistant along the circumference 110 of the main body 11. The first helical segments 30 and 40 are joined by a plurality of circumferential segments 50 to form a plurality of main body cylindrical elements 100, which may be only generally cylindrically shaped. In one embodiment, the circumferential segments 50 make up a majority of the circumference 110 of each cylindrical element 100. In addition to joining the circumferential elements 50 to form cylindrical elements 100, the helical segments 30 and 40 connect each cylindrical element 100 to an adjacent cylindrical element 100 to form the main body 11.

[0028] As is shown in FIGS. 2 and 3, the body of the stent 11 may comprise a plurality of main body cylindrical elements 100 formed from first circumferential segments 50 that are joined with second circumferential segments 60. The second circumferential segments 60 of each cylindrical element 100 may be joined with second circumferential segments 60 of adjacent cylindrical elements 100 to form a plurality of first helical segments 30 and 40 in the main body 11. (See FIG. 2). Each first circumferential segment 50 may have a circumferential dimension 55 and each second circumferential segments 60 may have a circumferential dimension 66' (See FIG. 3). In some embodiments, it may be desirable for the circumferential dimension 55 of the first expandable element 50 to be larger than the circumferential dimension 66' of the second expandable element 60.

[0029] The first circumferential segment 50 may be an expandable segment formed from plurality of segments joined together to form a pattern. The pattern, such as the one shown in the FIGS. 1-3, may be a repeating pattern that resembles a square wave form having curved peaks and valleys. Other patterns, both repeating and non-repeating, may be used. For example, and without limitation, the first circumferential segments 50 may resemble a triangle wave form, a sinusoidal wave form, other repetitious patterns, or any pattern that enables the segment to expand when a radial force is exerted on the stent from the inside or collapse radially when an external crimping force is applied.

[0030] The first circumferential elements 50 may have a filament width 420 (see FIG. 4). In one embodiment, the filament width may vary between 0.002 inches and 0.007 inches, but is preferably about 0.0050 inches. Other filament widths may be used depending on the parameters of the stent.

[0031] In the embodiment shown in FIGS. 1-5, the first circumferential elements 50 comprise linear portions 320 and curved portions 328 that join the linear portions 320 together to form a repeating pattern. In some, but not all, embodiments, the linear portion 320 may be parallel to the cylindrical axis of the stent. In other embodiments, the linear portion 320 lies at an angle of between 0-45 degrees with respect to the cylindrical axis. The first circumferential segment 50 has an amplitude 350 and a period 380. In one embodiment the amplitude may range from 0.5 mm to 2.0 mm and the period may range from 0.5 mm to 2.0 mm. In some embodiments, the amplitude is less than the period. Other amplitudes and periods may be used depending on the overall stent design and performance constraints.

[0032] The second circumferential element 60, which may be joined together in a helical pattern to form one or more

helical segments **30** or **40**, may also take numerous forms, in addition to the form shown in FIG. 6. In the embodiment shown in FIG. 6, the second circumferential element **60** comprises linear portions **412** and curved portions **414** having a filament width **407**, and resembles generally an S-shaped structure. In addition, the second element circumferential segment **60** may have an angled portion **417** attached to the linear portion **412** at an end opposite that of the curved portion **414**. The angled portion may be oriented to form an angle .alpha. relative to the cylindrical axis of the stent **5** in the range of 0-45 degrees. In at least one embodiment, the preferable angle .alpha. is about 10 degrees. In some embodiments, the linear portions **412** of the second circumferential element **60** lies at an angle .OMEGA. relative to the cylindrical axis of the stent, wherein .OMEGA. preferably ranges from 0 to 45 degrees. When viewed in a planar fashion as in FIG. 2, the linear portions **412** may, in some embodiments, form an angle .OMEGA., relative to the cylindrical axis of the stent. In some embodiments, .OMEGA. may be approximately equal to the helical angle of the first helical segments **30** and **40**. In one embodiment, the second circumferential elements **60** may have an amplitude **300** (see FIGS. 3, 4, and 6) ranging from 0.5 mm to 2.0 mm and a period **310** ranging from 0.5 mm to 2.0 mm. Other ranges may be used depending on the particular stent size and design being employed. In one embodiment, the preferred period is about 0.82 mm and the preferred length of the linear portion **412** is about 0.5 mm and the amplitude **300** is about 0.38 mm. The amplitude of the second circumferential element **60** may be greater than, equal to, or less than the amplitude of the first circumferential element **50**. In one embodiment, the circumferential contributions of the first circumferential elements **50** to the overall circumference of the main body **11** is greater than the circumferential contribution of the second circumferential element **60**, in terms of either circumferential length or circumferential cylindrical surface area. In one embodiment, the stent may have an overall outer surface area of about 0.029 square inches.

[0033] As is shown in FIG. 7, the stent may have a main body **11** comprised of two or more first helical segments **30** and **40**, as well as two or more second helical segments **200** and **210**. The first and second helical segments **30**, **40** and **200**, **210**, respectively, are joined together to form a generally cylindrically shaped body **11**. In some, but not all embodiments, the first and second helical segments may share a common connecting element **250**. In some embodiments, the common connecting element **250** may be H-shaped and the two generally parallel linear portions of the H-shaped connecting segment **250** may form an angle .delta. relative to the axis **5**. (See FIG. 6). .delta. may, in one embodiment, be about 14 degrees. As is shown in FIG. 7, the first helical segments **30** and **40** and second helical segments **200** and **210** may have different pitches, i.e. number of spirals per unit length, which results in the first and second helical segments as having different helical angles (.theta. and .beta., respectively) i.e. the angle of the helical segment relative to the cylindrical axis **5** of the stent. In one embodiment, the second helical segments **200** and **210** have a pitch approximately twice that of the first helical segments. In one embodiment .theta. may vary from 0 to 45 degrees and is preferably about 40 degrees and .beta. is preferably about twice .theta. In other embodiments the angle .theta. may range from 0 to 90 degrees to the circumference **110** of each cylindrical element **100**.

[0034] As is shown in FIGS. 2, 3, 4, and 6, the helical segments **30**, **40** are circumferentially expandable (i.e. they

expand along the circumference of the stent) and may be formed from a plurality of circumferential elements **60** that in turn are made up of linear **412** and/or curved **414** segments (see FIG. 6) that each have a filament width **407** (see FIG. 6) that is less than the circumferential dimension **66** of the circumferential element **60** (see FIG. 3). In some embodiments, each helical segment **30** or **40** will make a total contribution to the circumference of each cylindrical element **100** that is greater than the filament width **407**. The circumferential contribution of each helical segment **30** or **40** to the overall circumference of the stent (**110** in FIG. 1 or **105** in FIG. 11) may be greater than the circumferential contribution of the filament widths **407** of the segments (e.g. **412** and **414**) making up the circumferential elements **60** that in turn make up the helical segments. (I.e., in some embodiments the circumferential contribution of the helical segments **30** and **40** to the circumference **110** of each cylindrical element **100** is more than just a function of the filament width **407**, e.g., it may be a function of the geometry of the element **60**.) For the embodiment shown in FIGS. 1 and 11, this is the case when the stent is in both the unexpanded and expanded state. The geometry of the helical segments **30** and **40** are a factor in determining their expandability.

[0035] Likewise, the helical segments **200**, **210** are circumferentially expandable and may be comprised of other circumferential elements **50** that are in turn comprised of linear **320** and/or curved segments **328** (see FIGS. 3 and 5) that have a filament width **420** (see FIG. 4). The contribution of the helical segments **200**, **210** to the overall circumferential dimension **110** of each cylindrical element **100** is greater than just the contribution of the filament widths **420** of the individual segments **320** and **328** that make up the elements **50** that in turn make up the helical segments **200**, **210**. The geometry of the elements **50** making up the helical segments **200**, **210** may be a more important factor in determining the circumferential contribution of the helical segments **200** and **210** to the overall stent circumference than the filament width **420**. Thus, in one embodiment of the present invention, the circumference of the stent **110** in its unexpanded state and the circumference **105** when the stent is expanded are primarily functions of the geometry of the elements **50** and **60** that make up the helical segments **30**, **40** and **200**, **210**, respectively.

[0036] Some, but not all embodiments, of the present invention may employ endzones **10** and **20**. (See FIGS. 1, 2, and 11). Stents that employ endzones will generally have two endzone regions straddling a central zone in the middle of the stent. The stents may also have a transition region between the endzone and the central zone. The transition region serves to help smoothly transition between the expanded middle region and portions of the end of the stent that remain unexpanded after the stent is implanted. The size and characteristics of the transition region are a function of the material and geometry of the stent. For example, the transition range properties vary as a function of, among other things, the helical angle of the first helical segments, the number of curved segments located in the endzones, and the angle .epsilon. of the linear portions of the segments forming the endzones. (See e.g. FIG. 8).

[0037] The endzones **10** and **20** may take numerous forms. In some embodiments, the endzones may be comprised of one or more rings **17**. (See FIG. 8). The rings **17** may be generally cylindrically shaped, and in some embodiments, right cylindrically shaped. In one embodiment, the rings are formed from linear segments **28** joined together by curved segments **29** to form a pattern. The pattern, which is preferably—but

not necessarily—a repeating pattern may take numerous forms, including the one shown. The endzones **10** and **20** may be comprised of a plurality of rings **17** attached together. Struts **15** may be used to attach the rings together to form the endzone and to attach the endzone to the main body **11**. The struts, in some embodiments, act as cantilever springs and their stiffness, which is a function of their width and thickness, may define bending properties of the stent along its cylindrical axis **5**.

[0038] In the embodiment shown in FIGS. **1**, **7**, **8**, and **9**, which is exemplary only, the linear segments **28** in the endzone **10**, are oriented at an angle ϵ relative to the cylindrical axis of the stent. In one embodiment, the angle ϵ is greater than 0 degrees. In another embodiment, ϵ may range from 0 to 45 degrees and in still another embodiment is preferably about 10 degrees. The segments of the endzone may have a filament width **13** of between 0.002 and 0.007 inches. In one embodiment, the repeating pattern of the endzone has a period **2** of about 0.027 inches and an amplitude **21** of about 0.043 inches. Other values may be used. As is shown in FIG. **1**, the struts **15**, which are but one way to attach the endzones **10** and **20** to the main body **11**, may, in one embodiment have a width of between 0.002 inches and 0.08 inches and preferably the width does not exceed the wall thickness, which typically—but not necessarily ranges from about 0.002 to 0.008 inches.

[0039] The stent of the present invention may, after insertion into a vessel, be expanded such that it plastically deforms from the unexpanded state to an expanded state having a diameter increase of about 400 to 500%, which results in a larger circumference **105**. (See FIG. **11**). FIG. **11** depicts the stent shown in FIG. **1** in an expanded state. Upon expansion the stent's outer diameter in one particular embodiment increases from 1.0 mm to 3.00 mm and maintains a stent-to-vessel ratio in the expanded state that is greater than on average 16%.

[0040] While endzones **10** and **20** may be used to provide square edge, not all stents according to the present invention require endzones. FIGS. **12-15** depict an endzoneless stent. Like the stent shown in FIG. **19**, the stent of FIGS. **12-15** comprises a plurality of adjacent cylindrical elements **100**. The cylindrical elements **100** are formed from a plurality of first circumferential elements **50'** and second circumferential elements **60**. The first circumferential elements **50'** of the stent in FIGS. **12-15** are substantially identical to the second circumferential element **60** except that they are rotated to have a different orientation. The circumferential elements may be generally S-shaped having a linear portion **412**, a curved portion **414** having a radius **R**, and an angled portion **417**. **R** may vary widely depending on overall stent characteristics and in one embodiment varies between 0.001 and 0.02 inches and is preferably about 0.0083 inches. The angled portion **417** is spaced a distance **499** from the linear portion. In one particular embodiment, the distance **499** may vary from 0.002 to 0.020 inches and is preferably about 0.007 inches. The filament width **407** of the elements may, in one embodiment, be about 0.13 mm. The circumferential elements depicted in FIG. **14** and the expansion elements depicted in FIG. **15** are positioned about the cylindrical axis **5** as defined by angle **K** and may be generally S-shaped having a linear portion **412**, a curved portion **414** having a radius **R**, and an angled portion **417**. The angle **K** may vary widely depending on overall stent characteristics and range of radial compression or expansion about the axis **5**.

[0041] Adjacent cylindrical elements **100** are joined together by connecting first circumferential elements **50'** in each cylindrical element **100** with first circumferential elements **50'** in an adjacent cylindrical element **100**, such that the first circumferential elements **50'** in adjacent cylindrical elements **100** form helices through the stent and such that second circumferential elements form helices through the stent having an angle θ relative to the axis **5**. In some embodiments, a connecting segment **250** (see FIG. **7**) is used to connect first circumferential elements in adjacent cylindrical elements **100** and to connect second circumferential elements **60** in adjacent cylindrical elements **100**. In addition, the connecting segment, connects first circumferential elements **50'** in each cylindrical element **100** with two second circumferential elements **60** in each cylindrical element **100**. In one embodiment, the individual cylindrical elements **100** are adjacent to each other and are located a distance **666** apart. In one embodiment, the preferred may range between 0.002 and 0.020 inches, and is preferably about 0.009 inches.

[0042] The above description of the stent of the present invention is illustrative and not exhaustive. Various modifications may be made to the stent to change its overall characteristics without deviating from the scope and spirit of the invention as defined by the claims. For example and without limitation, the increasing the length of the linear segments and or increasing the arc of the second circumferential elements **60** will decrease the amount of radial force required to expand each circular section and will increase flexibility. Increasing the angle Ω of the second circumferential element **60** will: (i) increase the amount of radial force required for expansion, (ii) increase surface area, and (iii) decrease flexibility. Likewise, various modifications may be made to the struts **15**. (See FIG. **2**). Increasing strut width and wall thickness will: (i) increase surface area, (ii) increase radial strength, (iii) increase pressure required to expand the stent radially, (iv) decrease flexibility, and, in the case of increased wall thickness, (v) increase radiopacity.

[0043] The stent of the present invention may be manufactured in numerous ways. The stent may be formed from a metallic tube by removing various portions of the tube's wall to form the patterns described herein. The resulting stent will thus be formed from a single contiguous piece of material, eliminating the need for connecting various segments together. Material from the tube wall may be removed using various techniques including laser (YAG laser for example), electrical discharge, chemical etching, metal cutting, a combination of these techniques, or other well known techniques. See e.g. U.S. Pat. No. 5,879,381 to Moriuchi et al. and U.S. Pat. No. 6,117,165 to Becker, which are hereby incorporated in their entirety by reference. Forming stents in this manner allows for creation of a substantially stress-free structure where the helical segments are integral with the circumferential elements. In one embodiment, the tube from which the stent is formed may have an internal diameter of about 3.0 mm, a wall thickness of about 1.0 mm and a length of about 30 mm. Tubes having other dimensions may be used. In particular, the length may be adapted to that of the diseased part of the lumen in which the stent is to be placed. This may avoid using separate stents to cover the total diseased area.

[0044] Those skilled in the art will recognize that the stent and manufacturing method described above are illustrative and not exhaustive of the present invention and that modifi-

cations and variations may be made without deviating from the scope and spirit of the invention as defined by the following claims.

What is claimed is:

1. An expandable stent comprising:
 - a main body formed from a plurality of expandable helical segments that comprise expandable circumferential segments each having a single substantially S-shaped portion and substantially H-shaped connecting segments set at an angle with respect to a main body cylindrical axis; and
 - a plurality of main body cylindrical elements formed from a plurality of circumferential segments joined together by the H-shaped connecting segments, the main body cylindrical elements being adjacent to one another and being attached to one another by the H-shaped connecting-segments.
2. The expandable stent of claim 1, wherein the stent is in an unexpanded state.
3. The expandable stent of claim 1, wherein the stent is in an expanded state.
4. The expandable stent of claim 1, wherein the angle is at least about 14 degrees.
5. The expandable stent of claim 1, wherein the angle is less than about 90 degrees and greater than 0 degrees.
6. The expandable stent of claim 1, wherein each substantially S-shaped portion comprises at least one linear portion.
7. The expandable stent of claim 6, wherein the linear portion is set at a second angle with respect to the main body cylindrical axis.
8. The expandable stent of claim 7, wherein the second angle ranges from 0 degrees to about 45 degrees.
9. An expandable stent comprising:
 - a main body formed from a plurality of expandable helical segments that comprise expandable circumferential segments each having a single substantially S-shaped portion comprising at least one linear portion, wherein the linear portion is set at an angle with respect to a main body cylindrical axis; and
 - a plurality of main body cylindrical elements formed from a plurality of circumferential segments joined together by substantially H-shaped connecting segments, the main body cylindrical elements being adjacent to one

another and being attached to one another by the H-shaped connecting-segments.

10. The expandable stent of claim 9, wherein the substantially H-shaped connecting segments is set at a second angle with respect to the main body cylindrical axis.

11. The expandable stent of claim 10, wherein the second angle is at least about 14 degrees.

12. The expandable stent of claim 9, wherein the angle of the linear portion ranges from greater than 0 degrees to about 45 degrees.

13. An expandable stent comprising:

- a main body formed from a plurality of expandable helical segments that comprise expandable circumferential segments each having a circumferential element comprising at least one linear portion and substantially H-shaped connecting segments set at a first angle with respect to a main body cylindrical axis; and

- a plurality of main body cylindrical elements formed from a plurality of circumferential segments joined together by the H-shaped connecting segments, the main body cylindrical elements being adjacent to one another and being attached to one another by the H-shaped connecting-segments.

14. The expandable stent of claim 13, wherein the first angle is at least about 14 degrees.

15. The expandable stent of claim 13, wherein the first angle is less than about 90 degrees and greater than 0 degrees.

16. The expandable stent of claim 13, wherein the linear portion of the circumferential element is set at a second angle with respect to the main body cylindrical axis.

17. The expandable stent of claim 16, wherein the second angle ranges from 0 degrees to about 45 degrees.

18. The expandable stent of claim 13, wherein the circumferential element comprises at least three linear portions set at a second, third and fourth angle, respectively, relative to the main body cylindrical axis wherein at least two of the angles are equal.

19. The expandable stent of claim 18, wherein the second, third and fourth angles range from 0 to about 45 degrees with respect to the main body cylindrical axis.

20. The expandable stent of claim 13, wherein the stent is in an expanded state.

* * * * *