

(11) (21) (C) **2,023,432**
(22) 1990/08/16
(43) 1991/02/22
(45) 2000/02/01

(72) Ikeda, Yoshiyuki, JP
(72) Inoue, Atsuo, JP
(72) Tanabe, Yoshio, JP
(73) Nippon Kayaku Kabushiki Kaisha, JP
(51) Int.Cl.⁵ C06B 45/02
(30) 1989/08/21 (01-212899) JP
(54) **EXPLOSIF A EMULSION EAU DANS L'HUILE**
(54) **WATER-IN-OIL TYPE EMULSION EXPLOSIVE**

(57) This invention relates to a water-in-oil type emulsion explosive comprising an aqueous oxidizer solution, an oily material, an emulsifier and hollow microspheres, in which the whole or a part of the oily material is replaced with a polymer which is oil-soluble and has a ladder structure in the molecule. Preferably, the polymer is one obtained by polymerizing cyclopentadiene, dicyclopentadiene or methylocyclopentadiene.

ABSTRACT

This invention relates to a water-in-oil type emulsion explosive comprising an aqueous oxidizer solution, an oily material, an emulsifier and hollow microspheres, in which the whole or a part of the oily material is replaced with a polymer which is oil-soluble and has a ladder structure in the molecule. Preferably, the polymer is one obtained by polymerizing cyclopentadiene, dicyclopentadiene or methylcyclopentadiene.

1 BACKGROUND OF THE INVENTION

The present invention relates to a water-in-oil (W/O) type emulsion explosive which can be used for the industrial blasting for various purposes such as, for example, excavation of tunnels, quarrying and mining.

Many improvements and inventions have been made regarding the W/O type emulsion explosives ever since this type of explosive was disclosed for the first time in U.S. Patent No. 3,161,551. The W/O type emulsion explosives in these inventions are basically of the composition comprising a mineral oil, wax or other hydrophobic carbonaceous fuel (oil) as continuous phase, an aqueous solution of oxidizers mainly composed of ammonium nitrate as discontinuous phase, and a W/O type emulsifier. By properly adding a sensitizer such as hollow microspheres to the composition, there can be obtained the W/O type emulsion explosive of various level of initiating sensitivity ranging from booster initiation to cap initiation. As is well known, these W/O type emulsion explosives, because of use of oily material as continuous phase, are excellent in water resistance and safety in comparison with the conventional explosives.

The W/O type emulsion explosives have the problem that they lack stability since the emulsion is formed by mixing two mutually, insoluble liquids into a

1 homogeneous liquid mixture comprising fine droplets of one
liquid in the other liquid with the aid of an emulsifier.
Many inventions purposed to improve stability of this type
of emulsion explosives have been made. A method for
5 improving stability is to use a specific emulsifier as for
instance proposed in Japanese Patent Application Laid-Open
(Kokai) Nos. 58-120588 (1983) and 58-190890 (1983) and
U.S. Patent Nos. 4,482,403 and 4,698,105. Use of a
specific oil is another method for improving stability of
10 said emulsion explosives, as for instance proposed in
Japanese Patent Application Laid-Open (Kokai) Nos.
57-149893 (1982), 61-40892 (1986) and 61-40893 (1986) and
U.S. Patent Nos. 4,386,977, 4,548,660 and 4,470,855.

Stability of the W/O type emulsion explosives
15 was greatly improved by these inventions, and this type of
explosives has come to be used widely. However, the W/O
type emulsion explosives still have the problem that the
sensitivity lowers with the lapse of time, and some of
those W/O type emulsion explosives which have been kept in
20 storage for 2 to 3 years fail to detonate in the hole due
to insufficient sensitivity.

SUMMARY OF THE INVENTION

The present invention provides a water-in-oil
type emulsion explosive comprising an aqueous oxidizer
25 solution, an oily material, an emulsifier and hollow
microspheres, in which the whole or a part of the oily
material is replaced with a polymer which is oil-soluble

1 and has a ladder structure in the molecule.

DETAILED DESCRIPTION OF THE INVENTION

As a result of elaborate studies on change of stability with time of W/O type emulsion explosives, the present inventors have found that at the summer season, namely at the times when the temperature is high, there takes place lowering of sensitivity of the explosives, but at the spring, fall and winter seasons, namely at the times when the temperature is not so high, there occurs no reduction of sensitivity of said explosives. This fact directed the present inventors to the effort for obtaining a W/O type emulsion explosive which is stable at high temperatures such as experienced in the summer season.

Under this concept, the present inventors have carried out many researches and experiments and, as a result, found that when the whole or a part of the oily material forming the continuous phase of W/O type emulsion explosive is replaced with a polymer which is oil-soluble and has a ladder structure in the molecule, there can be obtained a W/O type emulsion explosive which is stable for a long time even under high temperatures.

The polymer used in the present invention is the one which is oil-soluble and has, in its molecule, a ladder structure such as described in Encyclopaedia of Polymer Science and Technology, Vol. 8, published by Inter-Science Publisher Co., Ltd. It is notable that an especially good result can be obtained when using said

1 type of polymers having a softening point of 0 to 150°C
and a number average molecular weight of 50 to 2,000.


This type polymer is prepared by using, as
starting material, cyclopentadiene, dicyclopentadiene or
5 methylcyclopentadiene etc.

A preferred result can be obtained when using
this type of polymer prepared by using, as starting
material, a dicyclopentadiene having, for


example, a chemical structure of , namely a

10 polymer or copolymer of dicyclopentadiene.

Examples of this type of polymer (being oil-
soluble and having a ladder structure in the molecule)
usable in the present invention are: Escorez® 5380 (a
hydrogenated alicyclic hydrocarbon resin having a soften-
15 ing point of 85°C and a specific gravity (25/4 deg.C) of
1.10, sold by Tonex Co., Ltd.); Escorez® 5300 (a hydro-
genated alicyclic hydrocarbon resin having a softening
point of 105°C, a specific gravity (25/4 deg.C) of 1.10
and a number average molecular weight of about 290);
20 Escorez® 5320 (a hydrogenated alicyclic hydrocarbon resin
having a softening point of 125°C, a specific gravity
(25/4 deg.C) of 1.10 and a number average molecular weight
of about 340), and believed to have the following ladder
structure as a basic structure:



- 1 Escorez® 8180 (an alicyclic hydrocarbon resin having a softening point of 86°C, a specific gravity (25/4 deg.C) of 1.10 and a number average molecular weight of about 200) believed to have the following ladder structure as a
5 basic structure:



- Escorez® 1401 (aliphatic/alicyclic hydrocarbon resin having a softening point of 119°C, a specific gravity (25/4 deg.C) of 0.97 and a number average molecular weight of about 1,000), ECR 327® (an alicyclic hydrocarbon resin
10 having a softening point of 15°C, a specific gravity (25/4 deg.C) of 1.10 and a number average molecular weight of

about 80) and ECR 356B® (an alicyclic hydrocarbon resin having a softening point of 140°C, a specific gravity (25/4 deg.C) of 1.10 and a number average molecular weight of about 390) having a basic ladder structure similar to those
5 shown above.

The publication (published February 1, 1989, by SEKIYU BUNKASHA, Japan) "JETI" (Japan Energy & Technology Intelligence) with the title "The Present Situation And
10 Hereafter Of Petroleum Resins Which Is Experiencing Increased Demand", pages 75-79, Vol.37, No. 2, (1989) proposes two other structural formulae of DCPD-type (dicyclopentadiene-type) petroleum resins:

15 Fig. 4 Estimated structural formula of DCPD-type petroleum resin (page 77)





Fig. 5 Estimated structural formula of hydrogenated petroleum resin (page 78)



The types of polymer used in the present invention can replace the whole or a part of the oily material in the W/O type emulsion explosive composition. Said polymer can be used in admixture with an oil component such as mineral
5 oil, vegetable oil, animal oil, fuel oil, kerosine, liquid paraffin, paraffin wax, microcrystalline wax, petrolatum and the like. The polymers can be also used in combination with other types of resin such as petroleum resin, epoxy resin, unsaturated polyester resin, polybutene,
10 polyisobutylene, butadiene resin, α -olefin polymer and the like.

For maintaining sensitivity of W/O type emulsion explosives stably at high temperatures, preferably 1% by weight or
15 more, more preferably 5 to 70% by weight of the oily material constituting the continuous phase in the explosive is replaced with the polymer being oil-soluble and having a ladder structure in the molecule.

20 In the explosives according to the present invention, the oily material is used in an amount preferably in the range of 1 to 10% by weight based on the total weight of the W/O type emulsion explosive. It is more preferable to constitute the continuous phase by using the oily material
25 in an amount in the range of 2 to

1 8% by weight.

An aqueous oxidizer solution used in the present invention can be prepared by dissolving one or a mixture of two or more of the following substances in water:

5 ammonium nitrate, alkali metal nitrates, alkaline earth metal nitrates, alkali metal chlorates, alkaline earth metal chlorates, alkali metal perchlorates, alkaline earth metal perchlorates and ammonium perchlorate.

In the aqueous oxidizer solution used in the present invention, there may be added a water-soluble amine nitrate such as monomethylamine nitrate, monoethylamine nitrate, hydrazine nitrate and dimethylamine dinitrate, a water-soluble alkanolamine nitrate such as methanolamine nitrate and ethanolamine nitrate, water-soluble ethylene glycol mononitrate or the like as an auxiliary sensitizer.

The water content in the aqueous oxidizer solution is preferably so selected that the crystallization temperature of said aqueous solution will become 30 to 90°C. Usually it is preferable that the water content is in the range of 5 to 40% by weight, more preferably 7 to 30% by weight, based on said aqueous oxidizer solution.

In the aqueous oxidizer solution, it is possible to add a water-soluble organic solvent such as methyl alcohol, ethyl alcohol, formamide, ethylene glycol, glycerin and the like as an auxiliary solvent for lowering the crystallization temperature of the solution.

In the present invention, the aqueous oxidizer

1 solution is used in an amount within the range of 50 to
95% by weight based on the total amount of W/O type
emulsion explosive.

The emulsifier used in the present invention is
5 of the type which is usually used for forming W/O type
emulsions. Examples of such emulsifier are alkali metal
stearates, ammonium stearate, calcium stearate, polyoxy-
ethylene ethers, sorbitan esters of a fatty acid, sorbitol
esters of a fatty acid and the like. These compounds may
10 be used either singly or in a suitable mixture.

The amount of the emulsifier used in the present
invention is preferably in the range of 0.5 to 7% by
weight based on the total weight of the W/O type emulsion
explosive.

15 In accordance with the present invention, there
can be obtained the W/O type emulsion explosives showing an
initiating sensitivity of a broad range from cap initiation
to booster initiation, by adding appropriate hollow micro-
spheres in the W/O type emulsion explosive. As the hollow
20 microspheres, there can be used hollow glass microspheres,
resin-made hollow microspheres, silastic balloon, perlite
and the like either singly or in combination.

The amount of the hollow microspheres used in
the present invention is so selected that the specific
25 gravity of the final product of the W/O type emulsion
explosive will become not higher than 1.40 g/cc,
preferably not higher than 1.30 g/cc. The amount of the
hollow microspheres used is variable according to the

1 specific gravity of the microspheres and other factors,
but usually used in an amount in the range of 0.5 to 20%
by weight based on the total weight of the W/O type
emulsion explosive.

5 In the W/O type emulsion explosives according to
the present invention, an explosive substance such as TNT,
penthrit and the like may be contained together with the
hollow microspheres. It is also possible to make the
bubbles contained in the W/O type emulsion explosive by
10 mechanical or chemical means to substitute a part of the
role of the hollow microspheres.

It is further possible to add a metal powder
such as aluminum and magnesium powder, or an organic
powder such as wood powder and starch in the W/O type
15 emulsion explosive according to this invention.

The W/O type emulsion explosive according to the
present invention is produced, for example, in the
following manner.

Ammonium nitrate or a mixture thereof with one
20 or more other oxidizer salts is dissolved in water at
about 85 to 95°C to prepare an aqueous oxidizer solution.
Meantime, an oil-soluble polymer having a ladder structure
in the molecule or a mixture of such a polymer and an oil
substance or resin are sufficiently and uniformly
25 dissolved at about 85 to 95°C, and an emulsifier is mixed
therein to form an oil-phase mixture. To this oil-phase
mixture is gradually added the previously prepared aqueous
oxidizer solution while stirring the mixture at a speed of

1 200 to 500 r.p.m. by using a spiral blade agitator which
is usually used for stirring highly viscous materials.
After the completion of the addition, stirring is further
continued at the same speed for one minute, followed by
5 additional two-minute stirring at a raised speed of 800 to
1,300 r.p.m. The resulting emulsion is added with the
hollow microspheres and if necessary other additive(s) and
mixed by a vertical kneader at a mixing speed of about 30
to 60 r.p.m. for 5 minutes to obtain a W/O type emulsion
10 explosive of the present invention.

In the present invention, the whole or a part of
the oily component constituting the continuous phase of a
W/O type emulsion explosive is replaced with a polymer
which is oil-soluble and has a ladder structure in the
15 molecular as described above, thereby giving a W/O type
emulsion explosive which is remarkably minimized in
lowering of sensitivity at high temperatures, that is,
very excellent in storage stability in comparison with the
conventional W/O type emulsion explosives.

20 The present invention will be described in
further detail below by showing the examples thereof.

Example 1

1.5% by weight of an oil-soluble aliphatic/
alicyclic hydrocarbon resin having a ladder structure in
25 the molecule [Escorez, 1401 (trade name) sold by Tonex
Co., Ltd.], which has been obtained by copolymerizing
dicyclopentadiene and C₅ petroleum fraction and has a

1 number average molecular weight of about 1,000 and a
softening point of 119°C, and 1.0% by weight of liquid
paraffin (reagent) were well mixed under heating at about
90°C. To this mixture were added 4.5% by weight of
5 sorbitol dioleate as emulsifier and an aqueous oxidizer
solution prepared by dissolving 62.8% by weight of
ammonium nitrate and 10.0% by weight of sodium nitrate in
14% by weight of water by heating at about 90°C, followed
by sufficient mixing by stirring to form a W/O type
10 emulsion. To this emulsion were added and mixed 6.2% by
weight of glass bubbles [B28/750 (trade name) produced by
3M Co., Ltd.], to obtain a W/O type emulsion explosive.
The obtained W/O type emulsion explosive was packed in the
25 mm-diameter paper tubes (100 g of explosive in each
15 paper tube) to form the cartridges.

Comparative Example 1

In the same way and with the same composition as
Example 1 except for use of 1.5% by weight of a micro-
crystalline wax (Eslux[®] 172 produced by Esso Standard Oil)
20 in place of the polymer used in Example 1, there were
produced a W/O type emulsion explosive and cartridges
thereof.


Example 2

0.3% by weight of an oil-soluble alicyclic
25 hydrocarbon resin having a ladder structure in the
molecule (Escorez[®] 8180 sold by Tonex Co., Ltd.), which has

1 been produced by polymerizing dicyclopentadiene and has a
 number average molecular weight of about 200 and a
 softening point of about 86°C, and 3.2% by weight of a
 microcrystalline wax (Eslux[®] 172) were mixed well under
 5 heating at about 90°C. To this mixture were added 2.0% by
 weight of sorbitan monooleate as emulsifier and an aqueous
 oxidizer solution previously prepared by dissolving 56.5%
 by weight of ammonium nitrate, 15.0% by weight of sodium
 nitrate and 10.0% by weight of hydrazine nitrate in 8% by
 10 weight of water by heating at about 100°C, followed by
 sufficient mixing with stirring to form a W/O type
 emulsion. To this emulsion were added and mixed 2.0% by
 weight of glass bubbles [B28/750 (trade name) produced by
 3M Co., Ltd.] and 3.0% by weight of perlite to obtain a
 15 W/O type emulsion explosive. The obtained explosive was
 packed in the 25 mm-diameter paper tubes (100 g of
 explosive in each paper tube) to form the cartridges.

Comparative Example 2

A W/O type emulsion explosive and cartridges
 20 thereof were produced by following the same procedure as
 Example 2 except that an alicyclic hydrocarbon resin
 having the basic structure of



with no ladder structure in the molecule [Arkon P-70[®]
 (trade name) produced by Arakawa Chemical Industries Co.,
 25 Ltd.] was used in an amount of 0.3% by weight in place of

1 the polymer used in Example 2.

Example 3

3.2% by weight of an oil-soluble hydrogenated alicyclic hydrocarbon resin having a ladder structure in the molecule [Escorez® 5300 (trade name) sold by Tonex Co., Ltd.], which has been obtained by polymerizing and hydrogenating dicyclopentadiene and has a number average molecular weight of about 290 and a softening point of about 105°C, was melted under heating at about 115°C. To this molten resin were added 2.7% by weight of sorbitol dioleate as emulsifier and an aqueous oxidizer solution previously prepared by dissolving 71.4% by weight of ammonium nitrate and 7.5% by weight of sodium nitrate in 11% by weight of water by heating at about 90°C, followed by sufficient mixing with stirring to form a W/O type emulsion. To this emulsion were added 4.2% by weight of glass bubbles [B28/750 (trade name) produced by 3M Co., Ltd.] to obtain a W/O type emulsion explosive. The obtained explosive was packed in the 25 mm-diameter paper tubes (100 g of explosive in each paper tube) to form the cartridges.

Comparative Example 3

A W/O type emulsion explosive and cartridges thereof were produced by following the same procedure as Example 3 except that 3.2% by weight of a petroleum resin

1 [Hi-rez C-110X[®] (trade name) produced by Mitsui
Petrochemical Co., Ltd.] obtained by polymerizing a C₅
petroleum fraction was used in place of the polymer used
in Example 3.

5 Example 4

1.0% by weight of an oil-soluble alicyclic
hydrocarbon resin having a ladder structure in the
molecule [Escorez ECR[®] 327 (trade name) sold by Tonex Co.,
Ltd.], produced by polymerizing dicyclopentadiene and
10 having a number average molecular weight of about 80 and a
softening point of about 15°C, 1.0% by weight of a
paraffin wax having a melting point of 146°F [145°
Paraffin (trade name) produced by Nippon Sekiyu KK] and
1.0% by weight of a petroleum resin (C-110X) were mixed
15 well under heating at about 90°C. To this mixture were
added 0.7% by weight of sorbitan monooleate and 0.5% by
weight of sorbitol dioleate as emulsifier and an aqueous
oxidizer solution previously prepared by dissolving 71.1%
by weight of ammonium nitrate and 7.5% by weight of sodium
20 nitrate in 12% by weight of water by heating at about
90°C, followed by sufficient mixing with stirring to form
a W/O type emulsion. To this emulsion were mixed 5.2% by
weight of glass bubbles (B28/750) to obtain a W/O type
emulsion explosive. The obtained explosive was packed in
25 the 25 mm-diameter paper tubes (100 g of explosive in each
paper tube) to form the cartridges.

1 Comparative Example 4

A W/O type emulsion explosive and cartridges thereof were produced by following the same procedure as Example 4 except that 1.0% by weight of Arkon P-70 used in
5 Comparative Example 2 was employed in place of the polymer used in Example 4.

Example 5

0.9% by weight of an oil-soluble alicyclic hydrocarbon resin having a ladder structure in the
10 molecule [Escorez 530 (trade name) sold by Tonex Co., Ltd.] which has been prepared by polymerizing dicyclopentadiene and has a number average molecular weight of about 290 and a softening point of about 105°C, and 2.1% by weight of a microcrystalline wax (Eslux 172) were mixed
15 well under heating at about 90°C. To this mixture were added 3.1% by weight of sorbitol dioleate as emulsifier and an aqueous oxidizer solution previously prepared by dissolving 73.4% by weight of ammonium nitrate and 6.0% by weight of sodium nitrate in 10% by weight of water by
20 heating at about 100°C, followed by sufficient mixing with stirring to form a W/O type emulsion. Then 4.5% by weight of glass bubbles (B28/750) were added to and mixed in the emulsion to obtain a W/O type emulsion explosive. The
obtained explosive was packed in the 25 mm-diameter paper
25 tubes (100 g of explosive in each paper tube) to form the cartridges.

1 Comparative Example 5

A W/O type emulsion explosive and cartridges thereof were produced by following the same procedure as Example 5 except that Arkon P-70 used in Comparative Example 2 was used in an amount of 0.9% by weight in place of the polymer used in Example 5.

The compositions of the W/O type emulsion explosives obtained in Examples 1-5 and Comparative Examples 1-5 are shown collectively in Table 1.

10 Test Example

The emulsion explosive cartridges of Examples 1-5 and Comparative Examples 1-5 were kept in a high-temperature (45°C) thermostat. The cartridges were taken out of the thermostat every one month and subjected to an initiation test by using No. 6 and No. 8 caps. The test results are shown in Table 2.

Table 1

	Example					Comparative Example				
	1	2	3	4	5	1	2	3	4	5
Escorez 1401	1.5									
Escorez 8180		0.3								
Escorez ECR327				1.0						
Escorez 5300			3.2		0.9					
Liquid paraffin	1.0					1.0				
145° Paraffin				1.0					1.0	
Eslux 172		3.2			2.1	1.5	3.2			2.1
C-110X				1.0				3.2	1.0	
Arkon/P-70							0.3		1.0	0.9
Water	14.0	8.0	11.0	12.0	10.0	14.0	8.0	11.0	12.0	10.0
Ammonium nitrate	62.8	56.5	71.4	71.1	73.4	62.8	56.5	71.4	71.1	73.4
Sodium nitrate	10.0	15.0	7.5	7.5	6.0	10.0	15.0	7.5	7.5	6.0
Hydrazine nitrate		10.0					10.0			

- cont'd -

Table 1 (cont'd)

Sorbitan monooleate		2.0		0.7			2.0		0.7	
Sorbitol dioleate	4.5		2.7	0.5	3.1	4.5		2.7	0.5	3.1
B28/750	6.2	2.0	4.2	5.2	4.5	6.2	2.0	4.2	5.2	4.5
Perlite		3.0					3.0			

Table 2

	Examples				
	1	2	3	4	5
Specific gravity	1.10	1.21	1.18	1.14	1.16
Just after Preparation	Detonated with No. 6 cap	Detonated with No. 6 cap	Detonated with No. 6 cap	Detonated with No. 6 cap	Detonated with No. 6 cap
After one months	"	"	"	"	"
After 2 months	"	"	"	"	"

- cont'd -

Table 2 (cont'd)

After 3 months	"	"	"	"	"	"
After 4 months	Failed with No. 6 cap Detonated with No. 8 cap	"	"	"	"	"
After 5 months	Failed with No. 8 cap	Failed with No. 6 cap Detonated with No. 8 cap	"	"	"	"
After 6 months	-	Failed with No. 8 cap	Failed with No. 6 cap Detonated with No. 8 cap	Failed with No. 6 cap Detonated with No. 8 cap	"	"

- cont'd -

A

Table 2 (cont'd)

After 7 months	-	-	Failed with No. 8 cap	Failed with No. 8 cap	Failed with No. 6 cap Detonated with No. 8 cap
After 8 months	-	-	-	-	Failed with No. 8 cap

Table 2 (cont'd)

Comparative Examples				
1	2	3	4	5
1.11	1.20	1.18	1.14	1.15
Failed with No. 6 cap	Failed with No. 6 cap	Failed with No. 6 cap	Failed with No. 6 cap	Failed with No. 6 cap
Failed with No. 6 cap Detonated with No. 8 cap	"	"	"	"
Failed with No. 8 cap	Failed with No. 6 cap Detonated with No. 8 cap	"	"	"

- cont'd -

Table 2 (cont'd)

-	Failed with No. 8 cap	"	Failed with No. 6 cap Detonated with No. 8 cap	"
-	-	Failed with No. 6 cap Detonated with No. 8 cap	Failed with No. 8 cap	Failed with No. 6 cap Detonated with No. 8 cap
-	-	Failed with No. 8 cap	-	Failed with No. 8 cap
-	-	-	-	-

- cont'd -



Table 2 (cont'd)

I	I
I	I
I	I
I	I
I	I

1 From comparison of the Examples with the
corresponding Comparative Examples (such as Example 1 and
Comparative Example 1) by the results shown in Table 1, it
is clearly seen that the explosives according to the
5 Examples of this invention are noticeably prolonged in the
storage period until the explosives loses its No. 8 cap
sensitivity due to lowering of sensitivity in comparison
with the explosives of the Comparative Examples.

 It is evident that the W/O type emulsion
10 explosives according to the Examples of this invention are
very stable even at high temperatures.

The embodiments of the invention in which an exclusive property or privilege is claimed are defined as follows:

1. A water-in-oil emulsion explosive comprising 50 to 95% by weight of an aqueous oxidizer solution, 1 to 10% by weight of a polymer, 0.5 to 7% by weight of an emulsifier and 0.5 to 20% by weight of hollow microspheres of said water-in-oil type emulsion explosive, wherein the polymer is one obtained by polymerizing cyclopentadiene, dicyclopentadiene or methylcyclopentadiene, or its hydrogenated product, and is one which is oil-soluble and has a ladder structure as a basic structure in the molecule, has a number average molecular weight of 50-2000, and has a softening point of 0-150°C.

2. A water-in-oil type emulsion explosive according to claim 1, wherein the polymer or its hydrogenated product is obtained by polymerizing dicyclopentadiene.

3. A water-in-oil type emulsion explosive according to claim 2, wherein the polymer or its hydrogenated product has one of the following ladder molecular structures as a basic structure: