



(86) Date de dépôt PCT/PCT Filing Date: 1995/02/27
 (87) Date publication PCT/PCT Publication Date: 1995/09/21
 (45) Date de délivrance/Issue Date: 2009/05/05
 (85) Entrée phase nationale/National Entry: 1996/09/12
 (86) N° demande PCT/PCT Application No.: US 1995/002350
 (87) N° publication PCT/PCT Publication No.: 1995/024873
 (30) Priorité/Priority: 1994/03/14 (US08/213,754)

(51) Cl.Int./Int.Cl. *C12N 5/06* (2006.01),
A61K 35/34 (2006.01), *A61L 27/36* (2006.01),
A61L 27/38 (2006.01), *C12N 5/08* (2006.01),
A61F 2/24 (2006.01), *A61F 2/06* (2006.01)
 (72) Inventeur/Inventor:
 GOLDSTEIN, STEVEN, US
 (73) Propriétaire/Owner:
 CRYOLIFE, INC., US
 (74) Agent: SMART & BIGGAR

(54) Titre : TISSU TRAITE POUR UNE IMPLANTATION ET PROCEDES POUR SA PREPARATION
 (54) Title: TREATED TISSUE FOR IMPLANTATION AND PREPARATION METHODS

(57) **Abrégé/Abstract:**

This disclosure includes a method for generating a functional hybrid bioprosthesis. Tissue formed naturally of interstitial collagens is treated to kill native cells and remove potentially immunologically active soluble molecules. Then it may be treated sequentially with extracellular matrix adhesion factor, extracellular matrix glycosaminoglycan, and growth factor appropriate to the cell type required to function within the matrix, and incubating the transplant tissue matrix with cells that are either allogeneic or autologous for the recipient thereby imparting to the matrix the characteristics of the cell type and tissue selected. Tissues with a variety of functional bioactivities can thus be formed in vitro prior to graft transplantation or implantation which will exhibit reduced or no stimulation of an immunological response in the recipient.



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61F 2/24	A1	(11) International Publication Number: WO 95/24873 (43) International Publication Date: 21 September 1995 (21.09.95)
(21) International Application Number: PCT/US95/02350 (22) International Filing Date: 27 February 1995 (27.02.95) (30) Priority Data: 08/213,754 14 March 1994 (14.03.94) US (71) Applicant: CRYOLIFE, INC. [US/US]; Suite 142, 2211 New Market Parkway, Marietta, GA 30067 (US). (72) Inventor: GOLDSTEIN, Steven; 2939 Greenbrook Way, Atlanta, GA 30345 (US). (74) Agents: DeLUCIA, Richard, L. et al.; Kenyon & Kenyon, One Broadway, New York, NY 10004 (US).	(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG). <div style="text-align: center;"> 2185447 Published <i>With international search report.</i> </div>	
(54) Title: TREATED TISSUE FOR IMPLANTATION AND PREPARATION METHODS		
(57) Abstract This disclosure includes a method for generating a functional hybrid bioprosthesis. Tissue formed naturally of interstitial collagens is treated to kill native cells and remove potentially immunologically active soluble molecules. Then it may be treated sequentially with extracellular matrix adhesion factor, extracellular matrix glycosaminoglycan, and growth factor appropriate to the cell type required to function within the matrix, and incubating the transplant tissue matrix with cells that are either allogeneic or autologous for the recipient thereby imparting to the matrix the characteristics of the cell type and tissue selected. Tissues with a variety of functional bioactivities can thus be formed <i>in vitro</i> prior to graft transplantation or implantation which will exhibit reduced or no stimulation of an immunological response in the recipient.		

2185447

TREATED TISSUE FOR IMPLANTATION AND PREPARATION METHODS

BACKGROUND

5 Surgical heart valve replacement may involve
implantation of one of three distinct prosthesis types;
mechanical (synthetic), bioprosthetic (chemically-fixed
porcine valve or bovine pericardium), or human allograft.
These prostheses provide effective hemodynamic
improvement for replacement of native aortic valves that
10 are either congenitally malformed or have been damaged by
degenerative changes or disease resulting in either
aortic insufficiency or aortic stenosis. Of the
approximately 55,000 aortic valve implants annually in
the U.S., 75% are mechanical valves. The remainder of
15 the replacements are of transplanted tissues. Of these,
over 80% are porcine bioprostheses; the relatively small
number of allografts (2,500 per year) is primarily due to
their limited availability.

The criteria for an ideal prosthesis would
20 include natural hemodynamics, long-term durability, low
incidence of thromboembolic complications, freedom from
calcification, proven lack of immunogenicity and no
inappropriate hyperplastic responses following implanta-
tion. Even in autologous transplant situations, the
25 surgical handling of the tissue, such as vein grafts, may

itself be a stimulus for tissue hyperplasia and subsequent failure of the graft.

In accordance with this invention, heart valves, pulmonary and aortic, may be prepared having
5 advantageous properties with respect to wear, tendency to calcify, stimulation of immune responses, and reduced difficulty in acquisition. It is also applicable to other forms of tissues particularly those composed of structural interstitial collagens.

10 Various synthetic grafts and mechanical organs have been developed and are currently in use. However, these synthetic replacements are known to be subject to embolic complications or decreases in material strength over long periods of implantation. Although structural
15 modifications in mechanical prostheses such as heart valves have been improved with respect to their wear characteristics, they remain liable to valve malfunction, which may occur suddenly and without warning, resulting in emergency situations requiring surgical intervention
20 and replacement of the artificial prosthetic device. Because of the surface properties of synthetic/mechanical prostheses used in the vasculature, platelet adhesion increases the likelihood of thrombus formation and anticoagulant therapy must be provided for the life of
25 the implant and makes such implants undesirable for certain groups of potential recipients (for example, women of child-bearing years).

5 One alternative, bioprosthetic heart valves,
are prepared from valve tissues of porcine or bovine
origin. Because these are species discordant
immunologically from man, they are rapidly rejected by
the implant recipient despite the use of
immunosuppression drug therapy that would otherwise
maintain an allograft. Significantly, these tissues are
liable to hyperacute rejection by the recipient because
of the presence in the recipient of preformed natural
10 antibodies which recognize antigens on the surface of
foreign cells, particularly those of the endothelial
lining of heart valves and blood vessels. While bovine
or porcine valve tissues are structurally and
biomechanically appropriate for use in humans, the
15 potential of such foreign tissue to stimulate immune
rejection in the recipient has in the past dictated
treatments with chemical cross-linking agents such as
glutaraldehyde. Such treatment of the tissue reduces the
stimulation of an immunological response by the recipient
20 to the foreign tissue, and also stabilizes the collagen
protein of the resulting non-viable valve tissue making
it more resistant to degradation by proteolytic enzymes.
However, because these tissue grafts are non-viable,
there is no biosynthetic mechanism to repair structural
25 proteins broken down during the operation of the tissue
in the recipient. Such tissue grafts tend to calcify
with time, increasing the risk of structural damage and
consequential failure. While occurring with less

2185447

frequency relative to mechanical grafts, thromboembolism is also a patient management issue for recipients of these grafts.

5 Similarly, organs such as kidneys have been transplanted allogeneically from one sibling to another in an effort to minimize immunologically mediated reactions in the transplant recipient, which would result in organ rejection. These patients, as well as patients receiving transplant organs from donors other than a
10 sibling, are frequently administered drugs to suppress their immune system. While the immunological response to transplant tissue or organs may be suppressed through the use of immunosuppressant drugs to minimize rejection, immunosuppressant therapy is general in nature. Hence,
15 immunosuppressant drugs also tend to suppress the immune response generally, which reduces the transplant recipient's ability to combat infection.

More recently processes have been described for generating improved bioprosthesis for human or mammalian
20 implant, by treatment of non-human tissue. See, Orton, E. Christopher, U.S. 5,192,312. Orton discloses generation of implant tissue by removing native cells from tissue of, for example, porcine origin; and then, repopulating the tissue with new cells in the presence of
25 growth factor. The repopulating cells are immunologically compatible with the intended implant recipient. The biografts produced by this process are

2185447

free from many of the disadvantages of other prior art bioprosthesis.

SUMMARY OF THIS INVENTION

5 This invention provides new and advantageous processes for generating implant tissue suitable for implant in humans or other mammals. The process of this invention generally relates to treatment of xenogeneic or allogeneic tissue to generate a viable bioprosthesis which does not produce an adverse immune response by the
10 recipient upon implant, and possesses the regenerative capabilities of allografts, while exhibiting only limited propensity to calcify and little stimulation of thromboembolism.

15 In accordance with the foregoing, the process of this invention includes the steps of preparing a xenogeneic (or allogeneic) tissue matrix for further processing by removing native cells and other antigens and cellular debris from the decellularized tissue matrix, and treating the matrix to inhibit generation of
20 new immunological sites. This tissue matrix is then treated with the cellular adhesion factors described below to enhance attachment of cells to the matrix during the process of repopulating the tissue matrix with such new cells.

25 Depending upon the cells used to repopulate the natural tissue matrices, differing properties of the species hybrid bioprosthesis may be obtainable, such as

2185447

the ability to synthesize proteins otherwise atypical for the natural tissue at the site of implantation or unique to certain age groups. These hybrid grafts would combine the structural advantages of bioprosthetic grafts with the functional and regenerative capabilities of allografts as well as display attenuated or no immune response, limited propensity to calcify, and little stimulation of thromboembolism. As with all bioprosthetic grafts currently in use, these modified tissues would not be supply limited and would afford the functionality of the graft to more recipients. In addition, these grafts would not be necessarily chemically altered to make them stable to the recipient's immune system; therefore, such materials would display biomechanical properties more like those of the tissue they are used to replace.

The invention described herein is useful for generating bioprosthetic xenografts suitable for human implantation. It is particularly well suited for generating xenogeneic grafts in which the major structural component is connective tissue matrix, such as heart valves, particularly heart valves of porcine or bovine origin. Examples of other tissues suitable for use in this invention may be, but are not limited to, aortic heart valves, pulmonary heart valves, fascia lata, dura mater, pericardium, meniscus, skin, ligament, tendon, and other connective tissue structures.

65902-129

Thus in one aspect, the present invention provides a process for generating implant tissue from collagenous tissue or connective tissue the process comprising: A. reducing or eliminating native cells from the collagenous tissue or connective tissue to provide a tissue matrix; B. treating the tissue matrix with cellular adhesion factor to promote subsequent attachment of cultured allogeneic or autologous cells to the surfaces of the tissue matrix; and C. repopulating the tissue matrix with the cultured allogeneic or autologous cells.

In another aspect, the present invention provides a process for treating xenogeneic tissue to produce a xenogeneic tissue having improved compatibility with the immune system of an implant recipient of a species different from the species of the source of the xenogeneic tissue, comprising the steps of A. applying an amount of cellular adhesion factors to a decellularized xenogeneic tissue matrix effective to promote the subsequent attachment of cultured cells to the xenogeneic tissue matrix, wherein the cellular adhesion factors comprise one or more extracellular proteins ordinarily associated with the xenogeneic tissue in a liquid vehicle, and B. repopulating the xenogeneic tissue matrix with autogeneous or allogeneic cells to provide a substantially non-immunogenic and biomechanically acceptable implant or graft which is vitalized by the cellular repopulation and has improved compatibility with the immune system of the implant recipient, wherein the xenogeneic tissue is generated from collagenous or connective tissue.

In another aspect, the present invention provides a process for generating a xenogeneic implant or graft from non-human collagenous tissue or connective tissue, the process comprising A. treating the collagenous tissue or connective tissue to decellularize it and remove cellular

65902-129

and extracellular antigens to provide a tissue matrix; B. treating the tissue matrix with adhesion factors comprising fibronectin and heparin effective to promote attachment thereto of fibroblast cells immunologically acceptable to the implant or graft recipient; and C. repopulating the tissue matrix treated with adhesion factors by incubating the tissue matrix in the presence of the fibroblast cells and fibroblast growth factor until such cellular repopulation provides a vitalized tissue, and wherein the xenogeneic implant or graft so generated is mechanically, biochemically and immunologically suitable for implantation.

In another aspect, the present invention provides a process for generating a substantially non-immunogenic tissue matrix suitable for subsequent processing into an implant tissue which comprises the steps of eliminating native cells comprising treating a tissue with components selected from the group comprising enzymes and nucleases effective to inhibit subsequent native cell growth in the treated tissue and effective to limit generation of new immunological sites in the tissue.

In another aspect, the present invention provides a process for generating a xenogeneic heart valve from porcine or bovine heart valve tissue which is histologically and immunologically suitable for implantation in a human or mammalian recipient comprising: A. decellularizing the porcine or bovine heart valve tissue to provide a tissue matrix substantially free of native cellular antigens and treated to limit generation of new immunological sites; B. applying cellular adhesion factors to the tissue matrix, comprised of one or more extracellular proteins ordinarily associated with the natural tissue, effective to promote attachment of fibroblast cells to the tissue matrix, and

65902-129

repopulating the tissue matrix with allogeneic or autologous fibroblast cells in the presence of fibroblast growth factor immunologically acceptable to the implant recipient to provide a vitalized valve tissue.

5 In another aspect, the present invention provides a process for generating a graft or heart valve implant suitable for use in a human comprising: A. preparing a porcine heart valve tissue matrix by decellularizing native porcine heart valve tissue and treating it with enzymes or
10 nucleases effective to decellularize the native porcine heart valve tissue and provide a tissue matrix of limited immunogenicity; B. applying an effective amount of human plasma fibronectin and heparin to the tissue matrix to promote cellular attachment of allogeneic or autologous
15 fibroblast cells; and C. repopulating the tissue matrix with fibroblast cells by incubating the tissue matrix in a nutrient media comprised of cultured human fibroblast cells and human recombinant fibroblast growth factor.

The invention further provides implant tissues,
20 tissue matrices, and xenogeneic valves generated in accordance with the processes of the invention.

2185447

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1. Photomicrograph of a fresh aortic leaflet.

5 Figure 2a. Photomicrograph showing pulmonary valve conduit after decellularization.

Figure 2b. Photomicrograph showing myocardium after decellularization.

Figure 3a. Photomicrograph of decellularized aortic leaflet.

10 Figure 3b. Photomicrograph of repopulated aortic leaflet.

Figure 4. Collagen and Non-collagen Protein Synthesis in Porcine Aortic Heart Valve Leaflets

15 Figure 5. Reactivity of Rabbit Antisera Raised to Extracts of Cryopreserved or Depopulated Porcine Heart Valve Leaflets - Antibody Capture.

Figure 6a. Photomicrograph showing the minimal cellular response triggered by decellularized porcine heart valve leaflets after implantation.

20 Figure 6b. Photomicrograph showing cellular response triggered by cryopreserved porcine aortic valve leaflet after implantation.

25 Figure 7a. Photomicrograph of fresh porcine aortic valve leaflet assayed for pig cell associated antigen.

Figure 7b. Photomicrograph of decellularized porcine aortic valve leaflet assayed for pig cell associated antigen.

2185447

Figure 8. Stress-Strain Relations of Porcine Aortic Valve Leaflets.

Figure 9. Stress Relaxation Curves of Porcine Aortic Leaflets After Preconditioning.

5

Figure 10. Tensile Failure Data for Porcine Aortic Valve Leaflets.

DETAILED DESCRIPTION OF THE INVENTION

Depending on the type of transplant intended, if the recipient is human, the initial transplant tissue or organ may be of non-human origin. These tissues or organs may be obtained at approved slaughterhouses from animals fit for human consumption or from herds of domesticated animals maintained for the purpose of providing these tissues or organs. The tissues or organs are handled in a sterile manner, and any further dissection of the tissue or organs is carried out under aseptic conditions.

Transplant tissue originating from a non-human sources and intended for use in a human recipient may be processed to generate a hybrid xenograft or xenogeneic implant tissue, which is formed from a non-human tissue matrix, free of native cells and other antigenic components and which is populated with viable human cells. The steps of the process for generating such immunologically tolerable implants are described below.

After collection and dissection, the transplant tissue may be sterilized by incubating it in a sterile buffered nutrient solution containing antimicrobial agents, for example an antibacterial, an antifungal, or a sterilant compatible with the transplant tissue.

The sterilized transplant tissue may then be cryopreserved for further processing at a later time or may immediately be further processed according to the

65902-129

next steps of this process including a later cryopreservation of the tissue matrix or other tissue products of the process.

Decellularization

5 A preliminary step of this invention calls for elimination of native viable cells as well as other cellular and acellular structures or components which may elicit an adverse immune response by the implant recipient.

10 Several means of reducing the viability of native cells in tissues and organs are known, including physical, chemical, and biochemical methods. See, e.g. U.S. Patent No. 5,192,312 .

Such methods may be employed in accordance

15 with the process described herein. However, the decellularization technique employed should not result in gross disruption of the anatomy of the transplant tissue or substantially alter the biomechanical properties of its structural elements. The treatment of the tissue to

20 produce a decellularized tissue matrix should also not leave a cytotoxic environment that mitigates against subsequent repopulation of the matrix with cells allogeneic or autologous with respect to the recipient. Cells and tissues that are allogeneic for the recipient

25 are those that originate with or are derived from a donor of the same species as the recipient. Autologous cells

2185447

or tissues are those that originate with or are derived from the recipient.

Physical forces, for example the formation of intracellular ice, can be used to decellularize
5 transplant tissues. For example, vapor phase freezing (slow rate of temperature decline) of intact heart valves can reduce the cellularity of the heart valve leaflets as compared to liquid phase freezing (rapid). However, slow freezing processes, in the absence of cryoprotectant, may
10 result in tissue disruption such as the cracking of heart valve conduits. Colloid-forming materials may be added during freeze-thaw cycles to alter ice formation patterns in the tissue. Polyvinylpyrrolidone (10% w/v) and dialyzed hydroxyethyl starch (10% w/v) may be added to
15 standard cryopreservation solutions (DMEM, 10% DMSO, 10% fetal bovine serum) to reduce extracellular ice formation while permitting formation of intracellular ice. This allows a measure of decellularization while affording the collagenase tissue matrix some protection from ice
20 damage. Additionally, it is noted, that tissues, particularly heart valve conduits, will crack if rapidly frozen irrespective of the presence of cryoprotectant.

Alternatively, various enzymatic or other chemical treatments to eliminate viable native cells from
25 implant tissues or organs may be used. For instance, extended exposure of cells to proteases such as trypsin result in cell death. However, because at least a portion of the type I collagen molecule is sensitive to a

2185447

variety of proteases, including trypsin, this may not be the approach of choice for collagenous grafts intended for implant in high mechanical stress locations.

Combinations of different classes of
5 detergents, for example, a nonionic detergent, Triton X-100, and an anionic detergent, sodium dodecyl sulfate, may disrupt cell membranes and aid in the removal of cellular debris from tissue. However, steps should be taken to eliminate any residual detergent levels in the
10 tissue matrix, so as to avoid interference with the later repopulating of the tissue matrix with viable cells.

The decellularization of the transplant tissue is preferably accomplished by the administration of a solution effective to lyse native cells in the transplant
15 tissue. Preferably, the solution may be an aqueous hypotonic or low ionic strength solution formulated to effectively lyse the native tissue cells. Such an aqueous hypotonic solution may be de-ionized water or an aqueous hypotonic buffer. Preferably the aqueous
20 hypotonic buffer may contain additives that provide sub-optimal conditions for the activity of selected proteases, for example collagenase, which may be released as a result of cellular lysis. Additives such as metal ion chelators, for example 1,10-phenanthroline and
25 ethylenediaminetetraacetic acid (EDTA), create an environment unfavorable to many proteolytic enzymes. Providing sub-optimal conditions for proteases such as collagenase, may assist in protecting the tissue matrix

from degradation during the lysis step. Particularly, suboptimal conditions for proteases may be achieved by formulating the hypotonic lysis solution to eliminate or limit the amount of calcium and zinc ions available in solution. Many proteases are active in the presence of calcium and zinc ions and lose much of their activity in calcium and zinc ion free environments.

Preferably, the hypotonic lysis solution will be prepared selecting conditions of pH, reduced availability of calcium and zinc ions, presence of metal ion chelators and the use of proteolytic inhibitors specific for collagenase, such as β_1 -anticollagenase, such that the solution will optimally lyse the native cells while protecting the underlying tissue matrix from adverse proteolytic degradation. For example a hypotonic lysis solution may include a buffered solution of water, pH 5.5 to 8, preferably pH 7 to 8, free from calcium and zinc ions and including a metal ion chelator such as EDTA. Additionally, control of the temperature and time parameters during the treatment of the tissue matrix with the hypotonic lysis solution, may also be employed to limit the activity of proteases.

It is preferred that the decellularization treatment of the tissue matrix also limits the generation of new immunological sites. While collagen is typically substantially non immunogenic, partial enzymatic degradation of collagen may lead to heightened immunogenicity. Accordingly, a preferable step of this

2185447

process includes treatment of the tissue with enzymes, such as nucleases, effective to inhibit cellular metabolism, protein production and cell division without degrading the underlying collagen matrix. Nucleases that can be used for digestion of native cell DNA and RNA include both exonucleases and endonucleases. A wide variety of which are suitable for use in this step of the process and are commercially available. For example, exonucleases that effectively inhibit cellular activity include DNAase I (SIGMA Chemical Company, St. Louis, MO.) and RNAase A (SIGMA Chemical Company, St. Louis, MO.) and endonucleases that effectively inhibit cellular activity include EcoR I (SIGMA Chemical Company, St. Louis, MO.) and Hind III (SIGMA Chemical Company, St. Louis, MO.).

It is preferable that the selected nucleases are applied in a physiological buffer solution which contains ions which are optimal for the activity of the nuclease, such ions include magnesium and calcium salts. It is also preferred that the ionic concentration of the buffered solution, the treatment temperature and the length of treatment are selected to assure the desired level of effective nuclease activity. The buffer is preferably hypotonic to promote access of the nucleases to the cell interiors. For treatment of endogenous endothelial cells of non-human heart valve tissue, particularly valves of porcine or bovine origin the tissue is preferably treated with a physiologically buffered medium comprised of nucleases DNAase I and

2185447

RNAase A. Preferably, the nuclease degradation solution contains about 0.1 $\mu\text{g/ml}$ to 50 $\mu\text{g/ml}$, preferably 10 $\mu\text{g/ml}$, of the nuclease DNAase I, and 0.1 $\mu\text{g/ml}$ to 10 $\mu\text{g/ml}$, preferably 1.0 $\mu\text{g/ml}$, of RNAase A. The tissue may
5 be decellularized by application of the foregoing at a temperature of about 20°C to 38°C, preferably at about 37°C for about 30 minutes to 6 hours, while at the same time the generation of new immunological sites as a result of collagen degradation is limited.

10 Other enzymatic digestions may be suitable for use herein, for example, enzymes that will disrupt the function of native cells in a transplant tissue may be used. For example, phospholipase, particularly
15 phospholipases A or C, in a buffered solution, may be used to inhibit cellular function by disrupting cellular membranes of endogenous cells. Preferably, the enzyme employed should not have a detrimental effect on the tissue matrix protein. The enzymes suitable for use may
20 also be selected with respect to inhibition of cellular integrity, and also include enzymes which may interfere with cellular protein production. The pH of the vehicle, as well as the composition of the vehicle, will also be adjusted with respect to the pH activity profile of the
25 enzyme chosen for use. Moreover, the temperature applied during application of the enzyme to the tissue should be adjusted in order to optimize enzymatic activity.

Subsequent to the chosen decellularization treatment, the resultant transplant tissue matrix is

2185447

washed to assure removal of cell debris which may include cellular protein, cellular lipids, and cellular nucleic acid, as well as any extracellular debris such as extracellular soluble proteins, lipids and proteoglycans.

5 Removal of this cellular and extracellular debris reduces the likelihood of the transplant tissue matrix eliciting an adverse immune response from the recipient upon implant. For example, the tissue may be incubated in a balanced salt solution such as Hanks' Balanced Salt

10 Solution (HBSS). The composition of the balanced salt solution wash, and the conditions under which it is applied to the transplant tissue matrix may be selected to diminish or eliminate the activity of the nuclease or other enzyme utilized during the decellularization

15 process. Such a balanced salt wash solution would preferably not contain magnesium or calcium salts, and the washing process may include incubation at a temperature of between about 2°C and 42°C, with 4°C most preferable. The transplant tissue matrix may be

20 incubated in the balanced salt wash solution for up to 10 to 12 days, with changes in wash solution every second or third day. Optionally, an antibacterial, an antifungal or a sterilant or a combination thereof, may be included in the balanced salt wash solution to protect the

25 transplant tissue matrix from contamination with environmental pathogens.

Where the tissue being prepared for transplantation by the process of this invention is skin,

the decellularized tissue matrix may be utilized without the subsequent steps of *in vitro* cellular repopulation. The decellularized and substantially non-immunogenic tissue matrix, is suitable for implant into a recipient.

5 The reduced immunogenicity of the skin tissue matrix will increase the tolerance of the transplanted skin by the recipient's immune system. The implant may then be repopulated *in vivo* by the implant recipient's own cells. Prior to use as a skin graft, the skin matrix may be

10 treated to enhance the ingrowth and attachment of the recipient's own skin cells. For instance, the matrix may be treated with adhesion factors or growth factors, such as keratinocyte growth factor, or both, to enhance the infusion of keratinocytes.

15 The tissue matrix prepared in accordance with the above is free of its native cells, and additionally cellular and extra-cellular antigen components have been washed out of the tissue matrix. Preferably the tissue matrix has been treated in a manner which limits the

20 generation of new immunological sites in the collagen matrix. The tissue matrix, however, retains the essential biomechanical strength necessary to provide the framework for further processing of the matrix.

25 The tissue matrix processed according to this invention may be cryopreserved for later use. Cryopreservation of decellularized transplant tissue would assure a supply or inventory of substantially non-immunogenic tissue matrices which, upon thawing, would be

65902-129

ready for further treatment according to the subsequent steps of this invention, or further processed as desired to provide an implant tissue product. For example, tissue matrices may be inventoried until such time as the particular cells to be employed during repopulation are identified. This may be of particular utility when the tissue matrix is to be repopulated with cells derived from the recipient or other cells selected for use based on their immunological compatibility with a specific recipient.

It is also envisioned that native transplant tissue may be cryopreserved prior to undergoing any of the processes of this invention. Tissues which are not decellularized retain their native cells in conjunction with the collagenous tissue matrix. Upon thawing these tissues may be further processed. Beneficially, the cryopreservation of intact transplant tissue may also aid in the depopulation of the tissue as a result of cellular death brought on by cryopreservation.

Techniques of cryopreservation of tissue are well known in the art. Brockbank, K.G.M. *Basic Principles of Viable Tissue Preservation*. In: Transplantation Techniques and Use of Cryopreserved Allograft Cardiac Valves and Vasular Tissue. D.R. Clarke (ed.), Adams Publishing Group, Ltd., Boston. pp 9-23, discusses cryopreservation of tissues and organs.

2185447

5 The tissue matrix, whether or not having been cryopreserved, may be next treated to enhance the adhesion and inward migration of the allogeneic or autologous cells, *in vitro*, which will be used to repopulate the transplant tissue.

Cell Adhesion

10 While not wishing to be bound by theory, there are several factors believed to effect the attachment of cells to tissue. For example, the adherence of fibroblasts to tissue surfaces involves interactions between the cell membrane and extracellular matrix components of native tissue such as fibrillar and sheet-forming collagen, proteoglycans, and glycoproteins. *In vitro*, dermal fibroblasts cultured without serum attach rapidly and equally to types I and IV collagen. The extent of attachment is increased by the addition of serum (human or fetal bovine, maximal binding with 1% serum) and by purified fibronectin to the culture medium. Each of the two homologous subunits of fibronectin has two cell recognition regions, the most important of which has the Arg-Gly-Asp (RGD) sequence. A second site, binding glycosaminoglycans, acts synergistically and appears to stabilize the fibronectin-cell interactions mediated by the RGD sequence. Heparin sulfate along with chondroitin sulfate are the two glycosaminoglycans identified on cell surfaces. Heparin sulfate is linked to core proteins (syndecan or hyaluronectin) which can

15
20
25

2185447

either be integral or membrane spanning. Cellular binding sites for extracellular matrix glycoproteins are called integrins and these mediate tight binding of cells to the adhesion factors. Each adhesion factor appears to have a specialized integrin although a single integrin may bind to several extracellular matrix factors. Fibroblasts, when adherent to intact fibronectin (cell and heparin-binding domains) display a contracted morphology with focal adhesions. Without the heparin binding domain, fibroblasts will spread but fail to develop focal adhesions.

Thus, a combination of factors may determine the rate at which cells can bind to a tissue surface. Many of these are fibroblast products, although some like fibronectin may be derived from serum supplementation as well. The rate at which these factors are expressed and secreted by cells will affect the attachment of cells to surfaces, and cytokines such as fibroblast growth factor and transforming growth factor- β are positive regulators of fibroblast collagen and fibronectin production.

It is believed that the effective attachment of cells to the tissue matrix is promoted by the interaction between the cell membrane, and extracellular components associated with the corresponding implant tissue. Accordingly, for a given cell type, and tissue type chosen for use, appropriate treatments which promote cellular attachment to the decellularized tissue matrix include treatment with extracellular tissue components

and, particularly, extracellular proteins, such as glycoproteins and/or proteoglycans or glycosaminoglycans which are effective to promote attachment of cells to the decellularized tissue matrix. Accordingly, a preferred
5 technique for repopulating the tissue matrix with cells is carried out by first treating the decellularized tissue matrix with cellular attachment factor effective to promote the attachment of the repopulating cells to the decellularized matrix.

10 For example, the decellularized tissue matrix may be incubated in nutrient solution containing extracellular matrix protein such as fibronectin and a glycosaminoglycan for a period effective for binding of the fibronectin to surfaces of the transplant tissue
15 matrix to be repopulated. Preferred buffers for use with fibronectin/glycosaminoglycan include sodium phosphate/glycerin/bovine serum albumin (Fetal Bovine Serum, BIO-WHITTAKER) and Dulbecco's Modified Eagle's Medium (DMEM), (GIBCO). These buffers typically are used
20 to provide a physiological acceptable pH of about 7.0 to 7.6. The presence of the extracellular matrix proteins establish a surface on the tissue matrix to which the cells that have been chosen to repopulate the matrix attach. The stimulus of the extracellular matrix protein
25 promotes cell repopulation in the graft.

The preferred extracellular matrix protein for use herein is the intact molecular form of fibronectin (Human Plasma Fibronectin, UPSTATE Biotechnology, Inc.).

2185447

This heterofunctional glycoprotein has affinity for extracellular matrix proteins, proteoglycans, and certain cell types. The fibronectin treatment solution preferably also contains a proteoglycan which may be
5 which may be one of the glycosaminoglycans heparin, heparin sulfate, chondroitin, chondroitin sulfate, dermatin, or dermatin sulfate. It is believed that the glycosaminoglycan promotes and stabilizes the binding between fibronectin and the tissue matrix associated
10 collāgen. The matrix advantageously is capable of interaction with fibronectin because it is not chemically cross-linked.

A source of fibronectin is from human blood, processed to limit contamination with virus. The
15 preferred glycosaminoglycan is heparin. The concentration of glycoprotein used as the adhesion factor to treat the tissue matrix may range from about 1 to about 100 $\mu\text{g}/\text{ml}$, with a fibronectin concentration of 10 $\mu\text{g}/\text{ml}$ being preferred. The preferred weight ratio of
20 fibronectin to heparin is about 10 parts fibronectin to about 1 part glycosaminoglycan, e.g. heparin. This is optimal for repopulation of porcine heart valve leaflets, but may range from about 0.1:1 to about 10:0.1 depending on the tissue used.

25 Preferably the components of the nutrient solution containing the adhesion factors are selected such that the solution is compatible with growth factors which are later added to the nutrient medium that the

transplant tissue matrix is incubating in. These growth factors are employed to facilitate cell growth and repopulation of the tissue matrix.

Cell Repopulation

5 An important aspect of this invention is that the decellularized transplant tissue matrix may be repopulated with cells *in vitro*. The cells employed to repopulate the decellularized matrix may be allogeneic cells cultured from the same species as the intended
10 implant recipient, or may be autologous cells cultured from the implant recipient. In either case, the autologous or allogeneic cells in the repopulated tissue matrix, known as a heterograft or chimeric graft, will elicit less of an adverse immune response than an
15 unprocessed xenogeneic transplant tissue.

 It is also envisioned that cells employed to repopulate the decellularized matrix may be cells that have been genetically manipulated to enhance the production of specific proteins. Numerous recombinant
20 DNA technologies are known in the art for altering, enhancing, and modifying cell metabolism.

 Repopulation may be accomplished by incubating the tissue matrix treated with cell adhesion factors in a nutrient medium containing the cells and growth factors
25 active to promote cell proliferation and, hence, repopulation of the tissue matrix. A preferred cell type for use herein is fibroblast cells.

2185447

A variety of substances may be employed to enhance cell chemotaxis, increasing the rate of directional movement along a concentration gradient of the substance in solution. With respect to fibroblast cells, fibroblast growth factor, platelet-derived growth factor, transforming growth factor- β , and the substrate-adhesion molecules, fibrillar collagens, collagen fragments, and fibronectin are chemotactic for fibroblasts. In contrast to cell adhesion, fibroblast migration requires *de novo* protein synthesis; protein synthesis in normal fibroblastic cells is stimulated by adhesion of cells to fibronectin, so the processes of cell adhesion and cell migration during repopulation are believed to be interrelated.

Cellular migration also allows cells to move through the tissue matrix repopulating interior interstitial spaces as well as the surfaces of the tissue transplant matrix.

The number of cells required to fully repopulate particular transplant tissue matrices depends upon the volume of the tissue used and the types of cells provided. However, concentrations of 20,000 to 125,000 fibroblasts per milliliter may provide suitable coverage of the heart valve leaflet and aortic conduit tissue.

2185447

Cell Proliferation

The steps of cellular repopulation of the tissue matrix preferably are conducted in the presence of growth factors effective to promote proliferation of the cultured cells employed to repopulate the matrix. For example, when fibroblast cells are employed, a growth factor for use herein may be fibroblast growth factor (FGF), most preferably basic fibroblast growth factor (bFGF) (Human Recombinant bFGF, UPSTATE Biotechnology, Inc.).

The fibroblast growth factors (heparin-binding) are a family of mitogens active on mesenchymal cells. FGFs are not detected free in conditioned medium, instead the FGFs are found in the extracellular matrix in association with heparin sulfate, localizing in the fibronectin-heparin layer prebound to the transplant tissue matrix. The glycosaminoglycans stabilize FGF activity and are required for FGF binding to cell surface receptors where they stimulate autocrine/paracrine growth.

The matrix and cells are preferably exposed to bFGF continuously during the repopulation step to provide for stimulation of cell replication and expression of collagen protein synthesis, as required for normal valve function. Culture times of the matrix with growth factor range from 10 to 21 days. The concentration of growth factor used to treat the tissue matrix may range from 100

ng/ml to 10 µg/ml with a growth factor concentration for bFGF of 2.5 µg/ml being preferred.

When fibroblasts are used as the graft-repopulating cells the culture medium may include
5 Dulbecco's Modified Eagle Medium (GIBCO) with 5-15% added serum. Autologous recipient serum is preferred but experience with implantation of allograft heart valves suggests that bovine serum may be utilized in the growth
10 medium without adverse immunologic consequences to the implant recipient. Continual stimulation of the cells with serum and medium conditioned by the repopulating cells may provoke a more rapid cellular repopulation of the tissue matrix. The matrix, cells and growth factors may be incubated in a humidified atmosphere at 37°C
15 provided with a 95% air and 5% CO₂ mixture throughout the culture period.

The transplant tissue matrix is cultured for a time sufficient to produce a repopulated graft with interstitial histology similar to that of fresh tissue.
20 Upon conclusion of the cellular repopulation process, the tissue will also preferably display metabolic parameters similar to those of fresh tissue.

Cellular Viability

An important aspect of this invention is that
25 the repopulated transplant tissues are functioning and viable prior to implantation in addition to being

65902-129

immunologically acceptable to the implant recipient or substantially non-immunogenic. Various assays exist to measure cellular activity and application of these assays to the implant tissues of this process provide a method of monitoring and quantifying the viability of the cells which repopulate the implant tissue.

It is preferable that an assay be selected that measures a cellular activity which bears a relation to the intended function of the transplant tissue. For example, the production of collagen is important in maintaining a functioning heart valve. In heart valve leaflets 5 to 15% of the total protein produced is collagen. Of that at least 75% will be type I collagen. Therefore in assaying a repopulated heart valve, it is preferable to assay for total collagen produced by the repopulating cells as an accurate measure of cellular viability. Assaying for cellular activity by measuring collagen production are well known in the art. Examples of references discussing assays for cellular collagen production are Buckley, A. et al. 1980 *Collagen Metabolism., Methods of Enzymology*, 163:674-69, and Hayashi, T. and Nagai, Y. 1979. *Separation of the α Chains of Type I and III Collagens by SDS-polyacrylamide Gel Electrophoresis, Journal of Biochemistry*. 86:453-459.

Other assays that can measure cell viability are envisioned for use in this invention. Total protein synthesis as measured by the incorporation of [³H]proline

2185447

is one such assay. Additional assays which may be useful in measuring cellular viability include assays for the metabolism of glucose and a variety of assays directed toward mitochondrial activity.

5 It is envisioned that any assay that quantifiably measures a cellular function indicative of viable cells may be used.

Differentiated Functions

10 Fibroblast cells are responsible for the production of most connective tissue components. They synthesize different collagen types, and the phenotype appears to be imposed by specific tissue environments; i.e., cultured fibroblasts synthesize collagen types according to their site of origin. Fibroblasts also
15 produce various glycosaminoglycans and fibronectin and growth factors. It is the ability of dermal fibroblasts to synthesize types I, III, and V collagens in the proportion present in the matrix of the heart valve leaflet which makes them appropriate cells for
20 repopulating the transplant tissue matrix and forming the hybrid graft described herein.

The cells which are used to repopulate the particular graft can be varied within wide limits, and different types of cells can be used in different
25 circumstances, depending upon the function of the transplant, the nature of the tissue being replaced or

augmented, the allergic sensitivity of the recipient in addition to other factors.

5 A preferred embodiment of the invention uses autologous cells in the process described herein. A tissue sample is taken from the recipient prior to transplant or implant surgery. The tissue is treated, in accordance with the methods described herein below, to produce fibroblasts or other cells which are then used to repopulate the allogeneic or xenogeneic tissue matrix, in accordance with this process. By repopulating the previously prepared decellularized and treated transplant tissue matrix with cells derived from the resected tissue taken from the recipient, the likelihood of an adverse immune system response and ultimately graft rejection can be minimized or avoided.

10

15

The cell source can be selected to match the tissue to be transplanted. For example, if a blood vessel is to be transplanted, cells can be taken from a recipient's healthy blood vessel and used as the source of cells for graft repopulation. In this fashion, the healthy graft can be very closely matched to the recipient's diseased tissue.

20

This aspect of the invention is particularly useful when the transplant recipient is highly allergic, or if the tissue is highly immunogenic, such as with respect to transplantable blood vessels.

25

Alternatively, allogeneic cell lines which are not likely to cause an unacceptable immune response upon

2185447

implant may be used to repopulate the tissue matrix. Cells with no more than a weak or tolerable allergic response may be used to repopulate the tissue matrix to provide a substantially non-immunogenic implant. These
5 cells may be naturally weakly immunogenic or be designed by virtue of recombinant cell technology to be weakly immunogenic.

Method for Isolating Fibroblasts

The tissue used to provide the fibroblast cell
10 link, for example skin (buttocks, thigh, or back) or heart valve leaflets, is recovered sterilely and provided to a processor in buffered nutrient medium. The tissue is cut into 1 mm³ pieces using a sterile dissection
15 technique. Groups of 10 pieces are then placed in 35 mm tissue culture dishes with a limiting amount of culture medium (DMEM plus 10% fetal bovine serum) sufficient to wet the tissue but not float the pieces. Incubate for one week at 37°C in a humidified culture incubator in a
20 5% CO₂ atmosphere in air. After one week of incubation, each piece of tissue is surrounded by a dense outgrowth of fibroblasts. Epithelial cells may also be present but are lost during subsequent cell culturing. The fibroblasts are removed by standard trypsin digestion after rinsing the cells with a calcium and magnesium-free
25 sterile buffered salt solution, and placed in larger cell culture vessels with fresh culture medium. The cell cultures can be expanded in this manner. The contents of

one flask can be divided and placed into three larger vessels, and this process can be repeated about once a week. Cells recovered from these flasks are used as the source of repopulating cells. Cells obtained in this manner are preferable to commercially available cell lines, because most cell lines are phenotypically altered and are no longer responsive in a normal manner to growth regulators (such as bFGF). Additionally most commercially available cell lines do not produce natural amounts and proportions of important protein products (such as collagen).

A preferred embodiment of the invention encompasses a xenograft treated to remove native cells and soluble proteins, the conditions are chosen to be non-toxic to cells used to repopulate the xenograft and chosen to render the final xenograft tissue matrix biomechanically sound and intact. The depopulated xenograft tissue matrix is then treated with extracellular matrix glycoprotein factor and glycosaminoglycan. The xenograft is then treated with a growth factor and glycosaminoglycan and incubated with exogenous cells that adhere to the graft. These exogenous cells migrate into the graft, proliferate within the graft, and express essential proteins and other factors critical to the function of the graft. The repopulated xenograft is rendered biologically functional by the repopulating cells and displays reduced or minimal immunogenicity as compared to either untreated xenograft or chemically-

fixed xenograft. The reduced antigenicity is a
consequence of the removal of xenoantigens or
alloantigens during the initial depopulation of the
tissue, and by the presence of repopulating cells which
5 are not recognized as foreign by the recipient. These
chimeric grafts should also display a reduced tendency
for calcification because cell debris, which forms either
as the result of cell death during procurement of tissue
or during the decellularization of the tissue, is removed
10 by the washing regimen. Because these chimeric grafts
retain a lining layer of cells as a result of the above
described procedure, the tendency of thrombi and
microemboli to form should also be is reduced as compared
to mechanical structures, structures made of purified
15 biological molecules, and chemically-fixed bioprosthetic
tissues.

2185447

EXAMPLES

Example 1. Depopulation of porcine aortic valve leaflets, aortic conduit, and associated myocardium according to hypotonic lysis/nuclease digestion procedure.

Pig hearts were obtained within two hours of slaughter, in order to limit the effects of uncontrolled cellular degradation on tissue structure, and returned to the processing facility at 4°C in a sterile solution of DMEM. Aortic heart valves were excised under sterile conditions, incubated in antibiotic mixture for 16 hr at 37°C in nutrient medium in 5% CO₂ atmosphere, and cryopreserved (cooling rate = -1°C/min) in DMEM containing 10% DMSO and 10% fetal bovine serum. After storage at -179°C, the valves were thawed rapidly at 37°C. The leaflets, aortic conduit, and myocardium were cut from the valve and divided portions of each tissue type were either placed directly into 10% buffered formalin for later histologic analysis or were processed for depopulation. After washing in lactated Ringers-5% dextrose solution three times for 15 min each at room temperature, tissues were incubated in 18 MΩ water for 2 hr at room temperature followed by digestion in 10 µg/ml DNAase I and 1 µg/ml RNAase A in 10 Mm Tris-Cl, pH 7.6, containing 3 mM magnesium and 1 mM calcium salts at 37°C for 120 min.

After lytic treatments, tissues were incubated for 8 days in DMEM-5% FBS. At this time, the treated tissues were fixed in formalin. All fixed tissues were mounted in paraffin, sectioned, and stained with hematoxylin and eosin to visualize cells. A representative micrograph in Figure. 1 shows the pattern of cellularity of a fresh aortic leaflet with an endothelial layer on both the fibrosa and ventricularis surfaces and fibroblasts throughout the full thickness of the tissue. Figures 2a and 2b show micrographs of pulmonary valve conduit and myocardium, respectively, after depopulation with essentially acellular appearance.

Example 2. Repopulation of depopulated porcine aortic valve leaflets with bovine dermal fibroblasts.

Porcine aortic leaflets were recovered and depopulated as defined in EXAMPLE 1. Leaflets were incubated in 5 ml NaH_2PO_4 /glycerin/BSA buffer at 37°C. Human plasma fibronectin was added to the buffer to a concentration of 10 $\mu\text{g/ml}$ along with 1 $\mu\text{g/ml}$ heparin for 16 hr followed with addition of human recombinant bFGF to a concentration of 2.5 $\mu\text{g/ml}$ along with 0.83 $\mu\text{g/ml}$ heparin for an additional 6 hr. After this incubation, bovine dermal fibroblasts, previously isolated by standard explant culture techniques, were added to the heart valve leaflets at 2×10^4 cell/ml. The leaflets and cells were incubated for 11 days. Following incubation, valve sections were placed in formal for histologic

2185447

analysis. Figure 3a is a representative micrograph of a
decellularized aortic leaflet. Figure 3b is a
representative micrograph of a decellularized aortic
leaflet treated with both fibronectin and bFGF showing
5 repopulation with exogenous fibroblasts.

Example 3. Biochemical activity of fibroblasts in
repopulated as compared to fresh and depopulated tissues.

Porcine aortic heart valve leaflets were
depopulated as in EXAMPLE 1 and repopulated with two
10 different isolates of sheep dermal fibroblasts according
to the technique in EXAMPLE 2. After 10 days of
repopulation, leaflets were moved to fresh vessels and
incubated for 48 hr in 1.0 μ Ci/ml [3 H]proline in DMEM
containing gentamycin and 50 μ g/ml ascorbic acid, 50
15 μ g/ml β -aminopropionitrile. Total proteins synthesized
were determined by 10% trichloroacetic acid precipitated
radioactivity recovered from medium and tissue extracts
made 10 mM in N-ethylmaleimide, 25 mM in EDTA, and 10 mM
in phenylmethylsulfonyl fluoride to prevent proteolysis;
20 precipitated protein was further analyzed by digestion
with *Clostridial* collagenase free of non-specific
protease activity to define the collagen content. As
shown in Figure 4, protein synthetic activity of
depopulated tissue was nil. Following repopulation,
25 significant protein synthesis was detected by [3 H]proline
incorporation which was synthesized at the same rate as
was determined in fresh porcine tissue; collagen

represented 3.6% of the total protein synthesis, and most of this was secreted into the medium. These results indicate that porcine leaflets rendered treated by the depopulation procedures described in the preferred embodiment of the invention display no protein synthetic capacity in general and no collagen synthesis in particular. The successful application of repopulation procedures is indicated by the ability to impart the cellular function of protein synthesis to the depopulated leaflet by the provision of exogenous fibroblasts during the repopulation procedure.

Example 4. Demonstration of reduced humoral immune response to depopulated porcine leaflet extracts injected in rabbits.

Removal of cells and soluble proteins was achieved by procedures described in EXAMPLE 1. The immunological consequences of depopulating leaflets were investigated by comparison with cryopreserved viable leaflets. The results of humoral immune response studies are presented in Figure 5. The humoral immune response was assessed using an antibody capture technique in which antigen extracts in 0.1 M NaCl of unmodified cryopreserved leaflets were used to screen sera from rabbits immunized with NaCl extracts of either modified cell depopulated leaflets or control leaflets. Emulsions of such extracts were made in 50% (v/v) Freund's complete adjuvant; 0.1 ml portions of these emulsions were placed

2185447

at ten intradermal sites along the backs of separate New Zealand white male rabbits. After two weeks, the animals were rechallenged with additional extracts of cryopreserved or depopulated leaflets emulsified in Freund's incomplete adjuvant. After 1.5 months, the animals were bled. Immune sera were prepared and were screened for both IgG and IgM antibodies using goat anti-rabbit IgG and goat anti-rabbit IgM antisera conjugated to alkaline phosphatase. In Figure 5, the serum from depopulated tissue recipients demonstrated ~50% of the IgG response and <5% of the IgM response observed in rabbits immunized with cryopreserved leaflet extracts. These findings indicate attenuation of the humoral immune response to tissue depopulated by the techniques described in the preferred embodiment of the invention.

Example 5. Demonstration of reduced cellular immune and inflammatory responses to depopulated porcine leaflets implanted in rabbits.

Removal of cells and soluble proteins was achieved by procedures described in EXAMPLE 1. Divided pieces of depopulated (acellular) and cryopreserved (cellular) porcine aortic valve leaflets were inserted into pouches formed in the dorsal subcutaneous of New Zealand white male rabbits. The pouches were closed and after two weeks the implants and surrounding tissues (skin to muscle) were recovered surgically and fixed in formalin for histopathologic analysis after staining

paraffin embedded sections with hematoxylin and eosin. Figure 6 shows that depopulated leaflets engendered minimal cellular responses compared with cryopreserved controls. The cryopreserved tissue which contains both an endothelial cell layer as well as fibroblasts stimulated significant immune and inflammatory cell response with large numbers of heterophils and lymphocytes and plasma cells in the implant area as well as within the implants themselves. In depopulated tissue implants, both inflammatory and immune cells were fewer in number and more limited in distribution.

Example 6. Demonstration of removal of antigens responsible for hyperacute rejection of porcine tissues in a human recipient.

Removal of cells and soluble proteins from porcine aortic heart valve leaflets and aortic conduit was achieved by procedures described in EXAMPLE 1. Divided pieces of these tissues and their counterparts from fresh and cryopreserved porcine aortic heart valves were fresh-frozen in liquid nitrogen in cryosection mounting medium, cut into 8-10 μ m sections, mounted on charge-modified glass slides. After fixation in 4°C acetone, the tissues were probed with a biotin-conjugated *Bandeiraea simplicifolia* lectin-I which binds to specific galactose- α 1,3-galactose modified proteins found on the membranes of porcine cells. These modified proteins are the sites of binding of preformed natural antiporcine

2185447

antibodies that initiate hyperacute rejection responses of porcine tissues in primates (including man). Proteins binding this lectin were detected by then reacting the sections with biotin-conjugated horseradish peroxidase-
5 avidin mixture, hydrogen peroxide, and 3,3'-diaminobenzidine. Presence of porcine antigens is detected by color development. In Figure 7a, microscopic analysis of sections demonstrates cell associated antigen in cryopreserved aortic leaflet. Figure 7b demonstrates
10 markedly diminished antigen binding after decellularization of the aortic leaflet. This study shows that the depopulation procedure as presented in the preferred embodiment of the invention reduces critical antigens likely to cause rejection of a porcine graft by
15 a human recipient.

Example 7. Biomechanical properties of depopulated porcine aortic heart valve leaflets - stress-strain analyses.

Porcine aortic heart valves, freshly obtained,
20 were sterilized with antibiotic mixture and cryopreserved under conditions that maintain cellular viability. For depopulation, aortic valves were thawed rapidly at 37°C, then treated with low hypotonicity solution, nucleases, and balanced salt solution for 10 days. For
25 biomechanical testing, leaflets were cut into circumferential or radial strips, mounted onto an Instron Model 1011 Materials Tester under calibrated clamping

2185447

pressure. Tissue was bathed in 37°C or 4°C Hanks balanced salt solution during testing. After determination of gauge length and 20 preconditioning cycles (100 g load for circumferential strips and 180 g for radial strips), each specimen was tested as follows:

1) A single load versus elongation test, results of which are shown in Figure 8. Radial strips were more extensible than circumferential under all conditions. Tissue modulus was unaffected by any treatment, but depopulated radial strips were significantly more extensible than fresh tissue (113 ± 11.8 vs. 85.9 ± 8.6 mm/mm);

2) A stress relaxation test, results of which are shown in Figure 9. For circumferential and radial strips approximately 10% of the original stress was dissipated in the first 10 sec. Overall, the rate of loss of stress appeared greater in radial strips in general and was fastest in cryopreserved radial strips. At the termination of the test, stress remaining in 37°C depopulated circumferential strips was significantly greater than in fresh tissue; there were no significant differences in the radial strips; and

3) A tensile failure test, results of which are shown in Figure 10. For each condition, circumferential strips were stronger, stiffer, and tougher than radial strips. Cryopreservation and depopulation did not affect these parameters measured in the circumferential direction. Radial strips cut from tissue depopulated at

2185447

either temperature did show greater toughness as compared to fresh.

The description contained herein contains the preferred embodiments of the invention. However, numerous alternative embodiments are contemplated as falling within the scope of the invention. By teaching and by example, the important features of the invention are demonstrated: 1) removal of xenogeneic cells and cell membranes from a tissue potentially useful as an implantable or transplantable graft in humans (shown by histologic and biochemical analyses); 2) under the influence of extracellular matrix glycoprotein, glycosaminoglycan, and growth factor, the acellular tissue can be repopulated with exogenous cells, potentially derived from the recipient of the grafts; 3) maintenance of biomechanical properties similar to those of cryopreserved tissues which are themselves utilized as stable graft materials; and 4) as a result of the depopulation procedure, the propensity of depopulated tissue to stimulate an inflammatory and cellular and humoral immune response in the recipient is reduced.

65902-129

CLAIMS:

1. A process for generating implant tissue from collagenous tissue or connective tissue, the process comprising:

5 A. reducing or eliminating native cells from the collagenous tissue or connective tissue to provide a tissue matrix;

B. treating the tissue matrix with cellular adhesion factor to promote subsequent attachment of cultured
10 allogeneic or autologous cells to the surfaces of the tissue matrix; and

C. repopulating the tissue matrix with the cultured allogeneic or autologous cells.

2. The process of claim 1 wherein the collagenous
15 tissue or connective tissue is selected from heart valve tissue or blood vessels.

3. The process of claim 2 wherein the heart valve tissue is pulmonary or aortic heart valve tissue.

4. The process of any one of claims 1 to 3 wherein
20 the collagenous tissue or connective tissue is of non-human origin, wherein the cells used to repopulate the tissue matrix are of human origin, and wherein the implant tissue generated is substantially non-immunogenic upon implant.

5. The process of claim 4 wherein the tissue matrix
25 is repopulated by incubating the tissue matrix in the presence of fibroblast cells and fibroblast growth factor.

6. The process of claim 5 wherein the fibroblast cells are allogeneous cells.

65902-129

7. The process of claim 5 or 6 wherein the fibroblast cells are derived from stable cell lines.

8. The process of any one of claims 5 to 7 wherein the fibroblast cells are modified genetically by techniques of stable transfection with exogenous genetic material.

9. The process of any one of claims 5 to 8 wherein the fibroblast cells are of human origin and are modified to be substantially non-immunogenic to a recipient of the tissue implant.

10 10. The process of any one of claims 5 to 9 wherein the fibroblast cells are of human origin and are modified to express specific proteins.

11. The process of any one of claims 1 to 10 wherein the native cells are eliminated by treating the collagenous tissue or connective tissue with a solution effective to lyse the cells.

12. The process of claim 11 further comprising treatment of the collagenous tissue or connective tissue with enzyme nuclease effective to decellularize the tissue matrix and provide a tissue matrix of limited immunogenicity.

13. The process of claim 12 wherein the tissue is treated with a nuclease selected from the group comprising RNAase A, DNAase I, EcoR I and Hind III.

25 14. The process of any one of claims 1 to 13 wherein step (A) comprises treating the collagenous tissue or connective tissue with low ionic strength solution and DNAase I and RNAase A, effective to eliminate native cells and provide a tissue matrix of limited immunogenicity, and
30 wherein cell debris, soluble protein and other matter are

65902-129

removed by washing the treated tissue to provide a tissue matrix substantially free of native tissue components antigenic with respect to the implant recipient.

15. The process of any one of claims 1 to 14 wherein
5 the tissue matrix is treated with a cellular adhesion factor comprised of a glycoprotein and a glycosaminoglycan effective to promote attachment of the cells to the tissue matrix during the step (C) of cellular repopulation.

16. The process of any one of claims 1 to 15 wherein
10 the tissue matrix is treated with cellular adhesion factor comprised of one or more extracellular proteins ordinarily associated with the native cells effective to promote cellular attachment to the tissue matrix during the repopulation step (C).

15 17. The process of claim 15 wherein the glycosaminoglycan is heparin, heparin sulfate, chondroitin, chondroitin sulfate, dermatin or dermatin sulfate and the glycoprotein is fibronectin.

18. The process of claim 15 or 16 wherein the
20 collagenous tissue or connective tissue is heart valve tissue of porcine origin.

19. The process of claim 18 wherein the heart valve
tissue matrix is repopulated by incubating the tissue matrix treated according to step (B) in the presence of allogeneic
25 or autologous fibroblast cells and fibroblast growth factor, to provide a xenogeneic valve implant repopulated and revitalized by said fibroblast cells and which is substantially non-immunogenic upon implantation.

20. The process of claim 19 wherein the heart valve
30 tissue matrix is prepared by eliminating native cells and by

65902-129

treatment with enzymes, nucleases, or the nucleases DNAase I and RNAase A to provide the tissue matrix.

21. The process of any one of claims 1 to 20 wherein the implant tissue is allogeneic or xenogeneic implant
5 tissue.

22. A process for treating xenogeneic tissue to produce a xenogeneic tissue having improved compatibility with the immune system of an implant recipient of a species different from the species of the source of the xenogeneic
10 tissue, comprising the steps of

A. applying an amount of cellular adhesion factors to a decellularized xenogeneic tissue matrix effective to promote the subsequent attachment of cultured cells to the xenogeneic tissue matrix, wherein the cellular adhesion
15 factors comprise one or more extracellular proteins ordinarily associated with the xenogeneic tissue in a liquid vehicle, and

B. repopulating the xenogeneic tissue matrix with autogenous or allogeneic cells to provide a substantially
20 non-immunogenic and biomechanically acceptable implant or graft which is vitalized by the cellular repopulation and has improved compatibility with the immune system of the implant recipient,

wherein the xenogeneic tissue is generated from
25 collagenous or connective tissue.

23. The process of claim 22 wherein the collagenous tissue or connective tissue is heart tissue or vascular tissue.

24. The process of claim 22 or 23 wherein the adhesion
30 factors include a glycoprotein and a glycosaminoglycan.

65902-129

25. The process of any one of claims 22 to 24 wherein the tissue matrix is repopulated with fibroblast cells immunologically compatible with the implant recipient.

26. The process of claim 25 wherein the fibroblast
5 cells are modified genetically by techniques of stable transfection with exogenous genetic material.

27. The process of claim 25 or 26 wherein the fibroblast cells are of human origin and are modified to be substantially non-immunogenic upon implantation.

10 28. The process of any one of claims 25 to 27 wherein the fibroblast cells are of human origin and are modified to express specific proteins.

29. The process of any one of claims 22 to 28 wherein the adhesion factors include fibronectin and a
15 glycosaminoglycan selected from the group consisting of dermatin, dermatin sulfate, chondroitin, chondroitin sulfate, heparin sulfate and heparin.

30. The process of claim 29 wherein the collagenous tissue or connective tissue is porcine heart valve tissue,
20 and wherein the cellular repopulation step is conducted by incubating the tissue matrix in a nutrient environment and in the presence of fibroblast cells and an effective amount of fibroblast growth factor.

31. A process for generating a xenogeneic implant or
25 graft from non-human collagenous tissue or connective tissue, the process comprising

A. treating the collagenous tissue or connective tissue to decellularize it and remove cellular and extracellular antigens to provide a tissue matrix;

65902-129

B. treating the tissue matrix with adhesion factors comprising fibronectin and heparin effective to promote attachment thereto of fibroblast cells immunologically acceptable to the implant or graft
5 recipient; and

C. repopulating the tissue matrix treated with adhesion factors by incubating the tissue matrix in the presence of the fibroblast cells and fibroblast growth factor until such cellular repopulation provides a vitalized
10 tissue, and wherein the xenogeneic implant or graft so generated is mechanically, biochemically and immunologically suitable for implantation.

32. The process of claim 31 wherein the fibronectin comprises human plasma fibronectin or human tissue
15 fibronectin.

33. The process of claim 31 or 32 wherein the collagenous tissue or connective tissue is collagenous tissue.

34. The process of claim 31 or 32 wherein the
20 collagenous tissue or connective tissue is connective tissue.

35. The process of claim 33 wherein the fibroblast cells are cultured human fibroblast cells.

36. The process of claim 35 wherein the collagenous
25 tissue is heart valve tissue, and wherein the repopulation cells are human fibroblast cells.

37. The process of any one of claims 31 to 36 further comprising the step of cryopreserving the tissue matrix at a stage prior to the cellular repopulation step.

65902-129

38. The process of claim 34 wherein the connective tissue is decellularized by treatments including treatment with nucleases so as to limit generation of new immunological sites.

5 39. The process of claim 31 wherein the heparin adheres fibronectin to portions of the tissue matrix, and wherein basic human recombinant fibroblast growth factor is employed.

10 40. The process of claim 39 wherein the tissue matrix is aortic or pulmonary heart valve tissue.

41. The process of any one of claims 31 to 40 wherein the fibroblast cells are autogenous cells.

42. The process of any one of claims 31 to 40 wherein the fibroblast cells are allogeneous cells.

15 43. The process of any one of claims 31 to 40 wherein the fibroblast cells are derived from stable cell lines.

44. The process of any one of claims 31 to 43 wherein the fibroblast cells are modified genetically by techniques of stable transfection with exogenous genetic material.

20 45. The process of any one of claims 31 to 43 wherein the fibroblast cells are of human origin and are modified to be substantially non-immunogenic upon implantation.

25 46. The process of any one of claims 31 to 43 wherein the fibroblast cells are of human origin and are modified to express specific proteins.

47. The process of any one of claims 31 to 46, wherein the xenogeneic tissue is of porcine or bovine origin, the adhesion factors comprise purified fibronectin and heparin,

65902-129

and wherein the repopulating cells are human fibroblast cells in the presence of effective amounts of basic or acid fibroblast growth factor and the tissue so produced is a xenogeneic implant substantially free of adverse
5 immunological response upon implantation into a human.

48. The process of any one of claims 31 to 46, wherein the step A comprises treating the xenogeneic tissue with a low ionic strength solution and nucleases.

49. The process of claim 48 wherein the nucleases
10 include at least one member of the group RNAase A, DNAase I, EcoR I and Hind III.

50. The process of claim 31 wherein the xenogeneic tissue is of non-human origin, and is a collagenous tissue; the tissue is decellularized and treated with a low ionic
15 strength solution and DNAase I and RNAase A, effective to eliminate native cells and provide a tissue matrix of limited immunogenicity; and the tissue matrix is treated with an amount of a buffered solution containing fibronectin and heparin sulfate effective to provide sites associated
20 with the tissue matrix which facilitate fibroblast cell attachment thereto; and wherein the tissue matrix is repopulated by incubating it together with fibroblast cells of human origin in the presence of an amount of fibroblast growth factor, effective to facilitate cell growth and
25 repopulation of the tissue matrix with fibroblast cells.

51. The process of claim 50 wherein the transplant tissue is porcine heart valve tissue.

52. The process of claim 50 wherein the fibroblast cells are autogenous.

65902-129

53. The process of claim 50 wherein the fibroblast cells are allogeneic.

54. A process for generating a xenogeneic heart valve from porcine or bovine heart valve tissue which is
5 histologically and immunologically suitable for implantation in a human or mammalian recipient comprising:

A. decellularizing the porcine or bovine heart valve tissue to provide a tissue matrix substantially free of native cellular antigens and treated to limit generation
10 of new immunological sites;

B. applying cellular adhesion factors to the tissue matrix, comprised of one or more extracellular proteins ordinarily associated with the natural tissue, effective to promote attachment of fibroblast cells to the
15 tissue matrix, and repopulating the tissue matrix with allogeneic or autologous fibroblast cells in the presence of fibroblast growth factor immunologically acceptable to the implant recipient to provide a vitalized valve tissue.

55. The process of claim 54 wherein the porcine or
20 bovine heart valve tissue is a pulmonary or an aortic heart valve.

56. A process for generating a graft or heart valve implant suitable for use in a human comprising:

A. preparing a porcine heart valve tissue matrix
25 by decellularizing native porcine heart valve tissue and treating it with enzymes or nucleases effective to decellularize the native porcine heart valve tissue and provide a tissue matrix of limited immunogenicity;

B. applying an effective amount of human plasma
30 fibronectin and heparin to the tissue matrix to promote

65902-129

cellular attachment of allogeneic or autologous fibroblast cells; and

C. repopulating the tissue matrix with fibroblast cells by incubating the tissue matrix in a nutrient media
5 comprised of cultured human fibroblast cells and human recombinant fibroblast growth factor.

57. The process of claim 56 wherein the porcine heart valve tissue is a pulmonary or an aortic heart valve.

58. The process of claim 56 or 57 wherein step A
10 comprises the steps of lysing the native tissue and treatment with RNAase A and DNAase I.

59. The process of any one of claims 56 to 58 wherein the fibroblast cells are autologous cells.

60. The process of any one of claims 56 to 59 wherein
15 the adhesion factors are applied by placing the tissue matrix in a nutrient media containing adhesion factors, and wherein the fibroblast cells and fibroblast growth factor are thereafter employed to repopulate the matrix by adding them in effective amounts to the nutrient media containing
20 the tissue matrix.

61. The process of any one of claims 56 to 60 wherein the fibroblast cells are allogeneic.

62. The process of claim 60 wherein the fibroblast cells are autologous.

25 63. The process of any one of claims 56 to 62 further comprising step D of cryopreserving the tissue matrix prior to further processing.

65902-129

64. The process of any one of claims 56 to 63 wherein the fibroblast cells are derived from stable cell lines.

65. The process of any one of claims 56 to 64 wherein the fibroblast cells are modified genetically by techniques
5 of stable transfection with exogenous genetic material.

66. The process of any one of claims 56 to 65 wherein the fibroblast cells are of human origin and are modified to be substantially non-immunogenic upon implantation.

67. The process of any one of claims 56 to 66 wherein
10 the fibroblast cells are of human origin and are modified to express specific proteins.

68. The process of claim 2, wherein the heart valve tissue is heart valve leaflets, myocardial tissue associated with the valve, aortic conduit extending on the outflow side
15 of the valve or the root of the valve extending to the atrium.

SMART & BIGGAR
OTTAWA, CANADA

PATENT AGENTS

FIG. 1



FIG. 2a




FIG. 2b




FIG. 3a



FIG. 3b



Figure 4.

COLLAGEN AND NONCOLLAGEN PROTEIN SYNTHESIS
IN PORCINE AORTIC HEART VALVE LEAFLETS

Fresh, depopulated (acellular), vs. repopulated with rabbit dermal fibroblasts

□ fresh ▨ depopulated 1 ▩ repopulated w/isolate 1 ▪ repopulated w/isolate 2




Figure 5.

REACTIVITY OF RABBIT ANTISERA RAISED TO EXTRACTS OF CRYOPRESERVED (\circ) OR DEPOPULATED (\square) PORCINE HEART VALVE LEAFLETS—ANTIBODY CAPTURE




FIG. 6a




FIG. 6b



FIG. 7a





FIG. 7b




2185447

Figure 8.

PORCINE AORTIC VALVE LEAFLETS Stress-Strain Relations

○ Fresh △ Cryopreserved ▽ Depopulated (37°C)



2185447



Figure 9.

STRESS RELAXATION IN PORCINE AORTIC LEAFLETS

Effects of Cryopreservation and Depopulation

STRESS RELAXATION IN PORCINE AORTIC LEAFLETS

Effects of Cryopreservation and Depopulation



2185447

Figure 10.

TENSILE FAILURE DATA FOR PORCINE AORTIC VALVE LEAFLETS
EFFECTS OF CRYOPRESERVATION AND DEPOPULATION

Circumferential Strips

	FRESH	CRYO-PRESERVED	DEPOPULATED (37°C)	DEPOPULATED (4°C)
Tissue Modulus	43.8 ± 8.3	35.8 ± 7.0 ^a	58.3 ± 7.6 ^a	46.0 ± 8.2 ^a
Ultimate Tensile Strength	7.4 ± 1.6	5.9 ± 1.1 ^a	10.7 ± 1.3 ^a	9.1 ± 1.5 ^a
Toughness (resilience)	1.6 ± 0.3	1.5 ± 0.4 ^a	2.5 ± 0.5 ^a	2.6 ± 0.6 ^a
Strain at Fracture %	43.7 ± 4.5	44.2 ± 7.3 ^a	57.7 ± 8.1 ^a	67.5 ± 5.0 ^a

Units of MN/m². Mean ± SEM. n, Fresh (8), Cryopreserved (8), Depopulated at 37°C (13), and Depopulated at 4°C (5). ^a Difference not significant compared to fresh tissue.

Radial Strips

	FRESH	CRYO-PRESERVED	DEPOPULATED (37°C)	DEPOPULATED (4°C)
Tissue Modulus	4.9 ± 0.4	5.2 ± 0.9 ^a	5.1 ± 1.3 ^a	7.7 ± 2.9 ^a
Ultimate Tensile Strength	0.9 ± 0.07	0.9 ± 0.2 ^a	1.2 ± 0.3 ^a	1.2 ± 0.2 ^a
Toughness (resilience)	0.4 ± 0.03	0.6 ± 0.2 ^a	1.5 ± 0.3 ^b	0.8 ± 0.1 ^b
Strain at Fracture %	117 ± 8.7	96.4 ± 11.5 ^a	161 ± 26.4 ^a	112 ± 41.9 ^a

Units of MN/m². Mean ± SEM. n, Fresh (8), Cryopreserved (5), Depopulated at 37°C (7), and Depopulated at 4°C (3). ^a Difference not significant compared to fresh tissue. ^b Difference significant at p < 0.05 compared to fresh tissue.