



(51) International Patent Classification:

C07F 15/00 (2006.01) H01L 51/00 (2006.01)

C09K 11/06 (2006.01)

(21) International Application Number:

PCT/US2019/056286

(22) International Filing Date:

15 October 2019 (15.10.2019)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/745,837 15 October 2018 (15.10.2018) US

(71) Applicants: **BOARD OF REGENTS, THE UNIVERSITY OF TEXAS SYSTEM** [US/US]; 210 West 7th Street, Austin, Texas 78701 (US). **THE REGENTS OF THE UNIVERSITY OF COLORADO** [US/US]; 1800 Grant Street, 8th Floor, Denver, Colorado 80203 (US).

(72) Inventors: **DIAS, Rasika**; 1235 Blue Lake Blvd, Arlington, Texas 76005 (US). **JAYARATNA, Naleen B.**; 701 South Nedderman Street, Suite 350, Arlington, Texas 76019 (US). **NOBLE, Richard D.**; 1262 Bear Mountain Court, Boulder, Colorado 80305 (US). **COWAN, Matthew G.**; 36 Alva Street, Denedin (NZ). **PARASAR, Devaborniny**; 701 South Nedderman Street, Suite 350, Arlington, Texas 76019 (US).

(74) Agent: **LEVITIN, Galit et al.**; Meunier Carlin & Curfman LLC, 999 Peachtree Street, NE, Suite 1300, Atlanta, Georgia 30309 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ,

CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).


Declarations under Rule 4.17:

— of inventorship (Rule 4.17(iv))

Published:

— with international search report (Art. 21(3))

(54) Title: SOLID-STATE COPPER(I) SORBENTS FOR OLEFIN SEPARATIONS



(57) Abstract: Disclosed herein is a process for separating a hydrocarbon feed gas mixture comprising constituents including ethylene to produce a separated ethylene product. The disclosed process employs a solid-state ethylene sorbent and temperature and/or pressure swing adsorption and membrane separation and demonstrates a methodology to reduce the net heat of reaction during the adsorption of ethylene onto an adsorbent.

SOLID-STATE COPPER(I) SORBENTS FOR OLEFIN SEPARATIONS**CROSS REFERENCE TO RELATED APPLICATIONS**

[0001] This application claims benefit of priority to U.S. Provisional Application No. 62/745,837, filed October 15, 2018, which is incorporated herein by reference in its entirety.

FIELD

[0002] The present disclosure relates generally to the field of separating a hydrocarbon feed gas mixture comprising alkenes and alkanes to produce a separated alkene product.

BACKGROUND

[0003] The production of polymers such as polyethylene from light gases requires a high purity feedstock of monomers and co-monomers. Due to the small differences in boiling points between the light gases in such a feedstock, industrial production of a high purity feedstock can require the operation of multiple distillation columns, high pressures, and cryogenic temperatures. As such, the energy costs associated with feedstock purification represent a significant proportion of the total cost for the production of such polymers. Further, the infrastructure required for producing, maintaining, and recycling high purity feedstock is a significant portion of the associated capital cost.

[0004] In order to offset some of the costs and maximize production, it can also be useful to reclaim and/or recycle any unreacted feedstock gases, especially the light hydrocarbon reactants, such as ethylene. Ethylene and propylene gases are the most-produced organic chemicals in the world, with their purification costs accounting for ca. 0.3% of the world's total energy consumption.¹ The high energy costs are driven by the use of cryogenic distillation, which could be supplemented or replaced by a lower-energy process such as membrane separation or swing adsorption.²⁻⁴ There has been considerable recent interest in developing materials for both technologies.

[0005] Adsorbent materials show either kinetic or thermodynamic selectivity for adsorbing components of a gas mixture and are used in pressure (PSA) and temperature swing adsorption (TSA) processes to produce high-purity gases. Key parameters for

adsorbent materials include heat of adsorption, working-capacity, selectivity, sorption kinetics, and tolerance to contaminants.

[0006] Various classes of adsorbents are known to be suitable for use in PSA systems, the selection of which is dependent upon the feedstream components and other factors are generally known to those skilled in the art. In general, suitable adsorbents include molecular sieves, silica gel, activated carbon, and activated alumina.

[0007] Heat of adsorption value is important for reducing the heat and cooling energy required to control adsorbent temperature during PSA cycles and control the swing energy required for a TSA process. S. Seo *et al.* combined a solid to liquid phase change ($\Delta H_{\text{melt}} < 19.9 \text{ kJ mol}^{-1}$) with CO_2 chemisorption (ca. -52 kJ mol^{-1}) and noted a significant reduction of the overall heat of adsorption.⁵ A process design taking advantage of the lower overall heat of adsorption showed 55% energy savings compared to standard MEA scrubbing technology.

[0008] N. Nijem *et al.* applied the idea to the well-known phenomena of ‘gate-opening’ phase changes in metal-organic frameworks, termed ‘intrinsic heat management,’ and shown to reduce the energy released by methane adsorption by 33% compared to non-‘gate opening’ frameworks.⁶

[0009] High working-capacity adsorbents are characterized by the observation of steep ‘steps’ in gas adsorption isotherms. These have been achieved through phase changes induced by osmotic pressure and chemical interaction and facilitated by flexible ligands, rearrangement of coordination spheres, or spin-crossover. Alternatively, intermolecular interactions inducing ordering of the gas (adsorbate) phase such as self-propagating reactions and clathrate formation.

[0010] High gas selectivities are required to produce a high-purity product from the adsorbed phase. For ethylene/ethane separation, thermodynamic selectivities of 390:1 have been reported for adsorbents with surface areas $\leq 15 \text{ m}^2\text{g}^{-1}$.⁷ In contrast, porous materials are limited by the high proportions of non-selective surface area, achieving thermodynamic selectivities of usually up to ~30:1 and capable of high kinetic selectivity (50-90:1), which would be useful if technical challenges around preparing thin-film defect-free membrane materials are overcome.

[0011] Accordingly, there is still a need for more efficient and cost-effective processes for ethylene separation. There is a further need for sorbents having high ethylene/ethane selectivities and low heat of adsorption values.

SUMMARY

[0012] In accordance with the purpose(s) of the invention, as embodied and broadly described herein, the invention in one aspect, relates to a process comprising: exposing a trinuclear copper(I) pyrazolate complex to a hydrocarbon feed gas mixture comprising one or more alkenes and one or more alkanes, to form a product comprising a dinuclear-copper(I)-alkene complex. In further disclosed aspects, the one or more alkenes comprise ethylene, propylene, butene, pentene, or isobutylene. In still further disclosed aspects, the one or more alkanes comprise ethane, methane, propane, butane, or pentane.

[0013] In some aspects, the trinuclear copper(I) pyrazolate complex of the disclosed process is a [3,4,5-tris(trifluoromethyl)pyrazolyl]Cu₃ complex ([3,4,5-(CF₃)₃Pz)Cu]₃, [Cu₃]). In yet other aspects, the dinuclear copper(I)-alkene complex comprises a dinuclear copper(I)-ethylene complex. In still further aspects, the dinuclear copper(I)-ethylene complex of the disclosed process is a [3,4,5-tris(trifluoromethyl)pyrazolyl]Cu(C₂H₄)₂ ([3,4,5-(CF₃)₃Pz)Cu(C₂H₄)]₂ complex, [Cu₂•(C₂H₄)₂]).

[0014] Also disclosed herein is a composition comprising a trinuclear copper(I) pyrazolate complex, wherein the composition is reversibly transformed to a dinuclear copper(I)-alkene complex, when exposed to a hydrocarbon feed gas mixture comprising one or more alkenes and one or more alkanes. In still further aspects, the disclosed composition comprises a [3,4,5-tris(trifluoromethyl)pyrazolyl]Cu₃ complex ([3,4,5-(CF₃)₃Pz)Cu]₃, [Cu₃]), wherein the composition is reversibly transformed to a [3,4,5-tris(trifluoromethyl)pyrazolyl]Cu(C₂H₄)₂ ([3,4,5-(CF₃)₃Pz)Cu(C₂H₄)]₂, [Cu₂•(C₂H₄)₂]) when exposed to a hydrocarbon feed gas mixture comprising ethylene and one or more alkanes comprising ethane.

[0015] Additional aspects of the invention will be set forth, in part, in the detailed description, and claims which follow, and in part will be derived from the detailed description or can be learned by practice of the invention. It is to be understood that both the foregoing general description and the following detailed description are exemplary and explanatory only and are not restrictive of the invention as disclosed.

BRIEF DESCRIPTION OF THE DRAWINGS

[0016] The following drawings illustrate by way of example and not limitation. For the sake of brevity and clarity, every feature of a given structure is not always labeled in every figure in which that structure appears.

[0017] **FIGs. 1A-1B** illustrate structures of (**FIG. 1A**) $[(3,4,5-(\text{CF}_3)_3\text{Pz})\text{Cu}]_3$, $[\text{Cu}_3]$ and (**FIG. 2B**) $[(3,4,5-(\text{CF}_3)_3\text{Pz})\text{Cu}(\text{C}_2\text{H}_4)]_2$, $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$.

[0018] **FIGs. 2A-2B** illustrate molecular structures of (**FIG. 2A**) $[(3,4,5-(\text{CF}_3)_3\text{Pz})\text{Cu}]_3$, $[\text{Cu}_3]$ and (**FIG. 2B**) $[(3,4,5-(\text{CF}_3)_3\text{Pz})\text{Cu}(\text{C}_2\text{H}_4)]_2$, $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$.

[0019] **FIGs. 3 A-3B** show (**FIG. 3A**) ethylene adsorption (solid symbols) and desorption (hollow symbols) isotherms of $[\text{Cu}_3]$ at 20, 50, and 70 °C; (**FIG. 3B**) working capacity from a temperature swing from 50 °C to 70 °C.

[0020] **FIG. 4** illustrates a stoichiometry of a reversible transformation of $[(3,4,5-(\text{CF}_3)_3\text{Pz})\text{Cu}]_3$, $[\text{Cu}_3]$ (**1**) to $[(3,4,5-(\text{CF}_3)_3\text{Pz})\text{Cu}(\text{C}_2\text{H}_4)]_2$, $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ (**2**) in an ethylene atmosphere.

[0021] **FIG. 5** shows a ^{19}F NMR spectrum of $[(3,4,5-(\text{CF}_3)_3\text{Pz})\text{Cu}]_3$, $[\text{Cu}_3]$ in CDCl_3 at room temperature.

[0022] **FIG. 6** shows a $^{13}\text{C}\{^1\text{H}\}$ NMR spectrum of $[(3,4,5-(\text{CF}_3)_3\text{Pz})\text{Cu}]_3$, $[\text{Cu}_3]$ in CDCl_3 at room temperature.

[0023] **FIG. 7** shows a ^1H NMR spectrum of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ in CDCl_3 at room temperature. This spectrum also shows the presence of free ethylene resulting from the reverse reaction noted in **FIG. 4**.

[0024] **FIG. 8** shows a ^{19}F NMR spectrum of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ in CDCl_3 at room temperature. This spectrum also shows the presence of $[\text{Cu}_3]$ resulting from the reverse reaction illustrated in **FIG. 4**.

[0025] **FIG. 9** shows a $^{13}\text{C}\{^1\text{H}\}$ NMR spectrum of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ in CDCl_3 at room temperature. Some disproportionation products noted in **FIG. 4** are also present.

[0026] **FIG. 10** shows a Van't Hoff plot for $[\text{Cu}_3]$ binding of ethylene in CDCl_3 solution.

[0027] **FIG. 11** shows a ^1H NMR spectrum of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ in the presence of excess ethylene at various temperatures.

- [0028] **FIG. 12** shows ^1H NMR spectra of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ at various temperatures.
- [0029] **FIG. 13** shows a ^1H NMR spectrum of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ at 35 °C.
- [0030] **FIG. 14** shows a ^1H NMR spectrum of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ at -30 °C.
- [0031] **FIG. 15** shows a ^{19}F NMR spectra of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ at various temperatures.
- [0032] **FIG. 16** shows a ^{19}F NMR spectrum of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ at 35 °C.
- [0033] **FIG. 17** shows a ^{19}F NMR spectrum of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ at -30 °C.
- [0034] **FIG. 18** shows ethylene adsorption (solid symbols) and desorption (hollow symbols) isotherms of $[\text{Cu}_3]$ at 20, 50 and 70 °C.
- [0035] **FIG. 19** shows ethylene adsorption isotherms of $[\text{Cu}_3]$ at 20, 50, and 70 °C past the ‘step’ associated with phase change and chemisorption.
- [0036] **FIG. 20** shows the Claussius-Clapeyron plot derived from the pressure where the step is observed in adsorption isotherms measured at 20, 50, and 70 °C.
- [0037] **FIG. 21** shows ethane adsorption (solid symbols) and desorption (hollow symbols) isotherms of $[\text{Cu}_3]$ at 20, 50, and 70 °C.
- [0038] **FIGs. 22A-22B** illustrate (**FIG. 22A**) an exemplary experimental set up for measurement of gas adsorption using the pressure drop method in one embodiment; and (**FIG. 22B**) an exemplary plot of the pressure vs. time data obtained from an exemplary experiment in one embodiment.
- [0039] **FIG. 23** shows the ethene uptake of $[\text{Cu}_3]$ over five exemplary sorption/desorption cycles. (The time axis has been truncated at 120 min for consistency).
- [0040] **FIG. 24** shows the effect of 4 acetylene and 4 ethylene adsorption/desorption cycles on the crystallinity of $[\text{Cu}_3]$ as evident from PXRD, as well as simulated PXRD data of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ and $[\text{Cu}_3]$ for comparison.
- [0041] **FIG. 25** describes TGA data for $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ and $[\text{Cu}_3]$ using the mass at 125 °C as a reference for the relative mass calculation.
- [0042] **FIG. 26** shows Infrared (IR) data for $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ and $[\text{Cu}_3]$.
- [0043] **FIG. 27** shows Raman data for $[\text{Cu}_3]$ (1), $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ (2) generated from exposure to ethylene in solution in one exemplary embodiment, and $[\text{Cu}_3]$ (3) produced by placing $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ under vacuum at 60 °C in one exemplary embodiment.

- [0044] **FIG. 28** describes a Raman spectrum of [**Cu₃**].
- [0045] **FIG. 29** describes a Raman spectrum of [**Cu₂•(C₂H₄)₂**].
- [0046] **FIG. 30** shows the DSC heating data for [**Cu₂•(C₂H₄)₂**], which converts to [**Cu₃**] during the first cycle. (mol⁻¹ refers to mole of [**Cu₃**] equivalents).
- [0047] **FIG. 31** shows the DSC heating data for [**Cu₃**], (mol⁻¹ refers to mole of [**Cu₃**]).
- [0048] **FIG. 32** shows the DSC cooling data for [**Cu₃**]. (mol⁻¹ refers to mole of [**Cu₃**]).
- [0049] **FIGs. 33A-33B** show the comparison of (**FIG. 33A**) an exemplary experimental PXRD pattern (25 °C) and (**FIG. 33B**) a simulated PXRD pattern from single crystal data (-73 °C) for [**Cu₃**].
- [0050] **FIGs. 34A-34B** show the comparison of (**FIG. 34A**) an exemplary experimental PXRD pattern and (**FIG. 34B**) a simulated PXRD pattern from single crystal data (green) for [**Cu₂•(C₂H₄)₂**] produced via an exemplary solution method in one embodiment.
- [0051] **FIG. 35** shows the comparison of the exemplary experimental PXRD patterns of [**Cu₃**], [**Cu₂•(C₂H₄)₂**] produced via the solution method, and [**Cu₂•(C₂H₄)₂**] produced by treating [**Cu₃**] with ethylene gas in the solid state. In the latter case, less than 1% of [**Cu₃**] remains.
- [0052] **FIG. 36** shows the comparison of the exemplary experimental PXRD patterns of [**Cu₃**] prepared from an exemplary solution and [**Cu₃**] prepared by placing a solid [**Cu₂•(C₂H₄)₂**] under vacuum at 60 °C for 6 hours.
- [0053] **FIGs. 37A-37C** illustrate fluorine atom disorder and atom labelling scheme (**FIG. 37A**), Cu₃N₆ core (**FIG. 37B**), and packing of four molecules of (bottom) of [**Cu₃**] (**FIG. 37C**).
- [0054] **FIG. 38** illustrates atom labelling scheme and asymmetric unit of [**Cu₂•(C₂H₄)₂**] (**2**).
- [0055] **FIG. 39** illustrates two views showing boat shaped Cu₂N₄ core of [**Cu₂•(C₂H₄)₂**] (**2**).

DETAILED DESCRIPTION

[0056] The present invention can be understood more readily by reference to the following detailed description, examples, drawings, and claims, and their previous and following description. However, before the present compositions, articles, devices, systems, and/or methods are disclosed and described, it is to be understood that this invention is not limited to the specific compositions, articles, devices, systems, and/or methods disclosed unless otherwise specified, as such can, of course, vary. It is also to be understood that the terminology used herein is for the purpose of describing particular aspects only and is not intended to be limiting.

[0057] The following description of the invention is also provided as an enabling teaching of the invention in its best, currently known aspect. To this end, those of ordinary skill in the relevant art will recognize and appreciate that changes and modifications can be made to the various aspects of the invention described herein, while still obtaining the beneficial results of the present invention. It will also be apparent that some of the desired benefits of the present invention can be obtained by selecting some of the features of the present invention without utilizing other features. Accordingly, those of ordinary skill in the relevant art will recognize that many modifications and adaptations to the present invention are possible and can even be desirable in certain circumstances and are thus also a part of the present invention. Thus, the following description is provided as illustrative of the principles of the present invention and not in limitation thereof.

DEFINITIONS

[0058] Various combinations of elements of this disclosure are encompassed by this invention, e.g. combinations of elements from dependent claims that depend upon the same independent claim.

[0059] Moreover, it is to be understood that unless otherwise expressly stated, it is in no way intended that any method set forth herein be construed as requiring that its steps be performed in a specific order. Accordingly, where a method claim does not actually recite an order to be followed by its steps or it is not otherwise specifically stated in the claims or descriptions that the steps are to be limited to a specific order, it is no way intended that an order be inferred, in any respect. This holds for any possible non-express basis for interpretation, including: matters of logic with respect to arrangement of steps or operational

flow; plain meaning derived from grammatical organization or punctuation; and the number or type of aspects described in the specification

[0060] All publications mentioned herein are incorporated herein by reference to disclose and describe the methods and/or materials in connection with which the publications are cited.

[0061] It is also to be understood that the terminology used herein is for the purpose of describing particular aspects only and is not intended to be limiting. As used in the specification and in the claims, the term “comprising” may include the aspects “consisting of” and “consisting essentially of.” It is further understood that the term “comprise” means “include,” “have,” and “contain,” but is not limited to, and is not intended to exclude, for example, other additives, components, integers, or steps.

[0062] Unless defined otherwise, all technical and scientific terms used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs. In this specification and in the claims, which follow, reference will be made to a number of terms which shall be defined herein.

[0063] As used herein, the singular forms “a,” “an” and “the” include plural referents unless the context clearly dictates otherwise. Thus, for example, reference to a “complex” or “a composition” includes aspects having two or more complexes or compositions unless the context clearly indicates otherwise.

[0064] Ranges can be expressed herein as from “about” one particular value, and/or to “about” another particular value. When such a range is expressed, another aspect includes from the one particular value and/or to the other particular value. Similarly, when values are expressed as approximations, by use of the antecedent “about,” it will be understood that the particular value forms another aspect. By “about” is meant within 5 % of the value, e.g. within 4, 3, 2, or 1 % of the value. It will be further understood that the endpoints of each of the ranges are significant both in relation to the other endpoint, and independently of the other endpoint. It is also understood that there are a number of values disclosed herein, and that each value is also herein disclosed as “about” that particular value in addition to the value itself. For example, if the value “10” is disclosed, then “about 10” is also disclosed. It is also understood that each unit between two particular units are also disclosed. For example, if 10 and 15 are disclosed, then 11, 12, 13, and 14 are also disclosed.

[0065] As used herein, the terms “optional” or “optionally” mean that the subsequently described event or circumstance may or may not occur, and that the description includes instances where said event or circumstance occurs and instances where it does not.

[0066] As used herein, the term “substantially,” in, for example, the context “substantially free” refers to a composition having less than about 1 % by weight of the stated component. This can include, for example, aspects of less than about 0.5 % by weight, less than about 0.1 % by weight, less than about 0.05 % by weight, or less than about 0.01 % by weight of the stated material, based on the total weight of the composition.

[0067] It is further understood that the term “substantially,” when used in reference to an amount of composition or a component in a composition, refers at least about 80 %, at least about 85 %, at least about 90 %, at least about 91 %, at least about 92 %, at least about 93 %, at least about 94 %, at least about 95 %, at least about 96 %, at least about 97 %, at least about 98 %, at least about 99 %, or about 100 % by weight, based on the total weight of the composition, of a specified feature or component.

[0068] As used herein, the term “substantially,” in, for example, the context “substantially identical reference composition” or “substantially identical reference process” refers to a reference composition comprising substantially identical components, or process steps, in the absence of an inventive component. In another exemplary aspect, the term “substantially,” in, for example, the context “substantially identical reference composition,” refers to a reference composition comprising substantially identical components and wherein an inventive component is substituted with a common or conventionally known in the art component. For example, a substantially identical reference process as described herein can comprise a substantially identical process steps of exposing a copper(I) complex other than a [3,4,5-tris(trifluoromethyl)pyrazolyl]Cu]₃ [(3,4,5-(CF₃)₃Pz)Cu]₃, [Cu₃] complex to a hydrocarbon feed gas mixture comprising one or more alkenes and one or more alkanes.

[0069] As used herein, the term “‘step’ pressure,” refers to a pressure value where a steep change in pressure as shown in gas adsorption isotherm occurs. It is understood that the step pressure is been achieved through phase changes induced by osmotic pressure and chemical interaction and is facilitated by flexible ligands, rearrangement of coordination spheres, or spin-crossover. Alternatively, the step pressure can be achieved through intermolecular interactions inducing ordering of the gas (adsorbate) phase such as self-

propagating reactions and clathrate formation. It is further understood that the 'step' pressure is dependent on a system and can be determined from the system's gas adsorption isotherm.

[0070] While aspects of the present invention can be described and claimed in a particular statutory class, such as the system statutory class, this is for convenience only, and one of skill in the art will understand that each aspect of the present invention can be described and claimed in any statutory class. Unless otherwise expressly stated, it is in no way intended that any method or aspect set forth herein be construed as requiring that its steps be performed in a specific order. Accordingly, where a method claim does not specifically state in the claims or descriptions that the steps are to be limited to a specific order, it is no way intended that an order be inferred, in any respect. This holds for any possible non-express basis for interpretation, including matters of logic with respect to arrangement of steps or operational flow, plain meaning derived from grammatical organization or punctuation, or the number or type of aspects described in the specification.

[0071] In certain aspects, the present disclosure relates to a process comprising: exposing a trinuclear copper(I) pyrazolate complex to a hydrocarbon feed gas mixture comprising one or more alkenes and one or more alkanes, to form a product comprising a dinuclear copper(I)-alkene complex. In yet further aspects, the one or more alkenes comprise ethylene, propylene, butene, pentene, or isobutylene. In still further aspects, the one or more alkanes comprise ethane, methane, propane, butane, or pentane. It is further understood that the disclosed herein trinuclear copper(I) pyrazolate complex is exemplary and other copper pyrazolate complexes can be also used. For example, and without limitation, tetranuclear and polymeric copper pyrazolate complexes can also be utilized in such processes. In still further aspects, the formed product can also comprise a mononuclear copper(I)-alkene complex. In yet further aspects, the formed product can also comprise a copper(I)-alkene complex that shows less drastic structural changes. In still further aspects, it is understood that the pyrazolate complexes useful in the inventive processes are not limited to copper metal. In some exemplary aspects, the pyrazolate complexes can comprise silver (Ag), iron (Fe), nickel (Ni), or cobalt (Co) metals.

[0072] In still further aspects, the hydrocarbon feed gas can be obtained by any methods known in the art. In still further aspects, the hydrocarbon feed gas mixture can comprise one or more alkenes and one or more alkanes. In yet other aspects, the hydrocarbon feed gas mixture can comprise ethylene, propylene, butene, pentene, isobutylene, ethane, methane, propane, butane, or pentane or any combination thereof. It is understood that the

hydrocarbon feed gas can be a raw olefin gas or a pretreated olefin gas. In aspects where the hydrocarbon feed gas is a pretreated olefin gas, the gas can be pretreated to remove one or more components depending on the desired application. In some exemplary aspects, the one or more alkenes present in the hydrocarbon feed gas mixture can comprise ethylene. In yet other aspects, the one or more alkanes present in the hydrocarbon feed gas mixture can comprise ethane. In still further exemplary aspects, the disclosed complexes can be used to separate ethylene from ethane. However, it is understood that such aspects are exemplary and non-limiting and the complexes described herein can be also used to separate other alkenes from other alkanes. It is further understood that the processes and the complexes described herein can be used to separate, for example, propylene gas from other components of the hydrocarbon feed gas. It is further understood that in some exemplary aspects, the presence of ethylene in the hydrocarbon feed gas mixture is not required in order to efficiently separate other alkenes from various alkanes. It is understood that in aspects, where ethylene is not present, other alkenes, such as propylene, butene, pentene, or isobutylene can adsorb similarly on a trinuclear copper(I) pyrazolate complex to form a specific dinuclear copper(I)-alkene complex.

[0073] In exemplary aspects, described herein are processes wherein the one or more alkenes comprise ethylene, wherein the one or more alkanes comprise ethane, and wherein the formed product comprises a dinuclear copper(I)-ethylene complex.

[0074] In yet other aspects, the trinuclear copper(I) pyrazolate complex is a [3,4,5-tris(trifluoromethyl)pyrazolyl]Cu₃ complex ([3,4,5-(CF₃)₃Pz)Cu]₃, [**Cu₃**]). In still further aspects, the dinuclear copper(I)-ethylene complex is a [3,4,5-tris(trifluoromethyl)pyrazolyl]Cu(C₂H₄)₂ ([3,4,5-(CF₃)₃Pz)Cu(C₂H₄)]₂ complex, [**Cu₂**•(C₂H₄)₂]).

[0075] In still further aspects, [**Cu₃**] of the present disclosure can be formed by: a) reacting copper (I) oxide with a precursor 3,4,5-(CF₃)₃pyrazole (3,4,5-(CF₃)PzH) in a solvent-free process to form a product comprising a [3,4,5-tris(trifluoromethyl)pyrazolyl]Cu₃ complex ([3,4,5-(CF₃)₃Pz)Cu]₃, ([**Cu₃**]); and b) extracting [**Cu₃**] with a solvent.

[0076] In certain aspects, the disclosed trinuclear copper(I) pyrazolate complex [**Cu₃**] can be used as an adsorbent for ethylene/ethane separations processes. In some exemplary aspects, the ethylene/ethane separation processes can comprise temperature and/or pressure swing adsorption and membrane separation. In certain aspects, when exposed to ethylene

gas, the copper(I) complex $[\text{Cu}_3]$ can adsorb ethylene. In yet other aspects, the adsorption of ethylene on $[\text{Cu}_3]$ can drive a reversible solid-state transformation to its dinuclear form, $[(3,4,5-(\text{CF}_3)_3\text{Pz})\text{Cu}(\text{C}_2\text{H}_4)]_2$ ($[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$).

[0077] **FIG. 1A** depicts a chemical structure of the copper(I) complex $[\text{Cu}_3]$. In certain aspects, the complex $[\text{Cu}_3]$ is an air-stable white solid that can be prepared by reacting copper(I) oxide with 3,4,5- $(\text{CF}_3)_3\text{PzH}^8$ in a solvent-free process. In yet other aspects, the formed complex $[\text{Cu}_3]$ can be further extracted with a solvent. In still further exemplary aspects, the solvent can comprise a dichloromethane, chloroform, tetrahydrofuran, acetonitrile, or toluene. In yet other aspects the solvent comprises a dichloromethane. In still further aspects, the solvent comprises a chloroform. It is understood that in certain aspects, copper(I) complexes can be sensitive to oxygen and moisture, especially in solutions. In yet other aspects, the presence of various functional groups can affect the sensitivity of copper(I) complex to oxygen and moisture. For example, in certain aspects, the presence of high fluorine content in $[\text{Cu}_3]$ complex can make the complex hydrophobic and/or resistant to oxidation, especially in the solid state. In such aspects, the $[\text{Cu}_3]$ complex comprises about 51% by mass content or the 50% by atom count of fluorine. In still further aspects, the $[\text{Cu}_3]$ complex can comprise about 43% by mass content of fluorine. It was found that the $[\text{Cu}_3]$ complex comprising about 43% fluorine by mass is also stable in air as a solid material but can slowly oxidize in a solution.

[0078] In yet further aspects, the disclosed $[\text{Cu}_3]$ complex can be characterized by any known in the art techniques, for example, and without limitation, by ^{19}F and ^{13}C NMR, Raman spectroscopy, single-crystal and powder XRD, or any combination thereof. Exemplary ^{19}F and ^{13}C NMR spectra of the disclosed $[\text{Cu}_3]$ complex are shown in **FIG. 5** and **FIG. 6**.

[0079] **FIG. 2A** depicts the molecular structure of $[\text{Cu}_3]$. As it is shown in **FIG. 2A**, the $[\text{Cu}_3]$ core comprises three copper atoms bridged by three pyrazolyl groups, forming a nine membered Cu_3N_6 ring as observed in other copper pyrazolates, such as for example and without limitation, $[(3,5-(\text{CF}_3)_2\text{Pz})\text{Cu}]_3$ complexes. However, in contrast to $[(3,5-(\text{CF}_3)_2\text{Pz})\text{Cu}]_3$, which forms columnar structures of zigzag Cu_3N_6 rings and somewhat close inter-trimer $\text{Cu}\cdots\text{Cu}$ contacts,⁹⁻¹¹ the disclosed $[(3,4,5-(\text{CF}_3)_3\text{Pz})\text{Cu}]_3$ complex crystallizes as discrete molecules with no inter-trimer Cu atoms at a close distance. In certain exemplary aspects, the closest inter-trimer $\text{Cu}\cdots\text{Cu}$ distance can be at 5.17 Å, which is much longer than the van der Waals separation of copper atoms, 2.80 Å. In some exemplary aspects, and as

described herein, exposing the disclosed trinuclear copper(I) pyrazolate complex to the hydrocarbon feed gas, can form a product comprising a dinuclear copper(I)-ethylene complex. In still further aspects, the dinuclear copper(I)-ethylene complex is formed by adsorption of ethylene on the trinuclear copper(I) pyrazolate complex. In still further exemplary aspects, the dinuclear copper(I)-ethylene complex $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ can be prepared by exposing $[\text{Cu}_3]$ to ethylene. In certain aspects, the disclosed $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ complex can be prepared by a solution-based process or by a solid-state based process.

[0080] In some exemplary aspects, the disclosed $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ complex can be formed by a solution-based process. In such exemplary aspects, the disclosed dinuclear copper(I)-ethylene complex $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ can be prepared by treating a dichloromethane solution of $[\text{Cu}_3]$ with ethylene gas. In such aspects, the structural transformation and coordination of ethylene can be detected by any known in the art methods, for example, and without limitation by single-crystal X-ray diffraction (SCXRD). **FIGs. 1B** and **2B** show a chemical and molecular structure of the disclosed $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ complex. **FIG. 1B** depicts a chemical structure of [3,4,5-tris(trifluoromethyl)pyrazolyl] $\text{Cu}(\text{C}_2\text{H}_4)_2$ ([3,4,5-(CF_3)₃Pz) $\text{Cu}(\text{C}_2\text{H}_4)_2$ complex, $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$) that is obtained when the complex $[\text{Cu}_3]$ is exposed to the hydrocarbon feed gas comprising ethylene.

[0081] In certain aspects, $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ molecules are dinuclear species with a boat-shaped Cu_2N_4 metallacycles. Copper atoms adopt trigonal planar geometry, and ethylene moieties coordinate with the copper ion in a typical η^2 fashion. In yet other aspects, the coordination of ethylene can also be directly observed by infrared (IR) and/or Raman spectroscopy. In still further aspects, the single-crystal structures of $[\text{Cu}_3]$ and $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ show that these complexes are dense solids.

[0082] It is understood that in some aspects, the product comprising a dinuclear copper(I)-ethylene complex can comprise additional components. **FIG. 7** and **8** show a ^1H and ^{19}F NMR spectra of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ in CDCl_3 at room temperature, respectively. ^1H and ^{19}F NMR spectra indicate that in addition to $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$, free ethylene and $[\text{Cu}_3]$ can also be present in the solution. Without wishing to be bound by any theory, it is hypothesized that a partial dissociation of the copper-ethylene adduct can occur to form its precursors. Proton signals due to free and copper bound ethylene can appear as separate but broad signals indicating an exchange process on the NMR time scale. A peak at 4.54 ppm, as shown in **FIG. 7**, can be attributed to coordinated ethylene, while a peak at 5.34 ppm, as shown in **FIG. 7**, can be attributed to free ethylene.

[0083] Similarly, as can be seen in **FIG. 8**, the presence of the $[\text{Cu}_3]$ complex, resulting from the disproportionation of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ to $[\text{Cu}_3]$ and free ethylene can be observed. For example, peaks at -54.95 ppm and -59.45 ppm, as shown in **FIG. 8**, can be attributed to ethylene coordinated Cu dimer, while peaks at -55.15 ppm and -60.17 ppm, as shown in **FIG. 8**, can be attributed to $[\text{Cu}_3]$.

[0084] **FIG. 9** shows a $^{13}\text{C}\{^1\text{H}\}$ NMR spectrum of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ in CDCl_3 at room temperature. Similarly to ^1H and ^{19}F NMR spectra, the $^{13}\text{C}\{^1\text{H}\}$ NMR also shows the presence of $[\text{Cu}_3]$ resulting from the disproportionation of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ to $[\text{Cu}_3]$ and free ethylene.

[0085] **FIG. 4** illustrates a stoichiometrical reaction of a reversible transformation of $[(3,4,5-(\text{CF}_3)_3\text{Pz})\text{Cu}]_3$, $[\text{Cu}_3]$ (**1**) to $[(3,4,5-(\text{CF}_3)_3\text{Pz})\text{Cu}(\text{C}_2\text{H}_4)]_2$, $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ (**2**) in an ethylene atmosphere.

[0086] It is understood, and as it is shown in detail below, the equilibrium energy for ethylene binding in a solution can be determined using variable temperature NMR, based on relative concentrations of C_2H_4 , $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$, and $[\text{Cu}_3]$ in CDCl_3 solution at temperatures between 35 and -30 °C. In still further aspects, the binding energy can be found using Van't Hoff analysis. In such exemplary aspects, the disclosed compounds can show binding energy of $-28 \text{ kJ}\cdot\text{mol}^{-1}$, which is significantly smaller than the $-41 \text{ kJ}\cdot\text{mol}^{-1}$ reported for a Cu(I) di-imine complex.¹² Without wishing to be bound by any theory, this difference in ethylene coordination energies can be attributed to a combination of ligand field effects and the net rearrangement energy of the $[\text{Cu}_3]$ to $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ transformation.

[0087] In yet other aspects, the disclosed dinuclear $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ complex can be prepared by a solid-state based process. In certain aspects, a solid $[\text{Cu}_3]$ complex can be treated, for example, with a hydrocarbon feed gas mixture comprising one or more alkenes and one or more alkanes. In yet other aspects, a solid $[\text{Cu}_3]$ complex can be treated, for example, with a hydrocarbon feed gas mixture comprising ethylene and one or more alkanes. Yet in other aspects, a solid $[\text{Cu}_3]$ complex can be treated with ethylene. The structure of the $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ complex can be confirmed using PXRD.

[0088] In still further aspects, the process of the instant disclosure can further comprise a step of desorption of ethylene from the dinuclear copper(I)-ethylene complex. In such exemplary aspects, the ethylene desorption can result in a regenerated trinuclear copper(I) pyrazolate complex, as disclosed herein. In certain aspects, the step of desorption

can be performed at a temperature from about -50 °C to about 200 °C, including exemplary values of about -40 °C, about -30 °C, about -20 °C, about -10 °C, about 0 °C, about 10 °C, about 20 °C, about 30 °C, about 40 °C, about 50 °C, about 60 °C, about 70 °C, about 80 °C, about 90 °C, about 100 °C, about 110 °C, about 120 °C, about 130 °C, about 140 °C, about 150 °C, about 160 °C, about 170 °C, about 180 °C, and about 190 °C. It is understood that the step of desorption can be performed at a temperature having any value between any two foregoing values. In still further aspects, the step of desorption can be performed at a pressure from about 0 bar to about 500 bar, including exemplary values of about 0.01 bar, about 0.02 bar, about 0.03 bar, about 0.04 bar, about 0.05 bar, about 0.06 bar, about 0.07 bar, about 0.08 bar, about 0.09 bar, about 0.1 bar, about 0.5 bar, about 1 bar, about 10 bar, about 20 bar, about 30 bar, about 40 bar, about 50 bar, about 60 bar, about 70 bar, about 80 bar, about 90 bar, about 100 bar, about 150 bar, about 200 bar, about 250 bar, about 300 bar, about 350 bar, about 400 bar, and about 450 bar. It is understood that the step of desorption can be performed at a pressure having any value between any two foregoing values. In yet other aspects, the step of desorption can be performed at a temperature from about -50 °C to about 200 °C and a pressure from about 0.1 bar to about 0 bar. In yet other aspects, the ethylene adsorption of the disclosed process can result in an endothermic structural rearrangement of [Cu₃] to [Cu₂•(C₂H₄)₂].

[0089] In certain aspects, the ethylene desorption can be achieved using temperature in a range from about 50 °C to about 150 °C, as demonstrated by TGA (**FIG. 25**) and DSC (**FIG. 30**) and vacuum in a pressure range from about 0.1 bar to about 0 bar, as demonstrated through Raman spectroscopy (**FIG. 27**), and gas adsorption isotherms (**FIG. 3A**, **FIG. 18**, and **FIG. 19**). Unexpectedly, inventors have found that a significant structural rearrangement [Cu₃] ↔ [Cu₂•(C₂H₄)₂] can be fully reversible. Such reversibility of the process can be further demonstrated through a comparison of experimental and simulated powder X-ray diffraction, as shown in **FIG. 33** through **FIG. 36**. These “Teflon lined” adducts contain heavily fluorinated peripheries and weakly coordinating pyrazolates.¹³ Materials containing C-F bonds are known to have low intermolecular dispersion and produce porous materials that undergo small structural changes in response to increasing pressure. Therefore, without wishing to be bound by any theory, it was suggested that the high degree of fluorination of [Cu₃] can provide a local “fluorocarbon” medium and weak Cu-N interactions to facilitate such unexpected solid-state transformation.

[0090] In still further exemplary aspects, the process described herein comprises a step of separating the one or more alkenes from one or more alkanes. In still further exemplary and non-limiting aspects, the process described herein comprises a step of separating ethylene from ethane. Without wishing to be bound by any theory, it is hypothesized that $[\text{Cu}_3]$ has different ethylene and ethane adsorption properties. In certain aspects, the ethylene and ethane adsorption properties of $[\text{Cu}_3]$ can be measured using variable temperature single-gas adsorption isotherms (**FIG. 3A-B, FIG.18, FIGs. 19-21**). In other aspects, the use of such isotherms can allow to determine a 'step' at which the most gas loading can occur as a function of temperature. As can be seen in **FIG. 3A-B and FIG.18**, most loading occurs at a 'step' pressure that increases with increasing temperature. It was found that in some aspects, the shape of adsorption of isotherm can have a significant potential for use in the pressure or temperature swing processes, because the pressure or temperature would only need to be changed by a small amount to bind/release almost the full capacity of the adsorbent. Similar adsorption isotherms have been observed for phase change sorption processes in porous solids, H_2 and N_2 clathrate formation, cooperative insertion of CO_2 , and the chemisorption of ethylene in small molecule adsorbents. Without wishing to be bound by any theory, it was hypothesized that for the $[\text{Cu}_3]$ complexes, the 'step' can be correlated to the phase change associated with the rearrangement from $[\text{Cu}_3]$ to $[\text{Cu}_2 \cdot (\text{C}_2\text{H}_4)_2]$. In certain exemplary aspects, The Claussius-Clapeyron equation can be used to determine the energy associated with the 'step.' In some exemplary aspects, the energy associated with the 'step,' calculated using Claussius-Clapeyron equation was 38 kJ mol^{-1} per $[\text{Cu}_3]$ ($13 \pm 1 \text{ kJ mol}^{-1}$ per Cu ion/ethylene interaction). Above the 'step,' Van't Hoff analysis of the isotherms can be used to determine chemisorption energy. In some exemplary aspects, based on Van't Hoff analysis, the chemisorption energy was found to be only -3 kJ mol^{-1} per Cu ion. Again, without wishing to be bound by any theory, these values can be reflective of either only surface adsorption, or a balance between endothermic phase change and exothermic chemisorption processes.

[0091] In still further aspects, the process described herein exhibits a decrease of a heat of adsorption by about 50 % to about 85 %, including exemplary values of about 60 %, about 65 %, about 70 %, about 75 %, and about 80 %, when compared to a substantially identical reference process comprising a copper (I) complex that is not $[\text{Cu}_3]$.

[0092] In still further aspects, at least a portion of the ethylene adsorption in disclosed process occurs at a 'step' pressure of about 2 kPa to about 30 kPa, including exemplary

values of about 5 kPa, about 10 kPa, about 15 kPa, about 20 kPa, and about 25 kPa (or about 0.02 bar to about 0.3 bar, including exemplary values of about 0.05 bar, about 0.1 bar, about 0.15 bar, about 0.2 bar, and about 0.25 bar), and a temperature from about 20 °C to about 75 °C, including exemplary values of about 25 °C, about 30 °C, about 35 °C, about 40 °C, about 45 °C, about 50 °C, about 55 °C, about 60 °C, about 65 °C, and about 70 °C (or about 293 K to about 348 K, including exemplary values of about 298 K, about 303 K, about 308 K, about 313 K, about 318 K, about 323 K, about 328 K, about 333 K, about 338 K, and about 343 K) .

[0093] In still further aspects, the at least a portion of the ethylene adsorption at the disclosed ‘step’ pressure comprises greater than 0 % to 100 %, including exemplary values of about 5 %, about 10 %, about 20 %, about 30 %, about 40 %, about 50 %, about 60 %, about 70 %, about 80 %, about 90 %, and about 95 % of the overall ethylene adsorption. In yet other aspects, the at least a portion of the ethylene adsorption at the disclosed ‘step’ pressure comprises more than about 5 %, more than about 10 %, more than about 20 %, more than about 30 %, more than about 40 %, more than about 50 %, more than about 60 %, more than about 70 %, more than about 80 %, more than about 90 %, or more than about 95 % of the overall ethylene adsorption. In still further aspects, the at least a portion of the ethylene adsorption at the disclosed ‘step’ pressure comprises at least about 5 %, at least about 10 %, at least about 20 %, at least about 30 %, at least about 40 %, at least about 50 %, at least about 60 %, at least about 70 %, at least about 80 %, at least about 90 %, or at least about 95 % of the overall ethylene adsorption.

[0094] In still other aspects, differential scanning calorimetry can be used to investigate the energies of the ethylene desorption process and associated phase change (**FIG. 30**). As can be seen in **FIGs. 30** and **32**, the melt and solidification energy of **[Cu₃]** was found to be 23.8-24.3 kJ mol⁻¹. **FIG. 30** shows a DSC scan of **[Cu₂•(C₂H₄)₂]**. This DSC scan of **[Cu₂•(C₂H₄)₂]** reveals several endothermic processes that occur at 100-130 °C with a total energy of 60.9 kJ mol⁻¹. Without wishing to be bound by any theory, these processes can be associated with the combination of melting and ethylene desorption.¹⁴ In yet other aspects, the ethylene desorption energy can be found by subtracting the **[Cu₃]** melt energy. Based on these calculations, it was found that the ethylene desorption energy is about 13 kJ mol⁻¹ per Cu ion/ethylene interaction (based on ethylene loading). The second cycle of the same sample shows no further gas desorption, indicating complete conversion of **[Cu₂•(C₂H₄)₂]** to **[Cu₃]** (i.e. release of all adsorbed ethylene). These results show that the use of inventive complexes

can overcome the slow desorption kinetics observed for other pressure swing adsorption processes and position $[\text{Cu}_3]$ as a potential adsorbent for a TSA process.

[0095] **Table 1** shows a summary of aggregated ethylene chemisorption/desorption energies of the $[\text{Cu}_3]$ to $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ transformation, as determined by various experimental techniques.

[0096] **Table 1. Aggregated ethylene chemisorption/desorption energies of the $[\text{Cu}_3]$ to $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ transformation, as determined by various experimental techniques.**

Energies associated with ethylene chemisorption	(kJ mol ⁻¹)
DSC	
Overall per $[\text{Cu}_3]$ unit	60.9
$[\text{Cu}_3]$ melt energy	24.5
Ethylene desorption energy for $[\text{Cu}_3]$	36.4
Per Cu – C_2H_4 interaction	13.1
Adsorption Isotherms	
Ethylene adsorption ‘step’ per $[\text{Cu}_3]$ unit	-38 ± 2
‘Step’ energy per Cu $\cdots\text{C}_2\text{H}_4$ interaction	-13 ± 1
After ‘step’ adsorption per $[\text{Cu}_3]$ unit	-8.9
After ‘step’ adsorption per Cu $\cdots\text{C}_2\text{H}_4$ interaction	-3
Solution State (NMR)	
Overall equilibrium	-171 ± 45
Per $[\text{Cu}_3]$ unit	-86 ± 24
Per Cu – C_2H_4 interaction	-28 ± 8

[0097] It can be seen from **Table 1** that the aggregated data for the overall energy of ethylene chemisorption during the $[\text{Cu}_3]$ to $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ transformation are internally consistent at ca. -13 ± 1 kJ mol⁻¹ per copper(I) ion/ethylene interaction. This value is significantly lower than ethylene adsorption/chemisorption on other copper(I) complexes, which ranges from -22 kJ mol⁻¹ to -55 kJ mol⁻¹ (Median -36 kJ mol⁻¹). Without wishing to be bound by any theory, the difference can be attributed to the phase change energy associated with the physical constraints of the solid-state $[\text{Cu}_3]$ to $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ transformation. The solution-state binding energy of -28 ± 8 kJ·mol⁻¹ captures the same bond-making and bond-breaking processes of the $[\text{Cu}_3]$ to $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ transformation, and thus it can be suggested that overcoming the intermolecular crystal lattice interactions and the movement of molecules in the solid can pose a further endothermic barrier to the structural rearrangement.

[0098] In certain aspects, the rate of ethylene chemisorption by $[\text{Cu}_3]$ can be measured using any appropriate methods known in the art. In certain aspects, the rate of ethylene chemisorption by $[\text{Cu}_3]$ can be measured using a dead-end adsorption apparatus. It

was found in some exemplary aspects, that the initial chemisorption (1 min) is rapid at $0.22\text{--}0.27\text{ mol}_{\text{ethylene}}\text{ mol}_{\text{complex}}^{-1}\text{ min}^{-1}$ but decreases significantly to $8 \times 10^{-3}\text{ mol}_{\text{ethylene}}\text{ mol}_{\text{complex}}^{-1}\text{ min}^{-1}$ and continues to decline over time. Without wishing to be bound by any theory, the decrease in uptake rate over time can be potentially linked to the low surface area of the **[Cu₃]** complex ($0.66\text{ m}^2\text{ g}^{-1}$). It was hypothesized that transport of ethylene through the interior of the **[Cu₃]** particles is further hindered by the kinetics of the solid-state structural transition of **[Cu₃]** to **[Cu₂•(C₂H₄)₂]**. It was found that the ethylene capacity of **[Cu₃]** after 120 minutes is 31%, similar to the results obtained for **[Ag(6,6'-dimethyl-2,2'-bipyridine)][BF₄]** (34%), which had close contacts between silver(I) ions, and much lower than **[Ag(6,6'-dimethyl-2,2'-bipyridine)][OTf]** (84%), which did not have close contacts between silver(I) ions⁷. It is inferred from breakthrough curve measurements that the adsorption rate of ethylene in porous solids (surface areas $>100\text{ m}^2\text{ g}^{-1}$) is much faster than in these discrete molecules ($<10\text{ m}^2\text{ g}^{-1}$).

[0099] Acetylene adsorption is a known issue for the industrial processing of raw olefin mixtures. Acetylene, however, is not present in the ethylene/ethane pre-feed for distillation, and therefore, ethylene/ethane separation in such processes is not expected to be affected by acetylene. In certain aspects, however, the presence of acetylene can affect the adsorption properties of **[Cu₃]** complex. In such exemplary aspects, the effect of acetylene on the adsorption properties of **[Cu₃]** complex can be determined by exposing **[Cu₃]** complex to acetylene. For example, seven alternate 120-minute acetylene/ethylene adsorption cycles were measured using a dead-end adsorption apparatus. The acetylene capacity remained consistent ($0.37\text{ mmol}\cdot\text{g}^{-1}$) over the cycles, but the ethylene capacity decreased from 0.44 to $0.13\text{ mmol}\cdot\text{g}^{-1}$. PXRD data showed a loss of order and patterns unrelated to either **[Cu₃]** or **[Cu₂•(C₂H₄)₂]**. Without wishing to be bound by any theory, it was hypothesized that the structure of the complex can be permanently degraded by exposure to acetylene.

[00100] It is understood that the disclosed composition of **[Cu₃]** can be used in various processes. In some exemplary aspects, however, where adsorbents or membrane systems are needed to treat raw olefin feeds, such olefin feeds need to be pretreated to remove acetylene. In yet other exemplary aspects, when acetylene is not present in olefin mixtures, for example, used for cryogenic distillation **[Cu₃]** can be used in a distillation/alternative hybrid process. In still further aspects, the disclosed composition of **[Cu₃]** can be used in a pressure swing adsorption, vacuum swing adsorption, or temperature swing adsorption process.

[00101] In still further aspects, the disclosed process can be used to separate ethylene from ethane. In certain aspects, the process does not comprise the adsorption of ethane on the trinuclear copper(I) pyrazolate complex. In yet other aspects, the process does not comprise the adsorption of ethane on the **[Cu₃]** complex.

[00102] In certain aspects, the disclosed trinuclear copper(I) pyrazolate complex exhibits a high ethylene/ethane selectivity of from about 0 to about 136:1, including exemplary values of about 1:1, about 2:1, about 5:1, about 10:1, about 20:1, about 30:1, about 40:1, about 50:1, about 60:1, about 70:1, about 80:1, about 90:1, about 100:1, about 110:1, about 120:1, about 130:1, and about 135:1, as determined from the equilibrium loadings at 1 atm and a temperature from about 20 °C to about 70 °C. In yet other aspects, the ethylene/ethane selectivity of **[Cu₃]** complex determined from the equilibrium loadings at 1 atm is 136:1 (at 20 °C). In yet other aspects, the ethylene/ethane selectivity of **[Cu₃]** complex determined from the equilibrium loadings at 1 atm is 131:1 (at 70 °C)

[00103] **Table 2** summarizes ethylene/ethane selectivities of various adsorbents. It can be seen from **Table 2** that the selectivities of the disclosed complexes are higher than those observed for chemisorption on porous solids (3.6-27 ethylene: 1 ethane), which suffer from high non-specific surface areas, but are lower than for other silver(I)-based small-molecule systems (390:1).

[00104] **Table 2. Comparison of ethene uptake and ethene/ethane sorption selectivity values of [Cu₃] measured in this study with those reported for other solid-state ethylene/ethane sorbent materials in the literature. (adapted from C. A. Grande *et al* (2010))**

<i>Material</i>	<i>Ethene Uptake (mmol_{ethene}/g_{material})</i>	<i>T (K)</i>	<i>P (atm)</i>	<i>Ethene/Ethane Selectivity</i>	<i>Reference</i>
Inventive [Cu₃]	2.63	343	1	131	
Inventive [Cu₃]	2.76	293	1	136	
[Ag ^I (2,2'-bipyridine)][BF ₄]	2.38	293	0.9	390	⁷
[Ag ^I (6,6'-dimethyl-2,2'-bipyridine)][OTf]	2.18	293	0.9	340	⁷
PAF-1-SO ₃ Ag	4.1	296	1	27 ^a	15
Zeolite 5A	~2.3	303	1	— ^b	16
Zeolite NaX	~4.2	305	1	8 ^a	15, 17
CuA ₁₀ B ₁	~1.8	298	0.79	3.8 ^a	15, 18
CoMOF-74	—	—	—	6.4 ^a	15, 19

<i>Material</i>	<i>Ethene Uptake (mmol_{ethene}/g_{material})</i>	<i>T (K)</i>	<i>P (atm)</i>	<i>Ethene/Ethane Selectivity</i>	<i>Reference</i>
MgMOF-74	7.2	296	1	5.6 ^a	15, 19
Cu-BTC	7.2	296	1	3.6 ^a	15, 19
NOTT-102	5.8	296	1	3.8 ^{a c}	15, 19
FeMOF-74	—	318	1	11 ^a	15, 20
HOF-4	11.1	296	1	14 ^a	21
Ag(I)/phenanthroline-based polymer	5.04	293	1 bar	15 ^d	22
[Ag ^I (phen-based ligand) ₂] ⁺ OTf ⁻	0.20	293	1 bar	13	15

^aCalculated using ideal absorbed solution theory (IAST) for an equimolar amount of ethene and ethane at 296 K and 100 KPa. ^bData not shown. ^cApproximately determined from Figure 3 in Ref. 1. ^dIdeal solubility selectivity.

DESCRIPTION OF ILLUSTRATIVE EMBODIMENTS

[00105] The current disclosure provides a number of advantages over known cryogenic ethylene/ethane separation processes. For example, the disclosure provides a solid-state ethylene sorbent that could underpin new ethylene/ethane separation processes. The disclosure also provides processes that include temperature and/or pressure swing adsorption and membrane separation. This disclosure describes the principle of using an endothermic structural rearrangement to compensate for an exothermic heat of adsorption--significantly reducing the net heat of adsorption of ethylene onto an adsorbent.

[00106] The disclosure further provides a synthetic design methodology to reduce the heat of adsorption for adsorbents designed to adsorb olefins (for example, ethylene) from paraffins (for example, ethane).

[00107] The limiting energy cost for the sorbent is approximately 1/10th that of cryogenic distillation, opening the door to energy and cost savings of up to 90%. By operating in the solid-state and avoiding reaction with trace contaminants in the raw ethylene feed, the invention overcomes limitations that have previously crippled the development of separation processes that could provide low-energy alternatives to cryogenic distillation.

EXAMPLES

[00108] The following examples are put forth so as to provide those of ordinary skill in the art with a complete disclosure and description of how the compounds, compositions, articles, devices and/or methods claimed herein are made and evaluated and are intended to be purely exemplary and are not intended to limit the disclosure. Efforts have been made to

ensure accuracy with respect to numbers (e.g., amounts, temperature, etc.), but some errors and deviations should be accounted for.

1.1 Search for comparable ethylene adsorption on copper

[00109] **Table 3** shows the ethylene binding energy on the inventive compositions compared to other known in the art copper and copper-containing materials.

[00110] **Table 3. Literature examples of ethylene binding on copper and copper-containing materials.**

Ethylene adsorption energy (kJ mol ⁻¹)	Measurement type	Reference
-13.8 (step)	Isotherm	Inventive composition
-3 (past 'step')	Isotherm	Inventive composition
-13.1	DSC	Inventive composition
-28.5	NMR (Solution)	Inventive composition
-24	Isotherm	23
-36.1	Isotherm	24
-21.5, -23.7	Calculation	25
-54.0	Calculation	26
-25	Isotherm	27
-22	Calculation	28
-82, -119	Calculation	29
-34	Isotherm	30
Exothermic	Isotherm	31
-29.1	Isotherm	32
-33.8, -125.4	Calculation	33
-55	Calculation	34
-45.0	Isotherm	35
-88	Isotherm	36
-37.6	Isotherm	37
-26 ± 8	Calculation	38
-55, -180	Desorption	39
-45	Calculation	38
-11.1, -10.9	Desorption	40
-86.8	Calculation	41
-32	Isotherm	42
-36	Desorption	43
Exothermic	Isotherm	44
-42.2	Isotherm	45
-36	Median	
-45	Average	

1. Experimental Section

1.1 Instrumentation

[00111] All manipulations were carried out under an atmosphere of purified nitrogen using standard Schlenk techniques or in a MBraun glove-box equipped with a -25 °C refrigerator. Solvents were purchased from commercial sources, purified prior to use. NMR spectra were recorded at 25 °C on a JEOL Eclipse 500 and JEOL Eclipse 300 spectrometer (¹H, 500.16 MHz and 300.53 MHz; ¹³C, 125.78 MHz, and 75.59 MHz; ¹⁹F, 470.62 MHz, and 282.78 MHz), unless otherwise noted. Proton and carbon chemical shifts are reported in ppm versus Me₄Si. ¹⁹F NMR values were referenced to external CFCI₃. Melting points were obtained on a Mel-Temp II apparatus and were not corrected. Elemental analyses were performed using a Perkin-Elmer Model 2400 CHN analyzer. Raman data were collected on a Horiba Jobin Yvon LabRAM Aramin Raman spectrometer with a HeNe laser source of 633nm. IR data were collected on a Bruker Alpha FTIR spectrometer with an ATR attachment. Gas sorption measurements were performed using an experimental apparatus and method described previously (see Ideal (i.e., Single-Gas) Ethylene/Ethane Uptake Data section for details). The gas sorption measurements were performed at 20±1 °C with a feed pressure of 1.0±0.1 atm. Powder X-ray diffraction (PXRD) spectra were collected using a Bruker D8 ECO or Inel CPS 120 PXRD system with a monochromated Cu K α radiation source. 3,4,5-(CF₃)₃PzH was prepared by reported methods.^{8,46} All other reactants and reagents were purchased from commercial sources.

1.2 Materials Preparation

[(3,4,5-(CF₃)₃Pz)Cu]₃ ([Cu₃]).

[00112] Freshly dried 3,4,5-(CF₃)₃PzH (500 mg, 1.83 mmol) and Cu₂O (217 mg, 1.51 mmol) were placed in a Schlenk flask attached to a reflux condenser, slowly heated to 125 °C and kept for 4 h while stirring. A heat gun was used to meltdown the pyrazole condensed on the wall of the Schlenk flask, as needed. Excess 3,4,5-(CF₃)₃PzH was removed by sublimation and the product was extracted into dichloromethane and filtered through a bed of Celite. The filtrate was collected and the solvent was removed under reduced pressure to obtain [(3,4,5-(CF₃)₃Pz)Cu]₃ as a white powder (1.36 g, 90% based on Cu₂O). A solution of [(3,4,5-(CF₃)₃Pz)Cu]₃ in CS₂ was evaporated to dryness to obtain X-ray quality crystals. M.p.: 110 °C. Anal. Calc. for C₁₈N₆F₂₇Cu₃: C, 21.54; H, 0.00; N, 8.37. Found: C, 21.23; H, <0.1; N, 8.81. ¹⁹F NMR (CDCl₃): δ (ppm) -55.10 (br s), -60.10 (q, 8.9 Hz) (**FIG. 5**) ¹³C[¹H] NMR (CDCl₃): δ (ppm) 111.3 (q, ²J_{C-F} = 40.7 Hz, CCF₃), 117.8 (q, ¹J_{C-F} = 274.7 Hz, CF₃), 119.1 (q, ¹J_{C-F} = 266.3 Hz, CF₃), 143.3 (q, ²J_{C-F} = 39.5 Hz, CCF₃) (**FIG. 6**). Comparison of PXRD data

of bulk material to simulated PXRD pattern based on single-crystal X-ray data and the cell dimensions also confirm the identity of the product.


[(3,4,5-(CF₃)₃Pz)Cu(C₂H₄)]₂ ([Cu₂•(C₂H₄)₂])

[00113] [(3,4,5-(CF₃)₃Pz)Cu]₃ (250 mg, 0.25 mmol) was dissolved in 10 mL of CH₂Cl₂, ethylene was bubbled for 10 min. The solution was kept at -5 °C to obtain X-ray quality colorless crystals of [(3,4,5-(CF₃)₃Pz)Cu(C₂H₄)]₂ (245 mg, 90% based on [(3,4,5-(CF₃)₃Pz)Cu]₃. M.p. 128 -130 °C. Comparison of PXRD data of bulk material to simulated PXRD pattern based on single-crystal X-ray data and the cell dimensions confirm the identity of the bulk product. Room temperature NMR data: ¹H NMR (CDCl₃): δ (ppm) 4.54 (br s, C₂H₄; resonance due to free ethylene resulting from dissociation from copper also observed at 5.34 (br s)) (**FIG. 7**). ¹⁹F NMR (CDCl₃): δ (ppm) -54.95 (sept, J = 7.2 Hz), -59.45 (q, J = 7.2 Hz) ([Cu₃] generated due to ethylene loss from [(3,4,5-(CF₃)₃Pz)Cu(C₂H₄)]₂ also present in the mixture and its signals were observed at -55.15 br s), -60.17 (d, J_{F-F} = 5.3)) (**FIG. 8**). ¹³C[¹H] NMR (CDCl₃): (selected peaks) δ (ppm) 85.6 (s, CH₂=CH₂; free ethylene signal in this mixture was found as a broad peak at δ 115.6) (**FIG. 9**) NMR data of [(3,4,5-(CF₃)₃Pz)Cu(C₂H₄)]₂ at -40 °C with added ethylene: ¹H NMR (CDCl₃): δ (ppm) 4.51 (br s). ¹⁹F NMR (CDCl₃): δ (ppm) -54.9 (sept, J = 6.5 Hz), -59.3 (q, J = 6.5 Hz). NMR data of [Cu₂•(C₂H₄)₂] at -80 °C with excess ethylene: ¹H NMR (CD₂Cl₂): δ (ppm) 4.47 (s). ¹⁹F NMR (CDCl₃): δ (ppm) -55.1 (m), -59.6 (m). Drying solid [Cu₂•(C₂H₄)₂] under vacuum leads to slow loss of coordinated ethylene (much faster at 60 °C). Solid samples of [Cu₂•(C₂H₄)₂] kept at room temperature also lose ethylene slowly over a period of many days.

1.3. Variable temperature ¹H NMR spectroscopic study of [Cu₂•(C₂H₄)₂] with excess ethylene in solution

[00114] A quantitative variable temperature experiment was then performed using a known concentration of [Cu₂•(C₂H₄)₂] to obtain equilibrium constant data (*K*) at various temperatures. Peak integrals were combined with the equilibrium expression (**Equation 1**). The concentrations of each species were related through ¹H and ¹⁹F NMR, i.e. ¹H quantifies the ratio of [Cu₂•(C₂H₄)₂] and free C₂H₄, and ¹⁹F NMR quantifies the ratio of [Cu₂•(C₂H₄)₂] and [Cu₃]. The heat of reaction was estimated using a Van't Hoff analysis (Eqn. 3) (**Table 4**). The presented results give the overall equilibrium energy for the equilibrium, which includes ethylene binding and rearrangement from [Cu₃] to [Cu₂•(C₂H₄)₂]. The measured heat of adsorption value of -28.5 kJ mol⁻¹ is ca. 10 kJ mol⁻¹ lower than other copper(I) complexes

reported in the literature. Likewise, the entropy change is ca. half (-96 J mol^{-1} vs. -200 J mol^{-1}). these observations were correlated to the structural rearrangement of $[\text{Cu}_3]$ to $[\text{Cu}_2 \cdot (\text{C}_2\text{H}_4)_2]$.



$$K = \frac{[\text{Cu}_2 \cdot (\text{C}_2\text{H}_4)_2]^3}{[\text{Cu}_3]^2 [\text{C}_2\text{H}_4]^6}$$

Equation 1. Equilibrium equation used for binding of ethylene in CDCl_3 solution.

$$\ln(K) = \frac{-\Delta H}{RT} + \frac{\Delta S}{R}$$

Equation 2. Equation used for the Van't Hoff analysis, where K = the equilibrium constant for the reversible reaction shown above; ΔH = change in enthalpy ($\text{J} \cdot \text{mol}^{-1}$); ΔS = change in entropy ($\text{J} \cdot \text{mol}^{-1}$); R = the gas constant ($\text{J} \cdot \text{mol}^{-1} \cdot \text{K}^{-1}$); T = temperature (K).

[00115] Table 4. ^1H and ^{19}F NMR data for $[\text{Cu}_3]$ binding of ethylene in CDCl_3 solution.

T (K)	^1H NMR Integrals		^{19}F NMR Integrals		K	$\ln(K)$	1/T
	Ethylene	$[\text{Cu}_2 \cdot (\text{C}_2\text{H}_4)_2]$	$[\text{Cu}_2 \cdot (\text{C}_2\text{H}_4)_2]$	$[\text{Cu}_3]$			
243	0.12	1	1	0.64	817622	13.6	0.00411
263	0.19	1	1	0.82	31612	10.4	0.00380
283	0.4	1	1	1.26	154	5.04	0.00353
294	0.9	1	1	1.33	1.07	0.0618	0.00340
308	1.5	1	1	2.37	0.0156	-4.16	0.00325

[00116] Table 5. Heat of equilibrium for $[\text{Cu}_3]$ binding of ethylene in CDCl_3 solution.

	ΔH (kJ mol^{-1})	ΔS (J mol^{-1})
Overall equilibrium	-171 ± 45	-578 ± 1
Per $[\text{Cu}_3]$ unit	-86 ± 24	-289 ± 1
Per Cu – C_2H_4 interaction	-28 ± 8	-96 ± 1

[00117] Table 6. Heat of equilibrium for Cu^+ binding of ethylene in solution.

(Examples were searched for using the string “ethylene adsorption energy in solution” in Scifinder.)

Complex	Solvent	ΔH (kJ mol^{-1})	ΔS (J mol^{-1})	Reference
$[\text{Cu}^I(\text{di-imine})]$	CD_2Cl_2	-41	-200	¹²

[00118] Van't Hoff plot for $[\text{Cu}_3]$ binding of ethylene in CDCl_3 solution is shown in **FIG. 10.** ^1H NMR spectrum of $[\text{Cu}_2 \cdot (\text{C}_2\text{H}_4)_2]$ in the presence of excess ethylene at various

temperatures is shown in **FIG. 11**. A peak at 4.47 ppm (-80°C) is the signal corresponding to coordinated ethylene while 5.37 ppm peak is the signal of free ethylene. ^1H NMR spectra of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ at various temperatures is shown in **FIG. 12**. This spectrum also shows the presence of free ethylene resulting from the disproportionation of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ to $[\text{Cu}_3]$ and free ethylene. A peak at 4.51 ppm (-30°C) is the signal corresponding to coordinated ethylene while 4.89 ppm peak is the signal of free ethylene in equilibrium with $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ and $[\text{Cu}_3]$. **FIG. 13** shows ^1H NMR spectrum of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ at 35°C . This spectrum also shows the presence of free ethylene resulting from the disproportionation of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ to $[\text{Cu}_3]$ and free ethylene. **FIG. 14** shows ^1H NMR spectrum of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ at -30°C . This spectrum also shows the presence of ethylene resulting from the disproportionation of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ to $[\text{Cu}_3]$ and free ethylene. A comparison to data at 35°C indicates the shift of equilibrium towards $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ and the lowering on free ethylene content. **FIG. 15** shows ^{19}F NMR spectra of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ at various temperatures. This spectrum also shows the presence of $[\text{Cu}_3]$ (labeled as Cu trimer) resulting from the disproportionation of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ to $[\text{Cu}_3]$ and free ethylene. Peaks at -54.87 and -59.31 ppm (-30°C) are the signals corresponding to Cu dimer $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ while peaks at -55.11 and -60.17 ppm correspond to $[\text{Cu}_3]$. **FIG. 16** shows ^{19}F NMR spectrum of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ at 35°C . This spectrum also shows the presence of $[\text{Cu}_3]$ resulting from the disproportionation of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ to $[\text{Cu}_3]$ and free ethylene. **FIG. 17** shows ^{19}F NMR spectrum of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ at -30°C . This spectrum also shows presence of $[\text{Cu}_3]$ resulting from the disproportionation of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ to $[\text{Cu}_3]$ and free ethylene and shows the reduction of $[\text{Cu}_3]$ content upon cooling (see 35°C spectrum for comparison) as a result of its reaction with ethylene to produce $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$.

1.4 Ideal (Single-Gas) Ethylene Isotherm Data

[00119] The single-gas sorption isotherms of solid $[\text{Cu}_3]$ were measured using a Quantachrome Autosorb AS-1C. Initially, the sample only adsorbed ca. 20% of the theoretical loading. Repeated cycling at room temperature showed continually increasing amounts of gas adsorption, and the influence of a conditioning process was hypothesized. The sample was then held under 1 bar of ethylene at 70°C for 3 days. Afterward, the maximum ethylene loadings at 20°C , 50°C and 70°C became reproducible (**FIG. 18**)


[00120] **Table 7. Ethylene loading of [Cu₃] with pressure.**

Temperature (K)	Ethylene loading at 100 kPa (mmol g ⁻¹)	'Step' pressure (kPa)	'Step Loading' (mmol g ⁻¹)
293	2.76	6.0	2.11
323	2.70	8.0	2.50
343	2.63	25.3	2.55

1.5 Van't Hoff analysis and Langmuir modeling of ethylene adsorption after 'step'

[00121] Van't Hoff analysis of the isotherms after the 'step' where chemisorption occurs has shown that the adsorption of ethylene becomes low energy ca. -3 kJ mol⁻¹ per ethylene interaction (**Table 9**).

[00122] The steepness of the 'step' increased with temperature, making the Langmuir behavior difficult to capture. Applying the Langmuir isotherm model to data around the 'step' pressure produced effective results for the data collected at 25 and 50 °C when isotherms with a resolution of 2 kPa were collected. However, the data at 70 °C did not follow the same trend, and the model did not capture the underlying physical phenomena. Van't Hoff analysis of the Langmuir model for the 25 and 50 °C isotherms produced a heat of adsorption of -32 kJ mol⁻¹. However, due to the lack of accuracy, it was hypothesized that Claussius-Clapeyron analysis of the 'step' pressure (which has shown to correlate directly to the heat of adsorption in small molecule adsorbents with step isotherms)⁷ is a more accurate reflection of the heat of adsorption).



$$K = \frac{[\text{Cu}_2 \cdot (\text{C}_2\text{H}_4)_2]^3}{[\text{Cu}_3]^2 [\text{C}_2\text{H}_4]^6}$$

[00123] **Equation. 3.** Equilibrium equation used for binding of ethylene in the solid-state.

$$\ln(K) = \frac{-\Delta H}{RT} + \frac{\Delta S}{R}$$

[00124] **Equation 4.** Equation used for the Van't Hoff analysis where K = the equilibrium constant for the reversible reaction shown above; ΔH = change in enthalpy (J·mol⁻¹); ΔS = change in entropy (J·mol⁻¹); R = the gas constant (J·mol⁻¹·K⁻¹); T = temperature (K).

[00125] **Table 8. Isotherm data for [Cu₃] binding of ethylene in the solid-state under 100.7 kPa of ethylene.**

Temperature (K)	[Ethylene] ⁶	[Cu ₂ ·(C ₂ H ₄) ₂] ³ /[Cu ₂ ·(C ₂ H ₄) ₂] ²	K	ln(K)	1/T
293	0.966	432	448	6.10	0.00340
323	0.966	264	273	5.61	0.00310
343	0.966	149	153	5.03	0.00291

[00126] **Table 9. Heat of equilibrium for [Cu₃] binding of ethylene in the solid-state under 100.7 kPa of ethylene.**

	ΔH (kJ mol ⁻¹)	ΔS (J mol ⁻¹)
Overall equilibrium	-17.8±1	-8±1
Per [Cu ₃] unit	-8.9±1	-4±1
Per Cu – C ₂ H ₄ interaction	-3.0±1	-2±1

$$\text{Loading of ethylene} = \frac{\alpha \cdot P \cdot N}{\alpha \cdot P + 1}$$

[00127] **Equation 5.** Equation used for the Langmuir modeling. Where α = the equilibrium constant for the adsorption site; P = pressure of ethylene (kPa); N = number of adsorption sites present.

[00128] **Table 10. Model parameters for [Cu₃] binding of ethylene in the solid-state under generated from isotherm data above an ethylene pressure of 60 kPa.**

Temperature (K)	'α' from model	'N' from model	K	ln(α)	1/T
293	19.4	2.76	448	2.96	0.00340
323	31.8	2.69	273	3.46	0.00310
343	44.7	2.64	153	3.80	0.00291

1.6 Claussius-Clapeyron analysis of isotherms and models

[00129] The Claussius-Clapeyron relationship (**Eqn. 6**) was used to estimate the energy of the adsorption process at the 'step' point using variable pressure and variable temperature data. Results show that the 'step' has an enthalpy of 38 kJmol⁻¹. This adsorption 'step' appears to occur at the same pressure for all copper-binding sites in the sample, resulting in occupancy of all available copper-binding sites to ethylene gas.

$$P_{step}(T) = P_{step,T_0} \left(\frac{\Delta H}{R} \right) \left(\frac{1}{T_0} - \frac{1}{T} \right)$$

$$\ln\left(\frac{P_{step}}{P_{step,T_0}}\right) = \left(\frac{\Delta H}{R}\right)\left(\frac{1}{T_0} - \frac{1}{T}\right)$$

[00130] **Equation 6.** Equation used for the Claussius-Clapeyron analysis where P_{step} = the ethylene partial pressure at the step; P_{step,T_0} = the ethylene partial pressure at the step at 293 K; ΔH = change in enthalpy ($\text{J}\cdot\text{mol}^{-1}$); R = the gas constant ($\text{J}\cdot\text{mol}^{-1}\cdot\text{K}^{-1}$); $T_0 = 293$ K; T = temperature (K).

[00131] **Table 11. Isotherm data for the phase change of $[\text{Cu}_3]$ to $[\text{Cu}_2\cdot(\text{C}_2\text{H}_4)_2]$ under increasing ethylene pressure.** The data is shown in **FIG. 20**.

T (K)	$1/T_0 - 1/T$	'Step' pressure (kPa)	P/P ₀	ln(P/P ₀)
293	0	2.44	1	0
323	3.17×10^{-4}	8.02	3.3	1.19
323	3.17×10^{-4}	8.85	3.6	1.23
343	4.98×10^{-4}	20.6	8.4	2.13
343	4.98×10^{-4}	53.5	9.6	2.27
343	4.98×10^{-4}	25.3	10.3	2.34

[00132] **Table 12. Data from fitting the Claussius-Clapeyron equation to the phase change of $[\text{Cu}_3]$ to $[\text{Cu}_2\cdot(\text{C}_2\text{H}_4)_2]$ under increasing ethylene pressure.**

Data Source	Slope	R ²	$\Delta H_{\text{ethylene}/[\text{Cu}_3]}$ (kJ mol^{-1})	$\Delta H_{\text{ethylene}/\text{Cu}}$ (kJ mol^{-1})
Step pressures	4588	0.9817	-38	-13±1

1.7 Ethane adsorption isotherms

[00133] Ethane isotherms at 20 °C, 50 °C, and 70 °C were collected after completion of the ethylene isotherms, and the results are shown in **FIG. 21**. These results show that ethane is not chemically adsorbed into $[\text{Cu}_3]$ and does not cause a phase change.

1.8 Measurement of ethylene/ethane adsorption rate using pressure drop method

[00134] These experiments were performed to measure the rate at which ethylene was adsorbed into the material. Overall the initial adsorption of ethylene occurs at a rate $>0.2 \text{ mol mol}^{-1} \text{ min}^{-1}$ for the first minute, slowing to $8 \times 10^{-3} \text{ mol mol}^{-1} \text{ min}^{-1}$ for approximately 40 minutes, and then slowing further. Without wishing to be bound by any theory, it was hypothesized that this change in the adsorption rate might represent transitions between rapid adsorption of ethylene onto copper-binding sites on the surface of the material, followed by different diffusion regimes within the crystal. Subsequent adsorption/desorption cycles condition the material, increasing the number of copper-binding sites initially 'available.'

These experiments, however, were not intended to show equilibrium loadings and were all performed at ambient temperature (21 °C).

[00135] The experimental rig used to make these measurements described herein, and is shown in FIG. 22A.⁷ [Cu₃] was ground into a fine powder using a mortar and pestle and placed in the sample chamber (108) having a predetermined volume. Residual gases were removed from the sample by opening valves 1 and 2 to dynamic vacuum (<0.1 torr) for 3–24 h (102). Valve 2 was closed after degassing, and the feed volume 106 was filled with approximately 1 bar (14.5 psi) of the gas to be measured. Valve 2 was opened for 1 s, filling the sample chamber with the gas of interest, and the pressure decrease in the sample chamber was measured with a pressure gauge (110) over time until a constant pressure (P_f) was observed (FIG. 22B). The temperature with the feed volume and sample chamber was measured with a temperature controller 112. The pressure difference, corrected for the empty cell, (Equations 7 and 8) was used to calculate the amount of gas adsorbed by the sample in units of mol_{gas}. The amount of gas adsorbed was then normalized by the amount of sample.

$$\Delta P = P_i - P_f - \Delta P_{Blank}$$

$$\Delta P_{Blank} = P_{i(empty)} - P_{f(empty)}$$

[00136] **Equation 7.** P_i = the initial pressure (time zero); P_f = the final pressure (time final).

$$n_{gas} = \frac{\Delta P \cdot V}{R \cdot T}$$

[00137] **Equation 8.** n_{gas} = moles of gas adsorbed; V = volume of the sample chamber; R = the ideal gas constant; T = temperature of the sample chamber.

[00138] **Table 13. Measured ethene uptake capacities of fresh [Cu₃] after 120 min expressed in different sorbent performance terms. Note the equilibrium pressure is around 0.4 atm (41 kPa). (FIG. 23)**

Run	Time min	Ethene Uptake mmol _{ethene} /g _{complex}	Ethene Uptake cc _{ethene} /g _{complex}	Ethene Uptake mol _{ethene} /mol _{complex}	% of Full Capacity	Ethene/Ethane Selectivity
1	120	0.06	1.3	0.06	3	6.2
2	120	0.50	11.1	0.50	23	54
3	120	0.62	13.9	0.62	27	67
4	120	0.62	13.9	0.62	27	67
5	120	0.70	15.6	0.70	31	76

[00139] **Table 14. The ethene uptake rates of [Cu₃] measured using the pressure drop method with ca. 1 atm starting feed pressure. The adsorption rate is broken into 3 phases, 0-1 min; 1-40 min; 40-120 min.**

<i>Cycle</i>	<i>Average rate (0-1 min)</i> <i>(mol_{ethene}/mol_{complex}/min)</i>	<i>Average rate (1-40 min)</i> <i>(mol_{ethene}/mol_{complex}/min)</i>	<i>Average rate (40-120 min)</i> <i>(mol_{ethene}/mol_{complex}/min)</i>
1	0.02	8×10^{-4}	1×10^{-4}
2	0.14	8×10^{-3}	1×10^{-3}
3	0.27	8×10^{-3}	7×10^{-4}
4	0.22	9×10^{-3}	1×10^{-3}
5	0.26	8×10^{-3}	2×10^{-3}

1.9 Measurement of acetylene/ethylene adsorption rate using pressure drop method

[00140] Resistance to acetylene is considered an important feature of potential sorbents targeting the application of raw olefin/paraffin separation (this is to avoid the formation of explosive copper(I) acetylides). The adsorption behavior with acetylene using the pressure drop method was established. It appears that acetylene can reversibly adsorb and desorb from [Cu₃]. However, such behavior has been shown to result in loss of crystallinity. Even further, it has appeared that the adsorption is not completely reversible, therefore, resulting in reducing the adsorption capacity of [Cu₃] for ethylene while remaining the adsorption capacity of [Cu₃] for acetylene high. **Table 15** shows the ethylene and acetylene uptake capacities of the inventive complex. Between each run the samples were degassed under dynamic vacuum (<0.1 torr) for 48 hours, with the exception of before runs 4 and 5, where shorter degas times of 2 hours under dynamic vacuum were used. The effect of 4 acetylene and 4 ethylene adsorption/desorption cycles on the crystallinity of [Cu₃] as evident from PXRF is shown in **FIG. 24**.

[00141] **Table 15. Measured ethylene and acetylene uptake capacities of the complex [Cu₃] after 120 min expressed in different sorbent performance terms. The equilibrium pressure is ca. 0.9 atm (92 kPa).**

<i>Cycle</i>	<i>Time</i> <i>(min)</i>	<i>Gas Uptake</i> <i>(mmol_{gas}/g_{complex})</i>	<i>Gas Uptake</i> <i>(cc_{gas}/g_{complex})</i>	<i>Gas Uptake</i> <i>(mol_{gas}/mol_{complex})</i>
1 (C₂H₄)	120	0.44	9.8	0.440
2 (C₂H₂)	120	0.37	8.3	0.373
3 (C₂H₄)	120	0.33	7.4	0.332
4 (C₂H₂)	120*	0.08	1.8	0.081
5 (C₂H₄)	120*	0.03	0.6	0.028
6 (C₂H₂)	120	0.37	8.3	0.375
7 (C₂H₄)	120	0.13	2.9	0.129

[00142] **Table 16. Ethylene and acetylene uptake rates of solid-state material [Cu₃] measured using the pressure drop method with ca. 1 atm starting feed pressure. The adsorption rate is broken into 3 phases, 0-1 min; 1-40 min; 40-120 min.**

Cycle	Average rate (0-1 min) (mol _{gas} /mol _{complex} /min)	Average rate (1-40 min) (mol _{gas} /mol _{complex} /min)	Average rate (40-120 min) (mol _{gas} /mol _{complex} /min)
1 (C ₂ H ₄)	0.11	7 x 10 ⁻³	7 x 10 ⁻⁴
2 (C ₂ H ₂)	0.13	4 x 10 ⁻³	6 x 10 ⁻⁴
3 (C ₂ H ₄)	0.11	3 x 10 ⁻³	1 x 10 ⁻³
4 (C ₂ H ₂)	0.02	2 x 10 ⁻⁴	9 x 10 ⁻⁴
5 (C ₂ H ₄)	0.03	2 x 10 ⁻⁴	5 x 10 ⁻⁵
6 (C ₂ H ₂)	0.32	2 x 10 ⁻³	0
7 (C ₂ H ₄)	0.08	2 x 10 ⁻³	2 x 10 ⁻⁴

1.10 Thermogravimetric analysis (TGA)

[00143] Three TGA studies were undertaken on [Cu₂•(C₂H₄)₂] and [Cu₃]. The results are shown in **FIG. 25**. The TGA results have shown that [Cu₂•(C₂H₄)₂] loses 2 moles of ethylene beginning at approximately 50 °C and increasing in rate as the temperature increases. At a heating rate of 10 °C/min both [Cu₂•(C₂H₄)₂] and [Cu₃] sublime at approximately the same rate and temperature. The temperature profile used was 25 °C to 300 °C at 10 °C/min then holding at 300 °C for 30 minutes.

1.11 Infrared data showing ethylene binding

[00144] Infrared data was used to confirm that ethylene had coordinated to the copper(I) centres. The data is shown in **FIG. 26**. The fine structure of the spectrum remained largely unchanged, indicative of no significant structural changes to the [(3,4,5-(CF₃)₃Pz)_nCu_n] core.

1.12 Raman spectroscopy showing ethylene binding

[00145] Ethylene adsorption and desorption was monitored by Raman spectroscopy (**FIG. 27**). It was observed that following ethylene adsorption, signals corresponding to coordinated ethylene are prominent at 1544 cm⁻¹, 1280 cm⁻¹, and 960 cm⁻¹. It was further observed that fine structure between 1100-1200 cm⁻¹ also changes considerably upon ethylene coordination, and returns to the previous state upon exposure to vacuum at 60 °C. These results demonstrate the reversible transitions between [Cu₃] and [Cu₂•(C₂H₄)₂]. **FIGs. 28-29** show a Raman spectrum of [Cu₃] and [Cu₂•(C₂H₄)₂] respectively.

1.13 Differential scanning calorimetry (DSC) data

[00146] DSC was used to investigate the desorption energies and phase transitions of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ and $[\text{Cu}_3]$ (FIGs. 30-32). The first cycle shown in the figures includes energy from unifying distinct crystal populations within the sample. Ethylene desorption appears to occur in a series of events that co-occur with the melting of the sample. Subtracting the melt energy of $[\text{Cu}_3]$ from the desorption process gives an ethylene desorption energy of 36.4 kJ mol^{-1} per $[\text{Cu}_3]$ unit (13.1 kJ mol^{-1} per $\text{Cu}\cdots\text{C}_2\text{H}_4$ interaction). This matches the adsorption energy observed for the ‘step’ in the variable temperature isotherm studies (-38 kJ mol^{-1} per $[\text{Cu}_3]$ unit). Once $[\text{Cu}_3]$ has been formed by loss of ethylene, the sample consistently melts at $135\pm 1^\circ\text{C}$ and solidifies at $119\pm 2^\circ\text{C}$ with energy of $25\pm 4 \text{ kJ mol}^{-1}$. This is ca. $10\text{-}20^\circ\text{C}$ different from the results obtained by visual melting point determination.

[00147] **Table 17. Heat of desorption and melt for $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$, melt/solidification energy of $[\text{Cu}_3]$, and comparison to isotherm and solution experiments.**

DSC	(kJ mol ⁻¹)
Per $[\text{Cu}_3]$ unit	36.4
Per Cu – C ₂ H ₄ interaction	13.1
$[\text{Cu}_3]$ melt/solidification energy	± 24.5
Overall per $[\text{Cu}_3]$ unit	60.9
Adsorption Isotherms	H (kJ mol ⁻¹)
Phase change at ethylene adsorption ‘step’	-38 ± 2
‘Step’ energy per Cu $\cdots$ C ₂ H ₄ interaction	-13 ± 1
After ‘step’ adsorption per $[\text{Cu}_3]$ unit	-8.9
After ‘step’ adsorption per Cu $\cdots$ C ₂ H ₄ interaction	-3
Solution State (NMR)	ΔH (kJ mol ⁻¹)
Overall equilibrium	-171 ± 45
Per $[\text{Cu}_3]$ unit	-86 ± 24
Per Cu – C ₂ H ₄ interaction	-28 ± 8

1.14 Powder X-ray crystallographic data

[00148] Powder X-ray diffraction was used to characterize $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ and $[\text{Cu}_3]$, monitor the transition of solid $[\text{Cu}_3]$ to $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ following exposure to ethylene gas (confirming that less than 1% $[\text{Cu}_3]$ remains based on peak analysis), and that $[\text{Cu}_3]$ is re-generated when ethylene is removed from solid samples of $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ by application of vacuum at 60°C for 6 hours. The results are shown in FIGs. 33-36.

[00149] In all experiments, the sample was placed in the sample holder of a two circle goniometer, enclosed in a radiation safety enclosure. The X-ray source was a 1kW Cu X-ray tube, maintained at an operating current of 40 kV and 25 mA. The X-ray optics was the standard Bragg-Brentano para-focusing mode with the X-ray diverging from a DS slit (0.6mm) at the tube to strike the sample and then converging at a position-sensitive X-ray Detector (Lynx-Eye, Bruker-AXS). The two-circle 280mm diameter θ - θ goniometer was computer-controlled with independent stepper motors and optical encoders for the θ circle with the smallest angular step size of $0.0001^\circ 2\theta$. The software suite for data collection and evaluation was windows based. Data collection was performed by automated COMMANDER program by employing a DQL file. Data were analyzed by the program EVA. The summary of the experimental parameters for PXRD collection is shown in Tables 18. Key data points for $[\text{Cu}_3]$ and $[\text{Cu}_2 \cdot (\text{C}_2\text{H}_4)_2]$ are summarized in **Tables 19** and **20**.

[00150] **Table 18. Experimental Parameters for PXRD collection.**

Bruker Powder ECO	
Scan Type	Coupled Theta-Theta
Scan Mode	Continuous
Start	3.0
End	70.0
Step Scan	0.01
Steps	6544
Scan Speed	1°/min
Goniometer Radius	280.00 mm
Sample Rotation in plane	5.0°/min
Anode	Cu
K α 1	1.56060 Å
K α 2	1.54440 Å
K α 2 ratio	0.5140
K β	1.39224 Å
Generator kV	40 kV
Generator mA	25 mA
Monochromator	Ni 0.02mm Filter
Divergence Slit	0.6mm
Anti-air scatter device	Knife-edge
Detector	LynxEYE XE PSD
PSD opening	3.0°

[00151] **Table 19. Key PXRD data for $[\text{Cu}_3]$.**

R-Values	
R _{exp}	3.18
R _{exp} ²	5.46

Rwp	8.84
Rwp [`]	15.19
Rp	5.91
Rp [`]	12.49
GOF	2.78
DW	0.57
Background	
Chebyshev polynomial	Coefficient
0	264.7938
1	51.11665
2	-85.359
3	121.1826
4	46.55985
5	-21.25148
6	-9.612418
7	-32.26846
Instrument	
Primary radius (mm)	217.5
Secondary radius (mm)	217.5
Corrections	
Zero error	-0.04106155
LP Factor	0
Miscellaneous	
Start X	6
Finish X	40
hkl Phase - 1 Pawley method	
Phase name	hkl_Phase
R-Bragg	13.284
Spacegroup	P2 ₁ /c
Cell Mass	0.000
Cell Volume (Å ³)	6032.50979
Wt% - Rietveld	0.000
Double-VoigtApproach	
Cry size Lorentzian	289.4
k: 1 LVol-IB (nm)	184.238
k: 0.89 LVol-FWHM (nm)	257.566
PV_TCHZ peak type	
U	-0.2988456
V	-0.004251204
W	0.009854906
Z	0
X	0.0001
Y	0

Lattice parameters	
a (Å)	24.0648163
b (Å)	16.9879630
c (Å)	14.7599273
beta (°)	91.28976

[00152] Table 20. Key PXRD data for [Cu₂•(C₂H₄)₂].

R-Values	
R _{exp}	5.45
R _{exp} ^h	11.92
R _{wp}	9.99
R _{wp} ^h	21.83
R _p	6.86
R _p ^h	18.61
GOF	1.83
DW	0.67
Background	
Chebyshev polynomial	Coefficient
0	187.9562
1	10.44336
2	-51.27976
3	16.23856
4	35.71489
5	-32.61826
6	33.63138
7	9.404404
Instrument	
Primary radius (mm)	217.5
Secondary radius (mm)	217.5
Corrections	
Specimen displacement	0.01154313
LP Factor	0
Miscellaneous	
Start X	3
Finish X	40
hkl Phase - 1 Pawley method	
Phase name	hkl Phase
R-Bragg	0.557
Spacegroup	Pnma
Cell Mass	0.000
Cell Volume (Å ³)	4752.25474
Wt% - Rietveld	0.000

Double-VoigtApproach	
Cry size Lorentzian	183.2
k: 1 LVol-IB (nm)	116.645
k: 0.89 LVol-FWHM (nm)	163.071
PV_TCHZ peak type	
U	-0.0192523
V	-0.0307023
W	0.00550668
Z	0
X	0.0001000286
Y	0
Lattice parameters	
a (Å)	18.3765097
b (Å)	28.8438297
c (Å)	8.9656909

1.15 Single crystal X-ray crystallographic data

[00153] A suitable crystal covered with a layer of hydrocarbon/Paratone-N oil was selected and mounted on a Cryo-loop, and immediately placed in the low-temperature nitrogen stream. The X-ray intensity data for **[Cu₃] (1)** were measured at 200(2) K on a Bruker D8 Quest with a Photon 100 CMOS detector equipped with an Oxford Cryosystems 700 series cooler, a Triumph monochromator, and a Mo K α fine-focus sealed tube ($\lambda = 0.71073$ Å), whereas data for **[Cu₂•(C₂H₄)₂] (2)** were measured at 100(2) K on the same instrument. Crystals of **[Cu₃]** were found to be soft and can shatter relatively easily at 100 K. Intensity data were processed using the Bruker Apex program suite. Absorption corrections were applied by using SADABS. All the calculations for the structure determination were carried out using the SHELXTL package (version 6.14). Initial atomic positions were located by direct methods using SHELXT, and the structures of the compounds were refined by the least-squares method using SHELXL within the Olex2 suite. All the non-hydrogen atoms were refined anisotropically. X-ray structural figures were generated using Olex2. The CCDC 1836466-1836467 contains the supplementary crystallographic data. These data can be obtained free of charge *via* <http://www.ccdc.cam.ac.uk/conts/retrieving.html> or from the Cambridge Crystallographic Data Centre (CCDC), 12 Union Road, Cambridge, CB2 1EZ, UK).

[00154] It was found that **[Cu₃] (1)** crystallizes in the $P2_1/c$ space group with two molecules of **[Cu₃]** in the asymmetric unit. Most of the fluorine atoms of CF₃ groups were shown positional disorder which was modeled effectively.

[00155] It was further found that $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$ (**2**) crystallizes in space group $P2_1/c$ with two independent molecules in the asymmetric unit. The cell dimensions mimic that of Orthorhombic crystal system with the β -angle of essentially 90° . These crystals show twinning by pseudomerohedry, and the use of Twin Law $(-1\ 0\ 0\ 0\ -1\ 0\ 0\ 0\ 1)$ during refinement led to a significant drop in the R-value and improvements in all refinement indicators. All the non-hydrogen atoms were refined anisotropically. Hydrogen atoms of ethylene moieties were located on a different map and included in the refinement. The structure in the Orthorhombic $Pccn$ space group was also considered, solved, and refined (as suggested by CheckCif as a possibility). However, the final refinement indicators (final R_1 was 0.0823 ($I > 2\sigma(I)$) and wR_2 was 0.2027 (all data), $\text{GooF} = 1.462$) were poor compared to those of the Monoclinic option (Final R_1 : 0.0248 ($I > 2\sigma(I)$) and wR_2 : 0.0587 (all data); $\text{GooF} = 1.029$), and indicate that Monoclinic indeed is the correct choice. **Table 21** summarizes the crystal data and structure refinement for $[\text{Cu}_3]$. **Table 22** shows Crystal data and structure refinement for $[\text{Cu}_2\bullet(\text{C}_2\text{H}_4)_2]$. The data is shown in **FIG. 37-39**.

[00156] **Table 21. Crystal data and structure refinement for $[\text{Cu}_3]$ (1).**

Identification code	rad322a_a
Empirical formula	$\text{C}_{18}\text{Cu}_3\text{F}_{27}\text{N}_6$
Formula weight	1003.86
Temperature/K	200.0
Crystal system	monoclinic
Space group	$P2_1/c$
$a/\text{\AA}$	23.9829(8)
$b/\text{\AA}$	16.6712(6)
$c/\text{\AA}$	14.0384(5)
$\alpha/^\circ$	90
$\beta/^\circ$	90.3310(10)
$\gamma/^\circ$	90
Volume/ $\text{\AA}^3$	5612.8(3)
Z	8
$\rho_{\text{calc}}/\text{g/cm}^3$	2.376
μ/mm^{-1}	2.459
$F(000)$	3840.0
Crystal size/ mm^3	$0.35 \times 0.32 \times 0.22$
Radiation	$\text{MoK}\alpha$ ($\lambda = 0.71073$)
2θ range for data collection/ $^\circ$	5.684 to 52
Index ranges	$-29 \leq h \leq 29, -20 \leq k \leq 20, -17 \leq l \leq 17$

Reflections collected	83538
Independent reflections	11022 [$R_{\text{int}} = 0.1013$, $R_{\text{sigma}} = 0.0447$]
Data/restraints/parameters	11022/5682/1365
Goodness-of-fit on F^2	1.050
Final R indexes [$I \geq 2\sigma(I)$]	$R_1 = 0.0681$, $wR_2 = 0.1528$
Final R indexes [all data]	$R_1 = 0.1166$, $wR_2 = 0.1750$
Largest diff. peak/hole / $e \text{ \AA}^{-3}$	1.21/-0.74

[00157] Table 22. Crystal data and structure refinement for $[\text{Cu}_2 \cdot (\text{C}_2\text{H}_4)_2] (2)$

Identification code	rad55a
Empirical formula	$\text{C}_{16}\text{H}_8\text{N}_4\text{F}_{18}\text{Cu}_2$
Formula weight	725.34
Temperature/K	103.15
Crystal system	monoclinic
Space group	$P2_1/c$
$a/\text{\AA}$	8.7832(4)
$b/\text{\AA}$	28.5511(13)
$c/\text{\AA}$	18.1962(8)
$\alpha/^\circ$	90
$\beta/^\circ$	90.0030(10)
$\gamma/^\circ$	90
Volume/ $\text{\AA}^3$	4563.1(4)
Z	8
$\rho_{\text{calc}}/\text{g cm}^{-3}$	2.112
μ/mm^{-1}	2.026
$F(000)$	2816.0
Crystal size/ mm^3	$0.327 \times 0.122 \times 0.088$
Radiation	$\text{MoK}\alpha$ ($\lambda = 0.71073$)
2θ range for data collection/ $^\circ$	5.708 to 56.68
Index ranges	$-11 \leq h \leq 11$, $-38 \leq k \leq 38$, $-24 \leq l \leq 24$
Reflections collected	59586
Independent reflections	11354 [$R_{\text{int}} = 0.0288$, $R_{\text{sigma}} = 0.0209$]
Data/restraints/parameters	11354/0/786
Goodness-of-fit on F^2	1.029
Final R indexes [$I \geq 2\sigma(I)$]	$R_1 = 0.0248$, $wR_2 = 0.0573$
Final R indexes [all data]	$R_1 = 0.0285$, $wR_2 = 0.0587$
Largest diff. peak/hole / $e \text{ \AA}^{-3}$	0.57/-0.26

[00158] The above specification and examples provide a complete description of the structure and use of illustrative embodiments. Although certain embodiments have been described above with a certain degree of particularity, or with reference to one or more individual embodiments, those skilled in the art could make numerous alterations to the disclosed embodiments without departing from the scope of this invention. As such, the various illustrative embodiments of the devices are not intended to be limited to the particular forms disclosed. Rather, they include all modifications and alternatives falling within the scope of the claims, and embodiments other than the one shown may include some or all of the features of the depicted embodiment. For example, components may be omitted or combined as a unitary structure, and/or connections may be substituted. Further, where appropriate, aspects of any of the examples described above may be combined with aspects of any of the other examples described to form further examples having comparable or different properties and addressing the same or different problems. Similarly, it will be understood that the benefits and advantages described above may relate to one embodiment or may relate to several embodiments.

[00159] The claims are not intended to include, and should not be interpreted to include, means-plus- or step-plus-function limitations, unless such a limitation is explicitly recited in a given claim using the phrase(s) “means for” or “step for,” respectively.

[00160] In view of the described processes and compositions, hereinbelow are described certain more particularly described aspects of the inventions. These particularly recited aspects should not, however, be interpreted to have any limiting effect on any different claims containing different or more general teachings described herein, or that the “particular” aspects are somehow limited in some way other than the inherent meanings of the language and formulas literally used therein.

[00161] Aspect 1: A process comprising: exposing a trinuclear copper(I) pyrazolate complex to a hydrocarbon feed gas mixture comprising one or more alkenes and one or more alkanes, to form a product comprising a dinuclear copper(I)-alkene complex.

[00162] Aspect 2: The process of aspect 1, further comprising a step of separating the one or more alkenes from the one or more alkanes.

[00163] Aspect 3: The process of aspects 1 or 2, wherein the one or more alkenes comprise ethylene, propylene, butene, pentene, or isobutylene.

[00164] Aspect 4: The process of any one of aspects 1-3, wherein the one or more alkanes comprise ethane, methane, propane, butane, or pentane.

[00165] Aspect 5: The process of any one of aspects 1-4, wherein the one or more alkenes comprise ethylene.

[00166] Aspect 6: The process of any one of aspects 1-5, wherein the one or more alkenes comprise ethylene, wherein the one or more alkanes comprise ethane, and wherein the formed product comprises a dinuclear copper(I)-ethylene complex.

[00167] Aspect 7: The process of aspect 6, wherein the step of separating comprises separating ethylene from ethane.

[00168] Aspect 8: The process of aspects 6 or 7, wherein the dinuclear copper(I)-ethylene complex is formed by adsorption of ethylene on the trinuclear copper(I) pyrazolate complex.

[00169] Aspect 9: The process of any one of aspects 6-8, further comprising a step of desorption of ethylene from the dinuclear copper(I)-ethylene complex.

[00170] Aspect 10: The process of aspect 9, wherein the step of desorption is performed at a temperature from about -50 °C to about 150 °C and a pressure from about 0 bar to about 500 bar.

[00171] Aspect 11: The process of aspects 9 or 10, wherein the ethylene desorption forms a regenerated trinuclear copper(I) pyrazolate complex.

[00172] Aspect 12: The process of any one of aspects 1-11, wherein the trinuclear copper(I) pyrazolate complex is a [3,4,5-tris(trifluoromethyl)pyrazolyl] Cu ₃ complex ([3,4,5-(CF₃)₃Pz) Cu]₃, ([**Cu**₃]).

[00173] Aspect 13: The process of any one of aspects 6-12, wherein the dinuclear copper(I)-ethylene complex is a [3,4,5-tris(trifluoromethyl)pyrazolyl] $\text{Cu}(\text{C}_2\text{H}_4)$]₂ ([3,4,5-(CF₃)₃Pz) $\text{Cu}(\text{C}_2\text{H}_4)$]₂ complex, ([**Cu**₂•(C₂H₄)₂]).

[00174] Aspect 14: The process of aspect 13, wherein the ethylene adsorption causes an endothermic structural rearrangement of [**Cu**₃] to [**Cu**₂•(C₂H₄)₂].

[00175] Aspect 15: The process of any one of aspects 12-14, wherein at least a portion of the ethylene adsorption occurs at a 'step' pressure of about 2 kPa to about 30 kPa and a temperature from about 20 °C to about 75 °C (from about 293 K to about 348 K).

[00176] Aspect 16: The process of any one of aspects 12-15, wherein the step of exposing comprises exposing a solid-state [**Cu₃**] to the hydrocarbon feed gas mixture.

[00177] Aspect 17: The process of any one of aspects 12-16, wherein the step of exposing comprises exposing a dichloromethane solution of [**Cu₃**] to the hydrocarbon feed gas mixture to produce [**Cu₂•(C₂H₄)₂**].

[00178] Aspect 18: The process of any one of aspects 12-17, wherein the ethylene desorption from [**Cu₂•(C₂H₄)₂**] to regenerate [**Cu₃**] is performed in a solid-state.

[00179] Aspect 19: The process of any one of aspects 12-18, wherein the step of exposing results in a reversible solid-state structural transformation [**Cu₃**] to [**Cu₂•(C₂H₄)₂**].

[00180] Aspect 20: The process of any one of aspects 6-19, wherein the process does not comprise adsorption of ethane on the trinuclear copper(I) pyrazolate complex.

[00181] Aspect 21: The process of any one of aspects 12-20, wherein an adsorption selectivity of ethylene/ethane on [**Cu₃**] is from about 1:1 to about 136:1 when measured at a temperature of 20 °C and an equilibrium loading at 1 atm.

[00182] Aspect 22: The process of any one of aspects 12-21, wherein an adsorption selectivity of ethylene/ethane on [**Cu₃**] is from about 1:1 to about 131:1 when measured at a temperature of 70 °C and an equilibrium loading at 1 atm.

[00183] Aspect 23: The process of any one of aspects 12-22, wherein the process exhibits a decrease of a heat of adsorption by 50 to 85 % when compared to a substantially identical reference process comprising a copper (I) complex that is not [**Cu₃**].

[00184] Aspect 24: The process of any one of aspects 12-23, wherein [**Cu₃**] is formed by: a) reacting copper (I) oxide with a precursor 3,4,5-(CF₃)₃pyrazole (3,4,5-(CF₃)PzH) in a solvent-free process to form a product comprising a [3,4,5-tris(trifluoromethyl)pyrazolyl]Cu₃ complex ([3,4,5-(CF₃)₃Pz]Cu)₃, ([**Cu₃**]); b) extracting [**Cu₃**] with a solvent.

[00185] Aspect 25: The process of aspect 24, wherein the solvent comprises dichloromethane.

[00186] Aspect 26: The process of aspects 24 or 25, further comprising removing the solvent to form a solid-state [**Cu₃**].

[00187] Aspect 27: A composition comprising a trinuclear copper(I) pyrazolate complex, wherein the composition is reversibly transformed to a dinuclear copper(I)-alkene

complex, when exposed to a hydrocarbon feed gas mixture comprising one or more alkenes and one or more alkanes.

[00188] Aspect 28: The composition of aspect 27, wherein the one or more alkenes comprise ethylene, propylene, butene, pentene, or isobutylene.

[00189] Aspect 29: The composition of aspects 27 or 28, wherein the one or more alkanes comprise ethane, methane, propane, butane, or pentane.

[00190] Aspect 30: The composition of any one of aspects 27-29, wherein the one or more alkenes comprise ethylene.

[00191] Aspect 31: The composition of any one of aspects 27-30, wherein the one or more alkanes comprise ethane.

[00192] Aspect 32: The composition of aspect 31, wherein the trinuclear copper(I) pyrazolate complex comprises a [3,4,5-tris(trifluoromethyl)pyrazolyl] Cu ₃ complex ([3,4,5-(CF_3)₃Pz) Cu]₃, ([**Cu**₃]), wherein the composition is reversibly transformed to the dinuclear copper(I)-alkene complex comprising a [3,4,5-tris(trifluoromethyl)pyrazolyl] $\text{Cu}(\text{C}_2\text{H}_4)$]₂ ([3,4,5-(CF_3)₃Pz) $\text{Cu}(\text{C}_2\text{H}_4)$]₂, ([**Cu**₂•(C_2H_4)₂]) when exposed to a hydrocarbon feed gas mixture comprising ethylene and one or more alkanes comprising ethane.

[00193] Aspect 33: The composition of aspect 32, wherein [**Cu**₂•(C_2H_4)₂] is formed by an ethylene adsorption on [**Cu**₃].

[00194] Aspect 34: The composition of aspects 32 or 33, wherein an ethylene desorption transforms [**Cu**₂•(C_2H_4)₂] to [**Cu**₃].

[00195] Aspect 35: The composition of any one of aspects 32-34, wherein the composition exhibits an adsorption selectivity of ethylene/ethane on [**Cu**₃] of from about 1:1 to about 136:1 when measured at a temperature of 20 °C and an equilibrium loading at 1 atm.

[00196] Aspect 36: The composition of any one of aspects 32-35, wherein the composition exhibits an adsorption selectivity of ethylene/ethane on [**Cu**₃] of from about 1:1 to about 131:1 when measured at a temperature of 70 °C and an equilibrium loading at 1 atm.

[00197] Aspect 37: The composition of any one of aspects 32-36, wherein the reversible transformation is an endothermic structural rearrangement of [**Cu**₃].

[00198] Aspect 38: The composition of any one of aspects 32-36, wherein the reversible transformation is a solid-state transformation.

REFERENCES

[00199] The following references, to the extent that they provide exemplary procedural or other details supplementary to those set forth above, are specifically incorporated by reference.

1. Scholl, D. S.; Lively, R. P., Seven chemical separations to change the world. *Nature* **2016**, 532 (7600), 435-437.
2. Grande, C. A.; Poplow, F.; Rodrigues, A. E., Vacuum Pressure Swing Adsorption to Produce Polymer-Grade Propylene. *Separation Science and Technology* **2010**, 45 (9), 1252-1259.
3. Rege, S. U.; Padin, J.; Yang, R. T., Olefin/paraffin separations by adsorption: π -Complexation vs. kinetic separation. *AIChE Journal* **1998**, 44 (4), 799-809.
4. Berger, A. H.; Bhowan, A. S., Comparing physisorption and chemisorption solid sorbents for use separating CO₂ from flue gas using temperature swing adsorption. *Energy Procedia* **2011**, 4, 562-567.
5. Seo, S.; Simoni, L. D.; Ma, M.; DeSilva, M. A.; Huang, Y.; Stadtherr, M. A.; Brennecke, J. F., Phase-Change Ionic Liquids for Postcombustion CO₂ Capture. *Energy & Fuels* **2014**, 28 (9), 5968-5977.
6. Nijem, N.; Wu, H.; Canepa, P.; Marti, A.; Balkus, K. J.; Thonhauser, T.; Li, J.; Chabal, Y. J., Tuning the Gate Opening Pressure of Metal–Organic Frameworks (MOFs) for the Selective Separation of Hydrocarbons. *Journal of the American Chemical Society* **2012**, 134 (37), 15201-15204.
7. Cowan, M. G.; McDanel, W. M.; Funke, H. H.; Kohno, Y.; Gin, D. L.; Noble, R. D., High Ethene/Ethane Selectivity in 2,2'-Bipyridine-Based Silver(I) Complexes by Removal of Coordinated Solvent. *Angewandte Chemie, International Edition* **2015**, 54 (19), 5740-5743.
8. Slobodyanyuk, E. Y.; Artamonov, O. S.; Shishkin, O. V.; Mykhailiuk, P. K., One-Pot Synthesis of CF₃-Substituted Pyrazolines/Pyrazoles from Electron-Deficient Alkenes/Alkynes and CF₃CHN₂ Generated in situ: Optimized Synthesis of Tris(trifluoromethyl)pyrazole. *European Journal of Organic Chemistry* **2014**, 2014 (12), 2487-2495.
9. Dias, H. V. R.; Diyabalanage, H. V. K.; Eldabaja, M. G.; Elbjeirami, O.; Rawashdeh-Omary, M. A.; Omary, M. A., Brightly Phosphorescent Trinuclear Copper(I) Complexes of Pyrazolates: Substituent Effects on the Supramolecular Structure and Photophysics. *Journal of the American Chemical Society* **2005**, 127 (20), 7489-7501.
10. Dias, H. V. R.; Diyabalanage, H. V. K.; Rawashdeh-Omary, M. A.; Franzman, M. A.; Omary, M. A., Bright Phosphorescence of a Trinuclear Copper(I) Complex: Luminescence Thermochromism, Solvatochromism, and "Concentration Luminochromism". *Journal of the American Chemical Society* **2003**, 125 (40), 12072-12073.
11. Omary, M. A.; Rawashdeh-Omary, M. A.; Gonser, M. W. A.; Elbjeirami, O.; Grimes, T.; Cundari, T. R.; Diyabalanage, H. V. K.; Gamage, C. S. P.; Dias, H. V. R., Metal Effect on the Supramolecular Structure, Photophysics, and Acid–Base Character of Trinuclear Pyrazolato Coinage Metal Complexes. *Inorganic Chemistry* **2005**, 44 (23), 8200-8210.
12. Klimovica, K.; Kirschbaum, K.; Daugulis, O., Synthesis and Properties of "Sandwich" Diimine-Coinage Metal Ethylene Complexes. *Organometallics* **2016**, 35 (17), 2938-2943.
13. Jayaratna, N. B.; Gerus, I. I.; Mironets, R. V.; Mykhailiuk, P. K.; Yousufuddin, M.; Dias, H. V. R., Silver(I) and Copper(I) Adducts of a Tris(pyrazolyl)borate Decorated with Nine Trifluoromethyl Groups. *Inorganic Chemistry* **2013**, 52 (4), 1691-1693.

14. Schick, C., Differential scanning calorimetry (DSC) of semicrystalline polymers. *Analytical and Bioanalytical Chemistry* **2009**, 395 (6), 1589.
15. Li, B.; Zhang, Y.; Krishna, R.; Yao, K.; Han, Y.; Wu, Z.; Ma, D.; Shi, Z.; Pham, T.; Space, B.; Liu, J.; Thallapally, P. K.; Liu, J.; Chrzanowski, M.; Ma, S., Introduction of π -Complexation into Porous Aromatic Framework for Highly Selective Adsorption of Ethylene over Ethane. *Journal of the American Chemical Society* **2014**, 136 (24), 8654-8660.
16. Mofarahi, M.; Salehi, S. M., Pure and binary adsorption isotherms of ethylene and ethane on zeolite 5A. *Adsorption* **2013**, 19 (1), 101-110.
17. Choudhary, V. R.; Mayadevi, S.; Singh, A. P., Sorption isotherms of methane, ethane, ethene and carbon dioxide on NaX, NaY and Na-mordenite zeolites. *Journal of the Chemical Society, Faraday Transactions* **1995**, 91 (17), 2935-2944.
18. Weston, M. H.; Colon, Y. J.; Bae, Y.-S.; Garibay, S. J.; Snurr, R. Q.; Farha, O. K.; Hupp, J. T.; Nguyen, S. T., High propylene/propane adsorption selectivity in a copper(catecholate)-decorated porous organic polymer. *Journal of Materials Chemistry A* **2014**, 2 (2), 299-302.
19. He, Y.; Krishna, R.; Chen, B., Metal-organic frameworks with potential for energy-efficient adsorptive separation of light hydrocarbons. *Energy & Environmental Science* **2012**, 5 (10), 9107-9120.
20. Bloch, E. D.; Queen, W. L.; Krishna, R.; Zadrozny, J. M.; Brown, C. M.; Long, J. R., Hydrocarbon Separations in a Metal-Organic Framework with Open Iron(II) Coordination Sites. *Science* **2012**, 335 (6076), 1606-1610.
21. Li, P.; He, Y.; Arman, H. D.; Krishna, R.; Wang, H.; Weng, L.; Chen, B., A microporous six-fold interpenetrated hydrogen-bonded organic framework for highly selective separation of C_2H_4/C_2H_6 . *Chemical Communications (Cambridge, United Kingdom)* **2014**, 50 (86), 13081-13084.
22. Yu, C.; Cowan, M. G.; Noble, R. D.; Zhang, W., A silver(I) coordinated phenanthroline-based polymer with high ethylene/ethane adsorption selectivity. *Chemical Communications (Cambridge, United Kingdom)* **2014**, 50 (43), 5745-5747.
23. Wang, F.; Kusaka, S.; Hijikata, Y.; Hosono, N.; Kitagawa, S., Development of a Porous Coordination Polymer with a High Gas Capacity Using a Thiophene-Based Bent Tetracarboxylate Ligand. *ACS Applied Materials & Interfaces* **2017**.
24. Duan, X.; Wang, H.; Ji, Z.; Cui, Y.; Yang, Y.; Qian, G., A novel NbO-type metal-organic framework for highly separation of methane from C_2 -hydrocarbon at room temperature. *Materials Letters* **2017**, 196, 112-114.
25. Campbell, C.; Ferreira-Rangel, C. A.; Fischer, M.; Gomes, J. R. B.; Jorge, M., A Transferable Model for Adsorption in MOFs with Unsaturated Metal Sites. *The Journal of Physical Chemistry C* **2017**, 121 (1), 441-458.
26. Amino, S.; Arguelles, E.; Agerico Dino, W.; Okada, M.; Kasai, H., C_2H_4 adsorption on Cu(210), revisited: bonding nature and coverage effects. *Physical Chemistry Chemical Physics* **2016**, 18 (34), 23621-23627.
27. Verma, G.; Kumar, S.; Pham, T.; Niu, Z.; Wojtas, L.; Perman, J. A.; Chen, Y.-S.; Ma, S., Partially Interpenetrated NbO Topology Metal-Organic Framework Exhibiting Selective Gas Adsorption. *Crystal Growth & Design* **2017**, 17 (5), 2711-2717.
28. Gammage, M. D.; Stauffer, S.; Henkelman, G.; Becker, M. F.; Keto, J. W.; Kovar, D., Ethylene binding to Au/Cu alloy nanoparticles. *Surface Science* **2016**, 653, 66-70.
29. Farmanzadeh, D.; Abdollahi, T., A model for the ethylene and acetylene adsorption on the surface of $Cun(n=10-15)$ nanoclusters: A theoretical study. *Applied Surface Science* **2016**, 385, 241-248.
30. Yan, Y.; Juríček, M.; Coudert, F.-X.; Vermeulen, N. A.; Grunder, S.; Dailly, A.; Lewis, W.; Blake, A. J.; Stoddart, J. F.; Schröder, M., Non-Interpenetrated Metal-Organic

- Frameworks Based on Copper(II) Paddlewheel and Oligoparaxylene-Isophthalate Linkers: Synthesis, Structure, and Gas Adsorption. *Journal of the American Chemical Society* **2016**, 138 (10), 3371-3381.
31. Hähnel, T.; Kalies, G.; Krishna, R.; Möllmer, J.; Hofmann, J.; Kobalz, M.; Krautscheid, H., Adsorptive separation of C2/C3/C4-hydrocarbons on a flexible Cu-MOF: The influence of temperature, chain length and bonding character. *Microporous and Mesoporous Materials* **2016**, 224, 392-399.
32. Martins, V. F. D.; Ribeiro, A. M.; Ferreira, A.; Lee, U. H.; Hwang, Y. K.; Chang, J.-S.; Loureiro, J. M.; Rodrigues, A. E., Ethane/ethylene separation on a copper benzene-1,3,5-tricarboxylate MOF. *Separation and Purification Technology* **2015**, 149, 445-456.
33. Bondarchuk, S. V.; Minaev, B. F., Thermally accessible triplet state of [small pi]-nucleophiles does exist. Evidence from first principles study of ethylene interaction with copper species. *RSC Advances* **2015**, 5 (15), 11558-11569.
34. Makino, T.; Okada, M.; Kokalj, A., Adsorption of C2H4 on Stepped Cu(410) Surface: A Combined TPD, FTIR, and DFT Study. *The Journal of Physical Chemistry C* **2014**, 118 (47), 27436-27448.
35. Liu, K.; Li, B.; Li, Y.; Li, X.; Yang, F.; Zeng, G.; Peng, Y.; Zhang, Z.; Li, G.; Shi, Z.; Feng, S.; Song, D., An N-rich metal-organic framework with an rht topology: high CO2 and C2 hydrocarbons uptake and selective capture from CH4. *Chemical Communications* **2014**, 50 (39), 5031-5033.
36. Denysenko, D.; Grzywa, M.; Jelic, J.; Reuter, K.; Volkmer, D., Scorpionate-Type Coordination in MFU-4l Metal–Organic Frameworks: Small-Molecule Binding and Activation upon the Thermally Activated Formation of Open Metal Sites. *Angewandte Chemie International Edition* **2014**, 53 (23), 5832-5836.
37. Felix, H.; Matthew, S. D.; Jonas, B.; Mats, P., Structure and stability of weakly chemisorbed ethene adsorbed on low-index Cu surfaces: performance of density functionals with van der Waals interactions. *Journal of Physics: Condensed Matter* **2012**, 24 (42), 424217.
38. Kravchuk, T.; Venugopal, V.; Vattuone, L.; Burkholder, L.; Tysse, W. T.; Smerieri, M.; Rocca, M., Ethene Adsorption and Decomposition on the Cu(410) Surface. *The Journal of Physical Chemistry C* **2009**, 113 (49), 20881-20889.
39. Rejmak, P.; Mitoraj, M.; Broclawik, E., Electronic view on ethene adsorption in Cu(i) exchanged zeolites. *Physical Chemistry Chemical Physics* **2010**, 12 (10), 2321-2330.
40. Watson, G. W.; Wells, R. P. K.; Willock, D. J.; Hutchings, G. J., π adsorption of ethene on to the {111} surface of copper. *Surface Science* **2000**, 459 (1), 93-103.
41. Linke, R.; Becker, C.; Pelster, T.; Tanemura, M.; Wandelt, K., Adsorption of ethene on Cu(111). *Surface Science* **1997**, 377, 655-658.
42. Kubota, J.; Kondo, J. N.; Domen, K.; Hirose, C., IRAS Studies of Adsorbed Ethene (C2H4) on Clean and Oxygen-Covered Cu(110) Surfaces. *The Journal of Physical Chemistry* **1994**, 98 (31), 7653-7656.
43. Graham, A. P.; Bertino, M. F.; Hofmann, F.; Toennies, J. P., Adsorption, desorption, monolayer structure and dynamics of C2H4 on Cu(001). *Journal of the Chemical Society, Faraday Transactions* **1996**, 92 (23), 4749-4757.
44. Cen, P. L., Adsorption uptake curves of ethylene on Cu(I)–NaY zeolite. *AIChE Journal* **1990**, 36 (5), 789-793.
45. Huang, Y.-y., Ethylene complexes in copper(I) and silver (I) Y zeolites. *Journal of Catalysis* **1980**, 61 (2), 461-476.
46. Gerus, I. I.; Mironetz, R. X.; Kondratov, I. S.; Bezudny, A. V.; Dmytriv, Y. V.; Shishkin, O. V.; Starova, V. S.; Zaporozhets, O. A.; Tolmachev, A. A.; Mykhailiuk, P. K.,

"Reported, but Still Unknown". A Closer Look into 3,4-Bis- and 3,4,5-Tris(trifluoromethyl)pyrazoles. *Journal of Organic Chemistry* **2012**, 77 (1), 47-56.

CLAIMS

What is claimed is:

1. A process comprising:
exposing a trinuclear copper(I) pyrazolate complex to a hydrocarbon feed gas mixture comprising one or more alkenes and one or more alkanes, to form a product comprising a dinuclear copper(I)-alkene complex.
2. The process of claim 1, further comprising a step of separating the one or more alkenes from the one or more alkanes.
3. The process of claim 1 or 2, wherein the one or more alkenes comprise ethylene, propylene, butene, pentene, or isobutylene.
4. The process of any one of claims 1-3, wherein the one or more alkanes comprise ethane, methane, propane, butane, or pentane.
5. The process of any one of claims 1-4, wherein the one or more alkenes comprise ethylene.
6. The process of any one of claims 1-5, wherein the one or more alkenes comprise ethylene, wherein the one or more alkanes comprise ethane, and wherein the formed product comprises a dinuclear copper(I)-ethylene complex.
7. The process of claim 6, wherein the step of separating comprises separating ethylene from ethane.
8. The process of claim 6 or 7, wherein the dinuclear copper(I)-ethylene complex is formed by adsorption of ethylene on the trinuclear copper(I) pyrazolate complex.
9. The process of any one of claims 6-8, further comprising a step of desorption of ethylene from the dinuclear copper(I)-ethylene complex.
10. The process of claim 9, wherein the step of desorption is performed at a temperature from about -50 °C to about 150 °C and a pressure from about 0 bar to about 500 bar.
11. The process of claim 9 or 10, wherein the ethylene desorption forms a regenerated trinuclear copper(I) pyrazolate complex.

12. The process of any one of claims 1-11, wherein the trinuclear copper(I) pyrazolate complex is a [3,4,5-tris(trifluoromethyl)pyrazolyl)Cu]₃ complex ([3,4,5-(CF₃)₃Pz)Cu]₃, ([Cu₃]).
13. The process of any one of claims 6-12, wherein the dinuclear copper(I)-ethylene complex is a [3,4,5-tris(trifluoromethyl)pyrazolyl)Cu(C₂H₄)]₂ ([3,4,5-(CF₃)₃Pz)Cu(C₂H₄)]₂ complex, ([Cu₂•(C₂H₄)₂]).
14. The process of claim 13, wherein the ethylene adsorption causes an endothermic structural rearrangement of [Cu₃] to [Cu₂•(C₂H₄)₂].
15. The process of any one of claims 12-14, wherein at least a portion of the ethylene adsorption occurs at a 'step' pressure of about 2 kPa to about 30 kPa and a temperature from about 20 °C to about 75 °C (from about 293 K to about 348 K).
16. The process of any one of claims 12-15, wherein the step of exposing comprises exposing a solid-state [Cu₃] to the hydrocarbon feed gas mixture.
17. The process of any one of claims 12-16, wherein the step of exposing comprises exposing a dichloromethane solution of [Cu₃] to the hydrocarbon feed gas mixture to produce [Cu₂•(C₂H₄)₂].
18. The process of any one of claims 12-17, wherein the ethylene desorption from [Cu₂•(C₂H₄)₂] to regenerate [Cu₃] is performed in a solid-state.
19. The process of any one of claims 12-18, wherein the step of exposing results in a reversible solid-state structural transformation [Cu₃] to [Cu₂•(C₂H₄)₂].
20. The process of any one of claims 6-19, wherein the process does not comprise adsorption of ethane on the trinuclear copper(I) pyrazolate complex.
21. The process of any one of claims 12-20, wherein an adsorption selectivity of ethylene/ethane on [Cu₃] is from about 1:1 to about 136:1 when measured at a temperature of 20 °C and an equilibrium loading at 1 atm.
22. The process of any one of claims 12-21, wherein an adsorption selectivity of ethylene/ethane on [Cu₃] is from about 1:1 to about 131:1 when measured at a temperature of 70 °C and an equilibrium loading at 1 atm.

23. The process of any one of claims 12-22, wherein the process exhibits a decrease of a heat of adsorption by 50 to 85 % when compared to a substantially identical reference process comprising a copper (I) complex that is not [**Cu₃**].
24. The process of any one of claims 12-23, wherein [**Cu₃**] is formed by:
 - a) reacting copper (I) oxide with a precursor 3,4,5-(CF₃)₃pyrazole (3,4,5-(CF₃)₃PzH) in a solvent-free process to form a product comprising a [3,4,5-tris(trifluoromethyl)pyrazolyl]Cu₃ complex ([3,4,5-(CF₃)₃Pz)Cu]₃, ([**Cu₃**]);
 - b) extracting [**Cu₃**] with a solvent.
25. The process of claim 24, wherein the solvent comprises dichloromethane.
26. The process of claims 24 or 25, further comprising removing the solvent to form a solid-state [**Cu₃**].
27. A composition comprising a trinuclear copper(I) pyrazolate complex, wherein the composition is reversibly transformed to a dinuclear copper(I)-alkene complex, when exposed to a hydrocarbon feed gas mixture comprising one or more alkenes and one or more alkanes.
28. The composition of claim 27, wherein the one or more alkenes comprise ethylene, propylene, butene, pentene, or isobutylene.
29. The composition of claims 27 or 28, wherein the one or more alkanes comprise ethane, methane, propane, butane, or pentane.
30. The composition of any one of claims 27-29, wherein the one or more alkenes comprise ethylene.
31. The composition of any one of claims 27-30, wherein the one or more alkanes comprise ethane.
32. The composition of claim 31, wherein the trinuclear copper(I) pyrazolate complex comprises a [3,4,5-tris(trifluoromethyl)pyrazolyl]Cu₃ complex ([3,4,5-(CF₃)₃Pz)Cu]₃, ([**Cu₃**]), wherein the composition is reversibly transformed to the dinuclear copper(I)-alkene complex comprising a [3,4,5-tris(trifluoromethyl)pyrazolyl]Cu(C₂H₄)₂ ([3,4,5-(CF₃)₃Pz)Cu(C₂H₄)₂,

- ([Cu₂•(C₂H₄)₂]) when exposed to a hydrocarbon feed gas mixture comprising ethylene and one or more alkanes comprising ethane.
33. The composition of claim 32, wherein [Cu₂•(C₂H₄)₂] is formed by an ethylene adsorption on [Cu₃].
 34. The composition of claim 32 or 33, wherein an ethylene desorption transforms [Cu₂•(C₂H₄)₂] to [Cu₃].
 35. The composition of any one of claims 32-34, wherein the composition exhibits an adsorption selectivity of ethylene/ethane on [Cu₃] of from about 1:1 to about 136:1 when measured at a temperature of 20 °C and an equilibrium loading at 1 atm.
 36. The composition of any one of claims 32-35, wherein the composition exhibits an adsorption selectivity of ethylene/ethane on [Cu₃] of from about 1:1 to about 131:1 when measured at a temperature of 70 °C and an equilibrium loading at 1 atm.
 37. The composition of any one of claims 32-36, wherein the reversible transformation is an endothermic structural rearrangement of [Cu₃].
 38. The composition of any one of claims 32-36, wherein the reversible transformation is a solid-state transformation.

1/27




FIG. 1A




FIG. 1B




FIG. 2A




FIG. 2B

2/27




FIG. 3A




FIG. 3B




FIG. 4

3/27




FIG. 5

4/27




FIG. 6

5/27




FIG. 7

6/27




FIG. 8

7/27




FIG. 9




FIG. 10




FIG. 11

9/27





FIG. 12


10/27



X: parts per Million: 1H

FIG. 13

11/27



X: parts per Million: 1H

FIG. 14

12/27




FIG. 15

13/27




FIG. 16

14/27




FIG. 17

15/27




FIG. 18




FIG. 19




FIG. 20




FIG. 21

17/27




FIG. 22A




FIG. 22B




FIG. 23




FIG. 24




FIG. 25




FIG. 26




FIG. 27




FIG. 28

20/27




FIG. 29




FIG. 30




FIG. 31




FIG. 32




FIG. 33A




FIG. 33B




FIG. 34A




FIG. 34B




FIG. 35




FIG. 36

24/27




FIG. 37A

25/27




FIG. 37C




FIG. 37B

26/27





FIG. 38

27/27



39
G.
F.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 19/56286

A. CLASSIFICATION OF SUBJECT MATTER

IPC - C07F 15/00; C09K 11/06; H01L 51/00 (2019.01)

CPC - C07F 15/0026; C07F 15/0033; C07F 15/0086

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

See Search History document

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

See Search History document

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

See Search History document

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2002/0042518 A1 (XU et al.) 11 April 2002 (11.04.2002); para [0016], [0029], [0032]	1-3, 27-29
A	HOU L. et al., "Trinuclear-based Copper(I) Pyrazolate Polymers: Effect of Trimer pi-Acid...Halide/Pseudohalide Interactions on the Supramolecular Structure and Phosphorescence", Inorganic Chemistry [online], 08 December 2010 (08.12.2010) [retrieved on 2019-12-04], volume 50, issue 1, retrieved from the Internet: < DOI: 10.1021/ic101901w >, pp. 261-270; see entire document, especially, pg 261-262.	1-3, 27-29
A	DIAS H. V. R. et al., "Copper(I) ethylene adducts and aziridination catalysts based on fluorinated tris(pyrazolyl)borates [HB(3-(CF ₃),5-(R)Pz) ₃] (where R = CF ₃ , C ₆ H ₅ , H; Pz = pyrazolyl)", Organometallics [online], 28 February 2002 (28.02.2002) [retrieved on 2019-12-04], volume 21, issue 7, retrieved from the Internet: < DOI: 10.1021/om010886v >, pp. 1466-1473; see entire document, especially, pg 1469-1470.	1-3, 27-29
A	JAYARATNA N. B. et al., "Silver(I) and Copper(I) Adducts of a Tris(pyrazolyl)borate Decorated with Nine Trifluoromethyl Groups", Inorganic Chemistry [online], 31 January 2013 (31.01.2013) [retrieved on 2019-12-04], volume 52, issue 4, retrieved from the Internet: < DOI: 10.1021/ic302715d >, pp. 1691-1693; see entire document, especially, pg 1692.	1-3, 27-29
A	STRAUB B. F. et al., "A remarkably stable copper(I) ethylene complex: synthesis, spectroscopy and structure", Chemical Communications [online], December 1999 (12.1999) [retrieved on 2019-12-04], issue 24, retrieved from the Internet: < DOI: 10.1039/a907928i >, pp. 2507-2508; see entire document, especially, pg 2507.	1-3, 27-29



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"D" document cited by the applicant in the international application	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"E" earlier application or patent but published on or after the international filing date	"&" document member of the same patent family
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

04 December 2019

Date of mailing of the international search report

07 JAN 2020

Name and mailing address of the ISA/US

Mail Stop PCT, Attn: ISA/US, Commissioner for Patents
P.O. Box 1450, Alexandria, Virginia 22313-1450

Facsimile No. 571-273-8300

Authorized officer

Lee Young

Telephone No. PCT Helpdesk: 571-272-4300

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 19/56286

Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☒ Claims Nos.: 4-26, 30-38
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying additional fees, this Authority did not invite payment of additional fees.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- ☐ The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- ☐ No protest accompanied the payment of additional search fees.