



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C09D 5/14	A1	(11) International Publication Number: WO 94/16024 (43) International Publication Date: 21 July 1994 (21.07.94)
<p>(21) International Application Number: PCT/US93/12366</p> <p>(22) International Filing Date: 17 December 1993 (17.12.93)</p> <p>(30) Priority Data: 000,170 4 January 1993 (04.01.93) US</p> <p>(71) Applicant: OLIN CORPORATION [US/US]; 350 Knotter Drive, P.O. Box 586, Cheshire, CT 06410-0586 (US).</p> <p>(72) Inventors: HANI, Rahim; 117 Winthrop Drive, Cheshire, CT 06410 (US). WALDRON, Craig; 101-19 Hitchcock Road, Waterbury, CT 06705 (US). FARMER, Douglas, A., Jr.; 35 Skytop Drive, Madison, CT 06443 (US).</p> <p>(74) Agents: CARLSON, Dale, Lynn et al.; Wiggin & Dana, One Century Tower, New Haven, CT 06508-1832 (US).</p>	<p>(81) Designated States: AU, BB, BG, BR, BY, CA, CZ, FI, HU, JP, KP, KR, KZ, LK, MG, MN, MW, NO, NZ, PL, RO, RU, SD, SK, UA, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>	
(54) Title: GEL-FREE PAINT CONTAINING CUPROUS OXIDE PLUS 2,2'-DITHIOBIS(PYRIDINE-1-OXIDE) COMPOUND		
(57) Abstract		
<p>The present invention relates generally to paints and paint bases, and, more specifically to a process for providing a stable gel-free dispersion of biocidal amounts of 2,2'-dithiobis(pyridine-1-oxide) or its metal salt adducts of the formula $(C_5H_4NOS)_2MY_t$ or their hydrates plus cuprous oxide biocide in paint, where M is an alkaline earth metal, Y is the anion of an organic or inorganic acid, and t is 1 or 2. The resulting paint is storage stable and remains gel-free after several months of storage at room temperature.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgystan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

-1-

**GEL-FREE PAINT CONTAINING CUPROUS OXIDE PLUS
2,2'-DITHIOBIS(PYRIDINE-1-OXIDE) COMPOUND**

The present invention relates generally to paints and paint bases, and, more specifically to a process for providing a stable, gel-free dispersion of biocidal amounts of 2,2'-dithiobis(pyridine-
5 1-oxide), or its metal salt adducts of the formula $(C_5H_4NOS)_2MY_t$, or their hydrates, plus cuprous oxide biocide in paint, where M is an alkaline earth metal, Y is the anion of an organic or inorganic acid, and t is 1 or 2.

10 Combinations of zinc pyrithione and cuprous oxide are known to be excellent antifouling agents when formulated into paints and paint bases (i.e., the paint before pigment addition) also containing rosin, as disclosed, for example, in U.S. Patent No.
15 5,057,153. Unfortunately, however, such paints have now been found to thicken or gel unacceptably within a few days, at best, or a few hours, at worst, when formulated with typical commercial grades of zinc pyrithione in combination with cuprous oxide.

20 Heretofore, various solutions to the problem of gellation of paints containing rosin and zinc pyrithione in combination with cuprous oxide, have been suggested. Illustrative solutions have been to use rigorously purified zinc pyrithione, as
25 disclosed in U.S. Patent No. 5,098,473, or to add amines or esterified rosin, as disclosed in U.S. Patent No. 5,112,397, or to use a metal salt of rosin, as disclosed in U.S. Patent No. 5,137,569. Since these solutions may have drawbacks such as
30 increased cost or lack of compatibility with some paints, a new, economical solution to the problem would be highly desired by the paint manufacturing

-2-

community in order to maximize flexibility in using this combination of biocides in view of its excellent biocidal activity.


The present invention provides one solution to this problem. Although individually cuprous oxide, 2,2'-dithiobis(pyridine-1-oxide) (hereinafter also referred to as "bispyrithione"), and its metal salt adducts and their hydrates are all known biocides, the use of a combination of bispyrithione or its metal salt adducts or their hydrates plus cuprous oxide as biocides in the production of a paint which is stable against gellation during storage have not been known heretofore to the knowledge of the present inventors.

In one aspect, the present invention relates to a process for providing a gel-free paint or paint base characterized by biocidal efficacy. The process comprises adding to a paint or paint base a biocidally effective amount of bispyrithione or its metal salt adducts or their hydrates plus cuprous oxide, or a combination thereof.

The bispyrithione metal salt adducts useful in the present invention have the formula $(C_5H_4NOS)_2 MY_t$, wherein M is an alkaline earth metal, Y is the anion of an inorganic or organic acid and t is either 1 or 2. More particularly, the adducts contain an alkaline earth metal (M) selected from the group consisting of calcium, magnesium, barium and strontium with calcium and magnesium being preferred and the anion (Y) is selected from the group consisting of halides, sulfates, nitrates, chlorates and acetates with the chlorides and sulfates being preferred. More particularly preferred are the adducts of calcium chloride ($CaCl_2$) or magnesium sulfate ($MgSO_4$). Also included in the adducts of this invention are hydrates of the

-3-

aforementioned compounds, i.e., adducts including
nH₂O groups where n is an integer of 0 to 10.
Additionally, the adducts may contain one or more
substituents on either or both pyridine ring
5 structures such as alkyls, halogens and alkoxy
groups. Reference to the adducts in the
specification and claims is intended to include
compounds containing such substituents. It is
further noted that (C₅H₄NOS)₂, as used above and
10 throughout the specification and claims represents
bis-(2-pyridyl-1-oxide) disulfide and has the
structural formula shown below:



The preparation of the adducts is described in
U.S. Patent No. 3,818,018.

15 In another aspect, the present invention
relates to a paint or paint base composition
characterized by enhanced biocidal efficacy and
gellation resistance wherein the paint or paint base
contains a biocide consisting essentially of
20 bispyrithione or its metal salt adducts or their
hydrates and cuprous oxide, or a combination
thereof. Preferably, the bispyrithione or its metal
salt adducts or their hydrates, or combination
thereof, are present in an amount of between about
25 1% and about 25% (preferably 5-25%, more preferably
10-25%), and the cuprous oxide being present in an
amount of between about 20% and about 70%, the total
amount of said bispyrithione or its metal salt
adducts or their hydrates plus said cuprous oxide

being between about 20% and about 80%, based upon the total weight of the paint or paint base.

These and other aspects of the invention will become apparent upon reading the following detailed
5 description of the invention.

It has been surprisingly found that the compositions of the present invention are storage stable and do not tend to form gels upon standing. This result is in distinct contrast to the tendency
10 for zinc pyrithione plus cuprous oxide compositions to form gels, as illustrated by the specific examples provided hereinbelow.

Although the improved biocidal efficacy and gellation resistance advantages associated with the
15 present invention are expected to provide advantages when used in a wide variety of paints, including indoor and outdoor household paints, industrial and commercial paints, particularly advantageous results are obtained when the process and composition of the
20 present invention are utilized in conjunction with marine paints for use, for example, on ship's hulls. In addition, the composition and process of the present invention provides highly desirable results in the context of exterior paints of both the latex
25 and alkyd types.

Typically, a paint composition will contain a resin, an organic solvent (such as xylene or methylisobutylketone), a pigment, and various
30 optional additives such as thickening agent(s), wetting agents, and the like, as is well-known in the art. The resin is preferably selected from the group consisting of vinyl, alkyd, epoxy, acrylic, polyurethane and polyester resins, and combinations thereof. The resin is preferably employed in an
35 amount of between about 20% and about 80% based upon the weight of the paint or paint base.

In addition, the paint composition of the present invention optionally additionally contains optional additives which have a favorable influence on the viscosity, the wetting power and the dispersibility, as well as on the stability to freezing and electrolytes and on the foaming properties. The total amount of optional additives is preferably no greater than 20% by weight, more preferably between about 1% and about 5% by weight, based upon the total weight of the paint composition.

Illustrative thickening agents include cellulose derivatives, for example methyl, hydroxyethyl, hydroxypropyl and carboxymethyl cellulose, poly(vinyl alcohol), poly(vinylpyrrolidone), poly(ethylene-glycol), salts of poly(acrylic acid) and salts of acrylic acid/acrylamide copolymers.

Suitable wetting and dispersing agents include sodium polyphosphate, aryl or alkyl phosphates, salts of low-molecular-weight poly(acrylic acid), salts of poly(ethane-sulfonic acid), salts of poly(vinyl-phosphonic acid), salts of poly(maleic acid) and salts of copolymers of maleic acid with ethylene, 1-olefins with 3 to 18 carbon atoms and/or styrene.

In order to increase the stability to freezing and electrolytes there may be added to the paint composition various monomer 1,2-diols, for example glycol, propylene-glycol-(1,2), and butylene-glycol-(1,2) or polymers thereof, or ethoxylated compounds, for example reaction products of ethylene oxide with long-chain alkanols, amines, carboxylic acids, carboxylic acid amides, alkyd phenols, poly(propylene-glycol) or poly(butylene-glycol).

The minimum temperature of film formation (white point) of the paint composition may be reduced by adding solvents, such as ethylene-glycol, butyl-glycol, ethyl-glycol acetate, ethyl-diglycol acetate, butyl-diglycol acetate, benzene or alkylated aromatic hydrocarbons. As defoaming agents there are suitable for example poly(propylene-glycol) and polysiloxanes.

The paint composition of the present invention may be used as a paint for natural or synthetic materials, for example wood, paper, metals, textiles and plastics. It is particularly suitable as an outdoor paint, and is excellent for use as a marine paint.

If a marine paint is being fabricated, the paint preferably contains a swelling agent to cause the paint to gradually "slough off" in its marine environment, thereby causing renewed biocidal efficacy of newly exposed biocide (i.e., the copper pyrithione or pyrithione disulfide plus the cuprous oxide) at the surface of the paint in contact with the water medium of the marine environment. Illustrative swelling agents are naturally-occurring or synthetic clays, such as kaolin, montmorillonite (bentonite), clay mica (muscovite), and chlorite (hectonite), and the like. In addition to clays, other swelling agents, including natural or synthetic polymers, such as that commercially available as POLYMERGEL, have been found to be useful in the compositions of the present invention to provide the desired abrasive "sloughing off" effect. Swelling agents can be used singly or in combination. The total amount of optional additives is preferably no greater than 20% by weight, more preferably between about 1% and about 5% by weight,

-7-

based upon the total weight of the paint composition.

The invention is further illustrated by the following Examples. Unless otherwise stated, the
 5 "parts" and "%" are "parts by weight" and "percent by weight", respectively based upon the weight of the paint or paint base.

While the invention has been described above with references to specific embodiments thereof, it
 10 is apparent that many changes, modifications and variations can be made without departing from the inventive concept disclosed herein. Accordingly, it is intended to embrace all such changes, modifications and variations that fall within the
 15 spirit and broad scope of the appended claims.

Comparative Example A

Demonstration of Gellation Results in a Paint containing Cuprous Oxide Plus Zinc Pyrithione

A paint was prepared using the following
 20 formulation:

The solvent mixture used was a 1:2:1 mixture of xylene MIBK and carbitol acetate (called mixed solvent).

The zinc pyrithione used was standard
 25 commercial grade and assayed 97.8% pure by iodometric titration.

	<u>Material</u>	<u>Parts</u>	<u>%</u>
	VAGH resin (1)	9.3	2.8
	DISPERBYK 163 (2)	5.1	1.5
30	Tributyl Phosphate	6.45	2.0
	Cuprous Oxide	136.5	41.4

-8-

	<u>Material</u>	<u>Parts</u>	<u>%</u>
	TITANOX (3)	7.5	2.3
	Zinc pyrithione powder	25.5	7.7
	Wood Rosin	6.3	1.9
5	Solvent Mixture	133.0	40.0

- 1) vinyl chloride-vinyl acetate-vinyl alcohol
terpolymer, a product of Union Carbide
Corporation.
- 10 2) a high molecular weight block copolymer, a
product of BYK-Chemie.
- (3) titanium dioxide, a product of DuPont
Company.

The procedure employed for preparing the paint
was as follows:

- 15 (1) A one pint paint can was charged with 41.93
g of a 22.2% VAGH resin solution in a 2:1
mixture by volume of MIBK and xylene.
- (2) A mixture of 5.1 g Disperbyk 163 and 5.1 g
mixed solvent was added.
- 20 (3) Tributyl phosphate was added to the paint
can and mixed with a high speed disperser at
1000 RPM for 10 minutes.
- (4) The cuprous oxide, zinc pyrithione,
titanox, and 10.8 g carbitol acetate were added
25 to the paint can and mixing was continued at
7000 RPM for 1 hr.
- (5) The mixing speed was reduced to 2500 RPM
and 35 g of mixed solvent was added.
- 30 (6) Once the temperature dropped from 45°C to
below 35°C, a solution of 6.3 g of wood rosin
in 50 g of mixed solvent was added to the can
and the mixture was mixed for 1.0 hr. at 2500
RPM.

-9-

The paint formulation made according to this procedure was of suitable viscosity for application by brush immediately after preparation, but thickened to an unpourable paste after approximately 5 6 hours.

Example 1

Demonstration of Stable Paint Containing Cuprous Oxide and Bispyrithione Magnesium Sulfate Hydrate Adduct

10 A paint was prepared using the following formulation:

	<u>Material</u>	<u>Parts</u>	<u>%</u>
	VAGH Resin (22%)	3.90	2.85
	Disperbyk 163	2.70	1.97
15	Cuprous Oxide	75.00	54.78
	Magnesium Sulfate Hydrate Adduct of Bispyrithione	6.85	5.00
	Tricresyl Phosphate	3.60	2.63
	Wood Rosin WW	6.85	5.00
20	Solvent Mixture *60% MIBK/40% XYLENE	38.00	27.76
	TOTAL	136.90	100.00

The Procedure was the same as the above example. The formulation remained gel-free, and 25 continues to remain gel-free, after one month of storage.

WHAT IS CLAIMED IS:

1. A paint or paint base composition characterized by enhanced biocidal efficacy and gellation resistance wherein the paint or paint base contains a biocide consisting essentially of cuprous oxide and 2,2'-dithiobis(pyridine-1-oxide) or a metal salt adduct thereof having the empirical formula $(C_5H_4NOS)_2 MY_t$, or a hydrate of said metal salt adduct, wherein M is an alkaline earth metal selected from the group consisting of calcium, magnesium, barium and strontium, Y is an anion selected from the group consisting of halides, sulfates, nitrates, chlorates and acetates and t is either 1 or 2.
2. The paint or paint base of claim 1 characterized in that M is calcium or magnesium.
3. The paint or paint base of claim 2 characterized in that Y is chloride or sulfate.
4. The paint or paint base of claim 3 characterized in that M is calcium, Y is chloride and t is 2.
5. The paint or paint base of claim 3 characterized in that M is magnesium, Y is sulfate and t is 1.
6. The paint or paint base of claim 1 characterized in that the formula is selected from the group consisting of $(C_5H_4NOS)_2CaCl_2$, $(C_5H_4NOS)_2MgSO_4 \cdot 3H_2O$, $(C_5H_4NOS)_2SrCl_2$, $(C_5H_4NOS)_2SrBr_2$, $(C_5H_4NOS)_2BaBr_2$, $(C_5H_4NOS)_2Ca(NO_3)_2$ and $(C_5H_4NOS)_2Ba(ClO_3)_2 \cdot 18H_2O$.

7. The paint or paint base of claim 1 characterized in that said 2,2'-dithiobis(pyridine-1-oxide) or a metal salt adduct thereof or a hydrate of said metal salt adduct is present in an amount of
5 between about 1% and about 25%, and said cuprous oxide is present in an amount of between about 20% and about 70%, the total amount of said
2,2'-dithiobis(pyridine-1-oxide) or a metal salt adduct thereof or a hydrate of said metal salt
10 adduct plus said cuprous oxide being between about 20% and about 80%, based upon the total weight of the paint or paint base.

8. The paint or paint base of claim 1 characterized in that said paint or paint base
15 additionally contains a resin selected from the group consisting of vinyl, alkyl, epoxy, acrylic, polyurethane and polyester resins, and combinations thereof.

9. The paint or paint base of claim 1
20 characterized in that said paint or paint base additionally contains a swelling agent selected from the group consisting of natural and synthetic clay and natural and synthetic polymer swelling agents.

10. The paint or paint base of claim 9
25 characterized in that said swelling agent is selected from the group consisting of kaolin, montomorillonite (bentonite), clay mica (muscovite), and chlorite (hectonite), and combinations thereof.

-12-

11. A process for providing a gellation-inhibited paint or paint base containing 2,2'-dithiobis(pyridine-1-oxide) or a metal salt adduct thereof or a hydrate of said metal salt adduct and cuprous oxide characterized by the step
5 of adding said 2,2'-dithiobis(pyridine-1-oxide) or a metal salt adduct thereof or a hydrate of said metal salt adduct and also adding cuprous oxide to a paint or paint base to provide a paint or paint base
10 characterized by enhanced biocidal efficacy and resistance to gellation, said 2,2'-dithiobis(pyridine-1-oxide) or a metal salt adduct thereof or a hydrate of said metal salt adduct being present in an amount of between about
15 1% and about 25%, and said cuprous oxide being present in an amount of between about 20% and about 70%, the total amount of said 2,2'-dithiobis(pyridine-1-oxide) or a metal salt adduct thereof or a hydrate of said metal salt
20 adduct plus said cuprous oxide being between about 20% and about 80% based upon the total weight of the paint or paint base.

12. The process of claim 11 characterized in that said 2,2'-dithiobis(pyridine-1-oxide) has the
25 empirical formula $(C_5H_4NOS)_2 MY_t$, wherein M is an alkaline earth metal selected from the group consisting of calcium, magnesium, barium and strontium, Y is an anion selected from the group consisting of halides, sulfates, nitrates, chlorates
30 and acetates and t is either 1 or 2.

13. The process of claim 12 characterized in that M is calcium or magnesium.

-13-

14. The process of claim 12 characterized in that Y is chloride or sulfate.

15. The process of claim 12 characterized in that M is calcium, Y is chloride and t is 2.

5 16. The process of claim 12 characterized in that M is magnesium, Y is sulfate and t is 1.

17. The process of claim 12 characterized in that the formula is selected from the group consisting of $(C_5H_4NOS)_2CaCl_2$, $(C_5H_4NOS)_2MgSO_4 \cdot 3H_2O$,
10 $(C_5H_4NOS)_2SrCl_2$, $(C_5H_4NOS)_2SrBr_2$, $(C_5H_4NOS)_2BaBr_2$,
 $(C_5H_4NOS)_2Ca(NO_3)_2$ and $(C_5H_4NOS)_2Ba(ClO_3)_2 \cdot 18H_2O$.

18. The process of claim 11 characterized in that the total amount of 2,2'-dithiobis(pyridine-1-oxide) or a metal salt adduct thereof or a hydrate
15 of said metal salt adduct plus said cuprous oxide is present in an amount of between about 20% and about 75% based upon the total weight of the paint or paint base composition.

19. The process of claim 11 characterized in that said paint or paint base additionally contains
20 a resin selected from the group consisting of vinyl, alkyl, epoxy, acrylic, polyurethane and polyester resins, and combinations thereof.


20. The process of claim 11 characterized in that said paint or paint base additionally contains
25 a swelling agent selected from the group consisting of natural and synthetic clay and natural and synthetic polymer swelling agents.

-14-

21. The process of claim 20 characterized in
that said swelling agent is selected from the group
consisting of kaolin, montomorillonite (bentonite),
clay mica (muscovite), and chlorite (hectonite), and
5 combinations thereof.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US93/12366

A. CLASSIFICATION OF SUBJECT MATTER IPC(5) :C09D 5/14 US CL :106/16, 18.33, 18.34; 514/345, 499, 500; 504/121 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) U.S. : 106/16, 18.33, 18.34; 514/345, 499, 500; 504/121 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched N/A Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) N/A		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US, A, 4,039,312 (PATRU) 02 AUGUST 1977, col. 1, lines 20-57.	1
A	US, A, 5,057,153 (RUGGIERO) 15 OCTOBER 1991, col. 1, line 44 - col. 2, line 64.	1-21
A	US, A, 5,112,397 (FARMER JR. et al) 12 MAY 1992, col. 1, line 30 - col. 2, line 64.	1-21
A	US, A, 5,137,569 (WALDRON et al) 11 AUGUST 1992, col. 1, line 39 - col. 3, line 66.	1-21
A, P	US, A, 5,185,033 (HANI et al) 09 FEBRUARY 1993, col. 1, line 49 - col. 2, line 59.	1-21
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* "A" "E" "L" "O" "P"	Special categories of cited documents: document defining the general state of the art which is not considered to be part of particular relevance earlier document published on or after the international filing date document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) document referring to an oral disclosure, use, exhibition or other means document published prior to the international filing date but later than the priority date claimed	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art *&* document member of the same patent family
Date of the actual completion of the international search	Date of mailing of the international search report	
02 February 1994	23 FEB 1994	
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231	Authorized officer  ANTHONY GREEN	
Facsimile No. NOT APPLICABLE	Telephone No. (703) 308-0661	