



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2639908 C 2016/04/05

(11)(21) **2 639 908**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(86) **Date de dépôt PCT/PCT Filing Date:** 2006/11/15
(87) **Date publication PCT/PCT Publication Date:** 2007/08/23
(45) **Date de délivrance/Issue Date:** 2016/04/05
(85) **Entrée phase nationale/National Entry:** 2008/07/22
(86) **N° demande PCT/PCT Application No.:** US 2006/044328
(87) **N° publication PCT/PCT Publication No.:** 2007/094831
(30) **Priorité/Priority:** 2006/02/14 (US11/353,606)

(51) **Cl.Int./Int.Cl. A61L 29/04** (2006.01),
A61L 29/12 (2006.01), **A61M 25/00** (2006.01),
C09K 19/38 (2006.01)
(72) **Inventeur/Inventor:**
CHEN, JOHN J., US
(73) **Propriétaire/Owner:**
BOSTON SCIENTIFIC LIMITED, BB
(74) **Agent:** PIASETZKI NENNIGER KVAS LLP

(54) **Titre : DISPOSITIF MEDICAL EMPLOYANT DES COPOLYMERES SEQUENCES A CRISTAUX LIQUIDES ET PROCEDE POUR
LE FABRIQUER**
(54) **Title: MEDICAL DEVICE EMPLOYING LIQUID CRYSTAL BLOCK COPOLYMERS AND METHOD OF MAKING THE SAME**

(57) **Abrégé/Abstract:**

A medical device, at least a portion of which is formed from a polymer composition including at least one liquid crystal block copolymer having at least one A block and at least one B block wherein the A block is formed of mesogenic repeat units and the B block is a soft block.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
23 August 2007 (23.08.2007)

PCT

(10) International Publication Number
WO 2007/094831 A3

(51) International Patent Classification:

A61L 29/04 (2006.01) *A61M 25/00* (2006.01)
A61L 29/12 (2006.01) *C09K 19/38* (2006.01)

(21) International Application Number:

PCT/US2006/044328

(22) International Filing Date:

15 November 2006 (15.11.2006)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

11/353,606 14 February 2006 (14.02.2006) US

(71) Applicant: **BOSTON SCIENTIFIC SCIMED, INC.**
[US/US]; One Scimed Place, Maple Grove, Minnesota
55311 (US).

(72) Inventor: **CHEN, John, J.**; 4725 Terraceview Lane
North, Plymouth, Minnesota 55446 (US).

(74) Agent: **RYAN-LINDQUIST, Lisa**; Vidas, Arrett
Steinkraus, P.A., 6640 Shady Oak Rd., Suite 400, Eden
Prairie, MN 55344-7834 (US).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- *with international search report*
- *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

(88) Date of publication of the international search report:
7 February 2008

(54) Title: MEDICAL DEVICE EMPLOYING LIQUID CRYSTAL BLOCK COPOLYMERS AND METHOD OF MAKING THE SAME

(57) Abstract: A medical device, at least a portion of which is formed from a polymer composition including at least one liquid crystal block copolymer having at least one A block and at least one B block wherein the A block is formed of mesogenic repeat units and the B block is a soft block.

WO 2007/094831 A3

**MEDICAL DEVICE EMPLOYING LIQUID CRYSTAL
BLOCK COPOLYMERS AND METHOD OF MAKING THE SAME**

FIELD OF THE INVENTION

5 The present invention relates to the field of insertable and/or implantable medical devices, particularly to balloon catheter assemblies and components thereof.

BACKGROUND OF THE INVENTION

10 It is known to use liquid crystal polymers (LCPs) in combination with thermoplastic polymers, i.e. matrix polymers, for use in the manufacture of insertable and/or implantable medical devices such as catheter assemblies and components thereof such as inflatable medical balloons which can be disposed at the distal end of a balloon catheter assembly. For example, see commonly assigned U.S. Patent Nos. 6977103, 6905743, 6730377 and 6284333. See also U.S. Patent Nos. 6596219, 6443925 and
15 6325780 to Schaible.

 Liquid crystal polymers are known to phase separate from commonly used thermoplastic polymers into multiphase polymer compositions. For example, see U.S. Patent Nos. 5248305 and 5156785 to Zdrahala.

20 Compatibilized blends of LCP and thermoplastic polymers have been found suitable for use as medical device balloon materials. See for example commonly assigned U.S. Patent No. 6,242,063.

 It would be desirable to have a liquid crystal polymer material or blend using a liquid crystal polymer material which has increased compatibility over other previous LCP/polymer blends which could be employed in the formation of medical
25 devices, particularly in the manufacture of catheter assemblies or components thereof.

 The art referred to and/or described above is not intended to constitute an admission that any patent, publication or other information referred to herein is "prior art" with respect to this invention. In addition, this section should not be construed to mean that a search has been made or that no other pertinent information exists.

30 Without limiting the scope of the invention a brief summary of some of the claimed embodiments of the invention is set forth below. Additional details of the summarized embodiments of the invention and/or additional embodiments of the invention may be found in the Detailed Description of the Invention below.

A brief abstract of the technical disclosure in the specification is provided as well. The abstract is not intended to be used for interpreting the scope of the claims.

SUMMARY OF THE INVENTION

5 The present invention relates to polymer compositions useful in the formation of medical devices which include at least one liquid crystal block copolymer having at least one A block and at least one B block.

 The polymer compositions may further comprise at least one polymer selected from the group consisting of polyamides, polyesters, polyethers, polyolefins, 10 polyimides, block copolymers comprising at least one polyolefin, polyester, polyether, polyamide, and/or polyimide segment, and silicones.

 The A block, which may also be referred to herein as the mesogenic (liquid crystal) block, may include any suitable mesogenic repeat (monomer) unit. As used herein, the term "mesogenic" shall be used to refer to those repeat units which 15 impart liquid crystal properties, such as stiffness and restriction to rotation, to the polymer. The term "mesogenic unit" as employed herein, shall be used to refer to any monomer having a mesogen, as well as those monomers including spacers such as methylene groups, therein.

 Any suitable mesogenic repeat unit may be employed herein. Suitably, 20 the A block has at least one aromatic group per each mesogenic repeat unit and more suitably the A block has at least two aromatic groups per each mesogenic repeat unit.

 The B block is the soft block. Suitably, the B block is aliphatic. Suitably the B block has less than 10% aromaticity by weight of the B block, more suitably less than 5% aromaticity by weight of the B block and most suitably substantially no 25 aromaticity.

 The polymers may be formed using conventional reaction techniques such as condensation reactions as will be described in more detail below.

 These polymers may be employed alone, or in combination with other polymers.

The polymers find particular utility in the formation of medical devices such as catheter assemblies and components thereof, including, for example, shafts, tips, manifolds and balloons.

The medical devices may be formed, for example, of a polymer composition comprising a blend of a thermoplastic base polymer comprising at least one segment of polyolefin, polyamide, polyester, polyether, or silicone wherein the polymer composition further comprises a liquid crystal block copolymer, the liquid crystal block copolymer comprises at least one A block and at least one B block, the structure of the B block being selected for compatibility with the at least one segment of polyolefin, polyamide, polyester, polyether or silicone of the thermoplastic base polymer. Preferably, the B block of the liquid crystal block copolymer and the at least one segment of polyamide, polyester, polyether or silicone in the thermoplastic base polymer are both substantially entirely aliphatic moieties. Preferably, if the at least one segment of polyamide, polyester, or polyether in the thermoplastic base polymer is:

polyamide, then the B block the liquid crystal block copolymer is a polyamide segment,
polyester, then the B block is a polyester segment,
polyether, then the B block is a polyether segment.

Preferably, the B block of the liquid crystal block copolymer is formed of the same repeating units as said at least one segment of polyamide, polyester, or polyether in the thermoplastic base polymer.

Preferably, the thermoplastic base polymer is a member of the group consisting of polyolefins, polyesters, polyethers, polyamides, polyimides, block copolymers comprising at least one polyolefin, polyester, polyether, polyamide, and/or polyimide segment, silicones, and mixtures thereof.

The medical devices may be used in combination with stents.

Therefore, in accordance with one aspect of the present invention, there is provided a medical device, wherein at least a portion of said device is formed from a polymer composition comprising:

at least one liquid crystal block copolymer having at least one A block and at least one B block; and
at least one polymer that is compatible with the B block of said at least one liquid crystal block copolymer;

2b

wherein the A block comprises from 2 to about 50 mesogenic repeat units, and the B block is a soft block.

In accordance with another aspect of the present invention there is provided a medical device, wherein at least a portion of said device is formed from a polymer composition, the polymer composition comprising:

at least one liquid crystal block copolymer having at least one A block and at least one B block wherein the A block is formed of from 2 to about 50 mesogenic repeat units and the B block is a soft block; and

at least one polymer which is compatible with said B block of said liquid crystal block copolymer, wherein said B block is derived from repeating units selected from the group consisting of olefins, esters, ethers, amides and siloxanes, and said polymer is a poly(ether-block-amide).

In accordance with another aspect of the present invention there is provided a medical device formed of a polymer composition comprising a blend of a thermoplastic base polymer comprising:

at least one segment of polyolefin, polyamide, polyimide, polyester, polyether, or silicone;

wherein the polymer composition further comprises a liquid crystal block copolymer;

wherein the liquid crystal block copolymer comprises at least one A block and at least one B block;

wherein the A block is formed of from 2 to about 50 mesogenic repeat units and the B block is a soft block; and

wherein the structure of the B block is selected for compatibility with the at least one segment of polyolefin, polyamide, polyimide, polyester, polyether or silicone of said thermoplastic base polymer.

In accordance with another aspect of the present invention there is provided a liquid crystal block copolymer which is the reaction product of:

an A block which is a liquid crystal polymeric unit; and

a B block which is formed from repeating units of amide, ether, olefin or siloxane;

in combination with a non-liquid crystal polymer;

2c

wherein said A block comprises from 2 to about 50 mesogenic repeat units and said B block is a soft block selected for compatibility with the non-liquid crystal polymer.

In accordance with another aspect of the present invention there is provided a medical device, wherein at least a portion of said device is formed from a polymer composition comprising:

at least one liquid crystal block copolymer having at least one A block and at least one B block; and

at least one polymer that is compatible with the B block of said at least one liquid crystal block copolymer;

wherein the A block comprises from 2 to about 50 mesogenic repeat units and has a polymer backbone comprising no aliphatic unsaturation; and

wherein the B block is a soft block.

In accordance with another aspect of the present invention there is provided a medical device, wherein at least a portion of said device is formed from a polymer composition, the polymer composition comprising:

at least one liquid crystal block copolymer having at least one A block and at least one B block, wherein the A block comprises from 2 to about 50 mesogenic repeat units and the B block is a soft block formed from an amide repeat unit; and

at least one polyether-polyamide block copolymer that is compatible with the B block of said at least one liquid crystal block copolymer.

In accordance with another aspect of the present invention there is provided a catheter assembly, wherein at least a portion of the catheter assembly is formed from a polymer composition, the polymer composition comprising:

a liquid crystal block copolymer having an A block and a B block, wherein the A block comprises from 2 to about 50 mesogenic repeat units and the B block is a soft block derived from a repeating unit selected from the group consisting of olefins, esters, ethers, amides, and siloxanes; and

at least one polymer which is not a liquid crystal polymer, wherein the at least one polymer is selected so as to be compatible with the B block of the liquid crystal block copolymer.

In accordance with another aspect of the present invention there is provided an expandable medical balloon formed from at least one poly(ether-block-

2d

amide) block copolymer, and reinforced with a liquid crystal block copolymer having at least one A block and at least one B block;

wherein said A block comprises from 2 to about 50 mesogenic repeat units and said B block is a soft block; and

5 wherein said poly(ether-block-amide) block copolymer is compatible with said B block of said liquid crystal block copolymer.

In accordance with another aspect of the present invention there is provided a medical device, wherein at least a portion of said device is formed from a polymer composition comprising at least one liquid crystal block copolymer having at
10 least one A block and at least one B block and wherein

the A block comprises from 2 to about 50 mesogenic repeat units; and

the B block is a soft block; and

at least one polymer that is compatible with the B block of said liquid crystal block copolymer,

15 wherein at least one segment in said at least one polymer is selected from the group consisting of polyamides, polyesters, polyethers and mixtures thereof; and

if said at least one segment of polyamide, polyester, or polyether in the at least one polymer is:

20 polyamide, then the B block is a polyamide segment,

polyester, then the B block is a polyester segment,

polyether, then the B block is a polyether segment.

In accordance with another aspect of the present invention there is provided an expandable medical balloon, wherein the medical balloon is formed from a
25 polymer composition, the polymer composition comprising about 50% to about 95% by weight of at least one first polymer, about 5% to about 50% by weight of at least one liquid crystal block copolymer having at least one A block and at least one B block, and the at least one first polymer is compatible with the B block of said at least one liquid crystal block copolymer;

30 wherein the A block comprises from 2 to about 50 mesogenic repeat units and has a polymer backbone comprising no aliphatic unsaturation; and wherein the B block is a soft block.

In accordance with another aspect of the present invention there is provided a composition comprising:

2e

a liquid crystal block copolymer, the liquid crystal block copolymer comprising:

i. at least one A block, wherein the A block comprises from 2 to about 50 mesogenic repeat units; and

5 ii. at least one B block, wherein the B block is a soft block comprising nylon; and

at least one polymer selected from the group consisting of polyolefins, polyesters, polyethers, polyamides, polyimides, block copolymer comprising at least one polyolefin, polyester, polyether, polyamide or polyimide segment,
10 silicones and mixtures thereof;

wherein said at least one polymer is compatible with the B block of said liquid crystal block copolymer.

In accordance with another aspect of the present invention there is provided a medical device wherein at least a portion thereof comprises:

15 a liquid crystal block copolymer, the liquid crystal block copolymer comprising:

i. at least one A block, wherein the A block comprises from 2 to about 50 mesogenic repeat units; and

20 ii. at least one B block, wherein the B block is a soft block comprising nylon;

and at least one non-liquid crystal polymer;

wherein said at least one non-liquid crystal polymer is compatible with the B block of said liquid crystal block copolymer.

In accordance with another aspect of the present invention there is provided a medical device, wherein at least a portion of said device is formed from a polymer composition comprising:

at least one liquid crystal block copolymer comprising:

i. at least one A block, wherein the A block comprises from 2 to about 50 mesogenic repeat units; and

30 ii. at least one B block, wherein the B block is a soft block comprising at least one member selected from the group consisting of polyamides, polyesters, polyethers, polyimides, polyolefins and polysiloxanes; and

at least one polymer that is compatible with the B block of said at least one liquid crystal block copolymer.

In accordance with another aspect of the present invention there is provided a catheter assembly, wherein at least a portion of the catheter assembly is formed from a polymer composition, the polymer composition comprising:

a liquid crystal block copolymer having an A block and a B block, wherein the A block comprises from 2 to about 50 mesogenic repeat units and the B block is a soft block derived from repeat units selected from the group consisting of olefins, esters, ethers, amides, and siloxanes; and

at least one polymer which is not a liquid crystal polymer, the at least one polymer selected so as to be compatible with the B block of the liquid crystal block copolymer.

In accordance with another aspect of the present invention there is provided an expandable medical balloon formed from at least one poly(ether-block-amide) block copolymer, and reinforced with a liquid crystal block copolymer having at least one A block and at least one non-liquid crystal polymer B block;

wherein said A block comprises from 2 to about 50 mesogenic repeat units and said B block is a soft block; and

wherein said poly(ether-block-amide) block copolymer is compatible with said non-liquid crystal polymer B block.

These and other aspects, embodiments and advantages of the present invention will become immediately apparent to those of ordinary skill in the art upon review of the Detailed Description and Claims to follow.

DETAILED DESCRIPTION OF THE INVENTION

While this invention may be embodied in many different forms, there are described in detail herein specific embodiments of the invention. This description is an exemplification of the principles of the invention and is not intended to limit the

5 invention to the particular embodiments illustrated.

The present invention relates to polymer compositions useful in the formation of medical devices or at least a portion of a medical device. The polymer compositions include at least one liquid crystal block copolymer having at least one A block and at least one B block.

10 The A block is formed from mesogenic (liquid crystal) repeat units. As employed herein, the term "mesogenic" shall be used to refer to those repeat units (monomers) which impart liquid crystal properties to the polymer. The mesogenic repeat unit may include a mesogen, as well as any spacers such as methylene groups. Liquid crystal polymers have a third phase of matter which exists between a crystalline
15 (solid) and an isotropic (liquid) phase, that has properties between those of a conventional liquid, and those of a solid crystal. For instance, a liquid crystal (LC) may flow like a liquid, but have the molecules in the liquid arranged and oriented in a crystal-like way. It is the mesogen of the mesogenic repeat unit which induces the structural order, rigidity and necessary restriction on movement that allows the polymer to display
20 these liquid crystal properties. The mesogen is typically made up of one or more aromatic rings. Suitably, each mesogenic repeat unit has at least one aromatic group per each repeat unit, and more suitably each mesogenic repeat unit has at least two aromatic groups per each repeat unit.

The B block is the soft block of the liquid crystal block copolymer.
25 Suitably, the B block is aliphatic. Suitably, the B block has less than 10% aromaticity

by weight of the B block, more suitably the B block has less than 5% aromaticity by weight of the B block, and most suitably the B block has substantially no aromaticity.

The block copolymers may be of the general formula A-B diblock, (A-B)_n wherein n is 3 to 20, B-(A-B)_n-B wherein n is 3 to 20, A-B-A triblock, B-A-B triblock having soft segments at the free chain end, A-B-A-B-A pentablock, multiblock polymers such as A-B-C or A-C-B triblock, B-(A-B-C)_n-B wherein n is 3 to 20, random block copolymers, etc.

The above list is intended for illustrative purposes only, and not as a limitation on the scope of the present invention.

10 The A block, which may also be referred to herein as the mesogenic block, may include any suitable mesogenic repeat unit. Suitably, the mesogenic repeat unit has at least one aromatic group per unit, and more suitably the mesogenic repeat unit has at least two aromatic groups per unit. The A block of the liquid crystal block copolymer is characterized by mesogenic repeat units which can provide the liquid
15 crystal block copolymer with stiffness resulting from restriction on rotation caused by steric hindrance and resonance. For example, aromatic ring(s) can provide both steric hindrance and resonance. Some mesogenic repeat units may include both aromatic and aliphatic rings.

The A block may contain any number of repeating units up to about 50.

20 Suitably, the mesogenic block has an axial ratio, defined by the length of the molecule divided by the diameter ($x = L/d$), of at least three. This axial ratio provides the mesogenic block with rod-like characteristics.

A variety of suitable mesogenic repeat units find utility in the formation of the A block of the liquid crystal block copolymer.

25 Classes of aromatic structural groups useful in the formation of each mesogenic repeat unit include, but are not limited to, aromatic dicarboxylic acids, aromatic hydroxycarboxylic acids, aromatic aminocarboxylic acids, diphenols, and aminophenols, for example.

Examples of useful aromatic dicarboxylic acids include, but are not
30 limited to, 1,4-naphthalenedicarboxylic acid, 1,5-naphthalenedicarboxylic acid, 2,6-naphthalenedicarboxylic acid, biphenyl-4,4'-dicarboxylic acid, biphenyl-3,3'-dicarboxylic acid, diphenoxyethane-4,4'-dicarboxylic acid, diphenyl ether-4,4'-dicarboxylic acid, methylterephthalic acid, methoxyterephthalic acid, chloroterephthalic acid, 4-chloronaphthalene-2,7-dicarboxylic acid, 1,3-naphthalenedicarboxylic acid, 1,6-

naphthalenedicarboxylic acid, 1,7-naphthalenedicarboxylic acid, 2,7-naphthalenedicarboxylic acid, biphenyl-3,4'-dicarboxylic acid, diphenyl ether-3,4'-dicarboxylic acid, 4-methylisophthalic acid, 5-methylisophthalic acid, diphenyl ether-4,4'-dichloro-3,3'-dicarboxylic acid and iso- and terephthalic acid.

5 Examples of useful aromatic hydroxycarboxylic acids include, but are not limited to, 4-hydroxy-3-methylbenzoic acid, 4-hydroxy-3-phenyl-benzoic acid, 4-hydroxy-2-ethylbenzoic acid, 3-chloro-4-hydroxy-benzoic acid, 4-hydroxy-3-methoxybenzoic acid, hydroxyl benzoic acid including 4-hydroxybenzoic acid and 3-hydroxybenzoic acid, hydroxynaphthoic acid including 6-hydroxy-2-naphthoic acid, etc.

10 Examples of useful diphenols include, but are not limited to, hydroquinone, t-butylhydroquinone, bromohydroquinone, chlorohydroquinone, methylhydroquinone, ethylhydroquinone, phenylhydroquinone, 4,4'-dihydroxydiphenyl, 4,4'-dihydroxydiphenyl ether, 4,4'-dihydroxydiphenylethane, 4,4'-dihydroxydiphenoxyethane, 3,5'-dihydroxydiphenyl, 4-hydroxy-4'-carboxydiphenyl, 15 3,5'-dihydroxydiphenyl ether, naphthalene, dihydroxynaphthalene including 1,4-, 1,5- and 2,6-dihydroxynaphthalene, for example, 4-methoxy-2,6-dihydroxynaphthalene, 1,3-dihydroxynaphthalene, 1,6-dihydroxynaphthalene, 1,7-dihydroxynaphthalene, 2,7-dihydroxynaphthalene, 2,5-dichloro-1,6-dihydroxynaphthalene, 4-methoxy-2,7-dihydroxynaphthalene, 2,2'-dimethyl-4,4'-dihydroxydiphenyl, 3,3',5,5'-tetramethyl-4,4'-dihydroxydiphenyl, 3,5'-dimethoxy-4,4'-dihydroxydiphenyl ether, 1,2-(2-chloro-4- 20 hydroxyphenoxy)-ethane resorcinol, 3,4'-dihydroxydiphenyl, 3,4'-dihydroxydiphenyl ether, 3,4'-dihydroxydiphenoxyethane, 4-chlororesorcinol, 4-bromoresorcinol, 4-methylresorcinol, 4-phenylresorcinol, 4-ethoxyresorcinol, etc.


 Examples of aromatic aminocarboxylic acids include, but are not limited 25 to, 2-aminobenzoic acid, 3-aminobenzoic acid, 4-aminobenzoic acid, 4-chloroanthranilic acid, 5-chloroanthranilic acid, 3-amino-4-chlorobenzoic acid, 4-amino-3-phenyl-benzoic acid, 4-amino-3-methoxybenzoic acid, 4-amino-3-phenoxybenzoic acid, 6-amino-5-chloro-2-naphthoic acid, 6-amino-5-methyl-2-naphthoic acid and 6-amino-5-methoxy-2-naphthoic acid, etc.

30 Examples of aminophenols include, but are not limited to, 3-aminophenol, 5-amino-2-chlorophenol, 4-aminophenol, 3-amino-2-methylphenol, 3-amino-4-methylphenol, 5-amino-1-naphthol, 6-amino-1-naphthol, 8-amino-2-naphthol, 6-amino-2-naphthol and 4-amino-1-hydroxy-biphenyl, etc.

Other groups which may be included in the mesogenic repeat unit include paraphenylene (—Ar—) wherein Ar represents an aromatic ring, as well as substituted paraphenylenes such as para-diacetoxyphenylene ($\text{—CH}_2\text{COOCH}_2\text{—Ar—CH}_2\text{COOCH}_2\text{—}$).

Any combination of such groups may also be incorporated into the repeat unit in the LC block of the LC block copolymer. For a discussion of these structural groups, see for example, U.S. Patent Nos. 4663422, 5017304, and 5030703 for a discussion of such structural units. See also U.S. Patent Nos. 4238599, 4801677, and 5173562, for further examples of suitable mesogenic units.

Other suitable mesogenic repeat units include those of the following general formula:



wherein X can be $(\text{CH}_2)_n$ wherein n is an integer from about 2 to about 10, m can range from about 2 to about 50, Y and Z can each independently be —COO— or —CONH— or can be a single bond between two carbon atoms, and A can be p-phenylene, 1,4-naphthylene, 2,6-naphthylene or 1,5-naphthylene, monosubstituted phenylene with methyl, chloro or phenyl substitution, —ArCH=CHAr— wherein Ar is a phenyl ring, —Ar—COOAr— , —Ar—CONHAr— , or $\text{—Ar—OOC—Ar—COO—Ar—}$, etc. For a discussion of such mesogenic repeat units, see U.S. Patent No. 4,952,334.

Another specific example of a suitable aromatic mesogenic repeat unit has the structure $\text{—Ar—CO—NH—Ar—NH—CO—Ar—}$.

Other suitable mesogenic repeat units which can be employed herein are described by Ober et al. in Polymer Journal, Vol. 14, No. 1, pp. 9-17 (1972) and have the following structure:



wherein Ar represents phenyl with para-bond sites, n may range from about 2 to about 10, and x can range from about 2 to about 50. These mesogenic units can be

characterized as aromatic ester mesogenic units comprising three linearly-aligned aromatic rings.

The type of mesogenic repeat unit represented by the formula above, wherein Ar represents phenyl with para-bond sites, n is an integer of from about 2 to about 10, and x is an integer of from about 5 to about 15, is described in U.S. Patent No. 5,508,338.


Other specific examples of suitable mesogenic repeat units include poly(hydroxynaphthoic acid) (—O—ArAr—CO— , wherein ArAr is two fused benzene rings) and poly(p-phenyleneterephthalate) (—O—Ar—OOC—Ar—CO—).

Another specific example of a suitable LC block employs a combination of hydroxybenzoic and hydroxynaphthoic acid and has repeating units of the formula $\text{—[O—AR—CO—]}_x\text{—[O—ArAr—CO—]}_y\text{—}$ wherein x and y are positive numbers of 1 or more, for instance, x and y may vary independently from about 1 to about 50, and suitably about 1 to about 25. In some embodiments $x = y = 1$ and in other embodiments $x \neq y$. See, for example, U.S. Patent Nos. 6552127, 6054537, 5869574, 5767198 and 5750626.

Another example of a mesogenic unit formed using a combination includes that shown in U.S. Patent No. 4912193, employing a combination of p-hydroxy benzoic acid, 4,4'-dihydroxy diphenyl, terephthalic acid, and isophthalic acid.

The mesogenic repeat unit of the present application may be said to include both a mesogenic portion and a spacer. The mesogenic repeat units of the A block can be attached together in such a way that the mesogen portion of the mesogenic repeat unit forms a part of the backbone (main chain liquid crystal polymer structure), or they may be attached together in such a way that the mesogen is attached to the polymer backbone as a pendant group (side chain liquid polymer structure). Examples of mesogenic repeat units employed in main chain liquid crystal polymers wherein the mesogen portion of the mesogenic repeat unit forms a part of the backbone is hydroxynaphthoic acid, and poly(p-phenyleneterephthalate).

An example of a mesogenic repeat unit resulting in a side chain liquid crystal polymer structure has the following structure:



The A block or LC block of the liquid crystal block copolymer may be made using any method known in the art. Most are made using conventional
 5 condensation reactions. See for example Chen, Bor-Kuan, et al., "Synthesis and properties of liquid crystalline polymers with low T_m and broad mesophase temperature ranges," *Polymer*, 46 (2005) 8624-8633, Hurdoc, Nicolae, et al., "Thermal behaviour and molecular modeling of some aromatic polyethers containing a hexamethylenic spacer," *Polymer Degradation and Stability*, 72 (2001) 441-445, Liu, Yingliang, et al.,
 10 "Synthesis and characterization of liquid crystalline copolyesters containing horizontal and lateral rods in main chain (II)," *Reactive & Functional Polymers*, 64 (2005) 35-46, Makaruk, Leszek, et al., "Mesophase transitions in liquid crystal polymers", *Reactive & Functional Polymers*, 33 (1997) 225-231, Gopalan, Padma, et al., "Rod-Coil Block Copolymers: An Iterative Synthetic Approach via Living Free-Radical Procedures,"
 15 *Journal of Polymer Science: Part A: Polymer Chemistry*, Vol. 41, (2003) 3640-3656, Hakemi, H., "On the miscibility of liquid crystalline polymers," *Polymer*, 41 (2000) 6145-6150.

Whereas it is the A block of the liquid crystal block copolymer which provides the block copolymer with strength, stiffness and rigidity, the B block of the
 20 liquid crystal block copolymer is the soft segment of the block copolymer and provides the polymer with flexibility. Suitably, the B block is aliphatic. Suitably, the B block has less than 10% aromaticity by weight of the B block, more suitably less than 5% by weight of the B block, and most suitably, the B block has substantially no aromaticity. Suitably, the B block is derived from repeating units of olefins, esters, ethers, amides,
 25 and siloxanes, for example.

Examples of suitable repeating units for formation of the B block include, but are not limited to, amides, esters, ethers, imides, olefins and siloxanes.


In some embodiments, the B block is formed from hydrophilic monomer units. Examples of suitably hydrophilic monomers include, but are not limited to, short
 30 chain aliphatic ethers such as polyethylene oxide glycol or polytetramethylene oxide glycol which are the chain ends of hydrophilic macromolecules, diols or dicarboxylic

acids containing a metal sulfonate group, oligomers such as polyalkylene glycol copolymerized with other monomers such as aliphatic dicarboxylic acids, hydrophilic acrylates available from Sartomer such as polyethylene glycol diacrylate, acrylamides and N,N-dimethylacrylamide, N-vinylpyrrolidone, etc.


5 The above lists are intended for illustrative purposes only, and not as a limitation on the scope of the present invention.

The A block may have anywhere from about 2 to about 50 repeating units, and more suitably about 2 to about 25 repeating units, and the B block may have anywhere from about 2 to about 25 repeating units, and suitably about 2 to about 10 repeating units.

In embodiments wherein the block copolymer further has a C block, the mesogenic units of the C block may be selected from those mesogenic repeat units discussed as useful in forming the A block. However, in a liquid crystal polymer having both an A block and a C block, the C block is formed from different mesogenic repeat units than those of the A block. For example, in one embodiment, the A block of the liquid crystal block copolymer is a polyamide segment formed using and the C block is a polyester segment formed using aromatic hydroxycarboxylic acids, for example. Examples of suitable mesogenic units for formation of the polyamide A block structure include, for example,



This portion of the liquid crystal block copolymer can be made by the condensation reaction between $\text{HOOC}-\text{AR}-\text{COOH}$ (benzene-1,4-dicarboxylic acid) and $\text{H}_2\text{N}-\text{AR}-\text{NH}_2$ (1,4-diaminobenzene) to form the following structure:




In this embodiment, suitable B blocks may be formed by condensation of hexanedioic acid and hexamethylenediamine (nylon 6,6), ring opening polymerization of


caprolactam (nylon 6) or ring opening polymerization of laurolactam (nylon 12), for example.

Nylon 6 (polycaprolactam) is not a condensation polymer, but rather is formed by the ring opening polymerization of caprolactam monomers.

5



caprolactam




nylon 6

10

Nylon 6,6, on the other hand, is formed by condensation between hexandioic acid (adipic acid) and 1,6-diaminohexane (hexamethylenediamine):
repeating unit:

15



Hexanedioyl dichloride may be used in place of hexanedioic acid.

The liquid crystal polyester A block, the nylon B block and the liquid
crystal polyamide C block can be connected via conventional condensation reactions.

The C block may also have anywhere from about 2 to about 50 repeating units, and more suitably anywhere from about 2 to about 25 repeating units.

The above lists are intended for illustrative purposes only, and not as a limitation on the scope of the present invention.

25

Suitably, the A block is from about 50% to about 95% by weight of the block copolymer and the B block is about 5% to about 50% by weight of the block copolymer, more suitably, the B block is about 10% to about 30% by weight of the

block copolymer. In some embodiments, the B block or soft segment is about 10% or less by weight of the LC block copolymer.

Any suitable method of polymerization may be employed depending on the monomers, oligomers, or polymers which are employed. Most commonly, the polymerization can be accomplished via condensation reactions which are achieved through reacting molecules incorporating alcohol, amine or carboxylic acid (or other derivative) functional groups. An ether, amide, or ester linkage is formed and a small molecule, commonly water, is released. Thus, only a part of the monomer becomes part of the polymer.

Addition polymerization, wherein the entire monomer becomes part of the polymer, may also be employed. For example, anionic polymerization can be used to prepare block copolymers. In such a process, a reactive site remains at the end of the chain until it is quenched. The unquenched polymer may be referred to as a living polymer, and the addition of a second monomer can result in a block polymer. These processes may be employed where reactive unsaturated sites, i.e. double or triple bonds, are present. Most addition polymerizations are also chain growth polymerizations wherein one monomer is added at a time, although there are exceptions.

Example

In a specific example 4-hydroxy-2-benzoic acid (HBA) may be acetylated to 4-acetoxybenzoic acid (ABA) with acetic anhydride as the solvent in the presence of a catalytic amount of sodium acetate in the manner of Chen et al, "Synthesis and properties of liquid crystalline polymers with low T_m and broad mesophase temperature ranges," *Polymer*, 46 (2005) 8624-8633. Still following the method of Chen et al, ABA then may be reacted with 1,4-butanediol (BDO) in a molar ratio of about 1:3 and Sb_2O_3 catalyst in an amount of about 300 ppm to produce the ester ABA-BDO-ABA.

Polymerization is then accomplished by adding a mixture of the ester ABA-TMG-ABA, terephthalic acid (TPA), a nylon 6 polymer terminated on both ends with acid groups (Ny6) and 250-300 ppm of Sb_2O_3 or $\text{Ti}(\text{OBu})_4$ catalysts to a flask with a nitrogen purge using a molar ratio of the ester to TPA to Ny6 dicarboxylic acid of 1.0:0.67:0.33. The nitrogen outlet is equipped with a distillation column with vacuum. The mixture is heated at melt for about 5 hours at a temperature of about 200 °C to about 250°C, depending on the temperature necessary to melt the mixture. Thermal stabilizers and antioxidants such as Irganox® 1010 available from Ciba-Geigy are used added to

inhibit decomposition. The mixture is stirred, for instance at 200 rpm once the melt temperature has been reached. The nitrogen flow is regulated to prevent evaporation of reactants. After about 3-5 hours the temperature is gradually increased to about 280° C and the acetic acid produced by condensation is removed by distillation. When no more
5 distillate is observed a vacuum of about 10 torr is applied for 2-3 hours and then the vacuum is reduced to 1-2 torr and the mixture stirred continuously for an additional 4 hrs, all the while maintaining the temperature at about 280°C. The product is then allowed to cool. Monomers and oligomers may be removed by Soxhlet extraction using acetone.

10 The resultant polymer is an A-B-A block copolymer having a structure of $[(ABA-BDO-ABA-TPA)_x ABA-BDO-ABA]-Ny6-[ABA-BDO-ABA-(TPA-ABA-BDO-ABA)_y]$.

In modifications of the above equivalent amounts of ethylene glycol or 1,3 propane diol may be substituted for 1,4-butanediol, 6-hydroxy-2-naphthoic acid may
15 be substituted for 4-hydroxy benzoic acid, 2,6-naphthalene dicarboxylic acid may be substituted for TPA, and/or other diacid terminated nylon polymers such as nylon 6,10 or nylon 9,12, may be substituted for the nylon 6 polymer. An A-B diblock copolymer may be synthesized in a similar manner using a mono-acid terminated nylon polymer such as nylon 12, in place of the nylon 6 diacid. Furthermore the relative ratio of short
20 diacid to acid terminated nylon can be varied over a very wide range for instance from about 1:10 to about 1:10 on an acid equivalents basis.

The liquid crystal block copolymer of the invention may itself be employed in the formation of medical devices or components thereof, or, the liquid crystal block copolymer may be blended with another polymer or polymers. In the latter
25 case, suitably, the polymer and the B block may be selected so as to be compatible with one another. Compatibility, as used herein, refers to compatibility on both the macroscopic and microscopic, i.e. molecular, scale. Thus, compatibility on a macroscopic scale, may refer to those polymer blends which do not exhibit gross phase separation.

30 In polymer mixtures, the matrix polymer may interact strongly with the LC block copolymer or one block of the LC block copolymer, thus providing desirable polymer properties.

In mixtures wherein the LC block copolymer is blended with other polymers, at least one other polymer of the blend, may be selected from those polymers

which are non-liquid crystal polymers. Examples of suitable polymers which may be used for blending with the LC block copolymer described herein include, but are not limited to, polyesters and copolyesters, polyamides, polyethers, polyimides, polyolefins and silicones, for example. These polymers are intended for illustrative purposes only,
5 and not as a limitation on the scope of the present invention.

Specific examples of suitable polymers which may be employed in a blend include polyamide elastomers such as those sold under the tradename of PEBAX® available from Arkema, headquarters in Paris, France, and polyester elastomers such as those sold under the name of HYTREL® available from DuPont in Dover, DE are also
10 suitable for use.

For example, if the liquid crystal block copolymer is blended with a poly(ether-block-amide) copolymer having an (AB)_n block copolymer structure wherein the A block is nylon and the B block is polytetramethylene oxide, a suitable LC block copolymer B block may include amide repeat units or a polytetramethylene oxide
15 structure. The block may suitably be less than about 50% by weight of the LC block copolymer, more suitably about 30% by weight or less of the LC block copolymer and most suitably about 10% by weight or less of the LC block copolymer.

The tensile strength of a typical poly(ether-block-amide) thermoplastic elastomer of the type described above has tensile strength of about 10,000 psi and DSC
20 melting point of about 174°C.

Suitably, the LC block copolymer, to act as a reinforcing material in such a polymer blend, has a tensile strength of greater than about 10,000 psi, for example, greater than about 12,000 psi, more suitably greater than about 20,000 psi and most suitably greater than about 30,000 psi.

25 Thus, it is desirable to select the LC block copolymer structure so that it has a strong interaction with the thermoplastic elastomer to achieve mechanical strength enhancement through effective load/force transferring.

It is also desirable that the LC block copolymer have a melting point within a thermoplastic processing window of less than the thermal degradation
30 temperature of the thermoplastic elastomer. In the case where the thermoplastic elastomer is poly(ether-block-amide), for example, the melting point range is suitably less than about 240°C. Extrusion/coextrusion is an example of a suitable method to process such thermoplastic materials.

The above example is intended for illustrative purposes only, and not as a limitation on the scope of the invention. Other polymers are known to those of skill in the art and may also be employed herein.

If a blend of polymers is employed, the amount of LC block copolymer is suitably about 75% or less and more suitably about 50% or less. The amount of LC block copolymer employed may be from about 5% to about 75% and more suitably about 5% to about 50% and even more suitably about 10% to about 30%.

The at least one second polymer or blend of polymers may be employed from about 25% to about 95%, more suitably about 50% to about 95% and even more suitably about 70% to about 90%.

The present compositions may be employed in the manufacture of any medical device or component thereof which is suitably formed from polymer compositions. Examples include catheter assemblies used in diagnosing and treating diseases such as vascular diseases.

The present invention finds utility in the manufacture of expandable medical balloons, particularly those employed in the cardiovascular system wherein the balloon size is very small.

Balloon formation is known in the art. In some processes, a tube of polymer material is extruded and then expanded radially and axially. Balloon formation is described in U.S. Patent No. 4490421 and in commonly assigned U.S. Patent Nos. 6024722. Of course, other processes are known and may be employed in the present invention.

While reference has been made to various preferred embodiments of the invention other variations, implementations, modifications, alterations and embodiments are comprehended by the broad scope of the appended claims. Some of these have been discussed in detail in this specification and others will be apparent to those skilled in the art. Those of ordinary skill in the art having access to the teachings herein will recognize these additional variations, implementations, modifications, alterations and embodiments, all of which are within the scope of the present invention, which invention is limited only by the appended claims."

**THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE
PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:**

1. A medical device, wherein at least a portion of said device is formed from a
5 polymer composition comprising:
at least one liquid crystal block copolymer having at least one A block and at
least one B block; and
at least one polymer that is compatible with the B block of said at least one liquid
crystal block copolymer;
10 wherein the A block comprises from 2 to about 50 mesogenic repeat units, and
the B block is a soft block.
2. The medical device of claim 1, wherein the liquid crystal block copolymer has a
structure selected from the group consisting of A-B diblock, $(A-B)_n$ wherein n is 3 to 20,
15 A-B-A triblock, B-A-B triblock, B- $(A-B)_n$ -B wherein n is 3 to 20, A-B-A-B-A
pentablock, random block, and multiblock polymers.
3. The medical device of claim 1, wherein the liquid crystal block copolymer
further includes a C block, wherein the C block comprises from 2 to about 50 mesogenic
20 repeat units, and wherein the mesogenic repeat units are different than those of the A
block.
4. The medical device of claim 3, wherein the liquid crystal block copolymer has a
structure selected from the group consisting of B- $(A-B-C)_n$ -B wherein n is 3 to 20, A-B-
25 C triblock, A-C-B triblock, and B- $(A-B-C)_n$ -B wherein n is 3 to 20.
5. The medical device of claim 1, wherein said A block comprises at least one
aromatic group per repeat unit of said A block.
- 30 6. The medical device of claim 1, wherein said A block comprises at least two
aromatic groups per repeat unit of said A block.
7. The medical device of claim 1, wherein said B block is aliphatic.

8. The medical device of claim 1, wherein said B block is derived from a repeating unit selected from the group consisting of olefins, esters, ethers, amides and siloxanes.

9. The medical device of claim 1, wherein said B block is hydrophilic.

5

10. The medical device of claim 1, wherein said A block comprises about 2 to about 25 repeat units and said B block comprises about 2 to about 25 repeat units.

11. The medical device of claim 10, wherein said B block comprises about 2 to about 10 repeat units.

12. The medical device of claim 1, wherein said at least one polymer is selected from the group consisting of polyamides, polyesters, polyethers, polyolefins, polyimides, block copolymers comprising at least one polyolefin, polyester, polyether, polyamide, and/or polyimide segment, and silicones.

15

13. The medical device of claim 1, wherein the B block is formed from an amide repeat unit and said at least one polymer is a polyether-polyamide block copolymer.

14. The medical device of claim 1, wherein said liquid crystal block copolymer comprises about 50% to about 95% by weight of said A block and about 5% to about 50% by weight of said B block.

20

15. The medical device of claim 1, wherein said medical device is a catheter assembly comprising at least one shaft or shaft assembly, and said at least a portion of said medical device formed from said polymer composition is said at least one shaft or shaft assembly.

25

16. The medical device of claim 1, wherein the medical device is an inflatable medical balloon.

30

17. The medical device of claim 16, wherein said balloon is mounted on a catheter.

18. The medical device of claim 16, further in combination with a stent.

19. A medical device, wherein at least a portion of said device is formed from a polymer composition, the polymer composition comprising:

at least one liquid crystal block copolymer having at least one A block and at least one B block wherein the A block is formed of from 2 to about 50 mesogenic repeat units and the B block is a soft block; and

at least one polymer which is compatible with said B block of said liquid crystal block copolymer, wherein said B block is derived from repeating units selected from the group consisting of olefins, esters, ethers, amides and siloxanes, and said polymer is a poly(ether-block-amide).

20. The medical device of claim 19, wherein the liquid crystal block copolymer has a structure selected from the group consisting of A-B diblock, $(A-B)_n$ wherein n is 3 to 20, A-B-A triblock, B-A-B triblock, $B-(A-B)_n-B$ wherein n is 3 to 20, A-B-A-B-A pentablock, random block, and multiblock polymers.

21. The medical device of claim 19, wherein the liquid crystal block copolymer further includes a C block, wherein the C block comprises from 2 to about 50 mesogenic repeat units, and wherein the mesogenic repeat units are different than those of the A block.

22. The medical device of claim 21, wherein the liquid crystal block copolymer has a structure selected from the group consisting of $B-(A-B-C)_n-B$ wherein n is 3 to 20, A-B-C triblock, A-C-B triblock, and $B-(A-B-C)_n-B$ wherein n is 3 to 20.

23. The medical device of claim 19, wherein said A block of said liquid crystal block copolymer is formed of mesogenic repeat units comprising at least one aromatic group per unit.

24. The medical device of claim 19, wherein said A block of said liquid crystal block copolymer is formed of mesogenic repeat units comprising at least two aromatic groups per unit.

25. The medical device of claim 19, wherein said B block is aliphatic.

26. The medical device of claim 19, wherein said B block is derived from said amide repeating units.

5 27. The medical device of claim 19, wherein said device is a catheter assembly.

28. The medical device of claim 27, wherein said at least a portion of said medical device is a balloon mounted on said catheter assembly.

10 29. A medical device formed of a polymer composition comprising a blend of a thermoplastic base polymer comprising:
at least one segment of polyolefin, polyamide, polyimide, polyester, polyether, or silicone;
wherein the polymer composition further comprises a liquid crystal block
15 copolymer;
wherein the liquid crystal block copolymer comprises at least one A block and at least one B block;
wherein the A block is formed of from 2 to about 50 mesogenic repeat units and the B block is a soft block; and
20 wherein the structure of the B block is selected for compatibility with the at least one segment of polyolefin, polyamide, polyimide, polyester, polyether or silicone of said thermoplastic base polymer.

30. The medical device as in claim 29, wherein the B block of the liquid crystal
25 block copolymer and the at least one segment of polyamide, polyester, polyether or silicone in the thermoplastic base polymer are both substantially entirely aliphatic moieties.

31. The medical device as in claim 29, wherein, if said at least one segment of
30 polyamide, polyester, or polyether in the thermoplastic base polymer is:
polyamide, then the B block the liquid crystal block copolymer is a polyamide segment,
polyester, then the B block is a polyester segment,
polyether, then the B block is a polyether segment.

32. The medical device as in claim 29, wherein the B block of the liquid crystal block copolymer is formed of the same repeating units as said at least one segment of polyamide, polyester, or polyether in the thermoplastic base polymer.

5

33. The medical device as in claim 29, wherein the thermoplastic base polymer is a member of the group consisting of polyolefins, polyesters, polyethers, polyamides, polyimides, block copolymers comprising at least one polyolefin, polyester, polyether, polyamide, and/or polyimide segment, silicones, and mixtures thereof.

10

34. A liquid crystal block copolymer which is the reaction product of:
an A block which is a liquid crystal polymeric unit; and
a B block which is formed from repeating units of amide, ether, olefin or siloxane;

15

in combination with a non-liquid crystal polymer;
wherein said A block comprises from 2 to about 50 mesogenic repeat units and said B block is a soft block selected for compatibility with the non-liquid crystal polymer.

20

35. A medical device, wherein at least a portion of said device is formed from a polymer composition comprising:
at least one liquid crystal block copolymer having at least one A block and at least one B block; and
at least one polymer that is compatible with the B block of said at least one liquid crystal block copolymer;
wherein the A block comprises from 2 to about 50 mesogenic repeat units and has a polymer backbone comprising no aliphatic unsaturation; and
wherein the B block is a soft block.

25

30

36. The medical device as in claim 35, wherein said B block is aliphatic.

37. A medical device, wherein at least a portion of said device is formed from a polymer composition, the polymer composition comprising:

at least one liquid crystal block copolymer having at least one A block and at least one B block, wherein the A block comprises from 2 to about 50 mesogenic repeat units and the B block is a soft block formed from an amide repeat unit; and

at least one polyether-polyamide block copolymer that is compatible with the B
5 block of said at least one liquid crystal block copolymer.

38. The medical device of claim 37, further comprising a thermoplastic base polymer, wherein said thermoplastic base polymer is aliphatic.

10 39. A catheter assembly, wherein at least a portion of the catheter assembly is formed from a polymer composition, the polymer composition comprising:

a liquid crystal block copolymer having an A block and a B block, wherein the A block comprises from 2 to about 50 mesogenic repeat units and the B block is a soft block derived from a repeating unit selected from the group consisting of olefins, esters,
15 ethers, amides, and siloxanes; and

at least one polymer which is not a liquid crystal polymer, wherein the at least one polymer is selected so as to be compatible with the B block of the liquid crystal block copolymer.

20 40. The catheter assembly of claim 39, wherein the B block is derived from amide repeating units.

41. The catheter assembly of claim 39, the catheter assembly further comprising an expandable balloon member, wherein said at least portion of the catheter assembly is the
25 expandable balloon member.

42. An expandable medical balloon formed from at least one poly(ether-block-amide) block copolymer, and reinforced with a liquid crystal block copolymer having at least one A block and at least one B block;

30 wherein said A block comprises from 2 to about 50 mesogenic repeat units and said B block is a soft block; and

wherein said poly(ether-block-amide) block copolymer is compatible with said B block of said liquid crystal block copolymer.

43. A medical device, wherein at least a portion of said device is formed from a polymer composition comprising at least one liquid crystal block copolymer having at least one A block and at least one B block and wherein

the A block comprises from 2 to about 50 mesogenic repeat units; and

5 the B block is a soft block; and

at least one polymer that is compatible with the B block of said liquid crystal block copolymer,

wherein at least one segment in said at least one polymer is selected from the group consisting of polyamides, polyesters, polyethers and mixtures thereof; and

10 if said at least one segment of polyamide, polyester, or polyether in the at least one polymer is:

polyamide, then the B block is a polyamide segment,

polyester, then the B block is a polyester segment,

polyether, then the B block is a polyether segment.

15

44. An expandable medical balloon, wherein the medical balloon is formed from a polymer composition, the polymer composition comprising about 50% to about 95% by weight of at least one first polymer, about 5% to about 50% by weight of at least one liquid crystal block copolymer having at least one A block and at least one B block, and
20 the at least one first polymer is compatible with the B block of said at least one liquid crystal block copolymer;

wherein the A block comprises from 2 to about 50 mesogenic repeat units and has a polymer backbone comprising no aliphatic unsaturation; and

wherein the B block is a soft block.

25

45. The expandable medical balloon of claim 44, said polymer composition comprising about 70% to about 95% by weight of said at least one first polymer and about 5% to about 30% by weight of said at least one liquid crystal block copolymer.

30 46. The expandable medical balloon of claim 44, wherein said at least one first polymer is selected from the group consisting of polyolefins, polyesters, polyethers, polyamides, polyimides, block copolymers comprising at least one polyolefin, polyester, polyether, polyamide, and/or polyimide segment, silicones, and mixtures thereof.

47. The expandable medical balloon of claim 44, said at least one first polymer is a thermoplastic elastomer.

48. The expandable medical balloon of claim 44, said at least one first polymer is a
5 poly(ether-block-amide).

49. The expandable medical balloon of claim 44, wherein the B block of said liquid crystal polymer is aliphatic.

10 50. The expandable medical balloon of claim 44, wherein said B block is derived from a repeating unit selected from the group consisting of olefins, esters, ethers, amides and siloxanes.

15 51. The expandable medical balloon of claim 48, wherein said poly(ether-block-amide) has an $(AB)_n$ block copolymer structure wherein n is 3 to 20, wherein the at least one A block of said at least one liquid crystal block copolymer is nylon, and wherein the at least one B block of said at least one liquid crystal block copolymer is polytetramethylene oxide.

20 52. The expandable medical balloon of claim 51, wherein said B block of said liquid crystal block copolymer comprises amide repeat units or a polytetramethylene oxide structure.

25 53. The expandable medical balloon of claim 52, wherein said B block is 50% or less by weight of said liquid crystal block copolymer.

54. The expandable medical balloon of claim 52, wherein said B block is 30% or less by weight of said liquid crystal block copolymer.

30 55. The expandable medical balloon of claim 52, wherein said B block is 10% or less by weight of said liquid crystal block copolymer.

56. The expandable medical balloon of claim 44, wherein said A block of said liquid crystal polymer comprises at least one aromatic group per repeat unit of said A block.

57. The expandable medical balloon of claim 44, wherein said A block of said liquid crystal polymer comprises at least two aromatic groups per repeat unit of said A block.

5 58. The expandable medical balloon of claim 44, wherein said B block of said liquid crystal polymer is derived from hydrophilic monomer units.

59. The expandable medical balloon of claim 58, wherein said B block of said liquid crystal polymer is derived from at least one hydrophilic monomer unit which is selected
10 from the group consisting of short chain aliphatic ethers, diols, dicarboxylic acids containing a metal sulfonate group, and acrylamides.

60. The expandable medical balloon of claim 59, wherein said at least one hydrophilic monomer unit is selected from the group consisting of ethylene oxide,
15 tetramethylene oxide, N,N-dimethylacrylamide and N-vinylpyrrolidone.

61. The expandable medical balloon of claim 58, wherein said B block of said liquid crystal polymer is derived from at least one member selected from the group consisting of polyalkylene glycol copolymerized with an aliphatic dicarboxylic acid and
20 polyalkylene glycol copolymerized a hydrophilic acrylate.

62. The expandable medical balloon of claim 44, wherein said liquid crystal block copolymer further comprises a C block comprising from 2 to about 50 mesogenic repeat units, wherein the C block is derived from different mesogenic repeat units than those of
25 the A block.

63. A composition comprising:

a liquid crystal block copolymer, the liquid crystal block copolymer comprising:

- 30 i. at least one A block, wherein the A block comprises from 2 to about 50 mesogenic repeat units; and
ii. at least one B block, wherein the B block is a soft block comprising nylon; and

at least one polymer selected from the group consisting of polyolefins, polyesters, polyethers, polyamides, polyimides, block copolymer comprising at least one

polyolefin, polyester, polyether, polyamide or polyimide segment, silicones and mixtures thereof;

wherein said at least one polymer is compatible with the B block of said liquid crystal block copolymer.

5

64. The composition of claim 63, wherein the B block comprises a polymeric segment selected from the group consisting of nylon 6,6, nylon 6 and nylon 12.


65. The composition of claim 63, wherein the A block comprises repeat units derived from 4-acetoxybenzoic acid and 1,4-butanediol.

10

66. The composition of claim 63, having the general structure $[(\text{ABA-BDO-ABA-TPA})_x\text{ABA-BDO-ABA}]\text{-Ny6-}[\text{ABA-BDO-ABA-(TPA-ABA-BDO-ABA)}_y]$, wherein ABA represents 4-acetoxybenzoic acid, BDO represents 1,4-butanediol, TPA represents terephthalic acid, Ny6 represents nylon 6, and x and y represent integers.

15

67. The composition of claim 63, wherein the A block comprises mesogenic repeat units having the following general structure:



20

wherein n is from 2 to 50.

68. The composition of claim 63, wherein said B block comprises 0% to about 10% aromaticity.

25

69. The composition of claim 63, wherein said A block comprises at least one member selected from the group consisting of aromatic dicarboxylic acids, aromatic hydroxycarboxylic acids, aromatic amino carboxylic acids, diphenols and aminophenols.

70. The composition of claim 63, wherein said A block comprises at least one aromatic group per repeat unit of said A block.

30

71. The composition of claim 63, wherein said A block comprises two aromatic groups per repeat unit of said A block.

72. The composition of claim 63, wherein said polyamides comprise poly(ether-
5 block-amide).

73. The composition of claim 72, wherein said composition comprises about 5% to about 30% by weight of said liquid crystal block copolymer and about 70% to about 95% by weight of said poly(ether-block-amide).

10

74. The composition of claim 63, wherein said liquid crystal block copolymer has a structure selected from the group consisting of A-B diblock, $(A-B)_n$ wherein n is 3 to 20, B- $(A-B)_n$ -B wherein n is 3 to 20, A-B-A triblock, B-A-B triblock, A-B-A-B-A pentablock, random block, and multiblock polymers.

15

75. The composition of claim 63, wherein the liquid crystal block copolymer further includes a C block, wherein the C block comprises from 2 to about 50 mesogenic repeat units, and wherein the mesogenic repeat units are different than those of the A block.

20 76. The composition of claim 75, wherein said liquid crystal block copolymer has a structure selected from the group consisting of A-B-C triblock, A-C-B triblock, and B- $(A-B-C)_n$ -B wherein n is 3 to 20.

77. A medical device wherein at least a portion thereof comprises:

25 a liquid crystal block copolymer, the liquid crystal block copolymer comprising:

- i. at least one A block, wherein the A block comprises from 2 to about 50 mesogenic repeat units; and
- ii. at least one B block, wherein the B block is a soft block comprising nylon;

30 and at least one non-liquid crystal polymer;

wherein said at least one non-liquid crystal polymer is compatible with the B block of said liquid crystal block copolymer.

78. The medical device of claim 77, wherein the medical device is a catheter assembly.

79. The medical device of claim 77, wherein said at least a portion thereof is a catheter shaft.

80. The medical device of claim 77, wherein said medical device is an expandable medical balloon.

81. A medical device, wherein at least a portion of said device is formed from a polymer composition comprising:

at least one liquid crystal block copolymer comprising:

- i. at least one A block, wherein the A block comprises from 2 to about 50 mesogenic repeat units; and
 - ii. at least one B block, wherein the B block is a soft block comprising at least one member selected from the group consisting of polyamides, polyesters, polyethers, polyimides, polyolefins and polysiloxanes; and
- at least one polymer that is compatible with the B block of said at least one liquid crystal block copolymer.

82. The medical device of claim 81, wherein said B block is aliphatic.

83. A catheter assembly, wherein at least a portion of the catheter assembly is formed from a polymer composition, the polymer composition comprising:
a liquid crystal block copolymer having an A block and a B block, wherein the A block comprises from 2 to about 50 mesogenic repeat units and the B block is a soft block derived from repeat units selected from the group consisting of olefins, esters, ethers, amides, and siloxanes; and
at least one polymer which is not a liquid crystal polymer, the at least one polymer selected so as to be compatible with the B block of the liquid crystal block copolymer.

84. The catheter assembly of claim 83, comprising an expandable balloon member, wherein the expandable balloon member is formed from said polymer composition.

85. The catheter assembly of claim 84, wherein said at least one polymer which is
5 not a liquid crystal polymer is a poly(ether-block-amide).

86. The catheter assembly of claim 85, wherein said B block comprises amide repeat units.

10 87. The catheter assembly of claim 86, wherein said A block comprises the reaction product of 4-acetoxybenzoic acid and 1,4-butanediol.

88. The catheter assembly of claim 86, wherein said A block is polymerized with terephthalic acid and nylon 6.

15

89. The catheter assembly of claim 88, wherein said liquid crystal block copolymer is an A-B-A block copolymer having the general formula $[(ABA-BDO-ABA-TPA)_x ABA-BDO-ABA]-Ny6-[ABA-BDO-ABA-(TPA-ABA-BDO-ABA)_y]$, wherein ABA represents 4-acetoxybenzoic acid, BDO represents 1,4-butanediol, TPA represents
20 terephthalic acid, Ny6 represents nylon 6, and x and y represent integers.

90. The catheter assembly of claim 86, wherein said A block comprises repeat units derived from 1,3-propane diol or ethylene glycol.

25 91. The catheter assembly of claim 87, wherein said A block is polymerized with a diacid terminated nylon polymer.

92. The catheter assembly of claim 88, wherein said A block is polymerized with 2,6-naphthalene dicarboxylic acid.

30

93. The catheter assembly of claim 87, wherein said A block is polymerized with 6-hydroxy-2-naphthoic acid.

94. The catheter assembly of claim 83, said catheter assembly comprising at least one catheter shaft, wherein at least a portion of said at least one catheter shaft comprises said polymer composition.

5 95. An expandable medical balloon formed from at least one poly(ether-block-amide) block copolymer, and reinforced with a liquid crystal block copolymer having at least one A block and at least one non-liquid crystal polymer B block;

wherein said A block comprises from 2 to about 50 mesogenic repeat units and said B block is a soft block; and

10 wherein said poly(ether-block-amide) block copolymer is compatible with said non-liquid crystal polymer B block.

96. The expandable medical balloon of claim 95, wherein said B block of said liquid crystal block copolymer comprises a diacid terminated nylon polymer segment.

15

97. The expandable medical balloon of claim 96, wherein said diacid terminated nylon polymer segment is nylon 6, nylon 6,10 or nylon 9,12.

98. The expandable medical balloon of claim 95, wherein said B block comprises a
20 mono-acid terminated nylon polymer segment and said block copolymer is an AB diblock copolymer.

99. The expandable medical balloon of claim 98, wherein said mono-acid terminated nylon polymer segment is nylon 12.

25

100. The expandable medical balloon of claim 95, wherein said A block is a nylon polymer segment and said B block comprises polytetramethylene oxide.

101. The expandable medical balloon of claim 100, wherein said nylon polymer
30 segment comprises at least one aromatic group per a repeat unit.