



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : D21F 1/00	A1	(11) International Publication Number: WO 98/41683 (43) International Publication Date: 24 September 1998 (24.09.98)
(21) International Application Number: PCT/SE97/00466 (22) International Filing Date: 20 March 1997 (20.03.97) (71) Applicant (for all designated States except US): STORA KOPPARBERGS BERGSLAGS AKTIEBOLAG [SE/SE]; Åsgatan 22, S-791 80 Falun (SE). (72) Inventors; and (75) Inventors/Applicants (for US only): HÅKANSSON, Philip [SE/SE]; Vintervägen 9, S-294 37 Sölvesborg (SE). CARLSSON, Tommy [SE/SE]; Getingvägen 14, S-294 36 Sölvesborg (SE). WIGSTEN, Anders [SE/SE]; Husmansvägen 7, S-790 15 Sundborn (SE). (74) Agent: HYNELL, Magnus; Hynell Patenttjänst AB, Patron Carls väg 2, S-683 40 Hagfors/Uddeholm (SE).		(81) Designated States: AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), EE, EE (Utility model), ES, FI, FI (Utility model), GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>In English translation (filed in Swedish).</i>
(54) Title: METHOD AND DEVICE IN THE PRODUCTION OF A WEB MATERIAL		
(57) Abstract <p>The invention relates to a method to, in connection with the preparation of a web which to an essential part consists of cellulosic fibres, improve the formation of the web material in a one or plural wire machine by, to an essential part, dispersing existing flocks in the stock which is led from an inlet box out onto at least one wire, and to counteract the reformation of flocks in the stock on the wire. The distinguishing feature is that ultrasound energy is furnished to the stock in at least one wire section. The invention also relates to a device for performance of the method.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

METHOD AND DEVICE IN THE PRODUCTION OF A WEB MATERIAL

TECHNICAL FIELD

5 The invention relates to a method to improve, in the production of a web which to an essential part consists of cellulosic fibres, the formation of the web material in a one or plural wire machine by, to an essential part, dispersing existing flocks in the stock which is led from an inlet box out onto at least one wire, and to counteract the reformation of flocks in the stock on the wire. The invention also relates to a device for performing the
10 method. The description also includes a short account of a method to clean press felts and wires.

BACKGROUND OF THE INVENTION

When producing paper and board, the raw material is mainly cellulosic fibres and in most
15 cases also fillers, such as calcium carbonate and/or clay, retention agents and so on are included. The included components tend, in connection with the production of paper and board, to form flocks in the stock with poor distribution of the components as a result. The formation is used as a measurement of how even the components, mainly the fibres and fillers, which are included in the paper or board, are distributed.

20 The formation is a very important property of paper and board. A paper or board with poor formation gives a stained impression, has poorer printing properties and poorer strength than a paper or a board with good formation. By improving the formation, essential improvements in quality can be achieved. As an alternative, the basis weight of
25 the paper or board can be decreased with sustained strength, which results in a not unessential economic potential.

Traditionally, it has been tried to solve the problem with fibre flocks by developing the design of the inlet boxes or equipment in near connection with the inlet box. It has
30 however proved impossible to definitely solve the problem with formation, since fibre flocks quickly reform after the stock has left the inlet box and has entered onto the wire.

It has also been suggested different arrangements within the wire section, which to a certain extent can prevent the reformation of fibre flocks, for example different types of
35 vibration and/or shaking means. The installation of top wire structures can also be said to be a part of this goal, although the installation of top wires in the first place is dictated by other purposes.

As a conclusion it can be said that the equipment, which so far has been used or proposed in order to take care of the problem of fibre flocks, is difficult to control, complicated, capital demanding and that it obstructs or prevents the optimisation of other quality properties than formation in the paper or board. A consequence of this compromising is e.g. that the orientation of fibres in the paper or board is difficult to optimise. A result of the use of so far known equipment for improving the formation, is typically such conditions that more fibres are oriented in the length direction of the web material than in its cross direction. This results in poorer strength properties in the cross direction of the product.

DESCRIPTION OF THE INVENTION

The object of the invention is to attack the above problems. This is, in connection with the method described in the introduction, achieved by ultrasound energy being furnished to the stock in at least one wire section, suitably by the ultrasound energy being furnished to the stock on the wire in at least one cross directional section of the wire section along the transport direction of the stock on the wire. The ultrasound energy is preferably furnished as ultrasound waves with frequencies between 15 and 75 kHz, which has surprisingly shown to result in considerably better formation when ultrasound elements (ultrasound generators or elements which can transmit ultrasound energy from one or more generators), which emit energy by means of oscillation with said frequency, are placed within the wire section of a paper or board machine in such a way that ultrasound energy is transmitted to the stock on the wire. In order to achieve the best effect, the ultrasound energy transmitting elements should be positioned directly below the wire or wires which follow after the inlet box or boxes of the paper or board machine. As a consequence of this positioning, the effect can also be achieved that the wire or wires are cleaned. The elements are moreover positioned so that an optimal effect, i.e. optimal ultrasound energy per mass unit of the stock (suspension of fibres/fillers) is achieved, at the same time as it is important that the concentration of the stock (the dry content) in at least one or some of said sections of the wire section still is adequately low so that flocks which are formed are not bound too strong, but can be broken apart. Consequently, at least some ultrasound elements are positioned e.g. so that they mainly influence the stock within at least one section of the wire section where the stock on the wire has a concentration of between 0,2 and 6 %, suitably between 0,5 and 5 % or between 1 and 6 %. A conceivable optimal range of content can also be between 1,5 and 5 %. A positioning of the ultrasound elements further back on the paper machine, e.g. in or on the inlet box, will for certain result in that flocks which may have been formed possibly can be dispersed there, but these can afterwards be reformed on the wire or wires.

Consequently, a positioning of the elements before the wire section will result in none or very small improvement of the formation.

5 In certain cases, it can be conceived to position elements which transmit ultrasound energy also within one or more sections where the concentration of the stock is more than 5 or 6 %, preferably in order to prevent flocks from being reformed. It can for example be conceived to place ultrasound elements within sections of the area which is common for a top wire section and a sub wire section, within which sections the concentration of the stock may be considerably higher than 5 à 6 % or up to 15 %, 10 preferably a maximum of 12 %, as well as within the introductory section of the sub wire, where the concentration of the stock may be lower than 5 à 6 %. The ultrasound elements within the introductory section of the sub wire, where the concentration of the stock is 0,2-6 %, preferably 0,5-5 % or 1-6 %, e.g. 1,5-5 %, hereby act to both dissolve flocks which have already been formed and to prevent new establishment of flocks, while 15 ultrasound elements within the area where the concentration is as much as between 5 and 15 %, preferably between 6 and 12 %, in the first place are acting to preserve the good formation.

20 The ultrasound energy is suitably furnished to the stock on the wire within a plurality of cross directional sections which are arranged after each other, e.g. within three to five after each other following, cross directional sections. This will also result in a possibility to adapt the frequency and/or power of the ultrasound to the concentration of the stock within different sections of the wire section, so that e.g. ultrasound energy with a higher frequency is furnished in at least one section which is closer to the inlet box, than within 25 a subsequent section further away from the inlet box.

The ultrasound elements are suitably arranged so that the ultrasound power (amplitude) and/or the frequency can be controlled. Hereby, an optimisation of the formation will be possible, so that it can be adapted to the composition of the stock. Consequently, flocks 30 which contain larger amounts of fines and fillers should demand a higher frequency than e.g. a stock which is based on a hard wood pulp with short fibres, which may demand a somewhat lower frequency. The lowest frequency should be demanded in connection with the dispersion of fibres from soft wood pulp with long fibres. Also the wire speed has effect on suitable frequency and/or power. The optimisation of the frequency and 35 power of the ultrasound elements can of course be made by means of a parent control and regulation equipment.

The ultrasound elements may consequently operate sequentially by changing the frequency and/or power or also the elements may be dedicated for certain prechosen frequencies and/or powers which attack certain flock sizes or a certain content of flock. One aspect of the invention is characterised in that the ultrasound elements are equipped
5 to operate in this way. Further features and aspects of the invention are apparent from the subsequent claims.

It is also possible to place ultrasound elements in direct contact with press felts, formation wires and/or drying wires in order to clean these felts and/or wires. A water
10 spray can be positioned either on the same side as the ultrasound element or on the opposite side in order to supply the water volume which is necessary to transmit the ultrasound from the element to the inner structure of the felt or wire.

CLAIMS

1. Method to improve, in the production of a web which to an essential part consists of cellulosic fibres, the formation of the web material in a one or plural wire machine by, to an essential part, dispersing existing flocks in the stock which is led from an inlet box out
5 onto at least one wire, and to counteract the reformation of flocks in the stock on the wire, characterised in that ultrasound energy is furnished to the stock in at least one wire section.
2. Method according to claim 1, characterised in that the ultrasound energy is
10 furnished to the stock on the wire within at least one cross directional section of the wire section along the transport direction of the stock on the wire.
3. Method according to claim 2, characterised in that the ultrasound energy is
15 furnished to the stock on the wire within a plurality of cross directional sections which are arranged after each other.
4. Method according to claim 3, characterised in that the ultrasound energy is
20 furnished to the stock within three to five cross directional sections which are arranged after each other.
5. Method according to any of claims 1-4, characterised in that the ultrasound
energy is furnished to the stock within at least some section where the stock on the wire has a concentration (dry content) of between 0,2 and 6 %, preferably between 0,5 and 5
25 % or between 1 and 6 %, suitably between 1,5 and 5 %.
6. Method according to claim 5, characterised in that ultrasound energy also is
furnished to the stock within at least some section where the concentration of the stock is 5-15 %, preferably 6-12 %.
7. Method according to any of claims 1-5, characterised in that the ultrasound
30 energy is furnished to the stock within the area of the first half of the wire section.
8. Method according to claim 1, characterised in that the ultrasound energy is
35 furnished as ultrasound waves with frequencies between 15 and 75 kHz.

9. Method according to any of the preceding claims, characterised in that the ultrasound waves which are furnished to the stock have different frequencies within at least a couple of said sections.
- 5 10. Method according to claim 9, characterised in that the ultrasound has a higher frequency within at least one section which is closer to the inlet box than a subsequent section further away from the inlet box, within which subsequent section the ultrasound has a lower frequency.
- 10 11. Device for performance of the method according to any of claims 1-10, characterised in that ultrasound elements which transmit the ultrasound energy to the stock are arranged in a wire loop in contact with the inside of the wire in the loop in the area of the distribution of the stock and thus also in contact with the liquid in the stock via the wire and via the mesh interspaces in the wire for transmission of the
15 ultrasound energy to the stock via the wire and directly to the liquid phase via the mesh interspaces.
12. Device according to claim 11, characterised in that ultrasound elements are arranged in a sub loop and/or in a top loop.
- 20 13. Device according to claim 12, characterised in that ultrasound elements are arranged opposite each other in a sub wire loop and in a top wire loop.
14. Device according to any of claims 11-13, characterised in that the
25 ultrasound elements and/or ultrasound generators which are connected to the ultrasound elements are adjustable in respect of power and/or frequency which is transmitted to the stock.
15. Device according to any of claims 11-14, characterised in that the
30 ultrasound elements consist of separate units.
16. Device according to any of claims 11-14, characterised in that the ultrasound elements are integrated with one or some dewatering elements of the type which include formation tables, foils and suction boxes.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 97/00466

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: D21F 1/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: D21F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

DIALOG: ALLSCIENCE

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>Dialog Information Services, File 240, PAPERCHEM, Dialog acc no. 0567131, Paperchem No: 65-07131, Mitsubishi Heavy Industries Ltd.: "Dispersion of Pulp in Papermaking"; Jap. pat. Kokai 33,283/93, February 9, 1993. 5 p.; & File 347, JAPIO, Acc no. 04041583; & File 351, DERWENT WPI, Dialog acc no. 009395680, WPI acc no. 93-089151/11; & JP,A, 5-33283, 930209, Figures 1-12</p> <p style="text-align: center;">-- -----</p>	1-16

☐ Further documents are listed in the continuation of Box C.

☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

21 October 1997

Date of mailing of the international search report

11-11-1997

Name and mailing address of the ISA/

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

Olav Jensen

Telephone No. +46 8 782 25 00