



(86) **Date de dépôt PCT/PCT Filing Date:** 2010/06/08  
(87) **Date publication PCT/PCT Publication Date:** 2010/12/16  
(45) **Date de délivrance/Issue Date:** 2017/02/14  
(85) **Entrée phase nationale/National Entry:** 2011/12/07  
(86) **N° demande PCT/PCT Application No.:** JP 2010/059719  
(87) **N° publication PCT/PCT Publication No.:** 2010/143638  
(30) **Priorité/Priority:** 2009/06/08 (JP2009-137467)

(51) **Cl.Int./Int.Cl. C08L 77/06** (2006.01),  
**C08K 5/13** (2006.01), **C08K 5/18** (2006.01),  
**C08K 5/20** (2006.01), **C08K 5/36** (2006.01),  
**C08K 5/435** (2006.01)

(72) **Inventeurs/Inventors:**  
MITADERA, JUN, JP;  
KUROKAWA, MASASHI, JP

(73) **Propriétaire/Owner:**  
MITSUBISHI GAS CHEMICAL COMPANY, INC., JP

(74) **Agent:** SMART & BIGGAR

(54) **Titre : COMPOSITION DE RESINE DE POLYAMIDE ET ARTICLE MOULE**  
(54) **Title: POLYAMIDE RESIN COMPOSITION AND MOLDED ARTICLE**

(57) **Abrégé/Abstract:**

Disclosed is a polyamide resin composition having excellent gas barrier properties and heat aging resistance, which contains (A) a polyamide composed of a diamine unit containing a 1,3-bis(aminomethyl)cyclohexane unit and a dicarboxylic unit and at least either of (B) an aromatic secondary amine based compound and (D) a phenol based antioxidant and has an oxygen permeability coefficient of not more than 1.5 cc•mm/m<sup>2</sup>•day•atm at 23°C and 75 % RH.