



(72) DIVONE, PETER ANTHONY, US

(72) DOBKOWSKI, BRIAN JOHN, US

(72) CHENEY, MICHAEL CHARLES, US

(72) PLIEGO, SALVADOR, US

(72) BIERCEVICZ, WALTER ANTHONY, US

(72) MANZARI, KENNETH PAUL, US

(71) UNILEVER PLC, GB

(51) Int.Cl.<sup>6</sup> A61K 7/48, B01J 2/20, B01J 2/18, B29B 9/00, C08L 83/04,  
A61K 7/00

(30) 1997/03/20 (08/822406) US

(54) **METHODE DE PREPARATION DE COMPOSITIONS  
D'ELASTOMERE DE SILICONE**

(54) **PROCESS FOR PREPARING SILICONE ELASTOMER  
COMPOSITIONS**

(57) L'invention concerne une méthode pour préparer des compositions d'élastomère de silicone destinées à la fabrication de produits cosmétiques. La méthode consiste à introduire dans un réacteur la composition d'élastomère de silicone contenant un caoutchouc de silicone dans un fluide porteur, à mélanger la composition dans le réacteur, à transférer ladite composition du réacteur vers une pompe haute pression, à pomper le fluide à l'intérieur d'un dispositif pour réduire les particules de caoutchouc en dimensions plus petites, puis à réintroduire les particules réduites ainsi obtenues dans le réacteur pour les y recycler. Le dispositif utilisé pour réduire la taille des particules est, de préférence, un homogénéisateur haute pression ou, mieux encore, un "sonolateur".

(57) A process is provided for preparing a silicone elastomer composition for cosmetic products which includes the steps of feeding the silicone elastomer composition comprising a silicone rubber in a carrier fluid into a reactor, mixing the composition in the reactor, delivering the composition from the reactor into a high pressure pump, pumping the fluid into a device for reducing particles of rubber into smaller sizes and recirculating the resultant size reduced particles back to the reactor. The device for reducing particle size is preferably a high pressure fed homogenizer, most advantageously a sonolator.

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification<sup>6</sup> :</b> <b>A61K 7/48, 7/00, C08L 83/04, B29B 9/00, B01J 2/18, 2/20</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 98/42307</b> <b>(43) International Publication Date:</b> 1 October 1998 (01.10.98)
<b>(21) International Application Number:</b> PCT/GB98/00828 <b>(22) International Filing Date:</b> 19 March 1998 (19.03.98) <b>(30) Priority Data:</b> 08/822,406                      20 March 1997 (20.03.97)                      US <b>(71) Applicant (for AU BB CA GB GH GM IE IL KE LC LK LS MN MW NZ SD SG SL SZ TT UG ZW only):</b> UNILEVER PLC [GB/GB]; Unilever House, Blackfriars, London EC4P 4BQ (GB). <b>(71) Applicant (for all designated States except AU BB CA GB GH GM IE IL KE LC LK LS MN MW NZ SD SG SL SZ TT UG ZW):</b> UNILEVER NV [NL/NL]; Weena 455, NL-3013 AL Rotterdam (NL). <b>(72) Inventors:</b> DIVONE, Peter, Anthony; 37 Windmill Lane, New City, NY 10956 (US). DOBKOWSKI, Brian, John; 31 Wakeley Street, Shelton, CT 06484 (US). CHENEY, Michael, Charles; 383 Sigwin Drive, Fairfield, CT 06430 (US). PLIEGO, Salvador; 3214 Town Walk Drive, Hamden, CT 06518 (US). BIERCEVICZ, Walter, Anthony; 9 Wagon Wheel Drive, Prospect, CT 06712 (US). MANZARI, Kenneth, Paul; 72 Burwell Road, West Haven, CT 06516 (US).		<b>(74) Agent:</b> MOLE, Peter, Geoffrey; Unilever PLC, Patent Division, Colworth House, Sharnbrook, Bedford MK44 1LQ (GB).  <b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.  Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> PROCESS FOR PREPARING SILICONE ELASTOMER COMPOSITIONS		
<b>(57) Abstract</b> <p>A process is provided for preparing a silicone elastomer composition for cosmetic products which includes the steps of feeding the silicone elastomer composition comprising a silicone rubber in a carrier fluid into a reactor, mixing the composition in the reactor, delivering the composition from the reactor into a high pressure pump, pumping the fluid into a device for reducing particles of rubber into smaller sizes and recirculating the resultant size reduced particles back to the reactor. The device for reducing particle size is preferably a high pressure fed homogenizer, most advantageously a sonolator.</p>		

- 1 -

**PROCESS FOR PREPARING**  
**SILICONE ELASTOMER COMPOSITIONS**

5 **BACKGROUND OF THE INVENTION**

**Field of the Invention**

10 The invention concerns a process for preparing cosmetic products or work-in-progress components of such products which include silicone elastomers as a functional ingredient.

**The Related Art**

15

Over the last four decades a rich variety of silicone materials have been commercialized for use in cosmetics. Although expensive, silicones have many unusual properties rendering them almost indispensable for certain types of products. Lubricity, compatibility, stability, dispersibility, thickening ability and other properties have been deemed quite valuable.

25 Among the multitude of silicone materials, the rubber-like polysiloxane elastomers have received attention as components in both aqueous emulsions and nonaqueous formulations. Illustrative of the art is WO 96/18374 (Estee Lauder) describing a stable water-in-oil emulsion incorporating an organopolysiloxane elastomer having a degree of cross-linking sufficient to provide a rubber-like material. A skin treatment cream was exemplified employing Gransil, a mixture of octamethylcyclotetrasiloxane and organopolysiloxane rubber. The components were formulated as three phases which were homogenized with a Silverson

30

- 2 -

Homogenizer. In a second example, a cosmetic foundation was prepared through a combination of low and high shear mixing.

U.S. Patent 4,983,418 (Murphy et al.) discloses hair spray  
5 compositions which include a silicone gum which when applied to hair imparts style, retention and conditioning benefits. Diphenyl-dimethyl polysiloxane gum is reported to be the preferred embodiment.

10 U.S. Patent 5,266,321 (Shukuzaki et al.) describes oily make-up cosmetic compositions normally in solid form. These compositions contain a silicone gel which includes a partially crosslinked organopolysiloxane polymeric compound and a low viscosity silicone oil. The polymeric compound is  
15 preferably prepared by the addition polymerization of an organo-hydrogen polysiloxane and an organopolysiloxane having unsaturated aliphatic groups. Solid foundations described in the examples are prepared in a step including homogenization in a triple roll mill.

20 U.S. Patent 4,980,167 (Harashama et al.) reports cosmetic compositions exhibiting lubricancy derived from a silicone rubber powder ingredient within a silicone oil. A preferred rubber derives from the addition reaction between an  
25 organopolysiloxane containing at least two vinyl groups, an organopolysiloxane containing at least two silicon bonded hydrogen atoms and a platinum catalyst. Oily foundations, lipsticks and moisturizing creams are exemplified. Related silicone rubbers are reported in U.S. Patent 4,742,142  
30 (Shimizu et al.). This patent focuses upon synthesis of the rubber.

Although of great potential, the silicone elastomer materials commercially available or even hitherto reported

- 3 -

in the literature have physical properties insufficiently suitable for elegant cosmetic products.

Accordingly, it is an object of the present invention to provide a process for preparation of silicone elastomer compositions containing a silicone rubber within a carrier fluid, the process converting the rubber to a form stably dispersed in the carrier fluid and exhibiting a silky skinfeel when combined into cosmetic products.

10

These and other objects of the present invention will become more apparent from the following summary and description.

#### **SUMMARY OF THE INVENTION**

15

According to a first aspect, the present invention provides a process for reducing the particle size of the silicone elastomer within a silicone elastomer composition comprising silicone elastomer in a carrier fluid, said process comprising putting the silicone elastomer composition through a high pressure homogeniser whereby the elastomer particle structure is broken down.

20

In a second aspect, the present invention provides a process for reducing the particle size of the silicone elastomer within a silicone elastomer composition comprising silicone elastomer in a carrier fluid, said process comprising forcing the silicone elastomer composition under pressure, preferably high pressure, through a means comprising a small orifice or gap whereby the elastomer particle structure is broken down.

30

The process of this invention is not directed at synthesis of any silicone elastomer as such but rather concerns a method to physically manipulate a pre-synthesized elastomer

35

- 4 -

into a form more suitable for certain cosmetic products and in particular into a form that may facilitate the processing of such silicone elastomer compositions in cosmetic products. Transformations of the present invention are intended to customize elastomer particle sizes and composition viscosities to match requirements for the cosmetic product.

The silicone elastomer for use in the process of the present invention is preferably a crosslinked non-emulsifying siloxane elastomer formed from a divinyl monomer reacting with Si-H linkages of a siloxane backbone. A volatile siloxane such as cyclomethicones is the preferred carrier fluid for delivery of the elastomer through the recirculating system.

Thus, according to a third aspect, the present provides a process for preparing silicone elastomer compositions for use in cosmetic products which compositions comprise a silicone elastomer within a carrier fluid, the process including the steps of:

- (i) feeding a silicone elastomer composition comprising a silicone elastomer and a carrier fluid into a reactor;
- (ii) mixing the silicone elastomer composition through agitation in the reactor;
- (iii) transferring the agitated silicone elastomer composition from the reactor into a high pressure pump;
- (iv) pumping the agitated silicone elastomer composition from the high pressure pump into a means for reducing the silicone elastomer within the composition into a smaller particle size; and

- 5 -

- (v) optionally, recirculating the resultant smaller sized silicone elastomer particles into the reactor.

5 The means for reducing particle size may be a special variety of homogenizer wherein under pressure the silicone composition is forced through a small orifice with high local energy applied to breakdown particle structure of the silicone elastomer. A particularly preferred device is a  
10 sonolator operating with an ultrasonic blade which generates turbulent cavitation bursts.

In a fourth aspect, the present invention provides for a silicone elastomer composition comprising a silicone rubber  
15 within a carrier fluid, the rubber having an average particle size ranging from 0.5 to 30 micron.

According to a further aspect of the invention, there is provided an antiperspirant or deodorant composition for  
20 topical application comprising:

- (i) an antiperspirant or deodorant active;
- (ii) volatile silicone; and
- (iii) a silicone elastomer composition,

25

characterised in that the silicone elastomer composition is prepared according to the process of the invention.

#### **BRIEF DESCRIPTION OF THE DRAWING**

30

The process of the present invention will now be described by way of example only, with reference to the following drawing in which figure 1 shows a schematic drawing of

- 6 -

according to the present invention a preferred embodiment of the process according to the present invention.

#### DETAILED DESCRIPTION OF THE INVENTION

5

Now it has been discovered that silicone elastomers can be prepared for use with cosmetic products in a procedure which reduces their particle size by repeated treatment in a high pressure fed homogenizer. Figure 1 illustrates a preferred  
10 embodiment. Therein a silicone elastomer dispersed within cyclomethicone carrier at an elastomer concentration of from 1 to 95%, preferably from 5 to 30%, optimally from 15 to 20% by weight of the silicone elastomer/cyclomethicone composition, is charged to a reactor 2 as a silicone  
15 elastomer composition. Additional cyclomethicone carrier in an amount from 0 to 95%, preferably from 50 to 80%, optimally from 65 to 75% by weight based on the amount of final recirculated elastomer composition may be charged to the reactor through a separate feed line 4. The silicone  
20 elastomer composition and any additional cyclomethicone carrier is then mixed by a slow speed counter-sweep mixer 6 to agitate the mixture.

Within reactor 2, is a high-shear homogenizer 8 employing a  
25 series of blades to produce high energy shear forces onto the mixture. Homogenizer 8 improves the resultant product but is not a necessary element of the process. In some configurations, homogenizer 8 may be placed outside reactor 2 in a location prior to the high pressure pump 10.

30

Upon completion of agitation in reactor 2, the resultant fluid mixture is delivered from the reactor into a feed pump  
9. The feed pump 9 is a positive displacement pump such as Waukesha PD gear pump. Thereafter the fluid mixture is  
35 transferred to a high pressure pump 10. Pressures generated

- 7 -

by pump 10 may range from 500 to 40,000, preferably from 1,200 to 20,000, optimally from 1,800 to 10,000 psi.

Typically, pump 10 may be a triplex plunger type available from the Giant Corporation, Toledo, Ohio or from the Cat  
5 Corporation.

Silicone elastomer composition under high pressure is then pumped into a type of homogenizer 12 requiring fluid to pass through a narrow orifice which reduces particle size. The  
10 preferred embodiment employs a sonolator available from the Sonic Corp., a unit of General Signal. The sonolator is an in-line device capable of converting the kinetic energy of a high velocity stream of liquid into a high intensity mixing action. Conversion is accomplished by pumping the liquid  
15 through an orifice against a bladelike obstacle immediately in the jet stream of the liquid. The liquid itself oscillates in a stable vortexing pattern, which in turn causes the blade-like obstacle to resonate, resulting in a high level of cavitation, turbulence and shear. The blade  
20 or knife is brought into an ultrasonic vibration by the fluid motion, which causes cavitation in the fluid. The cavitation (a phenomenon in which small gas bubbles in the fluid start to grow until they implode with very high local energy dissipation rates) then breaks up the droplet  
25 particles. U.S. Patent No. 3,176,964 to Cottell et al. describes the sonolator in detail and its disclosure is hereby incorporated by reference.

Alternative high-pressure fed homogenizers other than the  
30 sonolator (preferred) are the Manton Gaulin type homogenizer available from the APV Manton Corporation and the Microfluidizer available from Microfluidics Corporation. These type of high pressure homogenizers contain a valve which is pressed (hydraulically or by a spring) against a  
35 fixed valve seat. Under high pressure, fluid flows through

- 8 -

the opening in the seat and then through a gap between the valve and seat. Although geometries of different high pressure homogenizers may differ in details, and may even be roughened with sharp edges, they all are generally similar.

5 Often the high pressure homogenizer may consist of two or more valve-seat combinations.

Subsequent to high pressure homogenization, the silicone elastomer composition may, for best results, be recirculated  
10 into reactor 2. Recirculation according to the present process normally ranges from 1 to 200 passes, preferably from 2 to 60 passes, optimally from 10 to 40 recycling passes. Temperatures within reactor 2 and throughout the system may range from 20 to 100°C, preferably from 35 to  
15 60°C, optimally from 50 to 70°C. Silicone elastomer particles resulting from the process will have an average particle size ranging from 0.05 to 30 micron, preferably from 0.2 to 10 micron, optimally from 0.5 to 5 micron. These particles are uniformly dispersed within the silicone  
20 oil (e.g. cyclomethicone) carrier.

Particle size may be measured using a Electro Zone Particle Sizing System (from Particle data Europe S.a.r.l.). In such a system, particles flowing nearly singly through a small  
25 liquid resistor cause a series of electrical pulses. The pulse amplitude represents the space occupied by a particle in the electrical field and thus allows the particle size to be measured.

30 Silicone elastomers of the present invention preferably are crosslinked non-emulsifying siloxane elastomers with average number molecular weights in excess of 10,000, preferably in excess of 1 million and optimally will range from 10,000 to 20 million. The term "non-emulsifying" defines a siloxane  
35 from which polyoxyalkylene units are absent. Advantageously

- 9 -

the elastomers are formed from a divinyl monomer reacting with Si-H linkages of a siloxane backbone. Elastomer compositions are commercially available from the General Electric Company under product designation General Electric Silicone 1229 named PolydimethylHydrogenSiloxane -Reaction Products with Vinyl Terminated Polydimethylsiloxane, delivered as 20-35% rubber in a cyclomethicone carrier. A related elastomer under the CTFA name of Crosslinked Stearyl Methyl Dimethyl Siloxane Copolymer is available as Gransil SR-CYC (25-35% active elastomer in cyclomethicone) from Grant Industries, Inc., Elmwood Park, New Jersey. Amounts of the elastomer dispersed in the final cosmetic product formulated with the elastomeric composition derived from the process may range from 0.1 to 50%, preferably from 1 to 40%, more preferably from 3 to 20% by weight of the final product.

The silicone elastomer may be dispersed within a silicone carrier. Illustrative of such silicone carriers are silicone fluids such as the cyclo polydimethyl siloxane fluids of the formula  $[(CH_3)_2SiO]_x$ , wherein x denotes an integer of from 3 to 6. The cyclic siloxanes will have a boiling point of less than 250°C and a viscosity at 25°C of less than 10 centipoise. Cyclomethicone is the common name of such materials. The tetramer and pentamer cyclomethicones are commercially available as DC 244 or 344 and DC 245 or 345 from the Dow Corning Corporation. Also useful is hexamethyldisiloxane available as DC 200 fluid (0.65 cs).

Hydrophobic carriers other than silicone fluids may also be employed as carriers. Petrolatum is the most preferred. Other hydrocarbons that may be employed include mineral oil, polyolefins such as polydecene, and paraffins such as isohexadecane (e.g. Permethyl 997 and Permethyl 1017).

- 10 -

Compositions subject to the present method may either be anhydrous or contain water. When anhydrous, the amount of water will be confined to range from 0 to 5%, preferably not  
5 above 2%, optimally not above 0.5% by weight. When the compositions of this invention are in emulsion form, the amount of water will range from 5 to 50%, preferably from 7 to 30%, optimally from 10 to 20% by weight. The emulsions may be of the oil-in-water, water-in-oil or duplex variety.  
10 Aqueous to oily phases can range in weight from 10:1 to 1:10, preferably from 1:1 to 1:5, optimally from 1:1 to 1:2.

Hydrophillic carriers other than water may be present, such as polyhydric alcohols. Typical polyhydric alcohols include  
15 polyalkylene glycols and more preferably alkylene polyols and their derivatives. Illustrative are propylene glycol, dipropylene glycol, polypropylene glycol, polyethylene glycol, sorbitol, hydroxypropyl sorbitol, hexylene glycol, 1,3-butylene glycol, 1,2,6-hexanetriol, glycerin,  
20 ethoxylated glycerin, propoxylated glycerin and mixtures thereof. Most preferably the alcohol is glycerin. Amounts of alcohol may range anywhere from 1 to 50%, preferably from 10 to 40%, optimally from 25 to 35% by weight of the cosmetic product .

25 Beyond the basic components, other materials may be included depending upon the particular type of cosmetic composition sought. For instance, surfactants may be formulated into the compositions. These may be selected from nonionic,  
30 anionic, cationic or amphoteric emulsifying agents. They may range in amount anywhere from about 0.1 to about 20% by weight. Illustrative nonionic surfactants are alkoxyated compounds based on C<sub>10</sub>-C<sub>22</sub> fatty alcohols and acids, and sorbitan. These materials are available, for instance, from  
35 the Shell Chemical Company under the Neodol trademark.

- 11 -

Copolymers of polyoxypropylene-polyoxyethylene, sold by the BASF Corporation under the Pluronic trademark, are sometimes also useful. Alkyl polyglycosides available from the Henkel Corporation may also be utilized for purposes of this invention.

Anionic type surfactants include fatty acid soaps, sodium lauryl sulphate, sodium lauryl ether sulphate, sodium or magnesium glyceryl ether sulphonates, alkyl benzene sulphonate, mono- and di-alkyl acid phosphates and sodium fatty acyl isethionate.

Amphoteric surfactants include such materials as dialkylamine oxide and various types of betaines (such as cocoamidopropyl betaine).

Preservatives may be incorporated into the elastomer and cosmetic compositions of this invention to protect against the growth of potentially harmful microorganisms. While it is in the aqueous phase that microorganisms tend to grow, microorganisms can also reside in the oil phase. As such, preservatives which have solubility in both water and oil are preferably employed in the present compositions. Suitable traditional preservatives are hydantoin derivatives, propionate salts, and a variety of quaternary ammonium compounds. Cosmetic chemists are familiar with appropriate preservatives and routinely choose them to satisfy the preservative challenge test and to provide product stability. Particularly preferred preservatives are methyl paraben, propyl paraben, imidazolidinyl urea, sodium dehydroxyacetate and benzyl alcohol. The preservatives should be selected having regard for the use of the composition and possible incompatibilities between the preservatives and other ingredients. Preservatives are

- 12 -

preferably employed in amounts ranging from 0.01% to 2% by weight of the composition.

5 Minor adjunct ingredients may also be included such as fragrances, antifoam agents, opacifiers and colorants, each in their effective amounts to accomplish their respective functions.

10 Where the cosmetic composition is an antiperspirant composition it is preferable that the antiperspirant active is an astringent salt which combines the properties of deodorancy and astringency. Suitable antiperspirant actives are common in the art and include organic and inorganic salts of aluminium, zirconium, zinc and mixtures thereof.

15

Preferably the antiperspirant active is present at levels of from 5 to 30% by weight of the cosmetic composition and more preferably from 15 to 30%.

20 Where the cosmetic composition is a deodorant composition suitable deodorant actives include antimicrobials typically used as deodorant actives in the art, e.g. Triclosan, polyhexamethylene biguanide hydrochloride and ethanol.

25 Where the cosmetic composition is an antiperspirant and/or deodorant composition, the silicone elastomer composition is typically present at levels of from 0.1 to 10% by weight of the cosmetic composition, preferably from 0.5 to 6% and more preferably from 2.0 to 4%.

30

The volatile silicone suitably comprises from 10 to 90% by weight of the cosmetic composition and preferably from 10 to 80% by weight.

- 13 -

The composition according to the invention can optionally comprise other ingredients, in addition to those already identified, depending on the nature and form of the finished  
5 product.

Examples of other ingredients which can optionally be present in a deodorant or antiperspirant composition according to the invention include emollients, such as non-  
10 volatile silicones, hydrocarbons or mineral oils.

Non-volatile silicones include polydimethylsiloxane having a viscosity in excess of  $5 \text{ mm}^2\text{s}^{-1}$ , for example, from 50 to 1000  $\text{mm}^2\text{s}^{-1}$ , such as DOW CORNING 200 Fluids (standard viscosities  
15  $50\text{-}1000\text{mm}^2\text{s}^{-1}$ ).

Other useful emollients include PEG-400 distearate, and ethylene oxide and/or propylene oxide condensation products having the following formula:

20



where R is either hydrogen or a hydrocarbon chain having from about 2 to 20 carbon atoms, and a and b are each from  
25 about 0 to 35 and a + b is from about 5 to 35. One example of such an emollient is Fluid AP, a condensate of about 14 moles of propylene acid with about 1 mole of butyl alcohol sold by Union Carbide.

30 Still further emollients suitable for use in the present solid stick compositions include polyalphaolefins, e.g. polydecene, fatty acid and fatty alcohol esters and water insoluble ethers.

- 14 -

Where the cosmetic composition is an antiperspirant or deodorant composition, the composition may additionally comprise a masking oil, which can typically be present at a level of 3 to 40% by weight of the composition. Suitable masking oils include for example, polydecene, polybutene, PPG-14 butyl ether, non-volatile silicones, isopropyl myristate, isopropyl palmitate, C<sub>12</sub>-C<sub>15</sub> alkyl benzoates, and mineral oils.

10

Other optional ingredients include thickeners, such as clays, for example Bentone 38; and silica, for example Aerosil 200. However, in the present invention, preferred thickening agents are the silicone elastomer compositions.

15

Other optional ingredients include skin feel improvers, such as talc and finely divided polyethylene, an example of which is ACUMIST B18; cosmetically acceptable vehicles, such as anhydrous ethanol and other emollients; perfumes; and preservatives.

20

The composition according to the invention can take the form of a product suited to or adapted for topical application to human skin. Preferred product forms include soft solids, creams, lotions and sticks. In this respect, the cosmetic compositions may contain other cosmetic adjuncts conventionally employed in soft solid, cream, lotion or stick products, for example in deodorant or antiperspirant products.

25

One convenient form of the composition according to the invention is a cream usually contained in a suitable holder or dispenser to enable it to be applied to the area of the

30

- 15 -

skin, particularly the underarm, where control of perspiration and deodorancy is required.

5 Solid products according to the invention may include a wax such as, castor wax, Synchronax HRC, Carnaubau, beeswax, silicone waxes and glycerol monostearate and mixture thereof at levels of from about 1 to 10% preferably 2 to 8%. If present, the wax is believed to enhance structural stability of the composition in the molten state.

10

The ingredients which can optionally be present in the cosmetic composition can conveniently form the balance of the composition.

15 The following examples will more fully illustrate the embodiments of this invention. All parts, percentages and proportions referred to herein and in the appended claims are by weight of the composition unless otherwise indicated.

- 16 -

**EXAMPLE 1**

This Example illustrates processing of a silicone elastomer composition into a work-in-progress constituent of a water-in-oil skin lotion. A 25 gallon reactor fitted in an upper area with a low shear counter-sweep mixing blade and in a lower area with a homogenizing blade was charged with the components listed in Table I.

10 **TABLE I****Silicone Elastomer Composition**

COMPONENTS	WEIGHT %
General Electric Elastomer 1229 (25% elastomer solids in cyclomethicone)	25
Dow Corning 345 (cyclomethicone pentamer)	45
Dow Corning 244 (cyclomethicone tetramer)	30

15 Temperatures throughout the process were maintained between 17 and 28°C. Under pressure the fluid blend of Table I was fed to a sonolator operating between 246 and 295 rpm maintaining a pressure between 2,800 and 3,500 psi.

20 Sonolated product was then returned to the reactor. A total of 19 passes recirculated fluid blend through the system. Resultant silicone elastomer composition exhibited a viscosity of 560 cps at 25°C with elastomer of particle size sufficiently small and dispersed within the cyclomethicone carrier to avoid any grainy feel. Viscosity measurements

25 were taken on a Brookfield LV Viscometer (size 4 bar, 60 rpm, 15 sec.). Broad range of acceptable viscosity can vary from 500 to 40,000 cps at 25°C.

- 17 -

**EXAMPLE 2**

An essentially anhydrous final cosmetic product was prepared utilizing a silicone elastomer composition. The formulas  
5 are shown in Table II.

**TABLE II**

COMPONENT	SILICONE ELASTOMER COMPOSITION (WEIGHT %)	FINAL COSMETIC PRODUCT (WEIGHT %)
General Electric Elastomer 1229 (34% elastomer solid in cyclomethicone)	33.5	31.0
Dow Corning 345 (cyclomethicone pentamer)	45.4	42.0
Dow Corning 344 (cyclomethicone tetramer)	9.2	8.5
Petrolatum (2.5 Hard)	11.9	11.0
Potassium Lactate (50% aqueous soln.)	0.0	7.0
Abil EM 90 (cetyl dimethicone copolyol)	0.0	0.5

10

A 25 gallon reactor was charged with the silicone elastomer composition listed in Table II. Contents of the reactor were agitated with a Press-Industria mixer for a period of several minutes. A 25 DO Waukesha pump transferred the  
15 composition from the reactor to a high pressure pump operating at approximately 1,200 psi and thereafter into a sonolator (74-120 rpm). Sonolated fluid was then returned to the reactor and recycled through the system at flow rates ranging from 9 to 34 pounds per minute. Total process time

- 18 -

was 3 hours. The system was maintained at a temperature 54 to 62°F.

Sonolated fluid composition resulting from the process had a  
5 viscosity between 40,000 and 125,000 cps at 25°C measured on  
a Brookfield RTD (5 rpm heliopath spindle -30 sec). The  
composition was then combined with potassium lactate (50%  
solution) and a silicone copolyol (Abil EM 90) by agitation  
at a temperature between 37° to 60°F. The final cosmetic  
10 product formulation is listed in Table II.

CLAIMS

1. A process for preparing silicone elastomer compositions for use in cosmetic products which compositions  
5 comprise a silicone elastomer within a hydrophobic carrier fluid, the process comprising the steps of:
- (i) feeding the silicone elastomer composition into a reactor;
  - 10 (ii) mixing the silicone elastomer composition through agitation in the reactor;
  - (iii) transferring the agitated silicone elastomer composition from the reactor into a high pressure pump;
  - 15 (iv) pumping the mixed silicone elastomer composition at a pressure ranging from 500 to 40,000 psi from the high pressure pump into a means for reducing the silicone elastomer within the composition into a smaller particle size; and
  - 20 (v) optionally, recirculating the resultant smaller sized silicone elastomer particles into the reactor;
  - (vi) recovering a silicone elastomer composition wherein the silicone elastomer average particle  
25 size ranges from 0.05 to 30 microns.
2. The process according to claim 1 wherein recirculating  
between steps (ii) and (v) ranges from 1 to 200 passes.
- 30 3. The process according to any preceding claim wherein temperature ranges from 20 to 100°C.
4. The process according to any preceding claim wherein the means is a homogenizer.

35

AMENDED SHEET

J6398(C) WO

- 20 -

5. The process according to claim 4 wherein the homogenizer is a sonolator.
6. The process according to any preceding claim wherein the silicone elastomer is dispersed within a silicone carrier.
7. The process according to any preceding claim wherein the silicone elastomer is a crosslinked non-emulsifying polysiloxane prepared from the reaction of a divinyl monomer and a Si-H siloxane.
8. The process according to any preceding claim wherein the carrier fluid is cyclomethicone.
9. An silicone elastomer composition obtained by a process according to any one of claims 1 to 8.
10. The composition according to claim 9 wherein the silicone elastomer is a crosslinked non-emulsifying polysiloxane prepared from the reaction of a divinyl monomer and a Si-H siloxane.
11. The composition according to claim 9 and 10 wherein the carrier fluid is cyclomethicone.

---

12. ~~Cosmetic composition comprising:~~

---

- (i) an antiperspirant or deodorant active;
- (ii) volatile silicone; and
- (iii) a silicone elastomer composition,

characterised in that the silicone elastomer composition is prepared according to any one of claims 1 to 8.

- 21 -

12. The process according to claim 11 wherein the average particle size ranges from 0.5 to 5 micron.
13. The process according to any preceding claim wherein the silicone elastomer is a crosslinked non-emulsifying polysiloxane prepared from the reaction of a divinyl monomer and a Si-H siloxane.
14. The process according to any preceding claim wherein the carrier fluid is cyclomethicone.
15. An silicone elastomer composition obtained by a process according to any one of claims 1 to 14.
16. A silicone elastomer composition comprising a silicone elastomer within a carrier fluid, the elastomer having an average particle size ranging from 0.05 to 30 micron.
17. The composition according to claim 16 wherein the silicone elastomer is a crosslinked non-emulsifying polysiloxane prepared from the reaction of a divinyl monomer and a Si-H siloxane.
18. The composition according to claim 16 or 17 wherein the carrier fluid is cyclomethicone.
19. Cosmetic composition comprising:
- (i) an antiperspirant or deodorant active;
  - (ii) volatile silicone; and
  - (iii) a silicone elastomer composition,

- 22 -

characterised in that the silicone elastomer composition is prepared according to any one of claims 1 to 14.

Fig.1.

