

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08G 18/80, C09D 175/04	A1	(11) International Publication Number: WO 97/14735 (43) International Publication Date: 24 April 1997 (24.04.97)
(21) International Application Number: PCT/US96/16270 (22) International Filing Date: 11 October 1996 (11.10.96) (30) Priority Data: 08/543,773 16 October 1995 (16.10.95) US (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: ANTON, Douglas, Robert; 6 Perth Drive, Wilmington, DE 19803 (US). DARMON, Michael, J.; 609 Orchard Way, Aston, PA 19014-2536 (US). GRAHAM, William, Frank; 29 Newport Drive, Wayne, PA 19087-5849 (US). THOMAS, Richard, Ronald; 1309 Grinnell Road, Wilmington, DE 19803-5105 (US). (74) Agent: FRICKE, Hilmar, L.; E.I. du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: AU, BR, CA, JP, MX, NZ, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: FLUORINATED POLYISOCYANATES		
$R_f-(X)_n-(\overset{R^3}{\underset{ }{\text{CH}_2\text{CH}}}-\text{O})_m-\text{H} \quad (I)$		
(57) Abstract <p>A fluorinated polyisocyanate which comprises an organic polyisocyanate reacted with a fluorinated monofunctional alcohol represented by formula (I), where R_f is a fluoroalkyl containing group having at least 4 carbon atoms, X is a divalent radical, R^3 is H or an alkyl group having 1-4 carbon atoms, n is 0-1 and m is 0-30, provided that when n is 0 then m must be equal to or greater than 1 and when m is 0, n is 1, wherein about 0.1-33 mole percent of active isocyanate groups are reacted with the fluorinated monofunctional alcohol; the fluorinated polyisocyanate can be used with acrylic polymers, polyesters, alkyl resins, polyols and the like to form coating compositions, sealants, adhesives and the like.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgystan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

TITLE
FLUORINATED POLYISOCYANATES

BACKGROUND OF THE INVENTION

5 **1. Field of the Invention**

This invention is directed to fluorinated polyisocyanates that are useful in forming coating compositions, sealants and adhesives.

2. Description of the Prior Art


10 Fluorinated polyurethanes that are used as soil release agents are shown in Graham US Patent 3,759,874 issued September 18, 1973. Polyurethanes of fluorinated isocyanates that are used as adhesives are shown in Mitsch et al US Patent 3,972,856 issued August 3, 1976. Protective coatings of fluorinated polyurethanes of fluorinated diols or triols are shown in Re et al US Patent 4,782,130 issued November 1, 1988.

15 There is a need for fluorinated polyisocyanates that can be used with acrylic polymers, polyesters, alkyds, polyols to form coatings, adhesives, sealants and the like that can be applied with conventional equipment and cures to tough durable compositions without baking at elevated temperatures.

20

SUMMARY OF THE INVENTION

A fluorinated polyisocyanate of an organic polyisocyanate reacted with a fluorinated monofunctional alcohol represented by the formula



25

where R_f is a fluoroalkyl containing group having at least 4 carbon atoms, X is a divalent radical, R^3 is H or an alkyl group having 1-4 carbon atoms, n is 0-1 and m is 0-30 provided that when n is 0 then m must be equal to or greater than 1 and when m is 0 then n is 1; wherein about 0.1-33 mole percent of active isocyanate groups are reacted with the fluorinated monofunctional alcohol.

30

Compositions containing the fluorinated polyisocyanate and articles coated with such composition also are part of this invention.

35


DETAILED DESCRIPTION OF THE INVENTION

The fluorinated organic polyisocyanate is an adduct of a fluorinated monofunctional alcohol and a conventional organic

polyisocyanate. Any of the conventional aromatic, aliphatic, cycloaliphatic di and trifunctional polyisocyanates can be used. Typically useful diisocyanates are 1,6-hexamethylene diisocyanate, isophorone diisocyanate, 4,4'-biphenylene diisocyanate, toluene diisocyanate, bis cyclohexyl diisocyanate, tetramethylene xylene diisocyanate, ethyl ethylene diisocyanate, 2,3-dimethyl ethylene diisocyanate, 1-methyltrimethylene diisocyanate, 1,3-cyclopentylene diisocyanate, 1,4-cyclohexylene diisocyanate, 1,3-phenylene diisocyanate, 1,5-naphthalene diisocyanate, bis-(4-isocyanatocyclohexyl)-methane, 4,4'-diisocyanatodiphenyl ether and the like.


Typical trifunctional isocyanates that can be used are triphenylmethane triisocyanate, 1,3,5-benzene triisocyanate, 2,4,5-toluene triisocyanate and the like. Oligomers of diisocyanates also can be used such as the trimer of hexamethylene diisocyanate which is sold under the tradename "Desmodur" N. One particularly preferred oligomer is "Desmodur" N-3390.

Typical fluorinated monofunctional alcohols used to form the isocyanate functional adducts are represented by the formula




where R_f is as defined above, a fluoroalkyl containing group having at least 4 carbon atoms and preferably a straight chain or branched chain fluoroalkyl group having 4-20 carbon atoms which optionally can contain oxygen atoms as ether groups or can contain 1-5 chlorine atoms or 1-5 hydrogen atoms. Preferably, R_f is a perfluoroalkyl group having 4-20 carbon atoms and most preferably, R_f is a perfluoroalkyl group containing 6-12 carbon atoms. X is a divalent radical, preferably $-CH_2CH_2O-$, $-SO_2N(R^4)CH_2CH_2O-$, $-CH_2-$, $-O-$, $-CH_2O-$ where R^4 is an alkyl group preferably having 1-4 carbon atoms. R^3 is H or an alkyl group having 1-4 carbon atoms, H and methyl being preferred, n is 0-1 and m is 0-30, provided that if n is 0, then m must be greater than or equal to 1, if m is 0, then n is 1, if X is $-O-$, m must be greater than or equal to 1; m preferably is 1-20.

The following are preferred fluorinated monofunctional alcohols:




35

where R_f is a perfluoroalkyl group having 6-12 carbon atoms and n is 5-15;




where n is 1-6;



5

where R^5 is an alkyl group having 1-4 carbon atoms and n is 1-30;



where n is 0-10 and m is 1-20; and

10

$R_f-CH_2-CH_2-OH$ where R_f is described above.

The fluorinated organic polyisocyanate is prepared by conventional techniques in which the fluorinated monofunctional alcohol and organic polyisocyanate are charged into a reaction vessel optionally with solvents and a catalyst for about 0.1-4 hours and heated to about 50-120°C preferably, 60-85°C.

About 0.1-33 mole percent of active isocyanate groups of the organic polyisocyanate are reacted with the fluorinated monofunctional alcohol which leaves sufficient amount of unreacted isocyanate groups to react with functional groups of other components of a composition to form a crosslinked composition on curing. Preferably, about 0.1-10 mole percent of active isocyanate groups are reacted with the fluorinated monofunctional alcohol to provide a less costly fluorinated organic polyisocyanate which can be used with other film forming polymeric components having groups that are reactive with isocyanates to form crosslinked compositions.

Typical solvents that are used are alkyl acetates such as ethyl acetate, butyl acetate and the like, alkylene glycol alkyl ether acetates such as ethylene glycol, mono butyl ether acetate and the like.

Typical catalysts that are used are organo tin containing catalysts like alkyl tin laurates such as di-n-butyl tin dilaurate, dibutyl tin di-2-ethylhexoate, stannous octoate, stannous oleate and the like.

The fluorinated polyisocyanate when blended with another film forming binder is useful for forming coating compositions, adhesives, sealants, caulks and the like. Typical film forming binders are polymeric components having groups such as hydroxyl, carboxyl, epoxy amine, amide and the like that are reactive with an isocyanate such as acrylic polymers, polyesters, alkyd resins, polyethers, hydroxy or carboxyl containing polyurethanes and the like.

The fluorinated polyisocyanates are particularly useful in forming high quality coating compositions. These coating compositions can be clear coat compositions used over a pigmented base coat containing solid color pigments or metallic flake pigments or mixtures thereof and can be used as a conventional pigmented composition. The coating composition can be applied with conventional spray equipment and cured at ambient temperatures or slightly elevated temperatures which decrease drying time. The resulting finish whether clear or pigmented has excellent dirt, water and oil repellence, is easily cleaned by washing with water or a water surfactant mixture or can readily be wiped clean and has good stain resistance and good weatherability.

One useful coating composition is a clear coating composition, i.e. containing no pigments or a small amount of transparent pigment. The composition has a relatively high solids content of about 45-80% by weight of binder and about 20-55% by weight of an organic carrier which can be a solvent for the binder or a mixture of solvents and non solvent which would form a non aqueous dispersion. The composition has a low VOC (volatile organic content) and meets current pollution regulations.

Typically useful acrylic polymers that can be used to form the aforementioned coating compositions are formed by conventional polymerization procedures using conventional solvents and catalysts. Typical polymerizable monomers that are used to form these acrylic polymers are alkyl (meth)acrylates, meaning alkyl acrylates and alkyl methacrylates, having 1-18 carbon atoms in the alkyl group such as methyl methacrylate, ethyl acrylate, ethyl methacrylate, propyl acrylate, propyl methacrylate, isopropyl methacrylate, butyl acrylate, isobutyl methacrylate, butyl methacrylate, t-butyl methacrylate, pentyl acrylate, pentyl methacrylate, hexyl acrylate, hexyl methacrylate, octyl acrylate, octyl methacrylate, nonyl acrylate, nonyl methacrylate, decyl acrylate, decyl methacrylate, lauryl acrylate, lauryl methacrylate, stearyl acrylate, stearyl

methacrylate; other useful monomers are styrene, alpha methyl styrene, acrylamide, methacrylamide, acrylonitrile, hydroxy methacrylamide and the like or any mixtures of these monomers, and hydroxy alkyl (meth)acrylates meaning hydroxy alkyl acrylates and hydroxy alkyl methacrylates having 1-4 carbon atoms in the alkyl groups such as hydroxy methyl acrylate, hydroxy methyl methacrylate, hydroxy ethyl acrylate, hydroxy ethyl methacrylate, hydroxy propyl methacrylate, hydroxy propyl acrylate, hydroxy butyl acrylate, hydroxy butyl methacrylate and the like.

To improve weatherability of the coating composition, ultraviolet light stabilizers, screeners, quenchers and antioxidants can be added. Generally, the coating composition contains a catalyst such as an alkyl tin laurate to cure at ambient temperatures and often contains a flow control agent.

Coating compositions formulated with the fluorinated polyisocyanate can be used as a clear coating on a vehicle such as a car, truck, bus, train, or on construction equipment, industrial equipment, structures such as tanks, bridges, exterior or interior of buildings, a basecoating which may be either a solvent based or waterbased composition is first applied and then the clear coating is applied usually by conventional means such as spraying or electrostatic spraying. The clear coating is dried and cures at ambient temperatures but moderately high temperatures of up to about 90°C can be used to shorten drying time.

When the fluorinated polyisocyanate is used as a crosslinking agent in a clear coat that is used over a pigmented base coat, it is highly desirable to use at least some fluorinated polyisocyanate in the base coat to significantly reduce cratering in the base coat. Usually, about 10-40% by weight, based on the weight of the binder, of the fluorinated polyisocyanate is used in the base coat.

The following examples illustrate the invention. All parts and percentages are on a weight basis unless otherwise specified. Molecular weight was determined by gel permeation chromatography using polystyrene as the standard.

EXAMPLE 1

Fluorinated polyisocyanate solution I was prepared by mixing the following constituents in a reaction vessel equipped with a mechanical stirrer, condenser, nitrogen inlet and a thermocouple:

<u>Portion 1</u>	<u>Parts by Weight</u>
Aliphatic isocyanate resin - trimer of hexamethylene diisocyanate (98.9% solids)	3000.00
Butyl acetate	275.00
Ethyl acetate	550.00
Ethylene glycol monobutyl ether acetate	175.00
<u>Portion 2</u>	
Fluoroalkyl alcohol F(CF ₂) _n CH ₂ CH ₂ O(CH ₂ CH ₂ O) _m H where n is an average of 6 and m is an average of 7.5	27.20
Di-n-butyl tin dilaurate solution (2% solids in ethyl acetate)	<u>0.50</u>
Total	4027.70

Portions 1 and 2 were each added to the reaction vessel under a positive pressure of nitrogen and heated to about 75-80°C and held at this temperature for about 2 hours and allowed to cool overnight. The resulting fluorinated polyisocyanate solution I contained about 1% of the fluorinated component.

Fluorinated polyisocyanate solution II was prepared as above except the amount of the fluorinating component was reduced by 50% which resulted in a fluorinated polyisocyanate that contained 0.5% of the fluorinated component.

An acrylic polymer I solution was prepared in which the acrylic polymer has fluoro alkyl groups by charging the following constituents into a reactor equipped with a heat source, a thermometer and a stirrer:

<u>Portion 1</u>	<u>Parts By Weight</u>
Methyl amyl ketone	699.20
<u>Portion 2</u>	
Butyl methacrylate monomer (BMA)	583.80
Styrene monomer (S)	307.28
Butyl acrylate monomer (BA)	343.20
Hydroxy propyl acrylate monomer (HPA)	783.60
Methyl amyl ketone	4.72

Portion 3

Fluoroalkyl ethyl methacrylate monomer (FAMA) - (fluoroalkyl group containing C-4 about 4%, C-6 about 30%, C-8 about 30%, C-10 about 20%, C-12 about 10% C-14 and above about 5%)	30.73
--	-------

Methyl amyl ketone	30.00
--------------------	-------

Portion 4

T-butyl peroxy acetate	69.01
------------------------	-------

Methyl amyl ketone	114.59
--------------------	--------

Portion 5

Methyl amyl ketone	33.28
--------------------	-------

Total	2999.99
-------	---------

Portion 1 was charged into the reaction vessel and blanketed with nitrogen and Portion 2 was premixed and added over a 360 minute period while holding the resulting mixture at its reflux temperature of about 150°C. Portion 3 was premixed and then added at one time to the reaction mixture 350 minutes after the start of the addition of Portion 2. Portion 4 was premixed and added at the same time as Portion 2 to the reaction mixture over a 375 minute period and then Portion 5 was added and the reaction mixture was held at its reflux temperature for an additional 60 minutes. The resulting polymer solution was cooled to room temperature.

The resulting acrylic polymer solution I had a weight solids content of about 70%, a polymer of BMA/S/BA/HPA/FAMA in the following percentages 28.5%/15.0%/16.75%/38.25%/1.5% and the polymer had a weight average molecular weight of about 7,000.

A clear acrylic composition I was prepared as follows:

15

Parts by Weight

Portion 1

Methyl ethyl ketone	2.54
---------------------	------

Toluene	2.67
---------	------

Dibasic acid ester (ester mixture of adipic acid, glutaric acid and succinic acid)	1.79
--	------

Butyl Cellosolve Acetate	4.96
--------------------------	------

Portion 2

Acrylic polymer I solution (prepared above)	72.79
---	-------

Portion 3

Resiflow S (Acrylic polymer flow additive)	0.35
--	------

"Tinuvin" 328 - 2-(2-hydroxy-3,5-ditertiary amyl phenol) -2H-benzotriazole)	5.58
"Tinuvin" 292 - (1,2,2,6,6-pentamethyl-4-piperidiny1) sebacate	0.87
Dibutyl tin dilaurate	0.92
PM acetate	<u>7.38</u>
Total	100.00

The constituents of Portion 1 were charged into a mixing vessel in the order shown with continuous mixing. Portion 2 was added and mixed for 15 minutes. The constituents of Portion 3 were charged into the mixing vessel in the order shown with constant mixing. The resulting
5 composition had a solids content of about 53.5%.

A clear coating composition I was prepared by mixing the above clear acrylic composition I with a the above prepared fluorinated polyisocyanate solution I in a 3/1 volume ratio. Clear coating composition II was prepared by mixing the above clear acrylic composition I with the
10 above prepared fluorinated polyisocyanate solution II in a 3/1 volume ratio.

Two phosphated cold rolled steel panels that had been coated with a cured electrocoating composition of a polyepoxy hydroxy ether resin crosslinked with a polyisocyanate were spray coated with a white basecoat coating composition of an acrylic polymer containing an organic
15 polyisocyanate crosslinking agent to a dry film thickness of about 18-23 microns. The basecoat was allowed to stand for about 10 minutes to allow solvent to evaporate and then the above prepared clear coating composition I was spray applied. Two coats were applied with a solvent evaporation time of 2 minutes between the application of each coat. The resulting film
20 was dried at about 83°C for about 30 minutes. The dry film thickness of the clear coat was about 44-56 microns. The resulting clear coat was smooth and essentially free of craters and had an excellent appearance.

A second set of two panels was prepared. Phosphated cold rolled steel panel electrocoated with the same above described
25 electrocoating composition were coated with a black basecoat coating composition identical to the white basecoat coating composition except black pigmentation was used instead of white pigment and coated with the clear coating composition I as above and dried and cured as above. The resulting clear coat was smooth and essentially free of craters and had an
30 excellent appearance. The following properties of the clear coated panel

were measured and the results are shown in Table I: 20° Gloss and Distinctness of Image (DOI).

Acrylic polymer II solution was prepared which is identical to the above acrylic polymer I solution except that fluoroalkyl ethyl methacrylate monomer was not added. The molecular weight of the polymer and the solids of the solution were about the same. A clear coating composition III was prepared as above using fluorinated polyisocyanate solution I (prepared above) and acrylic polymer II solution was used in place of acrylic polymer I solution. Two panels of phosphatized cold rolled steel coated with the same electrocoating composition and with the same white base coat were sprayed with the clear acrylic coating composition III and cured as above. Also, two panels of phosphatized cold rolled steel coated with the same electrocoating composition and with the same black base coat were sprayed with the clear coating composition III and cured as above. The same properties were measured for both sets of panels as above and the results are shown in Table 1.

A clear coating composition IV was prepared as above using fluorinated polyisocyanate solution II (prepared above) and acrylic polymer II solution was used in place of acrylic polymer I solution. Two panels of phosphatized cold rolled steel coated with the same electrocoating composition and with the same white base coat were sprayed with the clear coating composition IV and cured as above. Also, two panels of phosphatized cold rolled steel coated with the same electrocoating composition and with the same black base coat were sprayed with the clear coating composition IV and cured as above. The same properties were measured for both sets of panels as above and the results are shown in Table 1.

TABLE 1

Clear Coat	Base Coat	20° gloss	DOI	Calculated PPM Fluorine in Composition
I	black	80.2	81.3	6500
I	black	86.6	89.2	6500
I	white	77.2	60.2	6500
I	white	83.2	67.4	6500
II	black	77.5	90.7	5600
II	black	85.3	91.3	5600

II	white	85.8	96.8	5600
II	white	86.1	89.2	5600
III	black	80.1	95.6	1700
III	black	81.7	95.7	1700
III	white	78.2	94.5	1700
III	white	76.9	90.0	1700
IV	black	76.5	97.1	900
IV	black	78.7	86.6	900
IV	white	80.0	96.3	900
IV	white	79.6	96.6	900

Each of the Clear Coats I-IV has excellent gloss and distinctness of image (DOI)

5 **EXAMPLE 2**

Fluorinated polyisocyanate solution III was prepared by mixing the following constituents in a reaction vessel equipped with a mechanical stirrer, condenser, nitrogen inlet and a thermocouple:

<u>Portion 1</u>	<u>Parts By Weight</u>
Aliphatic isocyanate resin (described in Example 1)	3,626.0
Butyl acetate	332.0
Ethyl acetate	665.0
Ethylene glycol monobutyl ether acetate	212.0
<u>Portion 2</u>	
Fluoroalkyl alcohol	116.0
[F(CF ₂ CF ₂) _n CH ₂ CH ₂ OH which is a blend of homologous series where 1-2% n = 2, 27-34% n = 3, 29-34% n = 4, 17-21% n = 5, 6-9% n = 6, 2-5% n = 7 and 1-2% n = 8]	
Di-n-butyl tin dilaurate (2% solids in ethyl acetate)	<u>0.5</u>
Total	4951.5

10 Portions 1 and 2 were each added to the reaction vessel under a positive pressure of nitrogen and heated to about 75-85°C and held at this temperature for about 2 hours and allowed to cool overnight. The resulting fluorinated polyisocyanate solution III contained about 2.5% of the fluorinated component.

15 A clear coating composition V was prepared by mixing the clear acrylic composition I, described in Example 1, with the above

fluorinated polyisocyanate solution III in a 3/1 volume ratio. Two phosphated cold rolled steel panels electrocoated as described in Example 1 were spray coated with a white base coat described in Example 1 and coated with the clear coating composition V and cured following the procedure of Example 1. The resulting clear coat was smooth and essentially free of craters and had an excellent appearance and had excellent soil resistance and was easily washed or wiped clean.

EXAMPLE 3

Fluorinated polyisocyanate solution IV was prepared by mixing the following constituents in a reaction vessel equipped with a mechanical stirrer, condenser, nitrogen inlet and a thermocouple:


<u>Portion 1</u>	<u>Parts By Weight</u>
Aliphatic isocyanate resin (described in Example 1)	3,064.0
Butyl acetate	281.0
Ethyl acetate	562.0
Ethylene glycol monobutyl ether acetate	179.0
<u>Portion 2</u>	
Fluoroalkyl alcohol	27.8
[Rf-CH ₂ CH ₂ -O-(CH ₂ CH ₂ O) _n -H where Rf is approximately 1% CF ₉ , 50-60% C ₆ F ₁₃ , 20-40% C ₈ F ₁₇ , 5-15% C ₁₀ F ₂₁ , 1-5% C ₁₂ F ₂₅ , n is 15-20]	
Di-n-butyl tin dilaurate (2% solids in ethyl acetate)	<u>0.5</u>
Total	4114.3

Portions 1 and 2 were each added to the reaction vessel under a positive pressure of nitrogen and heated to about 75-85°C and held at this temperature for about 2 hours and allowed to cool overnight.

A clear coating composition VI was prepared by mixing the clear acrylic composition I, described in Example 1, with the above fluorinated polyisocyanate solution IV in a 3/1 volume ratio. Two phosphated cold rolled steel panels electrocoated as described in Example 1 were spray coated with a white base coat described in Example 1 and coated with the clear coating composition VI and cured following the procedure of Example 1. The resulting clear coat was smooth and essentially free of craters and had an excellent appearance and had excellent soil resistance and was easily washed or wiped clean.

CLAIMS

1. A fluorinated polyisocyanate which comprises an organic polyisocyanate reacted with a fluorinated monofunctional alcohol
5 represented by the formula




where R_f is a fluoroalkyl containing group having at least 4 carbon atoms, X is a divalent radical, R³ is H or an alkyl group having 1-4 carbon atoms, n is 0-1 and m is 0-30, provided that when n is 0 then m must be equal to or
10 greater than 1 and when m is 0, then n is 1; wherein about 0.1-33 mole percent of active isocyanate groups are reacted with the fluorinated monofunctional alcohol.

2. The fluorinated polyisocyanate of claim 1 in which R_f is a
15 straight chain or branched chain perfluoroalkyl group having 4-20 carbon atoms.

3. The fluorinated polyisocyanate of claim 2 in which X is
20 -O-, -CH₂CH₂O-, -CH₂O-, -SO₂N(R⁴)CH₂CH₂O-, -CH₂- where R⁴ is an alkyl group having 1-4 carbon atoms, R³ is H or methyl, provided that when X is -O-, m must be equal to or greater than 1.

4. The fluorinated polyisocyanate of claim 1 in which the
25 organic polyisocyanate is an aromatic diisocyanate, aliphatic diisocyanate, cycloaliphatic diisocyanate, aromatic triisocyanate, aliphatic triisocyanate, cycloaliphatic triisocyanate or an oligomer of a diisocyanate.

5. A process for forming the fluorinated polyisocyanate of
30 claim 1 which comprises reacting a fluorinated monofunctional alcohol represented by the formula



where R_f is a fluoroalkyl group containing at least 4 carbon atoms, X is a divalent radical, R³ is H or an alkyl group having 1-4 carbon atoms, n is 0-1
35 and m is 0-30, provided that when n is 0 then m must be equal to or greater than 1 and when m is 0, then n is 1, with an organic polyisocyanate in the

presence of a catalyst and reacting about 0.1-33 mole percent of active isocyanate groups with the fluorinated monofunctional alcohol.

5 6. A composition comprising the fluorinated polyisocyanate of claim 1 and a film forming polymeric binder.

10 7. The composition of claim 6 in which the binder is an acrylic polymer, a polyester, an alkyd resin, a polyol or mixture of any of the above.

15 8. The composition of claim 6 in which the composition contains a solvent for the fluorinated polyisocyanate and polymeric binder.

 9. The composition of claim 7 which is an adhesive.

15

 10. The composition of claim 6 which is a sealant.

20 11. A substrate having a coating of pigmented base coat containing about 10-40% by weight, based on the weight of binder in the base coat, and a clear layer of a coating composition comprising a polymeric film forming binder and the fluorinated polyisocyanate of claim 1.

25

INTERNATIONAL SEARCH REPORT

International Application No
PC1/US 96/16270

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08G18/80 C09D175/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C08G C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	EP,A,0 719 809 (BAYER) 3 July 1996 see page 2, line 31 - page 4, line 14; claims 1-6; examples 1-7 ---	1-11
X	EP,A,0 605 105 (IMPERIAL CHEMICAL INDUSTRIES) 6 July 1994 see page 2, line 38 - page 4, line 54 see page 6, line 44 - page 8, line 9; claims 1-7; examples 1,3,5,7 ---	1-5
A	EP,A,0 480 089 (DAINICHISEIKA COLOR & CHEMICALS) 15 April 1992 see page 17, line 44 - page 19, line 8 ---	1
A	EP,A,0 540 976 (BAYER) 12 May 1993 see page 2, line 36 - page 6, line 10; claims 1,2; examples 6-10 ---	1
	-/--	

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

20 January 1997

Date of mailing of the international search report

12. 02. 97

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Bourgonje, A

INTERNATIONAL SEARCH REPORT

International Application No

PCI/US 96/16270

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>CHEMICAL ABSTRACTS, vol. 105, no. 9, November 1986 Columbus, Ohio, US; abstract no. 154760w, HAYASHI ET AL : "FLUORINE-CONTAINING ISOCYANATES FOR SURFACE FINISHING" page 89; column 2; XP002023089 see abstract & JP,A,61 063 646 (SAN NOPCO/SANYO CHEMICAL)</p> <p style="text-align: center;">-----</p>	1

1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No PCT/US 96/16270
--

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-719809	03-07-96	US-A- 5541281 CA-A- 2163590	30-07-96 21-06-96

EP-A-605105	06-07-94	AU-B- 665284 AU-A- 5212293 CA-A- 2110894 CN-A- 1090857 JP-A- 7070270 US-A- 5393799	21-12-95 14-07-94 01-07-94 17-08-94 14-03-95 28-02-95

EP-A-480089	15-04-92	US-A- 5321083 DE-D- 69027432	14-06-94 18-07-96

EP-A-540976	12-05-93	DE-A- 4136768 CA-A- 2082366 JP-A- 5255470 US-A- 5254660	13-05-93 09-05-93 05-10-93 19-10-93
