




(22) 1991/12/05

(43) 1992/06/07

(45) 2001/04/10

(72) Dessauer, Guido, DE

(72) Horn, Ute, DE

(73) BRABON GMBH & CO. KG, DE

(51) Int.Cl.⁵ C09D 1/00

(30) 1990/12/06 (P 40 38 886.7) DE

(54) **PHYLLOSILICATES ORGANOPHILES RENFERMANT DE
L'EAU**

(54) **WATER-CONTAINING ORGANOPHILIC PHYLLOSILICATES**

(57) The invention relates to the use of water-containing organophilic phyllosilicates obtained by the reaction of a phyllosilicate, which is completely delaminated colloiddally in water and is capable of cation exchange, with an organic onium salt in aqueous suspension and subsequent mechanical removal of the water, without drying by heating, as a rheological additive in organic media. The water-containing organophilic phyllosilicates are particularly suitable for coating paper.

Abstract of the Disclosure**Water-containing organophilic phyllosilicates**

The invention relates to the use of water-containing organophilic phyllosilicates obtained by the reaction of a phyllosilicate, which is completely delaminated colloiddally in water and is capable of cation exchange, with an organic onium salt in aqueous suspension and subsequent mechanical removal of the water, without drying by heating, as a rheological additive in organic media.

The water-containing organophilic phyllosilicates are particularly suitable for coating paper.

Description

Water-containing organophilic phyllosilicates


5 It is widely known that organophilically modified
phyllosilicates can be employed as rheological additives
in organic media. Examples of these are the commercial
products marketed under the names [®]Tixogel (manufacturer:
Südchemie AG) and [®]Bentone. These rheological additives
10 have the effect of the build-up of a thixotropic struc-
ture in organic media, for example in paints and var-
nishes. As a result of this thixotropic structure, such
organic media are easier to process. The organophilically
modified phyllosilicates are obtained by treating phyllo-
silicates in aqueous suspension with an aqueous solution
15 of an onium compound, preferably a quaternary organic
ammonium salt, this organic ammonium salt being embedded
between the layers of the phyllosilicate. The phyllo-
silicate organophilically modified in this manner is then
separated from the water by filtration and dried under
20 the action of heat, for example in a drum drier at about
100°C. The modified organophilic phyllosilicates obtained
in this manner are water-insoluble.

Such a drying operation has previously been considered
necessary, since the filtercake obtained when the water
25 is filtered off contains considerable amounts of water,
and this water content has been said to interfere in the
use of the organophilic phyllosilicates in the organic
media. It has now been found, surprisingly, that this is
not the case and that the filtercake of such organophilic
30 phyllosilicates can be employed as a rheological additive
in organic media even without being dried.

The invention thus relates to the use of water-containing
organophilic phyllosilicates which are obtained by the
reaction of a phyllosilicate, which is completely
35 delaminated colloiddally in water and is capable of cation
exchange, with an organic onium salt in aqueous

suspension and subsequent mechanical removal of the water, without drying by heating, as a rheological additive in organic media and for coating paper.

These organophilic phyllosilicates are obtained by methods which are known per se, which therefore do not have to be explained in more detail. Possible phyllosilicates which are capable of cation exchange and are completely delaminated colloiddally in water are all the synthetic or naturally occurring smectic phyllosilicates, preferably bentonite or montmorillonite, which, in addition to a smectic phyllosilicate, can also contain 25-30% by weight of impurities in the form of other minerals. The minerals are treated with an aqueous solution of onium compounds, such as, for example, phosphonium compounds, but preferably quaternary organic ammonium salts, these compounds being embedded between the layers of these minerals. Possible quaternary organic ammonium salts are, in particular, compounds of the formula



in which R^1 is C_8 - C_{22} -alkyl or C_8 - C_{22} -alkenyl, R^2 is C_1 - C_4 -alkyl and A is an anion, preferably chloride or methosulfate. The compound distearyl-dimethyl-ammonium chloride is particularly preferred. When the phyllosilicate is charged with the quaternary organic ammonium salt, the water is filtered off or pressed off. This is done by the customary processes of separation. The filtercake obtained consists, depending on the purity of the phyllosilicates, to the extent of about 65 to 83% of water and is employed according to the invention in this form directly as a rheological additive in organic media.

Examples of organic media in the sense of this invention

are paints, varnishes, coatings, putties, lubricating greases, cosmetics, paint removers, filler compositions and similar formulations containing organic solvents. The water-containing organophilically modified phyllosilicates according to the invention have a thixotroping effect in all these systems. As a result of this effect, the formulations mentioned are easier to process. In addition, these phyllosilicates also prevent settling of the insoluble components, for example the pigments within these media. As another surprising effect of these water-containing organophilic phyllosilicates it has been found that the thickening action here is significantly higher in comparison with the analogous commercially available products having the same solids content, but from which the water has been removed by drying by heating.

These water-containing organophilically modified phyllosilicates are added to the organic media by methods which are known per se. The amount of these rheological additives also lies within the range known to the expert in this field (about 0.5 to 3% by weight).

The water-containing organophilic phyllosilicates according to the invention are particularly suitable for coating paper. From economic considerations, efforts are made to use thin printing papers for printed products with a high circulation, for example newspapers or mail-order catalogs. However, problems arise here in respect of opacity, i.e. in the case of printing the print shows through in an interfering manner on the other side of the paper. To prevent this effect, it is already known (EP 192 252) that paper can be coated with an organophilic complex of a smectic phyllosilicate and a quaternary organic ammonium compound from a suspension in organic solvents. The starting material is present here in a form from which as much of the water as possible has been removed by heating. In the context of the present invention, it has now been found that drying of the organophilically modified phyllosilicate can be dispensed

with in this process (solvent coating) and the water-containing presscake of this organophilically modified phyllosilicate can be employed directly. It is surprising here that the water in the presscake does not interfere with the homogeneity of the overall organic system. The water remains in the inner phase, and no swelling of the paper fibers occurs, as would be the case with an aqueous coating. This finding is therefore of relatively great importance, since in future such "solvent coating" processes based on toluene or white spirit will gain increasing importance. The solids content (i.e. without the content of water from the presscake) of such suspensions is about 3 to 9% by weight. These "solvent coating" suspensions can furthermore also contain white pigments (TiO_2). As a result of the ability of the organophilically modified phyllosilicates to form films, these white pigments are bonded firmly to the paper by the phyllosilicates; no additional binder is therefore needed. A good hold-out effect is obtained in this manner, i.e. print-through on the printed paper is prevented.

Examples

A commercially available, non-purified Na bentonite (exchange capacity 80 milliequivalents/100 g) was stirred in a hot solution of distearyl-dimethyl-ammonium chloride at a ratio of the two products of 69% by weight of Na bentonite and 31% by weight of quaternary organic ammonium salt. When the reaction had ended, the mixture was filtered and the now organophilically modified bentonite was pressed off to a solids content of about 31% by weight. This filtercake was dispersed in toluene and the dispersion was applied in a thin layer to a sheet of paper and dried. The details of the examples and the particular evaluation of the hold-out effect can be seen from the following Tables 1 and 2.

As the examples show, a very good hold-out effect is

obtained with the water-containing organophilic phyllosilicates according to the present invention. The examples in the table show that customary white pigments can also be applied to the paper and firmly anchored there by means of the dispersion of the organophilically modified phyllosilicate in toluene; no additional binder is required here.

Table 1

10		1	2	3
	Toluene Filtercake	87.5 g 12.5 g	85 g 15 g	82.5 g 17.5 g
15	Brookfield viscosity in mPas at 100 rpm after 2 days	308	528	720
20	Weight applied (g/m ²)	1.5-1.8	1.6-1.7	1.4-1.6
	Hold-out	good	good	good
25	Weight applied (g/m ²)	2.3-2.5	2.8-3.0	2.5-2.7
	Hold-out	very good	best	very good

Table 2

		3	4	5
5	Toluene	to 100	to 100	to 100
	Filtercake	15 g	15 g	15 g
10	Titanium dioxide		0.4 g	
	China clay			0.4 g
	Optical brightener			0.1 g
15	Brookfield viscosity in mPas at 100 rpm after 2 days	298	324	216
20	Weight applied g/m ²)	1.3	1.4	1.5
	Hold-out	good	good	good

23589-146

7

CLAIMS:

1. The use of a water-containing organophilic phyllosilicate obtained by the reaction of a phyllosilicate, which is completely delaminated colloidally in water and is capable of cation exchange, with an organic onium salt in aqueous suspension and subsequent mechanical removal of the water, without drying by heating, as a rheological additive in organic media.
2. The use of a water-containing organophilic phyllosilicate obtained as claimed in claim 1 for coating paper from a suspension in an organic solvent.
3. The use as claimed in claim 1 or 2, wherein the phyllosilicate used for the reaction with the onium salt is a Na bentonite.
4. The use as claimed in claim 1, wherein the organic onium salt is an organic quaternary ammonium salt.
5. The use as claimed in claim 1 or 2, wherein the onium salt is distearyl-dimethyl-ammonium chloride.
6. An organic medium containing a water-containing organophilic phyllosilicate obtained by the reaction of a phyllosilicate, which is completely delaminated colloidally in water and is capable of cation exchange, with an organic onium salt in aqueous suspension and subsequent mechanical removal of the water without drying by heating.
7. The organic medium of claim 6 for use in coating paper from a suspension in an organic solvent.
8. The organic medium of claim 6 or 7 wherein the phyllosilicate used for the reaction with the onium salt is a Na bentonite.

23589-146

8

9. The organic medium of claim 6, 7 or 8 wherein the organic onium salt is an organic quaternary ammonium salt.

10. The organic medium of any one of claims 6 to 9 wherein the onium salt is distearyl-dimethyl-ammonium chloride.

5 11. A method of preparing an organic medium containing a water-containing organophilic phyllosilicate comprising the steps of:

- 10 a) preparing a water-containing organophilic phyllosilicate obtained by the reaction of a phyllosilicate which is completely delaminated colloiddally in water and is capable of cation exchange, with an organic onium salt in aqueous suspension and subsequent mechanical removal of the water without drying by heating; and
- 15 b) adding the water-containing organophilic phyllosilicate of step a) to an organic medium.

FETHERSTONHAUGH & CO.

OTTAWA, CANADA

PATENT AGENTS