

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 144 518 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:

31.03.2004 Bulletin 2004/14

(21) Application number: **00901116.4**

(22) Date of filing: **18.01.2000**

(51) Int Cl.7: **C09D 5/16**

(86) International application number:
PCT/EP2000/000398

(87) International publication number:
WO 2000/043460 (27.07.2000 Gazette 2000/30)

(54) **ANTIFOULING PAINT**

ANWUCHSVERHINDERNDE ÜBERZUGSZUSAMMENSETZUNG

PEINTURE ANTISALISSURE

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**

(30) Priority: **20.01.1999 EP 99300378**

(43) Date of publication of application:
17.10.2001 Bulletin 2001/42

(73) Proprietor: **Akzo Nobel N.V.**
6824 BM Arnhem (NL)

(72) Inventors:

- **FOX, John**
Walsend Tyne and Wear NE28 9YH (GB)
- **FINNIE, Alistair Andrew**
Whitley Bay Tyne and Wear NE25 8QH (GB)

(74) Representative: **Schalkwijk, Pieter Cornelis et al**
Akzo Nobel N.V.
Intellectual Property Department
P.O. Box 9300
6800 SB Arnhem (NL)

(56) References cited:

EP-A- 0 343 897	EP-A- 0 449 817
EP-A- 0 526 441	EP-A- 0 617 096
EP-A- 0 779 304	FR-A- 2 385 779

- **DATABASE WPI Week 8927 Derwent**
Publications Ltd., London, GB; AN 195192
XP002106644 "antifouling paint resin
composition" & JP 01 131286 A (CHUGOKU/DAI
NIPPON INK AND CHEMICALS) 24 May 1989
(1989-05-24)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] This invention relates to antifouling paint. An antifouling paint is used as a top coat on ships' hulls to inhibit the settlement and growth of marine organisms such as barnacles and algae, generally by release of a biocide for the marine organisms.

[0002] Traditionally, antifouling paints have comprised a relatively inert binder with a biocidal pigment which is leached from the paint. Among the binders which have been used are vinyl resins and rosin. The vinyl resins are seawater-insoluble and paints based on them use a high pigment concentration so that there is contact between pigment particles to ensure leaching. Rosin is a hard brittle resin which is very slightly soluble in seawater. Rosin-based antifouling paints have been referred to as soluble matrix or eroding paints. The biocidal pigment is very gradually leached out of the matrix of rosin binder in use, leaving a skeletal matrix of rosin which becomes washed off the hull surface to allow leaching of the biocidal pigment from deep within the paint film.

[0003] Many successful antifouling paints in recent years have been "self-polishing copolymer" paints based on a polymeric binder to which biocidal tri-organotin moieties are chemically bound and from which the biocidal moieties are gradually hydrolyzed by seawater, as described for example in GB-A-1457590. Self-polishing copolymer paints which release non-biocidal moieties are described in EP-A-69559, EP-A-204456, EP-A-529693, EP-A-779304, WO-A-91/14743, WO-A-91/09915, GB-A-231070 and JP-A-9-286933.


[0004] US-A-4675051 describes a marine antifouling paint which is gradually dissolved in seawater and which comprises a binder which is a resin produced by the reaction of rosin and an aliphatic polyamine containing at least one primary or secondary amine group. EP-A-802243 describes a coating composition comprising a rosin compound, a polymer containing organosilyl ester groups and an antifoulant.

[0005] Rosin is not a very good film-former, and it is known to add other film-forming resins to rosin based antifouling paints. This has sometimes led to paints which were difficult to wash off the hull surface. The present invention seeks to improve rosin-based antifouling paints with respect to the strength of the paint film and/or the reliable eroding away of the rosin-based paint matrix after biocide has been leached from the paint.


[0006] An antifouling paint according to the present invention has a binder comprising a rosin material and an auxiliary film-forming resin, the paint including an ingredient having marine biocide properties, characterized in that the binder comprises a blend of the rosin material and an auxiliary film-forming resin in ratio 20:80 to 95:5% by weight, the auxiliary film-forming resin comprising 20-100% by weight of an acid-functional film-forming polymer (A) whose acid groups are blocked by groups capable of hydrolyzing or dissociating to leave a polymer soluble in sea water, the blocking groups being selected from divalent metal atoms bonded to a monovalent organic residue, divalent metal atoms bonded to a hydroxyl residue and monoamine groups which form an organic solvent soluble amine salt of the polymer, and 80-0% by weight of a non-hydrolyzing water-insoluble film-forming polymer (B).

[0007] The rosin material is preferably rosin, particularly wood rosin or alternatively tall rosin or gum rosin. The main chemical constituent of rosin is abietic acid. The rosin can be any of the grades sold commercially, preferably that sold as WW (water white) rosin. The rosin material can alternatively be a rosin derivative, for example a maleinised or fumarised rosin, hydrogenated rosin, formylated rosin or polymerised rosin, or a rosin metal salt such as calcium, magnesium, copper or zinc rosinate.




[0008] The film-forming polymer (A) capable of hydrolyzing or dissociating to a polymer soluble in sea water is most preferably a hydrolysable polymer having at least one side chain bearing at least one terminal group of the formula:



wherein X represents




M is a metal selected from zinc, copper and tellurium; x is an integer of 1 to 2; R represents an organic residue selected from




and R1 is a monovalent organic residue, as described in EP-A-204456.

[0009] Such a hydrolysable polymer is preferably an acrylic polymer in which X represents



M is copper and R represents



The parent acrylic polymer having a -COOH group in place of -X-[O-M-R]_x preferably has an acid value of 25-350 mg KOH/g. Most preferably the hydrolysable polymer has a copper content of 0.3-20% by weight and R¹ is the residue of a high boiling organic monobasic acid. Such hydrolysable polymers can be prepared by the processes of EP-A-204456 and EP-A-342276. The copper-containing film-forming polymer (A) is preferably a copolymer comprising an acrylic or methacrylic ester whose alcohol residue includes a bulky hydrocarbon radical or a soft segment, for example a branched alkyl ester having 4 or more carbon atoms or a cycloalkyl ester having 6 or more atoms, a polyalkylene glycol monoacrylate or monomethacrylate optionally having a terminal alkyl ether group or an adduct of 2-hydroxyethyl acrylate or methacrylate with caprolactone, as described in EP-A-779304.

[0010] The hydrolysable film-forming polymer (A) can alternatively be a carboxylic acid-functional polymer, for example a copolymer of acrylic or methacrylic acid with one or more alkyl acrylate or methacrylate, at least some of the acid groups of which have been converted to groups of the formula -COO-M-OH, where M is a divalent metal such as copper, zinc, calcium, magnesium or iron, as described in GB-A-2311070.

[0011] The film-forming polymer (A) can alternatively be a salt of an amine, preferably an amine containing at least one aliphatic hydrocarbon group having 8 to 25 carbon atoms and an acid-functional film-forming polymer as described in EP-A-529693. The acid-functional polymer is preferably an addition copolymer of an olefinically unsaturated carboxylic acid, sulphonic acid, acid sulphate ester, phosphonic acid or acid phosphate ester and at least one olefinically unsaturated co-monomer. The unsaturated carboxylic acid can for example be acrylic or methacrylic acid. The unsaturated sulphonic acid can for example be 2-acrylamido-2-methylpropane sulphonic acid (AMPS), for example the film-forming polymer (A) may preferably be an amine sulphonate copolymer containing units of an organocyclic ester as described in our co-pending application GB 9801747.8.

[0012] The non-hydrolyzing water-insoluble film-forming polymer (B) can for example be a vinyl ether polymer, for example a poly(vinyl alkyl ether) or a copolymer of a vinyl alkyl ether with vinyl acetate or vinyl chloride, an acrylate ester polymer such as a homopolymer or copolymer of one or more alkyl acrylates or methacrylates which preferably contain 1 to 6 carbon atoms in the alkyl group and may contain a co-monomer such as acrylonitrile or styrene, or a vinyl acetate polymer such as polyvinyl acetate or a vinyl acetate vinyl chloride copolymer. The polymer (B) can alternatively be a polyamine, particularly a polyamide having a plasticising effect such as a polyamide of a fatty acid dimer or the polyamide sold under the Trademark "Santiciser".

[0013] We have found that the paints of the invention have the optimum combination of film-forming and eroding properties when the non-hydrolyzing water-insoluble film-forming polymer (B) is present in the composition, albeit as a minor proportion of the auxiliary film-forming resin. Most preferably the weight ratio of rosin to total auxiliary film-

forming resin is from 25:75, 50:50 or 55:45 up to 80:20. The hydrolyzing or dissociating film-forming polymer (A) preferably forms at least 30, most preferably at least 50, up to 80 or 90% by weight of the auxiliary film-forming resin, the non-hydrolyzing water-insoluble polymer (B) being the remainder.

[0014] The antifouling paint can include a non-polymeric plasticiser. Such a plasticiser can for example be present at up to 50% by weight based on the total binder polymer, most preferably at least 10% and up to 35% by weight based on binder polymer. Examples of such plasticisers are phthalate esters such as dibutyl phthalate, butyl benzyl phthalate or dioctyl phthalate, phosphate triesters such as tricresyl or tris(isopropyl)phenyl phosphate, or chlorinated paraffins.

[0015] The rosin and the polymers forming the auxiliary film-forming resin can be mixed in a common solvent which forms at least part of the paint solvent, for example an aromatic hydrocarbon such as xylene, toluene or trimethylbenzene, an alcohol such as n-butanol, an ether alcohol such as butoxyethanol or methoxypropanol, an ester such as butyl acetate or isoamyl acetate, an ether-ester such as ethoxyethyl acetate or methoxypropyl acetate, a ketone such as methyl isobutyl ketone or methyl isoamyl ketone, an aliphatic hydrocarbon such as white spirit, or a mixture of two or more of these solvents. The paint can alternatively be water-based, for example it can be based on a commercial aqueous rosin dispersion.

[0016] The binder may be the ingredient having marine biocide properties (for example some long chain amines used to form amine salt copolymers are biocidal) but more usually the binder is mixed with a biocide for aquatic organisms and usually with a pigment using conventional paint-blending techniques. The biocide may itself be all or part of the pigment of the paint. The coating composition preferably has a pigment volume concentration of, for example, 15 to 55%. The pigment preferably comprises at least one sparingly soluble metalliferous pigment having a solubility in seawater of from 0.5 to 10 parts per million by weight. Examples of such pigments which are also aquatic biocides include copper or zinc compounds, such as cuprous oxide, cuprous thiocyanate, cuprous sulphate, zinc ethylene bis(dithiocarbamate), zinc dimethyl dithiocarbamate, zinc pyrithione, copper pyrithione, zinc diethyl dithiocarbamate, copper resinate or cuprous ethylene bis(dithiocarbamate). Other sparingly soluble pigments having a solubility in sea water of 0.5 to 10 parts per million include barium sulphate, calcium sulphate, dolomite and zinc oxide. Mixtures of sparingly soluble pigments can be used, for example cuprous oxide, cuprous thiocyanate or zinc ethylene bis(dithiocarbamate), which are highly effective biocidal pigments, can be mixed with zinc oxide, which is not effective as a biocide but dissolves slightly more rapidly in seawater. Copper metal can be present as an aquatic biocide, for example in flake or powder form.

[0017] The antifouling coating composition can contain a non-metalliferous biocide for marine organisms, for example tetramethyl thiuram disulphide, methylene bis(thiocyanate), captan, pyridiniumtriphenylboron, a substituted isothiazolone such as 4,5-dichloro-2-n-octyl-4-isothiazolin-3-one, 2-methylthio-4-t-butylamino-6-cyclopropylamino-s-triazine, N-3,4-dichlorophenyl-N',N'-dimethyl-urea ("Diuron"), 2-(thio-cyanomethylthio) benzothiazole, 2,4,5,6-tetrachloro-isophthalonitrile, dichlorofluanid, tolylfluanid or 2,3,5,6-tetrachloro-4-(methyl-sulphonyl)pyridine. Such a non-metalliferous biocide can be used as the only biocide of the coating in a copper-free, or even metal-free or pigment-free, antifouling coating. Many of these non-metalliferous biocides are solid and all are sparingly soluble in seawater and may help the "self-polishing" action of the paint.

[0018] The coating composition can additionally contain a pigment which is not reactive with seawater and may be highly insoluble in seawater (solubility below 0.5 part per million by weight) such as titanium dioxide or ferric oxide or an organic pigment such as phthalocyanine or azo pigment. Such highly insoluble pigments are preferably used at less than 60% by weight of the total pigment component of the paint, most preferably less than 40%. The coating composition can additionally contain conventional thickeners, particularly thixotropes such as silica or bentonite and/or stabilisers, for example zeolites or aliphatic or aromatic amines such as dehydroabietylamine.

[0019] The invention is illustrated by the following Examples:-

Examples 1 to 14

[0020] The following materials were mixed in the stated % by weight in a high speed disperser to form antifouling paints according to the invention.

Example No.:	1	2	3	4	5	6	7	8	9	10	11	12	13	14
Rosin	10.01	10.01	10.09	9.68	10.06	10.00	9.94	9.93	10.01	7.81	4.27	9.83	11.08	3.88
Hydrolysable acrylic Polymer (A1)	4.89	-	-	6.66	5.54	-	5.47	5.46	5.51	9.42	12.07	-	-	-
Hydrolysable acrylic Polymer (A2)	-	5.37	5.56	-	-	-	-	-	-	-	-	6.09	6.86	11.98
Hydrolysable acrylic Polymer (A3)	-	-	-	-	-	4.37	-	-	-	-	-	-	-	-
Non-hydrolyzing acrylic polymer (B1)	1.72	1.30	-	-	-	-	1.18	1.18	1.19	2.03	2.50	0.58	0.65	1.14
Non-hydrolyzing acrylic polymer (B2)	-	-	1.11	-	1.11	1.10	-	-	-	-	-	-	-	-
Tris(isopropylphenyl) phosphate plasticiser	5.11	5.11	5.15	4.95	5.14	5.11	5.08	5.07	5.11	2.13	2.03	-	-	4.08
Red copper oxide	37.58	37.55	37.87	36.34	37.83	37.59	37.38	37.33	37.65	36.04	34.24	-	-	-
Purple copper oxide	-	-	-	-	-	-	-	-	-	-	-	38.70	39.56	36.06
Zinc Oxide	11.92	11.91	12.01	11.52	11.96	11.88	11.81	11.80	11.92	11.39	10.82	12.25	12.52	11.41
Zinc ethylene bis(dithiocarbamate)	2.88	2.88	-	-	-	4.10	-	4.08	-	1.97	-	-	-	-
Zinc pyrithione	-	-	1.94	1.86	-	-	-	-	-	-	-	-	-	-
Copper pyrithione	-	-	-	-	-	-	3.95	-	-	-	3.62	-	-	-
Organic biocide (C1)	0.76	0.76	1.28	1.23	-	-	-	-	-	-	-	-	-	-
Organic biocide (C2)	-	-	-	-	2.39	-	-	-	-	-	-	-	-	-
Dichlorofluanid	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Synthetic iron oxide	2.81	2.81	2.59	6.18	4.10	4.07	-	-	3.46	1.66	-	2.95	3.02	2.75
Natural iron oxide	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Carbon black	-	-	-	-	-	-	3.56	3.56	3.59	3.43	3.71	-	-	-
Solvent	19.61	19.61	19.69	20.59	19.66	19.57	19.43	19.4	19.34	22.00	24.72	18.71	19.5	25.74
Additives	2.70	2.70	2.60	0.98	2.23	2.22	2.20	2.20	2.22	2.12	2.02	2.18	2.23	2.03

[0021] Acrylic polymer A1 is an acrylic acid copolymer substantially according to Production Example 1 of EP-A-779304 in which the acrylic acid units are blocked by copper atoms bound to naphthenic acid residues.

[0022] Acrylic polymer A2 is similar to A1 but is based on an acrylic acid copolymer having a higher content of methoxypolyethylene glycol methacrylate.

5 [0023] Acrylic polymer A3 is a copolymer of the methyl bis (hydrogenated tallow) amine salt of 2-acrylamido-2-methylpropanesulphonic acid, isobornyl methacrylate and isobornyl acrylate in mole ratio 27.5:47.5:25.

[0024] Acrylic polymer B1 is an alkyl acrylate ester polymer sold under the Trademark "Paraloid B66".

Acrylic polymer B2 is a n-butyl acrylate polymer sold under the Trademark "Acronal 4F".

10 Organic biocide C1 is 4,5-dichloro-2-n-octyl-4-isothiazoline-3-one. Organic biocide C2 is sold under the Trademark "Irgarol 1051".

[0025] The solvent comprised mainly xylene with minor amounts of methyl isoamyl ketone, methyl isobutyl ketone and n-butanol. The rosin and acrylic polymers were dissolved in solvent before being mixed with the other paint ingredients.

[0026] Additives comprised an organo-clay structuring agent, silica, carbon black and molecular sieve zeolite.

15 [0027] As a test of antifouling performance the paints of Examples 1-14 were each applied to plywood boards which had been pre-painted with a commercial anticorrosive primer and the boards were immersed in the sea at Newton Ferrers, Devon, England, Burnham-on-Crouch, Essex, England and Singapore. As a comparative test, primed boards were coated with a rosin paint having a formulation similar to Example 1 but containing extra "Paraloid B66" in place of the hydrolysable acrylic polymer. These boards were immersed at the same time and at the same sites as comparisons to both Examples 1 and 2; the paints of Examples 3 to 14 were immersed similarly but not in a comparative experiment. The paint films were periodically assessed for settlement of marine fouling organisms and the results are shown below.

[0028] In all results quoted below, 100 = Totally clean, 0 = Totally fouled.


Example	Average fouling rating	number of sites
1	76.4	6
Comparative 1	70.6	6
2	71.3	3
Comparative 2	59.0	3
3	84.2	3
4	83.3	3
5	87.0	2
6	76.3	6
7	86.5	4
8	88.0	4
9	88.0	4
10	-	-
11	-	-
12	84.3	3
13	84.0	1
14	89.3	3

Claims


1. An antifouling paint having a binder comprising a rosin material and an auxiliary film-forming resin, the paint including an ingredient having marine biocide properties, **characterised in that** the binder comprises a blend of the rosin material and an auxiliary film-forming resin in ratio 20:80 to 95:5% by weight, the auxiliary film-forming resin comprising 20-100% by weight of an acid-functional film-forming polymer (A) whose acid groups are blocked by groups capable of hydrolyzing or dissociating to leave a polymer soluble in sea water, the blocking groups being selected from divalent metal atoms bonded to a monovalent organic residue, divalent metal atoms bonded to a hydroxyl residue and monoamine groups which form an organic solvent soluble amine salt of the polymer, and 80-0% by weight of a non-hydrolyzing water-insoluble film-forming polymer (B).

2. An antifouling paint according to claim 1 **characterised in that** the rosin material is rosin.


3. An antifouling paint according to claim 1 or claim 2, **characterised in that** the binder comprises a blend of the rosin material and the auxiliary film-forming resin in a ratio of 55:45 to 80:20 by weight.
- 5 4. An antifouling paint according to any of claims 1 to 3, **characterised in that** the auxiliary film-forming resin comprises 30-90% by weight of the film-forming polymer (A) capable of hydrolyzing or dissociating to a polymer soluble in sea water and 70-10% by weight of the non-hydrolyzing water-insoluble film-forming polymer (B).
- 10 5. An antifouling paint according to any of claims 1 to 4, **characterised in that** the film-forming polymer (A) is a hydrolysable polymer having at least one side chain bearing at least one terminal group of the formula:




15 wherein X represents



20 M is a metal selected from zinc, copper and tellurium; x is an integer of 1 to 2; R represents an organic residue selected from




25 $-\text{O}-\text{R}_1$, $-\text{S}-\text{R}_1$ or




30 and R₁ is a monovalent organic residue.

- 35 6. An antifouling paint according to claim 5, **characterised in that** the hydrolysable polymer is an acrylic polymer in which X represents




40 M is copper and R represents




7. An antifouling paint according to any of claims 1 to 4, **characterised in that** the film-forming polymer (A) is a carboxylic acid-functional polymer, at least some of the acid groups of which have been converted to groups of the formula -COO-M-OH, where M is a divalent metal.
8. An antifouling paint according to any of claims 1 to 4, **characterised in that** the film-forming polymer (A) is a salt of an amine and an addition copolymer of an olefinically unsaturated sulphonic acid or acid sulphate ester and at least one olefinically unsaturated co-monomer.
9. An antifouling paint according to any of claims 1 to 4, **characterised in that** the film-forming polymer (A) is a salt of an amine and an addition copolymer of an olefinically unsaturated carboxylic acid and at least one olefinically unsaturated co-monomer.
10. An antifouling paint according to claim 7 or claim 8, **characterised in that** the amine contains at least one aliphatic hydrocarbon group having 8 to 25 carbon atoms.
11. An antifouling paint according to any of claims 1 to 9, **characterised in that** the non-hydrolyzing water-insoluble film-forming polymer (B) is an acrylate ester polymer or a vinyl ether polymer.
12. An antifouling paint according to any of claims 1 to 10, **characterised in that** the binder includes a non-polymeric plasticiser present at up to 50% by weight based on the total binder polymer.

Patentansprüche





1. Anwuchsverhindernde Streichmasse mit einem Bindemittel, das ein Kolophoniummaterial und ein filmbildendes Hilfsharz umfasst, wobei die Streichmasse einen Bestandteil mit bioziden Eigenschaften für Meerestiere enthält, **dadurch gekennzeichnet, dass** das Bindemittel ein Gemisch des Kolophoniummaterials und eines filmbildenden Hilfsharzes im Verhältnis 20:80 bis 95:5 Gew.-% umfasst, wobei das filmbildende Hilfsharz folgendes umfasst: 20-100 Gew.-% eines säurefunktionellen filmbildenden Polymers (A), dessen Säuregruppen durch Gruppen blockiert sind, die zur Hydrolyse oder Dissoziation befähigt sind, so dass ein in Meerwasser lösliches Polymer zurückbleibt, wobei die blockierenden Gruppen aus zweiwertigen Metallatomen, die an einen einwertigen organischen Rest gebunden sind, zweiwertigen Metallatomen, die an einen Hydroxylrest gebunden sind, und Monoaminingruppen, die ein in organischem Lösungsmittel lösliches Aminsalt des Polymers bilden, ausgewählt sind, und 80-0 Gew.-% eines nichthydrolisierenden wasserunlöslichen filmbildenden Polymers (B).
2. Anwuchsverhindernde Streichmasse gemäß Anspruch 1, **dadurch gekennzeichnet, dass** es sich bei dem Kolophoniummaterial um Kolophonium handelt.
3. Anwuchsverhindernde Streichmasse gemäß Anspruch 1 oder 2, **dadurch gekennzeichnet, dass** das Bindemittel ein Gemisch des Kolophoniummaterials und des filmbildenden Hilfsharzes in einem Verhältnis von 55:45 bis 80:20 Gew.-% umfasst.
4. Anwuchsverhindernde Streichmasse gemäß einem der Ansprüche 1 bis 3, **dadurch gekennzeichnet, dass** das filmbildende Hilfsharz 30-90 Gew.-% des filmbildenden Polymers (A), das zu einem in Meerwasser löslichen Polymer hydrolysieren oder dissoziieren kann, und 70-10 Gew.-% des nichthydrolisierenden wasserunlöslichen filmbildenden Polymers (B) umfasst.
5. Anwuchsverhindernde Streichmasse gemäß einem der Ansprüche 1 bis 4, **dadurch gekennzeichnet, dass** das filmbildende Polymer (A) ein hydrolysierbares Polymer ist, das wenigstens eine Seitenkette aufweist, die wenigstens eine terminale Gruppe der Formel



trägt, wobei X



darstellt, M ein Metall ist, das aus Zink, Kupfer und Tellur ausgewählt ist, x eine ganze Zahl von 1 bis 2 ist, R einen organischen Rest darstellt, der aus




ausgewählt ist, und R1 ein einwertiger organischer Rest ist.

6. Anwuchsverhindernde Streichmasse gemäß Anspruch 5, **dadurch gekennzeichnet, dass** das hydrolysierbare Polymer ein Acrylpolymer ist, wobei X



darstellt, M Kupfer ist und R




darstellt.

7. Anwuchsverhindernde Streichmasse gemäß einem der Ansprüche 1 bis 4, **dadurch gekennzeichnet, dass** das filmbildende Polymer (A) ein carboxysäurefunktionelles Polymer ist, von dessen Säuregruppen wenigstens einige in Gruppen der Formel —COO—M—OH umgewandelt wurden, wobei M ein zweiwertiges Metall ist.
8. Anwuchsverhindernde Streichmasse gemäß einem der Ansprüche 1 bis 4, **dadurch gekennzeichnet, dass** das filmbildende Polymer (A) ein Salz eines Amins und eines Additions-copolymers einer olefinisch ungesättigten Sulfonsäure oder eines olefinisch ungesättigten sauren Schwefelsäureesters und wenigstens eines olefinisch ungesättigten Comonomers ist.
9. Anwuchsverhindernde Streichmasse gemäß einem der Ansprüche 1 bis 4, **dadurch gekennzeichnet, dass** das filmbildende Polymer (A) ein Salz eines Amins und eines Additions-copolymers einer olefinisch ungesättigten Carbonsäure und wenigstens eines olefinisch ungesättigten Comonomers ist.


10. Anwuchsverhindernde Streichmasse gemäß Anspruch 7 oder 8, **dadurch gekennzeichnet, dass** das Amin wenigstens eine aliphatische Kohlenwasserstoffgruppe mit 8 bis 25 Kohlenstoffatomen enthält.
11. Anwuchsverhindernde Streichmasse gemäß einem der Ansprüche 1 bis 9, **dadurch gekennzeichnet, dass** das nichthydrolysierende wasserunlösliche filmbildende Polymer (B) ein Acrylsäureesterpolymer oder ein Vinyletherpolymer ist.
12. Anwuchsverhindernde Streichmasse gemäß einem der Ansprüche 1 bis 10, **dadurch gekennzeichnet, dass** das Bindemittel einen nichtpolymeren Weichmacher enthält, der in einer Menge von bis zu 50 Gew.-%, bezogen auf das gesamte Bindemittelpolymer, vorhanden ist.

Revendications



1. Peinture antisalissure ayant un liant comprenant un matériau colophane et une résine filmogène auxiliaire, la peinture comprenant un ingrédient ayant des propriétés de biocide marin, **caractérisée en ce que** le liant comprend un mélange de la matière colophane et d'une résine filmogène auxiliaire en un rapport de 20/80 à 95/5 % en poids, la résine filmogène auxiliaire comprenant de 20 à 100 % en poids d'un polymère filmogène (A) à fonctionnalité acide, dont les groupes acides sont bloqués par des groupes capables de s'hydrolyser ou de se dissocier pour laisser un polymère soluble dans l'eau de mer, les groupes bloquants étant choisis parmi des atomes de métal divalent liés à un résidu organique monovalent, des atomes de métal divalent liés à un résidu hydroxyle et des groupes monoamines qui forment un sel d'amine du polymère, soluble dans les solvants organiques, et de 80 à 0 % en poids d'un polymère filmogène (B) ne s'hydrolysant pas, insoluble dans l'eau.
2. Peinture antisalissure selon la revendication 1, **caractérisée en ce que** la matière colophane est la colophane.
3. Peinture antisalissure selon la revendication 1 ou 2, **caractérisée en ce que** le liant comprend un mélange de la matière colophane et de la résine filmogène auxiliaire en un rapport de 55/45 à 80/20 en poids.
4. Peinture antisalissure selon l'une quelconque des revendications 1 à 3, **caractérisée en ce que** la résine filmogène auxiliaire comprend de 30 à 90 % en poids du polymère filmogène (A) capable de s'hydrolyser ou de se dissocier en un polymère soluble dans l'eau de mer et de 70 à 10 % en poids du polymère filmogène (B) ne s'hydrolysant pas, insoluble dans l'eau.
5. Peinture antisalissure selon l'une quelconque des revendications 1 à 4, **caractérisée en ce que** le polymère filmogène (A) est un polymère hydrolysable ayant au moins une chaîne latérale portant au moins un groupe terminal de formule :



dans laquelle X représente




M est un métal choisi parmi le zinc, le cuivre et le tellure ; x est un nombre entier de 1 à 2 ; R représente un résidu organique choisi parmi




et R1 est un résidu organique monovalent.

6. Peinture antisalissure selon la revendication 5, **caractérisée en ce que** le polymère hydrolysable est un polymère acrylique dans lequel X représente



M est le cuivre et R représente



7. Peinture antisalissure selon l'une quelconque des revendications 1 à 4, **caractérisée en ce que** le polymère filmogène (A) est un polymère à fonctionnalité acide carboxylique, dont quelques-uns au moins des groupes acides ont été convertis en groupes de formule —COO—M—OH , où M est un métal divalent.
8. Peinture antisalissure selon l'une quelconque des revendications 1 à 4, **caractérisée en ce que** le polymère filmogène (A) est un sel d'une amine et d'un copolymère d'addition d'un ester sulfate d'acide ou acide sulfonique oléfiniquement insaturé et d'au moins un co-monomère oléfiniquement insaturé.
9. Peinture antisalissure selon l'une quelconque des revendications 1 à 4, **caractérisée en ce que** le polymère filmogène (A) est un sel d'une amine et d'un copolymère d'addition d'un acide carboxylique oléfiniquement insaturé et d'au moins un co-monomère oléfiniquement insaturé.
10. Peinture antisalissure selon la revendication 7 ou 8, **caractérisée en ce que** l'amine contient au moins un groupe hydrocarboné aliphatique ayant de 8 à 25 atomes de carbone.
11. Peinture antisalissure selon l'une quelconque des revendications 1 à 9, **caractérisée en ce que** le polymère filmogène (B) ne s'hydrolysant pas, insoluble dans l'eau, est un polymère d'ester acrylate ou un polymère d'éther vinylique.
12. Peinture antisalissure selon l'une quelconque des revendications 1 à 10, **caractérisée en ce que** le liant comprend un plastifiant non polymère présent en une quantité allant jusqu'à 50 % en poids, rapportée au polymère total du liant.