

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(10) International Publication Number

WO 2019/002120 A1

(43) International Publication Date
03 January 2019 (03.01.2019)

(51) International Patent Classification:
B29C 64/10 (2017.01) **B29C 70/58** (2006.01)
B33Y 10/00 (2015.01) **B29C 64/209** (2017.01)
B33Y 80/00 (2015.01) **B29C 64/118** (2017.01)
B29C 70/00 (2006.01)

(21) International Application Number:
PCT/EP2018/066739

(22) International Filing Date:
22 June 2018 (22.06.2018)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
17178720.3 29 June 2017 (29.06.2017) EP

(71) Applicant: **PHILIPS LIGHTING HOLDING B.V.**
[NL/NL]; High Tech Campus 45, 5656 AE Eindhoven
(NL).

(72) Inventors: **HIKMET, Rifat, Ata, Mustafa**; c/o High Tech Campus 45, 5656 AE Eindhoven (NL). **KOOPMANS, Loes, Johanna, Mathilda**; c/o High Tech Campus 45, 5656 AE Eindhoven (NL). **GRUHLKE, Stefan, Willi, Julius**; c/o High Tech Campus 45, 5656 AE Eindhoven (NL).

(74) Agent: **VAN EEUWIJK, Alexander, Henricus, Walterus** et al.; Philips Lighting B.V., Intellectual Property, High Tech Campus 45, 5656 AE Eindhoven (NL).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))

Published:

- with international search report (Art. 21(3))

(54) Title: FDM PRINTED LUMINAIRES WITH SURFACE TEXTURE




FIG. 5A

(57) **Abstract:** A method for 3D printing a 3D item (10), the method comprising (i) providing 3D printable material (201) comprising particles (410) embedded in the 3D printable material (201), wherein the particles (410) have a longest dimension length (L1), a shortest dimension length (L2), and an aspect ratio AR defined as the ratio of the longest dimension length (L1) and the shortest dimension length (L2), and (ii) depositing during a printing stage 3D printable material (201) to provide the 3D item (10) to provide layers (230) of the 3D printed material (202) with a layer height (H), wherein: (i) $1 < AR < 4$ and $1 < H/L2 < 100$.

FDM PRINTED LUMINAIRES WITH SURFACE TEXTURE

FIELD OF THE INVENTION

The invention relates to a method for manufacturing a 3D item. The invention also relates to the 3D (printed) item obtainable with such method. Further, the invention relates to a lighting system including such 3D (printed) item. Yet further, the invention also 5 relates to a 3D printable thermoplastic polymer material (for use in such method).

BACKGROUND OF THE INVENTION

Textured 3D printed materials are known in the art. WO2016/083181, for instance, describes a printing head for a 3D printing device that comprises a nozzle arranged 10 to print a layer of a printing material on a receiving surface and a texturing member arranged to texture the layer or the receiving surface during printing of said layer. The nozzle comprises an outlet including the texturing member and the outlet is shaped to form protrusions extending from a main surface of the layer for interlocking with a subsequent layer. The texturing member ensures that contacting layers formed with the printing head 15 exhibit improved adhesion due to the increased contact surface area between the layers. This yields stronger 3D articles printed in this manner. A printing apparatus including the printing head, a printing method, and a printed article are also described in this document.

US 2017120326 A1 discloses a method of making an shaped article with an injection molding manufacturing system. The method comprises molding a composite to 20 form a green preform, with the system comprising a heated injector and a mold cavity. The composite comprises a thermoplastic which comprises about 70 to 1 wt. % of a thermoplastic polymer; and about 99 to 30 wt. % of a particulate, dispersed in the polymer. The particulate has a particle size of less than 500 microns, and an exterior coating of interfacial modifier in an amount of about 0.02 to 2.0 wt. %, all percentages based on the weight of the composite. 25 The green preform is sintered to remove the polymer and bond the particulate to form the object. The particulate comprises a metal alloy particle, a ceramic particle, a bi-metal particle or blends thereof.

SUMMARY OF THE INVENTION

Within the next 10-20 years, digital fabrication will increasingly transform the nature of global manufacturing. One of the aspects of digital fabrication is 3D printing. Currently, many different techniques have been developed in order to produce various 3D printed objects using various materials such as ceramics, metals and polymers. 3D printing can also be used in producing molds which can then be used for replicating objects.

For the purpose of making molds, the use of polyjet technique has been suggested. This technique makes use of layer by layer deposition of photo-polymerizable material which is cured after each deposition to form a solid structure. While this technique produces smooth surfaces the photo curable materials are not very stable and they also have relatively low thermal conductivity to be useful for injection molding applications.

The most widely used additive manufacturing technology is the process known as Fused Deposition Modeling (FDM). Fused deposition modeling (FDM) is an additive manufacturing technology commonly used for modeling, prototyping, and production applications. FDM works on an "additive" principle by laying down material in layers; a plastic filament or metal wire is unwound from a coil and supplies material to produce a part. Possibly, (for thermoplastics for example) the filament is melted and extruded before being laid down. FDM is a rapid prototyping technology. Other terms for FDM are "fused filament fabrication" (FFF) or "filament 3D printing" (FDP), which are considered to be equivalent to FDM. In general, FDM printers use a thermoplastic filament, which is heated to its melting point and then extruded, layer by layer, (or in fact filament after filament) to create a three-dimensional object. FDM printers are relatively fast and can be used for printing complicated object.

FDM printers are relatively fast, low cost and can be used for printing complicated 3D objects. Such printers are used in printing various shapes using various polymers. The technique is also being further developed in the production of LED luminaires and lighting solutions.

In injection molded parts surface finish and texture may be realized by texturing the mold. In the case of FDM, this may need to be done in a different way.

Hence, it is an aspect of the invention to provide an alternative 3D element, which preferably further at least partly obviates one or more of above-described drawbacks. It is also an aspect of the invention to provide an alternative 3D printing method, which preferably further at least partly obviates one or more of above-described drawbacks. Yet further, it is an aspect of the invention to provide an alternative lighting system comprising

such 3D item, which preferably further at least partly obviates one or more of above-described drawbacks. Yet further, it is an aspect to provide an alternative 3D printable material. The present invention may have as object to overcome or ameliorate at least one of the disadvantages of the prior art, or to provide a useful alternative.

5 Therefore, in a first aspect the invention provides a method for 3D printing a 3D item, the method comprising (i) providing 3D printable thermoplastic polymer material comprising particles embedded in the 3D printable thermoplastic polymer material, wherein the particles have a longest dimension length (L1), a shortest dimension length (L2), and an aspect ratio AR defined as the ratio of the longest dimension length (L1) and the shortest 10 dimension length (L2), and (ii) depositing during a printing stage 3D printable thermoplastic polymer material to provide the 3D item to provide layers of the 3D printed thermoplastic polymer material with a layer height (H), wherein: (a) $1 \leq AR \leq 4$ and $1 \leq H/L2 \leq 5$; or (b) $AR \geq 4$ and $H/L1 \leq 1$; or (c) $1 \leq AR \leq 4$ and $5 \leq H/L2 \leq 100$. Yet further, in an aspect the invention provides a 3D printable thermoplastic polymer material comprising an (thermoplastic) 15 polymer with particles embedded therein. In specific embodiments, the invention provides 3D printable thermoplastic polymer material comprising a thermoplastic material, wherein the thermoplastic material comprises particles embedded in thermoplastic material, wherein the particles have a longest dimension length (L1), a shortest dimension length (L2), and an aspect ratio AR defined as the ratio of the longest dimension length (L1) and the shortest 20 dimension length (L2), wherein: (i) $1 \leq AR \leq 4$; or (ii) $AR \geq 4$.

With such parameters, the surface roughness and surface texture can be controlled. This can be used for various reasons, such as to provide distance elements, to improve, or reduce fingerprint detection, to increase (or decrease) thermal transfer to the environment (or another product in physical contact with the surface of the 3D printed item 25 during use of the 3D printed item). Would the particulate material and/or polymeric material be used for light guiding, the surface texture may be used to control light outcoupling (or light incoupling). Further, control of the surface texture may be used to control hydrophobicity or impact on fluids or fluid streams streaming along the surface of the 3D item.

30 Hence, in first embodiments $1 \leq AR \leq 4$ and/or $1 \leq H/L2 \leq 100$, especially $1 \leq AR \leq 4$ and $1 \leq H/L2 \leq 100$, such as wherein $1 \leq H/L2 \leq 5$ or wherein $5 \leq H/L2 \leq 100$, applies.

With the first embodiments, is it possible to hide the ribbed structure or to provide a sub-structured matt surface. Hence, when desired the ribbed structure, which is inherent to FDM printed items, may be less pronounced. Hence, especially $1 \leq AR \leq 4$ and

$1 \leq H/L2 \leq 10$ applies. In specific embodiments $1 \leq AR \leq 2$ applies. In these ranges, the ribbed structure formation and properties may especially be controlled. Instead of the term "matt" also the terms "dull" or "frosted" may be applied.

Further, if desired a matt sub-structures surface may be provided. This may 5 e.g. be of interest for applications where shiny appearance can be reduced especially when there are also surface substructures are present. Hence, especially $1 \leq AR \leq 4$ and $5 \leq H/L2 \leq 100$ applies. In further specific embodiments $1 \leq AR \leq 2$. In specific embodiments $5 \leq H/L2 \leq 100$; in further specific embodiments $10 \leq H/L2 \leq 80$ applies. In these ranges, the matt appearance formation and matt property may especially be controlled.

10 In embodiments, the particles may comprise elongated shaped particles having an aspect ratio AR larger than 1. It is also possible to use "symmetric particles" with irregular shapes or regular shaped particles like spheres. With elongated particles, amongst optical effects may be created, fiber-like related aspects may be used, like transport of light, shape of the layers may be controlled, etc.

15 Especially, in second embodiments $AR \geq 4$ and $H/L1 \leq 1$ applies. In the second embodiments, it is possible to create a cactus like effect. Such latter surface may have specific properties for water retention or dust retention, etc., or more provide a kind of distance elements or light outcoupling elements, etcetera. Hence, with the present method it is possible to tailor the appearance of the (outer) surface of the 3D item. Hence, especially 20 $AR \geq 4$ and $H/L1 \leq 1$ applies. In specific embodiments $AR > 4$ applies; in further specific embodiments $AR \geq 100$, such as $4 \leq AR \leq 10,000$ applies. In specific embodiments $0.001 \leq H/L1 \leq 1$ applies; in further specific embodiments $H/L1 < 1$, such as $H/L1 \leq 0.5$ applies. In these ranges, the cactus appearance formation and cactus property may especially be controlled. The particles in this embodiment are preferably fiber like cylindrical particles.

25 Particle sizes above refer to average sizes as the particles do not necessarily have mono distribution.

30 The term dimension may refer to length, width, height, diameter, major axis length, minor axis length, etcetera. In case of a spherical particle, the longest dimension and shortest dimension are equal, and are the diameter. In case of a bar like element (rectangular cuboid), the longest dimension may be the length and the shortest dimension may be the height (assuming the width is larger than the height). For irregular shaped particles, for the sake of easiness, the smallest rectangular cuboid (rectangular parallelepiped) enclosing the irregular shaped particle may be used to define the length, width and height.

As indicated above, the 3D printable thermoplastic polymer material comprises particles embedded in the 3D printable thermoplastic polymer material. Such thermoplastic polymer material may be provided as filament, like a filament of thermoplastic material with particles in the filament, or such material may be provided as particulate 5 material, like particles of thermoplastic material with smaller particles in the particles of the particulate material.

The combination of particles and the 3D printable thermoplastic polymer material is chosen such that a 3D printable thermoplastic polymer material is provided, wherein the particles are embedded. This material may be expelled from printer nozzle 10 during the 3D printing stage. In embodiments, the 3D printable thermoplastic polymer material comprises up to 40 vol.% of the particles, relative to the total volume of the 3D printable thermoplastic polymer material. Even more especially, the 3D printable thermoplastic polymer material comprises in the range of 0.5-15 vol.%, especially 1-15 vol.%, of the particles, relative to the total volume of the 3D printable thermoplastic polymer 15 material, such as in embodiments in the range of 0.5-5 vol.%, such as especially 1-5 vol.%, of the particles, relative to the total volume of the 3D printable thermoplastic polymer material. With higher percentages, the 3D printable thermoplastic polymer material may be difficult to process, and with lower percentages the optical effects may be considered too small. Hence, especially 0.5-15 vol.%, such as 1-5 vol.% may be applied.

20 Essentially the same values may apply to the thus obtained 3D printed thermoplastic polymer material. Therefore, in embodiments the 3D printed thermoplastic polymer material comprises up to 40 vol.% of the particles, relative to the total volume of the 3D printed thermoplastic polymer material. Even more especially, the 3D printed thermoplastic polymer material comprises in the range of 0.5-15 vol.%, especially 1-15 vol.%, of the particles, relative to the total volume of the 3D printed thermoplastic polymer 25 material, such as in embodiments in the range of 0.5-5 vol.%, such as especially 1-5 vol.%, of the particles, relative to the total volume of the 3D printed thermoplastic polymer material.

With the printer, the 3D printable thermoplastic polymer material is expelled 30 from the printer nozzle and deposited on a receiver item (or on already 3D printed thermoplastic polymer material on the receiver item). Therefore, the method provides depositing during a printing stage 3D printable thermoplastic polymer material to provide the 3D item to provide layers of the 3D printed thermoplastic polymer material with a layer height (H). Especially, control of layer height may be executed with the nozzle, such as by

adjusting the distance between the nozzle and the layer deposited previously (or the receiver item, when no layer has deposited yet).

In specific embodiments, the particle dimensions and the layer height may be chosen such, that a substructure of a plurality of ribs is provided. Therefore, in embodiments 5 the 3D printed item has a surface (defined by a plurality of layers), wherein the surface comprises substructures with tops and bottoms, wherein the substructures comprise a plurality of layers with a top-top distance (d_3) between adjacent tops, wherein $d_3/H \geq 10$, such as especially wherein $10 \leq d_3/H \leq 1000$. This may especially apply in embodiments wherein $1 \leq AR \leq 4$ and $5 \leq H/L_2 \leq 100$. Such substructure may e.g. also be of relevance for inducing 10 decorative effects, or for other effects (such as defined above).

In embodiments, the 3D item may be generated on a flat substrate. In other embodiments, the 3D item may be generated on a substrate that may have one or more curved or faceted parts. Therefore, in embodiments the invention also provides printing during the printing stage the 3D printable thermoplastic polymer material on a substrate with 15 one or more of (i) a curved face, (ii) a faceted face, and (iii) faces configured relative to each under an angle. In this way, a 3D with a specific shape may be provided.

As further also elucidated below, in specific embodiments the 3D printable material may comprise one or more of acrylonitrile butadiene styrene copolymer (ABS), polystyrene (PS), polycarbonate (PC), polyethyleneterephthalate (PET), polymethyl- 20 methacrylate (PMMA), and copolymers of two or more of these.

In specific embodiments, one or more of the 3D printable thermoplastic polymer material and the particles are transmissive for one or more wavelengths in the visible. This may allow special optical effects like a transmissive polymer for light guiding and particles for outcoupling, or light guiding through light transmissive (elongated) 25 particles. Further, also both the 3D printable thermoplastic polymer material and the particles may be light transmissive, but may have different indices of refraction. This may also be used for optical effects like in optical elements, for light guiding, etc.

The herein described method provides 3D printed items. Hence, the invention also provides in a further aspect a 3D printed item obtainable with the herein described 30 method. Hence, in yet a further aspect the invention also provides a 3D printed item comprising 3D printed thermoplastic polymer material, wherein the 3D printed thermoplastic polymer material especially comprises a thermoplastic thermoplastic polymer material, wherein the 3D printed thermoplastic polymer material comprises particles embedded in the 3D printed thermoplastic polymer material, wherein the particles have a longest dimension

length (L1), a shortest dimension length (L2), and an aspect ratio AR defined as the ratio of the longest dimension length (L1) and the shortest dimension length (L2), and wherein the 3D item comprises layers of the 3D printed thermoplastic polymer material with a layer height (H), wherein: (i) $1 \leq AR \leq 4$ and $1 \leq H/L2 \leq 5$; or (ii) $AR \geq 4$ and $H/L1 \leq 1$; or (iii) $1 \leq AR \leq 4$ and $5 \leq H/L2 \leq 100$. As indicated above, such 3D printed item may be obtained with the herein described method.

In specific embodiments, the longest dimension length (L1) is selected from the range of 5 μ m – 1 mm, such as 5-500 μ m. Especially, the layer height (H) may be selected from the range of 50 μ m – 20 mm, like 50 μ m – 10 mm, such as especially 100 μ m – 10 mm. With such layer heights, it may especially be able to control the appearance of the outer surface.

As indicated above, in embodiments the 3D printed thermoplastic polymer material comprises up to 40 vol.% of the particles, relative to the total volume of the 3D printed thermoplastic polymer material. Even more especially, the 3D printed thermoplastic polymer material comprises in the range of 0.5-15 vol.%, especially 1-15 vol.%, of the particles, relative to the total volume of the 3D printed thermoplastic polymer material, such as in embodiments in the range of 0.5-5 vol.%, such as especially 1-5 vol.%, of the particles, relative to the total volume of the 3D printed thermoplastic polymer material.

As further also elucidated below (and above), in specific embodiments the 3D printed material may comprise one or more of acrylonitrile butadiene styrene copolymer (ABS), polystyrene (PS), polycarbonate (PC), polyethyleneterephthalate (PET), polymethylmethacrylate (PMMA), blends of two or more of these, and copolymers of two or more of these.

As indicated above, in specific embodiments one or more of the 3D printed thermoplastic polymer material and the particles are transmissive for one or more wavelengths in the visible.

Therefore, in yet a further aspect the invention also provides a lighting system comprising (a) a light source configured to generate light source light and (b) a 3D printed item as defined herein, configured to transmit or reflect at least part of the light source light.

Below, some aspects of or variants on the invention are further elucidated.

As indicated above, the invention may thus provide a method comprising providing a filament of 3D printable thermoplastic polymer material and printing during a printing stage said 3D printable thermoplastic polymer material on a substrate, to provide said 3D item.

Materials that may especially qualify as 3D printable materials may be selected from the group consisting of metals, glasses, thermoplastic polymers, silicones, etc. Especially, the 3D printable material comprises a (thermoplastic) polymer selected from the group consisting of ABS (acrylonitrile butadiene styrene), Nylon (or polyamide), Acetate (or 5 cellulose), PLA (poly lactic acid), terephthalate (such as PET polyethylene terephthalate), Acrylic (polymethylacrylate, Perspex, polymethylmethacrylate, PMMA), Polypropylene (or polypropene), Polystyrene (PS), PE (such as expanded- high impact-Polythene (or polyethylene), Low density (LDPE) High density (HDPE)), PVC (polyvinyl chloride) Polychloroethene, etc. Optionally, the 3D printable material comprises a 3D printable 10 material selected from the group consisting of Urea formaldehyde, Polyester resin, Epoxy resin, Melamine formaldehyde, Polycarbonate (PC), rubber, etc. Optionally, the 3D printable material comprises a 3D printable material selected from the group consisting of a polysulfone, a polyether sulfone, a polyphenyl sulfone, an imide (such as a poly ether imide) etc. Especially, the printable material *per se* is light transmissive, more especially optically 15 transparent. PPMA, PC, amorphous PET, PS and co-polyesters of two or more thereof are suitable polymers (see also other examples herein). Blends of two or more of these may also be applied. Hence, especially polymeric materials may be applied that are at least partially transmissive for visible light. For instance, the polymeric material may be transparent to light (assuming the particles are not (yet) available).

20 Herein, the term “3D printable thermoplastic polymer material” may also be indicated as “printable material. The term “polymeric material” may in embodiments refer to a blend of different polymers, but may in embodiments also refer to essentially a single polymer type with different polymer chain lengths. Hence, the terms “polymeric material” or “polymer” may refer to a single type of polymers but may also refer to a plurality of different 25 polymers. The term “printable material” may refer to a single type of printable material but may also refer to a plurality of different printable materials. The term “printed material” may refer to a single type of printed material but may also refer to a plurality of different printed materials.

Hence, the term “3D printable thermoplastic polymer material” may also refer 30 to a combination of two or more materials. In general these (polymeric) materials have a glass transition temperature T_g and/or a melting temperature T_m . The 3D printable thermoplastic polymer material will be heated by the 3D printer before it leaves the nozzle to a temperature of at least the glass transition temperature, and in general at least the melting temperature. Hence, in a specific embodiment the 3D printable thermoplastic polymer

material comprises a thermoplastic polymer having a glass transition temperature (T_g) and /or a melting point (T_m), and the printer head action comprises heating the 3D printable thermoplastic polymer material above the glass transition and if it is a semi-crystalline polymer above the melting temperature. In yet another embodiment, the 3D printable 5 thermoplastic polymer material comprises a (thermoplastic) polymer having a melting point (T_m), and the printer head action comprises heating the 3D printable thermoplastic polymer material to be deposited on the receiver item to a temperature of at least the melting point.

The glass transition temperature is in general not the same thing as the melting temperature. Melting is a transition which occurs in crystalline polymers. Melting happens 10 when the polymer chains fall out of their crystal structures, and become a disordered liquid. The glass transition is a transition which happens to amorphous polymers; that is, polymers whose chains are not arranged in ordered crystals, but are just strewn around in any fashion, even though they are in the solid state. Polymers can be amorphous, essentially having a glass transition temperature and not a melting temperature or can be (semi) crystalline, in 15 general having both a glass transition temperature and a melting temperature, with in general the latter being larger than the former.

Specific examples of materials that can be used are transparent materials can e.g. be selected from the group consisting of, polycarbonate (PC), amorphous polyamides (PA), amorphous PET, polystyrene (PS), PET, PMMA, etc., and copolymers of two or more 20 thereof (such as copolymers). They may also contain dyes which may optionally be luminescent to obtain enhanced effects.

The printable thermoplastic polymer material is especially printed on a receiver item. Especially, the receiver item can be the building platform or can be comprised by the building platform. The receiver item can also be heated during 3D printing. However, 25 the receiver item may also be cooled during 3D printing.

The phrase “printing on a receiver item” and similar phrases include amongst others directly printing on the receiver item, or printing on a coating on the receiver item, or printing on 3D printed thermoplastic polymer material earlier printed on the receiver item. The term “receiver item” may refer to a printing platform, a print bed, a substrate, a support, 30 a build plate, or a building platform, etc. Instead of the term “receiver item” also the term “substrate” may be used. The phrase “printing on a receiver item” and similar phrases include amongst others *also* printing on a separate substrate on or comprised by a printing platform, a print bed, a support, a build plate, or a building platform, etc. Therefore, the phrase “printing on a substrate” and similar phrases include amongst others directly printing on the substrate,

or printing on a coating on the substrate or printing on 3D printed thermoplastic polymer material earlier printed on the substrate. Here below, further the term substrate is used, which may refer to a printing platform, a print bed, a substrate, a support, a build plate, or a building platform, etc., or a separate substrate thereon or comprised thereby. See further also below 5 were specific (separate) substrates are discussed.

As indicated above, the 3D printable thermoplastic polymer material, and thus also the 3D printed thermoplastic polymer material comprises particulate material.

Different particles may have different dimensions. Hence, especially the dimensions indicated herein refer to an average of the dimension, especially an average over 10 the total number of particles (see also below). Hence, in embodiments the 3D printable thermoplastic polymer material comprises particulate material embedded therein.

The particulate may be polydisperse (in their size distribution).

As indicated above, the particles have a longest dimension length (L1), a shortest dimension length (L2), and an aspect ratio AR defined as the ratio of the longest 15 dimension length (L1) and the shortest dimension length (L2).

Therefore, in embodiments particles are used which have a longest dimension (A1) having a longest dimension length (L1), and a shortest dimension (A2) having a shortest dimension length (L2), wherein the longest dimension length (L1) and the shortest dimension length (L2) have an aspect ratio as defined herein. In case of spherical or cubic particles, L1 20 and L2 are identical.

Especially, the aspect ratios indicated herein, or the dimensions, such as the longest dimension, etc., indicated herein, refer to an average over the total number of particles. Hence, the term “in average” especially refers to a number average. As indicated above, the particulate may be polydisperse.

25 The particles may have a flake like structure, i.e. particles having a maximum width and a maximum length substantially larger than a maximum thickness, such as an aspect ratio of the maximum length and maximum thickness of especially at least 5, like at least 10, such as in the range of 10-10,000.

The aspect ratios, as indicated above, refer to the particles including an optional 30 coating of the particles. The phrase “coating of the particles” especially refers to a coating on an individual particle, i.e. a coating enclosing a single particle. Hence, also the term “particle coating” may be used. The coating may enclose the particle entirely or only a part of the particle. The particles of a subset of the total number of particles may include a particle coating and another subset of the total number of particles may not include a particle coating.

Further, the aspect ratios indicated above may refer to a plurality of particles having different aspect ratios. Hence, the particles may be substantially identical, but the particles in the coating may also mutually differ, such as two or more subsets of particles, wherein within the subsets the particles are substantially identical.

5 To define the longest dimension and the shortest dimension or minor axes for the particles, herein the axes of a (virtual) rectangular parallelepiped with the smallest volume that encloses the particle may be used. The main and minor axes are defined perpendicular to the faces of the rectangular parallelepiped, the longest dimension having a longest dimension length (L1), a shortest dimension with a shortest dimension length (L2) and another or further (orthogonal axis) having a further dimension length (L3). Hence, the 10 longest dimension may especially relate to a length of the particles, the shortest dimension may especially relate to a thickness or height of the particles, and the further dimension may especially refer to a width of the particles. Therefore, in embodiments the longest dimension, the shortest dimension, and a further dimension, define a rectangular parallelepiped with a 15 smallest volume that encloses the particle. In case of spherical or cubic particles, L1, L2 and L3 are identical. In such virtual rectangular parallelepiped, the dimensions are defined orthogonal.

For particles wherein $1 \leq AR \leq 4$, i.e. $1 \leq L1/L2 \leq 4$, in embodiments also $1 \leq L1/L3 \leq 4$, though L3 may also be much smaller. For particles wherein $AR \geq 4$, i.e. $L1/L2 \geq 4$ 20 in embodiments $L1/L3 \geq 1$, such as in embodiments $L1/L3 \geq 4$. The ratio $L1/L3$ may also be indicated as $AR2$. For instance, in embodiments $4 \leq AR2 \leq 10,000$ applies. Larger aspect ratios may be more difficult to process and/or more difficult to control the surface properties.

As indicated above, the particles may mutually differ. For instance, the particles may have a distribution of the sizes of one or more of the longest dimension, the 25 shortest dimension (and the further dimension). Therefore, in average, the particles will have dimensions as described herein. For instance, at least 50 wt.% of the particles comply with the herein indicated dimensions (including ratios), such as at least 75 wt.%, like at least 85 wt.%. As known in the art, the particles may also have effective diameters indicated with $d50$. Such diameters may thus vary, as there may be a distribution of particle sizes.

30 Hence, in embodiments at least 50 wt.% of the particles, such as at least 75 wt.%, like at least 85 wt.% has a longest dimension with a length (L1) as defined herein, which may e.g. be 5 μm – 1 mm, such as such as 5-500 μm .

The shortest dimension length may be selected from the same range as L1, but divided by AR.

Hence, in embodiments at least 50 wt.% of the particles, such as at least 75 wt.%, like at least 85 wt.% has a shortest dimension length (L2) as defined herein.

As indicated above, the further dimension length (L3) may be selected from the same range as L1, but divided by AR2 (though L3 may also be much smaller).

5 Hence, in embodiments at least 50 wt.% of the particles, such as at least 75 wt.%, like at least 85 wt.% has a further dimension length (L3) as defined herein.

In yet further embodiments, for at least 50 wt.% of the particles, such as at least 75 wt.%, like at least 85 wt.%, apply all these conditions for L1, L2 and L3 for each particle (of the at least 50 wt.%).

10 In specific embodiments, a mass median weight (or more) of the particles has a longest dimension with a length (L1) selected from the range as indicated herein. In yet further specific embodiments, a mass median weight (or more) of the particles has a shortest dimension length (L2) selected from the range as indicated herein. In further specific embodiments, a mass median weight (or more) of the particles has a further dimension with a 15 further dimension length (L3) selected from the range as indicated herein. In yet further embodiments, a mass median weight (or more) of the particles comply with all these conditions for L1, L2 and L3.

Particles may be in the form of beads, fibers, platelets irregular shaped particles. In the case of symmetric particles, the largest dimension of the particles is 20 especially in the range 5 μm -500 μm . In the case of asymmetric particles (fibers platelets) the largest dimension is preferably less than 1mm.

In specific embodiments, the particles comprise one or more coated particles and uncoated particles, wherein the coating may comprise in (further) embodiments one or more of silver and aluminum, and wherein in specific embodiments the particles comprise 25 one or more of mica particles, glass particles, and carbon particles.

In specific embodiments, also combinations of different type of particles may be used.

In specific embodiments, the 3D printable thermoplastic polymer material (and thus 3D printed thermoplastic polymer material) comprises one or more of 30 polycarbonate (PC), (amorphous) polyethyleneterephthalate (PET), polymethylmethacrylate (PMMA), polystyrene (PS) etc., and copolymers, such as copolymers, of two or more thereof. In specific embodiments, the 3D printable thermoplastic polymer material comprises up to 40 vol.% particles, relative to the total volume of the 3D printable thermoplastic polymer material (including the particles). Therefore, specific embodiments, the 3D printed

thermoplastic polymer material comprises up to 40 vol.% of the particles, relative to the total volume of the 3D printed thermoplastic polymer material (including the particles).

In specific embodiments, it is also possible to include colorants such as dyes as well as luminescent dyes to obtain enhanced effects.

5 Further, the invention relates to a software product that can be used to execute the method described herein.

The printed product can be a decorative or a functional part of an application such as a luminaire. The (with the herein described method) obtained 3D printed item may be functional per se. The thus obtained 3D item may (alternatively) be used for decorative or 10 artistic purposes. The 3D printed item may include or be provided with a functional component or may be comprised by a functional component. The functional component may especially be selected from the group consisting of an optical component, an electrical component, and a magnetic component. The term “optical component” especially refers to a component having an optical functionality, such a mirror, a light source (like a LED), etc.

15 The term “electrical component” may e.g. refer to an integrated circuit, PCB, a battery, a driver, but also a light source (as a light source may be considered an optical component and an electrical component), etc. The term magnetic component may e.g. refer to a magnetic connector, a coil, etc. Alternatively or additionally, the functional component may comprise a thermal component (e.g. configured to cool or to heat an electrical component). Hence, the 20 functional component may be configured to generate heat or to scavenge heat, etc.

Returning to the 3D printing process, a 3D printer may be used to provide the 3D printed item described herein. Therefore, in yet a further aspect the invention also provides a fused deposition modeling 3D printer, comprising (a) a printer head comprising a printer nozzle, and (b) a filament providing device configured to provide a filament 25 comprising 3D printable thermoplastic polymer material to the printer head, wherein the fused deposition modeling 3D printer is configured to provide said 3D printable thermoplastic polymer material to a substrate.

Of course, the method may include printing a part of the 3D item with 3D printable thermoplastic polymer material comprising particles and printing a part of the 3D 30 item with 3D printable thermoplastic polymer material without particles. Likewise, a 3D printed item may comprise regions with particles and regions without particles. Further, a 3D printed item may comprise regions with different structures and/or different regions with mutual different structures.

Instead of the term “fused deposition modeling (FDM) 3D printer” shortly the terms “3D printer”, “FDM printer” or “printer” may be used. The printer nozzle may also be indicated as “nozzle” or sometimes as “extruder nozzle”.

5 BRIEF DESCRIPTION OF THE DRAWINGS

Embodiments of the invention will now be described, by way of example only, with reference to the accompanying schematic drawings in which corresponding reference symbols indicate corresponding parts, and in which:

Figs. 1a-1b schematically depict some general aspects of the 3D printer;

10 Figs. 2a-2e schematically depict some aspects of the particles, such as flakes, that can be used herein;

Figs. 3a-3b schematically depict some applications, including 3D printed items;

Figs. 4a-4c schematically depict some further aspects of the invention; and

15 Figs. 5a-5c show some pictures of 3D items that were printed.

The schematic drawings are not necessarily on scale.

DETAILED DESCRIPTION OF THE EMBODIMENTS

Fig. 1a schematically depicts some aspects of the 3D printer. Reference 500 indicates a 3D printer. Reference 530 indicates the functional unit configured to 3D print, especially FDM 3D printing; this reference may also indicate the 3D printing stage unit. Here, only the printer head for providing 3D printed thermoplastic polymer material, such as a FDM 3D printer head is schematically depicted. Reference 501 indicates the printer head. The 3D printer of the present invention may especially include a plurality of printer heads, 20 though other embodiments are also possible. Reference 502 indicates a printer nozzle. The 3D printer of the present invention may especially include a plurality of printer nozzles, 25 though other embodiments are also possible. Reference 320 indicates a filament of printable 3D printable thermoplastic polymer material (such as indicated above). For the sake of clarity, not all features of the 3D printer have been depicted, only those that are of especial 30 relevance for the present invention (see further also below).

The 3D printer 500 is configured to generate a 3D item 10 by depositing on a receiver item 550, which may in embodiments at least temporarily be cooled, a plurality of filaments 320 wherein each filament 20 comprises 3D printable thermoplastic polymer material, such as having a melting point T_m . The 3D printer 500 is configured to heat the

filament material upstream of the printer nozzle 502. This may e.g. be done with a device comprising one or more of an extrusion and/or heating function. Such device is indicated with reference 573, and is arranged upstream from the printer nozzle 502 (i.e. in time before the filament material leaves the printer nozzle 502). The printer head 501 may (thus) include 5 a liquefier or heater. Reference 201 indicates printable material. When deposited, this material is indicated as (3D) printed material, which is indicated with reference 202. Reference 1550 refers to a substrate. As indicated above, the term “receiver item” may refer to a printing platform, a print bed, a substrate, a support, a build plate, or a building platform, etc. Instead of the term “receiver item” also the term “substrate” may be used.

10 Reference 572 indicates a spool or roller with material, especially in the form of a wire. The 3D printer 500 transforms this in a filament or fiber 320 on the receiver item or on already deposited printed material. In general, the diameter of the filament downstream of the nozzle is reduced relative to the diameter of the filament upstream of the printer head. Hence, the printer nozzle is sometimes (also) indicated as extruder nozzle. Arranging 15 filament by filament and filament on filament, a 3D item 10 may be formed. Reference 575 indicates the filament providing device, which here amongst others include the spool or roller and the driver wheels, indicated with reference 576.

Reference A indicates a longitudinal axis or filament axis.

20 Reference C schematically depicts a control system, such as especially a temperature control system, configured to control the temperature of the receiver item 550. The control system C may include a heater or may be functionally coupled to a heater, which may be able to heat the receiver item 550 to at least a temperature of 50 °C, but especially up to a range of about 350 °C, such as at least 200 °C. The control system may especially be configured to control the 3D printing method, such as including controlling a layer height, 25 etc.

Fig. 1b schematically depicts in 3D in more detail the printing of the 3D item 10 under construction. Here, in this schematic drawing the ends of the filaments 320 in a single plane are not interconnected, though in reality this may in embodiments be the case.

Hence, Figs. 1a-1b schematically depict some aspects of a fused deposition 30 modeling 3D printer 500, comprising (a) a first printer head 501 comprising a printer nozzle 502, (b) a filament providing device 575 configured to provide a filament 320 comprising 3D printable thermoplastic polymer material 201 to the first printer head 501, and optionally (c) a receiver item 550. In Figs. 1a-1b, the first or second printable material or the first or second

printed material are indicated with the general indications printable material 201 and printed material 202.

Figs 2a-2e schematically depict some aspects of the particles 410. Some particles 410 have a longest dimension A1 having a longest dimension length L1 and a shortest dimension A2 having a shortest dimension length L2. As can be seen from the drawings, the longest dimension length L1 and the shortest dimension length L2 have a first aspect ratio larger than 1. Fig. 2a schematically depicts a particle 410 in 3D, with the particle 410 having a length, height and width, with the particle (or flake) essentially having an elongated shape. Hence, the particle may have a further (minor or main) axis, herein indicated as further dimension A3. Essentially, the particles 410 are elongated thin particles, i.e. $L_2 < L_1$, especially $L_2 \ll L_1$, and $L_2 < L_3$, especially $L_2 \ll L_3$. L_1 may e.g. be selected from the range of 1-500 μm ; likewise L_3 may be. L_2 may e.g. be selected from the range of 0.1 μm – 10 μm . Also L_3 may e.g. be selected from the range of 0.1 μm – 10 μm . However, L_2 and/or L_3 may also be longer, such as up to 5 mm, such as up to 1 mm, like up to 100 μm .

Fig. 2b schematically depicts a particle that has a less regular shape such as pieces of broken glass, with a virtual smallest rectangular parallelepiped enclosing the particle.

Note that the notations L1, L2, and L3, and A1, A2 and A3 are only used to indicate the axes and their lengths, and that the numbers are only used to distinguish the axis. Further, note that the particles are not essentially oval or rectangular parallelepiped. The particles may have any shape with at least a longest dimension substantially longer than a shortest dimension or minor axes, and which may essentially be flat. Especially, particles are used that are relatively regularly formed, i.e. the remaining volume of the fictive smallest rectangular parallelepiped enclosing the particle is small, such as less than 50%, like less than 25%, of the total volume.

Fig. 2c schematically depicts in cross-sectional view a particle 410 including a coating 412. The coating may comprise light reflective material. For instance, the coating may comprise a (white) metal oxide. In other embodiments, the coating may essentially consist of a metal, such as an Ag coating. In other embodiments the coatings may only be on one or both of the large surfaces and not on the thin side surfaces of the particles.

Fig. 2d schematically depicts a relatively irregularly shaped particle. The particulate material that is used may comprise e.g. small broken glass pieces. Hence, the particulate material that is embedded in the 3D printable thermoplastic polymer material or is embedded in the 3D printed thermoplastic polymer material may include a broad distribution

of particles sizes. A rectangular parallelepiped can be used to define the (orthogonal) dimensions with lengths L1, L2 and L3.

Especially, particles with an irregular 3-D shape, a cylindrical shape (such as a short fiber), a spherical shape, are particularly relevant. Fig. 2e schematically depict 5 cylindrical, spherical, and irregularly shaped particles.

Fig. 3a schematically depicts a lighting system 1000 comprising a) a light source 1010 configured to generate light source light 1011 and b) an object 10, such as defined above, configured to reflect or transmit at least part of said light source light 1011. Other functions of the object 10 may also be possible, such as a lamp shade, a wall of a 10 device, etc.

For printing lamps and luminaires or other items, it may be desirable to create curved or angular shapes. Hence, amongst others we suggest herein the use of a curved or angular shapes receiver item 1550. The 3D printer can print on top of the surface of such shaped receiver item 1550, see Fig. 3b.

15 In injection molded parts surface finish and texture is realized by texturing the mold. As indicated above, in the case of FDM this need to be in a different way. For this purpose we suggest using various filler materials such as glass beads, fibers etc. In the case of essentially symmetric particles (beads, irregular shaped powders) to obtain the desired effect, the particle size may especially be in the range of 5 μm – 500 μm . In the case of asymmetric particles (fibers, platelets) the largest dimension of 1 mm and aspect ratio of in the range 1-5 20 appeared to be the most desired range (in experiments that were executed). The most desirable particle concentration is found to be less than 15% volume (relative to the total volume of the 3D printed thermoplastic polymer material.

Fig. 4a schematically depicts a filament 320, such as when escaping from a 25 printer nozzle (not depicted), which comprises 3D printable thermoplastic polymer material 201. The 3D printable thermoplastic polymer material comprise thermoplastic material 401 with particles 410 embedded therein.

Fig. 4b schematically depicts a 3D item 10, showing the ribbed structures (originating from the deposited filaments), having layer heights H and layer width W.

30 Fig. 4c schematically depicts a 3D printed item 10 with a substructure with a plurality of tops 13 and a plurality of bottoms 14. The top-top distance is indicated with reference d3.

A number of 3D printed items were generated

	Series 1	Series 2	Series 3
	$1 \leq AR \leq 4$ and $1 \leq H/L2 \leq 5$	$AR \geq 4$ and $H/L1 \leq 1$	$1 \leq AR \leq 4$ and $5 \leq H/L2 \leq 100$
Thermoplastic material	PC	PC	PC
Particle material	glass	glass	glass
Particle size (L1)	200 μm	140	30 μm
Shortest dimension length (L2)	200 μm	20	10 μm
Aspect ratio	1	7	3
Layer height (H)	0.4 mm; 0.6 mm; 0.8 mm	0.10 mm	0.1 mm; 0.4 mm
Substructure	-	-	$d3/H=8, 3.2$
Fig.	5a	5b	5c

5 In series 1, it was observed that up to 0.8 mm rib thickness the ribbed structure becomes less visible. The beads help to hide the ribbed structure. In these embodiments $1 \leq AR \leq 4$ and $1 \leq H/L2 \leq 5$ applies. In specific embodiments $1 \leq AR \leq 2$ applies. In even more specific embodiments $1 < AR < 2$ applies. In specific embodiments $1 < H/L2 < 5$ applies. In even more specific embodiments $2 \leq H/L2 \leq 4$ applies. In these ranges, the ribbed structure formation and properties may especially be controlled.

10 In series 2, cactus-type surfaces were obtained. Very rough surfaces layer where fibers get oriented and form needles.

10 In series 3, matt surfaces were obtained with a substructure.

15 The term "substantially" herein, such as "substantially consists", will be understood by the person skilled in the art. The term "substantially" may also include embodiments with "entirely", "completely", "all", etc. Hence, in embodiments the adjective substantially may also be removed. Where applicable, the term "substantially" may also relate to 90% or higher, such as 95% or higher, especially 99% or higher, even more especially 99.5% or higher, including 100%. The term "comprise" includes also embodiments wherein the term "comprises" means "consists of". The term "and/or" especially relates to one or more of the items mentioned before and after "and/or". For instance, a phrase "item 1 and/or item 2" and similar phrases may relate to one or more of 20 item 1 and item 2. The term "comprising" may in an embodiment refer to "consisting of" but

may in another embodiment also refer to "containing at least the defined species and optionally one or more other species".

Furthermore, the terms first, second, third and the like in the description and in the claims, are used for distinguishing between similar elements and not necessarily for 5 describing a sequential or chronological order. It is to be understood that the terms so used are interchangeable under appropriate circumstances and that the embodiments of the invention described herein are capable of operation in other sequences than described or illustrated herein.

10 The devices herein are amongst others described during operation. As will be clear to the person skilled in the art, the invention is not limited to methods of operation or devices in operation.

15 It should be noted that the above-mentioned embodiments illustrate rather than limit the invention, and that those skilled in the art will be able to design many alternative embodiments without departing from the scope of the appended claims. In the claims, any reference signs placed between parentheses shall not be construed as limiting the claim. Use 20 of the verb "to comprise" and its conjugations does not exclude the presence of elements or steps other than those stated in a claim. The article "a" or "an" preceding an element does not exclude the presence of a plurality of such elements. The invention may be implemented by means of hardware comprising several distinct elements, and by means of a suitably programmed computer. In the device claim enumerating several means, several of these means may be embodied by one and the same item of hardware. The mere fact that certain 25 measures are recited in mutually different dependent claims does not indicate that a combination of these measures cannot be used to advantage.

25 The invention further applies to a device comprising one or more of the characterizing features described in the description and/or shown in the attached drawings. The invention further pertains to a method or process comprising one or more of the characterizing features described in the description and/or shown in the attached drawings.

30 The various aspects discussed in this patent can be combined in order to provide additional advantages. Further, the person skilled in the art will understand that embodiments can be combined, and that also more than two embodiments can be combined. Furthermore, some of the features can form the basis for one or more divisional applications.

It goes without saying that one or more of the first (printable or printed) material and second (printable or printed) material may contain fillers such as glass and fibers which do not have (to have) influence on the T_g or T_m of the material(s).

CLAIMS:

1. A method for 3D printing a 3D item (10) by means of Fused Deposition Modeling (FDM), the method comprising (i) providing 3D printable thermoplastic polymer material (201) comprising particles (410) embedded in the 3D printable thermoplastic polymer material (201), wherein the particles (410) have a longest dimension length L1, a shortest dimension length L2, and an aspect ratio AR defined as the ratio of the longest dimension length L1 and the shortest dimension length L2, and (ii) depositing during a printing stage 3D printable thermoplastic polymer material (201) to provide the 3D item (10) to provide layers (230) of the 3D printed thermoplastic polymer material (202) with a layer height H, wherein $1 \leq AR \leq 4$ and $1 \leq H/L2 \leq 5$.

10

2. The method according to claim 1, wherein the longest dimension length L1 is selected from the range of 5 μ m – 1 mm, wherein the layer height H is selected from the range of 50 μ m – 10 mm, and wherein the 3D printable thermoplastic polymer material (201) comprises in the range of 1-15 vol.% of the particles (410), relative to the total volume of the 3D printable thermoplastic polymer material (201).

15

3. The method according to any one of the preceding claims 1-2, wherein $1 \leq AR \leq 2$.

20

4. The method according to any one of the preceding claims 1-2, wherein $2 \leq H/L2 \leq 4$.

25

5. The method according to any one of the preceding claims, wherein the 3D printable thermoplastic polymer material (201) may comprise one or more of acrylonitrile butadiene styrene, polystyrene, polycarbonate, polyethylenetelephthalate, polymethylmethacrylate, and copolymers of two or more of these.

6. The method according to any one of the preceding claims, wherein the particles (410) comprise one or more coated particles and uncoated particles, wherein the

coating comprises one or more of silver and aluminum, and wherein the particles comprise one or more of mica particles, glass particles, and carbon particles, wherein the particles (410) comprise elongated shaped particles having an aspect ratio AR larger than 1.

5 7. The method according to any one of the preceding claims, wherein one or more of the 3D printable thermoplastic polymer material (201) and the particles (410) are transmissive for one or more wavelengths in the visible.

8. A 3D printed item (10) obtainable by a method according to any one of claims 10 1, 2, 5, 6, 7, wherein the 3D printed item (10) comprises 3D printed thermoplastic polymer material (202), wherein the 3D printed thermoplastic polymer material (202) comprises a thermoplastic material, wherein the 3D printed thermoplastic polymer material (202) comprises particles (410) embedded in the 3D printed thermoplastic polymer material (202), wherein the particles (410) have a longest dimension length L1, a shortest dimension length 15 L2, and an aspect ratio AR defined as the ratio of the longest dimension length L1 and the shortest dimension length L2, and wherein the 3D item (10) comprises layers (230) of the 3D printed material (202) with a layer height (H), wherein $1 \leq AR \leq 4$ and $1 \leq H/L2 \leq 5$.

9. The 3D printed item (10) according to claim 8, wherein the longest dimension 20 length L1 is selected from the range of 5 μ m – 1 mm, wherein the layer height (H) is selected from the range of 50 μ m – 10 mm, and wherein the 3D printed thermoplastic polymer material (202) comprises in the range of 1-15 vol.% of the particles (410) relative to the total volume of the 3D printed thermoplastic polymer material (202).

25 10. The 3D printed item (10) according to any one of the preceding claims 8-9, wherein $1 \leq AR \leq 2$.

11. The 3D printed item (10) according to any one of the preceding claims 8-9, wherein $2 \leq H/L2 \leq 4$.

30 12. The 3D printed item (10) according to any one of the preceding claims 8-11, wherein the 3D printable thermoplastic polymer material (201) comprises in the range of 1-5 vol.% of the particles (410), relative to the total volume of the 3D printable thermoplastic polymer material (201), and wherein the 3D printed thermoplastic polymer material (202)

may comprise one or more of acrylonitrile butadiene styrene, polystyrene, polycarbonate, polyethyleneterephthalate, polymethylmethacrylate, and copolymers of two or more of these, and wherein the particles (410) comprise one or more coated particles and uncoated particles, wherein the coating comprises one or more of silver and aluminum, and wherein the particles 5 comprise one or more of mica particles, glass particles, and carbon particles.

13. The 3D printed item (10) according to any one of the preceding claims 8-12, wherein the 3D printed item (10) has a surface (12), wherein the surface (12) comprises substructures with tops (13) and bottoms (14), wherein the substructures (12) comprise a 10 plurality of layers (230) with a top-top distance (d3) between adjacent tops (13), wherein $d3/H \geq 10$.

14. A lighting system (1000) comprising (a) a light source (1010) configured to generate light source light (1011) and (b) a 3D printed item (10) according to any one of the 15 preceding claims 8-13, configured to transmit or reflect at least part of the light source light (1011).

15. A 3D printable thermoplastic polymer material (201) for use in the method according to any one of claims 1, 2, 4, 5, 6, 7, wherein the 3D printable thermoplastic 20 polymer material (201) comprises a thermoplastic polymer material, wherein the thermoplastic polymer material comprises particles (410) embedded in thermoplastic polymer material, wherein the particles (410) have a longest dimension length L1, a shortest dimension length L2, and an aspect ratio AR defined as the ratio of the longest dimension length L1 and the shortest dimension length L2, wherein $1 \leq AR \leq 4$.

1/7




FIG. 1A




FIG. 1B

2/7




FIG. 2A




FIG. 2B

3/7




FIG. 2C




FIG. 2D

4/7






FIG. 2E

5/7




FIG. 3A




FIG. 3B

6/7




FIG. 4A




FIG. 4B




FIG. 4C

7/7




FIG. 5A




FIG. 5B




FIG. 5C

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2018/066739

A. CLASSIFICATION OF SUBJECT MATTER	INV.	B29C64/10	B33Y10/00	B33Y80/00	B29C70/00	B29C70/58
		B29C64/209	B29C64/118			

ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

B29C B33Y F21S G02B F21V

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2017/120326 A1 (HEIKKILA KURT [US]) 4 May 2017 (2017-05-04)	1-5, 8-11,15
Y	paragraph [0019] paragraph [0026] paragraph [0038] paragraph [0090] paragraph [0092]	6,7, 12-14
A	----- DE 10 2014 107330 A1 (HERAEUS KULZER GMBH [DE]) 26 November 2015 (2015-11-26) paragraph [0005] paragraph [0007] paragraph [0022] paragraph [0040] paragraph [0071]	1-15
	----- -/-	

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
---	--

12 September 2018

21/09/2018

Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer
--	--------------------

Borsch, Sebastian

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2018/066739

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 2016/083797 A1 (NGF EUROP LTD [GB]; PILKINGTON GROUP LTD [GB]) 2 June 2016 (2016-06-02) paragraph [0030] ----- US 2016/346997 A1 (LEWIS JENNIFER A [US] ET AL) 1 December 2016 (2016-12-01) paragraph [0070] paragraph [0136] ----- US 2015/185375 A1 (HANNINGTON MICHAEL [US]) 2 July 2015 (2015-07-02) figure 5 ----- WO 2010/075395 A2 (VALSPAR SOURCING INC [US]; MARTINONI RAFFAELE [CH]) 1 July 2010 (2010-07-01) paragraph [0048] -----	6,12 7 13 14
1		

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2018/066739

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
US 2017120326	A1 04-05-2017	CA 2915662	A1	15-01-2015
		EP 3019648	A1	18-05-2016
		US 2015080495	A1	19-03-2015
		US 2016256925	A1	08-09-2016
		US 2017028475	A1	02-02-2017
		US 2017120326	A1	04-05-2017
		WO 2015006697	A1	15-01-2015
<hr/>				
DE 102014107330	A1 26-11-2015	CN 106456451	A	22-02-2017
		DE 102014107330	A1	26-11-2015
		EP 3145471	A1	29-03-2017
		JP 2017521481	A	03-08-2017
		KR 20170009907	A	25-01-2017
		US 2017196666	A1	13-07-2017
		WO 2015177348	A1	26-11-2015
<hr/>				
WO 2016083797	A1 02-06-2016	EP 3224308	A1	04-10-2017
		JP 2017538852	A	28-12-2017
		US 2017321037	A1	09-11-2017
		WO 2016083797	A1	02-06-2016
<hr/>				
US 2016346997	A1 01-12-2016	US 2016346997	A1	01-12-2016
		WO 2015120429	A1	13-08-2015
<hr/>				
US 2015185375	A1 02-07-2015	AU 2014379451	A1	04-08-2016
		CA 2935298	A1	30-07-2015
		CN 106068468	A	02-11-2016
		EP 3090290	A2	09-11-2016
		JP 2017503209	A	26-01-2017
		KR 20160105427	A	06-09-2016
		RU 2016131171	A	06-02-2018
		US 2015185375	A1	02-07-2015
		WO 2015112283	A2	30-07-2015
<hr/>				
WO 2010075395	A2 01-07-2010	CN 102325645	A	18-01-2012
		EP 2379311	A2	26-10-2011
		EP 3378886	A1	26-09-2018
		JP 5985827	B2	06-09-2016
		JP 2012513319	A	14-06-2012
		JP 2017019267	A	26-01-2017
		WO 2010075395	A2	01-07-2010
<hr/>				