

(12) STANDARD PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. AU 2017291057 B2

(54) Title
Synergized Acetals composition and method for scavenging Sulfides and Mercaptans

(51) International Patent Classification(s)
C09K 8/035 (2006.01) **C07D 251/02** (2006.01)
C07C 45/00 (2006.01) **C09K 8/532** (2006.01)

(21) Application No: **2017291057** (22) Date of Filing: **2017.05.17**

(87) WIPO No: **WO18/001631**

(30) Priority Data

(31)	Number	(32)	Date	(33)	Country
	15/200,471		2016.07.01		US
	15/467,688		2017.03.23		US
	15/200,390		2016.07.01		US

(43) Publication Date: **2018.01.04**

(44) Accepted Journal Date: **2021.05.20**

(71) Applicant(s)
Clariant International Ltd;Clariant S. A.

(72) Inventor(s)
De Oliveira Filho, Antonio Pedro;Kina, Alina;Taylor, Grahame;Wylde, Jonathan;Begeal, James;Yousef, Ali;Krull, Matthias;Sahl, Mike

(74) Agent / Attorney
Spruson & Ferguson, GPO Box 3898, Sydney, NSW, 2001, AU

(56) Related Art
WO 02051968 A1
US 5728263 A

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property

Organization

International Bureau




(10) International Publication Number

WO 2018/001631 A1

(43) International Publication Date

04 January 2018 (04.01.2018)



(51) International Patent Classification:

C09K 8/035 (2006.01) *C07D 251/02* (2006.01)
C07C 45/00 (2006.01) *C09K 8/532* (2006.01)

SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(21) International Application Number:

PCT/EP2017/061830

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

(22) International Filing Date:

17 May 2017 (17.05.2017)

Published:

— with international search report (Art. 21(3))

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

15/200,390	01 July 2016 (01.07.2016)	US
15/200,471	01 July 2016 (01.07.2016)	US
15/467,688	23 March 2017 (23.03.2017)	US

(71) Applicants: CLARIANT INTERNATIONAL LTD

[CH/CH]; Rothausstr. 61, 4132 Muttenz (CH).
CLARIANT S. A. [BR/BR]; Avenida das Nacoes Unidas
18001, 04795-900 Sao Paulo, 04795-900 Sao Paulo (BR).

(72) Inventors: DE OLIVEIRA FILHO, Antonio Pedro; Rua Moleire, 450 - Casa 08, Vila Sofia, CEP 04671 090 Sao Paulo SP (BR). KINA, Alina; Crispim Laranjeira 135, Apt. 302, Recreio dos Bandeirantes, 22790290 Rio de Janeiro (BR). TAYLOR, Grahame; 16438 De Lozier Street, Jersey Village, Texas 77040 (US). WYLDE, Jonathan; 54 N Turtle Rock CT, The Woodlands, Texas 77382 (US). BEGEAL, James; 829 Marbella, Cibolo, Texas 78108 (US). YOUSEF, Ali; 9227 Wind Talker, San Antonio, Texas 78251 (US). KRULL, Matthias; Am Rheinhessenblick 27, 55278 Harxheim (DE). SAHL, Mike; Erzgebirgestr. 14, 65520 Bad Camberg (DE).

(74) Agent: MIKULECKY, Klaus; Industriepark Höchst / G 860, 65926 Frankfurt (DE).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC,

A1

(54) Title: SYNERGIZED ACETALS COMPOSITION AND METHOD FOR SCAVENGING SULFIDES AND MERCAPTANS

(57) Abstract: This invention provides a composition comprising I. at least one reaction product between a nitrogen-free monohydric alcohol and an aldehyde or ketone, and II. at least one reaction product between a nitrogen-free polyhydric alcohol and an aldehyde or ketone, and optionally III. at least one reaction product from 111. a) formaldehyde, and III. b) an amine, selected from the group consisting of primary alkyl amines having 1 to 4 carbon atoms, and primary hydroxy alkyl amines having 2 to 4 carbon atoms, and optionally IV. at least one solid suppression agent selected from the group consisting of IV(a). alkali or alkaline earth metal hydroxides IV(b). mono-, di- or tri-hydroxy alkyl, aryl or alkylaryl amines, IV(c). mono-, di- or tri-alkyl, aryl or alkylaryl primary, secondary and tertiary amines or IV(d). multifunctional amines and IV(e). mixtures of compounds of groups IV(a) to IV(c). wherein alkyl is C₁ to C₁₅, aryl is C₆ to C₁₅ and alkylaryl is C₇ to C₁₅.

WO 2018/001631

SYNERGIZED ACETALS COMPOSITION AND METHOD FOR SCAVENGING SULFIDES AND MERCAPTANS

The invention relates to a composition and a process for scavenging hydrogen

5 sulfide from liquids and/or gas by using a synergistic combination of acetals with a reaction product from formaldehyde and amines and a solids suppression agent. The formulations containing the inventive composition have particular applicability in scavenging hydrogen sulfide and/or mercaptans yet at the same time prevent the formation of unwanted emulsions and/or deposition of unwanted byproducts

10 often associated with using chemistries and/or formulations of the prior art.

The presence of compounds containing a sulfhydryl group (-SH) and particularly of hydrogen sulfide pose challenges in many industries. Their presence can create a significant health, safety and environmental challenge. There are many different

15 types of compounds containing a sulfhydryl group ("sulfhydryl compounds"), with the most commonly encountered molecules including hydrogen sulfide (H₂S), organo-sulfur compounds containing R-SH groups (also called mercaptans), thiocarboxylic acids RC(O)SH, dithiocarboxylic acids RC(S)SH, and related compounds.

20

In the oil and gas industry the H₂S content of crude oil and natural gas in many areas of the world is high enough to present environmental and safety hazards.

Hydrogen sulfide is a flammable, corrosive, and highly toxic gas. H₂S is the most reduced form of sulfur and is produced by sulfate reducing bacteria (SRB) that are 25 often found in anaerobic oilfield environments, or caused by thermal cracking and thermochemical sulfate reduction (TSR) by hydrocarbons. As crude oil is produced, it is depressurized and dissolved H₂S is released and can then be transferred to, for example, oil based drilling fluid during the drilling process and this can become a hazard as the drilling fluid is recirculated from the well to the

30 surface. During the production phase of crude oil as and natural gas H₂S gas can create a significant asset integrity risk as it is an acid gas and upon dissolving into produced water creates a very corrosive environment. In addition, the presence of H₂S increases the risks of sulfide stress cracking, hydrogen embrittlement and

pitting corrosion of some structural materials and requires to be removed in order for fluids and gases to be safely processed.

The odor of sulfhydryl compounds is also a challenge in, for example, metal

5 working environments, but equally in water treatment processes, either municipal (e.g. waste water treatment) or industrial (e.g. recycling of mining water). SRB are often present in the recirculating fluid systems, and though the bacteria can usually be controlled by the use of biocidal compositions, often control of the biology in the system gets lost which results in the development of hazardous H₂S
10 and/or mercaptans in the system. Furthermore biocides are inefficient at removing H₂S after it forms and only anecdotally scavenge, *via* either oxidation (e.g. sodium hypochlorite application) or due to the release of low levels of aldehyde during their breakdown (e.g. with glutaraldehyde). Sulfhydryl compounds and particularly H₂S can present environmental, toxicity and integrity challenges in gaseous
15 phases in confined spaces, as for instance in sewage treatment facilities and particularly in shipping and storage containers for moisture sensitive materials that may emit H₂S which can accumulate in the gaseous headspace. It would be desirable to have a scavenger that can reduce the H₂S concentration in such locations.

20

Most commonly used sulfhydryl scavengers are based on metals as for example copper, zinc or iron which are converted to insoluble sulfides. A number of alternative, metal free methods have been proposed to scavenge hydrogen sulfide and to control sulfhydryl odors in hydrocarbon containing systems, including:

25

WO-98/02501 describes the use of bisoxazolidines prepared by the reaction of 1, 2 or 1, 3 amino alcohols containing 3 to 7 carbon atoms with aldehydes containing 4 or fewer carbon atoms, as for example 3,3'-methylenebis-5-methyloxazolidine. The relative oil and water solubility of these products can be controlled through the
30 choice of starting materials. These bisoxazolidines react with sulfhydryl compounds present in oil and gas streams to neutralize and therefore scavenge them.

US-5347004 teaches the use of reaction products of alkoxyalkylene amine, optionally in admixture with ammonia and/or alkylamines with aldehydes to remove H₂S from gas streams which are sparged into water solutions of the reaction products.

WO-2014/031537 teaches the use of an aldehyde releasing compound, preferably hydantoins, to remove sulfhydryl compounds from hydrocarbon fluids.

US-3928211 describes the use of inorganic zinc salts (most preferably zinc carbonate) preferably dispersed into aqueous or non-aqueous oil well drilling fluids with an organic dispersant such as lignin containing materials for scavenging hydrogen sulfide in aqueous drilling fluids.

WO-2002/051968 teaches a process for reducing the level of hydrogen sulfide in a liquid or gas by treatment of the liquid or gas with an H₂S-scavenger product derivable from the reaction of a carbonyl group-containing compound with an alcohol, thiol, amide, thioamide, urea or thiourea. The carbonyl group-containing compound is preferably formaldehyde, and preferably the product is derivable by reaction of formaldehyde with an amine-free alcohol or urea selected from ethylene glycol, propylene glycol, glycerol, diethylene glycol, triethylene glycol, ethyl alcohol, n-butanol, a sugar, a low molecular weight polyvinyl alcohol, castor oil fatty acid and urea. More especially, the scavenger product is used with an amine, especially monoethanolamine or monoethanolamine triazine.

US-4978512 teaches a method of reducing H₂S levels, the method comprising bringing the H₂S containing medium into contact with *inter alia* acetals and bisoxazolidines.

Any reference to publications cited in this specification is not an admission that the disclosures constitute common general knowledge in Australia.

Disclosed herein are compositions which can be used for scavenging of sulfhydryl compounds in crude oil, gas production, water production, water injection and combinations thereof, preferably, but not limited to, H₂S and/or mercaptans. The compositions disclosed herein may provide improved safety and/or performance compared to the formulations and chemistries of the prior art, i.e. they may contain low amounts of toxic substances like formaldehyde even after prolonged storage, have a higher scavenging efficiency and/or especially for the treatment of

gases as for example of natural gas may assure an efficient scavenging of sulphydryl compounds within a short contact time. Furthermore it is desirable to have a scavenger that does not produce unwanted solid by-products and/or form emulsions that can inadvertently contaminate the very systems they are treating.

Surprisingly it has been found that a composition comprising at least one reaction product between a monohydric alcohol and an aldehyde or ketone and at least one reaction product of a polyhydric alcohol and an aldehyde or ketone shows improved capability in scavenging sulphydryl compounds in comparison to reaction products of the individual alcohols. Such composition allows i) for a lower dosage rate of scavenger to obtain the same level of residual amount of sulphydryl compound and/or ii) for a lower level of residual amount of sulphydryl compound with the same dosage rate of scavenger. Furthermore, in combination with at least one reaction product from formaldehyde and an amine (hereinafter also referred to as "synergist") the kinetics of scavenging H₂S and/or mercaptans provided by the reaction products of a monohydric alcohol and a polyhydric alcohol with an aldehyde and/or ketone may be significantly accelerated. Alternatively or in addition to the first two components of the composition, the admixture of a solids suppression agent as further synergistic additive may facilitate the removal of sulphydryl reaction products in continuously operated scavenging processes. Furthermore such admixture may extend the gas breakthrough time of sulphydryl compounds in a contact tower containing the reaction product of a monohydric alcohol and a polyhydric alcohol with an aldehyde and/or ketone.

The use of the synergist and/or the further synergist may enable the mixed hemiacetals and acetals to react much more efficiently with sulphydryl compounds and especially with H₂S. The mechanism believed to be involved in this reaction, but should not be considered to be limiting in any way, may occur due to the likelihood that the synergist component may react preferentially with H₂S forming an intermediate reaction complex which then in turn may react with a molecule of hemiacetal respectively acetal reforming a molecule of synergist and liberation of the corresponding alcohol present in the acetal. After the H₂S scavenging process the residual synergist may then work as a corrosion inhibitor, protecting the integrity of the pipelines and equipment in which it has been applied.

Within the scope of this application the expressions "hemiacetal" and "acetal" encompass the reaction products of an alcohol with either an aldehyde or a ketone, i.e. they include hemiketals

respectively ketals when using a ketone instead of an aldehyde in the reaction with an monohydric and/or polyhydric alcohol. The expression "(hemi-)acetals" encompasses hemiacetals, acetals and their mixtures which are often formed during reaction of alcohols and carbonyl compounds.

In a first form, there is provided a composition when used for scavenging hydrogen sulphide and/or mercaptans, the composition comprising

- I. at least one reaction product between a nitrogen-free monohydric alcohol and an aldehyde or ketone, and
- II. at least one reaction product between a nitrogen-free polyhydric alcohol and an aldehyde or ketone,

wherein

the reaction products I. and II. are selected from hemiacetals and acetals,

the aldehyde or ketone contains 1 to 10 carbon atoms,

the monohydric alcohol comprises 1 to 15 carbon atoms, and

the polyhydric alcohol contains 2 to 20 carbon atoms and 2 to 6 hydroxy groups.

In a second form, there is provided a process for the scavenging of hydrogen sulphide and/or mercaptans, comprising adding to a medium comprising such hydrogen sulphide or mercaptans a composition comprising

- I. at least one reaction product between a nitrogen-free monohydric alcohol and an aldehyde or ketone, and
- II. at least one reaction product between a nitrogen-free polyhydric alcohol and an aldehyde or ketone,

wherein

the reaction products I. and II. are selected from hemiacetals and acetals,

the aldehyde or ketone contains 1 to 10 carbon atoms,
the monohydric alcohol comprises 1 to 15 carbon atoms, and
the polyhydric alcohol contains 2 to 20 carbon atoms and 2 to 6 hydroxy groups.

In a third form, there is provided use of a reaction product from formaldehyde and a compound selected from the group consisting of ammonia and an amine, the amine being selected from the group consisting of primary alkyl amines having 1 to 4 carbon atoms, and primary hydroxy alkyl amines having 2 to 4 carbon atoms, as a synergist in the reaction between hydrogen sulphide and/or a mercaptan and a composition comprising

- I. at least one reaction product between a nitrogen-free monohydric alcohol and an aldehyde or ketone, and
- II. at least one reaction product between a nitrogen-free polyhydric alcohol and an aldehyde or ketone,

wherein the reaction products I. and II. are hemiacetals and/or acetals,
the aldehyde or ketone contains 1 to 10 carbon atoms,
the monohydric alcohol comprises 1 to 15 carbon atoms, and
the polyhydric alcohol contains 2 to 20 carbon atoms and 2 to 6 hydroxy groups.

In a fourth form, there is provided a composition comprising

- I. at least one reaction product between a nitrogen-free monohydric alcohol and an aldehyde or ketone,
- II. at least one reaction product between a nitrogen-free polyhydric alcohol and an aldehyde or ketone, and
- III. at least one reaction product from formaldehyde and ammonia and/or an amine, selected from the group consisting of primary alkyl amines having 1 to 4 carbon atoms, and primary hydroxy alkyl amines having 2 to 4 carbon atoms.

wherein

the reaction products I. and II. are selected from hemiacetals and acetals,
the aldehyde or ketone contains 1 to 10 carbon atoms,
the monohydric alcohol comprises 1 to 15 carbon atoms, and
the polyhydric alcohol contains 2 to 20 carbon atoms and 2 to 6 hydroxy groups.

In a first aspect, there is provided a composition comprising

I. at least one reaction product between a nitrogen-free monohydric alcohol and an aldehyde or ketone, and

II. at least one reaction product between a nitrogen-free polyhydric alcohol and an aldehyde or ketone.

In a second aspect there is provided a composition comprising

I. at least one reaction product between a nitrogen-free monohydric alcohol and an aldehyde or ketone, and

II. at least one reaction product between a nitrogen-free polyhydric alcohol and an aldehyde or ketone, and

III. at least one reaction product from formaldehyde and ammonia and/or an amine, selected from the group consisting of primary alkyl amines having 1 to 10 carbon atoms and primary hydroxy alkyl amines having 2 to 10 carbon atoms.

In a third aspect there is provided a composition comprising

I. at least one reaction product between a nitrogen-free monohydric alcohol and an aldehyde or ketone, and

- II. at least one reaction product between a nitrogen-free polyhydric alcohol and an aldehyde or ketone, and
- III. at least one reaction product from formaldehyde and ammonia and/or an amine, selected from the group consisting of primary alkyl amines having 1 to 10 carbon atoms and primary hydroxy alkyl amines having 2 to 10 carbon atoms, and
- IV. at least one inorganic or organic alkaline compound that functions as a solids suppression agent.

10 In a fourth aspect of the invention, there is provided the use of the composition of the first, second or third aspect of the invention as a scavenger for sulfhydryl compounds for application in oilfield operations and process systems.

In a fifth aspect of the invention, there is provided a process for scavenging 15 sulfhydryl compounds in oilfield operations and process systems, the process comprising adding to a system susceptible to liberation of sulfhydryl compounds the composition of the first, second or third aspect of the invention.

In a sixth aspect of the invention there is provided the use of at least one reaction 20 product from

- III. formaldehyde and ammonia and/or an amine, selected from the group consisting of primary alkyl amines having 1 to 10 carbon atoms and primary hydroxy alkyl amines having 2 to 10 carbon atoms,

as a synergist in the reaction between

25 a) I. the reaction product between a nitrogen-free monohydric alcohol and an aldehyde or ketone, and

a) II. the reaction product between a nitrogen-free polyhydric alcohol and an aldehyde or ketone, and

b) a sulfhydryl compound.

30 In preferred embodiments of the invention, at least one demulsifier (V) and/or corrosion inhibitor (VI) is present in any aspect of the invention.

Group I

The group I compound is the reaction product of a monohydric alcohol and an aldehyde or ketone. The monohydric alcohol does not contain nitrogen.

5 Preferred monohydric alcohols as starting materials are alkyl, aryl and arylalkyl alcohols containing one hydroxy group and 1 to 15 carbon atoms, more preferably 1 to 10 carbon atoms and especially 2 to 5 carbon atoms as for example 1 to 5, 2 to 15 or 2 to 10 carbon atoms. The hydroxyl group of preferred alcohols is bound to an aliphatic, alicyclic and/or aromatic moiety, preferably to an aliphatic, alicyclic 10 and/or aromatic hydrocarbon moiety, and more especially to an aliphatic or cycloaliphatic moiety. The aliphatic and cycloaliphatic moieties may be saturated or unsaturated, preferably they are saturated. Aliphatic moieties with 3 or more carbon atoms may be linear or branched. More especially the monohydric alcohol is aliphatic. In particular the alcohol is an alkyl alcohol. Examples for preferred 15 alcohols are methanol, ethanol, propanol, iso-propanol, n-butanol, iso-butanol, tert-butanol and the various isomers of pentanol, hexanol, heptanol and octanol as for example 2-ethyl hexanol and their mixtures. Especially preferred are methanol and ethanol.

20 Preferred aldehydes or ketones as starting materials contain one or more carbonyl groups, more preferably one or two carbonyl groups and especially one carbonyl group. Furthermore, preferred aldehydes and ketones contain 1 to 10 carbon atoms, more preferably 1 to 7, and especially 1 to 4 carbon atoms. In preferred aldehydes the carbonyl group carries one and in preferred ketones two aliphatic, 25 alicyclic and/or aromatic substituents, more preferably aliphatic, alicyclic and/or aromatic hydrocarbon substituents. Preferred aliphatic and cycloaliphatic substituents may be saturated or unsaturated, most preferably they are saturated. In ketones both substituents may be the same or different.

30 In a preferred embodiment the carbonyl compound is an aldehyde, more preferably a mono- or di-aldehyde, and especially formaldehyde. It should be understood that the terms "aldehyde" and "formaldehyde" include precursors like e.g. para-formaldehyde, formalin, and other chemical forms from which the basic

structure HCHO can be released or set free during the reaction with an alcohol. Other suitable aldehydes include, for example, acetaldehyde, propionaldehyde, butyraldehyde, glutaraldehyde and glyoxal. Suitable ketones include, for example, acetone, methyl ethyl ketone, diethylketone, methyl isopropyl ketone, hexanones 5 and heptanones.

Mixtures of two or more carbonyl compounds, for example two or more of the aldehydes mentioned above, e.g. formaldehyde and one or more other aldehydes, may be used if desired.

10

In the reaction between monohydric alcohol and aldehyde and/or ketone part or all of the alcohols may be converted to hemiacetals and/or acetals. In a preferred embodiment, the reaction product is a hemiacetal. In a preferred embodiment at least 50 mol-% of the alcohol, more preferably 60 to 99 mol-% of the alcohol, 15 especially 65 to 95 mol-% of the alcohol and especially preferred 70 to 90 mol-% of the alcohol as for example more than 60 mol-%, more than 65 mol-%, more than 70 mol-%, % of the alcohol or 50 to 99 mol-%, 50 to 95 mol-%, 50 to 90 mol-%, 60 to 95 %, 60 to 90 mol-%, 65 to 99 mol-%, 65 to 90 mol-%, 70 to 99 mol-% or 70 to 95 mol-% of the alcohol are converted to hemiacetals and/or acetals. In case 20 the degree of conversion is low some unreacted monohydric alcohol remains in the composition. The presence of residual alcohol in the reaction mixture has proven to be advantageous as upon its reaction with sulphhydryl compounds often the formation of solid precipitate gets reduced. Furthermore, remaining alcohol will act as a solvent.

25

Group II

The group II compound is the reaction product of a polyhydric alcohol and an aldehyde or ketone. The polyhydric alcohol does not contain nitrogen.

30 Preferred polyhydric alcohols as starting materials contain 2 to 20 carbon atoms and two or more hydroxyl groups. A preferred polyhydric alcohol contains, 2 to 6, more preferably 3 to 6 hydroxy groups. Preferred polyhydric alcohols contain 2 to 50, more preferably 2 to 20 and especially 3 to 10 carbons atoms as for example 2

to 10 carbon atoms, 3 to 50 carbon atoms or 3 to 20 carbon atoms. Preferably they are aliphatic. Examples for preferred polyhydric alcohols are ethylene glycol, propylene glycol, butylene glycol, pentanediol, neopentyl glycol, hexanediol, glycerol, pentaerythritol, diethylene glycol, triethylene glycol, an oligomer of 5 glycerol with 2 to 15 and especially 3 to 10 as for example 2 to 10 or 3 to 15 repeating units, a sugar molecule (i.e. a monosaccharide or disaccharide compound), or a polyvinyl alcohol of low molecular weight such that the reaction product with the carbonyl starting material remains a liquid. It is preferred that the 10 number of hydroxyl groups in the polyhydric alcohol is lower or at most equal to the number of carbon atoms. Most preferred polyols are ethylene glycol and glycerol.


Preferred aldehydes and ketones as starting materials for the group II compounds are the aldehydes and ketones that have already been described above with 15 respect to Group I. Most preferred aldehyde for group II compounds is formaldehyde. The aldehyde or ketone used for reaction with the polyhydric alcohol may be the same as the one used for the monohydric alcohol, or it may be a different one.

20 In the reaction between polyhydric alcohol and aldehyde and/or ketone part or all of the hydroxyl groups may be converted to hemiacetals and/or acetals. In a preferred embodiment at least 50 mol-% of the hydroxyl groups, more preferably 60 to 99 mol-% of the hydroxyl groups, especially 65 to 95 mol-% of the hydroxyl groups and especially preferred 70 to 90 mol-% of the hydroxyl groups as for 25 example more than 60 mol-%, more than 65 mol-%, more than 70 mol-%, % of the alcohol or 50 to 99 mol-%, 50 to 95 mol-%, 50 to 90 mol-%, 60 to 95 %, 60 to 90 mol-%, 65 to 99 mol-%, 65 to 90 mol-%, 70 to 99 mol-% or 70 to 95 mol-% of the hydroxyl groups are converted to hemiacetals and/or acetals. In case the degree of conversion is low some unreacted polyhydric alcohol remains in the 30 composition. The presence of residual hydroxyl groups in the reaction mixture has proven to be advantageous as upon its reaction with sulphhydryl compounds the formation of solid precipitate gets reduced.

In a particularly preferred embodiment the reaction product is predominantly a hemiacetal derived from the polyhydric alcohol. Especially preferred are reaction products wherein the ratio between hemiacetals and acetals on a molar basis is between 50:1 and 1:10 and especially between 20:1 and 1:2 as for example

5 between 50:1 and 1:2 or between 20:1 and 1:10.


Preferred polyhydric hemiacetal compounds that can be used as the scavenger are described by the structures (2) to (5) below:



wherein

R_1 is H or C_1 to C_8 alkyl, and


R_2 is H or CH_2OH .



wherein


p is a number from 2 to 10, and

R_2 is H or CH_2OH



wherein

R_3 and R_4 independently are H or CH_2OH




wherein

m is 1 to 10, preferably 1 or 2

5 The most preferred structures are the ones derivable from either glycerol or ethylene glycol. These correspond to the formulae (3) and (4), or formula (2) wherein R₁ is H.

In another specific preferred embodiment the hemiacetal can have the structure below

10



wherein

R₅ is H, CH₃, (CH₂)₂CH₃, with the proviso that not all of R₅ are hydrogen,

15 z is 1 to 10, and

x is 1 to 5.

Reactions of aldehydes and ketones with alcohols are described in the literature.

"Formaldehyde", p 265, Joseph Frederic Walker, reprint 1975, Robert E. Krieger

20 Publishing Company Inc. discloses that hemiacetals are obtained when formaldehyde and alcohols are brought together under neutral or alkaline conditions, and that they form readily in the case of primary and secondary alcohols.

25 The synthesis of compounds of group I and group II may be accomplished in separate reactions. Preferably it is accomplished in a simultaneous reaction using a one pot reaction by charging a mixture of monohydric alcohol and polyhydric alcohol and reacting this mixture with the aldehyde and/or ketone. A one-pot reaction is especially preferred when the aldehyde used for the reaction with the 30 monohydric alcohol is the same as the aldehyde used for the reaction with the polyhydric alcohol.

In the synthesis of compounds of group I and group II the molar ratio of hydroxyl groups to carbonyl groups is preferably between 20:1 and 1:5 and more preferably between 10:1 and 1:2 and especially between 2:1 and 1:1 as for example between 5 20:1 and 1:2 or between 20:1 and 1:1 or between 10:1 and 1:5 or between 10:1 and 1:1 or between 2:1 and 1:5 or between 2:1 and 1:2.

Group III

The group III component is optional. The group III compound is the reaction 10 product from formaldehyde with ammonia and/or an amine, the amine being selected from the group consisting of primary alkyl amines having 1 to 10 carbon atoms and primary hydroxy alkyl amines having 2 to 10 carbon atoms. This group comprises the synergist component of the inventive composition.

15 Preferred primary amines comprise 1 to 4 carbon atoms, preferred primary hydroxy amines 2 to 4 carbon atoms. Especially preferred primary hydroxy amines correspond to the formula (1)



20

wherein A is a linear or branched alkylene group with 2 to 4 carbon atoms.

Examples of nitrogen containing compounds suitable for the present invention include, but are not limited to: ammonia, methylamine, ethylamine, propylamine, 25 isopropyl amine, monoethanolamine, 1-amino-2-propanol, 3-amino-1-propanol, 2-amino-1-butanol, 3-amino-1-butanol, 3-amino-1-butanol, 2-ethoxypropylamine, 3-ethoxypropylamine, 1-methoxyisopropylamine and 2-methoxyethylamine.


The nitrogen containing compound and formaldehyde may be reacted in any molar 30 ratio with a preferred ratio being from 1 mole aldehyde to 10 moles nitrogen containing compound to 10 moles aldehyde to 1 mole nitrogen containing compound, a more preferred ratio being from 1 mole aldehyde to 5 moles nitrogen containing compound to 5 moles aldehyde to 1 mole nitrogen containing

compound, an even more preferred ratio being 1 mole aldehyde to 3 moles nitrogen containing compound to 3 moles aldehyde to 1 mole nitrogen containing compound and a most preferred ratio being 1 mole aldehyde to 1 mole nitrogen containing compound.

5

The structure of the aminal formed from the reaction of formaldehyde and nitrogen containing compound is dependent upon the selected nitrogen containing compound and the selected molar ratio between formaldehyde and nitrogen compound, as is self-evident to those of ordinary skill in the art. Similarly, mixtures 10 of the above nitrogen containing compounds may also be reacted in order to form singular, or mixtures of various aminals as is also evident to one of ordinary skill in the art.

In one preferred embodiment the reaction product corresponds to formula (1a)



15

wherein


R is H or methyl, and

n is 1 or 2.

20

In an especially preferred embodiment R is CH₃. In another especially preferred embodiment, n is 1. In a particularly preferred embodiment n is 1 and R is CH₃. The name of this compound is 3,3'-methylenebis-5-methyl-oxazolidine (MBO).

In another preferred embodiment the reaction product corresponds to formula (1b)



5 wherein each R¹ is C₁ to C₄ alkyl or C₂ to C₄ hydroxy alkyl. Examples for especially preferred compounds are hexahydro-1,3,5-trimethyl-s-triazine, hexahydro-1,3,5-triethyl-s-triazine, hexahydro-1,3,5-tris(hydroxymethyl)-s-triazine and hexahydro-1,3,5-tris(2-hydroxyethyl)-s-triazine.

10 Mixtures of different reaction products of structures 1a and 1b are equally suited. The substituents R and R¹ may be the same or different.

Group IV

15 The group IV component is optional. The group IV compound is an inorganic or organic alkaline compound. This group comprises the solids suppression agent.

The solid usually formed by the reaction of group I and group II compounds with hydrogen sulfide is 1,3,5-trithiane. Addition of an alkaline compound to the compounds of groups I and II prevents or at least retards the formation of the 20 poorly soluble 1,3,5-trithiane upon reaction with sulfhydryl compounds. Without being bound to this theory it is believed that different intermediates as for example polyoxymethylenesulfide oligomers are formed and stabilized by the presence of the alkaline compound of group IV. By preventing the formation of solids the scavenging composition remains homogeneous and especially in a contact tower 25 application allows for more efficient and up to quantitative use of the (hemi-)acetals of group I and II compounds and thereby reduces the amount of chemicals required. This may result in an extended gas breakthrough time in such scavenging applications. Additionally, in direct injection applications for continuous scavenging of sulfhydryl compounds from e.g. natural gas streams the removal of

the liquid reaction products is much easier than removal of solids and it is not prone to blockage of tubings.

Furthermore, in the presence of an alkaline compound of group IV the stability of

5 compounds I and II is increased and gassing of formaldehyde is reduced or even prevented. This leads to a reduced level of free formaldehyde in the space above the composition and thereby improves the safety of the personnel handling the inventive composition.

10 Preferably, the compound of group IV is soluble in, or miscible with the mixture of compounds of groups I and II. In a further preferred embodiment the compound of group IV is soluble in, or miscible with the formulation of the mixture of compounds of groups I and II in the presence of an aqueous solvent.

15 In a preferred embodiment, the alkaline compound is selected from the group consisting of

IV(a). alkaline metal salts or alkaline earth metal salts,

IV(b). ammonia; alkyl, aryl or alkylaryl amines,

20 IV(c). hydroxy alkyl, hydroxyl aryl or hydroxy alkylaryl amines,

IV(d). multifunctional amines, and

IV(e). mixtures of compounds of groups IV(a) to IV(c).

In an aryl amine, the N atom is bonded to the aromatic system. In an alkyl aryl

25 amine, the N atom may be bonded to either the aromatic system or the alkyl group.

Preferred cations of the alkaline metal and alkaline earth metal salts IV(a) are

derived from lithium, sodium, potassium, rubidium, beryllium, magnesium, calcium

30 and strontium with sodium, potassium and calcium being especially preferred.

Preferred anions are hydroxyl and carbonate groups with hydroxyl being especially

preferred. Examples for preferred alkali or alkaline earth metal salts LiOH, NaOH,

KOH, Mg(OH)₂, Ca(OH)₂, Be(OH)₂, Na₂CO₃, K₂CO₃, NaHCO₃, KHCO₃, BeCO₃,

MgCO_3 , CaCO_3 , $\text{Mg}(\text{HCO}_3)_2$, $\text{Ca}(\text{HCO}_3)_2$ and their mixtures. Especially preferred alkali and alkaline earth metal salts of group IVa are NaOH , KOH , $\text{Mg}(\text{OH})_2$ and $\text{Ca}(\text{OH})_2$.

- 5 The amines of group IV(b) may be primary, secondary or tertiary amines. Preferred amines have up to 20 carbon atoms, more preferably between 1 and 10 and especially between 2 and 4 carbon atoms as for example between 1 and 20, between 1 and 4, between 2 and 20 or between 2 and 10 carbon atoms. Preferred hydrocarbyl residues are alkyl, aryl and alkylaryl residues, with alkyl residues being particularly preferred. Especially preferred amines are alkyl amines with 1 to 4 carbon atoms per alkyl residue. Examples for especially preferred amines are methylamine, dimethylamine, trimethylamine, ethylamine, diethylamine, triethylamine, propylamine, isopropylamine and butylamine.
- 10
- 15 The hydroxy amine of group IV(c) may be a primary, secondary or tertiary amine. It may contain one, two or three hydroxy groups. In a preferred embodiment each hydrocarbyl substituent of the nitrogen is substituted by not more than one hydroxy group. Preferred amines have up to 20 carbon atoms, more preferably between 1 and 10 and especially between 2 and 4 carbon atoms as for example between 1 and 20, between 1 and 4, between 2 and 20 or between 2 and 10 carbon atoms. Preferred hydrocarbyl residues are alkyl, aryl and alkylaryl residues, with alkyl residues being particularly preferred. Especially preferred hydroxy amines are hydroxyalkyl amines with 1 to 4 carbon atoms per alkyl residue. Examples for especially preferred hydroxy amines of group IV(c) are monoethanolamine, diethanolamine, 1-amino-2-propanol, 3-amino-1-propanol, 2-amino-1-butanol, 3-amino-1-butanol, 3-amino-1-butanol, 2-ethoxypropylamine, 3-ethoxypropylamine, 1-methoxyisopropylamine, 2-methoxyethylamine, 2-(2-aminoethoxy)ethanol, dimethylethanolamine, N-methyldiethanolamine and monomethylethanolamine.
- 20
- 25
- 30 Preferred multifunctional amines of group IV(d) contain, besides an amino group, at least one further functional group selected from the group consisting of amino groups, ether groups and acid groups or an ester, amide or salt thereof. Preferred

multifunctional amines have up to 50 carbon atoms, more preferably between 1 and 20 and especially between 2 and 10 carbon atoms as for example between 1 and 50, between 1 and 10, between 2 and 50 or between 2 and 20 carbon atoms.

The hydrocarbon chains may be linear, branched and/or cyclic. In a preferred

5 embodiment they contain 1 to 10 and especially 2 to 5 as for example 1 to 5 further amino groups and/or ether groups. Preferably the amino- and/or ether groups are separated by at least two carbon atoms. Examples for especially preferred multifunctional amines of group IV(d) are ethylenediamine, diethylenetriamine, triethylenetetramine, tetraethylenepentamine, poly(ethylene 10 imine), propylene diamine, dipropylenetriamine, N,N-dimethylpropylenetriamine, aminoethylenepiperazine, aminoethylethanolamine, tallow fatty propylene diamine ethoxylated with 2 to 20 moles ethylene oxide, oleyl amine ethoxylated with 2 to 20 mole ethylene oxide, morpholine and piperazine.

15 In a further preferred embodiment the multifunctional amines of group IV(d) contain, besides an amino group, an acid group or an ester, amide or salt thereof. Preferred acid groups are sulfonic acids, phosphoric acids and carboxylic acids. Especially preferred multifunctional amines carrying a carboxylic acid group are amino acids. Preferred amino acids include proteinogenic and non-proteinogenic 20 amino acids. The amino group and the carboxylic acid group may be located at the same or at different carbon atoms. Carboxylic acid groups and other acidic groups are especially preferred in their neutralized form, e.g. as alkaline or earth alkaline salts. Especially preferred amino acids contain further functional groups including, hydroxyl, carboxyl, amide, ether, guanidino, hydroxyphenyl, imidazolyl and/or 25 further amine groups. Examples of preferred multifunctional amines carrying an acid group are glycine, alanine, leucine, isoleucine, proline, serine, threonine, asparagine, glutamine, phenylalanine, tryptophan, tyrosine, valine, aspartic acid, glutamic acid, methionine, sarcosine and taurine and their carboxylate salts with sodium and/or potassium. Especially preferred amino acids are glycine, lysine, 30 histidine and arginine.

When mixtures IV(d) of alkaline compounds of the groups IV(a) to IV(c) are used, they may comprise 2 or more, preferably 2 to 10 and especially 3 to 5 as for

example two, three, four or five different components selected from the groups IV(a) to IV(c). The portion of each individual compound in the mixture of the compounds of groups IV(a) to IV(c) is preferably between 5 and 95 wt.-%, more preferably between 10 and 90 wt.-% and especially between 20 and 80 wt.-% as 5 for example between 5 and 90 wt.-%, between 5 and 80 wt.-%, between 10 and 95 wt.-%, between 10 and 80 wt.-%, between 20 and 95 wt.-% or between 20 and 90 wt.-%.


Group V

10 The group V component is optional. This group comprises emulsion breakers, demulsifiers and/or non-emulsifiers. The purpose of having the compounds of group V present is to prevent the formation of emulsions during the scavenging process and to improve the efficiency of the scavenging process. Often metal sulfides as for example iron sulfide are formed e.g. by corrosion of pipelines and 15 equipment in the presence of sulfhydryl compounds. Being in the form of fine solids they accumulate at the oil water interface, thereby stabilizing the water present in the oil and generating a stable emulsion which may affect phase separation and accessibility of the sulfhydryl compounds to be scavenged. The purpose of the emulsion breaker, demulsifier and/or non-emulsifier is to break the 20 oil/water emulsion by creating a preferentially water wet surface on the metal sulfide and also to modify the surface tension at the oil/water interface which is stabilized by the metal sulfides to one allowing coalescence of the emulsion .

In a preferred embodiment, the emulsion breaker of group V is part of the inventive 25 composition comprising compounds of groups I and II, of groups I, II and III, of groups I, II and IV or of groups I, II, III and IV. Preferred emulsion breakers are polymeric nonionic surfactants, including but not limited to polysorbates, polymers comprising ethylene oxide, polymers comprising propylene oxide, ethylene oxide-propylene oxide copolymers, alkyl polyglucosides such as decyl maltoside, 30 alkylphenol ethoxylates, and ethoxylated and/or propoxylated alkyl phenol-formaldehyde resins. The emulsion breaker can also be a fatty alcohol alkoxylated with 1 to 200 moles, preferably with 2 to 100 moles and especially with 5 to 50 moles as for example with 1 to 100 moles or 1 to 50 moles or 2 to 50 moles or with

5 to 100 moles of alkylene oxide. Examples for preferred alkylene oxides are ethylene oxide, propylene oxide and their mixtures; preferred fatty alcohols have a C₄- to C₃₆-alkyl residue and especially a C₈- to C₂₄-alkyl residue as for example a C₄- to C₂₄-alkyl residue or a C₈- to C₃₂-alkyl residue such as cetyl alcohol and oleyl alcohol.

In a preferred embodiment, the emulsion breaker is a compound according to the formula (6)



wherein

R₁₀ C₂ to C₄ alkylene

R₁₁ C₁ to C₁₈ alkyl

15 k a number from 1 to 200

m a number from 1 to 100 is.

In a preferred embodiment R₁₀ is an ethylene or a propylene group. R₁₀ may represent mixtures of different C₂ to C₄ alkylene groups, preferably ethylene and

20 propylene groups.

In another preferred embodiment, R₁₁ is a C₄ to C₁₂ alkyl group, more preferably a tertiary butyl group or an iso-nonyl group.


25 In formula (6), R₁₀, R₁₁ and k may be the same in each of the repeating units, or they may differ from unit to unit.

In another preferred embodiment k is a number from 2 to 20.

In another preferred embodiment m is a number from 3 to 20.

In another specific preferred embodiment the emulsion breaker is an

5 alkylbenzenesulfonic as for example dodecylbenzesulfonic acid (7) or its salt with an alkaline metal, ammonia or a primary, secondary or tertiary amine as for example methylamine, ethylamine, propylamine, diethylamine, dimethylamine, trimethylamine, ethanolamine, diethanolamine or triethanolamine.



10

In another preferred embodiment, the demulsifier is a mixture of at least one compound of formula (6) and an alkylbenzene sulfonic acid (7) or its salt. Such mixture preferably contains (6) and sulfonic acid (7), respectively its salt, in a weight ratio of from 5:1 to 1:5, more preferably in a weight ratio of from 3:1 to 1:

15 weight ratio of from 5:1 to 1:5, more preferably in a weight ratio of from 3:1 to 1:3.

The polymeric nonionic surfactant may be added to the further components of the inventive composition neat or preferably dissolved or suspended in a solvent. Any solvent suitable for dissolving or suspending a polymeric nonionic surfactant may be used. Examples of suitable solvents include water, ethylene glycol, propylene glycol, butylene glycol, oligoethylene glycols, oligopropylene glycols, ethers including glycol ethers like methoxyethane, dimethoxyethane and butoxyethanol, alcohols, toluene, xylene, aromatic naphtha, or any combination thereof. The alcohol may include any alcohol suitable for use with oil recovery and for dissolving the polymeric nonionic surfactant and is preferably selected from the

group consisting of methanol, ethanol, propanol, isopropyl alcohol, butanol, 2-ethyl hexanol or any combination thereof.

Group VI


5 The group VI component is optional. This group comprises corrosion inhibitors and serves to add corrosion inhibition functionality to the inventive composition. The addition of a corrosion inhibitor may not be required because the synergist of group III provides sufficient corrosion inhibition to protect the integrity of the whole asset.

10

However, often addition of a further corrosion inhibitor is advisable to reduce the overall corrosivity, protecting the tubulars and production equipment from corrosion caused by oilfield fluids and gases into which the instant invention is deployed.

15

A preferred embodiment of the current invention is to use alkyl dimethyl benzyl ammonium chloride according to formula (8) as a corrosion inhibitor that also provides functionality as an interfacial tension reducer.



20

wherein R⁹ is C₈ to C₁₈ alkyl.

The inventive composition may additionally contain biocides, for example, 25 formaldehyde or glutaraldehyde, water dispersants such as polyacrylamide dispersants, oxygen scavengers, antifoams such as acetylenic diols, silicones or polyethoxylated antifoams, and/or flocculants. Preferably their content is less than 10 wt.-% and especially less than 5 wt.-% relative to the components of the groups I to VI.

In a preferred embodiment, the inventive composition comprises 5 to 60 wt.-% of the reaction product of the monohydric alcohol described above in group I, preferably between 10 and 50 wt.-% and especially between 15 and 40 wt.-% as 5 for example between 5 and 50 wt.-% or between 5 and 40 wt.-% or between 10 and 60 wt.-% or between 10 and 40 wt.-% or between 15 and 60 wt.-% or between 15 and 50 wt.-%.

In a preferred embodiment, the inventive composition comprises 10 to 90 wt.-% of 10 the reaction product of the polyhydric alcohol described above in group II, preferably between 20 and 80 wt.-% and especially between 25 and 75 wt.-% as for example between 10 and 80 wt.-% or between 10 and 75 wt.-% or between 20 and 90 wt.-% or between 20 and 75 wt.-% or between 25 and 90 wt.-% or between 25 and 80 wt.-%.

15 The molar ratio between the reaction product of the monohydric alcohol and an aldehyde or ketone (group I) and the reaction product of the polyhydric alcohol and an aldehyde or ketone (group II) is preferably between 20:1 and 1:20, preferably between 10:1 and 1:10 and especially between 5:1 and 1:5 as for example 20 between 20:1 and 1:10, between 20:1 and 1:5, between 10:1 and 1:20, between 10:1 and 1:5, between 5:1 and 1:20 or between 5:1 and 1:10.

In a preferred embodiment, the inventive composition comprises 0.1 to 15 wt.-% of 25 the synergist described above in Group III, preferably between 0.5 and 10 wt.-% and especially between 1 and 8 wt.-% as for example between 0.1 and 10 wt.-% or between 0.1 and 8 wt.-% or between 0.5 and 15 wt.-% or between 0.5 and 8 wt.-% or between 1 and 15 wt.-% or between 1 and 10 wt.-%.

In a preferred embodiment, the inventive composition comprises 1 to 25 wt.-% of 30 at least one solids suppression agent described above in group IV, preferably between 5 and 20 wt.-% and especially between 7 and 18 wt.-%, as for example between 1 and 20 wt.-% or between 1 and 18 wt.-% or between 5 and 25 wt.-% or between 5 and 18 wt.-% or between 7 and 25 wt.-% or between 7 and 20 wt.-%.

In a preferred embodiment, the inventive composition comprises 0.1 to 10 wt.-% of at least one emulsion breaker described above in group V, preferably between 0.5 and 5 wt.-%.

5

In a preferred embodiment, the inventive composition comprises 0.1 to 10 wt.-% of the corrosion inhibitor described above in group VI, preferably between 0.2 and 5 wt.-%.

10 The preferred portions of the individual compounds of groups I to VI in the inventive composition are given in relation to the total quantity of the compounds of groups I to VI. In a preferred embodiment the compounds of groups I to IV sum up to 100 wt.-%.

15 The inventive composition is preferably applied to the oil or gas to be treated in amounts of 0.5 to 50 wt.-ppm, more preferably 1 to 30 wt.-ppm and especially 2 to 20 wt.-ppm as for example 0.5 to 3 wt.-ppm, 0.5 to 20 wt.-ppm, 1 to 50 wt.-ppm, 1 to 20 wt.-ppm, 2 to 50 wt.-ppm or 2 to 30 wt.-ppm per 1 ppm of sulfur contained in the oil or gas.

20

The use of undiluted compositions according to the invention has proven especially successful in gas contact towers.

25 In a preferred embodiment the compositions according to the different aspects of the invention are used in formulations additionally comprising water. The water in the formulation may be formed during the manufacture of hemiacetals, or it can be added to the composition to balance the formulation. Preferably water is present in a concentration from 1 to 90 wt.-%, preferably between 5 and 80 wt.-% as for example between 1 and 80 wt.-% or 5 and 90 wt.-% of the formulation. In another 30 preferred embodiment water is present to balance up to 100 wt.-% of the formulation.

Alternatively, any balance remaining in a formulated composition according to the different aspects of the invention is made up with water and/or glycol and/or alcohol based solvents in the amounts given above for water alone. Preferred alcohols and glycols are selected from, but not limited to, methanol, ethanol, 5 propan-1-ol, propan-2-ol, ethylene glycol, diethylene glycol, triethylene glycol, neopentyl glycol, 2-butoxyethanol and their mixtures.

The inventive compositions can be made by mixing of the compounds of groups I and II, of groups I, II and III, of groups I, II and IV respectively of groups I, II, II and 10 IV each optionally with compounds of groups V and/or VI. The sequence of addition of the individual compounds is not important. In a preferred embodiment the compounds of groups I and II are produced simultaneously in a single pot reaction and subsequently the compounds of groups III and/or IV and optionally V and/or VI are added. For the production of formulations water and/or other 15 solvents can be added to the inventive composition. Alternatively, some or all of the components to make up the inventive composition may contain solvent.

A formulated product containing the inventive composition and solvent is preferably applied in concentrations between 5 and 40,000 mg/L, preferably 20 between 50 and 30,000 mg/L and especially between 100 and 25,000 mg/L as for example between 5 and 40,000 mg/L, between 5 and 25,000 mg/L, between 50 and 40,000 mg/L, between 50 and 25,000 mg/L, between 100 and 40,000 mg/L and between 100 and 30,000 mg/L based on the volume of oil or gas production to be treated. The preferred and best suited concentration of the formulation depends 25 on the formulation activity itself, the type and amount of sulfhydryl compounds to be scavenged, static conditions, temperature and salinity of the system. Furthermore, the material grade of the equipment used for operating the scavenging process should be taken into account: If e.g. a contact tower is made of stainless steel a more concentrated product can be applied while it has proven 30 to be advantageous to apply more dilute product formulations, preferably containing a corrosion inhibitor of group VI, if a poor material of construction as for example carbon steel is used.

At the given concentration range, the inventive composition provides substantial scavenging of sulfhydryl compounds from the produced liquids and ensures a specified sulfur content of the produced hydrocarbon as it is brought to the market and therefore safe handling. Furthermore flowability of the treated hydrocarbon will

5 not be impaired due to prevention of the formation of solid reaction products.

The present invention also includes a process for application of the inventive composition in scavenging of sulfhydryl compounds present in the drilling and the production cycle of mineral oil, particularly as a component of well work-over, well

10 intervention, production enhancement and flow assurance packages.

The composition according to the invention may be injected into a sulfhydryl compound containing stream together with other ingredients known to those familiar with the art. Such other ingredients include acids, dispersants, viscosifiers,

15 lubricity agents, scale inhibitors, friction reducers, cross linker, surfactants, pH adjuster, iron control agents, breakers; this is especially advantageous if any produced water (or recycled water) is in contact with the compositions of the instant invention.

20 Employing the embodiments of the instant invention allows either i) for a lower dosage rate of scavenger to obtain the same level of residual amount of sulfhydryl compound or ii) for a lower level of residual amount of sulfhydryl compound with the same dosage rate of scavenger in comparison to hemiacetals and/or acetals according to the state of the art. Additionally, in combination with a reaction

25 product from formaldehyde and an amine the kinetics of scavenging H₂S and/or mercaptans provided by the mixture of hemiacetals and/or acetals of a monohydric alcohol and a polyhydric alcohol with an aldehyde and/or ketone can be significantly accelerated. This allows for a much more efficient scavenging of sulfhydryl compounds especially in applications where only short contact times

30 between the oil or gas and the scavenger are available, as for example in contact towers and direct injection applications for treatment of gases. By admixture of a solids suppression agent as a further synergistic additive the gas breakthrough time of a system containing sulfhydryl compounds is extended. While improving

the scavenging of sulphydryl compounds no formation of complex and difficult to treat emulsions is observed. Furthermore the embodiments of the instant invention will not corrode the oilfield equipment that it comes into contact with, nor will it allow the deposition of unwanted solids, such as polymethylenesulfide oligomers

5 and metal sulfide scales, so often found with applications of the prior art. Other applications of the embodiments of the instantaneous invention include treating water for downhole injection for pressure support, treatment of drilling and work-over operations, wettability alteration and well cleanout.

10 Within this specification, percentages are weight percentages unless specified otherwise.

EXAMPLES

15

Preparation of hemiacetals

In a stirred reactor alcohols were charged with the quantity given in table 1 together with 0.25 wt.-% of sodium hydroxide solution at 50 wt.-%. This mixture was homogenized for 10 minutes before paraformaldehyde (93 wt.-%) was added

20 in the amounts given in table 1 over a period of approximately 30 minutes. The reaction mixture was warmed while stirring for 2 hours at a temperature between 80 to 85 °C. After the reaction time, the mixture was cooled to 30 °C.

In the reaction products the molar amounts of hemiacetal in respect to the total

25 amount of hydroxyl groups charged and the content of free formaldehyde (CH_2O) were determined by ^1H NMR spectroscopy.

30

Table 1: Preparation of hemiacetals and acetals

(Hemi-) acetal	Reactor charge			reaction product	
	monohydric alcohol; charge [g]	polyhydric alcohol; charge [g]	paraform aldehyde [g]	(hemi-) acetal	CH ₂ O [wt.-%]
A1	methanol 500	—	500	98 %	0.07
A2	ethanol 600	—	420	99 %	0.06
A3	i-propanol 600	—	320	99 %	0.08
A4	2-EH 800	—	200	98 %	0.11
A5	—	ethyleneglycol 500	520	97 %	0.12
A6	—	diethyleneglycol 600	360	96 %	0.16
A7	—	glycerol 600	410	66 %	0.05
A8	—	pentaerythritol 500	480	98 %	0.12
A9	—	pentaerythritol 600	430	75 %	0.04
A10	ethanol 100	ethyleneglycol 490	430	75 %	0.02
A11	ethanol 80	ethyleneglycol 400	470	99 %	0.03
A12	methanol 70	glycerol 550	450	70 %	0.02
A13	methanol 80	glycerol 570	370	55 %	0.02
A14	ethanol 120	Glycerol 450	440	80 %	0.02
A15	ethanol 160	pentaerythritol 350	440	98 %	0.03

2-EH = 2-ethyl hexanol

5 Further materials used were

- hexahydro-1,3,5-trimethyl-s-triazin (HTT) and 3,3'-methylenebis-5-methyloxazolidine (MBO) as the synergists according to group III.
- NaOH (5 wt.-% aqueous solution), triethylamine (TEA), monoethanolamine (MEA) and piperazine (PIP) were used as the solids suppressants according to group IV. All these materials were commercial grades.

Scavenger performance tests – efficiency

In order to demonstrate the improved efficiency of the instant invention in

removing sulfhydryl compounds compared to group I respectively group II compounds alone, the removal of H₂S from an oil and from an oil/water mixture was measured.

5 The oil used was a mixture of kerosene with 10 % of xylene with zero bottom sediment and water (BS&W) to simulate oil field conditions.

10 The oil/water mixture was a mixture of the oil described above and brine (in a 50:50 volume ratio of oil to aqueous phase) to mimic the efficiency in hydrated crude oil.

In a 500 mL stirred autoclave (Parr reactor), 350 mL of the oil respectively the oil/brine mixture was de-aerated for 1 hour with N₂, then saturated with a sour gas mixture of 0,2 wt.-% H₂S and 99,8 wt.-% CO₂, by purging this gas into the oil resp. 15 oil/brine mixture with a flow rate of 0.6 L/min. After equilibration by the sour gas mixture, 1.000 ppm of the composition to be tested was injected into the autoclave by an HPLC pump. If mixtures of (hemi-)acetals were used, their proportions by weight are given in tables 2 and 3; the amounts of synergist and solids 20 suppressant refer to their portion in the composition and are therefore included in said dosage rate.

The performance tests were carried out at 30 °C and under 1 bar, using a gas chromatograph to measure the outlet H₂S content in the gas phase every two minutes. Then, a graph of the measured values of H₂S content (ppm) versus time 25 (min) was plotted. The amount of hydrogen sulfide scavenged is the area above the resultant performance curve, which is calculated by the integration of the curve. For all samples the integration of the curve was done up to 60 min after the injection of H₂S-scavenger. As the output parameter of this performance test L_{sc}/kgH₂S (Liters of H₂S scavenger required to remove 1 kg of H₂S from the 30 system) has been determined for 6 minutes and 1 hour of analysis. All consumption values are averages of three repeat tests. The test results have been summarized in Table 2 and Table 3. Percentages mean weight percent if not indicated otherwise.

5

Table 2: Performance tests for H₂S-scavengers in oil (zero BS&W)

Example	(Hemi)acetal	Synergist (2 wt.-%)	solids suppressant	L _{sc} /kg H ₂ S	
				@ 6 min.	@ 1 hour
P1 (comp.)	A2	—	—	20,76	9,56
P2 (comp.)	A3	—	—	21,23	10,04
P3 (comp.)	A4	—	—	32,60	16,20
P4 (comp.)	A5	—	—	18,65	9,01
P5 (comp.)	A6	—	—	18,09	8,47
P6 (comp.)	A1 +A2 (1:1)	—	—	19,12	9,85
P7 (comp.)	A5 + A6 (2:1)	—	—	17,24	8,86
P8	A2 + A5 (1:4)	—	—	14,10	7,02
P9	A2 + A5 (1:1)	—	—	14,48	7,35
P10	A4 + A5 (1:3)	—	—	13,86	7,13
P11	A10	—	—	12,95	6,89
P12	A11	—	—	13,22	6,70
P13	A3 + A6	—	—	14,27	7,54
P14(comp.)	A2	MBO	—	5,65	4,63
P15(comp.)	A3	MBO	—	5,86	4,86
P16 (comp.)	A4	MBO	—	9,98	8,05
P17 (comp.)	A5	MBO	—	5,10	4,21
P18 (comp.)	A6	MBO	—	5,28	4,36
P19	A2 + A5 (1:4)	MBO	—	3,10	2,72
P20	A2 + A5 (1:1)	MBO	—	3,21	2,86
P21	A4 + A5 (1:3)	MBO	—	3,25	2,80

P22	A10	MBO	—	2,98	2,61
P23	A11	MBO	—	2,92	2,55
P24	A3 + A6 (1:3)	MBO	—	3,11	2,75
P25 (comp.)	A2	MBO	5 % MEA	4,76	4,06
P26 (comp.)	A3	MBO	8 % PIP	4,80	4,12
P27 (comp.)	A4	MBO	10 % TEA	8,12	6,95
P28 (comp.)	A5	MBO	5 % MEA	4,29	3,68
P29 (comp.)	A6	MBO	8 % PIP	4,23	3,57
P30	A2 + A5 (1:4)	MBO	5 % MEA	2,27	1,97
P31	A2 + A5 (1:1)	MBO	5 % MEA	2,35	2,04
P32	A4 + A5 (1:3)	MBO	10 % TEA	2,64	2,25
P33	A10	MBO	5 % MEA	2,12	1,89
P34	A11	MBO	5 % MEA	2,26	2,00
P35	A3 + A6 (1:3)	MBO	8 % PIP	2,49	2,21

Table 3: Performance tests for H₂S-scavenging in a mixture of the oil and brine (50:50 volume ratio of oil to aqueous phase)

5

Example	(Hemi)acetal	Synergist	solids suppressant	L _{sc} /kg H ₂ S	
				@ 6 min.	@ 1 hour
P36 (comp.)	A1	—	—	23,36	10,04
P37 (comp.)	A2	—	—	23,82	10,20
P38 (comp.)	A5	—	—	23,11	9,50
P39 (comp.)	A7	—	—	20,80	8,91
P40 (comp.)	A8	—	—	19,64	8,52
P41 (comp.)	A9	—	—	19,22	8,20
P42	A2 + A5 (1:4)	—	—	15,22	6,69
P43	A10	—	—	15,47	6,77
P44	A1 + A7 (1:3)	—	—	14,96	6,61

P45	A1 + A7 (1:1)	—	—	15,82	6,96
P46	A12	—	—	14,92	6,48
P47	A13	—	—	15,44	6,88
P48	A2 + A8 (1:1)	—	—	15,71	6,90
P49	A2 + A8 (1:5)	—	—	14,88	6,56
P50	A2 + A9 (1:1)	—	—	16,05	7,01
P51	A14	—	—	14,66	6,50
P52 (comp.)	A1	HTT	—	8,76	7,04
P53 (comp.)	A2	MBO	—	8,40	6,88
P54 (comp.)	A5	MBO	—	8,56	6,80
P55 (comp.)	A7	HTT	—	9,30	7,56
P56 (comp.)	A8	HTT	—	8,07	6,52
P57 (comp.)	A9	HTT	—	8,41	6,92
P58	A2 + A5 (1:4)	MBO	—	6,28	5,44
P59	A10	MBO	—	6,15	5,26
P60	A1 + A7 (1:3)	HTT	—	6,25	5,30
P61	A1 + A7 (1:1)	HTT	—	6,38	5,45
P62	A12	HTT	—	5,84	5,12
P63	A13	HTT	—	6,50	5,78
P64	A2 + A8 (1:1)	HTT	—	5,95	5,17
P65	A2 + A8 (1:5)	HTT	—	5,85	5,03
P66	A2 + A9 (1:1)	HTT	—	5,92	5,28
P67	A14	HTT	—	6,14	5,19
P68 (comp.)	A1	HTT	5 % NaOH	6,91	5,72
P69 (comp.)	A2	MBO	10 % MEA	6,52	5,56
P70 (comp.)	A5	MBO	10 % MEA	7,05	5,92
P71 (comp.)	A7	HTT	5 % NaOH	7,33	6,24
P72 (comp.)	A8	HTT	10 % MEA	6,31	5,25
P73 (comp.)	A9	HTT	10 % MEA	6,73	5,57

P74	A2 + A5 (1:4)	MBO	10 % MEA	4,42	3,86
P75	A10	MBO	10 % MEA	3,96	3,54
P76	A1 + A7 (1:3)	HTT	5 % NaOH	4,26	3,68
P77	A1 + A7 (1:1)	HTT	5 % NaOH	4,49	3,89
P78	A12	HTT	5 % NaOH	3,93	3,47
P79	A13	HTT	5 % NaOH	4,07	3,62
P80	A2 + A8 (1:1)	HTT	10 % MEA	4,18	3,65
P81	A2 + A8 (1:5)	HTT	10 % MEA	3,72	3,35
P82	A2 + A9 (1:1)	HTT	10 % MEA	4,10	3,67
P83	A15	HTT	10 % MEA	3,86	3,38
P84	A2 + A5 (1:4)	—	10 % MEA	7,86	4,42
P85	A10	—	10 % MEA	7,73	4,28
P86	A14	HTT	—	6,23	5,35
P87	A14	—	10 % TEA	7,82	4,38

In the tests including a synergist the portion of MBO was 2 wt.-%, the portion of HTT was 6 wt.-% of the scavenger formulation

In tables 2 and 3 the lower consumption of the scavenger to remove 1 kg of H₂S, 5 the more efficient is the scavenger. In the inventive examples the mixtures of acetals being based on mixtures of monohydric alcohols and polyhydric alcohols are more efficient than the single components. The efficiency is further improved by the incorporation of a synergist and/or a solids suppressant. Furthermore, incorporation of the synergist enhances the reaction rate in the initial phase of the 10 test as can be seen from the difference between scavenging efficiency after 6 minutes versus 1 hour.

Scavenger performance tests – Gas Breakthrough

The performance of the H₂S scavengers according to the invention is evaluated for 15 their ability to remove H₂S from a flowing gas stream by passing gas laden with H₂S through a column of fluid containing the scavenger chemical. A sour gas mixture of 0,2 % H₂S and 99,8 % CO₂ is purged with a flow rate of 60 mL/min

through 440 mL of a 22 % active solution of the scavenger composition in water. Under these conditions the average contact time of gas and scavenger is about 4 seconds. Initially all of the H₂S is removed from the gas stream and no H₂S is detected in the effluent gas. At some point in time (the breakthrough time or TBT) 5 the chemical can no longer entirely remove H₂S from the gas stream and H₂S is observed in the effluent. This parameter is a measure of the efficacy of the scavenger especially for contact tower applications with short contact time. The longer the break through time the more efficient is the chemical scavenger.

10 The effect of the solids suppression agent is rated by visual inspection of the spent scavenger fluid after the gas breakthrough test. The degree of solids formation is rated opaque > turbid > opalescent > clear.

15 The overall concentration of the scavenger formulations in all examples is 22 wt.-%, i. e. in examples where synergist and/or solids suppressant is present the concentration of (hemi-)acetals is reduced accordingly.

Table 4: Gas breakthrough times for different (hemi-)acetals

example	(hemi-)acetal	synergist	solids suppressant	TBT [min]	visual inspection
B1 (comp.)	A1	—	—	31	opaque
B2 (comp.)	A2	—	—	29	opaque
B3 (comp.)	A3	—	—	27	opaque
B4 (comp.)	A5	—	—	17	opaque
B5 (comp.)	A7	—	—	35	opaque
B6 (comp.)	A1 + A2 (1:1)	—	—	31	opaque
B7 (comp.)	A5 + A7 (1:1)	—	—	37	opaque
B8	A2 + A5 (1:1)	—	—	45	opaque
B9	A2 + A5 (1:4)	—	—	47	opaque
B10	A10	—	—	52	opaque

B11	A11	—	—	58	opaque
B12	A12	—	—	55	opaque
B13	A1 + A7 (1:4)	—	—	58	opaque
B14	A3 + A7 (1:2)	—	—	49	opaque
B15	A1	7 % MBO	—	76	turbid
B16	A2	3 % HTT	—	69	turbid
B17	A3	5 % HTT	—	74	turbid
B18	A5	3 % HTT	—	78	turbid
B19	A7	7 % MBO	—	77	turbid
B20	A2 + A5 (1:1)	3 % HTT	—	82	turbid
B21	A2 + A5 (1:4)	3 % HTT	—	89	turbid
B22	A10	3 % HTT	—	87	turbid
B23	A11	3 % HTT	—	84	turbid
B24	A12	7 % MBO	—	81	turbid
B25	A1 + A7 (1:4)	5 % MBO	—	85	turbid
B26	A3 + A7 (1:2)	5 % HTT	—	80	turbid
B27	A1	—	10 % MEA	149	opalescent
B28	A2	—	15 % PIP	146	opalescent
B29	A3	—	15 % PIP	134	opalescent
B30	A5	—	15 % PIP	157	opalescent
B31	A7	—	10 % MEA	150	opalescent
B32	A2 + A5 (1:1)	—	15 % PIP	164	opalescent
B33	A2 + A5 (1:4)	—	15 % PIP	182	opalescent
B34	A10	—	15 % PIP	169	opalescent
B35	A11	—	15 % PIP	178	opalescent
B36	A12	—	10 % MEA	171	opalescent
B37	A1 + A7 (1:4)	—	15 % PIP	172	opalescent
B38	A3 + A7 (1:2)	—	15 % PIP	163	opalescent
B39	A1	7 % MBO	10 % MEA	215	clear

B40	A2	3 % HTT	15 % PIP	200	clear
B41	A3	5 % HTT	15 % PIP	192	clear
B42	A5	3 % HTT	15 % PIP	226	clear
B43	A7	7 % MBO	10 % MEA	222	clear
B44	A2 + A5 (1:1)	3 % HTT	15 % PIP	298	clear
B45	A2 + A5 (1:4)	3 % HTT	15 % PIP	321	clear
B46	A10	3 % HTT	15 % PIP	334	clear
B47	A11	3 % HTT	15 % PIP	348	clear
B48	A12	7 % MBO	10 % MEA	342	clear
B49	A1 + A7 (1:4)	5 % MBO	15 % PIP	346	clear
B50	A3 + A7 (1:2)	5 % HTT	15 % PIP	316	clear

A comparison of the inventive examples and the comparative examples shows that mixtures of (hemi-)acetals containing reaction products of monohydric and polyhydric alcohols have a higher TBT than the single components or mixtures of components of the same group. The addition of a synergist according to group III increases the H₂S scavenging activity of (hemi-)acetals and especially of mixtures of (hemi-)acetals significantly. The scavenging process becomes faster and more efficient. The addition of a solids suppressant further significantly improves the performance of the scavenger. Formation of solids is mostly inhibited which otherwise hampers the accessibility of part of the scavenger and furthermore bears the risk of clogging flow lines for the effluent. The enhancement in scavenging efficiency exceeds the stoichiometric H₂S scavenging capacity of the added synergist considerably.

CLAIMS

1. A composition when used for scavenging hydrogen sulphide and/or mercaptans, the composition comprising
 - I. at least one reaction product between a nitrogen-free monohydric alcohol and an aldehyde or ketone, and
 - II. at least one reaction product between a nitrogen-free polyhydric alcohol and an aldehyde or ketone,wherein


the reaction products I. and II. are selected from hemiacetals and acetals,

the aldehyde or ketone contains 1 to 10 carbon atoms,

the monohydric alcohol comprises 1 to 15 carbon atoms, and


the polyhydric alcohol contains 2 to 20 carbon atoms and 2 to 6 hydroxy groups.

2. The composition when used according to claim 1, wherein the composition further comprises
 - III. at least one reaction product from formaldehyde and a compound selected from the group consisting of ammonia and an amine, the amine being selected from the group consisting of primary alkyl amines having 1 to 4 carbon atoms, and primary hydroxy alkyl amines having 2 to 4 carbon atoms.
3. The composition when used according to claim 2, wherein the reaction product III. of an amine and formaldehyde corresponds to the formula (1b)



wherein each R₁ is C₁ to C₄ alkyl or C₂ to C₄ hydroxy alkyl.

4. The composition when used according to claim 2, wherein the reaction product III. of an amine and formaldehyde corresponds to formula (1a)



wherein

R is H or methyl, and

n is 1 or 2.

5. The composition when used according to claim 4, wherein the compound of formula (1a) is 3,3'-methylenebis-5-methyl-oxazolidine.

6. The composition when used according to any one of claims 2 - 5, wherein the reaction product III. of an amine and formaldehyde is present in the composition in an amount from 1 wt.-% to 20 wt.-%, preferably between 5 wt.-% and 15 wt.-%.

7. The composition when used according to any one of claims 1 - 6, wherein the composition further comprises

IV. at least one inorganic or organic alkaline compound that functions as a solids suppression agent.

8. The composition when used according to claim 7, wherein the alkaline compound IV. is selected from the group consisting of

- IV(a). alkaline metal salts or alkaline earth metal salts;
- IV(b). ammonia; alkyl, aryl or alkylaryl amines;
- IV(c). hydroxy alkyl, hydroxyl aryl or hydroxy alkylaryl amines;
- IV(d). multifunctional amines containing besides an amino group, at least one further functional group selected from the group consisting of amino groups, ether groups and acid groups or an ester, amide or salt thereof; and
- IV(e). mixtures of compounds of groups IV(a) to IV(c);

wherein "alkyl" means C₁ to C₂₀ alkyl, "aryl" means C₆ to C₂₀ aryl and "alkylaryl" means C₇ to C₂₀ alkylaryl.

9. The composition when used according to any one of claims 1 - 8, wherein the aldehyde or ketone contains 1 to 4 carbon atoms.

10. The composition when used according to any one of claims 1 - 9, wherein the aldehyde or ketone is selected from the group consisting of formaldehyde, paraformaldehyde, glyoxal, acetaldehyde, propionaldehyde, butyraldehyde and glutaraldehyde.

11. The composition when used according to any one of claims 1 - 10, wherein the aldehyde or ketone is formaldehyde.

12. The composition when used according to any one of claims 1 - 11, wherein the monohydric alcohol comprises 1 to 5 carbon atoms.



13. The composition when used according to any one of claims 1 - 12, wherein the monohydric alcohol is an aliphatic alcohol.

14. The composition when used according to any one of claims 1 - 13, wherein the monohydric alcohol is selected from the group consisting of methanol, ethanol, propanol, isopropanol, n-butanol, iso-butanol, tert-butanol, pentanol, hexanol, heptanol and octanol, and any mixture thereof.

15. The composition when used according to any one of claims 1 - 14, wherein the polyhydric alcohol is selected from the group consisting of monoethyleneglycol, diethylene

glycol, triethylene glycol propylene glycol, butylene glycol, neopentyl glycol, pen-taerythritol, glycerol and oligomers of glycerol.

16. The composition when used according to any one of claims 1 - 3, wherein the reaction product between a polyhydric alcohol and an aldehyde or ketone is selected from the group consisting of the compounds of formulae (2) to (5)




wherein

p is an integer from 2 to 10,


R_1 is H or C_1 to C_8 alkyl, and

R_2 is CH_2OH ;




wherein

R_3 and R_4 independently are H or CH_2OH ;



wherein

m is from 1 to 10, preferably 1 or 2; and




wherein

R_5 is H , CH_3 , $(\text{CH}_2)_z\text{CH}_3$,

z is 1 to 10, and

x is 1 to 5.

17. The composition when used according to any one of claims 1 - 16, wherein the composition further comprises an alkyl dimethyl benzyl ammonium chloride according to formula (8) as a corrosion inhibitor




wherein R_9 is C_8 to C_{18} alkyl.

18. The composition when used according to claim 17, wherein the compound of formula (8) is present in the composition in an amount between 0.01 and 5 wt.-%, preferably between 0.5 and 2 wt.-%.

19. The composition when used according to any one of claims 1 - 18, wherein the composition further comprises a demulsifier in an amount between 0.1 to 10 wt.-%, preferably between 0.5 and 2 wt.-%.

20. The composition when used according to claim 19, wherein the demulsifier is selected from the group consisting of polysorbates, fatty alcohols, polymers comprising ethylene oxide, polymers comprising propylene oxide, ethylene oxide-propylene oxide copolymers, alkyl polyglucosides, alkyl phenol ethoxylates, alkyl polyethylene oxide, alkylbenzenesulfonic acid and ethoxylated and/or propoxylated alkyl phenolformaldehyde resins.

21. The composition when used according to claim 19 or 20, wherein the demulsifier corresponds to the formula (6)



wherein


R₁₀ is C₂ to C₄ alkylene,

R₁₁ is C₁ to C₁₈ alkyl,

k is an integer from 1 to 200,

m is an integer from 1 to 100.

22. The composition when used according to claim 19, wherein the demulsifier is dodecylbenzenesulfonic acid



23. The composition when used according to any one of claims 19 - 21, wherein the demulsifier is a mixture of at least one compound of formula (6) and at least one compound of formula (7) in a weight ratio of from 5:1 to 1:5, preferably in a weight ratio of from 3:1 to 1:3.
24. The composition when used according to any one of claims 1 - 23, wherein the composition comprises 1 to 50 wt.-% of the reaction product between a monohydric alcohol and an aldehyde or ketone, preferably between 5 and 25 wt.-%.
25. The composition when used according to any one of claims 1 - 24, wherein the composition comprises 1 to 95 wt.-% of the reaction product between a polyhydric alcohol and an aldehyde or ketone, preferably between 20 and 75 wt.-%.
26. The composition when used according to any one of claims 1 - 25, wherein the composition comprises 0.1 to 10 wt.-%, preferably 0.5 to 5 wt.-%, of at least one solids suppression agent.
27. The composition when used according to one or more of claims 1 - 26, wherein the composition comprises water ad 100 wt.-%.
28. The composition when used according to any one of claims 1 - 27, wherein the scavenging occurs from fluids or gases produced from subterranean formations.
29. The composition when used according to any one of claims 1 - 28, wherein the scavenging is from gas and is conducted in a contact tower or by direct injection into the gas.
30. Process for the scavenging of hydrogen sulphide and/or mercaptans, comprising adding to a medium comprising such hydrogen sulphide or mercaptans a composition comprising

- I. at least one reaction product between a nitrogen-free monohydric alcohol and an aldehyde or ketone, and
- II. at least one reaction product between a nitrogen-free polyhydric alcohol and an aldehyde or ketone,

wherein

the reaction products I. and II. are selected from hemiacetals and acetals,
the aldehyde or ketone contains 1 to 10 carbon atoms,
the monohydric alcohol comprises 1 to 15 carbon atoms, and
the polyhydric alcohol contains 2 to 20 carbon atoms and 2 to 6 hydroxy groups.

31. Use of a reaction product from formaldehyde and a compound selected from the group consisting of ammonia and an amine, the amine being selected from the group consisting of primary alkyl amines having 1 to 4 carbon atoms, and primary hydroxy alkyl amines having 2 to 4 carbon atoms, as a synergist in the reaction between hydrogen sulphide and/or a mercaptan and a composition comprising

- I. at least one reaction product between a nitrogen-free monohydric alcohol and an aldehyde or ketone, and
- II. at least one reaction product between a nitrogen-free polyhydric alcohol and an aldehyde or ketone,

wherein the reaction products I. and II. are hemiacetals and/or acetals,

the aldehyde or ketone contains 1 to 10 carbon atoms,

the monohydric alcohol comprises 1 to 15 carbon atoms, and

the polyhydric alcohol contains 2 to 20 carbon atoms and 2 to 6 hydroxy groups.

32. A composition comprising

- I. at least one reaction product between a nitrogen-free monohydric alcohol and an aldehyde or ketone,

II. at least one reaction product between a nitrogen-free polyhydric alcohol and an aldehyde or ketone, and

III. at least one reaction product from formaldehyde and ammonia and/or an amine, selected from the group consisting of primary alkyl amines having 1 to 4 carbon atoms, and primary hydroxy alkyl amines having 2 to 4 carbon atoms.

wherein

the reaction products I. and II. are selected from hemiacetals and acetals,

the aldehyde or ketone contains 1 to 10 carbon atoms,

the monohydric alcohol comprises 1 to 15 carbon atoms, and

the polyhydric alcohol contains 2 to 20 carbon atoms and 2 to 6 hydroxy groups.

33. The composition of claim 32, further comprising

IV. at least one inorganic or organic alkaline compound that functions as a solids suppression agent.

Clariant S. A.

Clariant International Ltd

Patent Attorneys for the Applicant/Nominated Person

SPRUSON & FERGUSON