

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



(10) International Publication Number

WO 2015/085303 A1

(43) International Publication Date

11 June 2015 (11.06.2015)

(51) International Patent Classification:

B01D 53/94 (2006.01) B01J 29/74 (2006.01)
B01J 23/44 (2006.01)

(21) International Application Number:

PCT/US2014/069089

(22) International Filing Date:

8 December 2014 (08.12.2014)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/912,834 6 December 2013 (06.12.2013) US

(71) Applicant: JOHNSON MATTHEY PUBLIC LIMITED COMPANY [GB/GB]; 5th Floor, 25 Farringdon Street, London EC4A 4AB (GB).

(72) Inventor; and

(71) Applicant (for US only): CHEN, Hai-Ying [US/US]; 320 Arden Road, Conshohocken, Pennsylvania 19428 (US).

(72) Inventors: RAJARAM, Raj Rao; 34 Buckland Avenue, Slough berkshire SL3 7PH (GB). LIU, Dongxia; 1697 Bradford Road, Wayne, Pennsylvania 19087 (US).

(74) Agent: CARROLL, Kevin M.; c/o Johnson Matthey, Inc., 435 Devon Park Drive, Building 600, Wayne, Pennsylvania 19087 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))



WO 2015/085303 A1

(54) Title: PASSIVE NO_x ADSORBER COMPRISING NOBLE METAL AND SMALL PORE MOLECULAR SIEVE

(57) Abstract: A passive NO_x adsorber is disclosed. The passive NO_x adsorber is effective to adsorb NO_x at or below a low temperature and release the adsorbed NO_x at temperatures above the low temperature. The passive NO_x adsorber comprises a noble metal and a small pore molecular sieve. The small pore molecular sieve has a maximum ring size of eight tetrahedral atoms. The invention also includes an exhaust system comprising the passive NO_x adsorber, and a method for treating exhaust gas from an internal combustion engine utilizing the passive NO_x adsorber.

PASSIVE NO_X ADSORBER COMPRISING NOBLE METAL AND SMALL PORE MOLECULAR SIEVE

FIELD OF THE INVENTION

The invention relates to a passive NO_x adsorber and its use in an exhaust
5 system for internal combustion engines.

BACKGROUND OF THE INVENTION

Internal combustion engines produce exhaust gases containing a variety
of pollutants, including nitrogen oxides ("NO_x"), carbon monoxide, and
10 uncombusted hydrocarbons, which are the subject of governmental legislation.
Emission control systems are widely utilized to reduce the amount of these
pollutants emitted to atmosphere, and typically achieve very high efficiencies once
they reach their operating temperature (typically, 200°C and higher). However,
these systems are relatively inefficient below their operating temperature (the "cold
15 start" period).

For instance, current urea based selective catalytic reduction (SCR)
applications implemented for meeting Euro 6b emissions require that the
temperature at the urea dosing position be above about 180°C before urea can be
dosed and used to convert NO_x. NO_x conversion below 180°C is difficult to
20 address using the current systems, and future European and US legislation will
stress the low temperature NO_x storage and conversion. Currently this is achieved
by heating strategies but this has a detrimental effect of CO₂ emissions.

As even more stringent national and regional legislation lowers the amount
of pollutants that can be emitted from diesel or gasoline engines, reducing
25 emissions during the cold start period is becoming a major challenge. Thus,
methods for reducing the level of NO_x emitted during cold start condition continue
to be explored.

For instance, PCT Intl. Appl. WO 2008/047170 discloses a system wherein
NO_x from a lean exhaust gas is adsorbed at temperatures below 200°C and is
30 subsequently thermally desorbed above 200°C. The NO_x adsorbent is taught to

consist of palladium and a cerium oxide or a mixed oxide or composite oxide containing cerium and at least one other transition metal.

U.S. Appl. Pub. No. 2011/0005200 teaches a catalyst system that simultaneously removes ammonia and enhances net NO_x conversion by placing an ammonia-selective catalytic reduction (“NH₃-SCR”) catalyst formulation downstream of a lean NO_x trap. The NH₃-SCR catalyst is taught to adsorb the ammonia that is generated during the rich pulses in the lean NO_x trap. The stored ammonia then reacts with the NO_x emitted from the upstream lean NO_x trap, which increases NO_x conversion rate while depleting the stored ammonia.

PCT Intl. Appl. WO 2004/076829 discloses an exhaust-gas purification system which includes a NO_x storage catalyst arranged upstream of an SCR catalyst. The NO_x storage catalyst includes at least one alkali, alkaline earth, or rare earth metal which is coated or activated with at least one platinum group metal (Pt, Pd, Rh, or Ir). A particularly preferred NO_x storage catalyst is taught to include cerium oxide coated with platinum and additionally platinum as an oxidizing catalyst on a support based on aluminum oxide. EP 1027919 discloses a NO_x adsorbent material that comprises a porous support material, such as alumina, zeolite, zirconia, titania, and/or lanthana, and at least 0.1 wt% precious metal (Pt, Pd, and/or Rh). Platinum carried on alumina is exemplified. U.S. Appl. Pub. No. 2012/0308439 A1 teaches a cold start catalyst that comprises (1) a zeolite catalyst comprising a base metal, a noble metal, and a zeolite, and (2) a supported platinum group metal catalyst comprising one or more platinum group metals and one or more inorganic oxide carriers.

As with any automotive system and process, it is desirable to attain still further improvements in exhaust gas treatment systems, particularly under cold start conditions. We have discovered a new passive NO_x adsorber that provides enhanced cleaning of the exhaust gases from internal combustion engines. The new passive NO_x adsorber also exhibits improved sulfur tolerance.

SUMMARY OF THE INVENTION

The invention is a passive NO_x adsorber that is effective to adsorb NO_x at or below a low temperature and release the adsorbed NO_x at temperatures above the low temperature. The passive NO_x adsorber comprises a noble metal 5 and a small pore molecular sieve. The small pore molecular sieve has a maximum ring size of eight tetrahedral atoms. The invention also includes an exhaust system comprising the passive NO_x adsorber, and a method for treating exhaust gas from an internal combustion engine utilizing the passive NO_x adsorber.

10

DETAILED DESCRIPTION OF THE INVENTION

The passive NO_x adsorber of the invention is effective to adsorb NO_x at or below a low temperature and release the adsorbed NO_x at temperatures above the low temperature. Preferably, the low temperature is about 200°C. The 15 passive NO_x adsorber comprises a noble metal and a small pore molecular sieve. The noble metal is preferably palladium, platinum, rhodium, gold, silver, iridium, ruthenium, osmium, or mixtures thereof; more preferably, palladium, platinum, rhodium, or mixtures thereof. Palladium is particularly preferred.

The small pore molecular sieve has a maximum ring size of eight 20 tetrahedral atoms. The small pore molecular sieve may be any natural or a synthetic molecular sieve, including zeolites, and is preferably composed of aluminum, silicon, and/or phosphorus. The molecular sieves typically have a three-dimensional arrangement of SiO_4 , AlO_4 , and/or PO_4 that are joined by the sharing of oxygen atoms, but may also be two-dimensional structures as well. 25 The molecular sieve frameworks are typically anionic, which are counterbalanced by charge compensating cations, typically alkali and alkaline earth elements (e.g., Na, K, Mg, Ca, Sr, and Ba), ammonium ions, and also protons. Other metals (e.g., Fe, Ti, and Ga) may be incorporated into the framework of the small pore molecular sieve to produce a metal-incorporated molecular sieve.

30 Preferably, the small pore molecular sieve is selected from an aluminosilicate molecular sieve, a metal-substituted aluminosilicate molecular

sieve, an aluminophosphate molecular sieve, or a metal-substituted aluminophosphate molecular sieve. More preferably, the small pore molecular sieve is a molecular sieve having the Framework Type of ACO, AEI, AEN, AFN, AFT, AFX, ANA, APC, APD, ATT, CDO, CHA, DDR, DFT, EAB, EDI, EPI, ERI, 5 GIS, GOO, IHW, ITE, ITW, LEV, KFI, MER, MON, NSI, OWE, PAU, PHI, RHO, RTH, SAT, SAV, SIV, THO, TSC, UEI, UFI, VNI, YUG, and ZON, as well as mixtures or intergrowths of any two or more. Particularly preferred intergrowths of the small pore molecular sieves include KFI-SIV, ITE-RTH, AEW-UEI, AEI-CHA, and AEI-SAV. Most preferably, the small pore molecular sieve is AEI or 10 CHA, or an AEI-CHA intergrowth.

The passive NO_x adsorber may be prepared by any known means. For instance, the noble metal may be added to the small pore molecular sieve to form the passive NO_x adsorber by any known means, the manner of addition is not considered to be particularly critical. For example, a noble metal compound 15 (such as palladium nitrate) may be supported on the molecular sieve by impregnation, adsorption, ion-exchange, incipient wetness, precipitation, or the like. Other metals may also be added to the passive NO_x adsorber.

Preferably, some of the noble metal (more than 1 percent of the total 20 noble metal added) in the passive NO_x adsorber is located inside the pores of the small pore molecular sieve. More preferably, more than 5 percent of the total amount of noble metal is located inside the pores of the small pore molecular sieve; and even more preferably may be greater than 10 percent or greater than 25% or greater than 50 percent of the total amount of noble metal that is located inside the pores of the small pore molecular sieve.

25 Preferably, the passive NO_x adsorber further comprises a flow-through substrate or filter substrate. In one embodiment, the passive NO_x adsorber is coated onto the flow-through or filter substrate, and preferably deposited on the flow-through or filter substrate using a washcoat procedure to produce a passive NO_x adsorber system.

30 The flow-through or filter substrate is a substrate that is capable of containing catalyst components. The substrate is preferably a ceramic substrate

or a metallic substrate. The ceramic substrate may be made of any suitable refractory material, e.g., alumina, silica, titania, ceria, zirconia, magnesia, zeolites, silicon nitride, silicon carbide, zirconium silicates, magnesium silicates, aluminosilicates, metallo aluminosilicates (such as cordierite and spudomene), or 5 a mixture or mixed oxide of any two or more thereof. Cordierite, a magnesium aluminosilicate, and silicon carbide are particularly preferred.

The metallic substrates may be made of any suitable metal, and in particular heat-resistant metals and metal alloys such as titanium and stainless steel as well as ferritic alloys containing iron, nickel, chromium, and/or aluminum 10 in addition to other trace metals.

The flow-through substrate is preferably a flow-through monolith having a honeycomb structure with many small, parallel thin-walled channels running axially through the substrate and extending throughout from an inlet or an outlet of the substrate. The channel cross-section of the substrate may be any shape, 15 but is preferably square, sinusoidal, triangular, rectangular, hexagonal, trapezoidal, circular, or oval.

The filter substrate is preferably a wall-flow monolith filter. The channels of a wall-flow filter are alternately blocked, which allow the exhaust gas stream to enter a channel from the inlet, then flow through the channel walls, and exit the 20 filter from a different channel leading to the outlet. Particulates in the exhaust gas stream are thus trapped in the filter.

The passive NO_x adsorber may be added to the flow-through or filter substrate by any known means. A representative process for preparing the passive NO_x adsorber using a washcoat procedure is set forth below. It will be 25 understood that the process below can be varied according to different embodiments of the invention.

The pre-formed passive NO_x adsorber may be added to the flow-through or filter substrate by a washcoating step. Alternatively, the passive NO_x adsorber may be formed on the flow-through or filter substrate by first washcoating 30 unmodified small pore molecular sieve onto the substrate to produce a molecular sieve-coated substrate. Noble metal may then be added to the molecular sieve-

coated substrate, which may be accomplished by an impregnation procedure, or the like.

The washcoating procedure is preferably performed by first slurring finely divided particles of the passive NO_x adsorber (or unmodified small pore molecular sieve) in an appropriate solvent, preferably water, to form the slurry. Additional components, such as transition metal oxides, binders, stabilizers, or promoters may also be incorporated in the slurry as a mixture of water soluble or water-dispersible compounds. The slurry preferably contains between 10 to 70 weight percent solids, more preferably between 20 to 50 weight percent. Prior to forming the slurry, the passive NO_x adsorber (or unmodified small pore molecular sieve) particles are preferably subject to a size reduction treatment (e.g., milling) such that the average particle size of the solid particles is less than 20 microns in diameter.

The flow-through or filter substrate may then be dipped one or more times into the slurry or the slurry may be coated on the substrate such that there will be deposited on the substrate the desired loading of catalytic materials. If noble metal is not incorporated into the molecular sieve prior to washcoating the flow-through or filter substrate, the molecular sieve-coated substrate is typically dried and calcined and then, the noble metal may be added to the molecular sieve-coated substrate by any known means, including impregnation, adsorption, or ion-exchange, for example, with a noble metal compound (such as palladium nitrate). Preferably, the entire length of the flow-through or filter substrate is coated with the slurry so that a washcoat of the passive NO_x adsorber covers the entire surface of the substrate.

After the flow-through or filter substrate has been coated with the passive NO_x adsorber, and impregnated with noble metal if necessary, the coated substrate is preferably dried and then calcined by heating at an elevated temperature to form the passive NO_x adsorber-coated substrate. Preferably, the calcination occurs at 400 to 600°C for approximately 1 to 8 hours.

In an alternative embodiment, the flow-through or filter substrate is comprised of the passive NO_x adsorber. In this case, the passive NO_x adsorber

is extruded to form the flow-through or filter substrate. The passive NO_x adsorber extruded substrate is preferably a honeycomb flow-through monolith.

Extruded molecular sieve substrates and honeycomb bodies, and processes for making them, are known in the art. See, for example, U.S. Pat. 5 Nos. 5,492,883, 5,565,394, and 5,633,217 and U.S. Pat. No. Re. 34,804. Typically, the molecular sieve material is mixed with a permanent binder such as silicone resin and a temporary binder such as methylcellulose, and the mixture is extruded to form a green honeycomb body, which is then calcined and sintered to form the final small pore molecular sieve flow-through monolith. The 10 molecular sieve may contain the noble metal prior to extruding such that a passive NO_x adsorber monolith is produced by the extrusion procedure. Alternatively, the noble metal may be added to a pre-formed molecular sieve monolith in order to produce the passive NO_x adsorber monolith.

The invention also includes an exhaust system for internal combustion 15 engines comprising the passive NO_x adsorber. The exhaust system preferably comprises one or more additional after-treatment devices capable of removing pollutants from internal combustion engine exhaust gases at normal operating temperatures. Preferably, the exhaust system comprises the passive NO_x adsorber and one or more other catalyst components selected from: (1) a 20 selective catalytic reduction (SCR) catalyst, (2) a particulate filter, (3) a SCR filter, (4) a NO_x adsorber catalyst, (5) a three-way catalyst, (6) an oxidation catalyst, or any combination thereof. The passive NO_x adsorber is preferably a separate component from any of the above after-treatment devices. Alternatively, the passive NO_x adsorber can be incorporated as a component into 25 any of the above after-treatment devices.

These after-treatment devices are well known in the art. Selective catalytic reduction (SCR) catalysts are catalysts that reduce NO_x to N₂ by reaction with nitrogen compounds (such as ammonia or urea) or hydrocarbons (lean NO_x reduction). A typical SCR catalyst is comprised of a vanadia-titania 30 catalyst, a vanadia-tungsta-titania catalyst, or a metal/zeolite catalyst such as

iron/beta zeolite, copper/beta zeolite, copper/SSZ-13, copper/SAPO-34, Fe/ZSM-5, or copper/ZSM-5.

Particulate filters are devices that reduce particulates from the exhaust of internal combustion engines. Particulate filters include catalyzed particulate filters and bare (non-catalyzed) particulate filters. Catalyzed particulate filters (for diesel and gasoline applications) include metal and metal oxide components (such as Pt, Pd, Fe, Mn, Cu, and ceria) to oxidize hydrocarbons and carbon monoxide in addition to destroying soot trapped by the filter.

Selective catalytic reduction filters (SCRF) are single-substrate devices that combine the functionality of an SCR and a particulate filter. They are used to reduce NO_x and particulate emissions from internal combustion engines. In addition to the SCR catalyst coating, the particulate filter may also include other metal and metal oxide components (such as Pt, Pd, Fe, Mn, Cu, and ceria) to oxidize hydrocarbons and carbon monoxide in addition to destroying soot trapped by the filter.

NO_x adsorber catalysts (NACs) are designed to adsorb NO_x under lean exhaust conditions, release the adsorbed NO_x under rich conditions, and reduce the released NO_x to form N₂. NACs typically include a NO_x-storage component (e.g., Ba, Ca, Sr, Mg, K, Na, Li, Cs, La, Y, Pr, and Nd), an oxidation component (preferably Pt) and a reduction component (preferably Rh). These components are contained on one or more supports.

Three-way catalysts (TWCs) are typically used in gasoline engines under stoichiometric conditions in order to convert NO_x to N₂, carbon monoxide to CO₂, and hydrocarbons to CO₂ and H₂O on a single device.

Oxidation catalysts, and in particular diesel oxidation catalysts (DOCs), are well-known in the art. Oxidation catalysts are designed to oxidize CO to CO₂ and gas phase hydrocarbons (HC) and an organic fraction of diesel particulates (soluble organic fraction) to CO₂ and H₂O. Typical oxidation catalysts include platinum and optionally also palladium on a high surface area inorganic oxide support, such as alumina, silica-alumina and a zeolite.

The exhaust system can be configured so that the passive NO_x adsorber is located close to the engine and the additional after-treatment device(s) are located downstream of the passive NO_x adsorber. Thus, under normal operating conditions, engine exhaust gas first flows through the passive NO_x adsorber prior 5 to contacting the after-treatment device(s). Alternatively, the exhaust system may contain valves or other gas-directing means such that during the low temperature period (below a temperature ranging from about 150 to 220°C, preferably 200°C, about as measured at the after-treatment device(s)), the exhaust gas is directed to contact the after-treatment device(s) before flowing to 10 the passive NO_x adsorber. Once the after-treatment device(s) reaches the operating temperature (about 150 to 220°C, preferably 200°C, as measured at the after-treatment device(s)), the exhaust gas flow is then redirected to contact the passive NO_x adsorber prior to contacting the after-treatment device(s). This ensures that the temperature of the passive NO_x adsorber remains low for a 15 longer period of time, and thus improves efficiency of the passive NO_x adsorber, while simultaneously allowing the after-treatment device(s) to more quickly reach operating temperature. U.S. Pat. No. 5,656,244, the teachings of which are incorporated herein by reference, for example, teaches means for controlling the flow of the exhaust gas during cold-start and normal operating conditions.

20 The invention also includes a method for treating exhaust gas from an internal combustion engine. The method comprises adsorbing NO_x onto the passive NO_x adsorber at temperatures at or below a low temperature, thermally desorbing NO_x from the passive NO_x adsorber at a temperature above the low temperature, and catalytically removing the desorbed NO_x on a catalyst 25 component downstream of the passive NO_x adsorber. Preferably, the low temperature is about 200°C.

The catalyst component downstream of the passive NO_x adsorber is a SCR catalyst, a particulate filter, a SCR filter, a NO_x adsorber catalyst, a three-way catalyst, an oxidation catalyst, or combinations thereof.

The following examples merely illustrate the invention. Those skilled in the art will recognize many variations that are within the spirit of the invention and scope of the claims.

5 EXAMPLE 1: PREPARATION OF PASSIVE NO_x ADSORBERS (PNAs)

Palladium is added to a small pore chabazite (CHA) zeolite with a silica –to-alumina ratio (SAR) of 26, a medium pore ZSM-5 (MFI) zeolite with a SAR=23 and a large pore beta (BEA) zeolite with an SAR=26 to produce PNA 1A (Pd/CHA), Comparative PNA 1B (Pd/MFI) and Comparative PNA 1C (Pd/BEA)

10 according to the following general procedure: The powder catalyst is prepared by wet impregnation of the zeolite using palladium nitrate as the precursor. After drying at 100°C, the samples are calcined at 500°C. The samples are then hydrothermally aged at 750°C in an air atmosphere containing 10% H₂O. The Pd loading for all the three samples is 1 wt.%.

15 Comparative PNA 1D (Pd/CeO₂) is prepared following the procedures reported in WO 2008/047170. The Pd loading is 1 wt.%. The sample is hydrothermally aged at 750°C in an air atmosphere containing 10% H₂O.

EXAMPLE 2: NO_x STORAGE CAPACITY TESTING PROCEDURES

20 The PNA (0.4 g) is held at an adsorption temperature about 80°C for 2 minutes in an NO-containing gas mixture flowing at 2 liters per minute at a MHSV of 300 L * hr⁻¹ * g⁻¹. This adsorption stage is followed by Temperature Programmed Desorption (TPD) at a ramping rate of 10°C/minute in the presence of the NO-containing gas until the bed temperature reaches about 400°C in order

25 to purge the catalyst of all stored NO_x for further testing. The test is then repeated starting from an adsorption temperature of 170°C, instead of 80°C.

The NO-containing gas mixture during both the adsorption and desorption comprises 12 vol.% O₂, 200 ppm NO, 5 vol.% CO₂, 200 ppm CO, 50 ppm C₁₀H₂₂, and 5 vol.% H₂O.

The NO_x storage is calculated as the amount of NO₂ stored per liter of catalyst with reference to a monolith containing a catalyst loading of about 3 g/in³. The results at the different temperatures are shown in Table 1.

5 The results at Table 1 show that the PNA of the invention (PNA 1A) demonstrates comparable NO_x storage capacity both at 80 and 170°C as compared to Comparative PNA 1D. Although Comparative PNAs 1B and 1C exhibit higher NO_x storage capacity at 80°C, their NO_x storage capacity at 170°C is lower. For applications require high NO_x storage capacity at temperatures above
10 about 170°C, PNA 1A and Comparative PNA 1D show advantages over Comparative PNAs 1B and 1C.

EXAMPLE 3: NO_x STORAGE CAPACITY AFTER SULFUR EXPOSURE TESTING PROCEDURES

15 PNA 1A and Comparative PNA 1D were subjected to a high level of sulfation by contacting them with a SO₂ containing gas (100 ppm SO₂, 10% O₂, 5% CO₂ and H₂O, balance N₂) at 300°C to add about 64 mg S per gram of catalyst. The NO_x storage capacity of the catalysts before and after sulfation is measured at 100°C following the procedures of Example 2. The results are listed
20 in Table 2.

25 The results shown in Table 2 indicate that the PNA of the invention (PNA 1A) retains a significant amount of the NO_x storage capacity even after high a level of sulfur exposure. In contrast, Comparative PNA 1D loses almost all of its NO_x adsorption ability under the same sulfation conditions. The PNA of the invention exhibits much improved sulfur tolerance.

EXAMPLE 4: PREPARATION OF SMALL PORE MOLECULAR SIEVE SUPPORTED PASSIVE NO_x ADSORBERS (PNAs)

Palladium is added to a series of small pore molecular sieves following the
30 procedure of Example 1. The Pd loading is kept at 1 wt.% for all the samples. The samples are hydrothermally aged at 750°C in an air atmosphere containing 10%

H_2O . The aged samples are then tested for their NO_x storage capacities following the procedure of Example 2.

These PNAs and their NO_x storage capacity at 80 and 170°C are listed in Table 3.

5 The results in Table 3 show that a wide range of small pore molecular sieve supported PNAs have high NO_x storage capacity.

EXAMPLE 5: PREPARATION OF SMALL PORE MOLECULAR SIEVE SUPPORTED PASSIVE NO_x ADSORBERS (PNAS) WITH DIFFERENT

10 PALLADIUM LOADINGS

Palladium is added to a small pore molecular sieve CHA following the procedure of Example 1. The Pd loading is increased to 2 wt.% for the sample. The sample is hydrothermally aged at 750°C in an air atmosphere containing 10% H_2O . The aged sample is tested for its NO_x storage capacities following the procedure of Example 2. The NO_x storage capacities at 80 and 170°C on the sample are listed in Table 4.

15 The results in Table 4 show that increasing Pd loading increases the NO_x storage capacity.

20

TABLE 1: NO_x storage capacity (g NO_2/L)

Catalyst	NO_x storage capacity (80°C)	NO_x storage capacity (170°C)
1A	0.28	0.45
1B *	0.35	0.28
1C *	0.68	0.07
1D *	0.29	0.38

* Comparative Example

25

TABLE 2: NO_x storage capacity (g NO₂/L)

Catalyst	NO _x storage capacity at 100°C	
	Before Sulfation	After Sulfation
1A	0.41	0.28
1D *	0.31	0.01

* Comparative Example

5

TABLE 3: NO_x storage capacity (g NO₂/L)

Catalyst	Small pore molecular sieve	NO _x storage capacity (80°C)	NO _x storage capacity (170°C)
PNA 1A	CHA (SAR=26)	0.28	0.45
PNA 4A	CHA (SAR=12)	0.42	0.60
PNA 4B	CHA (SAR=13)	0.34	0.51
PNA 4C	CHA (SAR=17)	0.20	0.42
PNA 4D	CHA (SAR=22)	0.28	0.42
PNA 4E	AEI (SAR=20)	0.33	0.57
PNA 4F	ERI (SAR=12)	0.08	0.2
PNA 4G	CHA (SAPO-34)	0.29	0.41
PNA 4H	AEI-CHA Intergrowth (SAPO)	0.22	0.23

10

TABLE 4: NO_x storage capacity (g NO₂/L)

Catalyst	Molecular sieve	Pd loading (wt. %)	NO _x storage capacity (80°C)	NO _x storage capacity (170°C)
PNA 1A	CHA (SAR=26)	1	0.28	0.45
PNA 5A	CHA (SAR=26)	2	0.43	0.66

We claim:

1. A passive NO_x adsorber effective to adsorb NO_x at or below a low temperature and release the adsorbed NO_x at temperatures above the low temperature, said passive NO_x adsorber comprising a noble metal and a small 5 pore molecular sieve having a maximum ring size of eight tetrahedral atoms.
2. The passive NO_x adsorber of claim 1 wherein the noble metal is selected from the group consisting of platinum, palladium, rhodium, gold, silver, iridium, ruthenium, osmium, and mixtures thereof.
3. The passive NO_x adsorber of claim 1 wherein the noble metal is 10 palladium.
4. The passive NO_x adsorber of any of claims 1 to 3 wherein the small pore molecular sieve is selected from the group consisting of aluminosilicate molecular sieves, metal-substituted aluminosilicate molecular sieves, aluminophosphate molecular sieves and metal-substituted aluminophosphate 15 molecular sieves.
5. The passive NO_x adsorber of any of claims 1 to 4 wherein the small pore molecular sieve is selected from the group of Framework Type consisting of: ACO, AEI, AEN, AFN, AFT, AFX, ANA, APC, APD, ATT, CDO, CHA, DDR, DFT, EAB, EDI, EPI, ERI, GIS, GOO, IHW, ITE, ITW, LEV, KFI, MER, MON, 20 NSI, OWE, PAU, PHI, RHO, RTH, SAT, SAV, SIV, THO, TSC, UEI, UFI, VNI, YUG, ZON, and mixtures or intergrowths thereof.
6. The passive NO_x adsorber of claim 5 wherein the small pore molecular sieve is selected from the group Framework Type consisting of AEI and CHA.
- 25 7. The passive NO_x adsorber of claim 5 wherein the intergrowths of the small pore molecular sieves include KFI-SIV, ITE-RTH, AEW-UEI, AEI-CHA, and AEI-SAV.
8. The passive NO_x adsorber of any of claims 1 to 7 wherein the passive NO_x adsorber is coated onto a flow-through or filter substrate.
- 30 9. The passive NO_x adsorber of claim 8 wherein the flow-through substrate is a honeycomb monolith.

10. The passive NO_x adsorber of any of claims 1 to 7 wherein the passive NO_x adsorber is extruded to form a flow-through or filter substrate.

11. The passive NO_x adsorber of any of claims 1 to 10 wherein greater than 5 percent of the total amount of noble metal is located inside pores of the 5 small pore molecular sieve.

12. The passive NO_x adsorber of any of claims 1 to 11 wherein the low temperature is 200°C.

13. An exhaust system for internal combustion engines comprising the passive NO_x adsorber of any of the preceding claims and a catalyst component 10 selected from the group consisting a selective catalytic reduction (SCR) catalyst, a particulate filter, a SCR filter, a NO_x adsorber catalyst, a three-way catalyst, an oxidation catalyst, and combinations thereof.

14. A method for reducing NO_x in an exhaust gas, said method comprising adsorbing NO_x onto the passive NO_x adsorber of any of the preceding 15 claims at or below a low temperature, thermally desorbing NO_x from the passive NO_x adsorber at a temperature above the low temperature, and catalytically removing the desorbed NO_x on a catalyst component downstream of the passive NO_x adsorber.

15. The method of claim 14 wherein the catalyst component is selected 20 from the group consisting a selective catalytic reduction (SCR) catalyst, a particulate filter, a SCR filter, a NO_x adsorber catalyst, a three-way catalyst, an oxidation catalyst, and combinations thereof.

16. The method of claim 14 or claim 15 wherein the low temperature is 200°C.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2014/069089

A. CLASSIFICATION OF SUBJECT MATTER
INV. B01D53/94 B01J23/44 B01J29/74
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
B01D B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2012/166868 A1 (JOHNSON MATTHEY PLC [GB]; CHEN HAI-YING [US]; MULLA SHADAB [US]) 6 December 2012 (2012-12-06) abstract page 3, line 14 - page 6, line 16 page 9, lines 5-9,23-30 page 11, lines 1-8 page 15, lines 4-18 -----	1-16
X	WO 2012/170421 A1 (JOHNSON MATTHEY PLC [GB]; FEDEYKO JOSEPH MICHAEL [US]; CHEN HAI-YING [US]) 13 December 2012 (2012-12-13) abstract; examples 1,2 page 3, paragraph 1 - page 4, paragraph 5 page 6, paragraph 3 - page 7, paragraph 1 page 13, paragraph 3 page 14, paragraph 1 -----	1-13
A	----- - / --	14-16

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier application or patent but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
24 February 2015	05/03/2015
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Howe, Patrick

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2014/069089

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2011/112949 A1 (JOHNSON MATTHEY PLC [GB]; ANDERSEN PAUL J [US]; CACCI JOHN LEONELLO [G]) 15 September 2011 (2011-09-15) abstract; example 1 page 2, lines 2-28 page 3, line 26 - page 4, line 2 page 5, lines 14-20 page 14, lines 14-21 page 17, lines 6-17 -----	1-13
A	US 2010/267548 A1 (ANDERSEN P; ANDERSEN P J; CACCI J; CACCI J L; CACCI Y L; CHEN H; CHEN) 21 October 2010 (2010-10-21) abstract paragraphs [0002], [0011], [0012], [0018], [0019], [0025], [0026], [0028], [0063] -----	14-16
A	EP 1 184 556 A2 (NISSAN MOTOR [JP]) 6 March 2002 (2002-03-06) abstract paragraphs [0001], [0004] - [0008], [0016], [0017] -----	1-16
A	US 2003/115859 A1 (DEEBA MICHEL [US]) 26 June 2003 (2003-06-26) abstract paragraphs [0001], [0009], [0010], [0014], [0017], [0039], [0042], [0046], [0061], [0064]; figures 2,5 -----	1-16
A	EP 0 935 055 A2 (NISSAN MOTOR [JP]) 11 August 1999 (1999-08-11) abstract; figures 1,2 paragraphs [0005], [0007], [0010] - [0012], [0017], [0019] -----	1-16

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/US2014/069089

Patent document cited in search report	Publication date	Patent family member(s)			Publication date
WO 2012166868	A1 06-12-2012	CN EP JP KR US WO	103619469 A 2714267 A1 2014519975 A 20140035982 A 2012308439 A1 2012166868 A1		05-03-2014 09-04-2014 21-08-2014 24-03-2014 06-12-2012 06-12-2012
WO 2012170421	A1 13-12-2012	CN EP JP KR US WO	103648643 A 2718010 A1 2014522308 A 20140049992 A 2014170045 A1 2012170421 A1		19-03-2014 16-04-2014 04-09-2014 28-04-2014 19-06-2014 13-12-2012
WO 2011112949	A1 15-09-2011	CN EP JP KR RU US US WO	102869427 A 2555853 A1 2013522011 A 20120121925 A 2012143404 A 2012184429 A1 2012189518 A1 2011112949 A1		09-01-2013 13-02-2013 13-06-2013 06-11-2012 20-04-2014 19-07-2012 26-07-2012 15-09-2011
US 2010267548	A1 21-10-2010	CN EP GB GB GB JP KR RU US US US US US US US US WO	102802791 A 2419209 A1 2482094 A 2507006 A 2507902 A 2012523958 A 20120006053 A 2011146545 A 2010267548 A1 2011281720 A1 2012093702 A1 2012213673 A1 2013095012 A1 2013323146 A1 2014248203 A1 2010121257 A1		28-11-2012 22-02-2012 18-01-2012 16-04-2014 14-05-2014 11-10-2012 17-01-2012 27-05-2013 21-10-2010 17-11-2011 19-04-2012 23-08-2012 18-04-2013 05-12-2013 04-09-2014 21-10-2010
EP 1184556	A2 06-03-2002	NONE			
US 2003115859	A1 26-06-2003	AU EP EP JP KR US WO	2002362131 A1 1456511 A2 2048115 A2 2005514551 A 20040077683 A 2003115859 A1 03056150 A2		15-07-2003 15-09-2004 15-04-2009 19-05-2005 06-09-2004 26-06-2003 10-07-2003
EP 0935055	A2 11-08-1999	DE EP	69929396 T2 0935055 A2		21-09-2006 11-08-1999